

Description

This invention is a filter material of blended fibres. The filter material may find application in dust helmets, respirators, suction cleaners and air-conditioning systems as a disposable filter element, and even as a duster.

In air filters, a low resistance to air flow is desirable, coupled with, of course, a high filtration efficiency (= a high probability that a particle borne in the air flow through the filter will be captured by the filter). These properties can be met by a filter material having an open structure but carrying electric charge, to attract dust particles. Such a filter material is described in GB-A-384052, wherein wool fibres are carded with resin particles. In this filter material, the action during manufacture of rubbing the wool against the resin imparts a persistent negative charge to the resin and an induced positive charge to the wool. These charges attract dust particles.

It would be desirable to find an air filter with a high filtration efficiency, which is reasonably priced, which has a low resistance to air flow and which is non-flammable.

According to the present invention, a filter material for capturing dust comprises a blend of (i) polyolefine fibres and (ii) fibres of an addition polymer comprising one or more halogen substituted polyolefines, wherein the fibres (i) and the fibres (ii) both have no coating of lubricant or antistatic agent and are clean and are preferably in the ratio by surface area (i):(ii) = 30:70 to 80:20; the halogen is preferably fluorine or chlorine, and the polyolefine is preferably polyethylene or polypropylene. The fibres (ii) could thus contain for example one or more of chloroethylene units, for example $-\text{CHCl}-\text{CH}_2-$ or $-\text{CCl}_2-\text{CH}_2-$, or tetrafluoroethylene units $-\text{F}_2\text{C}-\text{CF}_2-$, and may also contain acrylonitrile units $-\text{CH}_2-\text{C}(\text{CN})\text{H}-$, and could thus be for example polyvinyl chloride, polyvinylidene chloride, vinyl chloride vinylidene chloride copolymer, chlorinated polyvinyl chloride, polytetrafluoroethylene or (preferably) modacrylic.

The invention also includes a method of making such a filter material, by steps set forth later, including the step of cleaning the fibres. By "clean" we mean that the fibre has no coating of lubricant or anti-static agent, or that any such coating was removed before blending, for example by scouring with a non-ionic detergent. By "modacrylic" we mean a copolymer comprising from 35 to 85 weight percent acrylonitrile units and preferably having the balance made up substantially of other addition-polymer-forming units, being halogenated hydrocarbon such as vinyl chloride or vinylidene chloride.

The polyolefine fibres (i) may be polyethylene,

ethylene-propylene copolymer, or (preferably) polypropylene.

The modacrylic is preferably Kanekalon (trade mark) by Kanegafuchi Chem. Co. and Kanekalon Co. of Japan or Teklan (trade mark) by Courtaulds. Kanekalon comprises 55 weight % vinyl chloride. Teklan comprises 50 weight % of vinylidene chloride and under 2 weight % of a third monomer for providing dye sites. The balance in both cases is substantially acrylonitrile. The modacrylic preferably comprises at least 40, more preferably at least 44, most preferably at least 50 weight % acrylonitrile.

The ratio of fibre (i) to fibre (ii) is preferably from 30:70 to 80:20 by surface area, more preferably from 40:60 to 70:30.

The fibres are preferably finer than 100 micrometres, preferably from 10 to 25 micrometres and preferably the fibre (i) cross-sectional area does not differ from the fibre (ii) cross-sectional area by more than a factor of 3. Staple length is preferably from 30 to 200 mm, more preferably 40 to 100 mm. The fibres (i) or (ii) or both are preferably crimped.

Preferably the material is a felt, preferably made by carding the fibres into a fleece and needling them. The carding is preferably performed by passing the material over a conventional two-swift card, or to substantially the equivalent extent by any alternative means. (The carding is likely to impose a practical limit on the fine-ness of usable fibres. The finer the fibres, the more efficient the filter but the higher the resistance to air flow.) The carding step must not be allowed to contaminate the fibres with anti-static agent or lubricant.

The invention will now be described by way of example.

The filter material is a mixture of two different crimped synthetic polymer fibres carded into a fleece and then needled to form a felt. The fibres are well mixed, and they became electrically charged during carding. The electric charge that they hold is critical in effecting the capture of small dust particles by the material.

The first fibre is polypropylene 20 micrometres thick, which in commerce is 2.8 decitex ($n \text{ tex} = n \text{ g/km}$). This may be e.g. round or trilobal. Polypropylene from various manufacturers has been tried, and found to be fairly consistent. Pigmented polypropylene is acceptable. Commercially produced polypropylene fibres normally have on them a "spin finish", which is a mixture of lubricant and anti-static agent. Polypropylene can be made finish-free quite easily, but usually it is not. This finish is removed before the fibres are carded. Any of the usual processes of textile scouring could be used, such as detergent, alkali or solvent scouring; scouring with a non-ionic detergent is quite effective.

tive provided it is thorough. Then the fibre is well rinsed.

The second fibre is modacrylic 18 micrometres thick, in particular Teklan (described above) of 3.5 decitex. Dyed modacrylic fibre is acceptable but undyed modacrylic fibre is preferred. Commercial modacrylic fibre cannot in practice be made without a "spin finish", which (as with polypropylene) is a mixture of lubricant and antistatic agent. This finish is removed before the fibres are carded. Any of the usual processes of textile scouring could be used, such as detergent, alkali or solvent scouring; scouring with a non-ionic detergent is quite effective provided it is thorough. Some benefit may be obtained from an alkali scour or chemical leaching. Acid scouring is not recommended.

These fibres are carded using a two-swift card, each swift having four worker-stripper units, in weight proportions 60 polypropylene: 40 modacrylic, i.e. to give surface areas roughly in the ratio 2:1, polypropylene: modacrylic, into a fleece. The carding causes both fibres to acquire electric charge, which, after falling during the next day, thereafter remains at a fairly constant level for several months. The fleece has a mass of 1.5 kg per square metre.

The fleeces are lightly needled, using a needle-punching loom, at 8mm penetration, 25 needlings/cm², to form a felt. Depending on the end use, where a stiffer or denser felt is wanted, heavier needling may be preferable.

The fibre processing machines (i.e. card and needle-loom) are kept clean to avoid contaminating the fibres, especially with spin finish from previous batches. Although not strictly essential, preferably all-metal card clothing is used, and if the needle-loom has boards with wooden backs, a new board should be used. Card clothing is usually contaminated with oil, and this must be removed.

The fibres may be (coarsely) mixed using a blender before the carding. The blender should likewise be kept clean. The carding completes the mixing, but if this is inadequate laterally across the fleece, a cross-laying stage can be interposed between the swifts, as is known practice.

The resulting filter material has low flammability, and may find use in dust helmets, disposable respirators and elsewhere.

The performance of the filter depends on its packing fraction (proportion of its volume occupied by fibres). Thus, the penetration of aerosols in general decreases (i.e. the filter is more effective) and the pressure drop increases (i.e. air flow is more impeded) as the packing fraction is increased at constant filter mass per unit area.

At a given packing fraction and mass per unit area, filters made from finer fibres are more effective than those made from coarser, but they also

have a higher resistance to airflow. The choice of fibre diameter is finally governed by the purpose for which the filter is intended, but it is likely that the most useful will be made from the finest fibres that can be carded without any difficulty.

A 'standard' aerosol (to B.S.4400 of 1969) at a fixed filtration velocity (0.28 m s⁻¹) was used on filters according to the invention on polypropylene/wool filters; and on filters made entirely from polypropylene, the respective filters being matched in a first series of comparative tests as regards pressure drop across them (100 Pa at the filtration velocity), and being matched in a second series as to mass per unit area (1.5 kg m⁻²).

In the first series of tests (constant pressure drop), the penetration of the 'standard' aerosol was 0.07% through the filter of the invention, 0.40% through the polypropylene/wool filters, and 10.2% through the pure polypropylene filter. In the second series of tests (constant filter mass per unit area), the penetration of the 'standard' aerosol through the filter of the invention was 0.032%, through the polypropylene/wool filter was 0.31% and through the pure polypropylene filters was 7.0%.

In a further test, the filter of the invention was encapsulated in a plastic filter cartridge of a type normally used in approved respirators. The cartridge was a short cylinder of approximately 13mm depth and 70 mm diameter. The filter was subjected to a test conforming in all essential features to that part of the British Standard BS 2091 test for respirators which comprises measurement of 'standard' aerosol penetration at a volume flow rate of 30 litres/minute through the filters, and measurement of the pressure drop across the filter at a flow rate of 85 litres/minute through the filter.

According to the Standard, a filter is rated as Class A if the aerosol penetration is no greater than 10% and the pressure drop is no greater than 200 Pa, and it is rated as Class B if the penetration is no greater than 2% (different criteria are applied to filters of different types; 2% penetration is applied to resin wool filters; it is the most rigorous and the most appropriate for the filter of the invention) and the pressure drop no greater than 320 Pa.

1.5 g of the material of the invention encapsulated in this way gave a penetration of 0.9% and a pressure drop of 63 Pa, and 3.0 g of the material of the invention so encapsulated gave a penetration of 0.3% and a pressure drop of 190 Pa. Both filters thus satisfied each class of the Standard.

Sufficient time has not elapsed for the stability of the charge on the filters described above to be conclusively established, but from previous experience it is considered that a substantial increase in aerosol penetration is likely in the first 24 hours after manufacture, followed by a much slower in-

crease. Penetration may double in the first 24 hours; from the 24 hour value it may increase by a factor of 1.5 in one month and 1.7 in one year. The filters used in the previous comparison tests were all therefore at least one day old.

Claims

1. A method of making a filter material for capturing dust, comprising taking (i) polyolefine fibres and removing lubricant and anti-static agent or ensuring the absence of lubricant and anti-static agent, taking (ii) fibres of an addition polymer comprising one or more halogen-substituted polyolefines, removing lubricant and anti-static agent from the fibres (ii), and blending the fibres (i) and (ii).
2. A method according to Claim 1, wherein the said halogen-substituted polyolefine is halogen-substituted polyethylene or polypropylene.
3. A method according to Claims 1 or 2, wherein the fibres (ii) contain one or more of chloroethylene units or acrylonitrile units or tetrafluoroethylene units.
4. A method according to Claim 3, wherein the fibres (ii) are polyvinyl chloride, polyvinylidene chloride, vinyl chloride - vinylidene chloride copolymer, chlorinated polyvinyl chloride or polytetrafluoroethylene.
5. A method according to Claim 3, wherein the fibres (ii) are modacrylic.
6. A method according to Claim 5, wherein the modacrylic is a copolymer comprising from 35 to 85 weight percent acrylonitrile units and having the balance made up substantially of halogenated hydrocarbon.
7. A method according to Claims 3 or 4, wherein the modacrylic comprises at least 40% acrylonitrile.
8. A method according to Claim 7, wherein the modacrylic comprises at least 44% acrylonitrile.
9. A method according to Claim 8, wherein the modacrylic comprises at least 50% acrylonitrile.
10. A method according to any preceding claim,

wherein the polyolefine fibres (i) are polyethylene or ethylene-propylene copolymer.

11. A method according to any preceding claim, wherein the polyolefine fibres (i) are polypropylene.
12. A method according to any preceding claim, wherein the ratio of fibre (i) to fibre (ii) is from 30:70 to 80:20 by surface area.
13. A method according to Claim 12, wherein the ratio of fibre (i) to fibre (ii) is from 40:60 to 70:30 by surface area.
14. A method according to any preceding claims, wherein the fibres are finer than 100 micrometres.
15. A method according to Claim 14, wherein the fibre diameters are from 10 to 25 micrometres.
16. A method according to any preceding claim, wherein the fibre (i) cross-sectional area does not differ from the fibre (ii) cross-sectional area by more than a factor of 3.
17. A method according to any preceding claim, wherein the fibre staple length is from 30 to 200 mm.
18. A method according to Claim 17, wherein the fibre staple length is from 40 to 100 mm.
19. A method according to any preceding claim, wherein the fibres (i) or (ii) or both are crimped before blending.
20. A method according to any preceding claim, further comprising forming the blended fibres into a felt.
21. A method according to Claim 20, wherein the felt is made by carding the fibres into a fleece and needling them.
22. The use of a filter material, made by the method of any preceding claim without any step detracting from the cleanliness of the fibres, for capturing dust electrostatically.
23. A filter material for capturing dust electrostatically, which has been made by the method of any of Claims 1 to 21.

Patentansprüche

1. Verfahren zur Herstellung eines Filtermaterials



crease. Penetration may double in the first 24 hours; from the 24 hour value it may increase by a factor of 1.5 in one month and 1.7 in one year. The filters used in the previous comparison tests were all therefore at least one day old.

Claims

1. A method of making a filter material for capturing dust, comprising taking (i) polyolefine fibres and removing lubricant and anti-static agent or ensuring the absence of lubricant and anti-static agent, taking (ii) fibres of an addition polymer comprising one or more halogen-substituted polyolefines, removing lubricant and anti-static agent from the fibres (ii), and blending the fibres (i) and (ii).
2. A method according to Claim 1, wherein the said halogen-substituted polyolefine is halogen-substituted polyethylene or polypropylene.
3. A method according to Claims 1 or 2, wherein the fibres (ii) contain one or more of chloroethylene units or acrylonitrile units or tetrafluoroethylene units.
4. A method according to Claim 3, wherein the fibres (ii) are polyvinyl chloride, polyvinylidene chloride, vinyl chloride - vinylidene chloride copolymer, chlorinated polyvinyl chloride or polytetrafluoroethylene.
5. A method according to Claim 3, wherein the fibres (ii) are modacrylic.
6. A method according to Claim 5, wherein the modacrylic is a copolymer comprising from 35 to 85 weight percent acrylonitrile units and having the balance made up substantially of halogenated hydrocarbon.
7. A method according to Claims 3 or 4, wherein the modacrylic comprises at least 40% acrylonitrile.
8. A method according to Claim 7, wherein the modacrylic comprises at least 44% acrylonitrile.
9. A method according to Claim 8, wherein the modacrylic comprises at least 50% acrylonitrile.
10. A method according to any preceding claim, wherein the polyolefine fibres (i) are polyethylene or ethylene-propylene copolymer.
11. A method according to any preceding claim, wherein the polyolefine fibres (i) are polypropylene.
12. A method according to any preceding claim, wherein the ratio of fibre (i) to fibre (ii) is from 30:70 to 80:20 by surface area.
13. A method according to Claim 12, wherein the ratio of fibre (i) to fibre (ii) is from 40:60 to 70:30 by surface area.
14. A method according to any preceding claims, wherein the fibres are finer than 100 micrometres.
15. A method according to Claim 14, wherein the fibre diameters are from 10 to 25 micrometres.
16. A method according to any preceding claim, wherein the fibre (i) cross-sectional area does not differ from the fibre (ii) cross-sectional area by more than a factor of 3.
17. A method according to any preceding claim, wherein the fibre staple length is from 30 to 200 mm.
18. A method according to Claim 17, wherein the fibre staple length is from 40 to 100 mm.
19. A method according to any preceding claim, wherein the fibres (i) or (ii) or both are crimped before blending.
20. A method according to any preceding claim, further comprising forming the blended fibres into a felt.
21. A method according to Claim 20, wherein the felt is made by carding the fibres into a fleece and needling them.
22. The use of a filter material, made by the method of any preceding claim without any step detracting from the cleanliness of the fibres, for capturing dust electrostatically.
23. A filter material for capturing dust electrostatically, which has been made by the method of any of Claims 1 to 21.

Patentansprüche

1. Verfahren zur Herstellung eines Filtermaterials



- zum Abfangen von Staub, bei dem man
 (i) Polyolefinfasern nimmt und Schmiermittel und antistatische Mittel entfernt oder die Abwesenheit von Schmiermitteln und antistatischen Mitteln sicherstellt,
 (ii) Fasern eines Additionspolymers, umfassend ein oder mehrere Halogen-substituierte Polyolefine, nimmt, Schmiermittel und antistatische Mittel von den Fasern (ii) entfernt,
 und die Fasern (i) und (ii) vermischt.
2. Verfahren nach Anspruch 1, wobei das Halogen-substituierte Polyolefin Halogen-substituiertes Polyethylen oder Polypropylen ist.
 3. Verfahren nach Anspruch 1 oder 2, wobei die Fasern (ii) eine oder mehrere Chlorethylen-Einheiten oder Acrylnitril-Einheiten oder Tetrafluorethylen-Einheiten enthalten.
 4. Verfahren nach Anspruch 3, wobei die Fasern (ii) Polyvinylchlorid, Polyvinylidenchlorid, Vinylchlorid/Vinylidenchlorid-Copolymer, chloriertes Polyvinylchlorid oder Polytetrafluorethylen sind.
 5. Verfahren nach Anspruch 3, wobei die Fasern (ii) Modacryl sind.
 6. Verfahren nach Anspruch 5, wobei das Modacryl ein Copolymer ist, umfassend 35 bis 85 Gew.-% Acrylnitril-Einheiten, und als Rest im wesentlichen halogenierten Kohlenwasserstoff.
 7. Verfahren nach Anspruch 3 oder 4, wobei das Modacryl mindestens 40% Acrylnitril umfaßt.
 8. Verfahren nach Anspruch 7, wobei das Modacryl mindestens 44% Acrylnitril umfaßt.
 9. Verfahren nach Anspruch 8, wobei das Modacryl mindestens 50% Acrylnitril umfaßt.
 10. Verfahren nach einem der vorangehenden Ansprüche, wobei die Polyolefinfasern (i) Polyethylen oder Ethylen/Propylen-Copolymer sind.
 11. Verfahren nach einem der vorangehenden Ansprüche, wobei die Polyolefinfasern (i) Polypropylen sind.
 12. Verfahren nach einem der vorangehenden Ansprüche, wobei das Verhältnis von Faser (i) zu Faser (ii) 30:70 bis 80:20, bezogen auf die Oberfläche, beträgt.
 13. Verfahren nach Anspruch 12, wobei das Verhältnis der Faser (i) zu Faser (ii) 40:60 bis 70:30, bezogen auf die Oberfläche, beträgt.
 14. Verfahren nach einem der vorangehenden Ansprüche, wobei die Fasern dünner als 100 µm sind.
 15. Verfahren nach Anspruch 14, wobei der Faserdurchmesser 10 bis 25 µm beträgt.
 16. Verfahren nach einem der vorangehenden Ansprüche, wobei der Querschnittsbereich der Faser (i) sich von dem Querschnittsbereich der Faser (ii) um nicht mehr als einen Faktor von 3 unterscheidet.
 17. Verfahren nach einem der vorangehenden Ansprüche, wobei die Stapellänge der Fasern 30 bis 200 mm beträgt.
 18. Verfahren nach Anspruch 17, wobei die Stapellänge der Faser 40 bis 100 mm beträgt.
 19. Verfahren nach einem der vorangehenden Ansprüche, wobei die Fasern (i) oder (ii) beide vor dem Vermischen gekräuselt worden sind.
 20. Verfahren nach einem der vorangehenden Ansprüche, umfassend ferner die Bildung eines Filzes aus den vermischten Fasern.
 21. Verfahren nach Anspruch 20, wobei der Filz hergestellt wird durch Kartieren der Fasern zu einem Vlies und Nadeln (des Vlieses).
 22. Verwendung eines Filtermaterials; hergestellt nach dem Verfahren nach einem der vorangehenden Ansprüche, ohne eine Stufe, die die Sauberkeit der Fasern verringert, zum elektrostatischen Abfangen von Staub.
 23. Filtermaterial zum elektrostatischen Abfangen von Staub, das nach dem Verfahren nach einem der Ansprüche 1 bis 21 hergestellt worden ist.

Revendications

1. Procédé pour fabriquer un matériau de filtre pour capturer des poussières, comprenant les étapes suivantes :
 - prendre (i) des fibres de polyoléfine et enlever le lubrifiant et l'agent antistatique ou s'assurer de l'absence de lubrifiant et d'agent antistatique,
 - prendre (ii) des fibres d'un polymère d'addition contenant des polyoléfines substituées par un ou plusieurs atomes



d'halogène,

- enlever le lubrifiant et l'agent antistatique des fibres (ii), et
- mélanger les fibres (i) et (ii).

2. Procédé selon la revendication 1, dans lequel la polyoléfine substituée par un halogène est un polyéthylène ou un polypropylène substitué par un halogène.

3. Procédé selon la revendication 1 ou la revendication 2, dans lequel les fibres (ii) contiennent une ou plusieurs unités de chloroéthylène ou d'acrylonitrile ou de tétrafluoroéthylène.

4. Procédé selon la revendication 3, dans lequel les fibres (ii) sont un polychlorure de vinyle, un polychlorure de vinylidène, un copolymère de chlorure de vinyle et de chlorure de vinylidène, un polychlorure de vinyle chloré ou un polytétrafluoroéthylène.

5. Procédé selon la revendication 3, dans lequel les fibres (ii) sont des fibres modacryliques.

6. Procédé selon la revendication 5, dans lequel la résine modacrylique est un copolymère comprenant de 35 à 85% en poids d'unités d'acrylonitrile et ayant le reste constitué pratiquement par un hydrocarbure halogéné.

7. Procédé selon la revendication 3 ou la revendication 4, dans lequel la résine modacrylique contient au moins 40% d'acrylonitrile.

8. Procédé selon la revendication 7, dans lequel la résine modacrylique contient au moins 44% d'acrylonitrile.

9. Procédé selon la revendication 8, dans lequel la résine modacrylique contient au moins 50% d'acrylonitrile.

10. Procédé selon l'une des revendications précédentes, dans lequel les fibres de polyoléfine (i) sont un polyéthylène ou un copolymère d'éthylène et de propylène.

11. Procédé selon l'une des revendications précédentes, dans lequel les fibres de polyoléfine (i) sont un polypropylène.

12. Procédé selon l'une des revendications précédentes, dans lequel le rapport des fibres (i) aux fibres (ii) est compris entre 30:70 et 80:20 par surface spécifique.

13. Procédé selon la revendication 12, dans lequel

le rapport des fibres (i) aux fibres (ii) est compris entre 40:60 et 70:30 par surface spécifique.

5 14. Procédé selon l'une des revendications précédentes, dans lequel les fibres sont plus fines que 100 µm.

10 15. Procédé selon la revendication 14, dans lequel les diamètres des fibres sont compris entre 10 et 25 µm.

15 16. Procédé selon l'une des revendications précédentes, dans lequel la surface en section transversale des fibres (i) ne diffère pas de la surface en section transversale des fibres (ii) de plus d'un facteur de 3.

20 17. Procédé selon l'une des revendications précédentes, dans lequel la longueur des fibres coupées est comprise entre 30 et 200 mm.

25 18. Procédé selon la revendication 17, dans lequel la longueur des fibres coupées est comprise entre 40 et 100 mm.

30 19. Procédé selon l'une des revendications précédentes, dans lequel les fibres (i), ou les fibres (ii), ou les deux, sont crépées avant le mélange.

35 20. Procédé selon l'une des revendications précédentes, comprenant en outre l'étape dans laquelle on forme les fibres mélangées en un feutre.

40 21. Procédé selon la revendication 20, dans laquelle le feutre est fabriqué en cardant les fibres en une nappe et en les aiguilletant.

45 22. Utilisation d'un matériau de filtre, fabriqué par le procédé selon l'une quelconque des revendications précédentes sans qu'aucune étape ne mette en cause la propreté des fibres, pour capturer la poussière par voie électrostatique.

50 23. Matériau de filtre pour capturer la poussière par voie électrostatique, qui a été fabriqué par le procédé selon l'une quelconque des revendications 1 à 21.

55