

# ABSTRACT

The low-dielectric-constant glass fiber of the present invention contains by weight, as a glass composition, 50 to 60 % of  $\text{SiO}_2$ , 10 to 20 % of  $\text{Al}_2\text{O}_3$ , 20 to 30 % of  $\text{B}_2\text{O}_3$ , 0 to 5 % of  $\text{CaO}$ , 0 to 4 % of  $\text{MgO}$ , 0 to 0.5 % of  $\text{Li}_2\text{O} + \text{Na}_2\text{O} + \text{K}_2\text{O}$  and 0.5 to 5 % of  $\text{TiO}_2$ , and is preferably used as glass for printed wiring boards.