

Description

The present invention pertains generally to a twist drill according to the preamble of claim 1, cf. EP-A-127 009, and in particular to improvements to reduce cutting resistance exerted thereon during drilling operation.

Prior Art

Twist drills made of HSS or sintered metal HSS have hitherto been developed as drills for effecting heavy-duty drilling operations. Figs. 1 and 2 depict a conventional twist drill of such type which has a cylindrical body 1, a pair of spiral grooves or flutes 2 formed in the outer peripheral surface of the body 1 and a pair of lands each disposed between the pair of flutes 2. That wall portion of each flute 2 facing in the direction of rotation of the body 1 terminates at the forward end in a cutting edge or lip 3. Each spiral flute 2 is so formed that its wall is concavely shaped. In the drill for heavy-duty operations, the web thickness T of the drill body 1 is made greater than a HSS drill for normal drilling operations so that it is about 30% of the drill diameter, while the flute-width ratio at the forward end defined by the arc length A of the flute to the arc length B of the land is set to be about 0.7. Furthermore, at a cross-section of the drill, away from the forward end, the ratio of the arc length A_1 of the flute to the arc length B_1 of the land is set to about 1.16. With this construction, the torsional rigidity of the body 1 of the twist drill is considerably enhanced.

Furthermore, twist drills formed of cemented carbide or cermet have also been extensively employed for heavy-duty drilling operations. Such drills are superior in wear resistance to HSS drills, but, due to the inferior mechanical strength, e.g., transverse rupture strength, a greater web thickness and a smaller flute-width ratio are necessary. Figs. 3 and 4 illustrate a prior art drill of such type as disclosed in Examined Japanese Patent Application Publication No. 61-30845 (EP-A-127 009), in which the symbols in common with those in Figs. 1 and 2 denote the same or like parts. In this drill, the web thickness T and the flute-width ratio A/B are set to range between 20 and 35% of the drill diameter and between 0.4 and 0.8, respectively, while the flute-width ratio A_1/B_1 at a cross-section away from the forward end is approximately 0.6.

In the twist drills of the afore-described types, however, there is always the problem that the drill body 1 is susceptible to breakage when subjected to heavy-duty drilling operations.

More specifically, chips or cuttings produced by the cutting lips 3 during a drilling operation are produced as if a sector-shaped folding fan were opened since their outer sides grow faster than the inner sides, and curl at their tip ends by the bottom 2a of the flute 2, i.e., by that portion of the flute wall where the distance between a line L perpendicular to a radial line N, connecting the axis O of the body 1 to a radially outermost end Q of the cutting lip 3, and the flute wall is greatest, so that the chips are broken at their roots by the resistance caused due to the curling. The chips thus formed are illustrated in Fig. 5, and are classified as "transition curled fractured type chips". In the above twist drills, the distance W between the line L and the bottom 2a of the flute 2 is made rather small in order to enhance torsional rigidity. As a result, the force exerted on the chips by the bottom 2a of the flute 2 acts in the direction opposite to the direction in which they grow, and hence thick chips, compressed strongly in the longitudinal direction, are produced. The addition of the relatively large force on the chips causes the drill body 1 to be subjected to a great cutting torque and thrust load.

Furthermore, in the above twist drills, the cross-sectional area of the flute 2 away from the forward end, which serves to discharge the chips, is rendered inevitably smaller, so that the chips may be jammed therein. This often causes the drill to break when the heavy-duty drilling operation is effected.

SUMMARY OF THE INVENTION

It is therefore a primary object of the invention to provide an improved twist drill which is less susceptible to breakage during heavy-duty drilling operations.

Another object of the invention is to provide a twist drill which can reduce the cutting resistance substantially by curling chips easily, and ensuring a smooth discharge of the chips through flutes during the drilling operation.

According to the present invention, there is provided a twist drill comprising the features defined in claim 1.

BRIEF DESCRIPTION OF THE DRAWINGS

- Fig. 1 is a forward end view of a conventional twist drill;
 Fig. 2 is a cross-sectional view of the drill of Fig. 1;
 5 Fig. 3 is a view similar to Fig. 1, but showing a different conventional twist drill;
 Fig. 4 is a cross-sectional view of the drill of Fig. 3;
 Fig. 5 is a view showing a chip produced during a drilling operation;
 Fig. 6 is a forward end view of a twist drill provided in accordance with a first embodiment;
 Fig. 7 is a side elevation of the drill of Fig. 6 as seen from the direction indicated by the arrow VII in Fig. 6;
 10 Fig. 8 is a cross-sectional view of the drill of Fig. 6 taken along the line VIII-VIII in Fig. 7;
 Fig. 9 is a forward end view of a modified twist drill in accordance with a second embodiment;
 Fig. 10 is an enlarged view of the circled portion labeled as X in Fig. 9;
 Fig. 11 is a forward end view of another modified twist drill in accordance with a third embodiment;
 15 Fig. 12 is a view of a part of the drill of Fig. 11 as seen from the direction designated by XII in Fig. 11;
 Fig. 13 is a side elevation of the drill of Fig. 11;
 Fig. 14 is a cross-sectional view of a part of the drill of Fig. 11 taken along the line XIV-XIV in Fig. 11;
 Fig. 15 is a view of the drill of Fig. 11 as seen from the direction indicated by the arrow XV in Fig. 12;
 Fig. 16 is a view of the drill of Fig. 11 as seen from the direction indicated by the arrow XVI in Fig. 12;
 20 Fig. 17 is an enlarged view of a chisel portion of the drill of Fig. 12;
 Fig. 18 is a view similar to Fig. 17, but showing a different arrangement of the chisel;
 Fig. 19 is a forward end view of a further modified drill in accordance with a fourth embodiment;
 Fig. 20 is a side elevation of the drill of Fig. 19 as seen from the direction designated by XX in Fig. 19;
 Fig. 21 is a cross-sectional view of the drill of Fig. 19 taken along the line XXI-XXI in Fig. 20;
 25 Fig. 22 is a forward end view of a further modified twist drill in accordance with a fifth embodiment;
 Fig. 23 is a side elevation of the drill of Fig. 22 as seen from the direction designated by XXIII in Fig. 22;
 Fig. 24 is a view similar to Fig. 22, but showing a modification of the drill of Fig. 22;
 Fig. 25 is also a view similar to Fig. 22, but showing a further modification of the drill of Fig. 22;
 Fig. 26 is an enlarged view of the circled portion labeled XXVI in Fig. 25;
 30 Fig. 27 is a view as seen from the direction designated by XXVII in Fig. 25, but showing a further modified drill in accordance with a sixth embodiment;
 Fig. 28 is a side elevation of the drill of Fig. 27;
 Fig. 29 is a cross-sectional view of the drill of Fig. 27 taken along the line XXIX-XXIX in Fig. 25;
 Fig. 30 is a view of a part of the drill of Fig. 27 as seen from the direction designated by the arrow XXX in Fig. 27;
 35 Fig. 31 is a view of a part of the drill of Fig. 27 as seen in the direction designated by the arrow XXXI in Fig. 27;
 Fig. 32 is an enlarged view showing a chisel portion of the drill of Fig. 27;
 Figs. 33 and 34 are views similar to Fig. 32, but showing further modifications of the chisel portion,
 40 respectively;
 Fig. 35 is a forward end view of a further modified twist drill in accordance with a seventh embodiment;
 Fig. 36 is a side elevation of the drill of Fig. 35 as seen from the direction designated by the arrow XXXVI in Fig. 35;
 Fig. 37 is a cross-sectional view of the drill of Fig. 35 taken along the line XXXVII-XXXVII in Fig. 36; and
 45 Fig. 38 is a view similar to Fig. 35, but showing a further modification of the drill of Fig. 35.

DESCRIPTION OF THE PREFERRED EMBODIMENTS OF THE INVENTION

In order to clarify the present invention as defined in claim 1, figures 6-38 describe different
 50 embodiments which do not all comprise all essential features defined in claim 1.

In Figs. 6 to 8, there is illustrated a twist drill in accordance with a first embodiment. The drill includes a
 cylindrical body 10 of high speed steel (HSS) or sintered metal HSS having an axis O of rotation
 therethrough and a forward end which contacts a workpiece. The body 10 has a pair of spiral flutes 11
 formed in the outer peripheral surface of the body and extending spirally along its length to the forward end,
 55 and a pair of lands 10a each disposed between the pair of flutes. Each flute 11 has a first wall facing in the
 direction of rotation of the body 10 and extending from the outer periphery of the body 10 generally radially
 inwardly and a second wall extending from an inner end of the first wall to the outer periphery of the body
 10. Each of the first walls terminates at the forward end in a first or primary cutting lip 12 which has a

radially outermost end Q disposed on the outer periphery of the body 10. Each second wall is a smooth continuation of the first wall and is concavely shaped when viewed from the forward end. In order to provide a greater torsional rigidity of the body, the body 10 has a web thickness T of 15 to 30% of the drill diameter D and a flute-width ratio A/B of 0.4 to 0.9. Those portions of relief surfaces or flanks disposed rearwardly with respect to the direction of rotation of the body 10 are ground off, as at 13, to provide cross- or X-type ground surfaces 15, and hence second cutting lips 13a, each extending away from the axis O of rotation to the radially innermost end of a respective first cutting lip 12, are formed at the web portion.

Furthermore, consider a line N connecting the axis O of the body 10 and the radially outermost end Q of the cutting lip 12 and a line L extending from the radially outermost end Q of the cutting lip 12 perpendicular to the line N in an end view seen from the forward end of the body. Then, the distance W between the line L and the bottom 11a of the flute 11, i.e., the maximum distance between the line L and the wall of the flute 11, is made to range from 45 to 65% of the drill diameter D. With this arrangement, the spiral flute 11 is so shaped that the second wall, including the bottom 11a, is deeply recessed in the direction of rotation of the body 10. Additionally, the entire surface of the drill body 10 is coated with a hard coating composed of at least one material selected from the group consisting of TiC, TiN, TiCN and Al_2O_3 . Such a coating may be made of carbide, nitride or carbo-nitride of other metal selected from Group IVa of the Periodic Table, and may be limited to the forward end of the body 10.

In the twist drill as described above, a chip produced by the cutting lip 12 grows and is curled at the bottom 11a of the flute 11, so that it is broken into pieces of a transition curled fractured type as illustrated in Fig. 5. Inasmuch as the distance W between the line L and the bottom 11a of the flute 11 is set to be no less than 45% of the drill diameter, the freedom of the chip to curl inwards is greater than for conventional drills. As a result, the resistance exerted on the chip in the direction opposite to the direction in which the chip grows is divided into forces to cause the chip to bend or to buckle. Accordingly, the load on the chip is not as great as for conventional drills so that the thrust load and cutting torque can be greatly reduced.

These points were verified by way of the following drilling tests.

Drilling Test 1

There were prepared several twist drills having various ratios of the distance W to the drill diameter. The test drill had a diameter of 12mm and a point angle of 140° , and the radial rake angle of the cutting lip was -15° . The drilling tests were conducted under the following conditions:

Cutting speed: 35m/min.

Workpiece: Steel (JIS SCM440; Hardness: H_B 100)

Feed rate: 0.15, 0.25, 0.35, 0.45 and 0.55mm/revolution

The thicknesses of chips produced during the drilling operation using the above various drills were measured at a point designated by S in Fig. 5. The results are shown in Table 1.

Table 1

Feed rate (mm/rev.)	Thickness of chips (mm)				
	Drills of the invention Ratio (%)			Prior art drills Ratio (%)	
	53	50	45	43	41
0.15	0.261	0.293	0.309	0.423	0.445
0.25	0.355	0.369	0.387	0.528	0.542
0.35	0.427	0.440	0.466	0.634	0.654
0.45	0.524	0.525	0.553	0.756	0.789
0.55	0.650	0.658	0.698	0.955	0.997

As will be seen from Table 1, when the ratio, i.e. the distance W from the line L to the bottom 11a of the flute 11, is no less than 45 % of the drill diameter, the thicknesses of the chips are reduced substantially. This means that the resistance exerted on the chip can be substantially reduced by setting the distance W to be no less than 45% of the drill diameter.

Drilling Test 2

The drill having a distance W of 53% of the drill diameter and the drill having a distance W of 41% of the drill diameter, both of which were prepared for Drilling Test 1, were again used, and the drilling tests were conducted under the same conditions as those in Drilling Test 1. In this test, the thrust load, cutting torque, cutting power and maximum amplitude of vibration of the spindle during the drilling operation were measured. The results are shown in Table 2.

Table 2

	Feed rate (mm/rev.)				
	0.15	0.25	0.35	0.45	0.55
Thrust load (Kg)					
Drill of the invention	120	164	208	308	356
Prior art drill	216	280	352	416	480
Cutting torque (Kg·mm)					
Drill of the invention	80	116	152	236	268
Prior art drill	116	184	218	264	354
Cutting power (Kw)					
Drill of the invention	0.45	0.68	0.86	1.22	1.39
Prior art drill	0.74	1.19	1.37	1.62	2.07
Amplitude of vibration of the spindle (μ)					
Drill of the invention	3.0	2.64	2.64	2.76	2.34
Prior art drill	3.6	5.76	2.7	4.2	6.54

It is seen from Table 2 that in the drill of the invention, the thrust load, cutting torque and cutting power are all reduced markedly in comparison with the prior art drill. This is because, by the drill of this invention, chips can be easily curled without being deflected sharply, and the force exerted on the chips can be reduced.

As verified in the above drilling tests, for the twist drill in accordance with the present invention, the cutting resistance during drilling operations can be reduced significantly. In addition, since the distance between the line L and the bottom 11a of the flute 11 is set to be no greater than 65% of the drill diameter D, the thickness of the body 10 between the second wall of the flute near a heel 11b and the peripheral land 10a is adequate to avoid chipping damage or cracking, and high torsional rigidity of the drill can be maintained. Additionally, since the surface of the drill body is coated with TiC, TiCN or the like, wear resistance is sufficiently enhanced, and this enables heavy-duty operations to be performed.

Furthermore, as also seen from the results of the above drilling tests, the vibration of spindle of the machine tool is reduced. Accordingly, not only is the chipping damage of the cutting lip reduced, but also drilling precision is enhanced. Moreover, since the flute 11 is so formed that the wall portion including the bottom 11a is recessed deeply in the direction of rotation of the body, the cross-sectional area of the flute 11 is large, and hence chips can be smoothly removed.

Figs. 9 and 10 depict a twist drill in accordance with a second embodiment. In this drill, the first cutting lip 12 and the second cutting lip 13a, formed by the cross-thinning or X-thinning as at 13, are formed so that when viewed from the forward end of the body 10, they are straight edges and the intersection 14 between the first cutting lip 12 and the second cutting lip 13a is curved at a prescribed radius of curvature r.

With this construction, the width of the chisel is rendered very small by the cross thinning, and hence the thrust load can be further reduced. In addition, since the first cutting lip 12 and the second cutting lip 13a are straight, the thickness of the chip becomes uniform in the transverse direction of the chip. For this reason, the chip tends to buckle easily when bent, so that it curls readily without being forced. Furthermore, since the intersection 14 of the first cutting lip 12 with the second cutting lip 13a is curved, chips are not prone to separation at the intersection 14, thereby preventing the jamming of the chip and hence the breakage of the drill.

In this illustrated embodiment, the radius of curvature r of the intersection 14 is set to satisfy the relationship $0.05D \leq r \leq 0.15D$. If the radius of curvature r exceeds $0.15D$, the effective portion of the cutting lip 12, which has a rake angle corresponding to the helix angle of the flute 11, is unduly reduced, and cutting resistance is increased. On the other hand, if the radius of curvature r is less than $0.05D$, chipping damage or separation of the chip is apt to occur at the intersection 14.

Figs. 11 to 18 illustrate a twist drill in accordance with a third embodiment. In this embodiment, when viewed from the forward end of the body, the first cutting lip 12 and the second cutting lip 13a are formed as straight edges intersecting each other at a sharp point P, and the following features are further added:

- (1) An angle α , defined as the angle between the second cutting lip 13a and the radial line N which connects the axis O of rotation and the outermost end Q of the cutting lip 12 together as viewed from the forward end of the body 10, is set to range from 15° to 35° .

The above range is the optimal one for preventing chips from jamming and to improve chip removal efficiency. More specifically, that portion of a chip cut by the second cutting lip 13a and that portion of the chip cut by the first cutting lip 12 grow at different speeds from each other, so that as the chip is produced, it curls toward the center of the drill. If the above angle α exceeds 35° , the direction of growth of the portion of the chip cut by the first cutting lip 12 is greatly different from the direction of growth of the portion of the chip cut by the second cutting lip 13a. Therefore, the chip is liable to be separated at a position corresponding to the intersection of the first cutting lip 12 with the second cutting lip 13a. Furthermore, since the angle $(\alpha + \delta)$, defined as the angle between the second cutting lip 13a and the first cutting lip 12, is rendered small, the cutting lips become susceptible to chipping damage at the intersection P.

On the other hand, if the angle α is less than 15° , the ratio of the length of the second cutting lip 13a with respect to the length of the first cutting lip 12, becomes large. Accordingly, the direction in which the chip grows is greatly affected by that portion of the chip cut by the second cutting lip 13a, so that required differential growth rate is not properly achieved. The longer second cutting lip 13a also causes the cutting resistance to increase.

- (2) The radial rake angle δ of the cutting lip 12 at its outer end is set to range between -10° to -20° , and the ratio of a length L_1 between the axis O of rotation and the intersection P to a length L_2 between the intersection P and the outermost end Q of the cutting lip 12 is set to range between 0.4:1 and 0.7:1. These ranges are the optimal ones for reducing cutting resistance to prevent the jamming of chips. More specifically, if the ratio L_1/L_2 is less than 0.4, the second cutting lip 13a cuts a narrow portion of a chip from a workpiece, so that, due to the large force exerted on the narrow portion when extended into the spiral flute 11, the narrow portion separates from the portion of the chip cut by the cutting lip 12. On the other hand, if the ratio L_1/L_2 exceeds 0.7, the growth direction of the chip is greatly affected by that portion of the chip cut by the second cutting lip 13a, so that a somewhat elongated chip, different from the normal transition curled fractured type, is formed. The increase of the proportion of the second cutting lip 13a also causes the cutting resistance to increase.

Furthermore, if the radial rake angle δ exceeds -10° , then the angle $(\alpha + \delta)$, defined as the angle between the cutting lip 12 and the second cutting lip 13a, becomes excessively small. As a result, the portions of chip do not interfere with each other, and the strength at the outermost end Q of the cutting lip 12 is unduly lowered. On the other hand, if the radial rake angle δ is less than -20° , the angle $(\alpha + \delta)$, defined as the angle between the cutting lip 12 and the second cutting lip 13a, increases, and hence the chip becomes liable to divide into two pieces at the intersection 14 therebetween, and the cutting resistance is increased.

- (3) An axial rake angle θ for the second cutting lip 13a is set to be from 0° to -5° (Fig. 14).

Since the axial rake angle θ for the second cutting lip 13a is negative, the ground surface can be left as a rake surface for the second cutting lip 13a when the drill is resharpened, so that resharpening can be easily effected. In addition, the strength of the second cutting lip 13a can be enhanced. However, if the axial rake angle θ is made too negative, the cutting resistance at the second cutting lip 13a increases. Therefore, the axial rake angle should be no more negative than -5° .

- (4) An angle λ , defined as the angle between a ground surface 15 and a rake surface 16 disposed along the second cutting lip 13a, is set to be 95° to 115° (Fig. 15).

Since the portion of the chip produced by the second cutting lip 13a passes into the flute 11 after it reaches the ground surface 15, it undergoes a high force at that time. If the angle λ is less than 95° , the force exerted on the portion of the chip cut by the second cutting lip 13a is increased excessively, and hence that portion of the chip tends to separate from the portion of the chip cut by the cutting lip 12. Furthermore, inasmuch as the force exerted on the chip is large, the thrust load is increased. On the other hand, if the angle λ exceeds 115° , that portion of the drill body 10 adjacent to the heel is reduced

too much, so that the chip will not be easily curled in the flute 11.

(5) A valley line 17 defined by the ground surface 15 and the rake surface 16 disposed along the second cutting lip 13a intersects with the axis O of the body 10 at an angle ϕ of 30° to 40° (Fig. 12).

If the angle ϕ exceeds 40° , the friction between the portion of the chip cut by the second cutting lip 13 and the ground surface 15 becomes great, so that the fragmentation of the chip as described above will occur and thrust load will increase. On the other hand, if the angle ϕ is set too small, an excess of the portion of the body 10 disposed adjacent to the heel is removed, and hence the angle should be no less than 30° . By setting the angle ϕ from 30° to 40° , separation of the portion of the chip cut by the second cutting lip 13a from the portion of the chip cut by the cutting lip 12 can be prevented, and the thrust load can be reduced substantially.

(6) An axial distance l between the outermost end Q of the cutting lip 12 and the outermost end H of the heel 11b is designed to be $0.3D$ to $1.0D$ (Fig. 12).

If the distance l is set to exceed $0.3D$, the fluid passage of cutting oil toward the cutting part is ensured. However, if the distance l exceeds $1.0D$, that portion of the body 10 adjacent to the heel will not be adequate.

(7) As shown in Figs. 11 and 16, the drill body 10 includes first and second planar flanks 18 and 19 formed on the forward end face thereof. The first flank 18, which is provided with a relief angle β_1 of 7° to 15° , is disposed along the first cutting lip 12, while the second flank 19, which is provided with a relief angle β_2 greater than that of the first flank so as to range from 15° to 25° , is disposed along the first flank 18. That ridge at F, defined by the intersection of the first and second flanks 18 and 19, is parallel to the cutting lip 12 and intersects with the axis O of the body 10.

The provision of the second flank 19 is to prevent frictional engagement between it and the bottom of a drilled hole, and to ensure a fluid passage for cutting oil, so that the cutting part can be lubricated and cooled efficiently by the cutting oil. This is very advantageous for the HSS drill which is often used for heavy-duty drilling operations.

Moreover, since the first and second flanks 18 and 19 are formed to be planar, the first and second flanks can be resharpenered by surface grinding. This ensures a better surface finish as compared with the conical sector grinding method which is conventionally used. In addition, since the grinding is easily conducted, minute chipping damage at the ridge lines such as the cutting lip 12 is prevented from occurring during the grinding. As a result, the service life of the drill can be extended and troubles such as early fracture can be avoided.

Furthermore, since the relief angle β_1 is set to be below 7° , flank wear can be effectively prevented. This feature is particularly effective in the case where a high-feed drilling operation is conducted. On the other hand, if the relief angle β_1 exceeds 15° , the included angle ρ of the cutting lip 12 is reduced, so that the cutting lip 12 becomes susceptible to chipping or fracture.

Moreover, since the relief angle β_2 is no less than 15° , the fluid passage for supplying cutting oil to the cutting part can be sufficiently ensured, and the cooling and lubricating effect of the oil can be improved. On the other hand, to obtain sufficient rigidity at the cutting lip, it is preferable that the relief angle β_2 should be no greater than 25° .

In the above, the reason why the ridge F, defined as the intersection of the first and second flanks 18 and 19, is set to be parallel to the cutting lip 12 and to intersect with the axis O of the body is as follows.

If the intersection ridge F is formed so that, as viewed from the forward end of the body 10, it is inclined in the direction of rotation of the body 10 with respect to the cutting lip 12, the width of the first flank 18 is reduced at its radially outer end portion, so that the rigidity of the cutting lip is unduly reduced at its outer portion. On the other hand, if the intersection ridge F is formed so that it is inclined in the direction opposite to the direction of rotation of the body 10 with respect to the cutting lip 12, the first flank 18 is enlarged in width at its outer end portion, so that a second impingement or flank-engagement tends to occur. Furthermore, if the intersection ridge F is formed so that it is inclined in the direction of rotation of the body 10, a chisel edge 20 with a greater chisel angle γ is formed at the border between the two second flanks 19 as shown in Fig. 18, and hence the mechanical strength of the chisel edge 20 is lowered. Accordingly, it is preferable that the intersection ridge F should be formed so as to pass through the axis O or to be inclined in the direction opposite to the direction of rotation of the body 10. The first and second flanks can be precisely formed again upon the resharpenering of the drill when the intersection ridge F is designed to intersect the axis O of the body 10.

(8) Suppose an imaginary line extends along the ridgeline of one of the second cutting lips 13a. Then, in the embodiment, the intervening distance C between the imaginary line and the other second cutting lip 13a is 0 to 0.3mm, and the chisel edge 20 is formed between adjacent ends of the two second cutting lips 13a. The width G of the chisel edge 20 is set to be 0 to 0.4 mm (Fig. 17).

The chisel edge 20 acts so as to separate the workpiece. If the chisel edge width G is great, the thrust load increases and the cutting speed increases at the ends of the chisel 20, so that the ends of the chisel are susceptible to chipping. Therefore, the chisel edge width G should be preferably near zero, so that the above disadvantage is avoided and stable engagement can be ensured by setting it to be no greater than 0.4mm.

(9) An oil hole 22 for passage of a cutting fluid is formed through the drill body 10 so as to extend spirally along the spiral flutes 11 (Fig. 13).

With this construction, even after resharpening, the position of the oil hole 22 would remain unchanged, and hence cutting operation can be always conducted under the same conditions. In addition, inasmuch as the oil hole 22 is spiral, the torsional rigidity of the body 10 is barely lowered. Therefore, in combination with the effects due to the optimal range relating to the distance W , the drill can be used for heavier duty drilling operations. These advantages could also be expected even if the drill was provided with non-linear first and second cutting lips.

(10) The heel 11b, defined by the intersection of the flute 11 with the outer peripheral land 10a, is relieved to provide a chamfered face extending along the flute 11. This chamfered face is about 0.5mm wide. Instead of chamfering, the heel may be rounded off so as to have a radius of curvature of about 0.5mm. With either of these machinings, the heel can be prevented from being chipped or fractured by the chips produced during the drilling operation.

Figs. 19 to 21 illustrate a further modified twist drill in accordance with a fourth embodiment. As is the case with the drill of the first embodiment, the drill body 10 is made of HSS or sintered metal HSS, and the web thickness T is set to be 15 to 30 % of the drill diameter D . Those portions of flanks located rearwardly with respect to the direction of rotation of the body 10 are subjected to cross thinning as at 13 to provide X-type ground surfaces 15, and second cutting lips 13a each extending away from the axis O of rotation to the radially innermost end of a respective first cutting lip 12 are formed at the web portion. The distance W between the line L and the bottom 11a of the flute 11 is designed to range from 45 % to 65 % of the drill diameter D , so that the second wall of the spiral flute 11 is recessed deeply in the direction of rotation of the body 10. Furthermore, the entire surface of the drill body 10 is coated with a hard coating composed of at least one material selected from the group consisting of TiC, TiN, TiCN and Al_2O_3 . In this drill, too, inasmuch as the distance W between the line L and the bottom 11a of the flute 11 is set to be no less than 45 % of the drill diameter, the resistance exerted on the chip in the direction opposite to the direction in which the chip grows is divided into forces to cause the chip to bend or buckle. Accordingly, the chip is prevented from being strongly compressed, so that the thrust load and cutting torque can be greatly reduced.

Furthermore, in this embodiment, the ratio of arc length A_1 of the flute 11 to arc length B_1 of the land in a cross-section taken perpendicular to the axis O of the body 10, i.e., a flute-width ratio A_1/B_1 at a cross-section away from the forward end, is set to range between 0.9 and 1.2. That portion of the wall of the flute 11 which contacts an imaginary cylinder inscribing the web portion of the body 10 is concavely arcuately shaped at such a radius of curvature R as to satisfy the relationship: $0.15D \leq R \leq 0.2D$. The length of this arcuately-shaped portion, as viewed axially of the body 10, is defined by an arc with a central angle ω from 19° to 49° , preferably from 24° to 44° , and more preferably from 29° to 39° . Within this range of the central angle ω , not only will a chip produced by the cutting lip 12 be curled positively, but also the friction between the chip and the wall of the flute 11 can be reduced, so that the curling of the chip can be smoothly effected.

As was the case with the first embodiment, the advantages of this embodiment were verified by way of the following drilling tests.

Drilling Test 3

There were prepared several twist drills, having various ratios of the distance W to the drill diameter, in accordance with the fourth embodiment of the invention. The test drill had a diameter of 12mm and a point angle of 140° , and the radial rake angle of the cutting lip was -15° . Then the procedures, as set forth in Drilling Test 1 were repeated under the same conditions, and the thicknesses of chips produced during the drilling operation were measured. The results are shown in Table 3.

As seen from Table 3, when the distance W from the line L to the bottom 11a of the flute 11 is no less than 45% of the drill diameter, the thicknesses of chips are reduced substantially as was the case with the first embodiment, and hence the resistance exerted on the chip can be substantially reduced.

Drilling Test 4

The drill having the distance W of 53% of drill diameter and the drill having the distance W of 41% of drill diameter, which were prepared for Drilling Test 3, were again used, and the drilling tests were carried out under the same conditions as those in Drilling Test 1. In this test, the thrust load, cutting torque, cutting power and maximum amplitude of vibration of the spindle during the drilling operation were measured. The results are shown in Table 4.

It is seen from Table 4 that in the drill of the invention, the thrust load, cutting torque and cutting power are all reduced markedly in comparison with the prior art drill. Therefore, in the drill of this invention, since the chips can be curled without being compressed strongly, the resistance exerted on the chips can be reduced, so that the cutting resistance such as thrust load can be decreased substantially.

Table 3

Feed rate (mm/rev.)	Thickness of chips (mm)				
	Drills of the invention Ratio (%)			Prior art drills Ratio (%)	
	53	50	45	43	41
0.15	0.257	0.289	0.301	0.426	0.451
0.25	0.349	0.370	0.391	0.523	0.546
0.35	0.420	0.438	0.466	0.635	0.661
0.45	0.511	0.523	0.550	0.761	0.790
0.55	0.646	0.657	0.657	0.954	0.991

Table 4

	Feed rate (mm/rev.)				
	0.15	0.25	0.35	0.45	0.55
Thrust load (Kg)					
Drill of the invention	118	159	208	310	360
Prior art drill	220	284	350	418	485
Cutting torque (Kg·mm)					
Drill of the invention	78	115	156	240	271
Prior art drill	121	181	219	259	351
Cutting power (Kw)					
Drill of the invention	0.42	0.70	0.85	1.23	1.45
Prior art drill	0.71	1.23	1.41	1.59	2.05
Amplitude of vibration of the spindle (μ)					
Drill of the invention	3.2	2.59	2.61	2.78	2.8
Prior art drill	3.7	5.41	2.87	4.21	5.98

Thus, in the twist drill in accordance with the above embodiment, the cutting resistance during the drilling operation can be reduced sufficiently. In addition, since the distance W between the line L and the bottom 11a of the flute 11 is set to be no greater than 65 % of the drill diameter D, the thickness of the body 10 between the second wall of the flute disposed adjacent to the heel and the peripheral land will be adequate, so that the drill is less susceptible to chipping damage or cracking. In addition, the torsional rigidity of the drill can be maintained at a high level.

Moreover, since the chip is extended along the wall of the spiral flute 11 and curls at the bottom 11a, the radius of curvature of the chip becomes generally identical to the radius of curvature R of the bottom of the spiral flute 11 defined at the cross-section. If the radius of curvature R of the bottom exceeds 0.2D, the chip protrudes radially outward from the flute 11 and is brought into frictional engagement with the wall of the drilled bore. As a result, the surface finish of the bore deteriorates and the chip removal efficiency is lessened. On the other hand, if the radius of curvature R is below 0.15D, the radius of curvature of the chip is unduly reduced. For this reason, the bending resistance exerted on the chip increases and is added to the cutting resistance to increase the cutting torque and thrust load.

Additionally, since the surface of the drill body is coated with TiC, TiCN or the like, the wear resistance is sufficiently enhanced to enable heavy-duty operations to be performed.

Furthermore, since in the above drill, the cutting resistance is considerably reduced, the vibration of spindle of the machine tool can be rendered small enough for the working precision to be highly enhanced. Moreover, since the flute is so formed that the second wall is recessed deeply in the direction of rotation of the body, the cross-sectional area is large, and hence chips can be smoothly removed.

In this embodiment, too, the first cutting lip 12 and the second cutting lip 13a may be formed so that when viewed from the forward end of the body 10, they appear linear and the intersection 14 is arcuately shaped at a prescribed radius of curvature r. Furthermore, the various limitations such as described in the third embodiment could also be added to this embodiment.

Figs. 22 and 23 depict a further modified twist drill in accordance with a fifth embodiment which differs from the drill of the previous embodiments in that the drill body 10 is made of cemented carbide, and that the body 10 has a web thickness T of 20 to 35 % of the drill diameter D and a flute-width ratio A/B of 0.5 to 0.9. Additionally, the entire surface of the drill body 10 is not coated with a hard coating.

In the twist drill as described above, too, the distance W between the line L and the bottom 11a of the flute 11 is set to be no less than 45 % of the drill diameter, and hence the resistance exerted on the chip in the direction opposite to the direction in which the chip is extended is divided into forces to cause the chip to bend or buckle. Accordingly, the chip is prevented from being strongly compressed, so that the thrust load and cutting torque can be greatly reduced.

These points were verified by way of the following drilling tests:

Drilling Test 5

There were prepared several twist drills having various ratios of the distance W to the drill diameter. The test drill had a diameter of 12mm and a point angle of 140° , and the radial rake angle of the cutting lip was -15° . The Drilling Test were conducted under the the following conditions:

Cutting speed: 65m/min.

Workpiece: Steel (JIS SCM440; Hardness: H_B100 and 300 to 350)

Feed rate: 0.15, 0.25, 0.35, 0.45 and 0.55mm/revolution

The thicknesses of chips produced during the drilling operation using the drills were measured at a point designated by S in Fig. 5. Table 5 shows the results for the drilling of a workpiece with a hardness of 300 to 350 while Table 6 shows those for the drilling of a workpiece with a hardness of 100.

As seen from Tables 5 and 6, when the distance W from the line L to the bottom 11a of the flute 11 is no less than 45 % of the drill diameter, the thicknesses of the chips are reduced substantially. This means that the resistance exerted on the chip can be substantially reduced by setting the distance W to be no less than 45% of the drill diameter.

Table 5

Workpiece of Hardness 300-350					
Feed rate (mm/rev.)	Thickness of chips (mm)				
	Drills of the invention Ratio (%)			Prior art drills Ratio (%)	
	53	50	45	43	41
0.15	0.131	0.134	0.142	0.195	0.203
0.25	0.218	0.223	0.237	0.322	0.338
0.35	0.275	0.283	0.301	0.412	0.425
0.45	0.353	0.364	0.383	0.527	0.545
0.55	0.431	0.446	0.471	0.642	0.667

Table 6

Workpiece of Hardness 100					
Feed rate (mm/rev.)	Thickness of chips (mm)				
	Drills of the invention Ratio (%)			Prior art drills Ratio (%)	
	53	50	45	43	41
0.15	0.200	0.206	0.217	0.297	0.311
0.25	0.332	0.345	0.362	0.494	0.515
0.35	0.420	0.433	0.459	0.625	0.648
0.45	0.539	0.557	0.587	0.803	0.834
0.55	0.657	0.682	0.718	0.982	1.020

Drilling Test 6

The drill with the distance W of 53% of the drill diameter and the drill with the distance W of 41% of the drill diameter, which were prepared in Drilling Test 5, were again used, and the drilling tests were conducted under the same conditions as those in Drilling Test 5. In this test, the thrust load, cutting torque, cutting power and maximum amplitude of vibration of the spindle during the drilling operation were measured. The results are shown in Tables 7 and 8.

It is seen from Tables 7 and 8 that in the twist drill of the invention, even though the radial rake angle is negative, the thrust load, cutting torque and cutting power are all reduced markedly in comparison with the prior art drill. Therefore, in the drill of this invention, since the chips can be curled without being compressed strongly, the resistance exerted on the chips can be reduced, so that the cutting resistance such as thrust load can be decreased substantially.

Table 7

Workpiece of Hardness 300-350					
	Feed rate (mm/rev.)				
	0.15	0.25	0.35	0.45	0.55
Thrust load (Kg)					
Drill of the invention	236	296	372	396	460
Prior art drill	288	332	400	480	580
Cutting torque (Kg•mm)					
Drill of the invention	96	128	168	204	240
Prior art drill	100	136	172	224	273
Cutting power (Kw)					
Drill of the invention	1.61	2.03	2.48	2.93	3.38
Prior art drill	1.76	2.18	2.63	3.15	3.75
Amplitude of vibration of the spindle (μ)					
Drill of the invention	1.98	2.22	2.16	2.88	2.52
Prior art drill	3.66	3.30	2.58	3.24	3.48

Table 8

Workpiece of Hardness 100					
	Feed rate (mm/rev.)				
	0.15	0.25	0.35	0.45	0.55
Thrust load (Kg)					
Drill of the invention	172	216	252	312	368
Prior art drill	230	280	350	460	550
Cutting torque (Kg•mm)					
Drill of the invention	84	112	148	188	220
Prior art drill	100	130	180	230	260
Cutting power (Kw)					
Drill of the invention	1.35	1.73	2.06	2.40	2.78
Prior art drill	1.63	2.00	2.53	3.08	3.45
Amplitude of vibration of the spindle (μ)					
Drill of the invention	2.64	2.82	2.76	2.52	2.70
Prior art drill	2.9	3.0	3.6	4.3	3.9

Thus, in the twist drill in accordance with this embodiment, too, the cutting resistance during the drilling operation can be reduced. In addition, since the distance between the line L and the bottom 11a of the flute 11 is set to be no greater than 65 % of the drill diameter D, the thickness of the body 10 between the second wall of the flute disposed adjacent to the heel and the peripheral land will be thick enough, so that the drill is less susceptible to chipping damage or cracking. In addition, the torsional rigidity of the drill can be maintained at a high level.

Furthermore, since in the above drill, the cutting resistance is considerably reduced, the vibration of spindle of the machine tool can be lessened, and the working precision is thereby highly enhanced. Moreover, since the flute is so formed that the second wall is recessed deeply in the direction of rotation of

the body, the cross-sectional area is large, and hence chips can be easily removed.

In the above embodiment, the cutting lip 12 is formed so that it is located forwardly from the radial line N with respect to the direction of rotation of the body 10. It, however, may be disposed rearwardly from the radial line N in the direction of rotation of the body 10 as shown in Fig. 24.

- Furthermore, the body 10 may be made of cermet. Generally, cermet is extremely hard and is superior in wear resistance, but it is more brittle and has less torsional rigidity in comparison to cemented carbide (the traverse rupture strength of cermet is 130Kg/mm² while that of cemented carbide is 200Kg/mm²), and hence it has been hitherto supposed to be inappropriate for use in drills. More specifically, if a drill is made of cermet, fatigue breakage readily develops when the drill is subjected repeatedly to cutting torque and thrust load, so that the drill is broken in a very short time. However, in the drill of this embodiment, the cutting torque and thrust load can be reduced while enhancing the torsional rigidity, and therefore the drill can be formed of cermet. These points were verified by way of the following drilling tests.

Drilling Test 7

15

Drills having the distance W of 53% of the drill diameter and the distance W of 41% of the drill diameter were made of cermet containing TiN, TiCN, and the like. The drilling tests were conducted under the following conditions. The drill diameter was 12.5mm, and the point angle was 140°.

20 Workpiece: JIS SCM440 (Hardness: H_{RC}30)

Cutting speed: 50m/min.

Feed rate: 0.3mm/revolution

In this test, the thrust load, cutting torque, cutting power and service life were observed. The results are shown in Tables 9 and 10, in which the term "cutting length" designates the summation of the thicknesses of all of the workpieces drilled by the test drill.

25

Table 9

30

	Drill of the invention	Prior art drill
Thrust load (Kg)	312	430
Cutting torque (Kg·mm)	166	180
Cutting power (Kw)	2.63	2.70
Service life (cutting length)	Still unbroken at about 20mm	Broken at about 7m

35

40

45

50

55

Table 10

5	Feed rate (mm/rev.)	0.15	0.20	0.25	0.30	0.35
	Thrust load (Kg)					
10	Drill of the invention	232	248	300	312	348
	Prior art drill	290	330	385	430	480
15	Cutting torque (Kg•mm)					
	Drill of the invention	108	126	150	166	188
20	Prior art drill	115	140	155	180	220
	Cutting power (Kw)					
	Drill of the invention	1.97	2.18	2.44	2.63	2.93
	Prior art drill	1.98	2.26	2.48	2.70	3.08
	Amplitude of vibration of the spindle (μ)					
	Drill of the invention	3.0	2.2	2.0	2.1	2.22
	Prior art drill	3.18	3.0	2.46	2.28	3.1

As seen from Table 9 that the twist drill of the invention could drill 20m without any problems while the prior art drill was broken after it drilled only 7m. This is because in the drill of the invention, even though the radial rake angle is negative, the thrust load, cutting torque, and cutting power are all reduced markedly in comparison with the prior art drill as will be seen from Table 10. Thus, the drill can be made of cermet, and this material has the advantage of superior wear resistance.

In the above embodiment, both of the first cutting lip 12 and the second cutting lip 13a may be formed to be linear and to intersect each other with an arcuately shaped corner formed therebetween. Figs. 25 and 26 illustrate such an embodiment, in which the radius of curvature r of the arcuate corner is set to range from 0.05D to 0.15D as is the case with the previous embodiments.

Moreover, the various features described in the third embodiment could as well be added to the drill of this embodiment as shown in Figs. 27 to 33. In this embodiment, however, the angle α , defined as the angle between the second cutting lip 13a and the line N as viewed from the forward end of the body 10, should be set to range from 20° to 40°. The optimal ranges for the other parameters are identical to those in the third embodiment. Furthermore, the second cutting lip 13a and the first cutting lip 12 may be honed as at 21 in Fig. 32. When an imaginary line is drawn along an inner ridgeline 21a of the honing 21 of one cutting lip, the intervening distance C between the imaginary line and an inner ridge line 21a of the honing 21 of the other cutting lip is within the range of 0 to 0.3mm, and a chisel edge 20 is formed between adjacent ends 21b of the two honings 21. If the honings 21 intersect at the axis, the engagement upon the drilling is caused at two points, so that the drill becomes susceptible to vibration and hence to chipping damage. For this reason, the adjacent ends of the honings 21b have to be spaced apart. The spacing C is set to be no greater than 0.3mm in order to reduce the thrust load by reducing the chisel width G.

The adjacent ends 21b of the honings 21 may be disposed so as to almost contact each other, but the spacing therebetween must be maintained. Fig. 33 depicts a modification of the honing, in which the adjacent ends of the two honings are made to contact each other, but their outer ridgelines 21c are arcuately shaped in the vicinity of the axis O and intersect each other at the axis O. With this construction, although small, a chisel is formed at the axis O, so that the engagement with the workpiece can be conducted at one point. The configuration of the honing may be further modified as illustrated in Fig. 34, in which the width decreases as it approaches the axis. With this configuration, the chipping at the outer side of the second cutting lip 13a, where the cutting speed is great, can be prevented. Since the cutting lip 12 is straight, the variation in the configuration of the honing 21 is small. Furthermore, in the drill of cemented carbide or cermet, too, the body 10 may be coated with a hard coating of TiC, TiN, TiCN, Al_2O_3 or the like to enhance the wear resistance. This kind of coating also reduces friction between the drill and the chips, and further reduces cutting torque and thrust load.

Figs. 35 to 37 depict a further modified twist drill in accordance with a seventh embodiment. As is the case with the drill of the fifth embodiment, the drill body 10 is made of cemented carbide or cermet, and the web thickness T is set to be from 20 to 35 % of the drill diameter D. Those portions of flanks disposed rearwardly with respect to the direction of rotation of the body 10 are ground off, as at 13, to provide X-type

ground surfaces 15, so that second cutting lips 13a, each extending away from the axis O of rotation to the radially innermost end of a respective first cutting lip 12, are formed at the web portion. The distance W between the line L and the bottom 11a of the flute 11 is designed to range from 45% to 65% of the drill diameter D, so that the second wall of the spiral flute 11 is recessed deeply in the direction of rotation of the body 10. Accordingly, in this drill, too, inasmuch as the distance between the line L and the bottom 11a of the flute 11 is set to be no less than 45% of the drill diameter, the resistance exerted on the chip in the direction opposite to the direction in which the chip grows is divided into forces to cause the chip to bend or buckle. Accordingly, the chip is prevented from being strongly compressed, so that the thrust load and cutting torque can be greatly reduced. Furthermore, in this embodiment, the flute-width ratio A_1/B_1 at a cross-section taken perpendicular to the axis O of the body 10 is set to range from 0.9 to 1.2. Additionally, that portion of the wall of the flute 11 which contacts an imaginary cylinder inscribing the web portion of the body 10 is concavely arcuately shaped at such a radius of curvature R as to satisfy the relationship: $0.15D \leq R \leq 0.2D$. The length of this arcuately shaped portion as viewed axially of the body 10 is defined by an arc with a central angle ω of 26° to 56° , more preferably of 31° to 51° , and most preferably of 36° to 46° . Within this range of the central angle ω , not only a chip produced by the cutting lip 12 is curled positively, but the friction caused between the chip and the wall of the flute 11 can as well be reduced, so that the curling of the chip can be smoothly effected.

As was the case with the first embodiment, the advantages of this embodiment were verified by way of the following examples.

Drilling Test 8

There were prepared several twist drills having various ratios of the distance W to the drill diameter. The test drill had a diameter of 12mm and a point angle of 140° , and the radial rake angle of the cutting lip was -15° . The drilling tests were conducted under the the following conditions:

Cutting speed: 65m/min.

Workpiece: Steel (JIS SCM440; Hardness: H_B100 and 300 to 350)

Feed rate: 0.15, 0.25, 0.35, 0.45 and 0.55mm/revolution

The thicknesses of chips produced during the drilling operation using the drills were measured at a point designated by S in Fig. 5. Table 11 shows the results for the drilling of a workpiece with a hardness of 300 to 350 while Table 12 shows those for the drilling of a workpiece with a hardness of 100.

Table 11

Workpiece of Hardness 300-350					
Feed rate (mm/rev.)	Thickness of chips (mm)				
	Drills of the invention Ratio (%)			Prior art drills Ratio (%)	
	53	50	45	43	41
0.15	0.111	0.114	0.122	0.165	0.173
0.25	0.188	0.193	0.207	0.302	0.318
0.35	0.255	0.263	0.281	0.382	0.395
0.45	0.325	0.334	0.353	0.502	0.525
0.55	0.411	0.426	0.457	0.612	0.637

Table 12

Workpiece of Hardness 100					
Feed rate (mm/rev.)	Thickness of chips (mm)				
	Drills of the invention Ratio (%)			Prior art drills Ratio (%)	
	53	50	45	43	41
0.15	0.180	0.186	0.197	0.297	0.281
0.25	0.302	0.315	0.332	0.474	0.495
0.35	0.400	0.413	0.439	0.595	0.618
0.45	0.509	0.527	0.557	0.783	0.814
0.55	0.637	0.662	0.698	0.952	1.000

As will be seen from Tables 11 and 12, when the distance W from the line L to the bottom 11a of the flute 11 is no less than 45% of the drill diameter, the thicknesses of the chips are reduced substantially. This means that the resistance exerted on the chip can be substantially reduced by setting the distance W to be no less than 45 % of the drill diameter.

Drilling Test 9

Drills having the distance W of 53% of the drill diameter and the distance W of 41% of the drill diameter, which were prepared for the Drilling Test 8, were again used, and the drilling tests were conducted under the same conditions as those in Drilling Test 8. In the test, the thrust load, cutting torque, cutting power and maximum amplitude of vibration of the spindle during the drilling operation were measured. The results are shown in Tables 13 and 14, in which Table 13 shows the results for the drilling of the workpiece with a hardness of 300 to 350 while Table 14 shows those for the drilling of the workpiece with a hardness of 100.

Table 13

Workpiece of Hardness 300-350					
	Feed rate (mm/rev.)				
	0.15	0.25	0.35	0.45	0.55
Thrust load (Kg)					
Drill of the invention	234	297	370	393	463
Prior art drill	288	332	400	480	580
Cutting torque (Kg·mm)					
Drill of the invention	93	122	165	201	246
Prior art drill	100	136	172	224	273
Cutting power (Kw)					
Drill of the invention	1.62	2.05	2.49	2.90	3.35
Prior art drill	1.76	2.18	2.63	3.15	3.75
Amplitude of vibration of the spindle (μ)					
Drill of the invention	1.95	2.33	2.09	2.85	2.55
Prior art drill	3.66	3.30	2.58	3.24	3.48

Table 14

Workpiece of Hardness 100					
	Feed rate (mm/rev.)				
	0.15	0.25	0.35	0.45	0.55
Thrust load (Kg)					
Drill of the invention	169	212	253	315	371
Prior art drill	230	280	350	460	550
Cutting torque (Kg·mm)					
Drill of the invention	82	113	151	182	223
Prior art drill	100	130	180	230	260
Cutting power (Kw)					
Drill of the invention	1.30	1.78	2.11	2.43	2.75
Prior art drill	1.63	2.00	2.53	3.08	3.45
Amplitude of vibration of the spindle (μ)					
Drill of the invention	2.61	2.78	2.72	2.50	2.68
Prior art drill	2.9	3.0	3.6	4.3	3.9

It is seen from Tables 13 and 14 that in the twist drill of the invention, even though the radial rake angle is negative, the thrust load, cutting torque, cutting power and amplitude of the vibration of the spindle are all reduced markedly in comparison with the prior art drill. Therefore, in the drill of this invention, since the chips can be curled without being compressed strongly, the resistance exerted on the chips is reduced, so that the cutting resistance such as thrust load can be decreased substantially.

Thus, in the twist drill in accordance with this embodiment, too, the cutting resistance caused during the drilling operation can be reduced sufficiently. In addition, since the distance between the line L and the bottom 11a of the flute 11 is set to be no greater than 65 % of the drill diameter D, the thickness of the body 10 between the second wall of the flute disposed adjacent to the heel 11b and the peripheral land 10a can be sufficiently ensured, so that the drill is less susceptible to chipping damage or cracking. In addition, the torsional rigidity of the drill can be maintained at a high level.

Furthermore, since in the above drill, the cutting resistance is considerably reduced, the vibration of the spindle of the machine tool can be lessened, and the working precision is highly enhanced. Moreover, since the flute is so formed that that wall portion facing in the direction of rotation of the body is recessed deeply in the direction of rotation of the body, the cross-sectional area is large, and hence chips can be smoothly removed.

In the above embodiment, the cutting lip 12 is formed so that it is located forwardly from the radial line N with respect to the direction of rotation of the body 10. It, however, may be located rearwardly from the radial line N in the direction of rotation of the body 10 as shown in Fig. 38.

Furthermore, the body 10 may be made of cermet. The following is a drilling test similar to Drilling Test 7.

Drilling Test 10

The drill with the distance W of 53% of the drill diameter and the drill with the distance W of 41% of the drill diameter were made of cermet containing TiN, TiCN and the like, and the drilling tests were conducted under the following conditions. The drill diameter was 12.5mm, and the point angle was 140°.

Workpiece: JIS SCM440 (Hardness: H_{RC}30)

Cutting speed: 50m/min.

Feed rate: 0.3mm/revolution

In this test, the thrust load, cutting torque, cutting power and service life were observed, respectively. The results are shown in Tables 15 and 16.

As can be seen from Table 15, the twist drill of the invention could drill 20m without any problems while the prior art drill was broken after it drilled only 7m. This is because in the drill of the invention,, even

though the radial rake angle is negative, the thrust load, cutting torque, cutting power and amplitude of the vibration of the spindle are all reduced markedly in comparison with the prior art drill as seen in Table 15. Thus, the drill can be made of cermet, and makes the best use of the property relating to the superior wear resistance.

5

Table 15

	Drill of the invention	Prior art drill
Thrust load (Kg)	310	430
Cutting torque (Kg·mm)	162	180
Cutting power (Kw)	2.58	2.70
Service life (cutting length)	Still unbroken at about 20m	Broken at about 7m

15

Table 16

	Feed rate (mm/rev.)				
	0.15	0.20	0.25	0.30	0.35
Thrust load (Kg)					
Drill of the invention	230	245	303	314	346
Prior art drill	290	330	385	430	480
Cutting torque (Kg·mm)					
Drill of the invention	105	123	152	168	189
Prior art drill	115	140	155	180	220
Cutting power (Kw)					
Drill of the invention	1.95	2.16	2.46	2.61	2.61
Prior art drill	1.98	2.26	2.48	2.70	3.08
Amplitude of vibration of the spindle (μ)					
Drill of the invention	2.90	2.30	2.12	2.20	2.10
Prior art drill	3.18	3.00	2.46	2.28	3.10

20

25

30

35

40

The modifications described in the previous embodiments are also applicable to this embodiment although their explanations will be omitted for the sake of brevity.

Obviously, many modifications and variations are possible in the light of the above teachings. It is therefore to be understood that within the scope of the appended claims, the invention may be practiced otherwise than as specifically described.

45

Claims

1. A twist drill comprising a cylindrical body (10) having an axis (O) of rotation therethrough, having a forward end which contacts a workpiece and having a web thickness (T) of 0.2D to 0.35D, wherein D is a diameter of said body (10);

50

said body (10) having a spiral flute (11) formed in an outer peripheral surface thereof so as to extend spirally along a length thereof to said forward end;

55

a land (10a) disposed adjacent to said flute (11), said flute (11) having a first wall facing in the direction of rotation of said body (10) and a second wall extending from an inner end of said first wall to the outer periphery of said body (10), said first wall terminating at said forward end in a first cutting lip (12) having a radially outermost end (Q) disposed on the outer periphery of said body (10), said second wall being concavely shaped when viewed from said forward end;

the wall of said flute (11) having an arcuately shaped portion which contacts an imaginary cylinder

though the radial rake angle is negative, the thrust load, cutting torque, cutting power and amplitude of the vibration of the spindle are all reduced markedly in comparison with the prior art drill as seen in Table 15. Thus, the drill can be made of cermet, and makes the best use of the property relating to the superior wear resistance.

5

Table 15

	Drill of the invention	Prior art drill
Thrust load (Kg)	310	430
Cutting torque (Kg·mm)	162	180
Cutting power (Kw)	2.58	2.70
Service life (cutting length)	Still unbroken at about 20m	Broken at about 7m

15

Table 16

	Feed rate (mm/rev.)				
	0.15	0.20	0.25	0.30	0.35
Thrust load (Kg)					
Drill of the invention	230	245	303	314	346
Prior art drill	290	330	385	430	480
Cutting torque (Kg·mm)					
Drill of the invention	105	123	152	168	189
Prior art drill	115	140	155	180	220
Cutting power (Kw)					
Drill of the invention	1.95	2.16	2.46	2.61	2.61
Prior art drill	1.98	2.26	2.48	2.70	3.08
Amplitude of vibration of the spindle (μ)					
Drill of the invention	2.90	2.30	2.12	2.20	2.10
Prior art drill	3.18	3.00	2.46	2.28	3.10

20

25

30

35

40

The modifications described in the previous embodiments are also applicable to this embodiment although their explanations will be omitted for the sake of brevity.

Obviously, many modifications and variations are possible in the light of the above teachings. It is therefore to be understood that within the scope of the appended claims, the invention may be practiced otherwise than as specifically described.

45

Claims

1. A twist drill comprising a cylindrical body (10) having an axis (O) of rotation therethrough, having a forward end which contacts a workpiece and having a web thickness (T) of 0.2D to 0.35D, wherein D is a diameter of said body (10);

50

said body (10) having a spiral flute (11) formed in an outer peripheral surface thereof so as to extend spirally along a length thereof to said forward end;

a land (10a) disposed adjacent to said flute (11), said flute (11) having a first wall facing in the direction of rotation of said body (10) and a second wall extending from an inner end of said first wall to the outer periphery of said body (10), said first wall terminating at said forward end in a first cutting lip (12) having a radially outermost end (Q) disposed on the outer periphery of said body (10), said second wall being concavely shaped when viewed from said forward end;

55

the wall of said flute (11) having an arcuately shaped portion which contacts an imaginary cylinder



inscribing a web portion of the drill;
characterized in that:

- (a) assuming a first line (L) extending from said radially outermost end (Q) perpendicular to a second line (N) which connects said radially outermost end (Q) and said axis (O) of said body (10), said second wall is formed so that the maximum distance (W) between said first line (L) and said second wall is set to range between 0.45D and 0.65D;
 - (b) said arcuately shaped portion has a radius of curvature (R) of between 0.15D to 0.2D;
 - (c) the drill has a ground surface (15) creating a second cutting lip (13a) extending away from said axis (O) of rotation of said body (10) with a rake surface (16) along said second cutting lip (13a); a valley line (17) between said ground surface (15) and said rake surface (16) along said second cutting lip (13a); and in which an angle (ϕ) defined by said axis (O) of rotation of said body (10) and said valley line (17) is set between 30° and 40°; and
 - (d) that the axial distance (I) between the radially outermost end (Q) of said first cutting lip (12) and a forward end (H) of a heel (11b) is set between 0.3D and 1.0D.
2. A twist drill as in Claim 1 and in which the cylindrical body (10) is made of a material selected from the group consisting of high speed steel and sintered metal high speed steel, at least the forward end of said body being coated with a hard coating which is harder than said body.
 3. A twist drill as in Claim 1 or Claim 2 and in which each of said first (12) and second (13a) cutting lips are formed to be linear as viewed from said forward end.
 4. A twist drill according to claim 3, in which, when a point P is defined by the intersection of a line tangential to said first cutting lip (12) with a line tangential to said second cutting lip (13a), the ratio of a distance (L_1) between said axis (O) of said body (10) and said point P to a distance (L_2) between said outermost end (Q) of said first cutting lip (12) and said point P is set to range between 0.4:1 and 0.7:1.
 5. A twist drill according to claim 4, in which said forward end includes a first planar relief surface (18) provided with a relief angle (β_1) of 7° to 15° and extending along said first cutting lip (12), and a second planar relief surface (19) provided with a relief angle (β_2) greater than that of said first relief surface (18) so as to range from 15° to 25° and extending along said first relief surface (18), the intersection of said first relief surface (18) with said second relief surface (19) being parallel to said first cutting lip (12) and intersecting said axis (O) of said body (10).
 6. A twist drill according to claim 5, in which the axial rake angle (θ) for said second cutting lip (13a) is set to be between 0° and -5°.
 7. A twist drill according to claim 6, in which the angle (λ) defined between said ground surface (15) formed by the grinding and said rake surface (16) along said second cutting lip (13a) is 95° to 115°.
 8. A twist drill according to claim 7, further comprising an oil passageway (22) formed in said body (10) and extending spirally along said flute (11).
 9. A twist drill according to claim 8, in which the intersection of the walls of said flute (11) and the land (10a) of said body (10) is honed to provide a honed face (21).
 10. A twist drill according to claim 9, in which said honed face (21) is a chamfered face.
 11. A twist drill according to claim 10, in which said honed face (21) is a rounded face.
 12. A twist drill according to claim 1 or 2, in which a second cutting lip (13a) formed by web thinning is inclined at an angle of 20° to 40° with respect to the line extending from the axis (O) of said body (10) to said outermost end (Q) of said first cutting lip (12).
 13. A twist drill according to claim 1, in which a second cutting lip (13a) formed by web thinning is inclined at an angle (α) of 15° to 35° with respect to the line (N) extending from the axis (O) of said body (10) to said outermost end (Q) of said first cutting lip (12).



14. A twist drill according to claim 12, in which a pair of said first cutting lips (12) and a pair of said second cutting lips (13a) are provided and honed, and in which, assuming a first imaginary line extending from an inner ridgeline of one of said honed second cutting lips (13a) and a second imaginary line extending from an inner ridgeline of the other honed second cutting lip (13a), an intervening distance (C) between said first and second imaginary lines is set to range between 0.0 to 0.3 mm, said honed second cutting lips defining a chisel edge (20) therebetween.
15. A twist drill according to claim 13, in which a pair of said first cutting lips (12) and a pair of said second cutting lips (13a) are provided, and in which, assuming a first imaginary line extending from an inner ridgeline of one of said second cutting lips (13a) and a second imaginary line extending from an inner ridgeline of the other second cutting lip (13a), an intervening distance (C) between said first and second imaginary lines is set to range between 0.0 to 0.3 mm, said second cutting lips defining a chisel edge (20) therebetween.
16. A twist drill according to claim 14 or claim 15, in which said chisel edge (20) has a width (G) of between 0.0 and 0.4 mm.
17. A twist drill according to claim 3, in which that corner at which said first cutting lip (12) and said second cutting lip (13a) meet forms a generally arcuately shaped edge when viewed from said forward end.
18. A twist drill according to claim 17, in which the radius of curvature (r) of said arcuately shaped edge is between 0.05D and 0.15D.
19. A twist drill according to claim 1, in which at least said forward end of said body (10) is coated with a hard coating.
20. A twist drill according to claim 2 or claim 19, in which said hard coating is composed of at least one material selected from the group consisting of TiN, TiC, TiCN and Al_2O_3 .
21. A twist drill according to claim 1, in which said first and second cutting lips meet at a corner forming a sharp edge.
22. A twist drill according to claim 1 in which said body (10) has a flute-width ratio (A/B) of 0.5 to 0.9.
23. A twist drill according to claim 1 in which said body (10) has a flute width ratio /A/B) of 0.4 to 0.9.
24. A twist drill according to claim 1 in which the ratio of arc length (A1) of said flute (11) to arc length (B1) of said land (10a) at a cross section taken perpendicular to said axis (O) of said body (10) is 0.9 to 1.2.

40 Patentansprüche

1. Spiralbohrer mit einem zylindrischen Körper (10) mit einer durch diesen verlaufenden Rotationsachse (O), der ein vorderes Ende aufweist, das ein Werkstück berührt und der eine Kerndicke (T) zwischen 0,2D und 0,35D aufweist, wobei D ein Durchmesser des Körpers (10) ist;
- wobei der Körper (10) eine Spiralspannut (11) aufweist, die in einer äußeren Umfangsfläche desselben derart ausgebildet ist, daß diese spiralförmig entlang eines Abschnitts desselben zu dem vorderen Ende verläuft;
- einer Freifläche (10a), die neben der Spannut (11) angeordnet ist, wobei die Spannut (11) eine erste Wand besitzt, die in Rotationsrichtung des Körpers (10) weist, sowie eine zweite Wand, die sich von einem inneren Ende der ersten Wand zu dem Außenumfang des Körpers (10) erstreckt, wobei die erste Wand an dem vorderen Ende in einer ersten Schneide (12) endet, die ein radial äußerstes Ende (Q) aufweist, das an dem Außenumfang des Körpers (10) angeordnet ist, wobei die zweite Wand gesehen aus der Richtung des vorderen Endes konkav geformt ist;
- wobei die Wand der Spannut (11) einen bogenförmig geformten Abschnitt aufweist, der einen imaginären Zylinder berührt, der einen Kernabschnitt des Bohrers einschließt;
- dadurch gekennzeichnet, daß:
- (a) die zweite Wand derart ausgebildet ist, daß der maximale Abstand (W) zwischen einer ersten Linie (L) und der zweiten Wand zwischen 0,45D und 0,65D beträgt, wobei die erste Linie (L) von



- dem radial äußersten Ende (Q) senkrecht zu einer zweiten Linie (N) verläuft, welche das radial äußerste Ende (Q) und die Achse (O) des Körpers (10) verbindet;
- (b) der gekrümmt ausgebildete Abschnitt einen Krümmungsradius (R) zwischen $0,15D$ und $0,2D$ aufweist;
- 5 (c) der Bohrer eine geschliffene Fläche (15) aufweist, die eine zweite Schneide (13a) erzeugt, die sich weg von der Rotationsachse (O) des Körpers (10) erstreckt, mit einer Spanfläche (16) entlang der zweiten Schneide (13a); eine Tallinie (17) zwischen der geschliffenen Fläche (15) und der Spanfläche (16) entlang der zweiten Schneide (13a); und wobei ein Winkel (ϕ), der durch die Rotationsachse (O) des Körpers (10) und die Tallinie (17) festgelegt ist, zwischen 30° und 40° liegt;
- 10 und daß
- (d) der axiale Abstand (L) zwischen dem radial äußersten Ende (Q) der ersten Schneide (12) und einem vorderen Ende (H) eines Schneidkantenrückens (11b) zwischen $0,3D$ und $1,0D$ liegt.
2. Spiralbohrer nach Anspruch 1,
- 15 wobei der zylindrische Körper (10) aus einem Material hergestellt, das aus der Gruppe ausgewählt ist, die aus Hochgeschwindigkeitsstahl und gesinterem Metall-Hochgeschwindigkeitsstahl besteht, wobei zumindest das vordere Ende des Körpers mit einer Hartbeschichtung beschichtet ist, die härter als der Körper ist.
- 20 3. Spiralbohrer nach Anspruch 1 oder 2,
- wobei sowohl die erste (12) wie auch die zweite (13a) Schneide geradlinig ausgebildet sind, gesehen von dem vorderen Ende aus.
4. Spiralbohrer nach Anspruch 3, wobei unter der Annahme, daß ein Punkt P durch den
- 25 Schnittpunkt einer Tangente an die erste Schneide (12) mit einer Tangente an die zweite Schneide (13a) definiert ist, das Verhältnis eines Abstandes (L_1) zwischen der Rotationsachse (O) des Körpers (10) und dem Punkt P zu einem Abstand (L_2) zwischen dem äußersten Ende (Q) der ersten Schneide (12) und dem Punkt P zwischen $0,4:1$ und $0,7:1$ gewählt ist.
- 30 5. Spiralbohrer nach Anspruch 4, wobei das vordere Ende eine erste planare Freifläche (18) aufweist, die mit einem Freiwinkel (β_1) zwischen 7° und 15° versehen ist und die sich entlang der ersten Schneide (12) erstreckt sowie eine zweite planare Freifläche (19), mit einem Freiwinkel (β_2) versehen ist, der größer ist als der der ersten Freifläche (18) und der zwischen 15° und 25° liegt und die sich entlang der ersten Freifläche (18) erstrecken, wobei die Schnittlinie zwischen der ersten
- 35 Freifläche (18) und der zweiten Freifläche (19) parallel zu der ersten Schneide (12) verläuft und die Rotationsachse (O) des Körpers (10) schneidet.
6. Spiralbohrer nach Anspruch 5,
- wobei der axiale Spanwinkel (θ) für die zweite Schneide (13a) zwischen 0° und -5° liegt.
- 40 7. Spiralbohrer nach Anspruch 6,
- wobei der Winkel (λ), der zwischen der geschliffenen Fläche (15), die durch Schleifen ausgebildet worden ist, und der Spanfläche (16) entlang der zweiten Schneide (13a) zwischen 95° und 115° beträgt.
- 45 8. Spiralbohrer nach Anspruch 7,
- ferner umfassend einen Ölkanal (22), der in dem Körper (10) ausgebildet ist und sich spiralförmig entlang der Spannute (11) erstreckt.
- 50 9. Spiralbohrer nach Anspruch 8, wobei die Schnittlinie der Wände der Spannute (11) und der Freifläche (10a) des Körpers (10) gehont ist, um eine gehonte Fläche (21) zu schaffen.
10. Spiralbohrer nach Anspruch 9, wobei die gehonte Fläche (21) eine abgeschrägte Fläche ist.
- 55 11. Spiralbohrer nach Anspruch 10,
- wobei die gehonte Fläche (21) eine abgerundete Fläche ist.



12. Spiralbohrer nach Anspruch 1 oder 2,
wobei eine zweite Schneide (13a), die durch eine Kernverdünnung ausgebildet ist, unter einem Winkel 20° und 40° , bezogen auf die Linie geneigt ist, die sich von der Achse (O) des Körpers (10) zu dem äußersten Ende (Q) der ersten Schneide (12) erstreckt.
- 5
13. Spiralbohrer nach Anspruch 1,
wobei eine zweite Schneide (13a), die durch eine Kernverdünnung ausgebildet ist, unter einem Winkel (α) zwischen 15° und 35° bezogen auf die Linie (N) geneigt ist, die sich von der Achse (O) des Körpers (10) zu dem äußersten Ende (Q) der ersten Schneide (12) erstreckt.
- 10
14. Spiralbohrer nach Anspruch 12, wobei zwei erste Schneiden (12) und zwei zweite Schneiden (13a) vorgesehen sind und gehont sind, und wobei unter der Annahme, daß eine erste imaginäre Linie sich von einer inneren Gratlinie einer der gehonten zweiten Schneiden (13a) erstreckt und eine zweite imaginäre Linie sich von einer inneren Gratlinie der anderen gehonten zweiten Schneide (13a) erstreckt, ein Abstand (C) zwischen der ersten und der zweiten imaginären Linie zwischen 0,0 und 0,3 mm beträgt, wobei die gehonten zweiten Schneiden zwischen sich eine Meißelkante (20) festlegen.
- 15
15. Spiralbohrer nach Anspruch 13,
wobei zwei erste Schneiden (12) und zwei zweite Schneiden (13a) vorgesehen sind, und wobei unter der Annahme, daß eine erste imaginäre Linie sich von einer inneren Gratlinie einer der zweiten Schneiden (13a) erstreckt, und eine zweite imaginäre Linie sich von einer inneren Gratlinie der anderen zweiten Schneide (13a) erstreckt, ein Abstand (C) zwischen der ersten und der zweiten imaginären Linie zwischen 0,0 und 0,3 mm beträgt, wobei die zweiten Schneiden zwischen sich eine Meißelkante (20) festlegen.
- 20
- 25
16. Spiralbohrer nach Anspruch 14 oder 15,
wobei die Meißelkante (20) eine Breite (G) zwischen 0,0 und 0,4 mm aufweist.
- 30
17. Spiralbohrer nach Anspruch 3,
wobei die Ecke, an der sich die erste Schneide (12) und die zweite Schneide (13a) treffen, eine im wesentlichen gekrümmt ausgebildete Kante bildet, gesehen von dem vorderen Ende aus.
- 35
18. Spiralbohrer nach Anspruch 17,
wobei der Krümmungsradius (r) der gekrümmt ausgebildeten Kante zwischen 0,05D und 0,15D beträgt.
- 40
19. Spiralbohrer nach Anspruch 1,
wobei zumindest das vordere Ende des Körpers (10) mit einer Hartbeschichtung beschichtet ist.
- 45
20. Spiralbohrer nach Anspruch 2 oder Anspruch 19,
wobei die Hartbeschichtung aus zumindest einem Material besteht, das aus der Gruppe ausgewählt ist, die aus TiN, TiC, TiCN und Al_2O_3 besteht.
- 50
21. Spiralbohrer nach Anspruch 1,
wobei die erste und die zweite Schneide sich an einer Ecke treffen, die eine scharfe Kante bildet.
- 55
22. Spiralbohrer nach Anspruch 1,
wobei der Körper (10) ein Spannuten-Breitenverhältnis (A/B) zwischen 0,5 und 0,9 aufweist.
23. Spiralbohrer nach Anspruch 1,
wobei der Körper (10) ein Spannuten-Breitenverhältnis (A/B) zwischen 0,4 und 0,9 aufweist.
24. Spiralbohrer nach Anspruch 1,
wobei das Verhältnis der Bogenlänge (A1) der Spannute (11) zu der Bogenlänge (B1) der Freifläche (10a) an einem Querschnitt senkrecht zu der Achse (O) des Körpers (10) zwischen 0,9 und 1,2 beträgt.



Revendications

1. Foret hélicoïdal comprenant un corps cylindrique (10) ayant un axe de rotation (O) le traversant, présentant une extrémité antérieure qui est en contact avec une pièce et ayant une épaisseur (T) de l'âme de 0,2D à 0,35D, où D est le diamètre dudit corps (10);
 - ledit corps (10) ayant une cannelure en spirale (11) formée dans sa surface périphérique extérieure de manière à s'étendre en spirale suivant sa longueur jusqu'à ladite extrémité antérieure;
 - un méplat (10a) disposé en étant adjacent à ladite cannelure (11), ladite cannelure (11) ayant une première paroi dirigée dans le sens de rotation dudit corps (10) et une seconde paroi s'étendant entre l'extrémité intérieure de ladite première paroi et la périphérie extérieure dudit corps (10), ladite première paroi se terminant au droit de ladite extrémité antérieure par une première lèvre coupante (10) ayant son extrémité radialement la plus à l'extérieur (Q) disposée sur la périphérie extérieure dudit corps (10), ladite seconde paroi étant de forme concave lorsqu'on la regarde à partir de ladite extrémité antérieure;
 - la paroi de ladite cannelure (11) ayant une partie en forme d'arc qui est en contact avec un cylindre imaginaire inscrivant une partie de l'âme du foret;
 caractérisé en ce que :
 - (a) si l'on suppose qu'une première ligne (L) s'étend entre ladite extrémité radialement la plus à l'extérieur (Q) en étant perpendiculaire à une seconde ligne (N) qui relie ladite extrémité radialement la plus à l'extérieur (Q) et ledit axe (O) dudit corps (10), ladite seconde paroi est formée de façon que la distance maximum (W) entre ladite première ligne (L) et ladite seconde paroi soit établie à une valeur comprise entre 0,45D et 0,65D;
 - (b) ladite partie en forme d'arc a un rayon de courbure (R) compris entre 0,15D et 0,2D;
 - (c) le foret a une surface meulée (15) créant une seconde lèvre coupante (13a) qui s'étend en s'éloignant dudit axe de rotation (O) dudit corps (10) avec une surface de dégagement (16) longeant ladite seconde lèvre coupante (13a); une ligne d'un creux (17) entre ladite surface meulée (15) et ladite surface de dégagement (16) le long de ladite seconde lèvre coupante (13a), et dans lequel l'angle (ϕ) défini par ledit axe de rotation (O) dudit corps (10) et ladite ligne du creux (17) est établi à une valeur comprise entre 30° et 40°; et
 - (d) la distance axiale (I) entre l'extrémité radialement la plus à l'extérieur (Q) de ladite première lèvre coupante (12) et une extrémité antérieure (H) d'un talon (11b) est établie à une valeur comprise entre 0,3D et 1,0D.
2. Foret hélicoïdal selon la revendication 1, dans lequel le corps cylindrique (10) est constitué d'un matériau choisi dans le groupe comprenant l'acier rapide et l'acier rapide en métal fritté, au moins l'extrémité antérieure dudit corps étant recouvert d'un revêtement dur qui est plus dur que ledit corps.
3. Foret hélicoïdal selon la revendication 1 ou la revendication 2 et dans lequel chacune desdites première (12) et seconde (13a) lèvres coupantes est formée de manière à être linéaire lorsqu'on regarde à partir de ladite extrémité antérieure.
4. Foret hélicoïdal selon la revendication 3 dans lequel, lorsqu'un point P est défini par l'intersection d'une ligne tangente à ladite première lèvre coupante (12) et d'une ligne tangente à ladite seconde lèvre coupante (13a), le rapport de la distance (L_1) entre ledit axe (O) dudit corps (10) et ledit point P et de la distance (L_2) entre ladite extrémité la plus à l'extérieur (Q) de ladite première lèvre coupante (12) et ledit point P est établi entre 0,4:1 et 0,7:1.
5. Foret hélicoïdal selon la revendication 4, dans lequel ladite extrémité antérieure comprend une première surface de dégagement plane (18) présentant un angle de dégagement (β_1) de 7° à 15° et s'étendant le long de ladite première lèvre coupante (12), et une seconde surface de dégagement plane (19) présentant un angle de dégagement (β_2) supérieur à celui de ladite première surface de dégagement (18) de façon à être compris entre 15° et 25° et s'étendant le long de ladite première surface de dégagement (18), l'intersection de ladite première surface de dégagement (18) et de ladite seconde surface de dégagement (19) étant parallèle à ladite première lèvre coupante (12) et coupant ledit axe (O) dudit corps (10).



6. Foret hélicoïdal selon la revendication 5, dans lequel l'angle de dégagement axial (θ) pour ladite seconde lèvre coupante (13a) est compris entre 0° et -5° .
7. Foret hélicoïdal selon la revendication 6, dans lequel l'angle (λ) défini entre ladite surface meulée (15) formée par le meulage et ladite surface de dégagement (16) le long de ladite seconde lèvre coupante (13a) est compris entre 95° et 115° .
8. Foret hélicoïdal selon la revendication 7, comportant en outre un canal d'huile (22) formé dans ledit corps (10) et s'étendant en spirale le long de ladite cannelure (11).
9. Foret hélicoïdal selon la revendication 8, dans lequel l'intersection des parois de ladite cannelure (11) et du méplat (10a) dudit corps (10) est aiguisée pour former une face aiguisée (21).
10. Foret hélicoïdal selon la revendication 9, dans lequel ladite face aiguisée (21) est une face chanfreinée.
11. Foret hélicoïdal selon la revendication 10, dans lequel ladite face aiguisée (21) est une face arrondie.
12. Foret hélicoïdal selon la revendication 1 ou 2, dans lequel une seconde lèvre coupante (13a) formée par l'amincissement de l'âme est inclinée à un angle de 20° à 40° par rapport à la ligne s'étendant entre l'axe (O) dudit corps (10) et ladite extrémité la plus à l'extérieur (Q) de ladite première lèvre coupante (12).
13. Foret hélicoïdal selon la revendication 1, dans lequel une seconde lèvre coupante (13a) formée par l'amincissement de l'âme est inclinée à un angle (α) de 15° à 35° par rapport à la ligne (N) s'étendant entre l'axe (O) dudit corps (10) et ladite extrémité la plus à l'extérieur (Q) de ladite première lèvre coupante (12).
14. Foret hélicoïdal selon la revendication 12, dans lequel une paire desdites premières lèvres coupantes (12) et une paire desdites secondes lèvres coupantes (13a) sont fournies et aiguisées, et dans lequel, en supposant une première ligne imaginaire s'étendant à partir d'une nervure intérieure de l'une desdites secondes lèvres coupantes aiguisées (13a) et une seconde ligne imaginaire s'étendant à partir d'une nervure intérieure de l'autre seconde lèvre coupante aiguisée (13a), une distance intermédiaire (C) entre lesdites première et seconde lignes imaginaires est comprise entre 0,0 et 0,3 mm, lesdites secondes lèvres coupantes aiguisées définissant entre elles un bord de ciseau (20).
15. Foret hélicoïdal selon la revendication 13, dans lequel une paire desdites premières lèvres coupantes (12) et une paire desdites secondes lèvres coupantes (13a) sont fournies, et dans lequel, en supposant une première ligne imaginaire s'étendant à partir d'une nervure intérieure de l'une desdites secondes lèvres coupantes (13a) et une seconde ligne imaginaire s'étendant à partir d'une nervure intérieure de l'autre seconde lèvre coupante (13a), une distance intermédiaire (C) entre lesdites première et seconde lignes imaginaires est comprise entre 0,0 et 0,3 mm, lesdites secondes lèvres coupantes définissant entre elles un bord de ciseau (20).
16. Foret hélicoïdal selon la revendication 14 ou la revendication 15, dans lequel ledit bord de ciseau (20) a une largeur (G) comprise entre 0,0 et 0,4 mm.
17. Foret hélicoïdal selon la revendication 3, dans lequel l'angle auquel ladite première lèvre coupante (12) et ladite seconde lèvre coupante (13a) se rencontrent forme un bord ayant la forme générale d'un arc lorsqu'on le regarde à partir de ladite extrémité antérieure.
18. Foret hélicoïdal selon la revendication 17, dans lequel le rayon de courbure (r) dudit bord en forme d'arc est compris entre 0,05D et 0,15D.
19. Foret hélicoïdal selon la revendication 1, dans lequel au moins ladite extrémité antérieure dudit corps (10) est recouverte d'un revêtement dur.
20. Foret hélicoïdal selon la revendication 2 ou la revendication 19, dans lequel ledit revêtement dur est constitué d'au moins un matériau choisi dans le groupe comprenant TiN, TiC, TiCN et Al_2O_3 .



21. Foret hélicoïdal selon la revendication 1, dans lequel lesdites première et seconde lèvres coupantes se rencontrent à un angle formant un bord aiguisé.
- 5 22. Foret hélicoïdal selon la revendication 1, dans lequel ledit corps (10) a un rapport largeur-cannelure (A/B) de 0,5 à 0,9.
23. Foret hélicoïdal selon la revendication 1, dans lequel ledit corps (10) a un rapport largeur-cannelure (A/B) de 0,4 à 0,9.
- 10 24. Foret hélicoïdal selon la revendication 1, dans lequel le rapport entre la longueur de l'arc (A1) de ladite cannelure (11) et la longueur de l'arc (B1) dudit méplat (10a) au droit d'une section transversale prise perpendiculairement audit axe (O) dudit corps (10) est de 0,9 à 1,2.

15

20

25

30

35

40

45

50

55

