

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
21 July 2005 (21.07.2005)

PCT

(10) International Publication Number
WO 2005/066225 A1

- (51) International Patent Classification⁷: **C08F 210/00**, 212/00, 214/00, 216/00, 218/00, 220/00
- (21) International Application Number:
PCT/US2004/040677
- (22) International Filing Date: 3 December 2004 (03.12.2004)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
10/748,582 30 December 2003 (30.12.2003) US
- (71) Applicant: **EQUISTAR CHEMICALS, LP** [US/US];
One Houston Center, 1221 McKinney Street, Houston, TX
77010 (US).
- (72) Inventors: **LIU, Jia-Chu**; 9643 Sparrow Place, Mason,
OH 45040 (US). **GUO, Shao-Hua**; 316 Horizon Court,
Exton, PA 19341 (US).
- (74) Agents: **GUO, Shao-Hua** et al.; Lyondell Chemical Com-
pany, 3801 West Chester Pike, Newtown Square, PA 19073
(US).
- (81) Designated States (*unless otherwise indicated, for every
kind of national protection available*): AE, AG, AL, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,
MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,
TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (*unless otherwise indicated, for every
kind of regional protection available*): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,
FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO,
SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN,
GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:**
— with international search report
- For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.*

(54) Title: LPMC POLYMERIZATION OF UNSATURATED MONOMERS

(57) Abstract: A process for polymerizing unsaturated monomers is disclosed. The process comprises polymerizing, in the presence of a late transition metal catalyst (LPMC), a variety of unsaturated monomers which are traditionally, some of which are exclusively, made by free radical polymerizations. The LPMC polymerization provides the polymer with improved properties such as no free radical residue and narrow molecular weight distribution.

WO 2005/066225 A1

LTMC POLYMERIZATION OF UNSATURATED MONOMERS

FIELD OF THE INVENTION

5 The invention relates to polymerization of unsaturated monomers. More particularly, the invention relates to polymerization of unsaturated monomers with late transition metal catalysts (LTMC).

BACKGROUND OF THE INVENTION

10 Chain polymerization of unsaturated monomers can be divided into free radical, ionic, and coordination polymerizations. Ionic polymerization includes anionic and cationic polymerizations. Cationic polymerization is usually initiated by the Lewis acids such as BF_3 . Polyisobutylene rubber is the commercially important polymer made by the cationic polymerization. Anionic polymerization
15 is usually initiated by alkylolithiums such as $n\text{-BuLi}$. Many anionic polymerizations are devoid of any termination reaction, and they are thus called "living" polymerization. Living anionic polymerization has led to the creation of thermoplastic elastomers such as SBS (styrene-butadiene-styrene block copolymers).

20 Coordination polymerization includes the Ziegler-Natta polymerization and the metallocene or single-site polymerization. The Ziegler-Natta polymerization is performed with zirconium or titanium salts, such as TiCl_4 , ZrCl_4 , and VCl_4 , as catalysts and alkyl aluminum compounds, such as trimethyl aluminum, as cocatalysts. Metallocene catalyst was discovered by Kaminsky in
25 the early 1980's (see U.S. Pat. Nos. 4,404,344 and 4,431,788). Metallocene catalyst comprises a transition metal complex that has one or more cyclopentadienyl (Cp) ligands. Unlike the Ziegler-Natta catalysts which have multiple active sites of polymerization, metallocene catalysts have only "single" polymerization site, and therefore they are called "single-site" catalysts. Many
30 non-metallocene single-site catalysts have also been developed over the past decade.

Among the chain polymerizations, free radical polymerization is the most widely used in the polymer industry. Commonly used free radical initiators include peroxides, azo compounds, and persulfates. Unlike ionic initiators or coordination catalysts which require restricted conditions such as moisture and impurity free reaction systems, free radical polymerization can readily tolerate moisture and impurities. More importantly, free radical polymerization can tolerate functional monomers such as hydroxyl, carboxyl, and amino monomers. Thus, free radical polymerizations are exclusively used for making hydroxyl acrylic resins, polyacrylic acid, olefin-acrylic copolymers, and many other functional polymers.

Since the late 1990s, olefin polymerization catalysts that incorporate late transition metals (especially iron, nickel, or cobalt) and bulky α -diimine ligands (or "bis(imines)") have been investigated. These late transition metal catalysts (LTMC) are of interest because, unlike the early transition metal metallocenes or Ziegler catalysts, the LTMC can incorporate alkyl acrylate comonomers into polyolefins. See U.S. Pat. Nos. 5,866,663 and 5,955,555.

However, the LTMC is considered to be a coordination catalyst, and thus study on LTMC has been limited to olefin-related polymerizations. No prior art discloses the use of LTMC for making hydroxyl acrylic resins, styrene-allyl alcohol copolymers, and many other important functional polymers. No prior art discloses the use of LTMC for the polymerization of unsaturated monomers in the absence of olefins.

Compared to conventional free radical polymerization, the LTMC has great potential in tailoring of critical polymer properties: molecular weight, crystallinity or melting point, and polydispersity. Therefore, the LTMC may provide better product quality and production consistency. Also, the LTMC does not require high temperature and high pressure polymerization. It avoids the use of explosive peroxides or azo compounds. Thus, the LTMC polymerization may provide a safer and more cost-effective alternative to the existing free radical technology.

In summary, it is apparently important to explore the use of LTMC for the polymerization of the unsaturated monomers which have been traditionally, some of which have been exclusively, polymerized by free radical polymerizations.

5

SUMMARY OF THE INVENTION

The process of the invention comprises polymerizing unsaturated monomers in the presence of a late transition metal catalyst (LTMC). The LTMC comprises a Group 8-10 late transition metal complex and an activator. By "complex," we mean the compounds which comprise a Group 8-10 metal and at least one polymerization-stable ligand which remains bound to the metal during the course of the polymerization process.


The process includes polymerizing one of the monomer groups (a) through (f): (a) a vinyl monomer selected from the group consisting of vinyl aromatics, vinyl ethers, vinyl esters, and vinyl halides; (b) a vinyl monomer selected from the group consisting of vinyl ethers, vinyl esters, and vinyl halides, and at least one olefin; (c) a hydroxy-functional monomer selected from the group consisting of hydroxyalkyl acrylates, hydroxyalkyl methacrylates, allylic alcohols, and alkoxylated allylic alcohols, and at least one alkyl or aryl acrylate or at least one alkyl or aryl methacrylate; (d) a hydroxy-functional monomer selected from the group consisting of hydroxyalkyl acrylates, hydroxyalkyl methacrylates, allylic alcohols, and alkoxylated allylic alcohols, at least one alkyl or aryl acrylate or at least one alkyl or aryl methacrylate, and at least one olefin; (e) a hydroxy-functional monomer selected from the group consisting of hydroxyalkyl acrylates, hydroxyalkyl methacrylates, allylic alcohols, and alkoxylated allylic alcohols, and at least one vinyl aromatic monomer; or (f) a hydroxy-functional monomer selected from the group consisting of hydroxyalkyl acrylates, hydroxyalkyl methacrylates, allylic alcohols, and alkoxylated allylic alcohols, at least one vinyl aromatic monomer, and at least one olefin.

30

DETAILED DESCRIPTION OF THE INVENTION

The process of the invention is polymerizing unsaturated monomers with a late transition metal catalyst (LTMC). The LTMC comprises a Group 8-10 late transition metal complex and an activator. Suitable LTMC include those known
5 in the art.

Preferred late transition metal complexes have the general structure:




The M is a Group 8-10 late transition metal. Preferably, the M is selected from the group consisting of Ni, Co, and Fe. More preferably, the M is Ni or Fe.
10 Most preferably, the M is Fe.

The L is a polymerization-stable ligand. By "polymerization-stable ligand," we mean that the ligand remains bound to the metal during the course of the polymerization process. Preferably, the L is an isoindoline or bis(imine).

Suitable L ligands also include those taught by U.S. Pat. Nos. 5,714,556
15 and 6,620,759.







The X is a labile ligand. By "labile ligand," we mean that the ligand is easily displaceable during the polymerization. Preferably, L is independently selected from the group consisting of hydrogen and halides, and n, the number of the X ligands, is greater than or equal to 1.

20 Suitable isoindoline ligands include those taught by co-pending Appl. Ser. No. 09/947,745, filed on Sept. 6, 2001. Preferably the isoindoline ligands have the general structure:




When forming a late transition metal complex, the hydrogen of the N-H group may be removed to form an ionic bonding between the nitrogen and the late transition metal. Optionally, the aromatic ring hydrogen atoms of the above structure are independently substituted. Suitable ring substitute groups include
5 alkyl, aryl, aralkyl, alkylaryl, silyl, halogen, alkoxy, aryloxy, siloxy, nitro, dialkyl amino, diaryl amino groups, and the like.

A is an aryl or a heteroaryl group. When A is aryl, it preferably is phenyl- or alkyl-substituted, such as 4-methylphenyl or 2,4,6-trimethylphenyl (2-mesityl). When A is heteroaryl, it is preferably 2-pyridyl, 2-pyrimidinyl, 4-pyrimidinyl, 2-
10 pyrazinyl, 2-imidazolyl, 2-thiazolyl, or 2-oxazolyl. The aryl and heteroaryl groups can be fused to other rings, as in a 2-naphthyl, 2-benzothiazolyl or 2-benzimidazolyl group. A few exemplary isoindolines appear below:



Suitable bis(imine) ligands include those taught by U.S. Pat. No. 5,866,663. Suitable bis(imine) ligands include those having the general structure:




5

wherein R^1 and R^4 are each independently hydrocarbyl or substituted hydrocarbyl. R^2 and R^3 are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl or R^2 and R^3 taken together are hydrocarbylene or substituted hydrocarbylene to form a ring.

10

Suitable bis(imine) ligands include those having the general structure:



R^5 is hydrocarbyl or substituted hydrocarbyl, and R^6 is hydrogen, hydrocarbyl or substituted hydrocarbyl, or R^5 and R^6 taken together form a ring. R^9 is hydrocarbyl or substituted hydrocarbyl, and R^8 is hydrogen, substituted hydrocarbyl or hydrocarbyl, or R^9 and R^8 taken together form a ring. Each R^7 is independently hydrogen, substituted hydrocarbyl or hydrocarbyl, or two of R^7 taken together form a ring; n is 2 or 3.

20

Suitable bis(imine) ligands include 2,6-pyridinecarboxaldehydebis(imines) and 2,6-diacetylpyridinebis(imines), which are taught, e.g., by U.S. Pat. No. 5,955,555.

25

Suitable bis(imine) ligands also include acenaphthene bis- N,N' -(2,6-diisopropylphenyl)imines, which are taught, e.g., by U.S. Pat. No. 6,127,497.

Suitable activators include alumoxane and alkylaluminum compounds. Examples of suitable alumoxane compounds include methyl alumoxane (MAO),

polymeric MAO (PMAO), ethyl alumoxane, diisobutyl alumoxane, and the like. Examples of suitable alkylaluminum compounds include triethylaluminum, diethyl aluminum chloride, trimethylaluminum, triisobutyl aluminum, and the like. Suitable alumoxane compounds also include those that are modified. Methods
5 for the modification of alumoxanes are known. For instance, U.S. Pat. No. 4,990,640 teaches the modification of alumoxanes with active hydrogen-containing compounds such as ethylene glycol. U.S. Pat. No. 6,340,771 teaches modifying MAO with sugar to make "sweet" MAO. Also, U.S. Pat. No. 5,543,377 teaches modifying alumoxanes with ketoalcohols and β -diketones.

10 Suitable activators also include acid salts that contain non-nucleophilic anions. These compounds generally consist of bulky ligands attached to boron or aluminum. Examples include lithium tetrakis(pentafluorophenyl)borate, lithium tetrakis-(pentafluorophenyl) aluminate, anilinium tetrakis(pentafluorophenyl)borate, and the like.

15 Suitable activators further include organoboranes, which are compounds of boron and one or more alkyl, aryl, or aralkyl groups. Suitable organoboranes include substituted and unsubstituted trialkyl and triarylboranes such as tris(pentafluorophenyl)borane, triphenylborane, tri-n-octylborane, and the like. Suitable organoborane activators are described in U.S. Pat. Nos. 5,153,157,
20 5,198,401, and 5,241,025. Suitable activators also include aluminoboronates, which are the reaction products of alkyl aluminum compounds and organoboronic acids. These activators are described in U.S. Pat. Nos. 5,414,180 and 5,648,440.

The late transition metal complex, the activator, or both are optionally
25 supported onto an inorganic solid or organic polymer support. Suitable supports include silica, alumina, silica-aluminas, magnesia, titania, clays, zeolites, or the like. The support is preferably treated thermally, chemically, or both prior to use to reduce the concentration of surface hydroxyl groups. Thermal treatment consists of heating (or "calcining") the support in a dry atmosphere at elevated
30 temperature, preferably greater than about 100°C, and more preferably from about 150°C to about 600°C, prior to use. A variety of different chemical treatments can be used, including reaction with organo-aluminum, -magnesium,

-silicon, or -boron compounds. See, for example, the techniques described in U.S. Pat. No. 6,211,311.

The invention includes a process for polymerizing, in the presence of the LTMC, a vinyl monomer selected from the group consisting of vinyl aromatics, vinyl ethers, vinyl esters, vinyl halides, the like, and mixtures thereof. Surprisingly, we found that these vinyl monomers, which are traditionally polymerized by free radical polymerization, can be readily polymerized by the LTMC without the presence of any olefin comonomer.

Suitable vinyl aromatic monomers preferably have a $-CR'=CH_2$ group connected to an aromatic group. R' is hydrogen or a C_1 to C_{10} alkyl group. Examples of suitable vinyl aromatic monomers are styrene, α -methylstyrene, p-methylstyrene, p-t-butylstyrene, chloromethylstyrene, trifluoromethylstyrene, ethoxymethylstyrene, acetoxymethylstyrene, methoxystyrene, 4-methoxy-3-methylstyrene, dimethoxystyrene, chlorostyrene, dichlorostyrene, trichlorostyrene, tetrachlorostyrene, pentachlorostyrene, bromostyrene, dibromostyrene, iodostyrene, fluorostyrene, trifluorostyrene, 2-bromo-4-trifluoromethylstyrene, 4-fluoro-3-trifluoromethylstyrene, 9-vinylnanthracene, 2-vinylnaphthalene, the like, and mixtures thereof. Styrene is particularly preferred.

Suitable vinyl ethers include vinyl alkyl ethers, vinyl aryl ethers, and mixtures thereof. Examples of suitable vinyl alkyl ethers are methyl vinyl ether, ethyl vinyl ether, hexyl vinyl ether, octyl vinyl ether, decyl vinyl ether, ethylhexyl vinyl ether, methoxyethyl vinyl ether, ethoxyethyl vinyl ether, chloroethyl vinyl ether, 1-methyl-2,2-dimethylpropyl vinyl ether, 2-ethylbutyl vinyl ether, hydroxyethyl vinyl ether, dimethylaminoethyl vinyl ether, diethylaminoethyl vinyl ether, butylaminoethyl vinyl ether, benzyl vinyl ether, tetrahydrofurfuryl vinyl ether, and the like, and mixtures thereof. Examples of suitable vinyl aryl ethers are vinyl phenyl ether, vinyl tolyl ether, vinyl chlorophenyl ether, vinyl-2,4-dichlorophenyl ether, vinyl naphthyl ether, vinyl anthranyl ether, the like, and mixtures thereof.

Suitable vinyl esters include vinyl acetate, vinyl butyrate, vinyl isobutyrate, vinyl trimethylacetate, vinyl diethylacetate, vinyl valerate, vinyl caproate, vinyl chloroacetate, vinyl dichloroacetate, vinyl methoxyacetate, vinyl butoxyacetate, vinyl phenylacetate, vinyl acetoacetate, vinyl lactate, vinyl- β -phenylbutyrate, vinyl cyclohexylcarboxylate, vinyl benzoate, vinyl salicylate, vinyl chlorobenzoate, vinyl tetrachlorobenzoate, and vinyl naphthoate, the like, and mixtures thereof.

Suitable vinyl halides include by halogen substituted ethylenes. Examples are vinyl chloride, vinyl fluoride, vinylidene chloride, chlorotrifluoro ethylene, the like, and mixtures thereof.

The invention includes a process for polymerizing an olefin and a vinyl monomer selected from the group consisting of vinyl ethers, vinyl esters, vinyl halides, the like, and mixtures thereof. Suitable vinyl ethers, vinyl esters and vinyl halides are discussed above. Suitable olefins include α -olefins, cyclic olefins, and mixtures thereof. C_2 - C_{10} α -olefins are preferred. Ethylene, propylene, 1-butene, 1-pentene, 1-hexene, 1-octene, and mixtures thereof are particularly preferred. Ethylene and propylene are most preferred.

The invention includes a process for polymerizing a hydroxy-functional monomer selected from the group consisting of hydroxyalkyl acrylates, hydroxyalkyl methacrylate, allylic alcohols, alkoxylated allylic alcohols, and mixtures thereof, and an alkyl or aryl acrylate or an alkyl aryl methacrylate.

Suitable hydroxyalkyl acrylates and methacrylates include hydroxyethyl acrylate and methacrylate, hydroxypropyl acrylate and methacrylate, and hydroxybutyl acrylate and methacrylate. Suitable allylic alcohols and alkoxylated allylic alcohols include allyl alcohol, methallyl alcohol, ethoxylated allyl alcohol, ethoxylated methallyl alcohol, propoxylated allyl alcohol, and propoxylated methallyl alcohol. Suitable alkyl or aryl acrylates and methacrylates include C_1 - C_{20} alkyl acrylates and methacrylates, C_6 - C_{20} aryl acrylates and methacrylates, the like, and mixtures thereof. Examples are n-butyl acrylate, n-butyl methacrylate, methyl methacrylate, t-butyl methacrylate, iso-butyl methacrylate, benzyl methacrylate, cyclohexyl methacrylate, the like, and mixtures thereof.

The invention includes a process for polymerizing a vinyl aromatic and a hydroxy-functional monomer selected from the group consisting of hydroxyalkyl acrylates, hydroxyalkyl methacrylates, allylic alcohols, alkoxylated allylic alcohols, and mixtures thereof. Suitable hydroxyalkyl acrylates and methacrylates, allylic alcohols, alkoxylated allylic alcohols, and vinyl aromatics are discussed above.

The invention also includes a process for polymerizing an olefin, a vinyl aromatic, and a hydroxy-functional monomer selected from the group consisting of hydroxyalkyl acrylates, hydroxyalkyl methacrylates, allylic alcohols, alkoxylated allylic alcohols, and mixtures thereof. Suitable olefins, hydroxyalkyl acrylates and methacrylates, allylic alcohols, alkoxylated allylic alcohols, and vinyl aromatics are discussed above.

The polymerization of the invention is preferably conducted at a temperature within the range of about 0°C to about 200°C. The polymerization temperature varies depending on the polymers to be made. For example, making hydroxyl acrylic resins or styrene-allyl alcohol copolymers requires a relatively high temperature (from about 80°C to about 150°C is preferred). High polymerization temperatures lead to low molecular weight resins which are suitable for high solids or low VOC (volatile organic compound) coatings.

The polymerization can be performed in bulk, solution, slurry, or any other suitable forms, depending on the polymers to be made. For instance, when a styrene-allyl alcohol copolymer is made, a bulk polymerization is preferred because allyl alcohol polymerizes slowly and the excess allyl alcohol functions as a solvent to control the polymerization. When a hydroxyl acrylic resin is made from an hydroxyalkyl acrylate and alkyl acrylate, the polymerization is preferably performed in solution wherein the solvent is used as a chain transfer agent to lower the polymer molecular weight and to control the polymerization rate.

The polymerization can be performed in a batch, semi-batch, or continuous process depending on the monomers used and the polymers made. For instance, a semi-batch process is preferred when a styrene-allyl alcohol

copolymer is made. In the semi-batch process, allyl alcohol is initially charged into the reactor, and styrene is gradually fed into the reactor during the polymerization. The gradual addition of styrene ensures an even distribution of the OH function groups along the polymer chain.

5 The invention includes the polymers made by the process of the invention. Particularly interesting polymers include hydroxyl acrylic resins (i.e., copolymers comprise hydroxyl-functional monomers, alkyl or aryl acrylates or alkyl or acryl methacrylates, and optionally vinyl aromatics), olefin-acrylic
10 copolymers, olefin-vinyl ester copolymers, and vinyl aromatic-allylic alcohol copolymers. The polymers made by the invention differ from the polymers made by the free radical polymerization in that the polymers of the invention do not contain residual free radical initiators or fragments from the initiator decomposition. Polymers made by free radical polymerization are thermally, chemically, or photo-chemically instable because of the residual initiator or
15 initiator fragments. Thus, the polymers of the invention are expected to have improved thermal, chemical, and photo-chemical resistance.

 The invention also includes articles made from the polymers of the invention. Examples of the useful articles which can be made from the polymers of the invention include films, sheets, containers, pipes, fibers, coatings,
20 adhesives, elastomers, sealants, and the likes. One advantage of the invention is that the LTMC provide better tailoring than the free radical polymerization in controlling the polymer properties such as density, molecular weight, and molecular weight distribution. For instance, the LTMC polymerization can provide hydroxyl acrylic resins with narrow molecular weight distribution. The
25 narrow molecular weight distribution results in lower VOC or higher solids coatings.

 The following examples merely illustrate the invention. Those skilled in the art will recognize many variations that are within the spirit of the invention and scope of the claims.

EXAMPLE 1

Copolymerization of Ethylene, n-Butyl Acrylate, and Allyl Monopropoxylate with
Iron(II) 1,3-Bis(2-Mesitylimino)isoindoline
Complex and Mao Activator

5 Catalyst Complex Preparation

A 100-mL round-bottom flask equipped with a nitrogen inlet and an internal fritted-glass filter is charged with phthalimide (2.94 g, 20.0 mmol) and ethyl acetate (60 mL). 2,4,6-Trimethylaniline (5.41 g, 40.0 mmol, 2.0 eq.) and iron(II) chloride (2.54 g, 20.0 mmol) are added to the flask, and the mixture is
10 stirred under nitrogen at room temperature for 1 h. The yellow mixture is heated to reflux (77°C) for 10 h, and is then stirred at room temperature for 32 h. A brown precipitate forms. The reaction mixture is concentrated by stripping out the ethyl acetate under a stream of nitrogen. Cold diethyl ether (30 mL) is added to the residue, and the mixture is stirred to wash the residue. The glass
15 filter is immersed in the liquid phase, which is then removed at reduced pressure through the internal filter. The solids are dried under vacuum for 2 h to give a brown powder.

Polymerization

The polymerization is performed in an Endeavor (Advantage™ Series
20 3400 Process Chemistry Workstation, made by Argonaut Technologies, Inc.). The Endeavor contains eight pressure reactor tubes each with individual temperature, pressure, stirring, and injection controls. The Endeavor is placed in a glove box for manual manipulations and an inert atmosphere of nitrogen. A pre-programmed computer monitors and collects data on pressure, temperature,
25 ethylene consumption in each reactor tube as a function of the reaction time.

A reactor tube (10 mL) is charged with n-butyl acrylate (2 mL), allyl monopropoxylate (2 mL), tri-isobutyl aluminum (0.1 mL, 1.0 M hexane solution), MAO (0.08 mL, 1.0 M toluene solution), and the catalyst complex (0.2 mL, 1.0 mg/ml toluene solution). The reactor tube is then sealed. The reactor is
30 pressured with ethylene to 400 psig and heated to 100°C. The polymerization

continues at these temperature and pressure readings for about 1 h with continuous feeding of ethylene. The ethylene consumption is about 0.02 g. After polymerization, the unreacted monomers are removed by vacuum, yielding 0.4 g of polymer. The polymer has Mw: 5650; Mn: 3220; and Mw/Mn: 1.75.

5

EXAMPLE 2

Copolymerization of Ethylene, n-Butyl Acrylate, and Hydroxyethyl Acrylate with Iron(II) 1,3-Bis(2-Mesitylimino)isoindoline Complex and Mao Activator

10 The general procedure of Example 1 is followed. A reactor tube (10 mL) is charged with n-butyl acrylate (2 mL), hydroxyethyl acrylate (2 mL), tri-isobutyl aluminum (0.1 mL, 1.0 M hexane solution), MAO (0.08 mL, 1.0 M toluene solution), and the catalyst complex (0.2 mL, 1.0 mg/ml toluene solution). The reactor tube is then sealed. The reactor is pressured with ethylene to 400 psig
15 and heated to 100°C. The polymerization continues at these temperature and pressure readings for about 1 h with continuous feeding of ethylene. The ethylene consumption is about 0.2 g. After polymerization, unreacted monomers are removed by vacuum, yielding 2.2 g of polymer.

20

EXAMPLE 3

Copolymerization of n-Butyl Acrylate and Allyl Monopropoxylate with Iron(II) 1,3-Bis(2-Mesitylimino)isoindoline Complex and Mao Activator

The general procedure of Example 1 is followed. A reactor tube (10 mL) is charged with n-butyl acrylate (2 mL), allyl monopropoxylate (2 mL), tri-isobutyl
25 aluminum (0.1 mL, 1.0 M hexane solution), MAO (0.08 mL, 1.0 M toluene solution), and the catalyst complex (0.2 mL, 1.0 mg/ml toluene solution). The reactor tube is then sealed. The reactor contents are heated to 100°C. The polymerization continues at this temperature reading for about 1 h. After polymerization, the unreacted monomers are removed by vacuum, yielding 2.1 g
30 of polymer.

EXAMPLE 4

Copolymerization of n-Butyl Acrylate and Hydroxyethyl acrylate with Iron(II) 1,3-Bis(2-Mesitylimino)isoindoline Complex and Mao Activator

The general procedure of Example 1 is followed. A reactor tube (10 mL) is charged with n-butyl acrylate (2 mL), hydroxyethyl acrylate (2 mL), tri-isobutyl aluminum (0.1 mL, 1.0 M hexane solution), MAO (0.08 mL, 1.0 M toluene solution), and the catalyst complex (0.2 mL, 1.0 mg/ml toluene solution). The reactor tube is then sealed. The reactor contents are heated to 100°C. The polymerization continues at this temperature reading for about 1 h. After polymerization, the unreacted monomers are removed by vacuum, yielding 3.4 g of polymer.

EXAMPLE 5

Copolymerization of Ethylene, Styrene, and Allyl Monopropoxylate with Iron(II) 1,3-Bis(2-Mesitylimino)isoindoline Complex and Mao Activator

The general procedure of Example 1 is followed. A reactor tube (10 mL) is charged with styrene (2 mL), allyl monopropoxylate (2 mL), tri-isobutyl aluminum (0.1 mL, 1.0 M hexane solution), MAO (0.08 mL, 1.0 M toluene solution), and the catalyst complex (0.2 mL, 1.0 mg/ml toluene solution). The reactor tube is then sealed. The reactor is pressured with ethylene to 400 psig and heated to 100°C. The polymerization continues at these temperature and pressure readings for about 1 h with continuous feeding of ethylene. The ethylene consumption is about 0.01 g. After polymerization, the unreacted monomers are removed by vacuum, yielding 0.23 g of polymer.

25

EXAMPLE 6

Copolymerization of Styrene and Allyl Monopropoxylate with Iron(II) 1,3-Bis(2-Mesitylimino)isoindoline Complex and Mao Activator

The general procedure of Example 1 is followed. A reactor tube (10 mL) is charged with styrene (2 mL), allyl monopropoxylate (2 mL), tri-isobutyl

aluminum (0.1 mL, 1.0 M hexane solution), MAO (0.08 mL, 1.0 M toluene solution), and the catalyst (0.2 mL, 1.0 mg/ml toluene solution). The reactor tube is then sealed. The reactor contents are heated to 100°C. The polymerization continues at this temperature reading for about 1 h. After
5 polymerization, the unreacted monomers are removed by vacuum, yielding 0.1 g of polymer.

EXAMPLE 7

Copolymerization of Ethylene, n-Butyl Acrylate and Allyl
10 Monopropoxylate with Iron(II) 1,3-Bis(2-pyridylimino)isoindoline
Complex and MAO Activator

Catalyst Preparation

A 100-mL round-bottom flask equipped with a nitrogen inlet and an internal fritted-glass filter is charged with phthalimide (2.94 g, 20.0 mmol) and
15 ethyl acetate (50 mL). 2-Aminopyridine (3.77 g, 40.0 mmol, 2.1 eq.) and iron(II) chloride (2.54 g, 20.0 mmol) are added to the flask, and the mixture is stirred under nitrogen at room temperature for 1 h. The mixture is stirred at room temperature for 120 h, yielding a white precipitate. After washing with cold diethyl ether (3 X 20 mL), the white solids are dried under vacuum for 1 h.

20 Polymerization

The polymerization procedure of Example 1 is followed, but the above prepared catalyst complex is used. The ethylene consumption is 0.01 g, and 0.15 g of polymer is collected.

25

30

EXAMPLE 8

Copolymerization of Ethylene, n-Butyl Acrylate, and Allyl Monopropoxylate with
Iron(II) Bis(imine) Complex and MAO ActivatorCatalyst Preparation

5 An iron(II) bis(imine) complex is prepared according Example 1 of U.S. Pat. No. 6,562,973. A 100-mL round-bottom flask equipped with a nitrogen inlet and an internal fritted-glass filter is charged with 2,6-diacetylpyridine (2.00 g, 12.2 mmol) and ethyl acetate (50 mL). 2,4,6-Trimethylaniline (3.52 g, 26.0 mmol, 2.13 eq.) is added to the stirred solution.

10 Iron(II) chloride (1.55 g, 12.2 mmol) is added to the flask, and the mixture is stirred under nitrogen at room temperature for 42 h. The reaction mixture is concentrated by stripping out solvents under reduced pressure. Cold diethyl ether (30 mL) is added to the residue, and the mixture is stirred to wash the residue. The glass filter is immersed in the liquid phase, which is then removed
15 at reduced pressure through the internal filter. The complex solids are dried under vacuum for 1 h.

Polymerization


 The polymerization procedure of Example 1 is followed, but the above prepared catalyst complex is used. The ethylene consumption is 0.01 g and
20 0.17 g of polymer is collected. The polymer has Mw: 6000; and Mn: 2170; and Mw/Mn: 2.76.

We claim:

1. A process comprising polymerizing, in the presence of a Group 8-10 metal complex and an activator, one of the monomer groups (a) through (f):


- 5 (a) a vinyl monomer selected from the group consisting of vinyl aromatics, vinyl ethers, vinyl esters, and vinyl halides thereof;
- (b) a vinyl monomer selected from the group consisting of vinyl ethers, vinyl esters, and vinyl halides, and at least one olefin;
- 10 (c) a hydroxy-functional monomer selected from the group consisting of hydroxyalkyl acrylates, hydroxyalkyl methacrylates, allylic alcohols, and alkoxylated allylic alcohols, and at least one alkyl or aryl acrylate or at least one alkyl or aryl methacrylate;
- 15 (d) a hydroxy-functional monomer selected from the group consisting of hydroxyalkyl acrylates, hydroxyalkyl methacrylates, allylic alcohols, and alkoxylated allylic alcohols, at least one alkyl or aryl acrylate or at least one alkyl or aryl methacrylate, and at least one olefin;
- 20 (e) a hydroxy-functional monomer selected from the group consisting of hydroxyalkyl acrylates, hydroxyalkyl methacrylates, allylic alcohols, and alkoxylated allylic alcohols, and at least one vinyl aromatic monomer; or
- (f) a hydroxy-functional monomer selected from the group consisting of hydroxyalkyl acrylates, hydroxyalkyl methacrylates, allylic alcohols, and alkoxylated allylic alcohols, at least one vinyl aromatic monomer, and at least one olefin.

25 2. The process of claim 1 wherein the complex has the general structure:



wherein M is a Group 8-10 metal; L is a polymerization-stable ligand selected from isoindolines or bis(imines); X is a labile ligand; and n is greater than or equal to 1.

30 3. The process of claim 2 wherein L is an isoindoline ligand having the general structure:



wherein A and A' are the same or different aryl or heteroaryl groups.

4. The process of claim 3 wherein A and A' are identical aryl groups.
5. The process of claim 3 wherein A and A' are identical heteroaryl groups.
- 5 6. The process of claim 2 wherein the M is Fe and L is a 1,3-bis(2-mesitylimino)isoindoline or a 1,3-bis(2-pyridylimino)isoindoline.
7. The process of claim 1 wherein the activator is selected from the group consisting of alkyl alumoxanes, alkylaluminum compounds, aluminoboronates, organoboranes, ionic borates, and ionic aluminates.
- 10 8. A polymer made by the process of claim 1.
9. An article comprising the polymer of claim 8.
10. A process which comprises polymerizing, in the presence of a Group 8-10 metal complex and an activator, a hydroxy-functional monomer selected from the group consisting of hydroxyalkyl acrylates, hydroxyalkyl methacrylates, allylic alcohols, and alkoxyated allylic alcohols, at least one alkyl or aryl acrylate or at

15 least one alkyl or aryl methacrylate, optionally a vinyl aromatic monomer, and optionally a C₂₋₁₀ α -olefin.
11. The process of claim 10 wherein the hydroxy-functional monomer is selected from the group consisting of hydroxyethyl acrylate, hydroxypropyl

20 acrylate, hydroxyethyl methacrylate, hydroxypropyl methacrylate, hydroxybutyl acrylate, hydroxybutyl methacrylate, allyl alcohol, methallyl alcohol, propoxylated allyl alcohol, and ethoxylated allyl alcohol.
12. The process of claim 10 wherein at least one of the alkyl or aryl acrylate, or the alkyl or aryl methacrylate, is selected from the group consisting of n-butyl

25 acrylate, n-butyl methacrylate, 2-ethylhexyl acrylate, 2-ethylhexyl methacrylate,

methyl acrylate, methyl methacrylate, t-butyl acrylate, t-butyl methacrylate, iso-butyl acrylate, iso-butyl methacrylate, iso-bornyl acrylate, and iso-bornyl methacrylate.

13. The process of claim 10 wherein the hydroxy-functional monomer is allyl
5 monopropoxylate and the alkyl acrylate or methacrylate is n-butyl acrylate or n-butyl methacrylate.

14. The process of claim 10 wherein the vinyl aromatic monomer is selected from the group consisting of styrene, α -methyl styrene, *p*-methyl styrene, and *p*-t-butyl styrene.

10 15. The process of claim 10 wherein the α -olefin is selected from the group consisting of ethylene, propylene, 1-butene, 1-pentene, 1-hexene, and 1-octene.

16. The process of claim 10 wherein the late transition metal complex comprises Fe and a 1,3-bis(2-mesitylimino)isoindoline or a 1,3-bis(2-pyridylimino)isoindoline ligand, and wherein the activator is an alkyl alumoxane.

15 17. A polymer made by the process of claim 10.

18. An article comprising the polymer of claim 10.

19. A process which comprises polymerizing, in the presence of a Group 8-10 metal complex and an activator, at least one vinyl ester and at least one C₂₋₁₀ α -olefin.

20 20. The process of claim 19 wherein the vinyl ester is vinyl acetate and the α -olefin is ethylene.

21. A polymer made by the process of claim 19.

22. An article comprising the polymer of claim 21.

23. A process which comprises polymerizing, in the presence of a Group 8-10 metal complex and an activator, a hydroxy-functional monomer selected from
25 the group consisting of hydroxyalkyl acrylates, hydroxyalkyl methacrylates, allylic

alcohols, and alkoxyated allylic alcohols, at least one vinyl aromatic monomer, and optionally at least one C₂₋₁₀ α -olefin.

24. The process of claim 23 wherein the vinyl aromatic monomer is styrene and the hydroxy-functional monomer is selected from the group consisting of
5 allyl alcohol, methallyl alcohol, alkoxyated allyl alcohol, and alkoxyated methallyl alcohol.

25. A polymer made by the process of claim 23.

26. An article comprising the polymer of claim 25.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US2004/040677

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08F210/00 C08F212/00 C08F214/00 C08F216/00 C08F218/00
C08F220/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, CHEM ABS Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
E	US 6 844 402 B1 (LIU JIA-CHU ET AL) 18 January 2005 (2005-01-18) the whole document	1-26
X	TIAN, GONGLU ET AL: "Neutral Palladium Complexes as Catalysts for Olefin -Methyl Acrylate Copolymerization: A Cautionary Tale" MACROMOLECULES, 34(22), 7656-7663 CODEN: MAMOBX; ISSN: 0024-9297, 2001, XP002325084 the whole document	1,2,8,9
X	US 2003/171209 A1 (WANG KUN ET AL) 11 September 2003 (2003-09-11) paragraphs '0010!, '0036! - '0038! ----- -/--	1,2,8,9, 19-22

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *Z* document member of the same patent family

Date of the actual completion of the international search

19 April 2005

Date of mailing of the international search report

02/05/2005

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Balmer, J-P

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US2004/040677

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 1 136 122 A (IDEMITSU PETROCHEMICAL CO., LTD) 26 September 2001 (2001-09-26) paragraph '0123!; claim 29 -----	1,2,8,9, 19-22
X	WO 01/07492 A (BASF AKTIENGESELLSCHAFT; QUEISSER, JOACHIM; GEPRAEGS, MICHAEL; LUINSTR) 1 February 2001 (2001-02-01) page 5 - page 6; claims 3,4 -----	1,2,8,9, 19-22
X	WO 01/92354 A (E. I. DU PONT DE NEMOURS AND COMPANY; JOHNSON, LYNDIA, K; WANG, LIN; MC) 6 December 2001 (2001-12-06) the whole document -----	1,2,8,9
X	PATENT ABSTRACTS OF JAPAN vol. 1998, no. 05, 30 April 1998 (1998-04-30) & JP 10 007719 A (MITSUI PETROCHEM IND LTD), 13 January 1998 (1998-01-13) abstract -----	1,2,8,9, 19-22
X	US 5 175 326 A (KLABUNDE ET AL) 29 December 1992 (1992-12-29) the whole document -----	1,19,21, 22
X	WO 99/58578 A (BP CHEMICALS LIMITED; GIBSON, VERNON, CHARLES; WASS, DUNCAN, FRANK) 18 November 1999 (1999-11-18) the whole document -----	1,2,8,9
X	WO 95/04759 A (ZENECA LIMITED; HADDLETON, DAVID, MARK; MUIR, ANDREW, VICTOR, GRAHAM) 16 February 1995 (1995-02-16) the whole document -----	1,2,8,9
X	"International Patent Classification Seventh Edition" 1999, WORD INTELLECTUAL PROPERTY ORGANISATION 3, XP002325085 the whole document -----	8,9,17, 18,21, 22,25,26

INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/US2004/040677

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 6844402	B1	18-01-2005	NONE	
US 2003171209	A1	11-09-2003	NONE	
EP 1136122	A	26-09-2001	AU 7314100 A BR 0007150 A CA 2345621 A1 EP 1136122 A1 CN 1321111 A ID 29091 A WO 0119513 A1	17-04-2001 14-08-2001 22-03-2001 26-09-2001 07-11-2001 26-07-2001 22-03-2001
WO 0107492	A	01-02-2001	DE 19934464 A1 WO 0107492 A1 EP 1200488 A1 JP 2003505559 T	01-02-2001 01-02-2001 02-05-2002 12-02-2003
WO 0192354	A	06-12-2001	AU 6526001 A AU 6663501 A AU 6972501 A AU 7507001 A BR 0111338 A BR 0111657 A CA 2408663 A1 CA 2408937 A1 CN 1432027 A CN 1444606 A EP 1292623 A2 EP 1292624 A2 EP 1290043 A2 JP 2004502652 T JP 2003535190 T JP 2003535107 T WO 0192354 A2 WO 0192342 A2 WO 0192347 A2 WO 0192348 A2 US 2003130449 A1 US 2003130453 A1 US 2002028897 A1 US 2002037982 A1 US 2002032289 A1 US 2002028741 A1 US 2005043496 A1 EP 1355956 A2 JP 2004517933 T WO 02059165 A2 US 2003125485 A1 US 2004158012 A1	11-12-2001 11-12-2001 11-12-2001 11-12-2001 17-06-2003 07-10-2003 06-12-2001 06-12-2001 23-07-2003 24-09-2003 19-03-2003 19-03-2003 12-03-2003 29-01-2004 25-11-2003 25-11-2003 06-12-2001 06-12-2001 06-12-2001 06-12-2001 10-07-2003 10-07-2003 07-03-2002 28-03-2002 14-03-2002 07-03-2002 24-02-2005 29-10-2003 17-06-2004 01-08-2002 03-07-2003 12-08-2004
JP 10007719	A	13-01-1998	NONE	
US 5175326	A	29-12-1992	US 4906754 A US 5030606 A US 4698403 A CA 1280250 C	06-03-1990 09-07-1991 06-10-1987 12-02-1991
WO 9958578	A	18-11-1999	AU 3834299 A	29-11-1999

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US2004/040677

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9958578	A	CN 1308641 A EP 1084154 A1 WO 9958578 A1 US 6555636 B1	15-08-2001 21-03-2001 18-11-1999 29-04-2003
WO 9504759	A	16-02-1995 AU 7270494 A DE 69409244 D1 EP 0714416 A1 WO 9504759 A1 US 5602220 A	28-02-1995 30-04-1998 05-06-1996 16-02-1995 11-02-1997