

Abstract

Thermoplastic elastomer composition, stopper for medical container, and medical container

This thermoplastic elastomer composition comprises: 100 parts by mass of a hydrogenated block copolymer (a); from 3 to 50 parts by mass of a polypropylene-based resin (b); from 5 to 100 parts by mass of a polyphenylene ether resin (c); and from 50 to 200 parts by mass of a non-aromatic softener (d), the hydrogenated block copolymer (a) is able to be formed by hydrogenating a block copolymer that comprises at least one polymer block A comprising a vinyl aromatic hydrocarbon compound monomer unit as a primary component and at least one polymer block B comprising a conjugated diene compound monomer unit as a primary component, and a weight average molecular weight of the hydrogenated block copolymer (a) is from 100,000 to 350,000.