

ABSTRACT

Ni alloy or Cu alloy containing P and /or B is plated on a base metal consisting of Cu or Cu alloy as an intermediate layer, Sn or Sn alloy is further plated on the surface thereof, then the content of P or B in the plating layer is limited by carrying out reflow treatment, whereby, heat resistance and insertion and withdrawal properties are improved.