

PROCESS FOR MANUFACTURING A COMPOSITION COMPRISING RECYCLED PET BY CONTROLLED COOLING

Field of the invention

5

The present invention relates to a process for manufacturing a shaped article from a composite material comprising a solid filler and a thermoplastic binder. The shaped article according to the present invention can conveniently be used as decoration elements, e.g. plates or slabs, which can for example very suitably be used in construction of floors, ceilings, wall panels, vanity tops, kitchen work surfaces or kitchen tops, bathrooms, internal and external cladding and other two-dimensional shapes by extrusion and or injection moulding techniques.

Background of the invention

15

Polymers and blends thereof with appropriate components have been used for many years as a staple material for the manufacture of short-life consumer goods such as drink bottles and food containers. However, due to their low biological degradability, such polymers and blends thereof are of great concern to the environment. Recycling of such polymers and blends thereof into valuable end-use products is therefore highly desirable.

WO 02/090288, incorporated by reference herein, discloses a process for the preparation of a composition comprising a matrix of solid particles and 1 - 50 wt.% of a binder, wherein the binder comprises an optionally recycled thermoplastic polymer, preferably selected from the group consisting of polyethylene, polypropylene, polyethylene terephthalate, polybutylene terephthalate and mixtures thereof. It is preferred that the binder comprises recycled polyethylene terephthalate, preferably as a major component (70 - 90 wt.%, preferably 80 - 85 wt.%), even more preferably in combination with recycled polypropylene (10 - 30 wt.%, preferably 15 - 20 wt.%).

According to the process disclosed in WO 02/090288, the solid particles and the binder are heated independently (the solid particles being heated to a higher temperature than the binder) and are subsequently mixed at a temperature of 230° to 300°C. Mixing of the filler and the binder is performed in a conventional mixing device comprising a

stirrer or in an extruder. Optionally, a flux oil or an organic solvent is added to reduce the viscosity of the mixture. The mixture is then formed or shaped and subsequently cooled. However, the method according to WO 02/090288 has several disadvantages leading to products having inferior properties. For example, Example 14 of WO 02/090288 discloses that when the mixing is performed in a twin-screw extruder and the mixture is shaped into a construction element followed by slow cooling ("cooled in the open air"), the construction element showed shrinkage cracks which is undesirable when it is intended for the construction of end-use products requiring a highly aesthetic appearance, e.g. floors, kitchen work surfaces or kitchen tops. WO 02/090288 further discloses that cooling can conveniently be conducted rapidly, preferably by quenching with e.g. water, which would likely result into poor mechanical properties.

WO 96/02373, incorporated by reference, discloses a method of manufacturing a multi-purpose building material from domestic waste, industrial waste or a combination thereof, wherein a waste material having a plastics material content of 20 wt.% to 65 wt.% is sheared to particles having a diameter 50 mm or less, subsequently mixed with a particulate filler at a temperature of 120° to 200°C until a uniform mixture is obtained and finally formed into a final product. WO 96/02373 does not provide details about cooling of the final product.

GB 2396354, incorporated by reference, discloses a method for manufacturing bulk products from plastics material comprising mixing plastic particles having a mean diameter of 10 mm or less in a mixing vessel while simultaneously feeding finely divided filler material. Subsequently, a first portion of the mixture of plastic material and filler material is separated and cooled, then blended with the further heated mixture of plastic particles and filler material, and finally the blended material is shaped into a product. GB 2396354 does not disclose further details of the cooling of the shaped product.

US 6.583.217, incorporated by reference, discloses a process for making a composite material from waste, chemically unmodified polyethylene terephthalate and 50 - 70 wt.% of fly ash particles, wherein the waste, chemically unmodified polyethylene terephthalate and fly ash particles are first mixed (i.e. unheated) and then heated to about 255° to about 265°C (but not higher than about 270°C to prevent decomposition of the waste, chemically unmodified polyethylene terephthalate) to melt the waste, chemically unmodified polyethylene terephthalate. The mixture is then

shaped into a construction element and cooled. US 6.583.217 addresses the importance of moulding temperatures and cooling rates for mechanical properties without, however, providing further details: the general method involves pouring the mixture into a mould and allowing the moulds to cool to ambient temperature in approximately
5 two hours (irrespective the size and shape of the mould).

US 2003/0122273, incorporated by reference, discloses a process for making a composite material from a filler and a thermoplastic binder, wherein the binder is an asphaltene-containing binder having a penetration of less than 15 dmm. The mixture is then formed by compaction into the end-product which is subsequently cooled under
10 either ambient conditions (for hours to days) or by quenching with e.g. water (that is, by immersion into a water bath or by drenching in water sprays).

US 6.472.460, incorporated by reference, discloses a method for producing a polymeric composite material comprising melt-kneading an organophilic clay and a polymer under certain process conditions including (a) pressure and (b) total shear
15 strain and/or total shear energy per unit volume. According to the examples, about 2 wt. % of the organophilic clay C12-Mt or C18-Mt is mixed with a nylon resin. US 6.472.460 discloses that the polymer composite material may be subjected to a moulding process without specifying any further details with respect to cooling.

US 6.521.155, incorporated by reference, discloses a process for manufacturing a
20 plastic pipe from recycled polyethylene terephthalate and a filler, wherein a mixture of the recycled polyethylene terephthalate and the filler, the filler being added in an amount of 2 – 60% by weight, are kneaded to form a homogeneous, substantially moisture free process viscous mixture. The mixture is fed to an extruder, where after the extruded mixture is fed to a corrugators while cooling at a temperature gradient of -
25 10°C/min to -50°C/min.

Consequently, there is still a need in the art to provide an efficient process for mixing relatively high amounts of solid filler particles and relatively low amounts of thermoplastic binders into a composite material and to convert this composite material into a shaped article having a highly aesthetic appearance, in particular a reduced
30 number of cracks.

Summary of the invention

The present invention relates to a process for manufacturing a shaped article from a composite material comprising a solid filler and a thermoplastic binder, said process comprising the following subsequent steps:

- (a) feeding a solid filler and a thermoplastic binder to a mixing device;
- (b) mixing the solid filler and the thermoplastic binder in the mixing device to obtain a composite material;
- (c) forming the composite material as obtained in step (b) into a shaped article; and
- (d) cooling the shaped article as obtained in step (c), wherein the shaped article is cooled at a cooling rate of at least about 35°C/min to about 100°C/min.

It is preferred that the process according to the present invention is a continuous process.

The present invention also relates to a shaped article as can be obtained by steps (a) – (d) of the process.

The present invention further relates to the use of the composite material for the manufacture of shaped articles, in particular floors, floor tiles, ceilings and ceiling tiles, wall panels, vanity tops, kitchen work surfaces, kitchen tops, bathrooms, internal and external cladding and other two-dimensional shapes by extrusion and or injection moulding techniques.

The present invention also relates to the use of the composition material for constructing floors, floor tiles, ceilings and ceiling tiles, wall panels, vanity tops, kitchen work surfaces, kitchen work tops, bathrooms, internal and external cladding and other two-dimensional shapes by extrusion and or injection moulding techniques.

Detailed description of the invention

Definitions

The verb “to comprise” as is used in this description and in the claims and its conjugations is used in its non-limiting sense to mean that items following the word are included, but items not specifically mentioned are not excluded. In addition, reference to an element by the indefinite article "a" or "an" does not exclude the possibility that

more than one of the element is present, unless the context clearly requires that there is one and only one of the elements. The indefinite article "a" or "an" thus usually means "at least one".

In this document, the term "recycled polyethylene terephthalate" is used to indicate material originating from packaging applications, e.g. beverage bottles and food containers, comprising polyethylene terephthalate and optionally other polyesters and non-polyethylene terephthalate components such as remnants of paper labels, glues, inks and pigments, polypropylene caps and aluminium caps. The packaging applications may also have multilayered structures. They may further include ethylene vinyl acetate (EVA), nylon and other polyamides, polycarbonate, aluminium foil, epoxy resin coatings, polyvinyl chloride (PVC), polypropylene, LDPE, LLDPE, HDPE, polystyrene, thermosetting polymers, textile, and mixtures thereof. Such packaging applications may also comprise recycled (polymeric) materials. Consequently, in this document, the term "recycled polyethylene terephthalate" is preferably a material comprising about 90 wt.% to about 100 wt.% of polyethylene terephthalate and about 0 wt.% to about 10 wt.% of non-polyethylene terephthalate components, based on the total weight of the material, wherein the fraction of non-polyethylene terephthalate components preferably comprises about 0.001 wt.% to about 10 wt.%, more preferably about 0.001 wt.% to about 5 wt.% of non-polymer components, based on the total weight of the fraction of non-polyethylene terephthalate components.

The term "modified polyethylene terephthalate" is also well known in the art and refers to copolymers of ethylene glycol and terephthalic acid which further comprise monomers such as isophthalic acid, phthalic acid, cyclohexane dimethanol and mixtures thereof.

The term "ambient temperature", although well known to the person skilled in the art, is herein defined as a temperature of about 15°C to about 40°C.

The thermoplastic binder

According to the present invention, the thermoplastic binder comprises about 60 wt.% to about 100 wt.% of a thermoplastic polyester, based on the total weight of the binder. Preferably, the thermoplastic binder comprises about 75 wt.% to about 100 wt.% of a thermoplastic polyester, more preferably about 75 wt.% to about 90 wt.%

and in particular about 80 wt.% to about 85 wt.% of the thermoplastic polyester. The thermoplastic polyester is preferably selected from the group of, optionally modified, optionally recycled polyethylene terephthalate and polybutylene terephthalate. The thermoplastic polyester is most preferably recycled polyethylene terephthalate. The thermoplastic polyester has preferably an intrinsic viscosity in the range of about 0.50 dl/g to about 0.90 dl/g, more preferably about 0.60 dl/g to about 0.85 dl/g, most preferably about 0.70 dl/g to about 0.84 dl/g, at 25°C according to ASTM D 4603.

The thermoplastic binder according to the present invention comprises about 0 wt.% to about 40 wt.% of a polyolefin, preferably about 0 wt.% to about 25 wt.%, more preferably about 10 wt.% to about 25 wt.%, and in particular about 15 wt.% to about 20 wt.%, based on the total weight of the thermoplastic binder.

The polyolefin is preferably selected from polyolefins based on linear or branched C₂ - C₁₂ olefins, preferably C₂ - C₁₂ α-olefins. Suitable examples of such olefins include ethylene, propylene, 1-butene, 2-butene, isobutene, 1-pentene, 1-hexene, 1-octene and styrene. The polyolefins optionally comprise a diolefin, e.g. butadiene, isoprene, norbornadiene or a mixture thereof. The polyolefins may be homopolymers or copolymers. Preferably, the polyolefins are selected from the group consisting of polyolefins comprising ethylene, propylene, 1-hexene, 1-octene and mixtures thereof. Additionally, the polyolefins may be essentially linear, but they may also be branched or star-shaped. The polyolefins are more preferably selected from polymers comprising ethylene, propylene and mixtures thereof. Even more preferably, the polyolefin is a propylene polymer, in particular a polypropylene. Preferably the density of the polyolefin is in the range of about 0.90 kg/dm³ to about 0.95 kg/dm³ according to ASTM D 792. Preferably, the melt flow rate of the propylene polymer is about 0.1 g/10 min (230°C, 2.16 kg) to about 200 g/10 min (230°C, 2.16 kg) according to ASTM D 1238.

According to the invention, the thermoplastic binder can be used in the form of grinded or milled particles having a maximum weight of 1 gram. It is, however, preferred that the thermoplastic binder is used in the form of flakes having preferably a size of about 2 - 10 mm by about 2 - 10 mm (about 0.5 mm to about 3 mm thickness).

The solid filler

As the solid filler, different materials may be used. Suitable examples include mineral particles, cement particles, concrete particles, sand, recycled asphalt, recycled
5 crumb rubber from tyres, clay particles, granite particles, fly ash, glass particles and the like. Preferably, the solid filler is a calcite based material which may be of natural or synthetic origin (such as marble) and/or a silica based material (such as quartz). Optionally, the solid filler may be constituted from different sources having different particle size distributions. However, it is preferred that that the maximum average
10 particle size is 1.2 mm or less and that the minimum average particle size is 3 μm or more.

Mixing step

15 The mixing process according to step (b) of the process according to the present invention may be performed in any suitable mixing device or in a plurality of mixing devices. If several mixing devices are used, they may differ from each other and they do not need to be identical. Suitable mixing devices include batch mixing devices, extruders (e.g. single-screw, double screw) and kneading devices which are all known
20 in the art. It is, however, preferred to employ a mixing device that enables continuous operation of the process according to the present invention. Consequently, extruders and kneading devices are preferred mixing devices for the process according to the present invention.

According to the present invention, in step (a) the solid filler and the
25 thermoplastic binder are fed to the kneading device in a weight ratio of about 1 : 1 to about 20 : 1. Preferably, this weight ratio is about 2 : 1 to about 15 : 1, more preferably about 4 : 1 to about 10 : 1. Since the thermal conductivity of the thermoplastic binder is far less than that of the solid filler, low binder level increases the thermal conductivity of the composite material and of the shaped article thereby reducing internal stresses in
30 the latter. In addition, the cooling process can be better controlled at higher thermal conductivity of the composite material and of the shaped article manufactured thereof.

When the solid filler and/or the thermoplastic binder are fed to the mixing device (in step (a) of the process according to the present invention), the solid filler, the

thermoplastic binder or both may optionally be subjected to a pre-heat step as is for example disclosed in WO 02/090288, incorporated by reference. However, they may also be fed without a pre-heat step, i.e. that the solid filler and/or the thermoplastic binder are around ambient temperature when fed to the mixing device.

- 5 Furthermore, step (b) of the process according to the present invention is performed at a temperature of about 230° to about 350°C, more preferably at a temperature of about 270° to about 320°C.

Compaction

10

In extruders, mixing and compaction may occur within the same device. On the other hand, the use of a kneading device enables to perform compaction in a separate, distinct step. Accordingly, the step (b) of the process of the present invention may optionally comprise a compaction step which may be conducted simultaneously with or
15 subsequently after the mixing step.

Preferably, the compaction step is performed in a conveying extruder which is operated at a pressure of about 5×10^3 kPa to about 5×10^4 kPa, more preferably of about 10^4 kPa to about 3×10^4 kPa.

20 Forming

- The forming step may also be conducted with devices known in the art, e.g. by compression moulding, wherein the composite material is loaded into a mould and the shaped article is formed under a load, by injection moulding, or by extrusion, wherein
25 the material is pressed through a die into the desired shape, and a knife is used to dimension the shaped article to the desired length. The latter method is in particular advantageous when the shaped article is a wall panel, a vanity top, a kitchen work surface or a kitchen top.

30 Cooling step

It was surprisingly found that cooling conditions had a significant impact on important properties of the shaped article according to the invention as produced along

conventional process conditions. In addition, prior art processes suffered from the disadvantage that they are not very efficient, in particular because these processes make use of moulding steps to form the shaped article. Hence, the shaped article could only be manufactured batch wise, whereas continuous manufacturing would be highly desirable for efficiency and consistency of product quality.

It appeared that, in particular when the shaped article is a slab, mechanical properties could be greatly improved by applying certain stringent cooling conditions and/or by using particular cooling devices. In particular, it appeared that cooling the upper surface and the bottom surface of the slab provided improved properties, e.g. less warping, higher flexural strength, higher compression strength and less surface cracks.

According to the present invention, the cooling rate is preferably at least about 5°C/min to about 120°C/min, more preferably at least about 7°C/min to about 100°C/min, and most preferably at least about 10°C/min to about 80°C/min.

According to the invention, the slab has preferably a thickness of about 0.3 cm to about 5 cm, more preferably about 0.5 cm to about 3.0 cm and in particular about 0.5 cm to about 2.5 cm. Furthermore, it is preferred that the slab has an average thickness of about 2.5 mm to about 50 mm, more preferably 3.0 mm to about 30 mm.

Desired properties, e.g. warping, strength and the number of surface cracks, could be further improved by performing step (d) by belt cooling.

Belt cooling such as single belt and double belt cooling, is well known in the art and is often used in the steel industry. However, steel has very different properties and must fulfil other requirements than the composite material according to the present invention.

Belt cooling is operated as follows. The shaped article to be cooled is loaded on a belt, usually made of steel. Since steel has an excellent thermal conductivity, heat can be dissipated quite rapidly. The rate of heat dissipation can be controlled by e.g. the run speed of the belt. The belt itself is cooled by external sources, e.g. sources spraying water and/or air against the belt. Preferably, when water is used as coolant, there is no contact between the shaped article and the cooling water. The cooling water can optionally be collected and, after cooling to the desired temperature, be recycled into the cooling process. It is therefore preferred that the cooling is achieved by using air, water or a combination thereof.

According to the present invention, the belt cooling can be performed by single belt cooling or double belt cooling, wherein one or more single belt cooling devices and/or one or more double belt cooling devices are used, respectively. Optionally, the cooling system may comprise a combination of one or more single belt cooling devices and one or more double belt devices. However, according to the present invention, it is preferred that at least a double belt cooling device is used.

Double belt cooling has as one advantage that the shaped articles can be produced with increased capacity, as the product is in contact with two cooling belts. Another important advantage is that the whole cooling process can be better controlled. Furthermore, double belt cooling provides more flexibility with respect to the thickness of the shaped article, i.e. that thicker articles can be cooled at about the same efficiency as less thicker products can be cooled on a single belt device.

In a double belt cooling device, the shaped article is fed onto the upper surface of the lower belt which transports it to the cooling zone or cooling zones, where the pressure of the upper belt ensures essentially constant contact with the surfaces of both the lower belt and the upper belt thereby providing an efficient and controlled cooling of the shaped article.

According to the present invention, it is preferred that the amount of energy per weight equivalent withdrawn from the shaped article during step (d) is about 100 kJ/kg to about 250 kJ/kg, more preferably about 150 kJ/kg to about 200 kJ/kg. The amount of energy withdrawn from the shaped article is calculated as the ratio of the cooling power of the cooling device (in kW) and the throughput of the shaped article or shaped articles (in kg/s; mass flow) and is therefore expressed as kJ/kg. Hence, the amount of energy is related to the weight (in kg) of the shaped article to be cooled.

In cooled shaped articles, the stress distribution is dependent from the well known Biot number. The Biot number (Bi) is a dimensionless number which is used in unsteady-state (or transient) heat transfer calculations and it relates to the heat transfer resistance inside and at the surface of the shaped article. The Biot number (dimensionless) is defined as:

$$Bi = \frac{Hd}{L}$$

wherein H is the heat transfer coefficient at the surface of the shaped article (in $\text{W/m}^2\cdot\text{K}$), $2d$ is the thickness of the shaped article (or characteristic length which is the ratio of the volume of the shaped article and the surface area of the shaped article; in m) and L is the heat conductivity of the shaped article (in $\text{W/m}\cdot\text{K}$). When the Biot number is (substantially) higher than 10, the number of internal stresses increases significantly which is obviously undesired for shaped articles (in particular slabs) according to this invention. Consequently, according to the present invention, it is preferred that the Biot number is less than about 10, more preferably less than about 5. However, if the Biot number is much less than 0.1, the heat transfer within the shaped article is much greater than the heat transfer from the surface of the shaped article (which implies that there are hardly any temperature gradients within the shaped article). Hence, according to the present invention it is preferred that the Biot number is about 0.1 or higher, preferably about 0.2 or higher.

15 Composite material

According to the present invention, the density of the composite material is preferably about $1.5 - 3 \text{ kg/dm}^3$, more preferably about $2.0 - 2.5 \text{ kg/dm}^3$.

20 Shaped article

The shaped articles according to the present invention have several important features. For example, they are characterised by a high alkali resistance making them very suitable for constructing floors, kitchen work surfaces and kitchen tops. The shaped articles also have good mechanical properties. In particular, it is preferred that the shaped article has a flexural strength of at least about 40 N/mm^2 according to test method NEN EN 198-1. In addition, it is preferred that the compression strength is at least about 50 N/mm^2 according to test method NEN EN 196-1.

The shaped articles according to the present invention also show low thermal expansion, very little warping and low brittleness. For example, US 6.583.217, incorporated by reference herein, discloses that shaped articles made from composite materials consisting of recycled PET and fly ash showed a shrinkage of 2.2% (100 wt.% recycled PET) to 0.7 wt.% (30 wt.% recycled PET, 70 wt.% of fly ash). In

contrast, it was found that shrinkage of the shaped articles manufactured according to the process of the present invention was virtually independent from thermoplastic binder content.

5 The shaped articles may further comprise other additives commonly used in engineering stone products, e.g. pigments, colorants, dyes and mixtures thereof. The maximum amount of such additives is preferably less than about 5 wt.%, based on the total weight of the shaped article.

10 It is furthermore preferred that the shaped article is a slab, wherein the average thickness of the slab is about 2.5 mm to about 50 mm, more preferably about 5.0 mm to about 30 mm.

Examples

Example 1

15 Recycled PET and silica (average diameter about 0.25 mm) in a weight ratio of 15 wt.% to 85 wt.% was processed in a single-screw kneader (Buss MDK 140; L/D = 11; shear rate 450 s^{-1} , residence time approximately 1 minute; 400 kPa maximum pressure) at a temperature of 310°C . The mixture of recycled PET and silica was
20 transferred through a die (270°C) to form slabs of 800 mm by 800 mm (thickness 25 mm). The slabs were cooled on a double belt cooling device (throughput 600 kg/h; cooling power 29 kW; amount of energy per weight equivalent withdrawn from the shaped article is 174 kJ/kg). Excellent slabs showing no surface cracks were obtained.

25 Example 2

Example 2 was repeated with marble as filler material. Excellent slabs showing no surface cracks were obtained.

30 Comparative Example 1

A slab was manufactured according to Example 14 of WO 02/090288. However, final slab showed shrinkage cracks (cf. Figure 1).

Example 3

Recycled PET and marble quartz (average particle diameter about 0.5 mm) in a weight ratio of 23 wt.% to 77 wt.% was processed in a single-screw kneader (Buss MDK 140; L/D = 11; shear rate (max) 450 s^{-1} ; residence time approximately 1 minute; 400 kPa maximum pressure) at a temperature of 300°C . The viscosity of the mixture was about 1700 Pa.s. The mixture of recycled PET and marble quartz was fed through a 15 mm die thereby producing a plate having a thickness of about 15 mm which was transferred to a cooling belt (Sandvik type DBU; temperature at the start of the cooling belt was about 270°C , temperature at the end of the cooling belt was about 100°C ; length of the cooling belt was 8 m; cooling rate was about $13^{\circ}\text{C}/\text{min}$). The amount of energy per weight equivalent withdrawn from the plate during step (d) of the process was about 180 kJ/kg (the cooling power was 45 kW and the throughput was $900\text{ kg/h} = 0.25\text{ kg/s}$). The Biot number was about 1. The plates showed no surface cracks and were not brittle.

Claims

1. A process for manufacturing a shaped article from a composite material comprising a solid filler and a thermoplastic binder, said process comprising the following subsequent steps:
 - (a) feeding a solid filler and a thermoplastic binder to a mixing device;
 - (b) mixing the solid filler and the thermoplastic binder in the mixing device to obtain a composite material;
 - (c) forming the composite material as obtained in step (b) into a shaped article; and
 - (d) cooling the shaped article as obtained in step (c), wherein the shaped article is cooled at a cooling rate of at least about 5°C/min to about 120°C/min, wherein in step (a) the weight ratio of the solid filler to the thermoplastic binder is about 2 : 1 to about 15 : 1.
2. The process according to Claim 1, wherein the shaped article is a slab.
3. The process according to Claim 2, wherein the slab has a thickness of about 0.3 cm to about 5 cm.
4. The process according to Claim 2 or Claim 3, wherein the average thickness of the slab is about 2.5 mm to about 50 mm.
5. The process according to any one of Claims 2 - 4, wherein the upper surface and the bottom surface slab are cooled simultaneously.
6. The process according to any one of Claims 1 - 5, wherein step (d) is performed by belt cooling.
7. The process according to Claim 6, wherein in step (d) a double belt cooling device is used.
8. The process according to any one of Claims 1 - 6, wherein the amount of energy per weight equivalent withdrawn from the shaped article during step (d) is about 100 kJ/kg to about 250 kJ/kg.
9. The process according to any one of Claims 1 - 7, wherein the Biot number during step (d) is about 0.1 to about 10.
10. The process according to any one of Claims 1 - 8, wherein cooling of the shaped article is achieved by using air, water or a combination thereof.

11. The process according to any one of the preceding claims, wherein in step (a) the solid filler and the thermoplastic binder are fed to the kneading device in a weight ratio of about 1 : 1 to about 20 : 1.
12. The process according to any one of the preceding claims, wherein the
5 thermoplastic binder comprises about 60 wt.% to about 100 wt.% of a thermoplastic polyester, based on the total weight of the binder.
13. The process according to Claim 8, wherein the thermoplastic polyester comprises about 90 wt.% to about 100 wt.% of recycled polyethylene terephthalate.
14. The process according to any one of the preceding claims, wherein the
10 thermoplastic binder comprises about 0 wt.% to about 40 wt.% of a polyolefin.
15. The process according to any one of the preceding claims, wherein step (b) is performed at a temperature of about 230° to about 350°C.