Claims

1. A method of preparing a pharmaceutical composition comprising:

a) coating inert particles with a drug layering composition comprising cyclobenzaprine or a pharmaceutically acceptable salt, solvate, and/or ester thereof, and a pharmaceutically acceptable solvent, thereby forming IR beads; and

b) coating the IR beads with an ER coating composition comprising a pharmaceutically acceptable water-insoluble polymer and a plasticizer under an atmosphere having a dew point ranging from ~~about~~ 5-20ºC, thereby forming ER beads; wherein coating the IR beads with an ER coating comprises stirring a mixture of a pharmaceutically acceptable water-insoluble polymer, plasticizer, and pharmaceutically acceptable solvent for at least 1 hour after adding the plasticizer to the pharmaceutically acceptable water-insoluble polymer and pharmaceutically acceptable solvent; and

c) curing the ER beads at about 60ºC for 4-12 hours under an atmosphere having a dew point ranging from 5-20ºC.

~~2. The method of claim 1, further comprising:~~

~~c) curing the ER beads at about 60ºC for about 4-12 hours under an atmosphere having a dew point ranging from about 5-20ºC.~~

~~3~~2. The method of claim 1, further comprising coating the IR beads of step a) with a seal-coating composition comprising a pharmaceutically acceptable water-soluble polymer before said ER coating step b).

~~4~~3. The method of claim ~~3~~ 2, wherein said inert particles have a particle size of ~~about~~ 20-25 mesh.

~~5~~4. The method of claim ~~3~~ 2, wherein said seal-coating composition further comprises water.

~~6~~5. The method of claim 1, wherein said coating steps a) and b) are carried out under an atmosphere having a dew point ranging from ~~about~~ 5-20ºC.

~~7~~6. The method of claim 1, wherein the pharmaceutically acceptable water-insoluble polymer, plasticizer, and pharmaceutically acceptable solvent are stirred for at least about 3 hours after addition of the plasticizer to the pharmaceutically acceptable water-insoluble polymer and pharmaceutically acceptable solvent.

~~8~~7. The method of claim 1, wherein the drug layering composition comprises cyclobenzaprine hydrochloride and about 50:50 acetone:water.

~~9~~8. The method of claim ~~3~~ 2, wherein the pharmaceutically acceptable water-soluble polymer comprises hydroxypropyl methylcellulose.

~~10~~9. The method of claim 1, wherein the pharmaceutically acceptable water-insoluble polymer is selected from the group consisting of ethylcellulose, ethers of cellulose, esters of cellulose, cellulose acetate, cellulose butyrate, cellulose propionate, polyvinyl acetate, neutral copolymers based on ethyl acrylate and methyl methacrylate, copolymers of acrylic and methacrylic acid esters with quaternary ammonium groups, pH-insensitive ammonio methacrylic acid copolymers, waxes, acetylated polysaccharides, polyurethanes, high molecular weight hydroxypropyl methylcellulose, polyacrylate and polymethacrylate polymers, and mixtures thereof.

~~11~~10. The method of claim 1, wherein the pharmaceutically acceptable water-insoluble polymer comprises ethylcellulose.

~~12~~11. The method of claim 1, wherein the plasticizer is selected from the group consisting of diethyl phthalate, triacetin, tributyl citrate, tri-ethyl citrate, acetyl tri-n-butyl citrate, dibutyl sebacate, polyethylene glycol, polypropylene glycol, castor oil, acetylated mono- and di-glycerides, glyceryl monostearate, glyceryl triacetate, glyceryl tributyrate, phthalates, citrates, glyceroltributyrate; sebacates, adipates, azelates, benzoates, chlorobutanol, polyethylene glycols, vegetable oils, olive oil, castor oil, mineral oil, fumarates, malates, oxalates, succinates, butyrates, cetyl alcohol esters, malonates, polysorbates, glycerine, N-butylbenzenesulfonamide, N-methylpyrrolidone, and mixtures thereof.

~~13~~12. The method of claim 1, wherein the plasticizer comprises diethyl phthalate.

~~14~~13. The method of claim 1, wherein the ER coating composition comprises ethylcellulose and diethyl phthalate dissolved in a solvent comprising acetone and water at a acetone/water weight ratio ranging from ~~about~~ 85/15 to ~~about~~ 98/2.

~~15~~14. The method of claim 1, wherein the ratio of water-insoluble polymer to plasticizer is about 9:1.

~~16~~15. The method of claim 1, wherein the drug layering composition comprises cyclobenzaprine hydrochloride, and after drying, the drug layered beads comprise from ~~about~~ 20 wt.% to ~~about~~ 30 wt.% cyclobenzaprine hydrochloride.

~~17~~16. The method of claim ~~16~~ 15, wherein the drug layering composition comprises cyclobenzaprine hydrochloride, and after drying, the drug layered beads comprise about 25 wt.% cyclobenzaprine hydrochloride.

~~18~~17. The method of claim 1, wherein the IR beads comprise about 2 wt% of the pharmaceutically acceptable water~~-insoluble~~ soluble polymer.

~~19~~18. The method of claim 1, wherein the ER beads comprise ~~about~~ 7 wt% to ~~about~~ 12 wt% of the pharmaceutically acceptable water insoluble polymer.

~~20~~19. The method of claim 1, wherein the ER beads comprise about 9 wt% of the pharmaceutically acceptable water-insoluble polymer and plasticizer.

~~21~~20. The method of claim 1, wherein the ER beads provide a drug release profile that does not deviate by more than about 10 wt% at any time point in the following dissolution pattern:

after 2 hours, no more than about 40 wt% of the total active is released;
after 4 hours, from ~~about~~ 40-65 wt% of the total active is released;
after 8 hours, from ~~about~~ 60-85 wt% of the total active is released; and
optionally after 12 hours, from ~~about~~ 75-85 wt% of the total active is released,

when tested using United States Pharmacopoeia Apparatus 2 (paddles @ 50 rpm) in 900 mL of 0.1 N HCl at 37ºC.

~~22~~21. The method of claim 1, wherein the ER beads provide a drug release of ~~about~~ 20 wt% to ~~about~~ 50 wt% after 2 hours when tested using United States Pharmacopoeia Apparatus 2 (paddles @ 50 rpm) in 900 mL of 0.1 N HCl at 37ºC.

~~23~~22. The method of claim 1, wherein said coating step b) is carried out under an atmosphere having a dew point ranging from ~~about~~ 6-17ºC.

~~24~~23. The method of claim ~~2~~ 1, wherein said curing step c) is carried out under an atmosphere having a dew point ranging from ~~about~~ 6-17ºC.

~~25~~24. The method of claim 1, wherein said coating step a) is carried out under an atmosphere having a dew point ranging from ~~about~~ 6-17ºC.

~~26~~25. The method of claim 1, wherein the pharmaceutical composition comprises 30 mg of cyclobenzaprine HCl and provides a maximum blood plasma concentration (C_{max}) within the range of ~~about~~ 80% to 125% of about 19.9 ng/mL of cyclobenzaprine HCl and an AUC_{0-168} within the range of ~~about~~ 80% to 125% of about 736.6 ng·hr/mL following a single oral administration thereof.

~~27~~26. The method of claim 1, wherein the pharmaceutical composition comprises 15 mg of cyclobenzaprine HCl and provides a maximum blood plasma concentration (C_{max}) within the range of ~~about~~ 80% to 125% of about 8.3 ng/mL of cyclobenzaprine HCl and an AUC_{0-168} within the range of ~~about~~ 80% to 125% of about 318.3 ng·hr/mL following a single oral administration thereof.