(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau

(43) International Publication Date
1 February 2001 (01.02.2001)

PCT

(10) International Publication Number
WO 01/07158 A1

(51) International Patent Classification[7]: B01J 37/00, 37/02, 29/064, 29/42, 29/66, 29/72, C10G 45/64

(21) International Application Number: PCT/EP00/07177

(22) International Filing Date: 25 July 2000 (25.07.2000)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
99305945.0 27 July 1999 (27.07.1999) EP

(71) Applicant: SHELL INTERNATIONALE RESEARCH MAATSCHAPPIJ B.V. [NL/NL]; Carel Van Bylandtlaan 30, NL-2596 HR The Hague (NL).

(72) Inventors: REMANS, Thomas, Joris; Badhuisweg 3, NL-1031 CM Amsterdam (NL). VAN VEGCHEL, Ingrid, Maria; Badhuisweg 3, NL-2501 CH Amsterdam (NL).

(81) Designated States *(national)*: AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.

(84) Designated States *(regional)*: ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:
— *With international search report.*
— *Before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments.*

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

WO 01/07158 A1

(54) Title: METHOD FOR IMPREGNATION OF MOLECULAR SIEVE-BINDER EXTRUDATES

(57) Abstract: Method for impregnating a Group VIII metal on a molecular sieve- binder extrudate wherein the binder comprises a low acidity refractory oxide binder material, which is essentially free of alumina, by: a) contacting the molecular sieve-binder extrudate with an aqueous solution of a corresponding Group VIII metal nitrate salt having a pH of below 8, wherein the molar ratio between the Group VIII metal cations in the solution and the number of sorption sites present in the extrudate is equal to or larger than 1; b) drying the molecular sieve-binder extrudate obtained from step a).