CLAIMS

[Claim 1]

A spun-bonded nonwoven fabric comprising a monocomponent fiber comprising a copolymerized polyester based resin in which 5 weight % or higher and 40 weight % or lower of a polyethylene glycol is copolymerized with a polyester based resin,

wherein the spun-bonded nonwoven fabric has a ΔMR of 0.5 % or higher and 15% or lower,

wherein the number-average molecular weight of the polyethylene glycol is 5,000 or more and 20,000 or less, and

wherein the monocomponent fiber has an average single fiber diameter of 10 μm or more and 15 μm or less.

[Claim 2]

The spun-bonded nonwoven fabric according to claim 1, wherein the polyester based resin is a polyethylene terephthalate.