

1 BONDING OF STEEL STRIPS IN STEEL STRIP LAMINATE PIPE

BACKGROUND OF THE INVENTION


5 High pressure conduits, such as oil and gas pipe lines have generally been constructed with conventional steel pipes. These pipelines are subject to both internal and external pressures. Internal pressure is required to transport the fluid or gases within the pipeline. External pressure is created by the weight of soil or water on the pipeline when the pipeline is embedded in the ground or submerged in water.

10 While steel pipes provide the requisite strength for withstanding the internal and external pressures, they have a high susceptibility to corrosion. A corrosive environment is fostered by contact between the internal foreign media (e.g., the liquids or gases being transported by the pipeline) and the steel, or by contact with external conductive foreign media and the steel. The external foreign media could be soil in cases where the pipe is buried under ground, or sea water in cases where the pipe is submerged in an ocean or water in cases where the pipe runs along
15 sewer systems or exposed to rain. Corrosion decreases the pipe strength and may cause the pipe to leak or burst under pressure.

To overcome this disadvantage, steel reinforced composite pipes have been developed. These pipes have a wall of steel coated with a polymeric material, or of steel embedded in the fiber reinforced composite, such as a fiber glass resin system. The coating or resin system
20 protects the steel from corrosion by shielding it from any contact with the foreign media. One example of steel reinforced composite pipe is disclosed in the Cocks Patent, No. 4,351,364, the subject matter of which is hereby incorporated by reference. The pipe disclosed therein is a structural wall section sandwiched between inner and outer linings. The linings are resin rich layers reinforced with glass or other fibers. The structural wall section is made of three or more
25 structural steel reinforcing layers coated with structural epoxy resin. The individual layers of the pipe are successively built up, one upon the other, on a mandrel or pipe winding machining. Each lining layer is formed by helically winding resin wetted fiber rovings. Each steel layer is formed by helically winding a steel strip coated with resin. The steel layers are wound one on top of the other. Once "wound" the pipe is cured. This type pipe is commonly referred to as steel
30 strip laminate pipe or "SSL pipe".

Typically the desired lap shear strength between overlapping steel layers in SSL pipe is 1800 psi. Such a strength cannot be achieved by adhering one steel layer to the other using only a resin system. In order to achieve such strength, it is common to sandblast the steel prior to winding for forming the steel layers in the pipe.

35 Sandblasting creates a mechanical roughness on the steel providing a stronger mechanical/adhesive bonding. However, this bonding does not have long term durability under wet environments. Testing of a lap shear specimen consisting of sandblasted steel specimens bonded using EPON 826/IPD adhesive showed an 80% lap shear strength loss after 505 hours



1 of hot water exposure. Moreover, the aging of the sandblasted steel surface significantly reduces
lap shear strength due to surface oxidation. Furthermore, sandblasting is a burdensome process.
Typically, a 5000 horsepower air compressor would be required to sandblast production
quantities of steel strips. A special facility would also be needed due to the dusty and noisy
5 nature of sandblasting.

As such, a system is needed for bonding the steel strip formed layers to each other and to
the SSL pipe linings that would avoid the need for sandblasting the steel strips.

It has also been discovered that steel strip layers, bonded to each other with only a resin
have inadequate peel strength. The inadequate peel strength is believed to be caused by a
10 variance in the bond thickness along the length of the steel strip forming the layer. Resin bond
thickness control is typically not very accurate at production speeds.

Glass flake fillers are sometimes used in the resin to improve the shear strength between
steel strips. Typically, glass flake fillers make up about 5 to 10% of the resin by weight.
However, even with the use of glass flake fillers it is difficult to control the bond thickness
15 between the strips at production speeds, thus, resulting in inadequate strip peel strength.

Another problem with the bonding of the steel strips to each other in SSL pipes is cracking
of the resin matrix between the steel strips also resulting in reduction of the peel strength. A
further problem is resin shrinkage which occurs during curing and also results in a decreased
bond strength between the steel strips.

20 SSL pipes are typically subjected to hot and wet conditions and the bond between the steel
layers often fails under a combined mode failure, i.e., a shear/peel-off failure. As such, it is
important that the bonds between the steel layers maintain a significant percentage of their lap
shear strength and peel off strength under hot and wet conditions. Moreover, in order to speed
up the SSL pipe manufacturing process, it is desirable that the debulking time (i.e., the time
25 required to remove excess resin between the steel strips forming the layers to be bonded) of any
resin system used is relatively short so as to reduce manufacturing times and thereby
manufacturing costs.

Thus, a resin system is needed which allows for controlling of the bond thickness between
adjacent steel strip layers and between the steel strip layers and the linings of the SSL pipe at
30 production speeds. Moreover, a resin system is needed with enhanced crack growth resistance
when cured and which is subject to reduced shrinkage during curing. Furthermore, a resin system
providing for improved peel and shear strengths between the steel strips of the SSL pipe in hot
and wet conditions and which allows for reduced debulking times is desired.

35 SUMMARY OF THE INVENTION

To improve the lap sheer strength between the steel layers in SSL pipe, an adhesion
promoter in the form of a sol-gel or an organofunctional silane is used to coat the steel strips
forming the steel layers. In one embodiment, a sol-gel coating is used as the adhesion promoter.

1 Sol is a solution containing partially reacted metal-organic precursors (often a metal-alkoxide
such as $-\text{OSi}(\text{OR})_3$) in a solvent, usually alcohol. R is a nonhydrolyzable organic radical that
possesses a functionality which enables the sol-gel coating to bond with epoxy or other organic
resins. Gel is a substance that contains a continuous solid skeleton enclosing a continuous liquid
5 phase formed by reaction in the sol. Sol-Gel processing involves preparation of a solid, usually
a film or coating, from sol and gel. Typically, sol-gel is formed by hydrolyzing and condensing
the sol solution. Sol-gel coating modified with chromate provides better long-term durability in
a hot and wet environment

10 In another embodiment, the steel strips are coated with an organofunctional or bifunctional
silane. Organofunctional silane such as Y-R-Si-X , silane has two classes of functionality. The
silane portion, Si, bonds to the inorganic substrate i.e., the steel. The bond between R, a bridging
group, and Si is a very stable organic bond, while the bond between X, a hydrolyzable group, and
the silicon atom in silane is a less stable inorganic bond and can be replaced by a bond between
the inorganic substrate (steel) and the silicon atom.

15 Because the SSL pipe bonded steel strip formed layers often fail under a combined mode
failure, i.e., a shear/peel-off failure, it is desirable for the bonded steel layers to maintain their lap
shear strength as well as their peel-off strength under hot and wet conditions. To accomplish this
in a preferred embodiment, the present invention incorporates the use of continuous fiber
reinforced fillers in the resin used to bond the steel strips. These fillers allow for the control of
20 the bond thickness, improve the shear strength of the bond between steel strips, improve the bond
peel strength and reduce resin matrix shrinkage as well as increase the resin matrix resistance to
cracking.

25 Exemplary continuous reinforced fiber fillers are made of Kevlar, carbon, and glass.
These fillers are preferably in the form of veils such as random synthetic veils such as C-glass
veils, and random veils, woven cloths such as boat tape, and roving tapes, unidirectional tapes,
and monofilament meshes.

30 Veils, woven cloths, tapes and meshes are all in "tape" form, i.e., they are in a continuous
layer form. As such, veils, woven cloths, tapes and meshes can be wound over the steel layers.
The veils, woven cloths, tapes and meshes may be impregnated with the appropriate resin prior
to winding around the steel strip pipe layer. Alternatively, resin may be applied on to a steel strip
layer prior to winding the veil, woven cloth, tape, or mesh or the resin may be applied over the
wound veil, woven cloth, tape, or mesh. Moreover, instead of using a veil, woven cloth, tape,
or mesh material, chopped or crushed fibers may be mixed with the resin in an amount yielding
a high fiber content prior to applying the resin over a wound first steel strip layer portion.
35 Alternatively, resin may be applied to the wound steel strip and the crushed or chopped fibers
may be applied over the resin. When using fiber fillers, the preferred fiber filler content is in the
order of 30 to 70% by volume.

1 The fibers in a fiber filler serve as a spacer controlling the spacing between subsequent layers of steel and thereby controlling the bond thickness between the steel layers resulting in an improved peel strength.

5 In an alternate embodiment, instead of a continuous fiber reinforced filler, glass spheres also known as Zeeospheres or microspheres, a discontinuous filler, are used. Due to their spherical shape, Zeeospheres can be densely packed in the resin. Use of continuous fiber reinforced fillers or Zeeospheres in the resin used to bond the steel strips in SSL pipes improves the operating life of the pipe. These fillers can be used to form a resin matrix that is used to bond steel strips that are treated with an adhesion promoter such as sol-gel or silane, or steel strips that are sandblasted or steel strips that are not treated in any way or form.

10 Moreover, instead of applying the adhesion promoter to the steel strips, the adhesion promoter may be mixed in the resin used to bond the strips.

BRIEF DESCRIPTION OF THE DRAWINGS

15 FIG. 1 depicts a schematic of an Fe-O-Si bond formed between a substrate and a sol-gel coating.

FIG. 2 is a graph of test results depicting the effect of hot water exposure on the lap shear strength of bonded steel strips coated with chromium-modified sol-gel and of sandblasted steel strips.

20 FIG. 3 depicts four exemplary structure formulas of a hydrolyzable group.

FIG. 4 depicts three exemplary structure formulas of nonhydrolyzable organic radicals.

FIG. 5 depicts the structure formula for Vinyltriethoxysilane.

FIG. 6 depicts an Si-C bond forming a bridge between an organofunctional silane coating and an epoxy.

25 FIG. 7 is a graph of average lap shear strength at 230° F of bonded steel strips coated with a chromate modified sol-gel and of bonded steel strips coated with an organofunctional silane.

FIG. 8 is a bar graph comparing the lap shear strength of various organofunctional silanes when exposed to hot water at 230°F for different amounts of time.

FIG. 9 is a table showing the abbreviation, chemical name and structure formula of the different components incorporated in the organofunctional silanes being compared in FIG. 7.

30 FIG. 10 is a schematic view of a process for coating a steel strip with an adhesion promoter.

FIG. 11 is a partial side view of a steel strip laminate pipe depicting the various pipe layers.

FIG. 12 is a schematic view of a pinch roll mechanism used in the pipe winding process.

35 FIG. 13 is a graph depicting load-deflection curves for SSL pipes with continuous filler impregnated tape between the steel strips and with Zeeospheres between the steel strips when under parallel plate loading.

FIG. 14 is a table comparing various factors considered in selecting a resin filler.

1 FIG. 15 is a table comparing lap shear strength, peel-off strength and debulking times of strips bonded with resin incorporating different fillers and coated with sot-gel or an organofunctional silane, or sandblasted.

5 FIG. 16 is a bar graph depicting to lap shear strength of steel strips coated with an organofunctional silane and bonded using a resin and different fillers after different times of water exposure at 230°F.

FIG. 17 is a bar graph comparing peel off strength of steel strips bonded using different fillers and exposed to water at 230°F for different times.

10 DETAILED DESCRIPTION

To improve the lap sheer strength between the steel layers in SSL pipe, an adhesion promoter in the form of a sol-gel or an organofunctional silane is used to coat the steel strips forming the steel layers. These adhesion promoters are used in lieu of sandblasting the steel strips. Resin, such as the EPON 826 resin, still needs to be applied to bond the steel strips as it was applied to bond the steel strips when sandblasted.

15 In one embodiment, a sol-gel coating is used as an adhesion promoter. Sol is a solution containing partially reacted metal-organic precursors (often a metal-alkoxide such as $-\text{OSi}(\text{OR})_3$ or $\text{ROSi}(\text{OC}_x\text{H}_{2x+1})_3$) in a solvent, usually alcohol. R is an organic radical that possesses a functionality which enables the sol-gel coating to bond with epoxy or other organic resins. Gel is a substance that contains a continuous solid skeleton enclosing a continuous liquid phase formed by reaction in the sol. Sol-gel processing involves preparation of a solid, usually a film or coating. Typically, sol-gel is formed by hydrolyzing and condensing the sol solution.

20 Applicants have discovered that the sol-gel coating modified with chromate provided better long-term bond durability in a hot and wet environment. Typically, the chromate is introduced in a primer. The primer is then mixed with the sol-gel solution.

25 In a first embodiment, the steel strips are coated with sol-gel. In an alternate embodiment, the strips may be coated with a sol solution and allowed to undergo hydrolysis and condensation to form a coating of sol-gel on the strips. Once a sol-gel coating is applied or formed on the strip, an Fe-O-Si bond forms between the substrate (steel) and the sol-gel coating in the sequence shown in FIG. 1. The bridge between the sol-gel coating and an epoxy, such as a resin, is an Si-O-R bond shown in FIG. 1. The bridge between the sol-gel coating and the epoxy used to bond the steel in the interpenetrate network (IPN) formed by the Si-O-R bond.

30 Applicants further discovered that use of a sol-gel coating as an alternative surface treatment to sandblasting the steel strips provides for an improved bonding of the steel strips. For example, the lap shear strength of chromium modified sol-gel coated SSL pipe steel strips bonded using EPON 826/IPD is about 40% higher than the lap shear strength of sandblasted, not coated, strips using the same resin at 230°F (FIG. 2). It should be noted that although testing

1 was performed on specimens bonded with EPON 826/IPD resin. the present invention is not limited to steel strips that are bonded with EPON 826/IPD resin. other resins may also be used.

Through testing, applicants also discovered that the lap shear strength of chromium modified sol-gel coated steel strips bonded with EPON 826/IPD resin at 230°F after 500 hours
5 of hot water exposure is about four times of that sandblasted steel strips bonded with the same resin under the same conditions as shown in FIG. 2.

In another embodiment, a steel strip is coated with an organofunctional silane. Organofunctional silane such as $Y-R-Si-X_3$ silane or $Y-(CH_2)_n-Si-X_3$ has two classes of functionality, i.e., it is a bi-functional silane. The silane portion, Si, bonds to the inorganic
10 substrate i.e., the steel. The bond between R or $(CH_2)_n$ a bridging group, and Si is a very stable organic bond, while the bond between X, a hydrolyzable group, and the silicon atom in silane is a less stable inorganic bond and can be replaced by a bond between the inorganic substrate (steel) and the silicon atom. Typical hydrolyzable groups X include but are not limited to alkoxy, acyloxy, amine, methoxy, ethoxy and Chlorine. Four exemplary structure formulas of the
15 hydrolyzable group X are presented in FIG. 3. The organofunctional group, Y, is a nonhydrolyzable organic radical that possesses a functionality, which bonds or interacts with organic resins such as epoxy which are typically used to bond the steel strip. Exemplary nonhydrolyzable organic radicals include glycidoxy and amino. Some exemplary nonhydrolyzable organic radical structure formulas are shown in FIG. 4. The bridge between the
20 organofunctional silane coating and an epoxy (e.g., resin) is Si-C bond as shown in FIG. 6. With some organofunctional silanes such as Vinyltriethoxysilane having the formulas shown in FIG. 5, the same group $-CH=CH_2$ (vinyl) forms both the bridging group and the organofunctional group. Organofunctional silane when used as an adhesion promoter can improve the wet/dry/thermal adhesion to a wide range of substrates.

25 Moreover, applicants have discovered that the use of organofunctional silane as the surface treatment instead of sol-gel modified with Chromate produced a lap shear strength of about 10% higher at 230°F without hot water exposure and about 25% and 40% higher at 230°F after 100 and 400 hours of hot water exposure, respectively as shown in FIG. 7.

Exemplary organofunctional silanes and their relative strengths under hot wet conditions
30 are depicted in FIG. 8. As can be seen from the legend in FIG. 8, these silanes contain a percentage of one or more of γ -Mercaptopropyltrimethoxysilane (MPS), γ -Glycidoxypropyltrimethoxysilane (GPS), γ -Tetraethoxysilane (TEOS), γ -Aminopropyltriethoxysilane (APS), and Bis-1,2-(triethoxysilyl)ethane (BTSE). The structure formulas for MPS, GPS, TEOS, APS, and BTSE are shown in FIG. 9.

35 A process has been developed by applicants that can coat the steel strips with sol-gel or an organofunctional silane at a speed as high as 50 ft/min. Steel in strip form is typically delivered coated with shipping oil. The inventive process involves the rolling of the steel strip 11 through a washing box 10 containing a washing solution for washing and removing the oils

1 and dirt from the steel (FIG. 10). The steel strip is then rolled through a rinsing box 12
containing a rinsing solution for rinsing the washing solution off the steel strip. The steel strip
is then rolled through an air knife 14 which in essence "scrapes" any fluids such as rinsing fluids
off the strip. The strip is then rolled through a tank 16 containing sol-gel or silane. The strip is
5 immersed into the sol-gel or silane. From there, the strip is guided through a drying box 18
where the sol-gel or silane is dried onto the steel strip surfaces. The steel strip then proceeds
through another air knife 20 which "scrapes" the excess sol-gel or silane off the steel strip
surfaces leaving a layer of silane or sol-gel on either surface of the steel strip having a
predetermined thickness. From there, the strip is rolled into a roll 22 and is ready to be used in
10 the pipe winding process.

In an alternate embodiment, the sol-gel or organofunctional silane coating is mixed in with
the resin that is used to bond the steel strips. In order to obtain a good bond between the strips
when mixing the sol-gel or silane with the resin, the steel strips should be thoroughly cleaned.

Because the SSL pipe bonded steel strip formed layers often fail under a combined mode
15 failure, i.e., a shear and peel-off failure, it is desirable for the bonded steel layers to maintain
their lap shear strength as well as their peel-off strength under hot and wet conditions. To
accomplish this, in a preferred embodiment the present invention incorporates the use of
continuous fiber reinforced fillers in the resin used to bond the steel strips and consequently,
the steel strip layers. These fillers allow for the control of the bond thickness, improve the
20 shear strength of the bond between steel strips, improve the bond peel strength, reduce resin
matrix shrinkage, and increase the resin matrix resistance to cracking.

Exemplary continuous reinforced fiber fillers are made of Kevlar, carbon, and glass.
These fillers are preferably in the form of veils e.g., random synthetic veils such as C-glass veils
and the random veils manufactured by Reemay and Freudenberg; woven cloths such as boat
25 tape, and roving tapes; unidirectional tapes; and monofilament meshes such as those
manufactured by Marquisette and Textie.

Veils are formed using chopped fibers which overlap each other and whose ends may be
fused or bonded together. C-glass veils for example, consist of chopped glass fibers which are
bonded together using a starch binder. Because the fibers are fused or bonded together, veils,
30 function and are deemed as continuous fiber reinforcement fillers. Veils typically cost less than
woven clothes which are formed by weaving fibers. Monofilament mesh is typically priced
similarly to the veils.

Veils, woven cloths, tapes and meshes are all in "tape" form, i.e., they are in a
continuous layer form and are referred to herein for convenience as "continuous fiber filler".
35 As such, continuous fiber filler can wound over the first steel layer formed by winding a steel
strip. The continuous fiber filler is preferably impregnated with the appropriate resin prior to
winding around the steel strip pipe layer. This can be accomplished by impregnating with resin
at the pipe manufacturing site or by acquiring the continuous fiber filler in pre-impregnated

1 form, i.e., by acquiring the continuous fiber filler already pre-impregnated with the appropriate
resin. Alternatively, resin may be applied on to the steel strip layer prior to winding the
continuous fiber filler or the resin may be applied over the wound continuous fiber filler. The
5 fiber filler content for continuous fiber filler is typically in the order of 30 to 70% of the total
fiber and resin combination volume. However, a high fiber filler content, e.g., a fiber filler
content at the higher end of this range or greater is preferred.

The fibers serve as a spacer controlling the spacing between subsequent layers of steel
and thereby controlling the bond thickness between the steel layers resulting in an improved
10 peel strength. The continuous fiber filler impregnated with resin can be wound simultaneously
with the steel layers at high speeds, allowing for higher production speeds (since the winding
process will not have to be stopped for the application of resin between the strips) while
providing a consistent bond thickness throughout the layers.

In a preferred embodiment, the impregnated continuous fiber filler is wound over the
inner lining 40 of an SSL pipe on a mandrel 42 simultaneously with the steel strips for forming
15 the SSL pipe. Preferably, the SSL pipe inner lining, steel strips, impregnated continuous fiber
filler and outer lining are wound relatively simultaneously. For example, in forming an SSL
pipe having three steel layers, the winding of the inner lining over the mandrel is first initiated.
As the inner lining 40 is being wound, the winding of the first steel strip 44 over a wound
portion of the inner lining is begun, followed by the winding of a first impregnated continuous
20 fiber filler 46 over the wound portion first steel strip 44, followed by the winding of the second
steel strip 48 over the wound portion of the first continuous fiber filler 46, followed by the
winding of a second impregnated continuous fiber filler 50, followed by the winding of a third
steel strip 52, followed by the winding of the pipe outer lining 54 over the wound portion of the
third steel strip 50. In this regard, the entire thickness of the pipe is wound as the winding
25 proceeds along the length of the mandrel in the direction shown by arrow 56 in FIG. 11. To
improve the winding process, the steel strips are preformed to be predisposed to helical
winding.

During winding of the pipe a pinch roll is used to apply a normal force on the wound
steel strip so as to remove excess resin between the strips forming adjacent steel layers or
30 between the strip and a pipe lining so as to better control the bond thickness. The normal force
applied by the pinch roll causes the excess resin underneath a steel strip to be removed from a
free edge of the strip. Furthermore, the normal force applied by the pinch roll enhances the
bond between the resin and the steel strip or the resin and the adhesion promoter coating on the
steel strip by creating higher surface contact loads.

35 The entire SSL winding process can be automated as shown in FIG. 12. There, a first
steel layer 78 is formed by winding a steel strip over a lining formed on a mandrel. A
continuous fiber filler 70 is then drawn from a drum 72 through an impregnation bath 74
containing resin (FIG. 12). The impregnated continuous fiber filler is then helically wound over

1 the mandrel 76 used in forming the pipe. A second steel strip 78A is helically wound over the impregnated continuous fiber filler over the mandrel. The steel strip is drawn from a drum 79.

5 In the preferred embodiment, an automated process is used to wind multiple steel strips over the mandrel simultaneously in lagging order. In other words, the winding of the first strip is begun first, followed by the winding of the second strip, and so forth. For example, a steel strip 78 may be drawn from drum 79 and another steel strip 78A may be drawn from a drum 79A as shown in FIG. 12. In this regard, the entire pipe can be wound in a single pass, thereby reducing the time required to form the pipe. Four strips from four different drums have been wound simultaneously by the applicants in forming SSL pipes. Applicants are currently planning to use ten strips from ten different drums simultaneously to wind a pipe.

10 A pinch roll 80 is used to apply a normal force 82 over each steel strip as it is being wound over the impregnated continuous fiber filler on the mandrel. Typically the roll is connected to an arm 84 which extends to location over the mandrel so as to allow the roll to apply a normal force to the wound steel strip. The arm is pivotally coupled to a fixture 85 about a pivot point 86. The arm can reciprocate for moving the pinch roller to a location over the mandrel. The arm may be pneumatically, hydraulically or electrically driven. A vertical member 88 is also pivotally coupled to the pivot point 86 on the fixture. A front portion 92 of a cylinder 90 is fixed to the member 88 such that the cylinder 90 is in a position relatively parallel to the arm 84. The rear 94 of the cylinder 90 is coupled to a rear portion 96 of the arm. Once the roller is in position over the mandrel, the cylinder 90 retracts causing the arm 84 to rotate (counterclockwise in FIG. 12) and the roll to apply a normal force to the strip.

20 Instead of using the mechanism described above, a roll with a predetermined weight may be used as the pinch roll for providing the requisite normal force. The roll may itself be of the predetermined weight or a separate weight may be added to the roll.

25 In an alternate embodiment, instead of using a continuous fiber filler, chopped or crushed fibers may be mixed with the resin in an amount yielding a high fiber content prior to applying the resin over a wound first steel strip layer portion. Alternatively, resin may be applied to the wound steel strip and the crushed or chopped fibers may be applied over the resin.

30 Because, the fibers themselves can carry load, the addition of the fiber fillers to the resin improves the peel strength and the shear strength of the bond between the steel strip layers of the SSL pipe. Moreover, the high fiber content reduces the shrinkage and thus, the shrinkage stresses developed in the resin during curing, improving the bond strength of the resin. In addition, the use of the fiber filler improves the resistance to crack growth in the resin between the steel strip layers. In essence, the fibers provide a stop to crack growth. The crack will grow into the resin until it reaches a fiber where it will stop. The crack may continue to grow at another portion of the resin and again will stop when it reaches another fiber. This phenomenon can be seen in FIG. 13 which depicts a graph of deflection as a function of load for an SSL pipe

1 under parallel plate loading performed per the ASTM D 2001 standard. As it can be seen, the
pipe carries load until a crack is developed at load level 100. As the crack grows with load
application, the load drops to level 102. When at load level 102, the crack growth is arrested
by a fiber and the specimen begins to carry load again to a load level 104. Another crack begins
5 to grow when at 104 and the load drops to level 106. At level 106 the crack growth is arrested
and the specimen begins to carry load again.

In yet a further embodiment instead of a continuous fiber reinforced filler, glass spheres
also known as Zeeospheres or microspheres, a discontinuous filler, are used. Zeeospheres are
typically made from a ceramic material and are shaped like spheres. Zeeospheres can be hollow
10 or solid. They are manufactured by 3M and Zeelan Industries, Inc.

Due to their spherical shape, Zeeospheres can be densely packed in the resin.
Preferably, the resin filled with Zeeospheres should include about 7.5% by weight Zeeospheres.
In lab testing, use of Zeeospheres improved the shear strength between the steel strips at hot
conditions (i.e., at a temperature of 230°F). However the load carrying capabilities of an SSL
15 pipe formed with steel strips bonded with a resin filled with Zeeospheres was less than
capabilities of an SSL pipe formed with steel strips bonded using a continuous fiber reinforced
filler impregnated with resin (FIG. 13). The addition of Zeeospheres also improves the crack
growth resistance of the resin matrix as can be seen from FIG. 13. When using a resin filled
with Zeeospheres, the bond thickness is controlled by using a squeegee. After a resin with
20 Zeeospheres coating is applied to a strip, excess resin is removed using the squeegee. A pinch
roll may also be used to control the bond thickness and to improve the quality of the bond.

Besides bond performance factors of peel strength and lap shear strength at hot
conditions and retention of lap shear strength at wet conditions, applicants discovered that other
important factors need to be considered in selecting a resin filler. These factors are: (1) resin
25 debulking time, i.e., the amount of time it takes to remove the excess resin between the strips
for maximizing the bond strength; (2) ease of application of the filler; and (3) cost of the filler.
Debulking time and ease of application of the filler effect the production of SSL pipe, in that
if debulking times are long and/or if application of the filler is difficult, the time and costs
associated with the SSL pipe production may become excessive. FIG. 14, provides a
30 comparison in relative terms of these factors for woven cloth, monofilament mesh, random
synthetic veil and Zeeospheres fillers. Where applicable the data for this table was obtained
through testing.

As can be seen from FIG. 14, use of a monofilament mesh allows for a very fast resin
debulking time. However, a bond formed with monofilament mesh has a high degradation in
35 shear strength under wet conditions. Random synthetic veil has a good overall balance in the
above factors in that it has a high peel strength, a high shear strength in hot conditions, a
moderate retention of shear strength in wet conditions, provides for an average resin debulking
time, is easy to apply and has a moderate cost. Woven cloth has similar performance

1 characteristics as the random synthetic veil but provides for long resin debulking times and has high material costs. Zeeospheres tend to have low peel strength.

5 Use of continuous fiber reinforced fillers or Zeeospheres in the resin used to bond the steel strips in SSL pipes improves the operating life of the pipe. These fillers can be used to form a resin matrix that is used to bond steel strips that are treated with an adhesion promoter such as sol-gel or silane, or steel strips that are sandblasted or steel strips that are not treated in any way or form.

10 Applicants have discovered, however, that the combination of using an adhesion promoter such as sol-gel or an organofunctional silane on the steel strip coupled with the use of the filler described herein provide for improved bond shear strength and for improved peel strength retention at hot and wet operating conditions. From tests conducted by applicants, the results of which are depicted in FIG. 15, it can be seen that the lap shear strength of the bond incorporating Zeeospheres as a filler between steel strips at 230°F is increased when the steel strips were treated with sol-gel and increased even further when the steel strips were treated with silane. Furthermore, the retention of shear strength at hot wet conditions, also increased from 560 psi after 505 hours of exposure to water at 230°F to 2360 psi and 3280 psi, when the steel strips were treated with sol-gel and silane, respectively and exposed to hot water at 230°F for 820 hours.

20 A comparison of lap shear strengths at different water exposure times at 230°F of steel strips which are coated with an organofunctional silane and bonded using either G-800 type Zeospheres, a Freudenberg 723020 veil, or a Reemay Type 2270 veil are shown in FIG. 16. As can be seen from FIG. 16, use of Reemay or Freudenberg veils significantly increased the peel strength of the bond even under hot water exposure as shown in FIG. 16 with acceptable increases in resin debulking times.

25 Although the present invention has been described and illustrated to respect to multiple embodiments thereof, it is to be understood that it is not to be so limited, since changes and modifications may be made therein which are within the full intended scope of this invention as hereinafter claimed.

CLAIMS

1. A method for forming a laminate pipe comprising the steps of:
forming at least a portion of an inner layer of the pipe;
coating a first steel strip with a sol-gel coating;
winding the steel strip over the inner layer; and
forming an outer layer over the wound steel strip.
2. A method as recited in claim 1 further comprising the steps of:
coating a second steel strip with a sol-gel coating; and
winding the second steel strip over a wound portion of the first steel strip.
3. A method as recited in claim 2 further comprising the step of forming a layer comprising resin between the two wound steel strips.
4. A method as recited in claim 3 wherein the step of coating comprises the step of forming the sol-gel coating, and wherein the step of forming the sol gel coating comprises the steps of:
forming a solution containing a partially reacted metal-organic precursor;
hydrolyzing the solution; and
condensing the solution.
5. A method as recited in claim 3 further comprising the step of mixing chromate in the sol-gel.
6. A method for forming a laminate pipe comprising the steps of:
forming at least a portion of an inner layer of the pipe;
coating a first steel strip with a silane coating;
winding the steel strip over the inner layer; and
forming an outer layer over the wound steel strip.
7. A method as recited in claim 6 further comprising the steps of:
coating a second steel strip with a silane coating; and
winding the second steel strip over a wound portion of the first steel strip.
8. A method as recited in claim 7 further comprising the step of forming a layer comprising resin between the two wound steel strips.

1 9. A method as recited in claim 8 wherein the resin is an organic resin, wherein the
silane comprises Y-R-Si-X₃, wherein the Si bonds with the surfaces of the steel strip, wherein
R is a bridging group, and wherein Y is a nonhydrolyzable organic radical that interacts with
the resin.

5 10. A method for forming laminate pipe comprising the steps of:
 forming a pipe inner lining;
 forming a first steel layer having an inner and an outer surface over the lining;
 bonding a second steel layer inner surface to the first steel layer using an adhesion
10 promoter mixed with a resin; and
 forming an outer lining over the second steel layer.

 11. A method as recited in claim 10 wherein the adhesion promoter is selected from
the group of adhesion promoters consisting of sol-gel and silane.

15 12. A method for coating a strip of material with an adhesion promoter comprising
the steps of:
 passing the strip through a washing fluid;
 passing the strip through a rinsing fluid to rinse the washing solution off the strip;
20 passing the strip through an adhesion promoter solution; and
 drying the adhesion promoter solution on the strip.

 13. A method for coating a strip of material with an adhesion promoter comprising
the steps of:
25 passing the strip through a washing fluid;
 passing the strip through a rinsing fluid to rinse the washing solution off the strip;
 passing the strip through an air knife to remove left over fluids from the strip;
 passing the strip through a sol-gel solution;
 passing the strip through a dryer for drying the sol-gel on the strip; and
30 passing the strip through a second air knife for removing excess the adhesion
promoter from the strip for obtaining an adhesion promoter coating on the strip having a
predetermined thickness.

 14. A laminate pipe comprising:
35 an inner lining defining an inner surface of the pipe;
 a first steel layer formed over the inner lining;

a second steel layer bonded over the first steel layer, wherein at least one of the first and second steel layers is coated with a sol-gel coating for promoting bonding of said one steel layer, and

an outer lining over the second steel layer defining an outer surface of the pipe

15. A laminate pipe as recited in claim 14 wherein the sol-gel coating comprises a partially reacted metal-organic precursor.

16. A laminate pipe as recited in claim 14 wherein the sol-gel coating comprises Chromate.

17. A laminate pipe comprising:
an inner lining defining an inner surface of the pipe;
a first steel layer formed over the inner lining;
a second steel layer bonded over the first steel layer, wherein at least one of the first and second steel layers is coated with a silane coating for promoting bonding of said one steel layer; and
an outer lining over the second steel layer defining an outer surface of the pipe.

18. A laminate pipe as recited in claim 17 wherein the silane comprises:
silicon;
a hydrolyzable group; and
an non-hydrolyzable organic radical.

19. A laminate pipe comprising:
an inner lining defining an inner surface of the pipe;
a first steel layer formed over the inner lining;
an intermediate layer comprising resin and a fibrous filler over the first steel layer;
a second steel layer bonded to the first steel layer via the intermediate layer; and
an outer lining formed over the second steel layer defining an outer surface of the pipe.

20. A laminate pipe as recited in claim 19 wherein the intermediate layer comprises fibrous material selected from the group of materials consisting of glass, carbon and Kevlar.

21. A laminate pipe as recited in claim 19 wherein the intermediate layer comprises chopped fibrous material.

22. A laminate pipe as recited in claim 19 wherein the intermediate comprises a continuous reinforced fiber layer.

1 23. A laminate pipe as recited in claim 22 wherein the continuous reinforced fiber layer is in the form selected from the groups of forms consisting of veils, woven cloths, tapes and monofilament meshes.

5 24. A laminate pipe as recited in claim 19 wherein at least one of the steel layers is coated with an adhesion promoter prior to bonding.

 25. A laminate pipe as recited in claim 24 wherein the adhesion promoter is selected from the group of adhesion promoters consisting of sol-gel and silane.

10 26. A method for forming a laminate pipe comprising the steps of:
 forming at least a portion of an inner lining;
 winding a first steel strip over the inner lining forming a first steel layer;
 forming a fibrous layer over the first steel layer;
15 winding a second steel strip over the fibrous layer forming a second steel layer;
 and
 forming an outer lining over the second steel layer.

20 27. A method as recited in claim 26 wherein the step of forming a fibrous layer comprises the step of forming a layer comprising resin and chopped fibers.

 28. A method as recited in claim 26 wherein the step of forming a fibrous layer comprises the step of wrapping a continuous reinforced fibrous layer over the first steel layer.

25 29. A method as recited in claim 26 further comprising the step of applying a sol-gel or silane coating to at least one of the steel strips.

 30. A method as recited in claim 26 further comprising the step of applying sol-gel or silane to the fibrous filler.

30 31. A laminate pipe comprising:
 an inner lining defining an inner surface of the pipe;
 a first steel layer formed over the inner lining, the first steel layer having an outer surface;
35 a layer glass spheres over outer surface of the first steel layer;
 a second steel layer bonded to the glass spheres; and
 an outer lining formed over the second steel layer defining an outer surface of the pipe.

1 32. A laminate pipe as recited in claim 31, wherein the layer of glass spheres
comprises a resin and sol-gel or silane.

5 33. A method for forming a laminate pipe comprising the steps of:
forming at least a portion of an inner lining;
winding a first steel strip over the inner lining forming a first steel layer;
forming a layer of glass spheres over the first steel layer;
winding a second steel strip over the fibrous layer forming a second steel layer:
and
10 forming an outer lining over the second steel strip.

15 34. A method as recited in claim 33 wherein the first steel strip has an outer surface
facing the layer of glass spheres and wherein the second steel strip has an inner surface facing
the layer of glass spheres, the method further comprising the step of applying sol-gel or silane
to at least one of said surfaces..

20 35. A method as recited in claim 33 wherein the step of forming a layer of glass
spheres comprises the steps of:
forming a mixture of glass spheres, resin and sol-gel or silane; and
applying said mixture over the first layer.

25

30

35