

A METHOD OF FORMING A CONTACT FOR A PHOTOVOLTAIC CELLField of the Invention

5

The present invention relates to a method of forming a contact for a photovoltaic (PV) cell and relates in particular, not exclusively though, to a method of forming a contact on a rear surface of the PV cell.

10

Background of the Invention

Typical PV cells of the first generation comprise large area p-n-junctions that are formed in doped silicon. Such PV cells have a passivation layer on a rear surface and electrical contacts penetrate through the passivation layer to contact selected highly doped regions of the silicon.

20 The alignment of the contacts relative to the selected highly doped regions of the silicon and electrical properties of the contact material influence the efficiency of the solar cell and there is a need for improvement.

25

Summary of the Invention

In a first aspect of the invention, there is provided a method of forming a contact for a photovoltaic (PV) cell, the method comprising the steps of:

30

providing a substrate of a semiconductor material, the substrate having at least one first region that has a first doping property and is located at a first surface portion;

35

depositing a passivation layer over at least a portion of the surface of the substrate including the at least one first surface portion;

- 2 -

depositing a conductive layer over the passivation layer such that material of the passivation layer is sandwiched between the at least one first region of the substrate and the conductive layer; and

5 applying an electric field between the at least one first region and the conductive layer in a manner such that locally a dielectric breakdown of the sandwiched passivation layer material is induced;

 wherein the method is conducted such that an
10 electrical resistance is reduced in the passivation layer at the at least one first region and an electrical contact is formed.

In one specific embodiment, the substrate comprises at
15 least one second region that is adjacent the at least one first region and may at least in part surround the at least one first region. The at least one first region may have a doping property that is different to that of the at least one first region. The at least one first region and
20 the at least one second region may have the same polarity. Alternatively, the at least one second region may have a p-n junction and the at least one first region may penetrate through the p-n junction.

25 The method typically is conducted such the electrical breakdown is only induced between the at least one first region and the conductive layer and not between the at least one second region and the conductive layer.
 The method typically is conducted such that the
30 passivation properties of the passivation layer material that is adjacent the formed contact are substantially unaffected.

Embodiments of the invention have significant advantages.
35 As the dielectric breakdown is induced only at the locations of the at least one first region, the contact is effectively self-aligned.

- 3 -

The method typically is conducted such that a plurality of contacts is formed.

- 5 Further, the method typically is conducted such that the contact is formed on a rear surface of the PV cell.

In one embodiment, the doping property is a doping concentration. Alternatively, the doping property may be
10 a type of doping material.

In a specific embodiment, the at least one first region has a higher doping concentration than the at least one second region. For example, the at least one first region
15 may be doped with boron or any other suitable dopant material. The dopant concentration of the at least one first region may range from $1e18/cm^3$ to $1e21/cm^3$, such as approximately $1e20/cm^3$. The at least one second region may also be doped with boron or with any other suitable dopant
20 material. The dopant concentration of the at least one second region may range from $1e15/cm^3$ to $1e17/cm^3$, such as approximately $1e16/cm^3$.

In one embodiment, the step of providing the substrate
25 comprises forming the at least one first region. Forming the at least one first region may comprise thermal diffusion. In one specific example forming the at least one first region comprises laser doping.

30 Forming the at least one first region may comprise depositing a layer that functions as a dopant source for the at least one first surface portion. The layer may include the dopant material, such as boron or any other suitable material. The layer may be formed by spin-on
35 deposition. In addition, forming the at least one first region may comprise directing a laser beam selectively towards the at least one first surface portion such that

- 4 -

the dopant material diffuses into the substrate and thereby forms the at least one first region.

5 The method may further comprise removing the layer that functions as a dopant source when the at least one first region has been formed. Removing the layer may comprise rinsing, RCA cleaning and/or selective etching.

10 In one specific embodiment the substrate is a p-type substrate, such as a p-type silicon wafer. In addition, the substrate may be selectively doped in the above-described manner and consequently the at least one first region may have a higher p-dopant concentration than some or all of the remaining regions of the substrate.

15 Alternatively, the substrate may also be an n-type substrate and the at least one first region may have a concentration of an n-type dopant that is higher than that of some or all of the remaining regions of the substrate.

20 In one embodiment, the step of depositing the passivation layer onto the at least a portion of the substrate is conducted by virtue of chemical vapour deposition, such as plasma-enhanced chemical vapour deposition.

25 The passivation layer may comprise amorphous silicon or any other suitable dielectric material.

30 The step of depositing the conductive layer over the passivation layer may be conducted using thermal evaporation. Alternatively, the conductive layer may be deposited over the passivation layer using sputtering or any other physical or chemical deposition technique.

35 The material of the conductive layer may be selected based on the doping property of the at least one first region. For example, if the at least one first region is p-doped,

- 5 -

the material of the conductive layer may be selected from suitable acceptor materials and may, for example, be aluminium.

- 5 Alternatively, if the at least one first region is n-doped, the material of the conductive layer may be selected from suitable donor materials, such as arsenic.

The method may further comprise a step of removing at
10 least a portion of the conductive layer.

In a second aspect of the invention, there is provided a method of forming a photovoltaic cell comprising forming a contact in accordance with the first aspect of the present
15 invention.

In a third aspect of the present invention there is provided a photovoltaic cell formed by the method in accordance with the second aspect of the present
20 invention.

Brief Description of the Drawings

In order to fully understand the present invention,
25 embodiments of the present invention will now be described, by way of example only, with reference to the accompanying drawings, in which:

Figure 1 is a flow diagram illustrating a method of
30 forming a contact for a photovoltaic cell in accordance with an embodiment of the invention; and

Figures 2 to 7 illustrate the formation of components of the photovoltaic cell formed in accordance with
35 embodiments of the present invention.

- 6 -

Description of an Embodiment of the Invention

Referring to the Figures, there is illustrated a method 10 of forming a contact for a photovoltaic (PV) cell in accordance with a specific embodiment of the invention. In this embodiment, the contact is formed on a rear surface of the PV cell that will not receive primary illumination. In this embodiment, the PV cell comprises suitably doped silicon.

10

Figure 1 shows a flow diagram illustrating a method 10 of forming a contact on a rear surface of the PV cell. Figures 2 to 7 illustrate the formation of the PV cell and show partially fabricated components.

15

In a first step 11, a substrate 22 is provided. In this embodiment, the substrate 22 is a p-type silicon wafer. The doping concentration of the p-type Silicon wafer is approximately $1e16/cm^3$.

20

The PV cell further comprises a layer (not shown) on a front surface portion of the substrate 22 which receives primary (solar) illumination when the PV cell is in use. Together with the substrate 22, this layer, which may for example be a thin n-type layer, is arranged to form a p-n junction.

In a further step 12, a plurality of first regions 24 is formed within the substrate 22 (only one first region is shown in Figures 2 to 7). The first regions 24 are located at respective first (rear) surface portions of the substrate 22 as exemplarily shown in Figure 3. The first regions are in the form of islands.

The first regions 24 have a doping concentration that differs from that of adjacent regions of the p-type silicon wafer 22. In this embodiment the first regions

- 7 -

are heavily p-doped and have p-doping concentration that is higher than that of adjacent regions of the p-type silicon wafer 22. In this example, the heavily p-doped region 24 has a p-doping concentration of approximately
5 $1e20/cm^3$.

A person skilled in the art will appreciate that in variations of the described embodiment the first region may also have a doping property other than a doping
10 concentration that is different to that of adjacent regions. For example, the doping property may be associated with a dopant type or material.

The heavily p-doped regions 24 may be formed using any
15 suitable method and in this example these regions are formed using laser doping. Forming the heavily p-doped regions 24 comprises depositing a material that functions as a dopant source onto the surface portions of the heavily p-doped regions 24. In this example, a spin on
20 liquid containing boron is deposited on the rear surface portions of the p-type silicon wafer 22. A laser beam is then directed onto the formed film in a manner such that boron diffuses selectively into the silicon wafer 22 to form the heavily p-doped region 24. The film is
25 subsequently removed from the surface portions of the substrate 22, for example, by rinsing or RCA cleaning.

Step 13 deposits a passivation layer 26 over the rear surface portions of the silicon wafer 22. In this
30 example, the passivation layer 26 is an amorphous silicon layer and has a thickness in the range of 30 to 120nm, in particular in the range of 50 to 70nm, such as approximately 50nm.

35 Step 14 deposits a conductive layer 28 on the amorphous silicon layer 26. In this particular embodiment, the conductive layer 28 is an aluminium layer. The aluminium

- 8 -

layer 28 is deposited by virtue of thermal evaporation. However, a person skilled in the art will appreciate that other suitable methods to deposit the conductive layer are envisaged, such as sputtering. Further, the conductive
5 layer may not necessarily be formed from a metallic material.

Step 15 applies an electric field between the aluminium layer 28 and the silicon wafer 22. As such, a voltage 30
10 is applied in reverse bias. In this example the substrate 22 is p-type and a positive voltage 30 is applied to the aluminium layer 28 as illustrated in Figure 6. In an alternative embodiment, in which the substrate comprises an n-type material, a negative voltage is applied to the
15 conductive layer.

By applying the voltage 30 in reverse bias, an electric field is generated across the passivation layer 26 between the aluminium layer 28 and the p-type silicon substrate
20 22. The strength of the generated electric field is higher across the region 32 that is located directly above the heavily p-doped region 24 than across adjacent regions of passivation layer. In this embodiment the heavily p-doped region 24 forms a depletion region that is narrow
25 enough for tunnelling to occur. Consequently, the electrical field is mainly applied across the passivation layer 26 at the first regions 24. The passivation layer 26 is sufficiently thin such that the relatively large applied field results in a breakdown of dielectric
30 properties and a related permanent local reduction of electrical resistance of the passivation layer 26 in the region 32. The dielectric breakdown is a "hard" breakdown such that the amorphous silicon layer 26 locally loses its insulating properties. The permanent change in local
35 electrical properties of the regions 32 results in the formation of an electrical contact.

- 9 -

The hard dielectric breakdown is limited to the local regions 32 directly at the heavily p-doped regions 24. Regions of the passivation layer 26 that are adjacent to region 32 are not significantly affected by the applied
5 voltage 30 and as a consequence these regions maintain the passivation properties of amorphous silicon.

The bias voltage required to induce the hard breakdown of the dielectric material 26 generally depends on material
10 properties of the heavily p-doped regions 24 and the dielectric material 26. The bias voltage typically is in the range of 5 to 30V, such as approximately 10V. Generally, the bias voltage increases with the resistivity of the dielectric material 26. The bias voltage is
15 affected by thickness of the dielectric material 26 and increases when the thickness of the dielectric material 26 increases.

The inventors have found that the bias voltage required to
20 induce the hard breakdown of a 64nm thick amorphous silicon layer is in the range 2 to 5V; a 10nm thick aluminium oxide layer is in the range of 5 to 10V; an 80nm thick silicon rich silicon nitride layer is in the range 13 to 18V and a 200nm silicon nitride layer is in the
25 range of 23 to 28V.

By conducting the method 10 in accordance with the specific embodiment of the invention, a self-aligned electrical contact is formed without the requirement of
30 patterning or masking the amorphous silicon layer 26. Furthermore, as dielectric properties of regions adjacent to the regions 32 of the passivation layer 26 are not significantly affected, recombination of charge carriers at the rear surface of the PV cell can be reduced.

35

In this particular example, the aluminium layer 28 forms a portion of the rear contact of the PV cell as shown in

- 10 -

Figure 7.

The method 10 may further comprise a step of removing the aluminium layer 28.

5

Advantageous embodiments of the method 10 can be used to form contacts to the base of a PV device through an emitter of a PV device. In these specific embodiments the steps of method 10 are carried out on a semiconductor

10 substrate, for example a silicon wafer, which comprises a p-n junction. The semiconductor substrate may be a p-type silicon wafer 11 (base) and an n-type region (emitter) may be formed on a surface of the p-type silicon wafer 11 by diffusion of n-type atoms, for example phosphorous atoms.

15 The remaining steps of method 10 are performed on the n-type surface of the silicon wafer 11. Some of the advantages of contacting the base of the PV device through the emitter of the PV device by using the method 10 include floating junction passivation, implementation of
20 inter-digitated rear contact designs, and minimisation of shunts.

A person skilled in the art will appreciate that the embodiments of the invention described in relation to a PV
25 device realised on a p-type substrate are applicable to PV devices realised on n-type substrates. Further, the person skilled in the art will appreciate that, in order to realise a complete and functioning, PV device additional processing steps are required. These further processing
30 steps are known in the art.

Modifications and variations as would be apparent to a skilled addressee are deemed to be within the scope of the present invention. For example, a person skilled in the
35 art will appreciate that the substrate 22 may be an n type wafer and the at least one first region may be a heavily n-doped region. Further, the variations of the described

- 11 -

method may be used to form selective contacts at a front surface of a PV cell.

- 12 -

The Claims:

1. A method of forming a contact for a photovoltaic (PV) cell, the method comprising the steps of:

5 providing a substrate of a semiconductor material, the substrate having at least one first region that has a first doping property and is located at a first surface portion;

10 depositing a passivation layer over at least a portion of the surface of the substrate including the at least one first surface portion;

15 depositing a conductive layer over the passivation layer such that material of the passivation layer is sandwiched between the at least one first region of the substrate and the conductive layer; and

applying an electric field between the at least one first region and the conductive layer in a manner such that locally a dielectric breakdown of the sandwiched passivation layer material is induced;

20 wherein the method is conducted such that an electrical resistance is reduced in the passivation layer at the at least one first region and an electrical contact is formed.

25 2. The method claim 1 wherein the substrate comprises at least one second region that is adjacent the at least one first region and has a doping property that is different to that of the at least one first region.

30 3. The method of claim 2 wherein the method is conducted such the electrical breakdown is only induced between the at least one first region and the conductive layer and not between the at least one second region and the conductive layer.

35

4. The method of any one of the preceding claims wherein the method is conducted such that the passivation

- 13 -

properties of passivation layer material that is adjacent the formed contact are substantially unaffected.

5 5. The method of any one of the preceding claims being conducted such that the contact is formed on a rear surface of the PV cell.

10 6. The method of any one of the preceding claims wherein the doping property comprises a doping concentration.

7. The method of any one of the preceding claims wherein the doping property comprises a type of doping material.

15 8. The method of any one of claim 2 or 3 or anyone of claims 5 to 7 when dependent on anyone of claims 2 or 3 wherein the at least one first region has a higher doping concentration than the at least one second region.

20 9. The method of any one of the preceding claims wherein the method is conducted such that a plurality of contacts is formed.

25 10. The method of any one of the preceding claims wherein the step of providing the substrate comprises forming the at least one first region.

11. The method of claim 10 wherein the at least one first region is formed using thermal diffusion.

30 12. The method of claim 11 wherein the at least one first region is formed using laser doping.

13. The method of claim 12 wherein forming the at least one first region comprises:

35 depositing a layer that functions as a dopant source for the at least one first surface portion; and
 directing a laser beam selectively towards the first

- 14 -

surface portion such that the dopant material diffuses into the substrate and thereby forms the at least one first region.

5 14. The method of any one of the preceding claims wherein the passivation layer comprises amorphous silicon.

15 15. The method of any one of the preceding claims wherein the material of the conductive layer is selected based on the doping property of the at least one first region.

15 16. The method of any one of the preceding claims wherein the substrate comprises at least one second region that is adjacent the at least one first region and has a doping property that is different to that of the at least one first region, the at least one first region and the at least one second region having the same polarity.

20 17. The method claim 2 or anyone of claims 3 to 15 when dependent on claim 2 wherein the at least one second region has a p-n junction and wherein the at least one first region penetrates through the p-n junction.

25 18. A method of forming a photovoltaic cell comprising forming a contact for a PV cell using a method in accordance with any one of the preceding claims.

19. A photovoltaic cell formed by the method of claim 18.