



- (51) International Patent Classification:
C08F 10/00 (2006.01) *C08F 210/02* (2006.01)
- (21) International Application Number:
PCT/US2012/041466
- (22) International Filing Date:
8 June 2012 (08.06.2012)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
13/156,102 8 June 2011 (08.06.2011) US
- (71) Applicant (for all designated States except US): **CHEVRON PHILLIPS CHEMICAL COMPANY LP** [US/US]; 10001 Six Pines Drive, The Woodlands, Texas 77380 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **YANG, Qing** [CN/US]; 2917 Montrose Drive, Bartlesville, Oklahoma 74006 (US). **MCDANIEL, Max P.** [US/US]; 1601 Melmart Drive, Bartlesville, Oklahoma 74006 (US). **BEAU-LIEU, William B.** [US/US]; 8731 E 104th Street, Tulsa, Oklahoma 74133 (US). **YU, Youlu** [CA/US]; 1532 Whitney Lane, Bartlesville, Oklahoma 74006 (US). **CRAIN, Tony R.** [US/US]; 474 Rd 30, Niotaze, Kansas 67355 (US).
- (74) Agent: **HUSEMAN, Cheryl L.**; Chevron Phillips Chemical Company LP, 10001 Six Pines Drive, The Woodlands, Texas 77380 (US).
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:
— with international search report (Art. 21(3))

(54) Title: POLYMER COMPOSITIONS FOR BLOW MOLDING APPLICATIONS

(57) Abstract: A polymer having a density of from about 0.960 g/cc to about 0.965 g/cc and a melt index of from about 0.2 g/10 min. to about 0.6 g/10 min. wherein an article formed from the polymer has an environmental stress crack resistance of equal to or greater than about 150 hours when measured in accordance with ASTM D 1693 condition B, 100 % Igepal. A polymer having a density of from about 0.955 g/cc to about 0.960 g/cc and a melt index of from about 0.2 g/10 min. to about 0.6 g/10 min. wherein an article formed from the polymer has an environmental stress crack resistance of equal to or greater than about 500 hours when measured in accordance with ASTM D 1693 condition B, 100 % Igepal

