

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
14 March 2002 (14.03.2002)


PCT

(10) International Publication Number
WO 02/020667 A3

- (51) International Patent Classification⁷: C08L 97/02, B27N 5/00, 7/00, B29C 33/00 // (C08L 97/02, 101:00) (C08L 97/02, 3:02, 101:00)
- (21) International Application Number: PCT/SG01/00180
- (22) International Filing Date:
7 September 2001 (07.09.2001)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
0005117-7 9 September 2000 (09.09.2000) SG
00104759-6 8 August 2001 (08.08.2001) SG
- (71) Applicant and
(72) Inventor: CHOO, Thiam, Huay, Gary [SG/SG]; 139 Namly Avenue, Singapore 267704 (SG).
- (74) Agent: TAN, JinHwee; Eunice & Lim ChooEng, P.O. Box 1381, Robinson Road, Singapore 902731 (SG).
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

[Continued on next page]

(54) Title: MOULDED PRODUCT



(57) Abstract: The present invention relates to a moulded product. The moulded product may be manufactured by a process comprising the following steps: (a) preparing a moulding mixture by: (i) taking 40 to 60 wt.% plant fibre pieces and optionally combining added starch with the plant fibre pieces; and (ii) adding thereto 10 to 55 wt.% water and 3 to 10 wt.% one or more water-soluble binding agents or adhesives; (b) pouring the mixture into a mould the mould being a temperature of at least 60 °C; (c) subjecting the mixture in the mould to a temperature in the range of 15 to 60 °C and a pressure in the range from 1000 to 7000 PSI for a period of time such that a portion of the water in the mixture is converted to steam which causes the mixture to fill the mould while remaining in a mouldable state; (d) reducing the pressure so that steam continues to form within the mould without causing an explosion whilst maintaining the mixture in a mouldable state; (e) increasing the temperature and pressure to a temperature in the range from 100 to 200 °C and a pressure in the range of 500 to 1500 PSI; (f) removing the steam or allowing the steam to escape until the moulded product is substantially dry; (g) removing the substantially dried and moulded product from the mould; the amount of starch added in between 0 and 10 wt. preferably 0 to 2 wt.% or 2 to 10 wt.%.

WO 02/020667 A3

**Declarations under Rule 4.17:**

- *as to the identity of the inventor (Rule 4.17(i)) for all designations*
- *of inventorship (Rule 4.17(iv)) for US only*

Published:

- *with international search report*
- *before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments*

(88) Date of publication of the international search report:

8 August 2002

(15) Information about Correction:**Previous Correction:**

see PCT Gazette No. 19/2002 of 10 May 2002, Section II

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.