

OXIDATION AND FATIGUE RESISTANT METALLIC COATINGBACKGROUND OF THE INVENTION

The present invention relates to an oxidation and fatigue resistant metallic coating for protecting high temperature gas turbine engine components.

Various metallic coatings have been developed in the past for the oxidation protection of high temperature gas turbine engine components. These coatings are often based on different aluminide compositions with nickel or cobalt base metal materials. Alternatively, they are based on overlay deposits with MCrAlY foundations where M is nickel, cobalt, iron or combinations of these materials. These coating systems suffer from shortcomings that preclude their use on newer advanced turbine components. The diffused aluminides, while possessing good fatigue resistance, are generally lacking in very high temperature oxidation resistance (above 2000 degrees Fahrenheit). The overlay MCrAlY coatings tend to have serious fatigue debts that limit their applications. The addition of active elements to the MCrAlY coatings not only provides excellent oxidation resistance, but makes them good candidates for bond-coats for thermal barrier ceramic coatings. While both aluminides and MCrAlY coatings have widespread applications, a new coating that could combine the best properties from both would have immediate application on advanced turbine components where fatigue, pull weight, and oxidation must all be minimized.



159159



G00002

SUMMARY OF THE INVENTION

Accordingly, it is an object of the present invention to provide a metallic coating composition which provides excellent oxidation and fatigue resistance properties.

It is another object of the present invention to provide a coating composition which reduces the thermal expansion mismatch between the coating and common turbine alloys.

The foregoing objects are attained by the coatings of the present invention.

In accordance with the present invention, a metallic coating is provided which has a composition comprising up to 18 wt% cobalt, 3.0 to 18 wt% chromium, 5.0 to 15 wt% aluminum, 0.1 to 1.0 wt % yttrium, up to 0.6 wt% hafnium, up to 0.3 wt% silicon, 3.0 to 10 wt% tantalum, up to 9.0 wt% tungsten, 1.0 to 6.0 wt% rhenium, up to 10 wt% molybdenum, and the balance nickel. The coating compositions of the present invention also have a total amount of tantalum and tungsten in the range of 3.0 to 16 wt%.

Other details of the oxidation and fatigue resistant metallic coatings of the present invention, as well as other objects and advantages attendant thereto, are set forth in the following detailed description.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT(S)

Turbine engine components are formed from nickel-based, cobalt-based, and iron-based alloys. Due to the extreme high temperature environments in which these components work, it is necessary to provide them with a protective coating. The coatings must have a composition which minimizes the fatigue impact on the turbine engine components to which they are applied and at the same time provide maximum oxidation

resistance properties. The coating must also be one where the thermal expansion mismatch between the coating and the alloy(s) used to form the turbine engine components is minimized. This mismatch is one of the causes of the poor fatigue performance of MCrAlY coatings.

In accordance with the present invention, metallic coatings have been developed which reduce the thermal mismatch and which provide a very desirable oxidation and fatigue resistance. These metallic coatings having a composition which broadly consists essentially of from up to 18 wt% cobalt, 3.0 to 18 wt% chromium, 5.0 to 15 wt% aluminum, 0.1 to 1.0 wt% yttrium, up to 0.6 wt% hafnium, up to 0.3 wt% silicon, 3.0 to 10 wt% tantalum, up to 9.0 wt% tungsten, 1.0 to 6.0 wt% rhenium, up to 10 wt% molybdenum, and the balance nickel. In these coatings, the tungsten and the tantalum are present in a total amount in the range of from 3.0 to 16 wt%.

Within the foregoing broad coating compositions, a first family of particularly useful coatings for turbine engine components has a composition which consists essentially of up to 15 wt%, preferably 2.0 wt% or less, cobalt, 5.0 to 18 wt%, preferably 10 to 15 wt% chromium, 5.0 to 12 wt%, preferably 6.0 to 10 wt% aluminum, 0.1 to 1.0 wt%, preferably 0.2 to 0.7 wt%, yttrium, up to 0.6 wt%, preferably 0.2 to 0.6 wt%, hafnium, up to 0.3 wt%, preferably 0.1 wt% or less, silicon, 3.0 to 10 wt%, preferably, 5.0 to 7.0 wt% tantalum, up to 5.0 wt%, preferably, 1.0 to 4.0 wt% tungsten, 1.0 to 6.0, preferably 1.0 to 3.5 wt%, rhenium, up to 10 wt%, preferably 4.0 wt% or less, molybdenum, and the balance nickel. The total amount of tantalum and tungsten in these metallic coatings is in the range of 3.0 to 12 wt% and preferably, in the range of 5.0 to 9.0 wt%.

Within this first family of coatings, a particularly useful coating composition consists of 12.5 wt% chromium, 8.0 wt% aluminum, 0.4 to 0.7 wt% yttrium, 0.4 wt% hafnium, 6.0 wt% tantalum, 2.0 wt% tungsten, 2.0 wt% rhenium, and the balance nickel.

A second family of particularly useful metallic coating compositions comprises 2.0 to 18 wt%, preferably 8.0 to 12 wt%, cobalt, 3.0 to 10 wt%, preferably 4.0 to 6.5 wt%, chromium, 5.5 to 15 wt%, preferably 7.5 to 12.5 wt% aluminum, 0.1 to 1.0 wt%, preferably 0.2 to 0.7 wt%, yttrium, up to 0.6 wt%, preferably, from 0.2 to 0.6 wt%, hafnium, up to 0.3 wt% silicon, 3.0 to 10 wt%, preferably from 5.0 to 7.0 wt%, tantalum, 1.0 to 9.0 wt%, preferably 4.2 to 5.8 wt%, tungsten, 1.0 to 5.0 wt%, preferably 2.3 to 3.7 wt%, rhenium, 0.2 to 4.0 wt%, preferably 1.4 to 2.0 wt%, molybdenum, and the balance nickel. The total amount of tungsten and tantalum in these coatings is from 3.0 to 12 wt%, preferably from 5.0 to 9.0 wt%.

Within this second family of coatings, a particularly useful coating composition consists of 10.5 wt% cobalt, 5.0 wt% chromium, 9.0 wt% aluminum, 0.4 to 0.7 wt% yttrium, 0.4 wt% hafnium, 0.1 wt% silicon, 6.0 wt% tantalum, 5.0 wt% tungsten, 3.0 wt% rhenium, 1.7 wt% molybdenum, and the balance nickel.

A driver of poor coating fatigue performance is excessive coating thickness. Typical methods of depositing overlay coatings include thermal spray techniques such as low pressure plasma spray (LPSS), which creates coating thicknesses in the range of 0.004 to 0.012 inches. Using cathodic arc plasma vapor deposition techniques, it is possible to apply coatings with the aforesaid compositions having a thickness of 0.002 inches. Techniques for applying the coatings of the present invention by cathodic arc plasma vapor deposition are discussed in U.S.

Patent Nos. 5,972,185; 5,932,078; 6,036,828; 5,792,267; and 6,224,726, all of which are incorporated by reference herein. Alternate methods of deposition, including other plasma vapor deposition techniques such as magnetron sputtering and electron beam plasma vapor deposition may be used. When thickness concerns are not present, various thermal spray techniques such as low pressure plasma spray and HVOF (high velocity oxy-fuel) techniques may be utilized.

Coatings having compositions in accordance with the present invention have demonstrated thermal fatigue resistance equal to the best fatigue resistant diffused aluminide coating. The following table illustrates the results of a 2100 degree Fahrenheit burner rig cyclic oxidation test comparing compositions in accordance with the present invention with other coating compositions.

2100F BURNER RIG CYCLIC OXIDATION TEST					
Candidate #	Thickness	Coating Life (Hrs)	CL **	System Failure (Hrs)	SF **
701	2.95	2320	1573	2713	1839
702	3.1	4105	2648	6285	4055
703	2.7	1591	1179	1932	1431
699	3.3	3060	1855	3622	2195
700	2.15	1170	1088	1399	1301
697	2.4	982	818	1045	871
695	2.8	826	590	1315	939
696	2.45	676	552	805	657
PWA 275	2	115	115	366	366

** Normalized to a 2 mil coating thickness.

Samples formed from material 701 had a composition consisting of 12.5 wt% chromium, 8.0 wt% aluminum, 0.4 to 0.7 wt% yttrium, 0.4 wt% hafnium, 6.0 wt% tantalum, 2.0 wt% tungsten, 2.0 wt% rhenium, and the balance nickel. Samples formed from material 702 had a composition consisting of 10.5 wt% cobalt, 5.0 wt% chromium, 9.0 wt% aluminum, 0.4 to 0.7 wt% yttrium, 0.4 wt% hafnium, 0.1 wt% silicon, 6.0 wt% tantalum, 5.0 wt% tungsten, 3.0 wt% rhenium, 1.7 wt% molybdenum, and the balance nickel.

Samples designated 703 had a composition of 7.0 wt% chromium, 6.0 wt% aluminum, 5.5 wt% tungsten, 4.0 wt% tantalum, 2.0 wt% rhenium, 4.0 wt% ruthenium, 0.5 wt% molybdenum, 0.4 wt% hafnium, 0.25 wt% yttrium, and the balance nickel.

Samples designated 699 are NiCoCrAlY compositions with rhenium and tantalum. Samples designated 700, 697, 695, and 696 are NiAl compositions with 2 - 4 wt% chromium, 0.2 to 0.6 wt% yttrium and 0.4 wt% hafnium. Samples designated PWA 275 are conventional low activity NiAl aluminides.

The test conditions were 57 minutes at 2100 degrees Fahrenheit and 3 minutes forced- air cooled, each hour. The burner rig used a supply of pre-heated, compressed air mixed with JP8 jet fuel to heat the samples in a dynamic environment.

It is apparent that there has been provided in accordance with the present invention an oxidation and fatigue resistant metallic coating which fully satisfies the objects, means and advantages set forth hereinbefore. While the present invention has been described in the context of specific embodiments thereof, other alternatives, modifications, and variations will become apparent to those skilled in the art having read the foregoing description. Accordingly, it is intended to embrace

those alternatives, modifications, and variations as fall within the broad scope of the appended claims.

WHAT IS CLAIMED IS:

1. A metallic coating for providing oxidation and fatigue resistance having a composition comprising up to 18 wt% cobalt, 3.0 to 18 wt% chromium, 5.0 to 15 wt% aluminum, 0.1 to 1.0 wt% yttrium, up to 0.6 wt% hafnium, up to 0.3 wt% silicon, 3.0 to 10 wt% tantalum, up to 9.0 wt% tungsten, 1.0 to 6.0 wt % rhenium, up to 10 wt% molybdenum, and the balance nickel.
2. A metallic coating according to claim 1, wherein a total amount of said tantalum and said tungsten is in a range from 3.0 to 16.0 wt%.
3. A metallic coating according to claim 1, wherein said cobalt is present in an amount less than 15 wt%, said chromium is present in an amount from 5.0 to 18 wt%, said aluminum is present in an amount from 5.0 to 12 wt%, and said tungsten is present in an amount less than 5.0 wt%.
4. A metallic coating according to claim 1, wherein said cobalt is present in an amount from 2.0 to 18 wt%, said chromium is present in an amount from 3.0 to 10 wt%, said aluminum is present in an amount from 5.5 to 15 wt%, said rhenium is present in an amount from 1.0 to 5.0 wt%, and said molybdenum is present in an amount from 0.2 to 4.0 wt%.
5. A metallic coating according to claim 1, wherein a total amount of said tantalum and said tungsten is in a range from 4.0 to 16 wt%.

6. A metallic coating having a composition consisting essentially of up to 15 wt% cobalt, 5.0 to 18 wt% chromium, 5.0 to 12 wt% aluminum, 0.1 to 1.0 wt% yttrium, up to 0.06 hafnium, up to 0.3 wt% silicon, 3.0 to 10 wt% tantalum, up to 5.0 wt% tungsten, 1.0 to 6.0 wt% rhenium, up to 10 wt% molybdenum, and the balance nickel.
7. A metallic coating according to claim 6, wherein a total amount of said tantalum and said tungsten is in a range of from 3.0 to 12 wt%.
8. A metallic coating according to claim 6, wherein a total amount of said tantalum and said tungsten is in a range of from 5.0 to 9.0 wt%.
9. A metallic coating according to claim 6, wherein said cobalt is present in an amount less than 2.0 wt%, said chromium is present in an amount from 10 to 15 wt%, said aluminum is present in an amount from 6.0 to 10 wt%, said yttrium is present in an amount from 0.2 to 0.7 wt%, said hafnium is present in an amount from 0.2 to 0.6 wt%, said silicon is present in an amount no greater than 0.1 wt%, and said tantalum is present in an amount from 5.0 to 7.0 wt%.
10. A metallic coating according to claim 6, wherein said chromium is present in an amount of 12.5 wt% and wherein said aluminum is present in an amount of 8.0 wt%.
11. A metallic coating according to claim 9, wherein said yttrium is present in an amount from 0.4 to 0.7 wt% and said hafnium is present in an amount of 0.4 wt%.

12. A metallic coating according to claim 6, wherein said rhenium is present in an amount from 1.0 to 3.5 wt%, preferably in an amount of 2.0 wt%.

13. A metallic coating according to claim 6, wherein said molybdenum is present in an amount no greater than 4.0 wt%.

14. A metallic coating consisting essentially of up to 2.0 wt% cobalt, 10 to 15 wt% chromium, 6.0 to 10 wt% aluminum, 0.2 to 0.7 wt% yttrium, 0.2 to 0.6 hafnium, 0.001 to 0.1 wt% silicon, 5.0 to 7.0 wt% tantalum, 1.0 to 4.0 wt% tungsten, 1.0 to 3.5 wt% rhenium, up to 4.0% molybdenum, and the balance nickel.

15. A metallic coating according to claim 14, wherein said tungsten and tantalum are present in a total amount in a range of 5.0 to 9.0 wt%.

16. A metallic coating consisting of 12.5 wt% chromium, 8.0 wt% aluminum, 0.4 to 0.7 wt% yttrium, 0.4 wt% hafnium, 6.0 wt% tantalum, 2.0 wt% tungsten, 2.0 wt% rhenium, and the balance nickel.

17. A metallic coating consisting essentially of 2.0 to 18 wt% cobalt, 3.0 to 10 wt% chromium, 5.5 to 15 wt% aluminum, 0.1 to 1.0 wt% yttrium, up to 0.6 wt% hafnium, up to 0.3 wt% silicon, 3.0 to 10 wt% tantalum, 1.0 to 9.0 wt% tungsten, 1.0 to 5.0 wt% rhenium, 0.2 to 4.0 wt% molybdenum, and the balance nickel.

18. A metallic coating according to claim 17, wherein said tantalum and said tungsten are present in a total amount in the range of from 4.0 to 16 wt%.

19. A metallic coating according to claim 17, wherein said tantalum and said tungsten are present in a total amount in the range of from 7.0 to 12 wt%.

20. A metallic coating according to claim 17, wherein said tantalum and said tungsten are present in a total amount of 11 wt%.

21. A metallic coating according to claim 17, wherein said cobalt is present in an amount from 8.0 to 12 wt%, said chromium is present in an amount from 4.0 to 6.5 wt%, said aluminum is present in an amount from 7.5 to 12.5 wt%, said yttrium is present in an amount from 0.2 to 0.7 wt%, said hafnium is present in an amount from 0.2 to 0.6 wt%, said silicon is present in an amount no greater than 0.1 wt%, and said tantalum is present in an amount from 5.0 to 7.0 wt%.

22. A metallic coating according to claim 17, wherein said cobalt is present in an amount of 10.5 wt%, said chromium is present in an amount of 5.0 wt%, said aluminum is present in an amount of 9.0 wt%, said yttrium is present in an amount from 0.4 to 0.7 wt%, said hafnium is present in an amount of 0.4 wt%, and said tantalum is present in an amount of 6.0 wt%.

23. A metallic coating according to claim 17, wherein said tungsten is present in an amount from 4.2 to 5.8 wt%, said

rhenium is present in an amount from 2.3 to 3.7 wt%, and said molybdenum is present in an amount from 1.4 to 2.0 wt%.

24. A metallic coating according to claim 17, wherein said tungsten is present in an amount of 5.0 wt%, said rhenium is present in amount of 3.0 wt%, and said molybdenum is present in an amount of 1.7 wt%.

25. A metallic coating having a composition consisting essentially of 8.0 to 12 wt% cobalt, 4.0 to 6.5 wt% chromium, 7.5 to 12.5 wt% aluminum, 0.2 to 0.7 wt% yttrium, 0.2 to 0.6 wt% hafnium, up to 0.3 wt% silicon, 5.0 to 7.0 wt% tantalum, 4.2 to 5.8 wt% tungsten, 2.3 to 3.7 wt% rhenium, 1.4 to 2.0 wt% molybdenum, and the balance nickel.

26. A metallic coating according to claim 25, wherein said tantalum and said tungsten are present in a total amount in the range of from 7.0 to 12 wt%.

27. A metallic coating consisting of 10.5 wt% cobalt, 5.0 wt% chromium, 9.0 wt% aluminum, 0.4 to 0.7 wt% yttrium, 0.4 wt% hafnium, 0.1 wt% silicon, 6.0 wt% tantalum, 5.0 wt% tungsten, 3.0 wt% rhenium, 1.7 wt% molybdenum, and the balance nickel.

28. A method for depositing an overlay coating on a substrate comprising:

providing a substrate material formed from at least one of a nickel-based, a cobalt-based, and an iron-based metallic material; and

depositing onto said substrate a coating having a composition consisting essentially of up to 18 wt% cobalt, 3.0 to 18 wt% chromium, 5.0 to 15 wt% aluminum, 0.1 to 1.0 wt% yttrium, up to 0.6 wt% hafnium, up to 0.3 wt% silicon, 3.0 to 10 wt% tantalum, up to 9.0 wt% tungsten, 1.0 to 6.0 wt% rhenium, up to 10 wt% molybdenum, and the balance nickel.

29. A method for depositing an overlay coating according to claim 28, wherein said deposition step is carried out using a cathodic arc process or a low pressure plasma spray technique.

30. A method according to claim 28, wherein said depositing step comprises depositing a coating having a composition consisting essentially of up to 15 wt% cobalt, 5.0 to 18 wt% chromium, 5.0 to 12 wt% aluminum, 0.1 to 1.0 wt% yttrium, up to 0.6 wt% hafnium, up to 0.3 wt% silicon, 3.0 to 10 wt% tantalum, up to 5.0 wt% tungsten, 1.0 to 6.0 wt% rhenium, up to 10 wt% molybdenum, and the balance nickel.

31. A method according to claim 28, wherein said depositing step comprises depositing a coating having a composition consisting essentially of up to 2.0 wt% cobalt, 10 to 15 wt% chromium, 6.0 to 10 wt% aluminum, 0.2 to 0.7 wt% yttrium, 0.2 to 0.6 wt% hafnium, up to 0.1 wt% silicon, 5.0 to 7.0 wt% tantalum, 1.0 to 4.0 wt% tungsten, 1.0 to 3.5 wt% rhenium, up to 4.0 wt% molybdenum, and the balance nickel.

32. A method according to claim 28, wherein said depositing step comprises depositing a coating having a composition consisting essentially of 2.0 to 18 wt% cobalt, 3.0 to 10 wt% chromium, 5.5 to 15 wt% aluminum, 0.1 to 1.0 wt% yttrium, up to

0.6 wt% hafnium, up to 0.3 wt% silicon, 3.0 to 10 wt% tantalum, 1.0 to 9.0 wt% tungsten, 1.0 to 5.0 wt% rhenium, 0.2 to 4.0 wt% molybdenum, and the balance nickel.

33. A method according to claim 28, wherein said depositing step comprises depositing a coating having a composition consisting essentially of 8.0 to 12 wt% cobalt, 4.0 to 6.5 wt% chromium, 7.5 to 12.5 wt% aluminum, 0.2 to 0.7 wt% yttrium, 0.2 to 0.6 wt% hafnium, up to 0.3 wt% silicon, 5.0 to 7.0 wt% tantalum, 4.2 to 5.8 wt% tungsten, 2.3 to 3.7 wt% rhenium, 1.4 to 2.0 wt % molybdenum, and the balance nickel.