

PATENT SPECIFICATION

(11) 1 519 702

- (21) Application No. 7990/76 (22) Filed 1 March 1976
 (31) Convention Application No. 50/026065
 (32) Filed 5 March 1975 in
 (33) Japan (JP)
 (44) Complete Specification published 2 Aug. 1978
 (51) INT CL² C25D 11/22
 (52) Index at acceptance
 C7B 114 124 304 320 325 340 421 620 682 683 686 770 DM



(54) PROCESS FOR ELECTROLYTICALLY COLORING ALUMINUM AND ALUMINUM ALLOYS

(71) We, YOSHIDA KOGYO K.K., a corporation duly organized under the laws of Japan and existing at No. 1, Kanda Izumi-cho, Chiyoda-ku, Tokyo, Japan, do hereby declare the invention, for which we pray that a patent may be granted to us, and the method by which it is to be performed, to be particularly described in and by the following statement:—

This invention relates to a process for electrolytically coloring aluminum or any of its various alloys.

For electrolytic coloring of aluminum or aluminum alloys, there has been suggested and practiced extensively a process wherein workpieces are first anodized to form oxide films thereon and then electrolyzed in an electrolytic solution containing a metallic salt such as nickel salt by use of alternating or direct current. The workpieces are colored by deposition of the metal or metal oxide in the pores of the oxide films thereon.

Such a prior art process is generally poor in throwing power, so that particularly in the case of an irregularly shaped workpiece, its protuberant and recessed portions tend to be tinted noticeably differently. Furthermore, since a darker shade is usually produced on the end faces of workpieces, the counter electrode requires intricate masking.

It has also been proposed to make suitably combined use, in the electrolyzing operation of the above described prior art process, of alternating and direct currents or of other currents similar to or quite dissimilar from such currents in waveform. This practice has drawbacks in connection with the complexity of equipment required and its control.

The present invention seeks to provide an improved electrolytic process for uniformly coloring aluminum and aluminum alloys.

The invention further seeks to provide a process of the character described such

that aluminum or aluminum alloy can be colored speedily to a desired degree.

According to the invention, there is provided a process for electrolytically colouring aluminium or an aluminium alloy which comprises electrolysing anodised aluminium or an aluminium alloy in an acidic, aqueous electrolyte containing at least two colouring metallic salts in the range of from 5 to 500 grams per litre in total and a strong reducing compound selected from dithionites, thiosulphates, thioglycolic acid, and thioglycolates in the range of from 0.05 to 10 grams per litre at an alternating current potential of up to 15 volts.

The above and other objects, features and advantages of this invention will become more apparent and understandable from the following detailed description, examples and claims.

It is understood that aluminium and aluminium alloys to be coloured by the process of this invention comprise pure aluminium and the alloys of pure aluminium and at least one of such elements as silicon, magnesium, copper, nickel, zinc, chromium, lead, bismuth, iron, titanium, and manganese.

For anodic treatment of aluminium or any of such aluminium alloys, a desired basis metal may first be degreased, rinsed and otherwise suitably pretreated in the conventional manner. The pretreated basis metal is made anodic in the usual acid electrolytic solution containing sulphuric acid, oxalic acid, sulphamic acid or the like, and electric current is passed through the solution between the anodic basis metal and a cathode also immersed therein as the counter electrode.

In accordance with this invention, the anodised workpiece of aluminium or aluminium alloy is electrolysed in an electrolytic solution containing at least two metallic salts and one of the strongly reducing compounds referred to above, in specified ranges using an alternating

50

55

60

65

70

75

80

85

90

95

current voltage up to about 15 volts. The metallic salts can be selected, for example, from such inorganic acid salts as nitrates, sulfates, phosphates, chlorides and chromates, and such organic acid salts as oxalates, acetates and tartrates, of various metals typically comprising nickel, cobalt, chromium, copper, magnesium, iron, cadmium, titanium, manganese, molybdenum, calcium, vanadium, tin, lead and zinc. The concentration of the total amount of any two or more selected metallic salts in the electrolytic solution should be in the range of from 5 to 500 grams per liter and, for the best results, from about 10 to 250 grams per liter.

The desired basis metal can be electrolytically coated in a color which is determined by the combination of any two or more selected metallic salts and by their concentrations in the electrolytic solution. The use of such metallic salts alone, however, would result in relatively low progress of coloring operation in the proposed low voltage process according to the invention, and the throwing power would also be insufficient. The process would therefore be still unsatisfactory particularly when applied to irregularly shaped articles.

The inventive process is totally free from such drawbacks, due to the addition of a strongly reducing compound to the electrolytic solution as taught by this invention. The strongly reducing compound is selected from dithionites such as sodium dithionite and zinc dithionite, thiosulfates such as ammonium thiosulfate, sodium thiosulfate, potassium thiosulfate and iron thiosulfate, thioglycolic acid, and thioglycollates such as ammonium thioglycollate and sodium thioglycollate. The concentration of any selected reducing compound in the electrolytic solution is in the range of from 0.05 to 10 grams per liter and, for the best results, from 0.2 to 3 grams per liter.

Usually, there is further added to the electrolytic solution according to the invention at least one of such inorganic acids as sulfuric acid, nitric acid, hydrochloric acid, phosphoric acid, boric acid, thiocyanic acid and chromic acid; such organic acids as oxalic acid, acetic acid, propionic acid, formic acid, tartaric acid and malic acid; and their ammonium salts, amino salts and imino salts. The concentration of any selected addition agent should range from about 5 to 250 grams per liter.

For electrolytically coloring aluminum or aluminum alloy in accordance with this invention, the anodized basis metal together with a counter electrode is immersed in a bath which has been

prepared as above described, and alternating current is passed through the bath at not more than about 15 volts, desirably from about 5 to 14 volts, and most desirably from about 10 to 12.5 volts.

For the best results, the temperature of the bath should be suitably elevated, preferably to a range of from about 40 to 50°C. Favorable results are also obtainable in a bath temperature range of 15 to 25°C. In practice the bath temperature should be suitably determined in consideration of such factors as the composition of the bath, its stability, the progress of sealing due to the temperature rise of the bath, and the drying of the workpiece at the time of the subsequent color matching operation.

It is for the following reasons that voltages of up to 15 volts are used in the process of this invention. Should the alternating current potential exceed 15 volts, the uniformity of coatings produced would materially deteriorate, although the coloring of the basis metal would proceed at higher speed due to the addition of some selected strongly reducing compound to the bath.

Thus, according to the invention, the desired basis metal can be colored uniformly and speedily by subjecting it to electrolysis in an acidic bath containing at least two metallic salts in the specified range and one of the specified strongly reducing compounds in the specified range by use of alternating current at not more than about 15 volts. Still more improved results are obtainable by suitably elevating the bath temperature, as previously mentioned. The process of this invention is therefore advantageous by reason of higher production, ease of control and, particularly in the case of irregularly shaped articles, uniformity of coloring.

The pores in the films which have been colored by the process of the invention may be sealed by boiling water, by chemicals, or by live steam, as has been known heretofore. After, or without, the sealing treatment, the colored surfaces may be protectively coated with a suitable resin paint as by the dipping or electrodeposition method.

The inventive process is hereinafter described more specifically in terms of several Inventive Examples, which, however, are meant purely to illustrate or explain and not to impose limitations on the invention. Also given hereinbelow are some Comparative Examples which are intended to make clear the advantages of the inventive process over the prior art.

Inventive Example I

For anodic treatment, a specimen consisting of an aluminum extrusion sized

150 millimeters by 70 by 1.3 was degreased, etched and desmutted in the usual manner. The thus pretreated specimen was made anodic in an aqueous solution of 17.5 W/V% sulfuric acid, and a DC voltage of 15 volts was impressed for 35 minutes across the anodic specimen and an aluminum cathode connected as the counter electrode in the bath. The current density was 1.2 amperes per square decimeter. An anodic oxide film with a thickness of about 12 microns was thus formed on the specimen, which was then rinsed.

The electrolytic coloring of the above anodized specimen was conducted in a vessel with a length of 300 millimeters, a width of 100 millimeters and a height of 150 millimetres, in which was filled an electrolytic solution of the following composition:

	g/l
Nickel sulfate (hexahydrate)	25
Magnesium sulfate (heptahydrate)	10
Ammonium thiosulfate	1
Ammonium sulfate	30
DL-malic acid	0.5
Boric acid	10

The pH of the above electrolytic solution was 5.6, and its temperature was 20°C.

The anodized specimen was immersed in the solution, and a single counter electrode was positioned at a distance of 250 millimeters from the specimen. The specimen was then subjected to electrolysis for three minutes by use of alternating current at 12.5 volts. The surfaces of the specimen were colored uniformly in bronze regardless of their positions with respect to the counter electrode.

The above obtained colored film on the specimen was then subjected to sealing treatment for 30 minutes by live steam, under pressure of five kilograms per square centimeter. A 3000-hour accelerated weathering test of the finished specimen by means of a weatherometer developed no change in its colored surfaces. Also, no change in color took place when the specimen was heated to 200°C for two hours, and the specimen remained intact when subjected to a 16-hour CASS (copper-accelerated acetic acid salt spray) test. It has thus been confirmed that aluminum or aluminum alloy colored by the process of this invention will sufficiently withstand exterior use.

Inventive Example II

An aluminum extrusion sized 150 millimeters by 70 by 1.3 was anodized through the same procedure as in Inventive Example I to form thereon an oxide film

with a thickness of about 12 microns. The anodized specimen was rinsed and then electrolyzed for three minutes by use of alternating current at 12 volts in an electrolytic solution of the following composition:

	g/l	
Nickel sulfate (hexahydrate)	25	70
Magnesium sulfate (heptahydrate)	10	
Ammonium dithionite	0.5	
Ammonium sulfate	30	75
Boric acid	10	
Ferrous sulfate (heptahydrate)	15	

The pH of this electrolytic solution was 5.6, and its temperature was 20°C. The specimen was colored uniformly in greenish bronze.

The pores in the thus obtained colored film were then sealed in the manner set forth in Inventive Example I. The finished specimen exhibited the same favorable results as that of the preceding Example when subjected to a 3000-hour accelerated weathering test by means of a weatherometer, a 2-hour heating test at 200°C, and a CASS test.

Inventive Example III

An aluminum extrusion sized 150 millimeters by 70 by 1.3 was anodized through the procedure of Inventive Example I to form thereon an oxide film about 12 microns thick. The anodized specimen was rinsed and then electrolyzed for five minutes by use of alternating current at 10 volts in an electrolytic solution of the following composition:

	g/l	
Nickel sulfate (hexahydrate)	30	
Magnesium sulfate (heptahydrate)	15	105
Copper sulfate (pentahydrate)	7	
Ammonium thiosulfate	1	
Ammonium sulfate	30	
Boric acid	15	

The pH of the above electrolytic solution was 5.6, and its temperature was 20°C. The specimen was colored uniformly in deep maroon.

The pores in the thus obtained colored film on the specimen were sealed in the same manner as in Inventive Example I. The finished specimen exhibited the same favorable results as that of Inventive Example I when subjected to a 3000-hour accelerated weathering test by means of a weatherometer, a 2-hour heating test at 200°C, and a CASS test.

(12)

Comparative Example I

An aluminium extrusion sized 150 millimeters by 70 by 1.3 was anodized through the procedure of Inventive Example I to form thereon an oxide film about 12 microns thick. The anodized specimen was rinsed and then electrolyzed for nine minutes by use of alternating current at 12 volts in an electrolytic solution of the following composition:

	g/l
Nickel sulfate (hexahydrate)	25
Magnesium sulfate (heptahydrate)	20
Boric acid	25
Ammonium sulfate	30

The pH of the above electrolytic solution was 5.6, and its temperature was 20°C.

The specimen was colored in bronze. Its surface which had been directed away from the counter electrode, however, was colored in a significantly lighter shade than the other surface which had been facing the counter electrode, the color on the first mentioned surface becoming still lighter toward its center.

Inventive Example IV

To the electrolytic solution of Comparative Example I was added, in accordance with the teaching of this invention, 0.5 gram per liter of sodium dithionite to prepare a solution of the following composition:

	g/l
Nickel sulfate (hexahydrate)	25
Magnesium sulfate (heptahydrate)	20
Boric acid	25
Ammonium sulfate	30
Sodium dithionite	0.5

The pH of this electrolytic solution was also 5.6, and its temperature was also 20°C.

An aluminium extrusion sized 150 millimeters by 70 by 1.3 was anodized and rinsed through the same procedure as in Comparative Example I and was then electrolyzed for three minutes in the solution of the above composition by use of alternating current at 12 volts. The specimen was colored uniformly in bronze on both of its surfaces, to the same coloring degree as the darker colored surface of the specimen of Comparative Example I which had been electrolyzed for nine minutes.

Comparative Example II

An aluminium extrusion sized 150 millimeters by 70 by 1.3 was anodized through the procedure set forth in Inventive Example I to form thereon an oxide film about 12

microns thick. The specimen was rinsed and then electrolyzed for eight minutes by use of alternating current at 12.5 volts in an electrolytic solution of the following composition:

	g/l
Nickel sulfate (hexahydrate)	30
Boric acid	25
Ammonium sulfate	30

The pH of the above electrolytic solution was 4.5, and its temperature was 40°C.

The specimen was coloured in generally light bronze. Its surface which had been directed away from the counter electrode was colored in a lighter shade than the other surface which had been confronting the counter electrode, and the color on the first mentioned surface became still lighter toward its center.

Comparative Example III

To the electrolytic solution of Comparative Example II was added 1.0 gram per liter of ammonium thiosulfate to form a solution of the following composition:

	g/l
Nickel sulfate (hexahydrate)	30
Boric acid	25
Ammonium sulfate	30
Ammonium thiosulfate	1

The pH of this electrolytic solution was also 4.5, and its temperature was also 40°C.

An aluminum extrusion of the same size as above was anodized and rinsed through the same procedure as in Comparative Example II and was then electrolyzed for eight minutes in the solution of the above composition by use of alternating current at 12.5 volts. The results were just as unsatisfactory as those set forth in Comparative Example II, in spite of the addition of ammonium thiosulfate to the bath.

Inventive Example V

To the electrolytic solution of Comparative Example III was further added, in accordance with the teaching of this invention, 20 grams per liter of magnesium sulfate to prepare a solution of the following composition:

	g/l
Nickel sulfate (hexahydrate)	30
Boric acid	25
Ammonium sulfate	30
Ammonium thiosulfate	1
Magnesium sulfate (heptahydrate)	20

The pH of this electrolytic solution was also 4.5, and its temperature was also 40°C.

5 An aluminum extrusion of the same size as above was anodized and rinsed through the same procedure as in Comparative Example II and was then electrolyzed for three minutes in the solution of the above composition by use of alternating current at 12.5 volts. The specimen was colored 10 uniformly in bronze on both of its surfaces, to the same degree as the darker colored surface of the specimen of Comparative Example II which had been electrolyzed for eight minutes.

15 Inventive Example VI

The procedure of Inventive Example I was faithfully repeated except that the anodized aluminum extrusion was electrolyzed for three minutes by use of 20 alternating current at 12 volts in a solution of the following composition, which had a pH of 5:

	g/l
25 Nickel sulfate (hexahydrate)	25
Magnesium sulfate (hepta-	
hydrate)	20
Ammonium thioglycollate	1.5
Ammonium sulfate	30
Boric acid	20

30 The results were the same as those set forth in Inventive Example III.

WHAT WE CLAIM IS:—

1. A process for electrolytically colouring aluminium or an aluminium alloy which comprises electrolysing anodised 35 aluminium or an aluminium alloy in an acidic, aqueous electrolyte containing at least two colouring metallic salts in the range of from 5 to 500 grams per litre in total and a strong reducing compound 40 selected from dithionites, thiosulphates, thioglycolic acid, and thioglycolates in the range of from 0.05 to 10 grams per litre at an alternating current potential of up to 15 45 volts.

2. The process according to Claim 1, wherein said metallic salts are selected from inorganic and organic acid salts of nickel, cobalt, chromium, copper, 50 magnesium, iron, cadmium, titanium, manganese, molybdenum, calcium, vanadium, tin, lead and zinc.

3. The process according to Claim 1, substantially as hereinbefore described in 55 the Examples.

For the Applicants,
G. F. REDFERN & CO.,
Marlborough Lodge,
14, Farncombe Road,
Worthing,
West Sussex.



(13)

5

1,519,702

5

The pH of this electrolytic solution was also 4.5, and its temperature was also 40°C.

5 An aluminum extrusion of the same size as above was anodized and rinsed through the same procedure as in Comparative Example II and was then electrolyzed for three minutes in the solution of the above composition by use of alternating current at 12.5 volts. The specimen was colored 10 uniformly in bronze on both of its surfaces, to the same degree as the darker colored surface of the specimen of Comparative Example II which had been electrolyzed for eight minutes.

15 Inventive Example VI

The procedure of Inventive Example I was faithfully repeated except that the anodized aluminum extrusion was electrolyzed for three minutes by use of 20 alternating current at 12 volts in a solution of the following composition, which had a pH of 5:

	g/l
25 Nickel sulfate (hexahydrate)	25
Magnesium sulfate (hepta-hydrate)	20
Ammonium thioglycollate	1.5
Ammonium sulfate	30
Boric acid	20

30 The results were the same as those set forth in Inventive Example III.

WHAT WE CLAIM IS:—

1. A process for electrolytically colouring aluminium or an aluminium alloy which comprises electrolysing anodised 35 aluminium or an aluminium alloy in an acidic, aqueous electrolyte containing at least two colouring metallic salts in the range of from 5 to 500 grams per litre in total and a strong reducing compound 40 selected from dithionites, thiosulphates, thioglycolic acid, and thioglycolates in the range of from 0.05 to 10 grams per litre at an alternating current potential of up to 15 volts. 45

2. The process according to Claim 1, wherein said metallic salts are selected from inorganic and organic acid salts of nickel, cobalt, chromium, copper, 50 magnesium, iron, cadmium, titanium, manganese, molybdenum, calcium, vanadium, tin, lead and zinc.

3. The process according to Claim 1, substantially as hereinbefore described in the Examples. 55

For the Applicants,
G. F. REDFERN & CO.,
Marlborough Lodge,
14, Farncombe Road,
Worthing,
West Sussex.