

ANTIFOULING PAINT COMPOSITION

ABSTRACT

An antifouling paint composition containing, as a binder, a mixture comprising (A) from 20 to 80 wt% of a water-insoluble and hydrophobic acrylic resin having a glass transition temperature of from -50 to 0°C and (B) from 80 to 20 wt% of a metal salt of rosin.