

**Specification****STRIPPING COMPOSITIONS FOR SEMICONDUCTOR SUBSTRATES**

5

Cross-Reference to Related Application

This application claims priority to U.S. provisional application serial number 60/085,879, filed May 18, 1998.

10

BACKGROUND OF THE INVENTION**Field of the Invention**

The present invention relates generally to chemical formulations used in semiconductor wafer fabrication and particularly to chemical formulations, including at least boric acid and one or more organic amines and water, that are utilized to remove residue from wafers following a resist plasma ashing step.

Description of the Prior Art

The prior art teaches the utilization of various chemical formulations to remove residue and clean wafers following a photoresist ashing step. Generally, these prior art chemical formulations include strong reagents such as strong acids or strong bases to help remove unwanted inorganic residues. However, such strong reagents can cause unwanted further removal of metal or insulator layers remaining on the wafer and are therefore undesirable in many instances. There is therefore a need for chemical formulations which effectively remove residue following a resist ashing step which do not attack and potentially degrade delicate structures which are meant to remain on a wafer.

SUMMARY OF THE INVENTION

The present invention comprises formulations for stripping wafer residues which originate from a halogen based plasma metal etching followed by oxygen plasma ashing. The



formulations contain the following general components (percentages are by weight):

	Boric Acid	2-17%
	Organic amine or mixture of amines	35-70%
	Water	20-45%
5	Glycol solvent (optional)	0-5%
	Chelating agent (optional)	0-17%

The preferred amines are:

	Monoethanolamine (MEA)
10	Triethanolamine (TEA)

It is an advantage of the present invention that it effectively removes inorganic residues following a plasma ashing step.

It is another advantage of the present invention that it effectively removes metal halide and metal oxide residues following plasma ashing.

It is a further advantage of the present invention that it effectively removes inorganic residue from a semiconductor wafer following plasma ashing without containing a strong acid or a strong base.

These and other features and advantages of the present invention will become understood to those of ordinary skill in the art upon review of the following detailed description of the preferred embodiments.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

Typical steps in the fabrication of semiconductor wafers involve the creation of metalized layers or insulating layers having patterned resist layers formed thereon. Such a wafer may then be exposed to plasmas (such as halogen based plasmas) to remove exposed metal or insulator. Thereafter, a plasma ashing step is conducted (typically using an oxygen based plasma) in which the remaining resist is removed from the wafer. The result is a patterned metal layer or a patterned insulator layer.

This series of steps generally results in a residue which must be removed from the wafer prior to further fabrication steps. The residue following the plasma ashing step is predominantly composed of inorganic compounds such as metal halides and metal oxides.

Various chemical formulations are currently used to remove the inorganic compound residues. These formulations are generally holdovers from older semiconductor fabrication

wet chemical resist removal processes that were used prior to the introduction of the resist plasma ashing technology. The prior formulations thus typically contain strong acids or strong bases to remove residues. The present invention comprises chemical formulations for the removal of inorganic compound residues, where the formulations do not contain the strong acids or strong bases of the prior art formulations.

The present invention comprises new formulations for stripping wafer residues which originate from high density plasma metal etching followed by plasma ashing. The formulations contain boric acid, one or more amines and water or another solvent as primary ingredients with a glycol solvent and/or a chelating agent as optional ingredients.

The preferred formulations utilize the following general components (percentages are by weight):

Boric acid	2-17%
Organic amine or mixture of amines	35-70%
Water	20-45%
Glycol solvent (optional)	0-5%
Chelating agent (optional)	0-17%

The preferred amines are:

Monoethanolamine (MEA)
Triethanolamine (TEA)

The utilization of boric acid in combination with amines is a unique feature of this invention. These formulations provided good stripping performance which can be enhanced by the addition of optional chelating agents and solvents.

The chelating agents are preferably weakly to moderately acidic and contain combinations of two functional groups which include carboxylic acids, aromatic hydroxyl groups, amides, ketones, and aldehydes such that the two groups in the chelating agent are in close proximity to each other.

Preferred chelating agents are:

Catechol	$C_6H_4(OH)_2$
Lactic acid	$CH_3CH(OH)CO_2H$

Other acceptable chelating agents are:

Acetoacetamide	$CH_3COCH_2CONH_2$
Salicylaldehyde	$2-(HO)C_6H_4CHO$

WO 99/60447

PCT/US99/10895

Examples of preferred formulations are:

5	Boric acid	17%
	Monoethanolamine	45%
	Water	32%
	Catechol	6%
10	Boric acid	15%
	Monoethanolamine	43%
	Water	34.8%
	Lactic acid	6.2%
15	Boric acid	10%
	Triethanolamine	38%
	Water	35%
	Acetoacetamide	17%
20	Boric acid	15%
	Monoethanolamine	35%
	Water	35%
	Salicylaldehyde	15%
25	Boric acid	15%
	Monoethanolamine	40%
	Water	45%
30	Boric acid	12%
	Monoethanolamine	45%
	Triethanolamine	10%
	Water	33%
35	Boric acid	17%
	Monoethanolamine	40%
	Water	38%
	Ethylene Glycol	5%

The inventors expect that other closely related ingredients would be expected to show comparable performance to those utilized in the preferred formulations.

These include:

- A. Other organic amines are expected to be suitable:
- B. Other glycol solvents are expected to be suitable.

WO 99/60447

PCT/US99/10895

C. Other chelating agents which are also weakly to moderately acidic and are structurally similar to those claimed are also expected to be suitable.

D. It would also be expected that inclusion of optional components such as surfactants, stabilizers, corrosion inhibitors, buffering agents, and cosolvents would constitute
5 obvious additions to those practiced in the art.

The formulations of the present invention are particularly useful on wafers which have been etched with chlorine- or fluorine-containing plasmas followed by oxygen plasma ashing. The residues generated by this type of processing typically contain inorganic materials such as, but not limited to, aluminum oxide and titanium oxide. These residues are often difficult
10 to dissolve completely without causing corrosion of metal and titanium nitride features required for effective device performance.

Examples

Two types of commercially generated wafers containing vias were evaluated using the
15 formulations of the present invention. In each case, following plasma etching and ashing the residue was removed from the wafer by immersion of the wafer in a formulation bath at 50°-60° for 30 minutes followed by washing with deionized water and drying with a stream of nitrogen gas. It is expected by the inventors that the formulations can also be applied by spraying onto the wafers in an automated spray tool followed by a water rinse.

20 Example 1. A wafer having 1.6 micron diameter, three layer vias comprised of a titanium nitride top layer (40 nm thick), a second layer of silicon oxide (1.3 microns thick), and a bottom layer of aluminum/copper alloy. The substrate was silicon oxide.

Example 2. A wafer having one micron diameter, three layer vias comprised of a silicon oxide top layer (7000 angstroms thick), a second layer of titanium nitride (1200
25 angstroms thick), and a bottom layer of aluminum. The substrate was silicon oxide.

All of the preferred formulations identified above were tested on the wafers of both Example 1 and Example 2. Other formulations within the range of components given above were also tested.

The formulations were rated for relative stripping effectiveness and corrosivity. The
30 preferred formulations scored best and, in overall performance based on both stripping effectiveness and low corrosivity, are approximately equal.

WO 99/60447

PCT/US99/10895

While the present invention has been shown and described with reference to particular preferred embodiments, it is to be understood that other and further changes and modifications of the invention will become apparent to those skilled in the art after understanding the present invention. It is therefore intended that the following claims cover

5 all such alterations and modifications as fall within the true spirit and scope of the invention.

What I claim is:

CLAIMS

1. A semiconductor wafer cleaning formulation for use in post plasma ashing semiconductor fabrication comprising the following components in the percentage by weight ranges shown:

5	Boric acid	2-17%
	At least one amine	35-70%
	Water	20-45%

2. A cleaning formulation as described in claim 1 further including a glycol solvent having a percentage by weight range of 0-5%.

3. A cleaning formulation as described in claim 1 further including a chelating agent having a percentage by weight range of 0-17%.

4. A cleaning formulation as described in claim 2 further including a chelating agent having a percentage by weight range of 0-17%.

5. A cleaning formulation as described in claim 1 wherein said amine is selected from the group consisting of:

Monoethanolamine (MEA)
Triethanolamine (TEA)

6. A cleaning formulation as described in claim 2 wherein said amine is selected from the group consisting of:

Monoethanolamine (MEA)
Triethanolamine (TEA)

7. A cleaning formulation as described in claim 3 wherein said amine is selected from the group consisting of:

Monoethanolamine (MEA)
Triethanolamine (TEA)

8. A cleaning formulation as described in claim 4 wherein said amine is selected from the group consisting of:

Monoethanolamine (MEA)
Triethanolamine (TEA)

WO 99/60447

PCT/US99/10895

9. A cleaning formulation as described in claim 3 wherein said chelating agent is selected from the group consisting of:

5 Catechol
Lactic acid
Acetoacetamide
Salicylaldehyde

10. A cleaning formulation as described in claim 4 wherein said chelating agent is selected from the group consisting of:

5 Catechol
Lactic acid
Acetoacetamide
Salicylaldehyde

11. A cleaning formulation as described in claim 1 further including one or more of the compounds selected from the group consisting of surfactants, stabilizers, corrosion inhibitors, buffering agents, and cosolvents.

12. A cleaning formulation as described in claim 9 comprising:

5 Boric acid 17%
Monoethanolamine 45%
Water 32%
Catechol 6%

13. A cleaning formulation as described in claim 9 comprising:

5 Boric acid 15%
Monoethanolamine 43%
Water 34.8%
Lactic acid 6.2%

14. A cleaning formulation as described in claim 9 comprising:

5 Boric acid 10%
Triethanolamine 38%
Water 35%
Acetoacetamide 17%

15. A cleaning formulation as described in claim 9 comprising:

5 Boric acid 15%
Monoethanolamine 35%
Water 35%
Salicylaldehyde 15%

WO 99/60447

PCT/US99/10895

16. A cleaning formulation as described in claim 1 comprising:
- | | |
|------------------|-----|
| Boric acid | 15% |
| Monoethanolamine | 40% |
| Water | 45% |
17. A cleaning formulation as described in claim 5 comprising:
- | | |
|------------------|-----|
| Boric acid | 12% |
| Monoethanolamine | 45% |
| Triethanolamine | 10% |
| Water | 33% |
18. A cleaning formulation as described in claim 6 comprising:
- | | |
|------------------|-----|
| Boric acid | 17% |
| Monoethanolamine | 40% |
| Water | 38% |
| Ethylene glycol | 5% |
19. A method for fabricating a semiconductor wafer including the steps comprising:
- plasma etching a metalized layer from a surface of the wafer;
 - plasma ashing a resist from the surface of the wafer following the metal etching step;
 - cleaning the wafer in a following step using a chemical formulation including the following components in the percentage by weight ranges shown:
- | | |
|--------------------|--------|
| Boric acid | 2-17% |
| At least one amine | 35-70% |
| Water | 20-45% |
20. A method as described in claim 19 further including a glycol solvent having a percentage by weight range of 0-5%.
21. A method as described in claim 19 further including a chelating agent having a percentage by weight range of 0-17%.
22. A method as described in claim 20 further including a chelating agent having a percentage by weight range of 0-17%.
23. A method as described in claim 19 wherein said amine is selected from the group consisting of:
- Monoethanolamine (MEA)

WO 99/60447

PCT/US99/10895

Triethanolamine (TEA)

24. A method as described in claim 20 wherein said amine is selected from the group consisting of:

Monoethanolamine (MEA)
Triethanolamine (TEA)

25. A method as described in claim 21 wherein said amine is selected from the group consisting of:

Monoethanolamine (MEA)
Triethanolamine (TEA)

26. A method as described in claim 22 wherein said amine is selected from the group consisting of:

Monoethanolamine (MEA)
Triethanolamine (TEA)

27. A method as described in claim 21 wherein said chelating agent is selected from the group consisting of:

5 Catechol
Lactic acid
Acetoacetamide
Salicylaldehyde

28. A method as described in claim 22 wherein said chelating agent is selected from the group consisting of:

5 Catechol
Lactic acid
Acetoacetamide
Salicylaldehyde

29. A method as described in claim 19 further including one or more of the compounds selected from the group consisting of surfactants, stabilizers, corrosion inhibitors, buffering agents, and cosolvents.

30. A method for fabricating a semiconductor wafer as described in claim 25, including the following components in the percentage by weight ranges shown:

Boric acid	17%
Monoethanolamine	45%

WO 99/60447

PCT/US99/10895

5	Water	32%
	Catechol	6%

31. A method for fabricating a semiconductor wafer as described in claim 25, including the following components in the percentage by weight ranges shown:

	Boric acid	15%
	Monoethanolamine	43%
5	Water	34.8%
	Lactic acid	6.2%

32. A method for fabricating a semiconductor wafer as described in claim 25, including the following components in the percentage by weight ranges shown:

	Boric acid	10%
	Triethanolamine	38%
5	Water	35%
	Acetoacetamide	17%

33. A method for fabricating a semiconductor wafer as described in claim 25, including the following components in the percentage by weight ranges shown:

	Boric acid	15%
	Monoethanolamine	35%
5	Water	35%
	Salicylaldehyde	15%

34. A method for fabricating a semiconductor wafer as described in claim 23, including the following components in the percentage by weight ranges shown:

	Boric acid	15%
	Monoethanolamine	40%
5	Water	45%

35. A method for fabricating a semiconductor wafer as described in claim 23, including the following components in the percentage by weight ranges shown:

	Boric acid	12%
	Monoethanolamine	45%
5	Triethanolamine	10%
	Water	33%

WO 99/60447

PCT/US99/10895

36. A method for fabricating a semiconductor wafer as described in claim 24, including the following components in the percentage by weight ranges shown:

5	Boric acid	17%
	Monoethanolamine	40%
	Water	38%
	Ethylene glycol	5%