

Polishing pad and method for polishing a semiconductor wafer

The invention relates to a polishing pad and to a
5 method for polishing a semiconductor wafer.

The semiconductor wafer to be polished is usually a silicon wafer or a substrate having layer structures derived from silicon (e.g. silicon-germanium). Said
10 silicon wafers are used in particular for producing semiconductor components such as memory chips (DRAM), microprocessors, sensors, light emitting diodes and many more.

15 The requirements made of silicon wafers for fabricating in particular memory chips and microprocessors are becoming more and more stringent. This concerns firstly the crystal properties themselves (e.g. with regard to the defect densities, internal getters for trapping
20 metallic impurities), but in particular also the geometry and the flatness of the wafer. A silicon wafer having two perfectly plane-parallel sides, excellent flatness in particular on that side of the silicon wafer on which components are to be fabricated, and low
25 surface roughness would be desirable. It would furthermore be desirable to be able to utilize the entire area of the component side, which is currently not possible on account of a decrease in thickness at the edge of the wafer and poor geometry in the edge
30 region.

It is known that the conventional methods for polishing semiconductor wafers are responsible for this edge roll-off. These include firstly double-side polishing
35 (DSP), which provides for simultaneously polishing both sides of a semiconductor wafer by means of a polishing

pad with the supply of a polishing slurry as removal polishing, and chemical mechanical polishing (CMP), which, by contrast, comprises a final polishing only of the front side ("component side") using a softer polishing pad as so-called haze-free polishing ("finishing"). In both these polishing processes, the abrasives are supplied in the form of a polishing agent slurry.

10 What is relatively new in the polishing of semiconductor wafers, but has already been known and well understood for a fairly long time in the components industry, is so-called "fixed abrasive polishing" (FAP) technology, in which the semiconductor
15 wafer is polished on a polishing pad containing an abrasive substance bonded in the polishing pad ("fixed-abrasive pad").

A polishing step in which such an FAP polishing pad is
20 used is referred to hereinafter for short as FAP step.

An essential difference from DSP and CMP is the fact that the polishing pad comprises no abrasives in DSP and CMP.

25 The German Patent Application DE 102 007 035 266 A1 describes a method for polishing a substrate composed of silicon material, comprising two polishing steps of FAP type, which differ in that, in one polishing step,
30 a polishing agent slurry containing non-bonded abrasive material as a solid material is introduced between the substrate and the polishing pad, while in the second polishing step the polishing agent slurry is replaced by a polishing agent solution that is free of solid
35 materials.

As already mentioned above, semiconductor wafers polished in accordance with the prior art exhibit an undesirable decrease in their thickness in the edge region (edge roll-off).

5

The edge geometry is usually quantified by specifying one or more edge roll-off parameters which usually relate to the total thickness of a silicon wafer or to the edge geometry of its front and/or rear side and
10 which can be used to characterize the customarily observed decrease in the thickness of the silicon wafer in its edge region or the flatness of front and/or rear side of the silicon wafer likewise in its edge region. A method for measuring the edge roll-off of silicon
15 wafers is described in Jpn. J. Appl. Phys. Vol. 38 (1999), pp. 38-39.

The object of the invention is achieved by means of a method for polishing a semiconductor wafer, wherein, in
20 a first step, the rear side of the semiconductor wafer is polished by means of a polishing pad comprising fixedly bonded abrasives having a grain size of 0.1-1.0 μm , and with the supply of a polishing agent which is free of solid materials and which has a pH value of
25 at least 11.8, and, in a second step, the front side of the semiconductor wafer is polished, wherein a polishing agent having a pH value of less than 11.8 is supplied.

30 The inventor has recognized that when polishing the rear side of the semiconductor wafer using a polishing pad comprising fixedly bonded abrasives and also an abrasive-free polishing agent having a pH of greater than or equal to 11.8, the edge roll-off of the
35 thickness of the semiconductor wafer that is observed in conventional polishing methods does not occur,

rather the semiconductor wafer polished in this way even has an increase in the thickness at the edge. It has been found that the pH value of the polishing agent is the crucial criterion in this regard.

5

By means of a subsequent process of polishing the front side using a polishing agent that has to have a pH value of less than 11.8, an outstanding edge geometry of the semiconductor wafer can be produced irrespective of whether the polishing pad contains fixedly bonded abrasives or whether it is free of abrasives (like conventional CMP polishing pads).

This is due to the fact that FAP methods using polishing agents having a pH of less than 11.8, in a similar manner to conventional CMP polishing methods (which are largely independent of the pH value of the polishing agent), tend toward producing an edge roll-off.

20

Since, however, an increase was previously produced at the edge during the polishing of the rear side, the polishing of the front side results in a compensation of these two effects.

25

This results in a semiconductor wafer having no edge roll-off of its thickness whatsoever.

A long-standing need is thus satisfied, especially since precisely the edge roll-off and the poor geometry in the edge region of the wafer were responsible for the fact that rather than the whole wafer area, only a wafer area minus a specific edge exclusion (2-3 mm) was able to be utilized for the production of components. A huge increase in productivity can be expected as a result of this invention, since, by means of the

invention, the edge exclusion is reduced practically to zero and a semiconductor wafer in which the entire wafer area can be utilized is actually made accessible for the first time.

5

The invention was not suggested by the prior art. Although it was known from DE 102 007 035 266 A1 to employ FAP using polishing agents in the alkaline range of pH 10-12, the method claimed therein necessarily
10 provides two FAP polishing processes, one with and one without polishing agent containing abrasives, on one and the same side of the semiconductor wafer. The combination of an FAP polishing process on the rear side and a second FAP or CMP polishing process on the
15 front side of the semiconductor wafer is not disclosed.

Moreover, it was not recognized in the prior art that at a pH of greater than or equal to 11.8 a selective material removal results by virtue of less material
20 being removed in the edge region of the semiconductor wafer than e.g. in the center of the semiconductor wafer. There is also no reason to carry out investigations in this regard since the person skilled in the art previously assumed that the pH value both in
25 the case of FAP and in the case of CMP could not have such a selective effect, but rather chemically supports or amplifies the mechanical removal by the abrasives bonded in the polishing pad in the case of FAP and chemically supports or amplifies the mechanical removal
30 by the abrasive materials contained in the polishing agent in the case of CMP, and this chemical support or amplification takes place uniformly over the entire wafer area.

35 The fact that this turns out to be quite different in the case of FAP and the pH value of the polishing agent

allows such a selective removal is surprising. The fact that FAP technology could be suitable for practically completely eliminating the edge roll-off that otherwise always occurs in all polishing methods was by no means
5 foreseeable. Those skilled in the art previously assumed that it is necessary to keep the material removals in any polishing methods as small as possible and to attempt, by means of concave or convex polishing of the semiconductor wafer, to restrict the edge roll-
10 off as far as possible to the outermost edge region.

Accordingly, the edge roll-off in polished wafers was accepted as given.

15 In subsequent epitaxy steps, attempts were made in the prior art to compensate for said edge roll-off in pretreatment steps in the epitaxy reactor.

Other attempts to remove the poor geometry in the edge
20 region by edge grinding do not constitute a suitable solution, especially since the damage produced at the edge in the process, during handling, constitutes a virtually intractable problem, that is to say that the edge grinding would in any event have to be followed by
25 an edge polishing process. Although this would be suitable for removing the edge roll-off after DSP, an edge roll-off would be established again after a later CMP step, such that this hardly proves to be economic either.

30 Thus, the method claimed here constitutes the only possibility for providing a finely polished wafer (after CMP or FAP of the front side) without such an edge roll-off directly after the polishing of the front
35 side and without any additional measures.

In the course of the production - becoming ever more important - of wafers having outstanding geometrical and nanotopological properties - specifically in the context of the 22 nm design rule requirements (according to ITRS = "International Technology Roadmap for Semiconductors") - and with regard to the progressive enlargement of the wafer diameter (transition from 300 nm to 450 nm), it was important to develop polishing methods that meet these requirements.

10

Especially in the context of obtaining the requisite geometry, here primarily the wafer edge geometry and the nanotopology, it had already been apparent for a fairly long time that a material-removing conventional chemical mechanical polishing (CMP) would no longer be able, in terms of process engineering, to meet these requirements, in particular with regard to the edge roll-off of the semiconductor wafer and, associated herewith, the edge exclusion or the area on the semiconductor wafer that can be utilized with regard to the required geometry properties (the person skilled in the art also uses the term "fixed quality area").

20

The polishing process according to the invention using a polishing pad comprises fixedly bonded abrasives in the claimed range of pH values is carried out either in the context of a single-side polishing of only the rear side or in a simultaneous double-side polishing process.

30

During the method, the pH value can be varied or can be set to a constant value, depending on the initial geometry of the semiconductor wafer to be polished.

35

A two-stage FAP, embodied as sequential polishing of the rear and front sides, by means of a polishing pad

comprising fixedly bonded abrasives, is especially preferred.

5 In this case, the two polishing processes, that is to say the rear side polishing and the front side polishing, can be coordinated with one another, such that targeted influencing of the wafer geometry and wafer nanotopology, especially in the wafer edge region, can be performed.

10

For this purpose, according to the invention, the rear side has to be polished using a different pH value than the front side.

15 Thus, by superposing the two polishing profiles (front side and rear side), in particular a very specific resultant edge profile can be produced and the edge roll-off can ideally be reduced to zero.

20 The variation of the pH value is thus used according to the invention for changing the thickness profile at the outer wafer edge.

25 By contrast, the diverse chemical mechanical polishing methods, irrespective of the way in which the method is carried out (double-side polishing, single-side polishing, removal or haze-free polishing), are carried out using a fixed pH value. Targeted influencing of the geometry in the edge region of the semiconductor wafer
30 is thus precluded.

The method according to the invention affords advantages in particular for the polishing of semiconductor wafers of the new technology generation
35 having a diameter of 450 mm, especially since the problems of the geometry in the edge region with the

use of conventional polishing methods are accentuated in the case of such large diameters. The pH-controlled polishing, as claimed in the method according to the invention, eliminates these problems.

5 The method according to the invention leads to an improvement in the geometry in the outer edge region of the semiconductor wafer, in particular in a range of a distance of less than or equal to 10 mm, particularly
10 preferably in the range of less than or equal to 5 mm with respect to the edge of the semiconductor wafer.

The polishing agent solution during the polishing of the rear side of the semiconductor wafer preferably
15 comprises compounds such as sodium carbonate (Na_2CO_3), potassium carbonate (K_2CO_3), sodium hydroxide (NaOH), potassium hydroxide (KOH), ammonium hydroxide (NH_4OH), tetramethylammonium hydroxide (TMAH) or any desired mixtures thereof.

20 The proportion of the stated compounds in the polishing agent solution is preferably 0.01 to 10% by weight, particularly preferably from 0.01 to 0.2% by weight.

25 The use of potassium carbonate is especially preferred.

The pH value of the polishing agent solution is at least 11.8.

30 The polishing agent solution can furthermore contain one or more further additives, for example surface-active additives such as wetting agents and surfactants, stabilizers acting as protective colloids, preservatives, biocides, alcohols and complexing
35 agents.

In the method according to the invention, a polishing pad containing an abrasive material bonded in the polishing pad (FAP or FA pad) is used during the polishing of the rear side.

5

Suitable abrasive materials comprise for example particles of oxides of the elements cerium, aluminum, silicon, zirconium and particles of hard materials such as silicon carbide, boron nitride and diamond.

10

Particularly suitable polishing pads have a surface topography shaped by replicated microstructures. These microstructures ("posts") have for example the form of columns having a cylindrical or polygonal cross section or the form of pyramids or truncated pyramids.

15

More detailed descriptions of such polishing pads are contained for example in WO 92/13680 A1 and US 2005/227590 A1.

20

The use of cerium oxide particles bonded in the polishing pad is particularly preferred, cf. also US6602117B1.

25 The average particle size of the abrasives contained in the FAP polishing pad is preferably 0.1-1.0 μm , particularly preferably 0.1-0.6 μm , and especially preferably 0.1-0.25 μm .

30 A polishing pad having a multilayered construction is particularly suitable for carrying out the method. One of the layers of the polishing pad is compliant in this case. The pad height can thus be adapted and follow continuous transitions. The compliant layer is
35 preferably a non-woven layer. A layer composed of

polyester fibers impregnated with polyurethane is particularly suitable ("non-woven").

5 The compliant layer preferably corresponds to the bottom-most layer of the polishing pad. Situated above it is preferably a foam layer composed of polyurethane, for example, which is fixed on the compliant layer by means of an adhesive layer. Situated above the PU foam is a layer composed of a harder, stiff material,
10 preferably composed of a hard plastic, for which polycarbonate, for example, is suitable. Situated above this stiff layer is the layer having the micro-replicated structures, that is to say the actual fixed abrasive layer.

15 However, the compliant layer can also be situated between the foam layer and the stiff layer or directly underneath the fixed abrasive layer.

20 The various layers are fixed to one another preferably by means of pressure-sensitive adhesive layers (PSA).

The inventor has recognized that a polishing pad without the PU foam layer that is always present in the
25 prior art of FAP polishing pads leads to good results.

In this case, the polishing pad comprises a layer having the microreplicated structures, a compliant layer and a layer composed of a stiff plastic such as
30 polycarbonate, wherein the compliant layer can be either the middle or the bottom-most layer of the polishing pad.

These novel polishing pads are suitable in particular
35 for use in a multi-plate polishing machine (AMAT Reflection from Applied Materials, Inc.). This

polishing machine comprises a 5 zone membrane carrier, which permits the pressure profile of the carrier to be set differently in 5 zones. In conjunction with the compliant polishing pads, this leads to outstanding results with regard to the geometry of the polished wafers.

A polishing agent containing abrasives is preferably used during the polishing of the front side of the semiconductor wafer.

The proportion of the abrasive material in the polishing agent slurry is preferably 0.25 to 20% by weight, particularly preferably 0.25 to 1% by weight.

The size distribution of the abrasive material particles is preferably monomodal in nature.

The average particle size is 5 to 300 nm, particularly preferably 5 to 50 nm.

The abrasive material comprises a material that mechanically removes the substrate material, preferably one or more of the oxides of the elements aluminum, cerium or silicon.

A polishing agent slurry containing colloiddally disperse silica is particularly preferred.

The polishing agent slurry preferably contains added to it additives such as sodium carbonate (Na_2CO_3), potassium carbonate (K_2CO_3), sodium hydroxide (NaOH), potassium hydroxide (KOH), ammonium hydroxide (NH_4OH), tetramethylammonium hydroxide (TMAH)

However, the polishing agent slurry can contain one or more further additives, for example surface-active additives such as wetting agents and surfactants, stabilizers acting as protective colloids, 5 preservatives, biocides, alcohols and complexing agents.

The pH value during the polishing of the front side must be less than 11.8.

10

The pH value preferably lies in the range of 10-11.5.

A polishing pad comprising no fixedly bonded abrasives is preferably used during the polishing process.

15

Conventional CMP polishing pads are suitable for this purpose. The CMP polishing pads used are polishing pads having a porous matrix.

The polishing pad preferably comprises a thermoplastic or heat-curable polymer. A multiplicity of materials, 20 e.g. polyurethanes, polycarbonate, polyamide, polyacrylate, polyester, etc., are appropriate as material.

25

The polishing pad preferably comprises solid, microporous polyurethane.

The use of polishing pads composed of foamed plates or felt or fiber substrates which are impregnated with 30 polymers is also preferred.

35

Coated/impregnated polishing pads can also be configured in such a way that there is a different pore distribution and sizes in the substrate than in the coating.

The polishing pads can be substantially planar or else perforated.

In order to control the porosity of the polishing pad,
5 fillers can be introduced into the polishing pad.

Commercially available polishing pads are e.g. the SPM 3100 from Rodel Inc. or the pads of the DCP-Series and also the pads with the trade marks IC1000™, Polytex™ or
10 SUBA™ from Rohm & Hass.

Instead of the polishing pads described, however, it is possible, which is likewise preferred, to use an FAP pad such as the one used during the polishing of the
15 rear side.

In principle, the semiconductor wafers are pressed by the side surface to be polished against the polishing pad lying on a polishing plate, with the aid of a
20 polishing head.

A polishing head also includes a retainer ring which laterally encloses the substrate and prevents it from sliding from the polishing head during polishing.

25

In the case of modern polishing heads, that side surface of the silicon wafer which is remote from the polishing pad lies on an elastic membrane that transmits the polishing pressure exerted. The membrane
30 is part of a possibly subdivided chamber system that forms a gas or liquid cushion.

However, polishing heads are also used in the case of which an elastic support ("backing pad") is used
35 instead of a membrane.

The substrate is polished with a polishing agent being supplied between the substrate and the polishing pad and with the polishing head and the polishing plate being rotated.

5

In this case, the polishing head can additionally also be moved translationally over the polishing pad, whereby a more comprehensive utilization of the polishing pad area is obtained.

10

Furthermore, the method according to the invention can equally be carried out on single-plate and multi-plate polishing machines.

15

The use of multi-plate polishing machines having preferably two, especially preferably three, polishing plates and polishing heads is preferred.

Example

20

In a first step, by means of a polishing pad comprising fixedly bonded abrasives with the supply of a polishing solution set to a specific pH value, the rear side of a silicon wafer having a diameter of 300 mm is polished in such a way that a specific thickness profile arises at the edge.

25

The polishing pad comprises microreplicated structures in the form of truncated pyramids having particles of cerium oxide (CeO_2).

30

The particle size is 0.1 to 1.0 μm .

The FAP polishing process is able, exclusively by means of an increase in the pH value of an alkaline solution, without the use of a silica sol, to convert the

35

otherwise expected edge roll-off into an edge elevation, that is to say to produce curvatures in opposite directions as required.

5 As a result of the polishing of the rear side by means of an abrasive-free polishing solution having a pH value of at least 11.8, an elevation is produced in the wafer edge region and a bias is thus created which, during a subsequent process of polishing the front side
10 of the wafer, which takes place with a pH value of 11.2, compensates for the edge roll-off that tends to be formed in this case, and a planar wafer edge region is thus formed.

15 In this case, the polishing of the front side can be implemented as a customary CMP step or as fixed abrasive polishing with a pH value of less than 11.8. Both polishing methods lead to the formation of a wafer edge roll-off. The method according to the invention
20 was carried out successfully for both types of front side polishing.

It was found in the experiments that it is advantageous, for setting a desired surface roughness
25 of the rear side of the wafer, to carry out a second partial polishing step using a suitable silica sol, such as e.g. Glanzox 3900*, which likewise takes place on the FAP polishing pad.

30 *Glanzox 3900 is the product name for a polishing agent slurry that is offered as a concentrate by Fujimi Incorporated, Japan. The concentrate having a pH of 10.5 contains approximately 9% by weight of colloidal SiO₂ having an average particle size of 30 to 40 nm.

Further typical conventional CMP polishing steps (soft pad + alkaline silica sol) can be added at any time as haze-free polishing processes with small removals for further reduction of the surface roughness and for
5 reduction of the defect density (e.g. LLS = "localized light scatterers"), but are not essential to the success of the invention.

Patent Claims:

1. A polishing pad for use in apparatuses for polishing semiconductor wafers, comprising a layer containing abrasives, a layer composed of a stiff plastic and also a compliant, non-woven layer, wherein the layers are bonded to one another by means of pressure-sensitive adhesive layers.
2. The polishing pad as claimed in claim 1, wherein the layer composed of a stiff plastic comprises polycarbonate.
3. The polishing pad as claimed in claim 1 or 2, wherein the polishing pad comprises an additional layer composed of polyurethane form.
4. The polishing pad as claimed in any of claims 1 to 3, wherein the compliant layer comprises polyester fibers.
5. The polishing pad as claimed in any of claims 1 to 4, wherein the layer containing abrasives comprises particles of oxides of the elements cerium, aluminum, silicon or zirconium or particles of hard materials such as silicon carbide, boron nitride or diamond.
6. Polishing a semiconductor wafer using a polishing pad containing abrasives as claimed in claims 1 to 5.