



Description

The present invention relates generally to devices incorporating liquid crystals and, more particularly, to devices incorporating liquid crystal material and containment means therefor. Moreover, the invention relates to devices using encapsulated liquid crystals and to methods of making encapsulated liquid crystals.

Liquid crystals currently are used in a wide variety of devices, including optical devices such as visual displays. Such devices usually require relatively low power and have satisfactory response time, provide reasonable contrast, and are relatively economical. The property of liquid crystals enabling use, for example, in visual displays, is the ability of liquid crystals to transmit light on one hand, and to scatter light and/or to absorb light, on the other, in dependence on whether the liquid crystals are in a relatively free, i.e. deenergized or field off state or in a strictly aligned, i.e. an energized or field on state, e.g. with an electric field applied across the liquid crystal material. An example of electrically responsive liquid crystal material and use thereof is provided in U.S. Patent 3,322,485.

Certain liquid crystal material is responsive to temperature, changing optical characteristics in response to temperature of the liquid crystal material.

The invention of the present application is disclosed hereinafter particularly, but not exclusively, with reference to use of liquid crystal material that is particularly responsive to electric field.

Currently there are three categories of liquid crystal materials, namely cholesteric, nematic and smectic types. The invention of the present application relates in a preferred embodiment described below to use of nematic liquid crystal material or to a combination of nematic and some cholesteric type. However, various principles of the invention may be employed with various one or ones of the known types of liquid crystal material or combinations thereof. The various characteristics of the cholesteric, nematic and smectic types of liquid crystal material are described in the prior art. One known characteristic of liquid crystal material is that of reversibility; in particular it is noted here that nematic liquid crystal material is known to be reversible, but cholesteric material is not reversible.

To enhance contrast and possibly other properties of liquid crystal material, pleochroic dyes have been mixed with the liquid crystal material to form a solution therewith. The molecules of pleochroic material generally align with the molecules of the liquid crystal material. Therefore, such pleochroic dyes will tend to function optically in a manner similar to that of the liquid crystal material in response to a changing parameter, such as application or non-application of an electric field. Examples of pleochroic dyes with liquid crystal material are described in U.S. Patents 3,499,702 and 3,551,026.

An important characteristic of liquid crystal material is anisotropy. Anisotropic material has different physical properties in different directions. For example, liquid crystals may be optically anisotropic such that when the molecules are randomly oriented they permit light transmission and, when they are aligned due to application of an electric field thereacross, light may be transmitted through the liquid crystal material.

Liquid crystal material also has electrical anisotropy. For example, the dielectric constant for nematic liquid crystal material may be one value when the liquid crystal molecules are parallel to the electric field and may have a different value when the liquid crystal molecules are aligned perpendicular to an electric field. Since such dielectric value is a function of alignment, for example, reference to the same as a "dielectric coefficient" may be more apt than the usual "dielectric constant" label. Similar properties are true for other types of liquid crystals.

Some brief discussion of encapsulation of cholesteric liquid crystal material is presented in U.S. Patents 3,720,623, 3,341,466 and 2,800,457, the latter two Patents being referred to in the former Patent.

In the past devices using liquid crystals, such as visual display devices or other devices, have been of relatively small size. Large size devices using liquid crystals, such as, for example, a billboard display or a sign have not been able to be made satisfactorily for a number of reasons. One reason is the fluidity of the liquid crystals, (the liquid crystal material may tend to flow creating areas of the display that have different thicknesses). As a result, the optical characteristics of the display may lack uniformity, have varying contrast characteristics at different portions of the display, etc.; the thickness variations cause variations or gradations in optical properties of the liquid crystal device. Moreover, the varying thickness of the liquid crystal material will cause corresponding variations in the electrical properties of the liquid crystal material, such as capacitance and impedance, further reducing uniformity of a large size liquid crystal device. The varying electrical properties of the liquid crystal material, then, also may cause a corresponding variation in the effective electric field applied across the liquid crystal material and/or in response to a constant electric field would respond differently at areas of the liquid crystal that are of different thicknesses.

A pleochroic display, i.e. one in which pleochroic dye and liquid crystal material are in solution, has the advantage of not requiring a polarizer. However, such a pleochroic device has a disadvantage of relatively low contrast when used directly in the nematic form. It was discovered in the past, though, that a cholesteric liquid crystal material could be added to the nematic one together with the dye to improve the contrast ratio. See White et al article, "Journal of Applied Physics", Volume 45, No. 11, November 1974, at pages 4718-4723, for example. The cholesteric material would tend



not to return to its original zero field form when the electric field is removed.

Another problem encountered with pleochroic dye included in solution with liquid crystal material, regardless of the particular type of liquid crystal material, is that the absorption of the dye is not zero in the field-on condition; rather such absorption in the field-on condition follows a so-called ordering parameter, which relates to or is a function of the relative alignment of the dyes. The optical transmission characteristic of liquid crystal material is an exponential function of thickness of the liquid crystal material; specifically, the on state or field-on or energized state of the liquid crystal material is an exponential function of thickness of the liquid crystal material, and the absorbing state or off state also is a different exponential function of thickness.

To overcome those problems described in the two immediately preceding paragraphs, the liquid crystal material should have an optimum uniform thickness. (As used herein liquid crystal material means the liquid crystals themselves and, depending on context, a pleochroic dye in solution therewith.) There also should be an optimum spacing of the electrodes by which the electric field is applied to the liquid crystal material. To maintain such optimum thickness and spacing, rather close tolerances must be maintained. To maintain close tolerances, there is a limit as to the size of the device using such liquid crystals, for it is quite difficult to maintain close tolerances over large surface areas, for example.

In accordance with one aspect of the invention there is provided a liquid crystal device comprising liquid crystal material and containment means therefor for inducing a distorted alignment of said liquid crystal material, and which in response to such alignment scatters and/or absorbs light and which in response to an input reduces the amount of scattering and/or absorption.

In another aspect, the invention provides a liquid crystal device comprising liquid crystal material and containment means for containing the liquid crystal material in a plurality of volumes, wherein the ordinary index of refraction of the liquid crystal material is substantially equal to the index of refraction of the containment means for maximizing optical transmission through the apparatus in the presence of an input.

In a further aspect, the invention provides a method of making encapsulated nematic liquid crystal material comprising mixing at least an encapsulating medium, a nematic liquid crystal material, and a pleochroic dye.

In a still further aspect, the invention provides a method of causing nematic liquid crystal material to perform substantially independently of the optical polarization direction of incident light, comprising confining such nematic liquid crystal material in at least one capsule which causes distortion of the direction of the liquid crystal material.

In a yet further aspect, the invention provides a method of making encapsulated liquid crystal material comprising mixing an encapsulating medium and a nematic liquid crystal material, wherein the liquid crystal material has an ordinary index of refraction substantially the same as the index of refraction of the encapsulating medium.

Various preferred features and embodiments of the invention are described below.

Briefly, embodiments of the invention are particularly concerned with liquid crystal material and especially nematic material, which is encapsulated and used in liquid crystal devices, such as relatively large size display devices.

Some terms used herein generally are defined as follows: liquid crystal material broadly refers to any type of liquid crystal material that will work in the context of the present invention, but preferably refers to nematic type. Such liquid crystal material also may include pleochroic dye or other ingredient. A capsule refers to a containment device or medium that confines a quantity of liquid crystal material, and encapsulating medium or material is that medium or material of which such capsules are formed. An encapsulated liquid crystal or encapsulated liquid crystal material means a quantity of liquid crystal material confined or contained in the encapsulating medium, such as the noted capsules. A liquid crystal device is a device formed of liquid crystal material, in the present invention such devices are formed of encapsulated liquid crystals capable of providing a function of the type typically inuring to liquid crystal material; for example, such a liquid crystal device may be a visual display that in response to application and removal of an electric field effects a selected attenuation of visible light.

One method of making encapsulated liquid crystals includes mixing together liquid crystal material and an encapsulating medium in which the liquid crystal material will not dissolve and permitting formation of discrete capsules containing the liquid crystal material.

A method of making a liquid crystal device including such encapsulated liquid crystal includes, for example applying such encapsulated liquid crystal material to a substrate. Moreover, such a method may include providing means for applying an electric field to the liquid crystal material to affect a property thereof.

According to one embodiment of the invention a nematic material with positive dielectric anisotropy in which may be dissolved a pleochroic dye is placed in a generally spherical capsule. The capsule wall distorts the liquid crystal molecules so they and the dye when no field is applied will tend to absorb all directions of polarized light. When a suitable electric field is applied across such a capsule, for example across an axis thereof, the liquid crystal material will tend to align parallel to such field causing the absorption characteristics of such material to be reduced to one assumed when the liquid crystal material is in



planar configuration. To help assure that adequate electric field is applied across the liquid crystal material in the capsule, and not just across or through the encapsulating medium, and, in fact, with a minimum voltage drop across the wall thickness of the respective capsules, the encapsulating material may have a dielectric constant near to that of the liquid crystal material, on the one hand, and a relatively large impedance, on the other hand, and the liquid crystal material itself may have a positive dielectric anisotropy.

Contrast of a liquid crystal device employing encapsulated liquid crystals may be improved by selecting an encapsulating medium that has an index of refraction that is matched to the ordinary index of refraction of the liquid crystal material. The encapsulating medium may be used not only to encapsulate liquid crystal material but also to adhere the capsules to a substrate for support thereon. Alternatively, a further binding medium may be used to hold the liquid crystal capsules relative to a substrate. In the latter case, though, preferably the additional binding medium has an index of refraction which is matched to that of the encapsulating medium for maintaining the improved contrast characteristic described above.

A feature of the spherical or otherwise curved capsule which confines the liquid crystal material therein in accordance with embodiments of the present invention is that the liquid crystal material tends to follow the curvature or otherwise to align generally parallel with the curved surfaces of such capsule. Accordingly, the individual liquid crystal molecules tend to be forced or distorted to a specific form, being folded back on themselves in a sense as they follow the capsule wall, so that the resulting optical characteristic of a given capsule containing liquid crystal material is such that substantially all light delivered thereto will be absorbed when no electric field is applied, regardless of the polarization direction of the incident light. Even without dye this effect causes scattering and thus opacity.

Another feature is the ability to control the effective thickness of the liquid crystal material contained in a capsule by controlling the internal diameter of such capsule. Such diameter control may be effected by a separation process during the method of making the encapsulated liquid crystals using any one of a variety of conventional or novel sorting techniques as well as by controlling the mixing process, the quantities of ingredients, and/or the nature of the ingredients provided during mixing. By controlling such thickness parameter to relatively close tolerances, then, the subsequent tolerance requirements when the final liquid crystal device is made using the encapsulated liquid crystals will not be as critical as was required in the past.

Moreover, a further and very significant

feature of the present invention is that there appears to be no limitation on the size of a high quality liquid crystal device that can be made using the encapsulated liquid crystals in accordance with the present invention. More specifically, by providing confinement for discrete quantities of liquid crystal material, for example, in the described capsules, the various problems encountered in the past that prevented use of liquid crystal material in large size devices are overcome, for each individual capsule in effect can still operate as an independent liquid crystal device. Moreover, each capsule, then, preferably has physical properties enabling it to be mounted in virtually any environment including one containing a plurality of further such liquid crystal capsules mounted to a substrate or otherwise supported for use in response to application and removal of some type of excitation source, such as, for example, an electric field or the like.

Important considerations in accordance with the invention, and the discovery of the inventor, are that an encapsulating medium having electrical properties matched in a prescribed way to the electrical properties of liquid crystal material encapsulated thereby and additionally preferably optically matched to optical properties of such liquid crystal material permits efficient and high quality functioning of the liquid crystal material in response to excitation or non-excitation by an external source; and that the interaction of the encapsulating medium with the liquid crystal material distorts the latter in a prescribed manner changing an operational mode of liquid crystal material. Regarding the latter, by forcing the liquid crystal molecules to distort into generally parallel or conforming alignment with the capsule wall, the liquid crystals will absorb or block, rather than transmit, light when not subject to an electric field and will be functional with respect to all manners of incident light regardless of the direction of polarization of such incident light.

Thus, we have found it possible, in accordance with various embodiments of the invention, to enable the use of liquid crystal material over relatively large surfaces, and especially to effect the same while maintaining relatively high quality of operation, controlled uniformity of output and satisfactory contrast;

to confine liquid crystal material while maintaining optical characteristics of such material, and especially to effect the same also maintaining electrical responsiveness of the liquid crystal material;

to encapsulate nematic liquid crystal material in a non-interacting medium;

to achieve a useful encapsulation of nematic liquid crystal material;

to utilize both physical e.g. alignment, and optical, e.g. index of refraction, characteristics of material of the liquid crystal type;



utilize resin material for encapsulating liquid crystal material, and especially to effect the same to form curved and most preferably spherical capsules containing discrete quantities of liquid crystal material;

to eliminate restrictions on size of displays or other devices of the liquid crystal type, especially while achieving high quality operation, satisfactory contrast, wide viewing angle and adequate response time;

to force a liquid crystal material to its zero field form, particularly when such material includes a combination of liquid crystal material and pleochroic dye material and even when the liquid crystal material includes more than one type of liquid crystal material;

to enable use of nematic liquid crystal material with pleochroic dye in solution therewith while obtaining an effect of having cholesteric material added thereto even without the latter, and more specifically, to enable liquid crystal material that contains pleochroic dye to absorb light in all directions and to minimize partial light transmission when in field off conditions, i.e. when no electric field is applied to the liquid crystal material;

to distort the internal structure of liquid crystal material to achieve enhanced optical properties;

to achieve controlled light distortion and especially such controlled distortion of light entering liquid crystal material that is contoured in an encapsulating medium;

to provide a uniform area over which a constant and uniform electric field may be delivered to discrete quantities of liquid crystal material and especially when such material is contained in discrete capsules;

to control the size of the electric field required to operate the liquid crystal device;

to improve the uniformity of turn on or operation of a liquid crystal device, and especially to facilitate the control of such turn on or operation;

to control the uniformity of the size and/or other dimensional characteristics of liquid crystal capsules;

to encapsulate liquid crystal material in a resin or other material and most preferably to effect such encapsulation while forming discrete capsules containing liquid crystal material;

to use a single medium for encapsulating liquid crystal material in discrete capsules or the like and for binding the capsules together and/or to a support substrate or the like;

to use an optically anisotropic liquid crystal in a limited optically isotropic manner, e.g. by causing a polarization direction sensitive liquid crystal material to eliminate such sensitivity;

to impose elastic energy on liquid crystal material, and especially to effect the same to cause unusual properties in such liquid crystal material;

to control the ease of alignment of liquid crystals;

to facilitate applying liquid crystal material to a substrate;

to facilitate interfacing or applying of electrodes with respect to liquid crystal type material;

to apply electrodes directly to liquid crystal material;

to improve a method for making liquid crystal devices, especially by encapsulating the liquid crystal materials;

to control the requirements of voltage or electric field required to operate a liquid crystal device;

to stop scattering or absorption by liquid crystal material when an electric field is applied thereto; and

to control the amount of voltage drop that occurs across liquid crystal material.

The following description and the annexed drawings set forth in detail certain non-limiting illustrative embodiments of the invention.

In the annexed drawings:

Fig. 1 is a schematic representation of a prior art liquid crystal device;

Fig. 2 is a schematic representation of a liquid crystal device in accordance with the present invention;

Fig. 3 is an isometric view of a liquid crystal display device in accordance with the present invention;

Fig. 4 is an enlarged fragmentary view, partly broken away, of a portion of the liquid crystal display device of Fig. 3;

Fig. 5 is an enlarged schematic illustration of a liquid crystal capsule in accordance with the present invention under a no field condition;

Fig. 6 is a view similar to Fig. 5 under an applied electric field condition; and

Fig. 7 is a schematic electric circuit diagram representation of the capsule with an applied field.

Referring now in detail to the drawings, wherein like reference numerals designate like parts in the several Figures, and initially to Fig. 1, a prior art liquid crystal device is generally indicated at 1. Such device 1 includes liquid crystal material 2 sandwiched between electrodes 3 of, for example, indium doped titanium oxide that are deposited for support on respective mounting or confining substrates 4, such as glass, plastic sheets or the like. The sheets 4 may be clear as may be the electrodes 3 so that the device 1 is an optical transmission control device, whereby incident light may be scattered when no electric field is applied by the electrodes 3 across a liquid crystal material 2 and the incident light may be transmitted through the liquid crystal material 2 when an electric field is applied thereacross. Electric leads 5 and switch 6 selectively couple voltage source 7 across the electrodes 3 to provide such electric field. The voltage source 7 may be either an AC or a DC voltage source.

The liquid crystal material 2, and specifically the individual molecules thereof, in the device 1 are somewhat confined by the substrates 4 for retention in a desired location, say for example, to be used overall as part of a digital display device. On the other hand, the liquid crystal material 2, and



specifically the individual molecules thereof, must have adequate freedom of movement so that they may assume either a random orientation or distribution when no electric field is applied or a prescribed distributional or orientational alignment when an electric field is applied across the electrodes 3. If desired, one of the substrates 4 may be reflective to reflect incident light received through the liquid crystal material 2 back through the latter for delivery through the other substrate 4 for subsequent use. The various principles of operation and features and disadvantages of the liquid crystal device 1 are summarized above and are described in the prior art literature.

The liquid crystal material 2 may be of virtually any type that is responsive to an electric field applied thereacross so as to have a desired operating characteristic intended for the device 1; the liquid crystal material 2 also may include, if desired, pleochroic dye material in solution therewith.

Turning now to Fig. 2, an improved liquid crystal device in accordance with the present invention is indicated at 10. The device 10 includes an encapsulated liquid crystal 11 which is supported from a mounting substrate 12 across which an electric field may be applied via electrodes 13, 14.

The electrode of 13 may be, for example, a quantity vacuum deposited indium doped titanium oxide applied to the substrate 12, and the electrode 14 may be, for example, electrically conductive ink. A protective layer or coating 15 may be applied over the electrode 14 for protective purposes but such layer 15 ordinarily would not be necessary for supporting or confining the encapsulated liquid crystal 11 or the electrode 14. Voltage may be applied to the electrodes 13, 14 from an AC or DC voltage source 16, selectively closable switch 17, and electrical leads 18, 19 in turn to apply an electric field across the encapsulated liquid crystal 11 when the switch 17 is closed.

The encapsulated liquid crystal 11 includes liquid crystal material 20 contained within the confines or interior volume 21 of a capsule 22. According to the preferred embodiment and the best mode of the present invention, the capsule 22 is generally spherical. However, the principles of the invention would apply when the capsule 22 is of a shape other than spherical; such shape should provide the desired optical and electrical characteristics that will satisfactorily coexist with the optical characteristics of the liquid crystal 20, e.g. index of refraction, and will permit an adequate portion of the electric field to occur across the liquid crystal material 20 itself for effecting desired alignment of the liquid crystal molecules when it is desired to have a field on condition. A particular advantage to the preferred spherical configuration of the capsule 22 will be described below with respect to the distortion it effects on the liquid crystal molecules.

The mounting substrate 12 and the electrodes 13, 14 as well as the protective coating 15 may be

optically transmissive so that the liquid crystal device 10 is capable of controlling transmission of light therethrough in response to whether or not an electric field is applied across the electrodes 13, 14 and, thus, across the encapsulated liquid crystal 11. Alternatively, the mounting substrate 12 may be optically reflective or may have thereon an optically reflective coating so that reflection by such reflective coating of incident light received through the protective coating 15 will be a function of whether or not there is an electric field applied across the encapsulated liquid crystal 11.

According to the preferred embodiment and best mode of the invention a plurality of encapsulated liquid crystals 11 would be applied to the mounting substrate 12 in a manner such that the encapsulated liquid crystals adhere to the mounting substrate 12 or to an interface material, such as the electrode 13, for support by the mounting substrate 12 and retention in position fixed relative to the other encapsulated liquid crystals 11. Most preferably the encapsulating medium of which the capsule 22 is formed is also suitable for binding or otherwise adhering the capsule 22 to the substrate 12. Alternatively, a further binding medium (not shown) may be used to adhere the encapsulated liquid crystals 11 to the substrate 12. Since the capsules 22 are adhered to the substrate 12, and since each capsule 22 provides the needed confinement for the liquid crystal material 20, a second mounting substrate, such as the additional one shown in the prior art liquid crystal device 1 of Fig. 1, ordinarily should be unnecessary. However, for the purpose of providing protection from scarring, electrochemical deterioration, e.g. oxidation, or the like, of the electrode 14, the protective coating 15 may be provided on the side or surface of the liquid crystal device 10 opposite the mounting substrate 12, the latter providing the desired physical protection on its own side of the device 10.

Since the encapsulated liquid crystals 11 are relatively securely adhered to the substrate 12 and since there ordinarily would be no need for an additional substrate, as was mentioned above, the electrode 14 may be applied directly to the encapsulated liquid crystals 11.

Turning now to Fig. 3, an example of a liquid crystal device 10' in accordance with the invention is shown in the form of a liquid crystal display device, which appears as a square cornered figure eight 30 on the substrate 12, which in this case preferably is a plastic material, such as Mylar, or may alternatively be another material, such as glass, for example. The shaded area appearing in Fig. 3 to form the square cornered figure eight is formed of plural encapsulated liquid crystals 11 arranged in one or more layers on and adhered to the substrate 12.

An enlarged fragmentary section view of a portion 32 of the figure eight 30 and substrate 12 is illustrated in Fig. 4. As is seen in Fig. 4, on the surface 31 of the substrate 12, which may be approximately 250 μ m (10 mils) thick, is deposited

5

10

15

20

25

30

35

40

45

50

55

60

65



a 20 nm (200 angstrom) thick electrode layer 33 of indium doped titanium oxide. One or more layers 34 of plural encapsulated liquid crystals 11 are applied and adhered directly to the electrode layer 33. Such adherence according to the preferred embodiment and best mode is effected by the encapsulating medium that forms respective capsules 22, although, if desired, as was mentioned above, an additional adhering or binding material may be used for such adherence purposes. The thickness of the layer 34 may be for example, approximately 25 μm (1 mil). A further electrode layer 35 is deposited on the layer 34 either directly to the material of which the capsules 22 are formed or, alternatively, to the additional binding material used to bind the individual encapsulated liquid crystals 11 to each other and to the mounting substrate 12. The electrode layer 35 may be, for example, approximately 13 μm (1/2 mil) thick and may be formed, for example, of electrically conductive ink. A protective coating layer 36 for the purposes described above with respect to the coating 15 in Fig. 3 also may be provided as is shown in Fig. 4.

In a conventional visual display device either of the liquid crystal or light emitting diode type, the figure eight element 30 ordinarily would be divided into seven electrically isolated segments, each of which may be selectively energized or not so as to create various numeral characters. For example, energization of the segments 30a and 30b would display the numeral "1" and energization of the segments 30a, 30b, 30c would display the numeral "7".

A feature of the present invention utilizing the encapsulated liquid crystals 11 is that a versatile substrate 12 can be created to be capable of displaying virtually any desired display as a function of only the selective segments of conductive ink electrodes printed on the liquid crystal material. In this case, the entire surface 31 of the substrate 12 may be coated with electrode material 33, and even the entire surface of that electrode material may be coated substantially contiguously with layer 34 of encapsulated liquid crystals 11. Thereafter, a prescribed pattern of electrode segments of conductive ink 35 may be printed where desired on the layer 34. A single electrical lead may attach the surface 31 to a voltage source, and respective electrical leads may couple the respective conductive ink segments via respective controlled switches to such voltage source. Alternatively, the encapsulated liquid crystals 11 and/or the electrode material 33 may be applied to the surface 31 only at those areas where display segments are desired.

Although a detailed description of operation of the individual encapsulated liquid crystals 11 will be presented below, it will suffice here to note that the encapsulated liquid crystals in the layer 34 function to attenuate or not to attenuate light incident thereon in dependence on whether or not an electric field is applied thereacross. Such an electric field may be, for example, one produced as a result of coupling of the electrode layer

portions 33, 35 at an individual segment, such as segment 30a, of the liquid crystal device 10' to an electrical voltage source. The magnitude of the electric field required to switch the encapsulated liquid crystals 11 from a no field (deenergized) condition to a field on (energized) condition may be a function of several parameters including, for example, the thickness of the layer 34, which in turn may depend on the diameter of individual capsules 22 and the number of such capsules in the thickness direction of layer 34. Importantly, it will be appreciated that since the liquid crystal material 20 is confined in respective capsules 22 and since the individual encapsulated liquid crystals 11 are secured to the substrate 12, the size of the liquid crystal device 10' or any other liquid crystal device employing encapsulated liquid crystals in accordance with the present invention is nearly unlimited. Of course, at those areas where it is intended to effect a change in the optical properties of the encapsulated liquid crystals of such a device in response to a no field or field on condition, it would be necessary to have there electrodes or other means for applying to such liquid crystals a suitable electric field.

The electrode layer 33 may be applied to the substrate 12 by evaporation, by vacuum deposition, by sputtering, by printing or by any other technique that may be desired. Moreover, the layer 34 of encapsulated liquid crystals 11 may be applied, for example, by a web or gravure roller or by reverse roller printing techniques. The electrode layer 35 also may be applied by various printing, stenciling or other techniques. If desired, the electrode layer 33 may be prepared as a full coating of the substrate 12, such as Mylar, as was described above, as part of the process in which the Mylar sheet material is manufactured, and the layer 34 also may be applied as part of such manufacturing process.

The ability to make and to use successfully liquid crystal devices of the type just described using encapsulated liquid crystals is due to the ability to make encapsulated liquid crystals and to the properties of such encapsulated liquid crystals, both of which are features of the present invention. These features now will be described with reference to Figs. 5, 6 and 7 in particular.

Referring specifically to Fig. 5, the capsule 22 has a generally smooth curved interior wall surface 50 defining the boundary of the volume 21. The actual dimensional parameters of the wall surface 50 and of the overall capsule 22 are related to the quantity of liquid crystal material 20 contained therein and to the size of the individual liquid crystal molecules. Additionally, the capsule 22 applies a force to the liquid crystals 20 tending to pressurize or at least to maintain substantially constant the pressure within the volume 21. As a result of the foregoing, and due to the surface wetting nature of the liquid crystal molecules, such molecules, which ordinarily in free form would tend to be straight, although perhaps randomly distributed, are distorted to curve in a direction that generally is parallel to a relatively



proximate portion of the interior wall surface 50. Due to such distortion the liquid crystals store elastic energy. For simplicity of illustration, and for facility of comprehending the foregoing concept, a layer 51 of liquid crystal molecules represented by respective dashed lines 52 is shown in closest proximity to the interior wall surface 50. The molecules 52 are distorted to curve in the direction that is parallel to a proximate area of the wall surface 50. Other layers, such as layer 53, etc., of liquid crystal molecules 52 are shown in the capsule 22. The liquid crystal molecules are shown in such layers, although it will be appreciated that the liquid crystal molecules may be oriented somewhat more randomly than in the ordered layers illustrated in Fig. 5; however, such molecules nevertheless will tend to align with some degree of parallel relationship to the respective proximate areas of the interior wall surface 50.

In the preferred embodiment and best mode of the present invention the liquid crystal molecules 52 are of the nematic type. Such molecules usually assume a straight line thread-like configuration, and a liquid crystal material comprised of such nematic molecules usually is optical polarization direction sensitive. However, since the molecules 52 in the encapsulated liquid crystal 11 are distorted or forced to curved form in the full three dimensions of the capsule 22, such nematic liquid crystal material in such capsule takes on an improved characteristic of being insensitive to the direction of optical polarization of light incident thereon. The inventor has discovered, moreover, that when the liquid crystal material 20 in the capsule 22 has pleochroic dye dissolved therein, such dye, which ordinarily also would be expected to have optical polarization sensitivity, no longer is polarization sensitive because the dye tends to follow the same kind of curvature orientation or distortion as that of the individual liquid crystal molecules 52.

It is noted here that the liquid crystal material 20 in the capsule 22 has a discontinuity 55 in the generally spherical orientation thereof. Such discontinuity is caused by the incapability of the liquid crystal to align uniformly in a manner compatible with parallel alignment with the wall 54 and a requirement for minimum elastic energy. The liquid crystal molecules 52, though, will tend to follow around the discontinuity in the manner shown in planar form in Fig. 5, but in reality in three dimensions, following a pattern along the three dimensional generally cylindrical internal boundary wall surface 50a of the protruding discontinuity 55. Such discontinuity further distorts the liquid crystal molecules which further decreases the possibility that the liquid crystal material 20 would be sensitive to optical polarization direction of incident light.

With the individual liquid crystal molecules 52 being distorted to fold in on themselves generally in the manner illustrated in Fig. 5, the encapsulated liquid crystal 11 ordinarily will absorb or block light from being transmitted therethrough

when no electric field is applied across the encapsulated liquid crystal 11 and particularly across the liquid crystal material 20 thereof.

However, when an electric field is applied across the encapsulated liquid crystal 11 in the manner illustrated in Fig. 6, the liquid crystal molecules 52 and any pleochroic dye in solution therewith will align in response to the electric field in the manner shown in such Figure. Such alignment permits light to be transmitted through the encapsulated liquid crystal 11, for example as described above with reference to Figs. 2, 3 and 4.

In the field off condition since the liquid crystal molecules 52 are distorted to curved form, they have a certain elastic energy. Such elastic energy causes the crystals to function doing things that otherwise were not possible when the liquid crystal molecules assume their ordinary linear form. For example, the discontinuity protrusion 55 would tend to cause scattering and absorption within the capsule, and the tangential or parallel alignment of the liquid crystal molecules to respective portions of interior wall surface 50 both cause scattering and absorption within the capsule 22. On the other hand, when the electric field is applied in the manner illustrated in Fig. 6, not only do the liquid crystal molecules 52 align as shown, but also the discontinuity 55 tends to align in parallel with the electric field. Accordingly, such discontinuity will have a minimum effect on optical transmission when the encapsulated liquid crystal 11 is in a field on condition.

To optimize contrast characteristics of a liquid crystal device, such as that shown at 10' in Fig. 3, comprised of encapsulated liquid crystals 11, and, more particularly, to avoid optical distortion due to refraction of incident light passing from the encapsulating medium into the liquid crystal material and vice versa of the encapsulated liquid crystal 11 of Fig. 6, the index of refraction of the encapsulating medium and that of the ordinary index of refraction of the liquid crystal material should be matched to be as much as possible the same.

However, when no field is applied there will be a difference in indices of refraction at the boundary of the liquid crystal and capsule wall due to the extraordinary index of refraction of the liquid crystal being greater than the encapsulating medium. This causes refraction at that interface or boundary and thus further scattering and is a reason why the invention of encapsulated nematic liquid crystal material, in particular, will function to prevent transmission of light even without the use of pleochroic dye.

Ordinarily the encapsulated liquid crystals 11 would be applied to the substrate 12 (Fig. 3) such that the individual encapsulated liquid crystals 11 are relatively randomly oriented and preferably several capsules thick to assure an adequate quantity of liquid crystal material on the surface 31 of the substrate to provide the desired level of light blockage and/or transmission characteristics for, for example, a liquid crystal device 10' or the like.



In a liquid crystal device, such as that shown in 10' in Fig. 3, which is comprised of liquid crystal material 20 including pleochroic dye to form encapsulated liquid crystals 11 according to the invention, it has been discovered that the degree of optical absorbency is at least about the same as that of relatively free (unencapsulated) liquid crystal material, including pleochroic dye such as that shown in Fig. 1. It also has been discovered unexpectedly that when the electric field is applied in the manner illustrated in Fig. 6, for example, the clarity or lack of opaqueness of the encapsulated liquid crystal material 20 including pleochroic dye is at least about the same as that of the ordinary case in the prior art device 1 having dye in solution with the relatively free liquid crystal material.

It is important that electrical field E shown in Fig. 6 is applied to the liquid crystal material 20 in the capsule 22 for the most part rather than being dissipated or dropped substantially in the encapsulating material of which the capsule itself is formed. In other words, it is important that there not be a substantial voltage drop across or through the material of which the wall 54 of the capsule 22 is formed; rather, the voltage drop should occur across the liquid crystal material 20 within the volume 21 of the capsule 22.

The electrical impedance of the encapsulating medium preferably should be larger than that of the liquid crystal material in the encapsulated liquid crystal 11 (Fig. 6) and also should be large enough that a short circuit will not occur exclusively through the wall 54 bypassing the liquid crystal material. Therefore, for example, the impedance to current flow through or via the wall 54, say from point A to point B, would be rather substantial as opposed to the impedance that would be encountered in a current path directly from point A to point A' inside the interior wall surface 50, directly through the liquid crystal material 20 to point B' still within the volume 21, ultimately to point B again.

The dielectric constants (coefficients) of the material of which the encapsulating medium is formed and of which the liquid crystal material is comprised and the effective capacitance values of the capsule wall 54 particularly in a radial direction and of the liquid crystal material across which the electric field E is imposed all should be so related that the wall 54 of the capsule 22 does not substantially drop the magnitude of the applied electric field E.

A schematic electric circuit diagram representing the circuit across which the electric field E of Fig. 6 is imposed is illustrated in Fig. 7. The electric field is derived from the voltage source 16 when the switch 17 is closed. A capacitor 70 represents the capacitance of the liquid crystal material 20 in the encapsulated liquid crystal 11 when such electric field is applied in the manner illustrated in Fig. 6. The capacitor 71 represents the capacitance of the capsule 22 wall 54 at an upper area (the direction conveniently referring to the drawing but having no

other particular intentional meaning) and is, accordingly, curved in a manner similar to that of the upper portion of the capsule 22 of Figs. 5 and 6. The capacitor 72 similarly represents the capacitance of the lower portion of the capsule exposed to the electric field E. The magnitudes of capacitance for each capacitor 70—72 will be a function of the dielectric constant (coefficient) of the material of which the respective capacitors are formed and of the spacing of the effective plates thereof. It is desirable that the capacitors 71, 72 be larger in magnitude than the capacitor 70 so that the voltage drop occurring across the respective capacitors 71, 72 will be less than the voltage drop across the capacitor 70; the result, then, is application of a maximum portion of the electric field E across the liquid crystal material 20 in the encapsulated liquid crystal 11 for achieving optimized operation, i.e. alignment, of the liquid crystal molecules thereof with a minimum total energy requirement of the voltage source 16.

In connection with capacitor 71, for example, the dielectric material is that of which the wall 54 is formed relatively near the upper portion of the capsule 22. The effective plates of such capacitor 71 are the exterior and interior wall surfaces 73, 51, and the same is true for the capacitor 72 at the lower portion of the capsule 22 relative to the illustration of Fig. 6, for example. By making the wall 54 as thin as possible, while still providing adequate strength for containment of the liquid crystal material 20 in the volume 21, the magnitudes of capacitors 71, 72 can be maximized, this especially in comparison to the rather thick or lengthy distance between the upper portion 74 of the liquid crystal material 20 of the lower portion 75 thereof which approximately or equivalently form the plates of the same number of the capacitor 70.

The liquid crystal material 20 will have a dielectric constant value that is anisotropic. It is preferable that the dielectric constant (coefficient) of the wall 54 be no lower than the lower dielectric constant (coefficient) of the anisotropic liquid crystal material 20 to help meet the above conditions.

The encapsulated liquid crystal 11 has features that since the liquid crystal molecules 52 are distorted and since the pleochroic dye similarly is distorted, absorbency or blockage of light transmission through the encapsulated liquid crystals will be highly effective when no electric field E is applied thereacross. On the other hand, due both to the efficient application of electric field across the liquid crystal material 20 in the encapsulated liquid crystals 11 to align the liquid crystal molecules and the dye along therewith as well as the above described preferred index of refraction matching, i.e. of the encapsulating medium and of the liquid crystal material, so that incident light will not be refracted or bent at the interface between the capsule wall 54 and the liquid crystal material 20, when an electric field is applied the encapsulated liquid crystal 11 will have a good optically transmissive characteristic.



Since a plurality of encapsulated liquid crystals 11 ordinarily is required to construct a final liquid crystal device, such as the device 10' of Fig. 3, and since those encapsulated liquid crystals are in several layers, it is desirable to have a relatively high dielectric anisotropy in order to reduce the voltage requirements for the electric field E. More specifically, the differential between the dielectric constant (coefficient) for the liquid crystal material 20 when no electric field is applied which constant (coefficient) should be rather small, and the dielectric constant (coefficient) for the liquid crystal material when it is aligned upon application of an electric field, which constant (coefficient) should be relatively large, should be as large as possible.

The capsules 22 may be of various sizes. The smaller the capsule size, though, the higher the requirements will be for the electric field to effect alignment of the liquid crystal molecules in the capsule. Also, when the capsule size is relatively small, more capsules are required per unit area of the layer 34, and, therefore, more electric voltage drop losses will occur in the encapsulating medium than for larger size capsules, the density per unit area of which would be smaller. According to the preferred embodiment and best mode of the present invention, though, a device made with the encapsulated liquid crystals 11, such as the liquid crystal device 10', should use capsules of uniform size parameters so that the device 10' can be energized or deenergized in a relatively uniform and well controlled manner. In contrast, when the capsules are of a non-uniform size, the non-uniform energization of the respective capsules, i.e. alignment of the liquid crystal molecules of each, would occur upon application of the electric field. Ordinarily the capsules 22 should have a size on the order of from about 2 to about 25 microns in diameter.

As was noted above, the larger the capsule size, the smaller the electric field required to effect alignment of the liquid crystal molecules therein. However, the larger the sphere, the longer the response time.

Regardless of the capsule size and the particular field off arrangement of liquid crystal molecules within the capsule 22, it is important to know what the field off alignment would be and what would be the distorted alignment when there is a field on condition so that the encapsulated liquid crystals 11 may be used effectively.

In the preferred embodiment and best mode of the present invention the liquid crystal material used in the encapsulated liquid crystal 11 is of the nematic type.

Currently a most preferred liquid crystal material is that as nematic material NM8250 sold by American Liquid Xtal Chemical Corp., Kent, Ohio, U.S.A. Others may be ester combinations, bipheny combinations and the like.

The encapsulating medium forming respective capsules 22 should be of a type that is substantially completely unaffected by and does not affect the liquid crystal material. The other charac-

teristics described above concerning dielectric constants (coefficients) and indices of refraction with respect to the liquid crystal material and to the encapsulating medium also constrain material selection. Moreover, when pleochroic dye is employed, the encapsulating medium also should be totally unaffected by and should not affect the dye material. On the other hand, the dye should be oil soluble and not subject to absorption by the water phase (see below) or polymer phase of the encapsulating medium. Additionally, to achieve the desired relatively high impedance for the encapsulating medium, such medium should have a relatively high level of purity.

An example of a pleochroic dye that may be used in the encapsulated liquid crystals 11 in accordance with the present invention are indophenol blue, Sudan black B, Sudan 3 and Sudan 2.

Various resins and/or polymers may be used as the encapsulating medium. However, an encapsulating medium according to the preferred embodiment and best mode of the present invention is polyvinyl alcohol (PVA), which has been found to have the desired properties mentioned above, especially in relation to the above described preferred liquid crystal and pleochroic dye material. Specifically, PVA has a good, relatively high, dielectric constant and has an index of refraction that is relatively closely matched to that of the preferred liquid crystal material.

To purify PVA, the same may be dissolved in water and washed out with alcohol using a precipitate technique. Other techniques also may be used for purifying PVA so that it will have minimum salt or other content that would reduce appreciably the electrical impedance thereof. The preferred purified PVA is SA72 sold by American Liquid Xtal Chemical Corp. If PVA is properly cleaned or purified, as aforesaid, it will serve well as its own emulsifier and as a wetting agent for facilitating the method of making encapsulated liquid crystals which will be described below. Other types of encapsulating medium may be, for example, gelatin, Carbopole, Gantrez, the latter two being polyelectrolytes; and these media may be used alone or in combination with other polymers, such as PVA. The wetting ability of the PVA also assists in allowing freedom of movement of the liquid crystal molecules in the respective capsules 22 facilitating the preferred parallel alignment especially at the interior wall surface 50 in the field off condition and easy changing to the aligned position of Fig. 6 when an electric field is applied.

A method for making encapsulated liquid crystals 11 may include mixing together the encapsulating medium, the liquid crystal material (including, if used, the pleochroic dye material), and perhaps a carrier medium, such as water. Mixing may occur in a variety of mixer devices, such as a blender, a colloid mill, which is most preferred, or the like. What occurs during such mixing is the formation of an emulsion of the ingredients, which subsequently can be dried



eliminating the carrier medium, such as water, and satisfactorily curing the encapsulating medium, such as the PVA. Although the capsule 22 of each thusly made encapsulated liquid crystal 11 may not be a perfect sphere, each capsule will be substantially spherical in configuration because a sphere is the lowest free energy state of the individual droplets, globules or capsules of the emulsion, both when originally formed and after drying and/or curing has occurred.

It is noted here briefly that the characteristic of the pleochroic dye that it must be oil soluble, provides for solution thereof with the liquid crystal material and that it not be subject to absorption by the water phase or polymer phase assures that such pleochroic dye will not be absorbed by the PVA or other encapsulating medium or by the carrier medium, such as the water, used during the manufacturing process for the encapsulated liquid crystals 11.

The following Example serves to further illustrate the invention.

Example

A .45% Sudan black B pleochroic dye was dissolved in a liquid crystal which was composed of aromatic esters. Such combined material is commercially sold under the designation 8250 by American Liquid Xtal Chemical Corp. of Kent, Ohio. Such material was mixed with a solution of 7% PVA, which was treated to remove all salts. The solution also was made with ASTM-100 water. The resulting mixture was put into a colloid mill whose conegap setting was 100 μ m (4 mils), and the material was milled for four minutes to give a rather uniform particle suspension size. The result was a stable emulsion whose suspended particle size was approximately 3 μ m. The emulsion was cast on a Mylar film which was precoated with a 31 ohm per cm^2 (200 ohm per square inch) layer of tin oxide electrode purchased from Sierracin. A doctor blade was used to cast the emulsion material on the Mylar film on the electrode coated side.

A 180 μ m (7 mil) lay-down of the emulsion material was placed on such electrode and was allowed to dry to a total thickness of 20 μ m (0.8 mil). A second layer of such emulsion subsequently was laid on the first with a resulting aggregate layer of liquid crystal droplets in a polyvinyl alcohol matrix having a thickness of 40 μ m (1.6 mil). Preferably, though, the encapsulated liquid crystals may be laid down in a single layer one or plural capsules thick.

The thusly formed liquid crystal device, including the layer of Mylar, electrode and encapsulated liquid crystals then was tested by applying an electric field, whereupon the material changed from black to nearly clear-transparent. The material exhibited a very wide viewing angle, i.e. the angle at which light was transmitted, and the contrast ratio was 7:1 at 50 volts of applied electric field. The switching speed was about two milliseconds on and about 4 milliseconds off.

In accordance with the present invention the

quantities of ingredients for making the encapsulated liquid crystals 11, for example in the manner described above, may be as follows:

The liquid crystal material—This material may be from about 5% to about 20% and preferably about 10%, including the pleochroic dye, by volume of the total solution delivered to the mixing apparatus, such as the colloid mill. The actual amount of liquid crystal material used, though, ordinarily should exceed the volume quantity of encapsulating medium, e.g. PVA to optimize the capsule size.

The PVA—The quantity of PVA in the solution should be on the order of from about 5% to about 20% and preferably, as was described above, about 7%, this depending, though, on the molecular weight of the PVA. For example, if the PVA has too large a molecular weight, the resulting material will be like glass, especially if too much PVA is used in the solution. On the other hand, if the molecular weight is too low, used of too little PVA will result in too low a viscosity of the material, and the resulting emulsion will not hold up well, nor will the droplets of the emulsion solidify adequately to the desired spherical encapsulated liquid crystals.

Carrier medium—The remainder of the solution would be water or other carrier medium, as described above, with which the emulsion can be made and the material laid down appropriately on a substrate, electrode or the like.

It will be appreciated that since the uncured capsules or droplets of encapsulating medium and liquid crystal material are carried in a liquid, various conventional or other techniques may be employed to grade the capsules according to size so that the capsules can be reformed if of an undesirable size by feeding again through the mixing apparatus, for example, and so that the finally used capsules will be of a desired uniformity for the reasons expressed above.

Although the presently preferred invention operates in response to application and removal of an electric field, operation also may be effected by application and removal of a magnetic field.

Our Divisional Application No. 87116099.0 (published as EP—A—0268877) describes and claims a liquid crystal structure comprising a liquid crystal material and a medium for containing a multiplicity or discrete quantities of such liquid crystal material, and pleochroic dye in the liquid crystal material.

Claims

1. A liquid crystal device comprising liquid crystal material and containment means therefor for inducing a distorted alignment of said liquid crystal material, and which in response to such alignment scatters and/or absorbs light and which in response to an input reduces the amount of scattering and/or absorption.

2. A device according to claim 1 wherein a pleochroic dye is present in the liquid crystal material.



eliminating the carrier medium, such as water, and satisfactorily curing the encapsulating medium, such as the PVA. Although the capsule 22 of each thusly made encapsulated liquid crystal 11 may not be a perfect sphere, each capsule will be substantially spherical in configuration because a sphere is the lowest free energy state of the individual droplets, globules or capsules of the emulsion, both when originally formed and after drying and/or curing has occurred.

It is noted here briefly that the characteristic of the pleochroic dye that it must be oil soluble, provides for solution thereof with the liquid crystal material and that it not be subject to absorption by the water phase or polymer phase assures that such pleochroic dye will not be absorbed by the PVA or other encapsulating medium or by the carrier medium, such as the water, used during the manufacturing process for the encapsulated liquid crystals 11.

The following Example serves to further illustrate the invention.

Example

A .45% Sudan black B pleochroic dye was dissolved in a liquid crystal which was composed of aromatic esters. Such combined material is commercially sold under the designation 8250 by American Liquid Xtal Chemical Corp. of Kent, Ohio. Such material was mixed with a solution of 7% PVA, which was treated to remove all salts. The solution also was made with ASTM-100 water. The resulting mixture was put into a colloid mill whose conegap setting was 100 μ m (4 mils), and the material was milled for four minutes to give a rather uniform particle suspension size. The result was a stable emulsion whose suspended particle size was approximately 3 μ m. The emulsion was cast on a Mylar film which was precoated with a 31 ohm per cm^2 (200 ohm per square inch) layer of tin oxide electrode purchased from Sierracin. A doctor blade was used to cast the emulsion material on the Mylar film on the electrode coated side.

A 180 μ m (7 mil) lay-down of the emulsion material was placed on such electrode and was allowed to dry to a total thickness of 20 μ m (0.8 mil). A second layer of such emulsion subsequently was laid on the first with a resulting aggregate layer of liquid crystal droplets in a polyvinyl alcohol matrix having a thickness of 40 μ m (1.6 mil). Preferably, though, the encapsulated liquid crystals may be laid down in a single layer one or plural capsules thick.

The thusly formed liquid crystal device, including the layer of Mylar, electrode and encapsulated liquid crystals then was tested by applying an electric field, whereupon the material changed from black to nearly clear-transparent. The material exhibited a very wide viewing angle, i.e. the angle at which light was transmitted, and the contrast ratio was 7:1 at 50 volts of applied electric field. The switching speed was about two milliseconds on and about 4 milliseconds off.

In accordance with the present invention the

quantities of ingredients for making the encapsulated liquid crystals 11, for example in the manner described above, may be as follows:

The liquid crystal material—This material may be from about 5% to about 20% and preferably about 10%, including the pleochroic dye, by volume of the total solution delivered to the mixing apparatus, such as the colloid mill. The actual amount of liquid crystal material used, though, ordinarily should exceed the volume quantity of encapsulating medium, e.g. PVA to optimize the capsule size.

The PVA—The quantity of PVA in the solution should be on the order of from about 5% to about 20% and preferably, as was described above, about 7%, this depending, though, on the molecular weight of the PVA. For example, if the PVA has too large a molecular weight, the resulting material will be like glass, especially if too much PVA is used in the solution. On the other hand, if the molecular weight is too low, used of too little PVA will result in too low a viscosity of the material, and the resulting emulsion will not hold up well, nor will the droplets of the emulsion solidify adequately to the desired spherical encapsulated liquid crystals.

Carrier medium—The remainder of the solution would be water or other carrier medium, as described above, with which the emulsion can be made and the material laid down appropriately on a substrate, electrode or the like.

It will be appreciated that since the uncured capsules or droplets of encapsulating medium and liquid crystal material are carried in a liquid, various conventional or other techniques may be employed to grade the capsules according to size so that the capsules can be reformed if of an undesirable size by feeding again through the mixing apparatus, for example, and so that the finally used capsules will be of a desired uniformity for the reasons expressed above.

Although the presently preferred invention operates in response to application and removal of an electric field, operation also may be effected by application and removal of a magnetic field.

Our Divisional Application No. 87116099.0 (published as EP—A—0268877) describes and claims a liquid crystal structure comprising a liquid crystal material and a medium for containing a multiplicity or discrete quantities of such liquid crystal material, and pleochroic dye in the liquid crystal material.

Claims

1. A liquid crystal device comprising liquid crystal material and containment means therefor for inducing a distorted alignment of said liquid crystal material, and which in response to such alignment scatters and/or absorbs light and which in response to an input reduces the amount of scattering and/or absorption.

2. A device according to claim 1 wherein a pleochroic dye is present in the liquid crystal material.





3. A device according to either of claims 1 and 2 wherein the liquid crystal material has an ordinary index of refraction and an extraordinary index of refraction, and the ordinary index of refraction of the liquid crystal material and the index of refraction of the containment means are substantially identical.

4. A device according to any one of claims 1—3 wherein the liquid crystal material has an ordinary index of refraction and an extraordinary index of refraction is different from the index of refraction of the containment means to cause scattering of light in the absence of the input.

5. A device according to any one of claims 1—4 wherein the containment means has non-planar wall means that tends to distort and/or align at least some of the liquid crystal material generally with respect thereto when in the absence of an input.

6. A device according to any one of claims 1—4 wherein the containment means has non-planar wall means that tends to distort at least some of the liquid crystal material to random alignment when in the absence of an input.

7. A device according to any one of claims 1—6 wherein the containment means comprises a containment medium having therein a plurality of volumes of liquid crystal material.

8. A device according to any one of claims 1—7, wherein the containment means forms discrete curved volumes containing discrete quantities of liquid crystal material and operative to distort the natural structure of the liquid crystal material.

9. A device according to any one of claims 1—8, wherein said liquid crystal material and containment means comprises an encapsulated liquid crystal.

10. A device according to any one of claims 1—9, wherein the containment means forms a plurality of capsules of liquid crystal material bounded by walls formed by the containment means, and the dielectric constant of the walls of such capsules is such that the impedance in a radial direction of the capsules does not cause a substantial voltage drop relative to the voltage drop across the liquid crystal material upon application of an electric field across the capsules.

11. A device according to any one of claims 1—10, wherein the liquid crystal material and containment means comprise volumes of liquid crystal material having a size of from about 2 micrometers to about 25 micrometers.

12. A device according to any one of claims 1—11, wherein the containment means comprises a resin or polymeric material.

13. A device according to claim 12 wherein the resin or polymeric material is selected from gelatin, a carboxy polymethylene polymer, a maleic anhydride-derived copolymer, poly(methyl vinyl ether/maleic anhydride) and polyvinyl alcohol.

14. A device according to any one of claims 1—13 which includes substrate means for supporting the combination of liquid crystal material and containment means.

15. A device according to claim 14 which includes means for adhering the combination of liquid crystal material and containment means to the substrate means.

16. A device according to any one of claims 1—15 wherein the input is an electric field or a magnetic field, the liquid crystal material being responsive to the field to align with respect thereto and the liquid crystal material and containment means are cooperative to cause scattering or absorption of light in the absence of the field and to reduce scattering or absorption in the presence of the field.

17. A device according to claim 16 which includes means for applying an electric field to the liquid crystal material.

18. A device according to claim 17 wherein the means for applying the electric field comprises electrodes.

19. A device according to claim 18 wherein at least one of the electrodes is transparent and another of the electrodes is in the form of a pattern.

20. A device according to claim 19 which includes circuit means for applying electrical energy to the electrodes.

21. A device according to any one of claims 1—20 wherein the containment means includes surface-defining means that tends to align at least some of the liquid crystal material generally in parallel thereto when in the absence of the input.

22. A device according to any one of claims 1—21 wherein the liquid crystal material has positive dielectric anisotropy.

23. A device according to any one of claims 1—22 wherein the liquid crystal material is operationally nematic liquid crystal material.

24. A device according to any one of claims 1—23 wherein the liquid crystal material is a nematic liquid crystal material.

25. A liquid crystal device comprising liquid crystal material and containment means for containing the liquid crystal material in a plurality of volumes, wherein the ordinary index of refraction of the liquid crystal material is substantially equal to the index of refraction of the containment means for maximizing optical transmission through the device in the presence of an input.

26. A device according to claim 25 wherein the liquid crystal material has positive dielectric anisotropy.

27. A device according to either of claims 25 and 26 wherein the liquid crystal material has an extraordinary index of refraction different from the index of refraction of the containment means.

28. Optical apparatus comprising a liquid crystal device as defined in any one of claims 1—27.

29. Optical apparatus according to claim 28 in the form of an optical display device.

30. A method of making encapsulated nematic liquid crystal material comprising mixing at least an encapsulating medium, a nematic liquid crystal material and a pleochroic dye.

31. A method of causing nematic liquid crystal material to perform substantially independently





of the optical polarization direction of incident light, comprising confining such nematic liquid crystal material in at least one capsule which causes distortion of the direction of the liquid crystal material.

32. A method according to claim 31 wherein said confining comprises mixing an encapsulating medium and the nematic liquid crystal material.

33. A method according to claim 32 wherein the dielectric constant of the encapsulating material is greater or equal to the lower dielectric constant of the liquid crystal material.

34. A method according to either of claims 32 and 33 wherein the liquid crystal material has a positive dielectric anisotropy.

35. A method according to either of claims 33 and 34 wherein the liquid crystal material has an ordinary index of refraction substantially the same as the index of refraction of the encapsulating medium.

36. A method of making encapsulated liquid crystal material comprising mixing an encapsulating medium and a nematic liquid crystal material, wherein the liquid crystal material has an ordinary index of refraction substantially the same as the index of refraction of the encapsulating medium.

37. A method according to claim 36 wherein the liquid crystal material has an extraordinary index of refraction that is different from the index of refraction of the encapsulating medium.

38. Optical apparatus comprising encapsulated liquid crystal material prepared in accordance with any one of claims 30 to 37.

Patentansprüche

1. Flüssigkristallvorrichtung mit einem Flüssigkristallmaterial und einer Rückhalteeinrichtung hierfür zur Einleitung einer verzerrten Ausrichtung des Flüssigkristallmaterials, die in Reaktion auf eine solche Ausrichtung Licht streut und/oder absorbiert und in Reaktion auf eine Eingabe die Streuungs- und/oder Absorptionsmenge reduziert.

2. Vorrichtung nach Anspruch 1, worin ein pleochroitischer Farbstoff in dem Flüssigkristallmaterial vorhanden ist.

3. Vorrichtung nach einem der Ansprüche 1 und 2, worin das Flüssigkristallmaterial einen gewöhnlichen Brechungsindex und einen außergewöhnlichen Brechungsindex hat und der gewöhnliche Brechungsindex des Flüssigkristallmaterials und der Brechungsindex der Rückhalteeinrichtung im wesentlichen identisch sind.

4. Vorrichtung nach einem der Ansprüche 1 bis 3, worin das Flüssigkristallmaterial einen gewöhnlichen Brechungsindex und einen außergewöhnlichen Brechungsindex hat und der außergewöhnliche Brechungsindex von dem Brechungsindex der Rückhalteeinrichtung verschieden ist, um die Lichtstreuung in Abwesenheit der Eingabe zu bewirken.

5. Vorrichtung nach einem der Ansprüche 1 bis

4, worin die Rückhalteeinrichtung nichtebene Wandeinrichtungen hat, die dazu neigen, wenigstens etwas von dem Flüssigkristallmaterial in Abwesenheit einer Eingabe zu verformen und/oder in Bezug auf diese Einrichtungen auszurichten.

6. Vorrichtung nach einem der Ansprüche 1 bis 4, worin die Rückhalteeinrichtung nichtebene Wandeinrichtungen haben, die dazu neigen, wenigstens etwas von dem Flüssigkristallmaterial zu einer willkürlichen Ausrichtung in Abwesenheit einer Eingabe zu verformen.

7. Vorrichtung nach einem der Ansprüche 1 bis 6, worin die Rückhalteeinrichtung ein Rückhalte-medium umfaßt, das darin eine Vielzahl von Flüssigkristallmaterialvolumina hat.

8. Vorrichtung nach einem der Ansprüche 1 bis 7, worin die Rückhalteeinrichtung einzelne gekrümmte Volumina bildet, die einzelne Mengen an Flüssigkristallmaterial enthalten, und die natürliche Struktur des Flüssigkristallmaterials verformt.

9. Vorrichtung nach einem der Ansprüche 1 bis 8, worin das Flüssigkristallmaterial und die Rückhalteeinrichtung einen eingekapselten Flüssigkristall umfaßt.

10. Vorrichtung nach einem der Ansprüche 1 bis 9, worin die Rückhalteeinrichtung eine Vielzahl von Kapseln von Flüssigkristallmaterial, das durch Wände gebunden ist, welche von der Rückhalteeinrichtung gebildet werden, bildet und daß die dielektrische Konstante der Wände dieser Kapseln derart ist, daß die Impedanz in einer radialen Richtung der Kapseln keinen wesentlichen Spannungsabfall gegenüber dem Spannungsabfall quer zu dem Flüssigkristallmaterial bei Anlegen eines elektrischen Feldes quer zu den Kapseln, verursacht.

11. Vorrichtung nach einem der Ansprüche 1 bis 10, worin das Flüssigkristallmaterial und die Rückhalteeinrichtung Flüssigkristallmaterialvolumina mit einer Größe von etwa 2 µm bis etwa 25 µm umfassen.

12. Vorrichtung nach einem der Ansprüche 1 bis 11, worin die Rückhalteeinrichtung ein Harz oder Polymermaterial umfaßt.

13. Vorrichtung nach Anspruch 12, worin das Harz oder Polymermaterial aus Gelatine, einem Carboxypolymethylenpolymer, einem sich von Maleinsäureanhydrid herleitenden Copolymer, Poly(methylvinylether/maleinsäureanhydrid) und Polyvinylalkohol ausgewählt ist.

14. Vorrichtung nach einem der Ansprüche 1 bis 13, die ein Substrat zum Unterstützen der Kombination von Flüssigkristallmaterial und Rückhalteeinrichtung aufweist.

15. Vorrichtung nach Anspruch 14, die Einrichtungen zum Anhaften der Kombination von Flüssigkristallmaterial und Rückhalteeinrichtung an dem Substrat aufweist.

16. Vorrichtung nach einem der Ansprüche 1 bis 15, bei der die Eingabe ein elektrisches Feld oder ein Magnetfeld ist, wobei das Flüssigkristallmaterial auf das Feld reagiert, indem es sich in Bezug auf dieses ausrichtet, und das Flüssigkri-





stallmaterial und die Rückhalteeinrichtung derart zusammenarbeiten, daß Licht in Abwesenheit des Feldes gestreut oder absorbiert wird und die Streuung oder Absorption in Gegenwart des Feldes reduziert werden.

17. Vorrichtung nach Anspruch 16, die Einrichtungen zum Anlegen eines elektrischen Feldes an das Flüssigkristallmaterial aufweist.

18. Vorrichtung nach Anspruch 17, worin die Einrichtung zum Anlegen des elektrischen Feldes Elektroden umfaßt.

19. Vorrichtung nach Anspruch 18, worin wenigstens eine der Elektroden transparent und die andere der Elektroden in der Form eines Musters vorliegt.

20. Vorrichtung nach Anspruch 19, die einen Stromkreis zum Anlegen elektrischer Energie an die Elektroden aufweist.

21. Vorrichtung nach einem der Ansprüche 1 bis 20, bei der die Rückhalteeinrichtung oberflächendefinierende Einrichtungen aufweist, die dazu neigen, wenigstens etwas von dem Flüssigkristallmaterial allgemein parallel zu ihnen in Abwesenheit der Eingabe auszurichten.

22. Vorrichtung nach einem der Ansprüche 1 bis 21, bei der das Flüssigkristallmaterial positive dielektrische Anisotropie hat.

23. Vorrichtung nach einem der Ansprüche 1 bis 22, worin das Flüssigkristallmaterial wirkungsmäßig nematisches Flüssigkristallmaterial ist.

24. Vorrichtung nach einem der Ansprüche 1 bis 23, bei der das Flüssigkristallmaterial ein nematisches Flüssigkristallmaterial ist.

25. Flüssigkristallvorrichtung mit Flüssigkristallmaterial und Rückhalteeinrichtung, um das Flüssigkristallmaterial in einer Vielzahl von Volumina zu enthalten, wobei der gewöhnliche Brechungsindex des Flüssigkristallmaterials im wesentlichen gleich dem Brechungsindex der Rückhalteeinrichtung ist, um optische Übertragung durch die Vorrichtung in Gegenwart einer Eingabe zu maximieren.

26. Vorrichtung nach Anspruch 25, worin das Flüssigkristallmaterial positive dielektrische Anisotropie hat.

27. Vorrichtung nach einem der Ansprüche 25 und 26, worin das Flüssigkristallmaterial einen außergewöhnlichen Brechungsindex hat, der von dem Brechungsindex der Rückhalteeinrichtung verschieden ist.

28. Optische Apparatur mit einer Flüssigkristallvorrichtung nach einem der Ansprüche 1 bis 27.

29. Optische Apparatur nach Anspruch 28 in der Form einer optischen Displayvorrichtung.

30. Verfahren zur Herstellung von eingekapseltem nematischem Flüssigkristallmaterial, bei dem man wenigstens ein Einkapselungsmedium, ein nematisches Flüssigkristallmaterial und einen pleochroitischen Farbstoff miteinander vermischt.

31. Verfahren zum im wesentlichen Unabhängigmachen nematischen Flüssigkristallmaterials von der optischen Polarisierungsrichtung von einfallendem Licht, indem man solches nematisches Flüssigkristallmaterial in wenigstens einer Kapsel

einschließt, die eine Verformung der Richtung des Flüssigkristallmaterials bewirkt.

32. Verfahren nach Anspruch 31, bei dem das Einschließen darin besteht, daß man ein Einkapselungsmedium und das nematische Flüssigkristallmaterial miteinander vermischt.

33. Verfahren nach Anspruch 32, bei dem die dielektrische Konstante des Einkapselungsmaterials größer als oder gleich wie die niedrigere dielektrische Konstante des Flüssigkristallmaterials ist.

34. Verfahren nach einem der Ansprüche 32 und 33, bei dem das Flüssigkristallmaterial eine positive dielektrische Anisotropie hat.

35. Verfahren nach einem der Ansprüche 33 und 34, bei dem das Flüssigkristallmaterial einen gewöhnlichen Brechungsindex hat, der im wesentlichen gleich wie der Brechungsindex des Einkapselungsmediums ist.

36. Verfahren zur Herstellung von eingekapseltem Flüssigkristallmaterial, bei dem man das Einkapselungsmedium und ein nematisches Flüssigkristallmaterial miteinander vermischt, wobei das Flüssigkristallmaterial einen gewöhnlichen Brechungsindex hat, der im wesentlichen gleich wie der Brechungsindex des Einkapselungsmediums ist.

37. Verfahren nach Anspruch 36, bei dem das Flüssigkristallmaterial einen außergewöhnlichen Brechungsindex hat, der verschieden von dem Brechungsindex des Einkapselungsmaterials ist.

38. Optische Apparatur mit einem eingekapselten Flüssigkristallmaterial, das nach einem der Ansprüche 30 bis 37 hergestellt wurde.

Revendications

1. Dispositif à cristaux liquides caractérisé en ce qu'il comprend du cristal liquide et des moyens pour contenir celui-ci servant à induire un alignement déformé dudit cristal liquide, et qui, en réponse à cet alignement, disperse et/ou absorbe la lumière et qui, en réponse à un signal d'entrée, réduit la quantité de dispersion et/ou d'absorption.

2. Dispositif selon la revendication 1, caractérisé en ce qu'une teinture pléochroïque est présente dans le cristal liquide.

3. Dispositif selon l'une des revendications 1 et 2, caractérisé en ce que le cristal liquide a un indice ordinaire de réfraction et un indice extraordinaire de réfraction, et en ce que l'indice extraordinaire de réfraction du cristal liquide et l'indice de réfraction du moyen de contention sont sensiblement identiques.


4. Dispositif selon l'une des revendications 1 à 3, caractérisé en ce que le cristal liquide a un indice ordinaire de réfraction et un indice extraordinaire de réfraction, et en ce que l'indice extraordinaire de réfraction est différent de l'indice de réfraction du moyen de contention pour provoquer une dispersion de la lumière en l'absence du signal d'entrée.

5. Dispositif selon l'une des revendications 1 à 4, caractérisé en ce que le moyen de contention a





* C L M S *



un moyen formant paroi non plane qui tend à déformer et/ou aligner au moins une partie du cristal liquide généralement par rapport à celui-ci en l'absence d'un signal d'entrée.

6. Dispositif selon l'une des revendications 1 à 4, caractérisé en ce que le moyen de contention a un moyen formant paroi non plane qui tend à déformer et/ou aligner au moins une partie du cristal liquide selon un alignement aléatoire en l'absence d'un signal d'entrée.

7. Dispositif selon l'une des revendications 1 à 6, caractérisé en ce que le moyen de contention comprend un moyen de contention contenant à l'intérieur une pluralité de volumes de cristal liquide.

8. Dispositif selon l'une des revendications 1 à 7, caractérisé en ce que le moyen de contention forme des volumes incurvés discrets contenant des quantités discrètes de cristal liquide et sert à déformer la structure naturelle du cristal liquide.

9. Dispositif selon l'une des revendications 1 à 8, caractérisé en ce que ledit cristal liquide et le moyen de contention comprennent un cristal liquide encapsulé.

10. Dispositif selon l'une des revendications 1 à 9, caractérisé en ce que le moyen de contention forme une pluralité de capsules de cristal liquide reliées par des parois formées par le moyen de contention, et en ce que la constante diélectrique des parois de ces capsules est telle que l'impédance dans un sens radial des capsules ne provoque pas une chute de tension substantielle par rapport à la chute de tension à travers le cristal liquide lors de l'application d'un champ électrique à travers les capsules.

11. Dispositif selon l'une des revendications 1 à 10, caractérisé en ce que le cristal liquide et le moyen de contention comportent des volumes de cristal liquide ayant une dimension allant d'environ 2 microns à environ 25 microns.

12. Dispositif selon l'une des revendications 1 à 11, caractérisé en ce que le moyen de contention comprend une résine ou un polymère.

13. Dispositif selon la revendication 12, caractérisé en ce que la résine ou le polymère sont sélectionnés parmi la gélatine, un polymère carboxy-polyméthylène, un copolymère dérivé d'anhydride maléique, un poly(méthyle vinyle éther/anhydride maléique), et de l'alcool polyvinylique.

14. Dispositif selon l'une des revendications 1 à 13, caractérisé en ce qu'il comporte un moyen formant substrat pour supporter la combinaison de cristal liquide et du moyen de contention.

15. Dispositif selon la revendication 14, caractérisé en ce qu'il comprend des moyens servant à faire adhérer la combinaison de cristal liquide et du moyen de contention au moyen formant substrat.

16. Dispositif selon l'une des revendications 1 à 15, caractérisé en ce que le signal d'entrée est un champ électrique ou un champ magnétique, le cristal liquide réagissant au champ pour s'aligner par rapport à celui-ci, et en ce que le cristal liquide et les moyens de contention coopèrent pour provoquer la dispersion ou l'absorption de la

lumière en l'absence du champ et pour réduire la dispersion ou l'absorption en présence du champ.

17. Dispositif selon la revendication 16, caractérisé en ce qu'il comprend des moyens servant à appliquer un champ électrique au cristal liquide.

18. Dispositif selon la revendication 17, caractérisé en ce que les moyens pour appliquer le champ électrique comprennent des électrodes.

19. Dispositif selon la revendication 18, caractérisé en ce qu'au moins une des électrodes est transparente et une autre des électrodes a la forme d'un motif.

20. Dispositif selon la revendication 19, caractérisé en ce qu'il comporte des moyens formant circuit pour appliquer l'énergie électrique aux électrodes.

21. Dispositif selon une des revendications 1 à 20, caractérisé en ce que le moyen de contention comporte des moyens définissant une surface qui tendent à s'aligner par rapport à au moins une partie du cristal liquide généralement parallèlement à celui-ci en l'absence d'un signal d'entrée.

22. Dispositif selon une des revendications 1 à 21, caractérisé en ce que le cristal liquide a une anisotropie diélectrique positive.

23. Dispositif selon une des revendications 1 à 22, caractérisé en ce que le cristal liquide est fonctionnellement un cristal liquide nématique.

24. Dispositif selon une des revendications 1 à 23, caractérisé en ce que le cristal liquide est un cristal liquide nématique.

25. Dispositif à cristaux liquides comprenant un cristal liquide et un moyen de contention pour contenir le cristal liquide dans une pluralité de volumes, caractérisé en ce que l'indice ordinaire de réfraction du cristal liquide est sensiblement égal à l'indice de réfraction du moyen de contention pour rendre maximale la transmission optique à travers le dispositif en présence d'un signal d'entrée.

26. Dispositif selon la revendication 25, caractérisé en ce que le cristal liquide a une anisotropie diélectrique positive.

27. Dispositif selon une des revendications 25 ou 26, caractérisé en ce que le cristal liquide a un indice extraordinaire de réfraction différent de l'indice de réfraction du moyen de contention.

28. Appareil optique comprenant un dispositif à cristaux liquides tel que défini dans l'une des revendications 1 à 27.

29. Appareil optique selon la revendication 28, caractérisé en ce qu'il se présente sous la forme d'un dispositif d'affichage optique.

30. Procédé pour fabriquer un cristal liquide nématique encapsulé, caractérisé en ce qu'il comprend le mélange d'au moins un moyen d'encapsulation, un cristal liquide nématique et une teinture pléochroïque.

31. Procédé pour faire fonctionner un cristal liquide sensiblement indépendamment de la direction de polarisation optique de la lumière incidente, caractérisé en ce qu'il comprend l'emprisonnement de ce cristal liquide dans au moins une capsule qui provoque la distorsion de la direction du cristal liquide.



29

EP 0 088 126 B1

30

32. Procédé selon la revendication 31, caractérisé en ce que ledit emprisonnement comprend le mélange d'un moyen d'encapsulation et du cristal liquide nématique.

33. Procédé selon la revendication 32, caractérisé en ce que la constante diélectrique du matériau d'encapsulation est supérieure ou égale à la constante diélectrique inférieure du cristal liquide.

34. Procédé selon l'une des revendications 32 et 33, caractérisé en ce que le cristal liquide a une anisotropie diélectrique positive.

35. Procédé selon l'une des revendications 33 et 34, caractérisé en ce que le cristal liquide a un indice ordinaire de réfraction sensiblement égal à

l'indice de réfraction du moyen d'encapsulation.

36. Procédé pour la fabrication de cristal liquide encapsulé comprenant le mélange d'un moyen d'encapsulation et d'un cristal liquide nématique, caractérisé en ce que le cristal liquide a un indice ordinaire de réfraction sensiblement égal à l'indice de réfraction du moyen d'encapsulation.

37. Procédé selon la revendication 36, caractérisé en ce que le cristal liquide a un indice de réfraction extraordinaire différent de l'indice de réfraction du moyen d'encapsulation.

38. Appareil optique comprenant du cristal liquide encapsulé préparé selon l'une des revendications 30 à 37.

5

10

15

20

25

30

35

40

45

50

55

60

65

16



* C L M S *