

TITLE OF THE INVENTION:

Low Oxide Trench Dishing Chemical Mechanical Polishing

CROSS REFERENCE TO RELATED PATENT APPLICATIONS

[0001] This application claims the benefit of priority under 35 U.S.C. § 119(e) to earlier filed U.S. patent applications Serial Numbers 62/692,633, and 62/692,639 filed on June 29, 2018, which are entirely incorporated herein by reference.

5

BACKGROUND OF THE INVENTION

[0002] This invention relates to the chemical mechanical planarization (CMP) of oxide and doped oxide films.

[0003] In the fabrication of microelectronics devices, an important step involved is polishing, especially surfaces for chemical-mechanical polishing for the purpose of recovering a selected material and/or planarizing the structure.

[0004] For example, a SiN layer is deposited under a SiO₂ layer to serve as a polish stop. The role of such polish stop is particularly important in Shallow Trench Isolation (STI) structures. Selectivity is characteristically expressed as the ratio of the oxide polish rate to the nitride polish rate. An example is an increased polishing selectivity rate of silicon dioxide(SiO₂) as compared to silicon nitride(SiN).

[0005] In the global planarization of patterned structures, reducing oxide trench dishing is a key factor to be considered. The lower trench oxide loss will prevent electrical current leaking between adjacent transistors. Non-uniform trench oxide loss across die (within Die) will affect transistor performance and device fabrication yields. Severe trench oxide loss (high oxide trench dishing) will cause poor isolation of transistor resulting in device failure. Therefore, it is important to reduce trench oxide loss by reducing oxide trench dishing in CMP polishing compositions.

[0006] US Patent 5,876,490 discloses the polishing compositions containing abrasive particles and exhibiting normal stress effects. The slurry further contains non-polishing particles resulting in reduced polishing rate at recesses, while the abrasive

particles maintain high polish rates at elevations. This leads to improved planarization. More specifically, the slurry comprises cerium oxide particles and polymeric electrolyte, and can be used for Shallow Trench Isolation (STI) polishing applications.

[0007] US Patent 6,964,923 teaches the polishing compositions containing cerium oxide particles and polymeric electrolyte for Shallow Trench Isolation (STI) polishing applications. Polymeric electrolyte being used includes the salts of polyacrylic acid, similar as those in US Patent 5,876,490. Ceria, alumina, silica & zirconia are used as abrasives. Molecular weight for such listed polyelectrolyte is from 300 to 20,000, but in overall, <100,000.

[0008] US Patent 6,616,514 discloses a chemical mechanical polishing slurry for use in removing a first substance from a surface of an article in preference to silicon nitride by chemical mechanical polishing. The chemical mechanical polishing slurry according to the invention includes an abrasive, an aqueous medium, and an organic polyol that does not dissociate protons, said organic polyol including a compound having at least three hydroxyl groups that are not dissociable in the aqueous medium, or a polymer formed from at least one monomer having at least three hydroxyl groups that are not dissociable in the aqueous medium.

[0009] US Patent 6,544,892 teaches the polishing compositions containing using abrasive, and an organic compound having a carboxylic acid functional group and a second functional group selected from amines and halides. Ceria particles were used as abrasives.

[0010] However, those prior disclosed Shallow Trench Isolation (STI) polishing compositions did not address the importance of oxide trench dishing reducing.

[0011] It should be readily apparent from the foregoing that there remains a need within the art for compositions, methods and systems of chemical mechanical polishing that can afford the reduced oxide trench dishing and improved over polishing window stability in a chemical and mechanical polishing (CMP) process, in addition to high removal rate of silicon dioxide as well as high selectivity for silicon dioxide to silicon nitride.

BRIEF SUMMARY OF THE INVENTION

[0012] The present invention provides Chemical mechanical polishing(CMP) polishing compositions, methods and systems for a reduced oxide trench dishing and

thus improved over polishing window stability by introducing chemical additives as oxide trench dishing reducing additives compositions at wide pH range including acidic, neutral and alkaline pH conditions.

5 **[0013]** The present invention also provides the benefits of achieving high oxide film removal rates, low SiN film removal rates, high and tunable Oxide: SiN selectivity, lower total defect counts post-polishing, and excellent mean particle size(nm) stability.

10 **[0014]** In one aspect, there is provided a CMP polishing composition comprises:
abrasive particles selected from the group consisting of inorganic oxide particles,
metal-coated inorganic oxide particles, organic polymer particles, metal oxide-coated
organic polymer particles and combinations thereof;
chemical additive as oxide trenching dishing reducer,
a solvent; and
optionally
biocide; and
15 pH adjuster;
wherein the composition has a pH of 2 to 12, preferably 3 to 10, and more preferably 4 to 9.

20 **[0015]** The inorganic oxide particles include but are not limited to ceria, colloidal silica, high purity colloidal silica, colloidal ceria, alumina, titania, zirconia particles.

20 **[0016]** An example of ceria particles are calcined ceria particles. An example of calcined ceria particles are calcined ceria particles manufactured from milling process.

[0017] An example of colloidal ceria particles is typically manufactured from chemical reactions and crystallization processes.

25 **[0018]** The metal-coated inorganic oxide particles include but are not limited to the ceria-coated inorganic oxide particles, such as, ceria-coated colloidal silica, ceria-coated high purity colloidal silica, ceria-coated alumina, ceria-coated titania, ceria-coated zirconia, or any other ceria-coated inorganic oxide particles.

30 **[0019]** The organic polymer particles include, but are not limited to, polystyrene particles, polyurethane particle, polyacrylate particles, or any other organic polymer particles.


[0020] The metal-coated organic polymer particles are selected from the group consisting of ceria-coated organic polymer particles, zirconia-coated organic polymer particles, silica-coated organic polymer particles, and combinations thereof.

[0021] The preferred abrasive particles are ceria-coated inorganic oxide particles and ceria particle. More preferred abrasive particles are ceria-coated silica particles and calcined ceria particles.

[0022] The solvent includes but is not limited to deionized (DI) water, distilled water, and alcoholic organic solvents.

[0023] The chemical additives as oxide trenching dishing reducers contain at least two or more, preferably four or more, more preferably six or more hydroxyl functional groups in their molecular structures.

[0024] In one embodiment, the chemical additive has a general molecular structure as shown below:




[0025] In the general molecular structure, n is selected from 2 to 5,000, from 3 to 12, preferably from 4 to 7.

[0026] R1, R2, and R3 can be the same or different atoms or functional groups.

[0027] Each of Rs in the group of R1 to R3 can be independently selected from the group consisting of hydrogen, alkyl, alkoxy, organic group with one or more hydroxyl groups, substituted organic sulfonic acid, substituted organic sulfonic acid salt, substituted organic carboxylic acid, substituted organic carboxylic acid salt, organic carboxylic ester, organic amine groups, and combinations thereof; wherein, at least two or more, preferably four of them are hydrogen atoms.


[0028] When R1, R2, and R3 are the same and are hydrogen atoms, the chemical additive bears multi hydroxyl functional groups.

[0029] The molecular structures of some examples of such chemical additives are listed below:




Ribitol,

5




Xylitol,




Meso-erythritol,


10




D-sorbitol,



Mannitol,




Dulcitol,



Iditol,

[0030] In another embodiment, the chemical additive has a structure shown below:




[0031] In this structure, one -CHO functional group is located at one end of the molecule as the terminal functional group; n is selected from 2 to 5,000, from 3 to 12, preferably from 4 to 7.

[0032] Each of R1 and R2 can be independently selected from the group consisting of hydrogen, alkyl, alkoxy, organic group with one or more hydroxyl groups, substituted organic sulfonic acid, substituted organic sulfonic acid salt, substituted organic carboxylic acid, substituted organic carboxylic acid salt, organic carboxylic ester,

5 organic amine groups, and combinations thereof.


[0033] When R1 and R2 are all hydrogen atoms, and $n=3$, the chemical additive is D-arabinose or L-arabinose:



D-Arabinose

L-Arabinose


10 **[0034]** When R1 and R2 are all hydrogen atoms, and $n=4$, the chemical additive is D-mannose or L-mannose.



D-Mannose

L-Mannose

[0035] In yet another embodiment, the chemical additive has a molecular structure selected from the group comprising of at least one (f), at least one (g), at least one (h) and combinations thereof;




[0036] In these general molecular structures; R1, R2, R3, R4, R5, R6, R7 R8, R9, R10, R11, R12, R13, and R14 can be the same or different atoms or functional groups.


[0037] They can be independently selected from the group consisting of hydrogen, alkyl, alkoxy, organic group with one or more hydroxyl groups, substituted organic sulfonic acid, substituted organic sulfonic acid salt, substituted organic carboxylic acid, substituted organic carboxylic acid salt, organic carboxylic ester, organic amine groups, and combinations thereof; wherein, at least two or more, preferably four or more of them are hydrogen atoms.

[0038] When R1, R2, R3 R4, R5, R6, R7 R8, R9, R10, R11, R12, R13, and R14 are all hydrogen atoms which provide the chemical additives bearing multi hydroxyl functional groups.


[0039] The molecular structures of some examples of such chemical additives are listed below:




10 D- (-)-Fructose,





Sorbitan,




Sucrose,



beta-lactose,



Inositol, and




5

- 10 **[0040]** Yet, in another embodiment, the chemical additives contain at least one six-member ring structure motif ether bonded with at least one polyol molecular unit

containing multiple hydroxyl functional groups in the molecular unit structures or at least one polyol molecular unit containing multiple hydroxyl functional groups in the molecular unit structures and at least one six-member ring polyol. A polyol is an organic compound containing hydroxyl groups.

- 5 **[0041]** The chemical additives as oxide trenching dishing reducers contain at least two, at least four, or at least six hydroxyl functional groups in their molecular structures.


[0042] The general molecular structure for the chemical additives is shown in (a):



10

(a).

[0043] In one embodiment, at least one R in the group of R1 to R5 in the general molecular structure is a polyol molecular unit having a structure shown in (b):




(b);

- 15 wherein n and m can be the same or different. m or n is independently selected from 1 to 5, preferably from 1 to 4, more preferably from 1 to 3, and most preferably from 1 to 2; R6 to R9 can be the same or different atoms or functional groups; and

the rest of Rs in the group of R1 to R5 can be independently selected from the group consisting of hydrogen, alkyl, alkoxy, organic group with one or more hydroxyl groups, substituted organic sulfonic acid or salt, substituted organic carboxylic acid or salt, organic carboxylic ester, organic amine, and combinations thereof.

20

[0044] In another embodiment, at least one R in the group of R1 to R5 in the general molecular structure is a polyol molecular unit having a structure shown in (b); at least one R in the group of R1 to R5 in the general molecular structure is a six-member ring polyol as shown in (c):



5

(c);

wherein one of OR in group of OR11, OR12, OR13 and OR14 will be replaced by O in structure (c); and R10 and each of other R in group of R11, R12, R13 and R14 is independently selected from the group consisting of hydrogen, alkyl, alkoxy, organic group with one or more hydroxyl groups, substituted organic sulfonic acid or salt, substituted organic carboxylic acid or salt, organic carboxylic ester, organic amine, and combinations thereof;

10


and the rest of Rs in the group of R1 to R5 can be independently selected from the group consisting of hydrogen, alkyl, alkoxy, organic group with one or more hydroxyl groups, substituted organic sulfonic acid or salt, substituted organic carboxylic acid or salt, organic carboxylic ester, organic amine, and combinations thereof.

15


[0045] In the general molecular structure, at least two, preferably four, more preferably six of the Rs in the group of R1 to R9 are hydrogen atoms.

[0046] When only one R, such as R5 in the group of R1 to R5 in the general molecular structure is a polyol molecular unit (b) having $n = 2$ and $m = 1$; and all rest of Rs in the group of R1 to R9 are all hydrogen atoms, the following two chemical additives are obtained:

20




Maltitol



Lactitol

- 5 [0047] When one R, such as R5 is a polyol molecular unit (b) having $n = 2$ and $m = 1$; and one R, such as R2 is a six-member ring polyol; and all rest of Rs in the group of R1 to R14 are all hydrogen atoms, the following chemical additive is obtained:



Maltotritol

[0048] The chemical additive comprises maltitol, lactitol, maltotritol, ribitol, D-sorbitol, mannitol, dulcitol, iditol, D- (-)-Fructose, sorbitan, sucrose, ribose, Inositol, glucose, D-arabinose, L-arabinose, D-mannose, L-mannose, meso-erythritol, beta-lactose, arabinose, and combinations thereof. The preferred chemical additives are maltitol, lactitol, maltotritol, D-sorbitol, mannitol, dulcitol, iditol, D- (-)-Fructose, sucrose, ribose, Inositol, glucose. D-mannose, L-mannose, beta-lactose, and combinations thereof. The more preferred chemical additives are maltitol, lactitol, maltotritol, D-sorbitol, mannitol, dulcitol, D- (-)-Fructose, beta-lactose, and combinations thereof.

[0049] In some embodiments, the CMP polishing compositions can be made into two or more parts and mixed at the point of use.

[0050] In another aspect, there is provided a method of chemical mechanical polishing (CMP) a substrate having at least one surface comprising silicon dioxide (such as tetraethyl orthosilicate or TEOS) using the chemical mechanical polishing (CMP) composition described above.

[0051] In yet another aspect, there is provided a system of chemical mechanical polishing (CMP) a substrate having at least one surface comprising silicon dioxide using the chemical mechanical polishing (CMP) composition described above.

[0052] The polished oxide films can be Chemical vapor deposition (CVD), Plasma Enhance CVD (PECVD), High Density Deposition CVD(HDP), spin on oxide films, flowable CVD oxide film, carbon doped oxide film, nitrogen doped oxide film, or combinations thereof.

[0053] The substrate disclosed above can further comprises a silicon nitride(SiN) surface. The removal selectivity of SiO₂: SiN is greater than 10, preferably greater than 20, and more preferably greater than 30.

BRIEF DESCRIPTION OF SEVERAL VIEWS OF THE DRAWINGS

[0054] Figure 1. Depicts the effects of Ceria-coated Silica/D-Sorbitol Ratio on Film RR (A/min.)

[0055] Figure 2. Depicts the effects of Ceria-coated Silica/D-Sorbitol Ratio on Oxide Trench Dishing

DETAILED DESCRIPTION OF THE INVENTION

5 **[0056]** This invention relates to the Chemical mechanical polishing(CMP) compositions, methods and systems for oxide and doped oxide films polishing.

[0057] In the global planarization of patterned structures, reducing oxide trench dishing is a key factor to be considered. The lower trench oxide loss will prevent electrical current leaking between adjacent transistors. Non-uniform trench oxide loss
10 across die or/and within Die will affect transistor performance and device fabrication yields. Severe trench oxide loss (high oxide trench dishing) will cause poor isolation of transistor resulting in device failure. Therefore, it is important to reduce trench oxide loss by reducing oxide trench dishing in CMP polishing compositions.

[0058] The CMP compositions comprise the unique combination of abrasive particles
15 and the suitable chemical additives, such as maltitol, lactitol, and maltotritol, or any other chemical molecules with similar molecular structures and functional groups.

[0059] This invention provides a reduced oxide trench dishing and thus improved over polishing window stability by introducing chemical additives as oxide trench dishing reducing additives in the Chemical mechanical polishing(CMP) compositions at
20 wide pH range including acidic, neutral and alkaline pH conditions.

[0060] The Chemical Mechanical Polishing (CMP) compositions provide high oxide film removal rates, low SiN film removal rates and high SiO₂: SiN selectivity.

[0061] The Chemical Mechanical Polishing (CMP) compositions also provided significant total defect count reduction while comparing the CMP polishing
25 compositions using calcinated ceria particles as abrasives.

[0062] The Chemical Mechanical Polishing (CMP) composition also further provides excellent mean particle size and size distribution stability for the abrasive particles which is very important in maintaining robust CMP polishing performances with minimized polishing performance variations.

30 **[0063]** In one aspect, there is provided a CMP polishing composition comprises:

abrasive particles selected from the group consisting of inorganic oxide particles, metal-coated inorganic oxide particles, organic polymer particles, metal oxide-coated organic polymer particles and combinations thereof;

chemical additive as oxide trenching dishing reducer,

5 a solvent; and

optionally

biocide; and

pH adjuster;

wherein the composition has a pH of 2 to 12, preferably 3 to 10, and more preferably 4
10 to 9.

[0064] The inorganic oxide particles include but are not limited to ceria, colloidal silica, high purity colloidal silica, colloidal ceria, alumina, titania, zirconia particles.

[0065] An example of ceria particles are calcined ceria particles. An example of calcined ceria particles are calcined ceria particles manufactured from milling process.

15 **[0066]** An example of colloidal ceria particles is typically manufactured from chemical reactions and crystallization processes.

[0067] The metal-coated inorganic oxide particles include but are not limited to the ceria-coated inorganic oxide particles, such as, ceria-coated colloidal silica, ceria-coated high purity colloidal silica, ceria-coated alumina, ceria-coated titania, ceria-coated zirconia, or any other ceria-coated inorganic oxide particles.
20

[0068] The organic polymer particles include, but are not limited to, polystyrene particles, polyurethane particle, polyacrylate particles, or any other organic polymer particles.

25 **[0069]** The metal-coated organic polymer particles are selected from the group consisting of ceria-coated organic polymer particles, zirconia-coated organic polymer particles, silica-coated organic polymer particles, and combinations thereof;


[0070] The average mean particle sizes or mean particle sizes (MPS) of the abrasive particles are ranged from 2 to 1,000nm, 5 to 500nm, 15 to 400 nm or 25 to 250nm. MPS refers to diameter of the particles and is measured using dynamic light
30 scattering (DLS) technology.

- [0071]** The concentrations of these abrasive particles range from 0.01 wt.% to 20 wt.%, the preferred concentrations range from 0.05 wt.% to 10 wt.%, the more preferred concentrations range from 0.1 wt.% to 5 wt.%.
- [0072]** The preferred abrasive particles are ceria-coated inorganic oxide particles and ceria particle. More preferred abrasive particles are ceria-coated silica particles and calcined ceria particles.
- [0073]** The solvent includes but is not limited to deionized (DI) water, distilled water, and alcoholic organic solvents.
- [0074]** The preferred solvent is DI water.
- 10 **[0075]** The CMP slurry may contain biocide from 0.0001 wt.% to 0.05 wt.%; preferably from 0.0005 wt.% to 0.025 wt.%, and more preferably from 0.001 wt.% to 0.01 wt.%.
- [0076]** The biocide includes, but is not limited to, Kathon™, Kathon™ CG/ICP II, from Dupont/Dow Chemical Co. Bioban from Dupont/Dow Chemical Co. They have active ingredients of 5-chloro-2-methyl-4-isothiazolin-3-one or 2-methyl-4-isothiazolin-3-one.
- 15 **[0077]** The CMP slurry may contain a pH adjusting agent.
- [0078]** An acidic or basic pH adjusting agent can be used to adjust the polishing compositions to the optimized pH value.
- 20 **[0079]** The pH adjusting agents include, but are not limited to nitric acid, hydrochloric acid, sulfuric acid, phosphoric acid, other inorganic or organic acids, and mixtures thereof.
- [0080]** pH adjusting agents also include the basic pH adjusting agents, such as sodium hydride, potassium hydroxide, ammonium hydroxide, tetraalkyl ammonium hydroxide, organic quaternary ammonium hydroxide compounds, organic amines, and other chemical reagents that can be used to adjust pH towards the more alkaline direction.
- 25 **[0081]** The CMP slurry contains 0 wt.% to 1 wt.%; preferably 0.01 wt.% to 0.5 wt.%; more preferably 0.1 wt.% to 0.25 wt.% pH adjusting agent.

[0082] The CMP slurry contains 0.01 wt.% to 20 wt.%, 0.025 wt.% to 10 wt.%, 0.05 wt.% to 5 wt.%, or 0.1 to 3.0 wt.% of the chemical additives as oxide trenching dishing and total defect count reducers.

[0083] The chemical additives as oxide trenching dishing reducers contain at least two or more, preferably four or more, more preferably six or more hydroxyl functional groups in their molecular structures.

[0084] In one embodiment, the chemical additive has a general molecular structure as shown below:




[0085] In the general molecular structure, n is selected from 2 to 5,000, from 3 to 12, preferably from 4 to 7.

[0086] R1, R2, and R3 can be the same or different atoms or functional groups.


[0087] Each of Rs in the group of R1 to R3 can be independently selected from the group consisting of hydrogen, alkyl, alkoxy, organic group with one or more hydroxyl groups, substituted organic sulfonic acid, substituted organic sulfonic acid salt, substituted organic carboxylic acid, substituted organic carboxylic acid salt, organic carboxylic ester, organic amine groups, and combinations thereof; wherein, at least two or more, preferably four of them are hydrogen atoms.

[0088] When R1, R2, and R3 are the same and are hydrogen atoms, the chemical additive bears multi hydroxyl functional groups.


[0089] The molecular structures of some examples of such chemical additives are listed below:




Ribitol,




Xylitol,




Meso-erythritol,




D-sorbitol,



Mannitol,




Dulcitol,



Iditol.


[0090] In another embodiment, the chemical additive has a structure shown below:




[0091] In this structure, one -CHO functional group is located at one end of the molecule as the terminal functional group; n is selected 2 to 5,000, from 3 to 12, preferably from 4 to 7.

[0092] R1 and R2 can be independently selected from the group consisting of hydrogen, alkyl, alkoxy, organic group with one or more hydroxyl groups, substituted organic sulfonic acid, substituted organic sulfonic acid salt, substituted organic carboxylic acid, substituted organic carboxylic acid salt, organic carboxylic ester, organic amine groups, and combinations thereof.


[0093] When R1 and R2 are all hydrogen atoms, and $n=3$, the chemical additive is D-arabinose or L-arabinose.




[0094] When R1, R2 and R3 are all hydrogen atoms, and $n=4$, the chemical additive is D-mannose or L-mannose.




[0095] In yet another embodiment, the chemical additive has a molecular structure selected from the group comprising of at least one (f), at least one (g), at least one (h) and combinations thereof;



(f).



(g).



(h)

5

[0096] In these general molecular structures; R1, R2, R3, R4, R5, R6, R7 R8 , R9, R10, R11, R12, R13, and R14 can be the same or different atoms or functional groups.


[0097] They can be independently selected from the group consisting of hydrogen, alkyl, alkoxy, organic group with one or more hydroxyl groups, substituted organic sulfonic acid, substituted organic sulfonic acid salt, substituted organic carboxylic acid, substituted organic carboxylic acid salt, organic carboxylic ester, organic amine groups, and combinations thereof; wherein, at least two or more, preferably four or more of them are hydrogen atoms.

[0098] When R1, R2, R3 R4, R5, R6, R7 R8 , R9, R10, R11, R12, R13, and R14 are all hydrogen atoms which provide the chemical additives bearing multi hydroxyl functional groups.


[0099] The molecular structures of some examples of such chemical additives are listed below:

[00100]

5




D- (-)-Fructose,




Sorbitan,

10





Sucrose,




beta-lactose,

15



Inositol, and




5

- 10 **[00101]** Yet, in another embodiment, the chemical additives contain at least one six-member ring structure motif ether bonded with at least one polyol molecular unit

containing multiple hydroxyl functional groups in the molecular unit structures or at least one polyol molecular unit containing multiple hydroxyl functional groups in the molecular unit structures and at least one six-member ring polyol. A polyol is an organic compound containing hydroxyl groups.

- 5 **[00102]** The chemical additives as oxide trenching dishing reducers contain at least two, at least four, or at least six hydroxyl functional groups in their molecular structures.


[00103] The general molecular structure for the chemical additives is shown in (a):



10

(a).

[00104] In one embodiment, at least one R in the group of R1 to R5 in the general molecular structure is a polyol molecular unit having a structure shown in (b):




(b);

- 15 wherein n and m can be the same or different. m or n is independently selected from 1 to 5, preferably from 1 to 4, more preferably from 1 to 3, and most preferably from 1 to 2; R6 to R9 can be the same or different atoms or functional groups; and

the rest of Rs in the group of R1 to R5 can be independently selected from the group consisting of hydrogen, alkyl, alkoxy, organic group with one or more hydroxyl groups, substituted organic sulfonic acid or salt, substituted organic carboxylic acid or salt, organic carboxylic ester, organic amine, and combinations thereof.

20

[00105] In another embodiment, at least one R in the group of R1 to R5 in the general molecular structure is a polyol molecular unit having a structure shown in (b); at least one R in the group of R1 to R5 in the general molecular structure is a six-member ring polyol as shown in (c):



5

(c);

wherein one of OR in group of OR11, OR12, OR13 and OR14 will be replaced by O in structure (c); and R10 and each of other R in group of R11, R12, R13 and R14 is independently selected from the group consisting of hydrogen, alkyl, alkoxy, organic group with one or more hydroxyl groups, substituted organic sulfonic acid or salt, substituted organic carboxylic acid or salt, organic carboxylic ester, organic amine, and combinations thereof;

10


and the rest of Rs in the group of R1 to R5 can be independently selected from the group consisting of hydrogen, alkyl, alkoxy, organic group with one or more hydroxyl groups, substituted organic sulfonic acid or salt, substituted organic carboxylic acid or salt, organic carboxylic ester, organic amine, and combinations thereof.

15


[00106] In the general molecular structure, at least two, preferably four, more preferably six of the Rs in the group of R1 to R9 are hydrogen atoms.

[00107] When only one R, such as R5 in the group of R1 to R5 in the general molecular structure is a polyol molecular unit (b) having $n = 2$ and $m = 1$; and all rest of Rs in the group of R1 to R9 are all hydrogen atoms, the following two chemical additives are obtained:

20




Maltitol



Lactitol

- 5 **[00108]** When one R, such as R5 is a polyol molecular unit (b) having $n = 2$ and $m = 1$; and one R, such as R2 is a six-member ring polyol; and all rest of Rs in the group of R1 to R14 are all hydrogen atoms, the following chemical additive is obtained:



Maltotritol

[00109] The chemical additive comprises maltitol, lactitol, maltotritol, ribitol, D-sorbitol, mannitol, dulcitol, iditol, D- (-)-Fructose, sorbitan, sucrose, Inositol, glucose, D-
5 arabinose, L-arabinose, D-mannose, L-mannose, meso-erythritol, ribose, beta-lactose, and combinations thereof. The preferred chemical additives are maltitol, lactitol, maltotritol, D-sorbitol, mannitol, dulcitol, iditol, D- (-)-Fructose, sucrose, ribose, Inositol, glucose. D-(+)-mannose, beta-lactose, and combinations thereof. The more preferred chemical additives are maltitol, lactitol, maltotritol, D-sorbitol, mannitol, dulcitol, D- (-)-
10 Fructose, beta-lactose, and combinations thereof.

[00110] In some embodiments, the CMP polishing compositions can be made into two or more parts and mixed at the point of use.

[00111] In another aspect, there is provided a method of chemical mechanical polishing (CMP) a substrate having at least one surface comprising silicon dioxide
15 using the chemical mechanical polishing (CMP) composition described above. The polished oxide films can be CVD oxide, PECVD oxide, High density oxide, or Spin on oxide films.

[00112] The polished oxide films can be Chemical vapor deposition (CVD), Plasma Enhance CVD (PECVD), High Density Deposition CVD(HDP), spin on oxide films,
20 flowable CVD oxide film, carbon doped oxide film, nitrogen doped oxide film, or combinations thereof.

[00113] The substrate disclosed above can further comprises a silicon nitride surface. The removal selectivity of SiO₂: SiN is greater than 10, preferably greater than 20, and more preferably greater than 30.

25 **[00114]** Dishing performance of the CMP compositions can also be characterized by the ratio of oxide trench dishing rate (Å/min.) vs the blanket HDP film removal rate(Å/min.).

[00115] The smaller of this ratio is, the lower oxide trench dishing is.

[00116] The CMP compositions having the ratio of ≤ 0.1 , 0.08, 0.06, 0.05, 0.03, or
30 0.02 provide good oxide dishing performance.

[00117] In CMP polishing compositions, it is very important to keep abrasive particles stable to assure consistent desired CMP polishing performance.

[00118] When using the chemical additives in the CMP polishing compositions, these chemical additives can have some impacts on the stability of abrasive particles
5 in the compositions.

[00119] For example, when maltitol, lactitol or their derivatives, are used as oxide trench reducing agents in polishing compositions, these chemical additives can have some impacts on the stability of ceria-coated inorganic oxide abrasives in the CMP polishing compositions.

10 **[00120]** Typically, the abrasive particle stability is tested by monitoring the mean particle size (MPS) (nm) and particle size distribution parameter D99(nm) changes vs the times or at elevated temperatures.

[00121] Particle size distribution may be quantified as a weight percentage of particles that has a size lower than a specified size. For example, parameter D99(nm)
15 represents a particle size (diameter) where 99 wt.% of all the slurry particles would have particle diameter equal to or smaller than the D99(nm). That is, D99(nm) is a particle size that 99 wt.% of the particles fall on and under.

[00122] The smaller of MPS (nm) and D99(nm) changes, the more stable of the abrasive particles are and thus the CMP polishing compositions are.

20 **[00123]** Particle size distribution can be measured by any suitable techniques such as imaging, dynamic light scattering, hydrodynamic fluid fractionation, disc centrifuge etc.

[00124] MPS(nm) and D99 (nm) are both measured by dynamic light scattering in this application.

[00125] CMP compositions providing abrasive particle stability have the changes for
25 MPS (nm) and D99(nm) $\leq$ 6.0%, 5.0%, 3.0%, 2.0%, 1.0%, 0.5 %, 0.3% or 0.1% for a shelf time of at least 30 days, 40 days, 50 days, 60 days, 70 days or 100 days at a temperature ranging from 20 to 60 °C, 25 to 50 °C.

[00126] The following non-limiting examples are presented to further illustrate the present invention.

30

[00127] In the examples presented below, CMP experiments were run using the procedures and experimental conditions given below.

GLOSSARY

5

COMPONENTS

[00128] Calcinate ceria particles: used as abrasives having a particle size of approximately 150 nanometers (nm); such ceria-coated silica particles can have a particle size of ranged from approximately 5 nanometers (nm) to 500 nanometers (nm).

[00129] Ceria-coated Silica: used as abrasive having a particle size of approximately 100 nanometers (nm); such ceria-coated silica particles can have a particle size of ranged from approximately 5 nanometers (nm) to 500 nanometers (nm);

[00130] Ceria-coated Silica particles (with varied sizes) were supplied by JGC Inc. in Japan.

[00131] Chemical additives, such as D-sorbitol, dulcitol, fructose, maltitol, lactitol and other chemical raw materials were supplied by Sigma-Aldrich, St. Louis, MO.

[00132] TEOS: tetraethyl orthosilicate

[00133] Polishing Pad: Polishing pad, IC1010 and other pads were used during CMP, supplied by DOW, Inc.

PARAMETERS

General

[00134] Å or A: angstrom(s) – a unit of length

[00135] BP: back pressure, in psi units

[00136] CMP: chemical mechanical planarization = chemical mechanical polishing

[00137] CS: carrier speed

[00138] DF: Down force: pressure applied during CMP, units psi

[00139] min: minute(s)

[00140] ml: milliliter(s)

[00141] mV: millivolt(s)

[00142] psi: pounds per square inch

5 **[00143]** PS: platen rotational speed of polishing tool, in rpm (revolution(s) per minute)

[00144] SF: slurry flow, ml/min

[00145] Wt. %: weight percentage (of a listed component)

[00146] TEOS: SiN Selectivity: (removal rate of TEOS)/ (removal rate of SiN)

[00147] HDP: high density plasma deposited TEOS

10 **[00148]** TEOS or HDP Removal Rates: Measured TEOS or HDP removal rate at a given down pressure. The down pressure of the CMP tool was 2.5 psi, 3.0 psi or 3.3 psi or 4.3 psi in the examples.

[00149] SiN Removal Rates: Measured SiN removal rate at a given down pressure. The down pressure of the CMP tool was 3.0 psi in the examples listed.

15

Metrology

[00150] Films were measured with a ResMap CDE, model 168, manufactured by Creative Design Engineering, Inc, 20565 Alves Dr., Cupertino, CA, 95014. The ResMap tool is a four-point probe sheet resistance tool. Forty-nine-point diameter scan at 5mm edge exclusion for film was taken.

20

CMP Tool

[00151] The CMP tool that was used is a 200mm Mirra, or 300mm Reflexion manufactured by Applied Materials, 3050 Bowers Avenue, Santa Clara, California, 95054. An IC1000 pad supplied by DOW, Inc, 451 Bellevue Rd., Newark, DE 19713 was used on platen 1 for blanket and pattern wafer studies.

25

[00152] The IC1010 pad or other pad was broken in by conditioning the pad for 18 mins. At 7 lbs. down force on the conditioner. To qualify the tool settings and the pad

break-in two tungsten monitors and two TEOS monitors were polished with Versum® STI2305 slurry, supplied by Versum Materials Inc. at baseline conditions.

Wafers

- 5 **[00153]** Polishing experiments were conducted using PECVD or LECVD or HD TEOS wafers. These blanket wafers were purchased from Silicon Valley Microelectronics, 2985 Kifer Rd., Santa Clara, CA 95051.

Polishing Experiments

- 10 **[00154]** In blanket wafer studies, oxide blanket wafers, and SiN blanket wafers were polished at baseline conditions. The tool baseline conditions were: table speed; 87 rpm, head speed: 93 rpm, membrane pressure; 2.5 psi, 3.0 psi or 3.3 psi or 4.3 psi, inter-tube pressure; 3.1 psi or others, retaining ring pressure; 5.1psi or others,

- 15 **[00155]** The slurry was used in polishing experiments on patterned wafers (MIT860), supplied by SWK Associates, Inc. 2920 Scott Blvd. Santa Clara, CA 95054). These wafers were measured on the Veeco VX300 profiler/AFM instrument. The 3 different sized pitch structures were used for oxide dishing measurement. The wafer was measured at center, middle, and edge die positions.

- 20 **[00156]** TEOS: SiN Selectivity: (removal rate of TEOS)/ (removal rate of SiN) obtained from the CMP polishing compositions were tunable.

Working Examples

- 25 **[00157]** In the following working examples, a polishing composition comprising 0.2 wt.% cerium-coated silica, a biocide ranging from 0.0001 wt.% to 0.05 wt.%, and deionized water was prepared as reference (ref.).

[00158] The polishing compositions were prepared with the reference (0.2 wt.% cerium-coated silica, a biocide ranging from 0.0001 wt.% to 0.05 wt.%, and deionized water) plus a chemical additive in 0.01 wt.% to 2.0 wt.%.

- 30 **[00159]** All examples, except pH condition examples the composition had a pH at 5.35.

[00160] pH adjusting agent used for acidic pH condition and alkaline pH condition were nitric acid and ammonium hydroxide respectively.

Example 1

5 [00161] The working slurries has 0.15 wt.% chemical additives added to the reference slurry.

[00162] The effects of various selected chemical additives on the film removal rates and selectivity were observed.

10 [00163] The removal rates (RR at Å/min) for different films were tested. The test results were listed in Table 1.

Table 1. Effects of Chemical Additives on Film RR (Å/min.) & TEOS: SiN Selectivity

Samples	TEOS-RR (ang/min)	HDP-RR (ang/min)	SiN-RR (ang/min)	TEOS: SiN Selectivity
0.2 wt.% Ceria-coated Silica (Ref.)	3279	2718	349	9
Ref.+0.15 wt.% D-Sorbitol	2394	2299	75	32
Ref.+0.15 wt.% D-Mannitol	2741	2372	124	22
Ref.+0.15 wt.% D- (+)- Mannose	2839	2104	148	19
Ref.+ 0.15 wt.% Xylitol	2694	2256	109	25
Ref.+ 0.15 wt.% meso- Erythritol	2808	2064	366	8

[00164] As the results showed in Table 1, the slurries based on ceria-coated silica offered higher removal rate for TEOS.

15 [00165] As the results further showed in Table 1, the chemical additives D-sorbitol, D-mannitol, D-mannose, and xylitol, except meso-erythritol suppressed SiN removal rates comparing with the Ref., while still afforded high TEOS and HDP film removal rates and provided high Oxide: SiN selectivity.

20

Example 2

[00166] In Example 2, 0.2 wt.% ceria-coated silica abrasive based formulation without chemical additives was used as reference.

[00167] The chemical additives were used at 0.15 wt.% (0.15X) concentrations respectively with 0.2 wt.% ceria-coated silica as abrasives in the working slurries.

[00168] The effects of various selected chemical additives on the oxide trenching dishing vs over polishing times were observed.

- 5 **[00169]** The test results were listed in Table 2. HDP RR (Å/min.) from Table 1 was also listed in Table 2.

Table 2. Effects of Chemical Additives on Oxide Trench Dishing & HDP RR (Å/min.)

Compositions	OP Time (sec.)	100um pitch dishing	200um pitch dishing	Blanket HDP RR (Å/min.)
0.2% Ceria-coated Silica pH 5.35	0	165	291	2718
	60	857	1096	
	120	1207	1531	
0.2% Ceria-coated Silica + 0.15X D-Sorbitol	0	137	276	2299
	60	247	411	
	120	380	544	
0.2% Ceria-coated Silica + 0.15X D-mannitol	0	162	285	2372
	60	368	580	
	120	563	816	
0.2% Ceria-coated Silica + 0.15X D-(+)-Mannose	0	181	272	2401
	60	660	973	
	120	1121	1553	
0.2% Ceria-coated Silica + 0.15X Xylitol	0	144	258	2256
	60	485	800	
	120	760	1166	
0.2% Ceria-coated Silica + 0.15X meso-Erythritol	0	131	265	2064
	60	732	896	
	120	1125	1392	

Table 3. The Ratio of Trench Dishing Rate (Å)/Blanket HDP RR (Å/min.)

Compositions	P100 Dishing Rate (Å/min.) /Blanket HDP RR (Å/min.)	P200 Dishing Rate (Å/min.) /Blanket HDP RR (Å/min.)
0.2% Ceria-coated Silica pH 5.35	0.13	0.16
0.2% Ceria-coated Silica + 0.15X D-Sorbitol	0.06	0.06
0.2% Ceria-coated Silica + 0.15X D-mannitol	0.08	0.12
0.2% Ceria-coated Silica + 0.15X D-(+)-Mannose	0.2	0.24
0.2% Ceria-coated Silica + 0.15X Xylitol	0.12	0.16
0.2% Ceria-coated Silica + 0.15X meso-Erythritol	0.19	0.24

[00170] Table 3 listed the ratio of oxide trench dishing rate ($\text{\AA}/\text{min.}$) vs the blanket HDP film removal rate($\text{\AA}/\text{min.}$),

[00171] As the results shown in Tables 2 and 3, the addition of various chemical additives as oxide trench dishing reducer in polishing compositions showed different effects.

[00172] The polishing compositions using D-sorbitol and D-mannitol provided significant oxide trench dishing reductions on both 100 μm pitch and 200 μm pitch respectively, comparing to the reference.

[00173] The polishing composition using xylitol showed no impact on oxide trench dishing in polishing comparing to the reference. The polishing compositions using D-(+)-mannose or meso-erythritol had the oxide trench dishing worse than the reference.

[00174] The effects of chemical additives on the slopes of oxide trenching dishing vs over polishing removal amounts were listed in Table 4.

Table 4. Effects of Chemical Additives on Slopes of Dishing vs OP Removal Amount

Compositions	P100 dishing/OP Amt Slope	P200 dishing/OP Amt Slope	P1000 dishing/OP Amt Slope
0.2X Ceria-coated Silica	0.19	0.23	0.25
0.2X Ceria-coated Silica + 0.15x D-Sorbitol	0.05	0.06	0.08
0.2X Ceria-coated Silica + 0.15x D-Mannitol	0.08	0.11	0.40
0.2X Ceria Coated + 0.15x D- (+)-Mannose	0.20	0.27	0.38
0.2X Ceria-coated Silica + 0.15x Xylitol	0.14	0.20	0.41

[00175] As the results shown in Table 4, the polishing composition using D-sorbitol or D-mannitol afforded much lower slope values of oxide trench dishing vs over polishing amounts on 100 μm and 200 μm features while comparing to the reference.

[00176] The other additives offered no dishing improvements comparing to the reference.

Example 3

[00177] The effects of various selected chemical additives on the film removal rates (RR at Å/min) and selectivity were observed. These chemical additives were used at 0.1 wt.% concentrations respectively with 0.2 wt.% ceria-coated silica as abrasives.

[00178] The test results were listed in Table 5.

5 Table 5. Effects of Chemical Additives on Film RR (Å/min.) & TEOS: SiN Selectivity

Samples	TEOS-RR (ang/min)	HDP-RR (ang/min)	SiN-RR (ang/min)	TEOS: SiN Selectivity
0.2% Ceria-Coated Silica	3279	2718	349	9.4
+ 0.1x D-Sorbitol	2968	2814	92	32.3
+ 0.1x D- (-)-Fructose	1662	1781	34	48.9
+ 0.1x Maltitol	2834	2679	38	74.6
+ 0.1x Dulcitol	3127	2995	45	69.5

[00179] As the results showed in Table 5, these chemical additives D-sorbitol, D- (-)-Fructose, Maltitol and Dulcitol suppressed SiN removal rates while comparing with reference, and still afforded high TEOS and HDP film removal rates.

Table 6. Effects of Chemical Additives on Oxide Trench Dishing & HDP RR (Å/min.)

Samples	OP Time (Sec.)	100um pitch dishing	200um pitch dishing	1000um pitch dishing	Blanket HDP RR (Å/min.)
0.2% Ceria-coated Silica	0	165	291	1013	2718
	60	857	1096	1821	
	120	1207	1531	2392	
0.2% Ceria-coated Silica + 0.1x D-Sorbitol	0	98	184	432	2814
	60	261	383	1494	
	120	418	583	1936	
0.2% Ceria-coated Silica + 0.1x D- (-)-Fructose	0	123	229	694	1781
	60	315	372	962	
	120	458	527	1175	
0.2% Ceria-coated Silica + 0.1x Maltitol	108	218	620	620	2679
	228	355	873	873	
	333	482	1068	1068	
0.2% Ceria-coated Silica + 0.1x Dulcitol	0	152	252	770	2995
	60	238	370	10	
	120	366	495	1081	

[00180] CMP composition having D- (-)-fructose suppressed removal of TEOS in addition of SiN, but still afforded high TEOS: SiN selectivity.

[00181] The effects of various selected chemical additives on the oxide trenching dishing vs over polishing times were observed.

5 **[00182]** The test results were listed in Table 6. HDP RR (Å/min.) from Table 5 was also listed in Table 6.

[00183] As the oxide trench dishing vs over polishing time results showed in Table 6, the CMP compositions with chemical additives afforded lower oxide trench dishing on 100um pitch, and 200um pitch, respectively. The compositions provided significant
10 oxide trench dishing reductions comparing to the reference composition.

[00184] Table 7 listed the ratio of oxide trench dishing rate (Å/min.) vs the blanket HDP film removal rate(Å/min.),

Table 7. The Ratio of Trench Dishing Rate (Å)/Blanket HDP RR (Å/min.)

Compositions	P100 Dishing Rate (Å/min.) /Blanket HDP RR (Å/min.)	P200 Dishing Rate (Å/min.) /Blanket HDP RR (Å/min.)
0.2X Ceria-coated Silica	0.13	0.16
+ 0.1x D-Sorbitol	0.06	0.07
+ 0.1x D- (-)-Fructose	0.08	0.09
+ 0.1x Maltitol	0.05	0.07
+ 0.1x Dulcitol	0.04	0.04

15 **[00185]** As the results shown in Table 7, the addition of the chemical additives to the polishing compositions significantly reduced the ratio of trench dishing rate vs the blanket HDP film removal rates than the ratio obtained from the reference sample at pH 5.35.

[00186] The slopes of the various sized pitch dishing vs oxide over polishing amounts
20 were listed in Table 8.

[00187] As the results of slopes of the various sized pitch dishing vs oxide over polishing amounts showed in Table 8, the chemical additives and ceria-coated silica abrasives based CMP polishing compositions afforded much lower slope values comparing to those slope values obtained from the reference.

25 **[00188]**

Table 8. Effects of Chemical Additives on Slopes of Dishing vs OP Removal Amount

Compositions	P100 dishing/OP Amt Slope	P200 dishing/OP Amt Slope	P1000 dishing/OP Amt Slope
0.2X Ceria-coated Silica	0.19	0.23	0.25
+ 0.1x D-Sorbitol	0.06	0.07	0.27
+ 0.1x D- (-)-Fructose	0.09	0.08	0.14
+ 0.1x Maltitol	0.04	0.05	0.08
+ 0.1x Dulcitol	0.04	0.04	0.05

Example 4

- 5 **[00189]** In Example 4, the removal rates, and TEOS: SiN selectivity were tested tests were performed with CMP polishing compositions with chemical additives having different concentrations at pH 5.35.

[00190] The test results were listed in Table 9.

- 10 Table 9. Effects of Additive Conc. on Film RR (A/min.) & Selectivity of Oxide: SiN

Samples	TEOS-RR (ang/min)	HDP-RR (ang/min)	SiN-RR (ang/min)	TEOS: SiN Sel.
0.2% Ceria-coated Silica + 0.05x D-Sorbitol	3595	3128	110	33
0.2% Ceria-coated Silica + 0.1x D-Sorbitol	3821	3425	112	34
0.2% Ceria-coated Silica + 0.15x D-Sorbitol	3651	3517	83	44

- [00191]** As the results showed in Table 9, when the concentration of D-sorbitol used in the compositions increased, similar TEOS removal rates were obtained, and HPD film removal rates were increased and TEOS: SiN selectivity were also increased slightly or significantly.
- 15

[00192] The effects on the oxide trenching dishing vs over polishing times from the selected chemical additive D-sorbitol concentrations on the various sized pitch features were tested.

[00193] The test results were listed in Table 10.

5

Table 10. Effects of Chemical Additive D-Sorbitol Conc. On Oxide Trench Dishing vs OP Times(sec.)

Compositions	Polish Time (Sec.)	100um pitch dishing	200um pitch dishing	Blanket HDP RR
0.2% Ceria-coated Silica + 0.05x D-Sorbitol	0	198	332	3128
	60	453	690	
	120	573	842	
0.2% Ceria-coated Silica + 0.1x D-Sorbitol	0	182	288	3425
	60	355	551	
	120	499	736	
0.2% Ceria-coated Silica + 0.15x D-Sorbitol	0	132	246	3517
	60	269	423	
	120	423	595	

[00194] As the results showed in Table 10, all 3 tested CMP polishing compositions contained D-sorbitol with different concentrations gave low oxide trench dishing on both 100μm pitch and 200μm pitch.

[00195] Also, as the chemical additive D-sorbitol concentrations increased, the oxide trench dishing are further reduced.

[00196] As the results showed in Table 10, all 3 tested CMP polishing compositions contained D-sorbitol with different concentrations gave low oxide trench dishing on both 100μm pitch and 200μm pitch.

[00197] Also, as the chemical additive D-sorbitol concentrations increased, the oxide trench dishing are further reduced.

Table 11 Ratio of Trench Dishing Rate (Å)/Blanket HDP RR (Å/min.)
vs Conc. of D-Sorbitol

Compositions	P100 Dishing Rate (Å/min.) /Blanket HDP RR (Å/min.)	P200 Dishing Rate (Å/min.) /Blanket HDP RR (Å/min.)
0.2% Ceria-coated Silica + 0.05X D-Sorbitol	0.04	0.05
0.2% Ceria-coated Silica + 0.1X D-Sorbitol	0.04	0.05
0.2% Ceria-coated Silica + 0.15X D-Sorbitol	0.04	0.05

[00198] Table 11 listed the ratio of Trench Dishing Rate (Å)/Blanket HDP RR (Å/min.) from the compositions with different concentrations of D-Sorbitol.

[00199] As the results shown in Table 11, D-sorbitol used in the composition at pH 5.35, all significantly reduced the ratio of trench dishing rate vs the blanket HDP film removal rates across the different tested concentrations.

[00200] Therefore, D-sorbitol can be used as an effective oxide trench dishing reducer in the wide concentration range

[00201] The slopes of the various sized pitch dishing vs oxide over polishing amounts were tested and the results were listed in Table 12.

Table 12. Effects of Additive Conc. on Slopes of Dishing vs OP Removal Amount

Compositions	P100 dishing/OP Amt Slope	P200 dishing/OP Amt Slope
STI2305 (Reference)	0.01	0.01
0.2% Ceria-coated Silica + 0.05x D-Sorbitol	0.06	0.08
0.2% Ceria-coated Silica + 0.1x D-Sorbitol	0.05	0.07
0.2% Ceria-coated Silica + 0.15x D-Sorbitol	0.04	0.05

5 **[00202]** As the results of slopes of the various sized pitch dishing vs oxide over polishing amounts showed in Table 12, different concentrations of D-sorbitol in CMP polishing compositions all afforded similar slope values comparing to the reference sample.

10 **[00203]** Also, as the D-sorbitol concentration increased, the slopes of the various sized pitch dishing vs oxide over polishing while at over polishing time at zero seconds gradually decreased.

Example 5

[00204] In Example 5, the tests were performed with CMP polishing compositions having different pH values.

[00205] The composition composed of 0.2 wt.% ceria-coated silica as abrasives and 0.1 wt.% D-sorbitol as chemical additive was tested at three different pH conditions.

[00206] The removal rates (RR at Å/min) for different films were tested. The test results were listed in Table 13.

Table 13. Effects of pH on Film RR (Å/min.) & Selectivity of Oxide: SiN

0.2% Ceria-coated Silica + 0.1% D- Sorbitol	TEOS-RR (ang/min)	HDP-RR (ang/min)	SiN-RR (ang/min)	TEOS: SiN Sel.
pH 5.35	3821	3425	112	34
pH 6	3759	3415	131	29
pH 8	2932	3084	94	31

[00207] As the results showed in Table 10, the compositions showed a consistent performance by offering high TEOS and HDP film removal rates, low SiN removal rates, and high TEOS: SiN selectivity in acidic, neutral or alkaline pH conditions..

[00208] The test results on the effects of pH conditions using the CMP polish compositions on oxide trench dishing vs over polishing times were listed in Table 14.

[00209] As the results showed in Table 14, similar oxide trenching dishing vs over polishing times and HDP film removal rates were obtained for the same concentration of ceria-coated silica as abrasives and D-sorbitol as oxide trenching dishing reducing agent at 3 different pH conditions.

Table 14. Effects of pH Conditions on Oxide Trench Dishing vs Over Polishing Times(sec.) & HDP Film RR (Å/min.)

Compositions & pH	Polish Time (Sec.)	100um pitch dishing	200um pitch dishing	Blanket HDP RR
0.2% Ceria-coated Silica + 0.1x D-Sorbitol (pH 5.35)	0	182	288	3425
	60	355	551	
	120	499	736	
0.2% Ceria-coated Silica + 0.1x D-Sorbitol (pH 6)	0	169	325	3415
	60	354	566	
	120	506	800	
0.2% Ceria-coated Silica + 0.1x D-Sorbitol (pH 8)	0	193	360	3084
	60	391	615	
	120	537	814	

[00210] Table 15 showed the results of the ratio of Trench Dishing Rate (Å)/Blanket HDP RR (Å/min.),

Table 15 Ratio of Trench Dishing Rate (Å)/Blanket HDP RR (Å/min.) at Different pH

Compositions	P100 Dishing Rate (Å/min.) /Blanket HDP RR (Å/min.)	P200 Dishing Rate (Å/min.) /Blanket HDP RR (Å/min.)
0.2% Ceria-coated Silica + 0.1X D-Sorbitol (pH 5.35)	0.04	0.05
0.2% Ceria-coated Silica + 0.1X D-Sorbitol (pH 6)	0.04	0.07
0.2% Ceria-coated Silica + 0.1X D-Sorbitol (pH 7)	0.05	0.06

5

[00211] As the results shown in Table 15, the addition of the chemical additives, D-sorbitol, used as oxide trench dishing reducer in polishing compositions at different pH conditions, showed significantly reduction of the ratio which indicated that D-sorbitol can be used as a very effective oxide trench dishing reducing agent at wide pH window.

10

Example 6

[00212] In Example 6, the effects of various selected chemical additives from afore listed several types of chemical additives on the film removal rates and selectivity were observed.

15

[00213] The same molar concentrations of all tested chemical additives at 8.132mM was used respectively.

[00214] All examples, except examples for the pH condition test had a pH at 5.35.

[00215] For the examples used in the pH condition test, pH adjusting agent was used for acidic pH condition and alkaline pH condition were nitric acid and ammonium hydroxide respectively.

[00216] The removal rates (RR at Å/min) and removal selectivity for different films were tested. The test results were listed in Table 16.

Table 16. Effects of 8.132mM Concentration of Chemical Additives on Film RR (Å/min.) & TEOS: SiN Selectivity

Compositions	TEOS RR (Å/min.)	HDP RR (Å/min.)	PECVD SiN RR (Å/min.)	TEOS: SiN Selectivity
0.2% Ceria-coated Silica	2754	1886	432	6.4
0.2% Ceria-coated Silica + 8.132mM Maltitol	2609	2493	45	58.4
0.2% Ceria-coated Silica + 8.132mM Ribose	2862	2512	114	25.1
0.2% Ceria-coated Silica + 8.132mM Arabinose	2963	1985	393	7.5
0.2% Ceria-coated Silica + 8.132mM Beta-lactose	2913	2186	115	25.3
0.2% Ceria-coated Silica + 8.132mM Myo-Inositol	2899	2028	201	14.4

[00217] As the results showed in Table 16, these chemical additives, when used at 8.132mM concentrations in the polishing compositions afforded similar TEOS film removal rates, HDP film removal rates, slightly or significantly suppressed SiN removal rates comparing with the reference.

[00218] The Oxide: SiN selectivity was fluctuating from slightly increased (arabinose, myo-inositol) to significantly increased (maltitol, ribose and beta-lactose). Among these tested chemical, maltitol showed as the most efficient SiN removal rate suppressing chemical additive, and ribose and beta-lactose also showed as quite efficient SiN removal rate suppressing additives.

Example 7

[00219] The following chemical additives, maltitol, D-sorbitol, lactitol, ribose, and beta-lactose were used in the polishing compositions with 0.2 wt.% ceria-coated silica

abrasives at pH 5.35 to have conducted polishing tests on polishing oxide patterned wafers. The chemical additives were used at 0.15 wt.% in the compositions.

[00220] The effects of various chemical additives on the film removal rates and selectivity were observed.

5 **[00221]** The test results were listed in Table 17.

Table 17. Effects of Chemical Additives on Film RR (A/min.) & TEOS: SiN Selectivity

Composition	TEOS RR (A/min)	HDP RR (A/min)	SiN RR (A/min)	TEOS: SiN Selectivity
0.2% Ceria-coated Silica pH 5.35	4310	3047	557	8
0.2% Ceria-coated Silica + 0.15% D-sorbitol	3605	3992	65	36
0.2% CPOP + 0.15% Maltitol	4505	4203	61	39
0.2% CPOP + 0.15% Lactitol	4563	4183	85	41
0.2% CPOP + 0.15% Ribose	4517	4325	103	39
0.2% CPOP + 0.15% Beta-Lactose	4716	4049	80	46

10 **[00222]** As the results showed in Table 17, all compositions afforded similar high TEOS film removal rates, increased HDP film high removal rates, significantly suppressed SiN removal rates, significantly increased Oxide: SiN selectivity comparing with the reference sample.

[00223] The effects of various chemical additives on the oxide trenching dishing vs
15 over polishing times were observed. These chemical additives were used at 0.15 wt.% (0.15X) concentrations respectively with 0.2 wt.% ceria-coated silica as abrasive, and with all formulations at pH 5.35.

[00224] The test results were listed in Table 18.

[00225] As the oxide trench dishing vs over polishing time results showed in Table 18,
20 all of these chemical additives, when used with ceria-coated silica abrasives in the CMP polishing compositions, afforded largely reduced oxide trench dishing vs over polishing times at 60seconds or 120seconds respectively on 100μm pitch and 200μm pitch features, and provided significant oxide trench dishing reductions comparing to the reference.

25

Table 18. Effects of Chemical Additives on Oxide Trench Dishing & HDP RR (Å/min.)

Compositions	OP Time (sec.)	100um pitch dishing	200um pitch dishing
0.2% Ceria-coated Silica pH 5.35	0	165	291
	60	857	1096
	120	1207	1531
0.2% Ceria-coated Silica + 0.15% Sorbitol	0	94	222
	60	216	351
	120	314	475
0.2% Ceria-coated Silica + 0.15% Maltitol	0	135	261
	60	293	463
	120	413	641
0.2% Ceria-coated Silica + 0.15% Lactitol	0	120	193
	60	313	436
	120	468	646
0.2% Ceria-coated Silica + 0.15% Ribose	0	88	176
	60	290	409
	120	441	606
0.2% Ceria-coated Silica + 0.15% Beta-Lactose	0	141	259
	60	387	587
	120	579	870

[00226] As the oxide trench dishing vs over polishing time results showed in Table 18, all of these chemical additives, when used with ceria-coated silica abrasives in the CMP polishing compositions, afforded largely reduced oxide trench dishing vs over polishing times at 60seconds or 120seconds respectively on 100µm pitch and 200µm pitch features, and provided significant oxide trench dishing reductions comparing to the reference.

[00227] Table 19 showed the results of the ratio of Trench Dishing Rate (Å)/Blanket HDP RR (Å/min.),

Table 19 Ratio of Trench Dishing Rate (Å)/Blanket HDP RR (Å/min.)

Compositions	P100 Dishing Rate (Å/min.) /Blanket HDP RR (Å/min.)	P200 Dishing Rate (Å/min.) /Blanket HDP RR (Å/min.)
0.2% Ceria-coated Silica pH 5.35	0.13	0.16
0.2% Ceria-coated Silica + 0.15% Sorbitol	0.02	0.03
0.2% Ceria-coated Silica + 0.15% Maltitol	0.05	0.04
0.2% Ceria-coated Silica + 0.15% Lactitol	0.04	0.05
0.2% Ceria-coated Silica + 0.15% Ribose	0.03	0.05
0.2% Ceria-coated Silica + 0.15% Beta-Lactose	0.05	0.07

[00228] As the results shown in Table 19, all tested polishing compositions using chemical additives showed significantly reduction of the ratio of trench dishing rate vs the blanket HDP film removal rates which indicated that all these chemical additives

can be used as very effective oxide trench dishing reducing agents in the invented CMP polishing compositions.

Working Example 8

5 [00229] The polishing compositions were prepared with the reference (0.2 wt.% ceria-coated silica, a biocide ranging from 0.0001 wt.% to 0.05 wt.%, and deionized water) and maltitol or lactitol were used at 0.28 wt.%.

[00230] All example compositions had a pH at 5.35.

10 [00231] The removal rates (RR at Å/min) for different films were tested. The effects of two selected chemical additives, maltitol and lactitol on the film removal rates and selectivity were observed.

[00232] The test results were listed in Table 20.

Table 20. Effects of Maltitol or Lactitol on Film RR (Å /min.) & TEOS: SiN Selectivity

Compositions	TEOS Film RR (Å/min.)	HDP Film RR (Å/min.)	SiN Film RR (Å/min.)	TEOS: SiN Selectivity
0.2% Ceria-coated Silica pH 5.35	3279	2718	349	9.4
0.2% Ceria-coated Silica + 0.28% Maltitol pH 5.35	2623	2639	46	57.0
0.2% Ceria-coated Silica + 0.28% Lactitol pH 5.35	2630	2547	55	47.8

15 [00233] As the results shown in Table 20, the addition of the chemical additives, maltitol or lactitol, in the polishing compositions, significantly suppressed SiN removal rates while still afforded high TEOS and HDP film removal rates, thus, significantly increased Oxide: SiN film polishing selectivity.

Example 9

20 [00234] The example compositions in Example 8 were used in this Example.

[00235] Oxide trenching dishing for without/or with different over polishing times were tested. The effects of maltitol or lactitol on the oxide trenching dishing vs over polishing times were observed.

[00236] The test results were listed in Table 21.

Table 21. Effects of Maltitol or Lactitol on Oxide Trench Dishing vs OP Times (Sec.)

Compositions	OP Times (Sec.)	100um pitch dishing	200um pitch dishing
0.2% Ceria-coated Silica pH 5.35 Ref.	0	165	291
	60	857	1096
	120	1207	1531
0.2% Ceria-coated Silica + 0.28% Maltitol pH 5.35	0	408	616
	60	480	713
	120	542	803
0.2% Ceria-coated Silica + 0.28% Lactitol pH 5.35	0	349	563
	60	438	702
	120	510	779

[00237] As the results shown in Table 21, the polishing compositions with the addition of the chemical additives, maltitol or lactitol, afforded low oxide trench dishing on 100μm pitch, and 200μm pitch respectively when 60second or 120second over polishing times were applied.

[00238] The compositions provided significant oxide trench dishing reductions comparing to the reference composition which did not have the chemical additives, maltitol or lactitol.

10 [00239] Table 22 showed the results of the ratio of Trench Dishing Rate (Å)/Blanket HDP RR (Å/min.),

Table 22. The Ratio of Trench Dishing Rate (A)/Blanket HDP RR (A/min.)

Compositions	P100 Dishing Rate (Å/min.) /Blanket HDP RR (A/min.)	P200 Dishing Rate (Å/min.) /Blanket HDP RR (A/min.)
0.2% Ceria-coated Silica pH 5.35	0.13	0.16
0.2% Ceria-coated Silica + 0.28% Maltitol pH 5.35	0.02	0.03
0.2% Ceria-coated Silica + 0.28% Lactitol pH 5.35	0.03	0.03

15 [00240] As the results shown in Table 22, the addition of either maltitol or lactitol as oxide trench dishing reducer in polishing compositions significantly reduced the ratio of trench dishing rate vs the blanket HDP film removal rates, the lower of this ratio is, the lower of oxide trench dishing is.

[00241] The slopes of oxide trench dishing vs the OP removal amount was showed in Table 23.

Table 23. Effects of Maltitol or Lactitol on Slopes of Dishing vs OP Removal Amount

Compositions	P100 dishing/OP Amt Slope	P200 dishing/OP Amt Slope	P1000 dishing/OP Amt Slope
0.2% Ceria-coated Silica pH 5.35 Ref.	0.19	0.23	0.25
0.2% Ceria-coated Silica + 0.28% Maltitol pH 5.35	0.04	0.05	0.08
0.2% Ceria-coated Silica + 0.28% Lactitol pH 5.35	0.04	0.06	0.09

- 5 **[00242]** The results listed in Table 23 indicated that the compositions with chemical additives, maltitol or lactitol provided lower slopes which indicated good over polishing window for maintaining low oxide trench dishing even more oxide film removed in over polishing steps.

- 10 **[00243]** As showing in Table 23, these chemical additives, maltitol or lactitol, and ceria-coated silica based CMP polishing compositions again showed much lower slope values comparing to those slope values obtained for the ceria-coated silica abrasive based reference sample.

Example 10

- 15 **[00244]** In Example 10, the trench oxide loss rates were compared for the polishing compositions using maltitol or lactitol and reference as listed in Table 24.

Table 24. Effects of Maltitol or Lactitol on Trench Loss Rates ($\text{\AA}/\text{min.}$)

Compositions	P100Trench Loss Rate ($\text{\AA}/\text{sec.}$)	P200Trench Loss Rate ($\text{\AA}/\text{sec.}$)
0.2% Ceria-coated Silica pH 5.35 Ref.	18.5	19.3
0.2% Ceria-coated Silica + 0.28% Maltitol pH 5.35	2.0	2.5
0.2% Ceria-coated Silica + 0.28% Lactitol pH 5.35	2.3	2.6

[00245] As the results shown in Table 24, the addition of maltitol or lactitol as oxide trench dishing reducing agent into the polishing compositions, the trench loss rates were significantly reduced vs the reference sample without using any chemical additives.

5

Example 11

[00246] The compositions were prepared as shown in Table 19.

[00247] The compositions used of 0.2 wt.% ceria-coated silica as abrasives, 0.28 wt.% lactitol as chemical additive, biocide, DI water, and a pH adjusting agent to provide different pH conditions.

10

[00248] The removal rates (RR at Å/min) for different films were tested. The effects of pH conditions on the film removal rates and selectivity were observed.

[00249] The test results were listed in Table 25.

15 Table 25. Effects of pH on Film RR (Å /min) & Selectivity of Oxide: SiN

Compositions	TEOS Film RR (Å/min.)	HDP Film RR (Å/min.)	SiN Film RR (Å/min.)	TEOS: SiN Selectivity
0.2% Ceria-coated Silica pH 5.35	3279	2718	349	9.4
0.2% Ceria-coated Silica + 0.28% Lactitol pH 5.35	2623	2639	46	57.0
0.2% Ceria-coated Silica + 0.28% Lactitol pH 7.0	2524	2517	56	45.1
0.2% Ceria-coated Silica + 0.28% Lactitol pH 8.0	2401	2417	52	46.2

[00250] As the results shown in Table 25, the addition of lactitol as oxide trench dishing reducing agent into the polishing compositions at three different pH conditions, (acidic, neutral or alkaline) gave similar TEOS and HDP film removal rates, very effectively suppressed SiN film removal rates, and yielded much higher TEOS: SiN selectivity than the reference sample without using lactitol as chemical additive.

20

[00251] Oxide trenching dishing for without/or with lactitol as chemical additive over polishing times were tested.

[00252] The effects of lactitol containing polishing composition at different pH conditions on the oxide trenching dishing vs over polishing times were observed.

[00253] The test results were listed in Table 26.

[00254] As the results shown in Table 26, the polishing compositions with the addition of lactitol, at different pH conditions afforded low oxide trench dishing on 100µm pitch, and 200µm pitch respectively when 60second or 120second over polishing times were applied.

[00255] The compositions with lactitol as oxide trench dishing reducing agent provided significant oxide trench dishing reductions comparing to the reference polishing composition which did not have the chemical additive, lactitol.

Table 26. Effects of Lactitol at Different pH Conditions on Oxide Trench Dishing vs OP Times (Sec.)

Compositions	OP Times (Sec.)	100um pitch dishing	200um pitch dishing
0.2% Ceria-coated Silica pH 5.35 Ref.	0	165	291
	60	857	1096
	120	1207	1531
0.2% Ceria-coated Silica + 0.28% Lactitol pH 5.35	0	349	563
	60	438	702
	120	510	779
0.2% Ceria-coated Silica + 0.28% Lactitol pH 7.0	0	73	182
	60	222	390
	120	346	532
0.2% Ceria-coated Silica + 0.28% Lactitol pH 8.0	0	269	386
	60	425	576
	120	568	766

[00256] Table 27 depicted the ratio of Trench Dishing Rate (A)/Blanket HDP RR (A/min.) at Different pH.

Table 27. Ratio of Trench Dishing Rate (A)/Blanket HDP RR (A/min.) at Different pH

Compositions	P100 Dishing Rate (Å/min.) /Blanket HDP RR (A/min.)	P200 Dishing Rate (Å/min.) /Blanket HDP RR (A/min.)
0.2% Ceria-coated Silica pH 5.35	0.13	0.16
0.2% Ceria-coated Silica + 0.28% Lactitol pH 5.35	0.03	0.03
0.2% Ceria-coated Silica + 0.28% Lactitol pH 7.0	0.05	0.06
0.2% Ceria-coated Silica + 0.28% Lactitol pH 8.0	0.06	0.08

[00257] As the results shown in Table 27, the addition of lactitol as oxide trench dishing reducer in polishing composition significantly reduced the ratio of trench dishing rate vs the blanket HDP film removal rates at different pH conditions than that ratio obtained for reference sample at pH 5.35.

[00258] The slopes of oxide trench dishing vs the OP removal amount at different pH conditions was showed in Table 28.

Table 28. Effects of Lactitol at Different pH on Slopes of Dishing vs OP Removal Amount

Compositions	P100 dishing/OP Amt Slope	P200 dishing/OP Amt Slope
0.2% Ceria-coated Silica pH 5.35	0.19	0.23
0.2% Ceria-coated Silica + 0.28% Lactitol pH 5.35	0.04	0.06
0.2% Ceria-coated Silica + 0.28% Lactitol pH 7.0	0.06	0.08
0.2% Ceria-coated Silica + 0.28% Lactitol pH 8.0	0.06	0.08

[00259] The results listed in Table 28 indicated that the compositions with chemical additive lactitol at different pH conditions provided lower slopes of trench dishing vs the over polishing removal amounts which indicated good over polishing window for maintaining low oxide trench dishing even more oxide film removed in over polishing steps.

[00260] As showing in Table 28, lactitol and ceria-coated silica based CMP polishing compositions again showed much lower slope values at different pH conditions comparing to those slope values obtained for the ceria-coated silica abrasive based reference sample at pH 5.35.

[00261] In Example 11, the trench oxide loss rates were compared for the polishing compositions using lactitol at different pH conditions or without using lactitol at pH 5.35 and listed in Table 29.

Table 29. Effects of Lactitol at Different pH Conditions on Trench Loss Rates (Å/min.)

Compositions	P100Trench Loss Rate (Å/sec.)	P200Trench Loss Rate (Å/sec.)
0.2% Ceria-coated Silica pH 5.35 Ref.	18.5	19.3
0.2% Ceria-coated Silica + 0.28% Lactitol pH 5.35	2.3	2.6
0.2% Ceria-coated Silica + 0.28% Lactitol pH 7.0	3.3	4.0
0.2% Ceria-coated Silica + 0.28% Lactitol pH 8.0	3.7	4.2

[00262] As the results shown in Table 29, the addition of lactitol as oxide trench dishing reducing agent into the polishing compositions at different pH conditions, the trench loss rates were significantly reduced vs the reference sample without using lactitol as chemical additive.

[00263] The polishing test results obtained at different pH conditions using lactitol as oxide trench dishing reducer proved that the CMP polishing compositions can be used in wide pH range including acidic, neutral or alkaline pH conditions.

Example 12

[00264] When using the suitable chemical additives, such as maltitol or lactitol or their derivatives, as oxide trench reducing agents in polishing compositions, these chemical additives can have some impacts on the stability of ceria-coated inorganic oxide abrasives in the CMP polishing compositions.

[00265] In CMP polishing compositions, it is very important to have good abrasive particle stability to assure constant and desirable CMP polishing performances.

[00266] Typically, the abrasive particle stability is tested through monitoring the MPS (nm) (=mean particle size) and D99(nm) changes vs the times or at elevated temperatures. The smaller of MPS (nm) and D99(nm) changes, the more stable of the invented polishing compositions are.

[00267] In this example, the stability of ceria-coated silica abrasive particles in the compositions having chemical additives was monitored by measuring the change of the mean particles size and the change of particle size distribution D99.

[00268] The testing samples were made using 0.2 wt.% or other wt.% ceria-coated silica abrasive; very low concentration of biocide; 0.15 wt.% maltitol, 0.15 wt.% lactitol or 0.0787 wt.% Myo-inositol as oxide trench dishing reducer; and with pH adjusted to 5.35.

[00269] The abrasive stability tests on the polishing compositions were carried out at 50 °C for at least 10 days or more.

[00270] The MPS (nm) or D99(nm) of the tested polishing compositions were measured using DLS technology (DLS = dynamic light scattering).

[00271] The stability test results of the used ceria-coated silica abrasives with the chemical additives were listed in Table 30.

Table 30. Particle Size Stability (MPS) Test Results@50 °C – D99(nm)

Compositions/Days	0	1	2	3	4	11	18	32
0.2% Ceria-coated Silica + 0.15% Maltitol	179.6	179.6	178.4	179.6	180		183	
0.2% Ceria-coated Silic + 0.15% Lactitol	180	178.8	180.9	179.6	180.6			182.3
0.2% Ceria-coated Silic + 0.0787% Myo-Inositol	180.8	178.5	179.6	180.4	181.5	182.3		

[00272] By day 4 at 50 °C, 0.2 wt. % ceria-coated silica particles had MPS changes of

0.23%, 0.34% and 0.39% in the compositions having 0.15 wt. % maltitol, 0.15 wt. % lactitol and 0.0787 wt.% myo-inositol respectively.

[00273] 0.2 wt. % ceria-coated silica particles in the composition having 0.15 wt. % maltitol had a mean particle size change of less than 1.9 % by day 18 at 50 °C.

[00274] 0.2 wt. % ceria-coated silica particles in the composition having 0.0787 wt.% myo-inositol had a mean particle size change of less than 0.83 % by day 11 at 50 °C.

[00275] 0.2 wt. % ceria-coated silica particles in the composition having 0.15 wt.% lactitol had a mean particle size change of less than 1.3 % by day 32 at 50 °C.

[00276] More stability test were listed in Table 31.

Table 31. Particle Size Stability Test Results@50 °C – MPS (nm) & D99(nm)

Compositions	Particle Sizes (nm)	Day 0	Day 1	Day 4	Day 8	Day 15	Day 22	Day 33	Day 40	Day 62
0.2% Ceria-coated Silica + 0.15% Maltitol pH 5.35	MPS(nm)	120	121.1	122.8	123	123.2	121.5	121.9	120.6	119.9
	D99(nm)	176.3	178	180.9	180.4	180	172.4	178.3	176.2	177.4

[00277] 0.2 wt. % ceria-coated silica particles in the composition having 0.15 wt.% maltitol had a mean particle size and D99 changes of less than 8.34×10^{-4} and 0.63 % respectively by day 62 at 50 °C.

- 5 **[00278]** Furthermore, the particle stability tests were also conducted at 50 °C on polishing compositions comprised more concentrated ceria-coated silica abrasives (more than 0.2 wt. %) and more concentrated maltitol (more than 0.15 wt. %) as oxide trench dishing reducer.

[00279] The test results were listed in Table 32.

10

Table 32. Particle Size Stability Test Results@50 °C – MPS (nm) & D99(nm)

Compositions	Particle Sizes (nm)	Day 0	Day 3	Day 5	Day 7	Day 14	Day 19	Day 25	Day 42
0.8% Ceria-coated Silica + 0.6% Maltitol pH 5.35	MPS(nm)	122	122	121.9	122	121	121	121.4	122.5
	D99(nm)	180.5	179.5	180	179.6	185.3	185.3	179.6	180.9
1.6% Ceria-coated Silica + 1.2% Maltitol pH 5.35	MPS(nm)	121.2	122.1	122.1	121.5	121.3	121.2	121.4	122.6
	D99(nm)	179.5	180	180	179.2	179.6	179.6	180.5	182.3
2.4% Ceria-coated Silica + 1.8% Maltitol pH 5.35	MPS(nm)	122.1	121.9	121.5	121.1	121	121	122	122.5
	D99(nm)	180.5	180	179.2	178	180.1	180.1	180.5	180.9

- 15 **[00280]** Data showed that 0.8 wt. % of the ceria-coated silica particles had MPS and D99 changes of less than 0.41 % and less than 0.23 % respectively by day 42 at 50 °C in the composition having 0.6 wt. % of maltitol respectively.

[00281] Data also showed that 0.8 wt. % of the ceria-coated silica particles had MPS and D99 changes of less than 0.41 % and less than 0.23 % respectively by day 42 at 50 °C in the composition having 0.6 wt. % of maltitol respectively.

- 20 **[00282]** 1.6 wt. % of the ceria-coated silica particles had MPS and D99 changes of less than 1.2% and less than 1.6 % respectively by day 42 at 50 °C in the composition having 1.2 wt. % of maltitol respectively..

- 25 **[00283]** 2.4 wt. % of the ceria-coated silica particles had MPS and D99 changes of less than 0.33 % and less than 0.23 % respectively by day 42 at 50 °C in the composition having 1.8 wt. % of maltitol respectively.

[00284] As the results shown in Table 30 to 32, when maltitol, lactitol or Myo-inositol used as oxide trench dishing reducer with ceria-coated silica particles as abrasives, the polishing compositions showed very good particle size stability of MPS(nm) and D99(nm) even at elevated testing temperatures.

- 5 **[00285]** The polishing compositions comprised of ceria-coated colloidal silica abrasives and more concentrated maltitol as oxide trench dishing reducer all showed very good particle size stability of MPS (nm) and D99(nm) at elevated temperatures.

Example 13

- 10 **[00286]** Another key benefit of using the present invented CMP polishing compositions is the reduced total defect counts through and post-polishing which is resulted in by using the ceria-coated colloidal silica composite particles as abrasives instead of using calcined ceria particle as abrasives.

[00287] The following three polishing compositions were prepared for defects testing.

- 15 The first sample was made using 0.5 wt.% calcined ceria abrasives, 0.05 wt.% polyacrylate salt and low concentration of biocide; the second sample was made using 0.2 wt.% ceria-coated silica abrasives, 0.28 wt.% maltitol and low concentration of biocide; the third sample was made using 0.2 wt.% ceria-coated silica abrasives, 0.28 wt.% lactitol and low concentration of biocide. In order to obtain similar dielectric film
20 removal rates to be compared, higher concentration of calcinated ceria abrasive was used in sample 1.

[00288] All three formulations have pH valued at 5.35.

- [00289]** The total defect counts on polished TEOS and SiN wafers were compared by using three afore listed polishing compositions. The total defect count results were
25 listed in Table 33.

Table 33. Effects of Different Polishing Compositions on TEOS & SiN Total Defect Counts

Compositions	TEOS Total Defect Count@0.13μm LPD	SiN Total Defect Count@0.13μm LPD
0.2% Calcined Ceria + 0.05% Polyacrylate Salt pH 5.35	3847	498
0.2% Ceria-coated Silica + 0.28% Maltitol pH 5.35	438	73
0.2% Ceria-coated Silica + 0.28% Lactitol pH 5.35	493	73

[00290] As the total defect count results shown in Table 33, the polishing compositions using ceria-coated silica particles as abrasives and either of maltitol or lactitol as trench dishing reducing agent afforded significantly lower total defect counts on the polished TEOS and SiN wafers than the total defect counts obtained using the polishing composition comprised of calcined ceria abrasives and polyacrylate salt as chemical additive.

Example 14

[00291] The following four polishing compositions were prepared for the defects testing.

[00292] The first two polishing compositions used calcined ceria abrasives, 0.28 wt.% maltitol or 0.28 wt.% lactitol as oxide trenching dishing reducing agent and low concentration of biocide; the other two polishing compositions were made using ceria-coated silica abrasives, 0.28 wt.% maltitol or 0.28 wt.% lactitol as oxide trenching dishing reducing agent and low concentration of biocide. All four formulations have pH valued at 5.35.

[00293] All chemical additives used at the same wt.%, but different types of abrasives were used, e.g., calcined ceria vs ceria-coated silica particles as abrasives.

[00294] The effects of different types of abrasives on the film removal rates and TEOS: SiN selectivity were observed and the results were listed in table 34.

Table 34. Effects of Different Types of Abrasives on Film RR & TEOS: SiN Selectivity

Compositions	TEOS RR (Å/min.)	HDP RR (Å/min.)	SiN RR (Å/min.)	TEOS: SiN Selectivity
Calcined Ceria + 0.28% Maltitol	1774	1839	38	43
Calcined Ceria + 0.28% Lactitol	1997	1996	37	54
Ceria-coated Silica + 0.28% Maltitol	3085	2956	60	51
Ceria-coated Silica + 0.28% Lactitol	3188	2885	69	46

[00295] As the results shown in Table 34, the polishing compositions that used ceria-coated silica as abrasives did afford much higher TEOS and HDP film removal rates than those film removal rates obtained from the polishing compositions which used calcined ceria as abrasives.

- 5 **[00296]** The normalized total defect counts on polished TEOS and SiN wafers were compared by using four afore listed polishing compositions. The normalized total defect count results were listed in Table 35.

Table 35. Effects of Different Types of Abrasives on Normalized TEOS & SiN Total Defect Counts

Compositions	TEOS 0.07um LPD	TEOS 0.13um LPD	PECVD SiN 0.1um LPD	PECVD SiN 0.13um LPD
Calcined Ceria + 0.28% Maltitol	1.00	1.00	1.00	1.00
Calcined Ceria + 0.28% Lactitol	1.03	0.64	0.96	1.04
Ceria-coated Silica + 0.28% Maltitol	0.21	0.07	0.25	0.58
Ceria-coated Silica + 0.28% Lactitol	0.43	0.10	0.49	0.58

10

[00297] As the normalized total defect count results shown in Table 35, the polishing compositions using ceria-coated silica particles as abrasives and either maltitol or lactitol as trench dishing reducing agent afforded significantly lower normalized total defect counts on the polished TEOS and SiN wafers than the normalized total defect counts obtained using the polishing composition comprised of calcined ceria abrasives, and either maltitol or lactitol as oxide trench dishing reducing chemical additive.

15

Example 15

[00298] In Example 15, both calcined ceria and ceria-coated silica particles based polishing compositions were tested.

20

[00299] The composition comprising calcined ceria particles but no chemical additives was used as a reference.

[00300] Calcined ceria or ceria-coated silica particles were used at 1.0 wt.%, D-sorbitol and D-Mannitol were used at 2.0 wt.% respectively.

25

[00301] All samples have alkaline pH at 9.5. IC1010 used as polishing pad, and 3.3 psi down force was applied.

[00302] The film removal rate results were listed in Table 36.

Table 36. Film Removal Rates (A/min.) vs Polishing Compositions

Compositions	TEOS RR (Å/min.)	HDP RR (Å/min.)	SiN RR (Å/min.)
1.0% Calcined Ceria pH 9.5 Ref.	3509	3290	227
1.0% Calcined Ceria + 2.0% D-sorbitol pH 9.5	118	121	28
1.0% Calcined Ceria + 2.0% D-mannitol pH 9.5	181	144	29
1.0% Ceria-coated Silica + 2.0% D-sorbitol pH 9.5	133	137	39

[00303] As the results shown in Table 36, when no chemical additive was used in polishing composition, the polishing composition with 1.0 wt.% calcined ceria abrasives afforded high TEOS and HDP film removal rates at pH 9.5.

[00304] With either D-sorbitol or D-mannitol used at 2.0 wt.% as chemical additive in the polishing compositions at pH 9.5, much lower TEOS and HDP film removal rates were obtained.

[00305] It appears that the polishing compositions with such low TEOS and HDP film removal rates cannot meet the oxide film removal rate requirements in CMP applications.

[00306] It is very important to identify the suitable concentration range and the suitable ratios of abrasive/chemical additive, and optimized pH conditions in the CMP polishing compositions which are able to provide high enough oxide film removal rates and high TEOS: SiN selectivity to satisfy the CMP application needs.

Example 16

[00307] In Example 16, the weight% ratios of ceria-coated silica vs the chemical additive D-sorbitol were tested on their effects on various film polishing removal rates and on oxide trench dishing vs over polishing times.

[00308] In the composition, the ceria-coated silica abrasives was used from 0.2 wt.% to 0.4 wt.%, and D-sorbitol was used from 0.0 wt.% to 0.30 wt.%; which gave the ratio of ceria-coated silica abrasive wt.% vs the chemical additive D-sorbitol wt.% from 0.0 to 4.0. pH was 5.35 for all testing compositions.

[00309] The test results were depicted in Figure 1 and 2 respectively.

[00310] Please note, three points at 0 for both figures were for the composition having abrasive particles only i.e., not for the ratio of ceria-coated silica vs D-sorbitol, since no D-sorbitol was used in the composition.

[00311] As the results shown in Figures 1 and 2, when the weight% ratios of ceria-coated silica vs D-sorbitol ranged from 0.0 to 4.0, high TEOS and HDP film removal rates were high.

[00312] But at ratio of 0.0, SiN removal rate was also high, therefore, the selectivity of TEOS: SiN is low.

[00313] When the ratio of ceria-coated silica vs D-sorbitol was ranged from 0.7 to 2.0, the high TEOS and HDP film removal rates, low SiN removal rates, and high TEOS: SiN selectivity were achieved.

[00314] When this ratio was > 2.0, the SiN removal rate was increased gradually and the selectivity of TEOS: SiN was decreased.

[00315] The oxide trench dishing vs over polishing times shown in Figure 2 also shown that between 0.7 to 2.0 weight% ratio range for ceria-coated silica vs D-sorbitol was more suitable range for achieving high oxide film removal rates, low SiN removal rates, high TEOS: SiN selectivity and low oxide trench dishing.

[00316] The test results shown that the selection of the suitable ratio range of ceria-coated silica abrasive wt.% vs the chemical additive D-sorbitol wt.% allows the high oxide film removal rates, low SiN film removal rates, high selectivity of Oxide: SiN films, and low oxide trench dishing.

Example 17

[00317] In this Example, calcined ceria as abrasives and polyacrylate salt (PAA Salt) and sorbitol with different concentrations were used as chemical additives to compare the polishing performances at pH 5.35. 3.0 psi down force was applied in these polishing tests. The composition without using chemical additive was used as a reference.

[00318] The testing results were listed in Table 37.

Table 37. Effects of Additive Conc. on Film RR (A/min.) & Selectivity of Oxide: SiN

Samples	TEOS -RR (ang/min)	HDP -RR (ang/min)	PECVD SiN (ang/min)	TEOS: SiN Selectivity
Calcined Ceira only	2210	2313	110	20
Ceria + 0.05X PAA Salt	1657	1627	97	17
Ceria + 0.05X D-Sorbitol	1956	1990	68	29
Ceria + 0.15X D-Sorbitol	1602	1579	49	33
Ceria + 0.3X D-Sorbitol	1294	1179	43	30

[00319] As the results showed in Table 37, the chemical additive, PAA salt in calcined ceria particle-based formulation suppressed TEOS and HDP film removal rates and reduced SiN film removal rate and TEOS: SiN selectivity.

- 5 [00320] The chemical additive, D-sorbitol, when used in three different concentrations in calcined ceria particles based CMP polishing compositions also suppressed TEOS and HDP film removal rates, but significantly reduced SiN removal rates and thus increased TEOS: SiN selectivity from 20:1 to around 30:1.

- 10 [00321] The effects of chemical additives, PAA Salt and 3 different concentrations of D-sorbitol plus same concentrations of calcined ceria abrasive based polishing compositions on the various sized oxide trench dishing vs over polishing times were observed. The results were listed in Table 38.

- 15 [00322] As the results showed in Table 38, the chemical additive, PAA salt in calcined ceria particle-based formulation reduced oxide trench dishing while comparing to the calcined ceria only based reference.

Table 38. Effects of Additives or Conc. on Oxide Trench Dishing (A)

Samples	Over Polish Time (Sec.)	100um pitch dishing (A)	200um pitch dishing (A)	1000um pitch dishing (A)
Calcined Ceria only	0	96	184	779
	60	949	1238	2043
Ceria + 0.05X PAA Salt	0	91	210	954
	60	117	228	990
Ceria + 0.05X D- Sorbitol	0	100	219	783
	60	226	366	1126
Ceria + 0.15X D- Sorbitol	0	101	213	700
	60	166	280	787
Ceria + 0.3X D- Sorbitol	0	93	206	811
	60	109	236	834

[00323] The chemical additive, D-sorbitol, when used in three different concentrations in calcined ceria particles based CMP polishing compositions also reduced oxide trench dishing across three different sized features.

[00324] When D-sorbitol used at 0.15X or 0.3X concentrations, much lower oxide trench dishing obtained than that from D-sorbitol used at 0.05X concentration vs 60 second over polishing time.

Example 18

[00325] In Example 18, the CMP polishing compositions were tested at different pH values.

[00326] The compositions composing of 0.5 wt.% calcined ceria as abrasives only or with 0.15 wt.% D-sorbitol as chemical additive.

[00327] Film removal rates were tested at two different pH conditions.

[00328] Tests on film removal rates, TEOS: SiN selectivity and oxide trench dishing were performed.

[00329] The results were listed in Table 39 and Table 40 respectively.

Table 39. Effects of pH on Film Removal Rates & TEOS: SiN Selectivity

Samples	TEOS -RR (ang/min)	HDP -RR (ang/min)	PECVD SiN (ang/min)	TEOS: SiN Selectivity
Calcined Ceira only, pH 5.35	2210	2313	110	20
Ceria + 0.15X D-Sorbitol pH 5.35	1602	1579	49	33
Ceria + 0.15X D-Sorbitol pH 9.39	1467	1697	40	37

[00330] As the results showed in Table 39, when the STI polishing composition having 0.5 wt.% calcined ceria particles as abrasives and 0.15 wt.% D-sorbitol as a chemical additive, slightly lower TEOS removal rate was obtained at acidic pH and slightly higher HDP film removal rate was obtained at alkaline pH, and SiN removal rate was reduced from 49 Å /min. at pH 5.35 to 40Å/min. at pH 9.39.

Table 40. Effects of pH Conditions on Oxide Trench Dishing (A)

Samples	OP Times(sec.)	100µm Pitch Dishing (Å)	200µm Pitch Dishing (Å)	1000µm Pitch Dishing (Å)
Calcined Ceria only pH 5.35	0	96	184	779
	60	949	1238	2043
Calcined Ceria + 0.5% D-sorbitol pH 5.35	0	101	213	700
	60	166	280	787
Calcined Ceria + 0.5% D-sorbitol pH 9.39	0	104	220	982
	60	176	321	1140

[00331] As the results showed in Table 40, when the polishing composition having 0.5 wt.% calcined ceria particles as abrasives and 0.15 wt.% D-sorbitol as a chemical additive, low oxide trench dishing obtained on 100µm and 200µm pitch respectively at both pH values. Even at pH 9.39, 0.5 wt.% calcined ceria particles as abrasives and 0.15 wt.% D-sorbitol used as a chemical additive still affords more stable oxide trench dishing vs over polishing time increases.

[00332] Thus, the CMP polishing compositions provide good dishing performance at a wide pH range for CMP applications.

10

Example 19

[00333] In Example 19, polishing testes were on various films using the CMP polishing compositions made with calcined ceria particles or ceria-coated silica particles as abrasives and maltitol or lactitol as chemical additives at pH 5.35.

[00334] The polishing pad used was Dow's IC1010 pad, the down force used for polishing tests was 3.0 psi.

[00335] The test results on various film removal rates and TEOS: SiN selectivity were listed in Table 41.

Table 41. Film RR (A/min.) & TEOS: SiN Selectivity Comparison

Compositions	TEOS RR (A/min.)	HDP RR (A/min.)	SiN RR (A/min.)	TEOS: SiN Selectivity
Calcined Ceria pH 5.35 Ref. 1	2210	2313	110	20
Calcined Ceria + 0.15% Maltitol	2257	2235	40	56
Ceria-coated Silica + 0.28% Maltitol	1774	1839	38	43
Ceria-coated Silica + 0.28% Lactitol	1997	1996	37	54
Ceria-coated Silica pH 5.35 Ref. 2	3279	2718	349	9
Ceria-coated Silica + 0.15% Maltitol	3157	2747	43	73
Ceria-coated Silica + 0.28% Maltitol	3085	2956	60	51
Ceria-coated Silica + 0.28% Lactitol	3188	2885	69	46

20

[00336] As the results shown in Table 41, the polishing compositions having chemical additive maltitol or lactitol with either calcined ceria particles or ceria-coated silica particles offered high TEOS and good HDP film removal rates, significantly suppressed SiN film removal rates, thus, increased TEOS: SiN selectivity significantly.

5 **[00337]** Oxide trench dishing vs over polishing times at pH 5.35 were tested.

Table 42. Effects of Chemical Additives on Trench Dishing vs OP Times (sec.)

Compositions	OP Times (sec.)	100µm Pitch Dishing (Å)	200µm Pitch Dishing (Å)
Calcined Ceria pH 5.35 Ref. 1	0	96	184
	60	949	1238
	120		
Calcined Ceria + 0.15% Maltitol	0	200	392
	60	268	463
	120	337	565
Ceria-coated Silica + 0.28% Maltitol	0	144	318
	60	168	373
	120	234	407
Ceria-coated Silica + 0.28% Lactitol	0	155	319
	60	198	352
	120	245	439
Ceria-coated Silica pH 5.35 Ref. 2	0	165	291
	60	857	1096
	120	1207	1531
Ceria-coated Silica + 0.15% Maltitol	0	198	347
	60	392	562
	120	503	707
Ceria-coated Silica + 0.28% Maltitol	0	174	343
	60	273	455
	120	371	566
Ceria-coated Silica + 0.28% Lactitol	0	189	361
	60	309	501
	120	406	651

10 **[00338]** The polishing pad used was Dow's IC1010 pad, the down force used for polishing tests was 3.0 psi.

[00339] The test results on oxide trench dishing vs over polishing times were listed in Table 42.

15 **[00340]** As the results shown in Table 42, whether using calcined ceria or ceria-coated silica particles as abrasives, the polishing compositions having maltitol or lactitol at lower or higher concentrations very effectively reduced the oxide trench dishing vs over polishing times across various sized oxide trench features, and also provide more uniform and stable over polishing windows.

Example 20

[00341] All tested CMP polishing compositions had pH values at 5.35. Dow's IK4140 pad was used to replace Dow's IC1010 for

[00342] When Dow's IK4140 pad was used, 4.3psi DF was applied for polishing with calcined ceria abrasive based polishing composition, and 2.5psi DF was applied with ceria-coated silica abrasive based polishing compositions. The same table/head speeds at 50/48 rpm were applied for all polishing compositions.

[00343] The test results on polishing various types of blanket wafers using Dow's IK4140H polishing pad were listed in Table 43.

Table 43. Various Polishing Compositions@Different Polishing DF
vs Film RR(A/min.) & Selectivity

Compositions	HDP Film RR (Å/min.)	SiN Film RR (Å/min.)	HDP: SiN Selectivity
0.5% Ceria + 0.0506% Polyacrylate salt pH 5.35 @4.3psi DF	1428	100	14.3
0.2% Ceria-coated Silica + 0.15% D-Sorbitol pH 5.35 @2.5psi DF	1455	61	23.9
0.2% Ceria-coated Silica + 0.15% Maltitol pH 5.35 @2.5psi DF	1490	72	20.1
0.2% Ceria-coated Silica + 0.28% Maltitol pH 5.35 @2.5psi DF	1502	53	28.3

[00344] As the results shown in Table 43, when different polishing down forces used for different polishing compositions to polish various blanket films, very similar HDP film removal rates were obtained.

[00345] The polishing compositions using ceria-coated silica abrasives gave similar HDP film removal rates even at much lower applied down force and with lower abrasive concentrations comparing with the HDP film removal rate obtained at 4.3psi DF using calcined ceria abrasive based polishing composition.

[00346] Also, in overall, ceria-coated silica abrasive containing polishing compositions gave lower SiN removal rates than the polishing composition using ceria particles as abrasives while comparing their SiN removal rates obtained at different polishing down forces.

[00347] The polishing test results on polishing patterned wafers at different down forces were listed in Table 44.

Table 44. Various Polishing Compositions@Different Polishing DF on Polishing Patterned Wafers

Compositions	P200 Trench Loss Rate (Å/sec.)	P200 SiN Loss Rate (Å/sec.)	P200 SiN /HDP Blanket Ratio
0.5% Ceria + 0.0506% Polyacrylate salt pH 5.35 @4.3psi DF	2.1	0.9	0.038
0.2% Ceria-coated Silica + 0.15% D-Sorbitol pH 5.35 @2.5psi DF	1.9	0.6	0.025
0.2% Ceria-coated Silica + 0.15% Maltitol pH 5.35 @2.5psi DF	2.4	0.7	0.028

- 5 **[00348]** As the patterned wafer polishing results shown in Table 44, when ceria-coated silica particles were used as abrasives and D-sorbitol or maltitol as chemical additive, the polishing compositions gave similar P200 oxide trench loss rates, lower P200 SiN loss rates and also lower SiN/HDP blanket ratio than the polishing composition using calcined ceria particles as abrasives and polyacrylate salt as chemical additive.
- 10

[00349] In another set of tests shown in Table 45, Dow's IK4250UH pad was also used with 3.0psi DF for both polishing compositions. For the polishing tests, the same table/head speeds at 87/93 rpm were applied.

- [00350]** The polishing test results on polishing various types of blanket wafers using Dow's IK4250UH polishing pad were listed in Table 45.
- 15

Table 45. Various Polishing Compositions vs Film RR(A/min.) & Selectivity

Compositions	HDP Film RR (Å/min.)	SiN Film RR (Å/min.)	HDP: SiN Selectivity
0.5% Ceria + 0.0506% Polyacrylate salt pH 5.35	2715	196	13.9
0.2% Ceria-coated Silica + 0.15% D-Sorbitol pH 5.35	5913	114	51.9

- 20 **[00351]** As the results shown in Table 45, at same pH conditions, when using 0.2 wt.% ceria-coated silica particles as abrasives, and 0.15 wt.% D-Sorbitol as additives,

the more suppressed SiN removal rate was obtained and 118% higher HDP film removal rate was achieved while comparing with the results using the polishing composition comprised of 0.5 wt.% calcined ceria particles as abrasives and 0.0506 wt.% polyacrylate salt as additive while using Dow's IK4250UH polishing pad.

- 5 **[00352]** At the same time, the HDP film: SiN selectivity was increased from 13.9:1 to 51.9:1.

[00353] The patterned wafers were also polished using Dow's IK4250UH pad. The polishing results and polishing compositions were listed in Table 46.

10 Table 46. Various Polishing Compositions on Polishing Patterned Wafers


Compositions	P200 Trench Loss Rate (Å/sec.)	P200 SiN Loss Rate (Å/sec.)	P200 SiN /HDP Blanket Ratio
0.5% Ceria + 0.0506% Polyacrylate salt pH 5.35	6.1	2.2	0.048
0.2% Ceria-coated Silica + 0.15% D-Sorbitol pH 5.35	4.3	1.3	0.013

- 15 **[00354]** As the results shown in Table 46, lower P200 oxide trench loss rates, lower P200 SiN loss rates and also lower SiN/HDP blanket ratio were obtained when ceria-coated silica particles were used as abrasives and D-sorbitol as chemical additive.

- 20 **[00355]** The embodiments of this invention listed above, including the working example, are exemplary of numerous embodiments that may be made of this invention. It is contemplated that numerous other configurations of the process may be used, and the materials used in the process may be elected from numerous materials other than those specifically disclosed.

Claims


1. A Chemical Mechanical Polishing(CMP) composition comprising:
abrasive particles selected from the group consisting of inorganic oxide particles,
5 metal-coated inorganic oxide particles, organic polymer particles, metal oxide-coated organic polymer particles, and combinations thereof;
chemical additive;
solvent selected from the group consisting of deionized (DI) water, distilled water, and alcoholic organic solvents; and
10 optionally
biocide; and
pH adjuster;
wherein
the composition has a pH of 2 to 12;
15 the inorganic oxide particles are selected from the group consisting of ceria, colloidal silica, high purity colloidal silica, colloidal ceria, alumina, titania, zirconia particles, and combinations thereof;
the metal-coated inorganic oxide particles are selected from the group consisting of ceria-coated inorganic oxide particles selected from the group consisting of ceria-coated colloidal silica, ceria-coated high purity colloidal silica, ceria-coated
20 alumina, ceria-coated titania, ceria-coated zirconia particles and combinations thereof;
the organic polymer particles are selected from the group consisting of polystyrene particles, polyurethane particles, polyacrylate particle, and combinations thereof;
25 the metal-coated organic polymer particles are selected from the group consisting of ceria-coated organic polymer particles, zirconia-coated organic polymer particles, silica-coated organic polymer particles, and combinations thereof; and
the chemical additive is selected from the group consisting of
(A)a molecular structure (a):



(a)

wherein R1, R2, R3, R4 and R5 (Rs in group of R1 to R5) are selected from the group consisting of

(1) (i) at least one R in the group of R1 to R5 is a polyol molecular unit having a structure shown in (b):



(b);

wherein m or n is independently selected from 1 to 5; and each of R6, R7, R8 and R9 is independently selected from the group consisting of hydrogen, alkyl, alkoxy, organic group with one or more hydroxyl groups, substituted organic sulfonic acid or salt, substituted organic carboxylic acid or salt, organic carboxylic ester, organic amine, and combinations thereof;

and

(ii) each of other Rs in the group of R1 to R5 is independently selected from the group consisting of hydrogen, alkyl, alkoxy, organic group with one or more hydroxyl groups, substituted organic sulfonic acid or salt, substituted organic carboxylic acid or salt, organic carboxylic ester, organic amine, and combinations thereof;

5

10



15

20




- 69 -

organic carboxylic acid or salt, organic carboxylic ester, organic amine, and combinations thereof;


and

(iii) each of other Rs in the group of R1 to R5 is independently selected from the group consisting of hydrogen, alkyl, alkoxy, organic group with one or more hydroxyl groups, substituted organic sulfonic acid or salt, substituted organic carboxylic acid or salt, organic carboxylic ester, organic amine, and combinations thereof;


(B) a molecular structure selected from the group consisting of at least one (d), at least one (e), at least one (f), at least one (g), at least one (h) and combinations thereof;




(d)




(e)



(f)



(g)



(h);

wherein n is selected from 3 to 12;

5 R1, R2, R3, R4, R5, R6, R7 R8, R9, R10, R11, R12, R13, and R14 can be the same or different atoms or functional groups; and each R is independently selected from the group consisting of hydrogen, oxygen, alkyl, alkoxy, organic group with one or more hydroxyl groups, substituted organic sulfonic acid, substituted organic sulfonic acid salt, substituted organic carboxylic acid, substituted organic carboxylic acid salt, organic carboxylic ester, organic amine groups, and combinations thereof; wherein, at least four of them are hydrogen atoms.

15 2. The Chemical Mechanical Polishing(CMP) composition of Claim 1, wherein the abrasive particles range from 0.05 wt.% to 10 wt.% and have mean particle size ranging from 5nm to 500nm;

the chemical additive ranges from 0.01 wt.% to 20.0% wt.% and has at least four hydroxyl functional groups in its molecular structure; and

the composition has a pH of 3 to 10.

20 3. The Chemical Mechanical Polishing(CMP) composition of Claim 2, wherein the abrasive particles have changes of mean particle size MPS(nm) and $D_{99}(\text{nm}) \leq 5.0\%$ over shelf time of ≥ 30 days at a temperature ranging from 20 to 60 °C; wherein $D_{99}(\text{nm})$ is a particle size that 99 wt.% of the particles fall on and under.

25 4. The Chemical Mechanical Polishing(CMP) composition of Claim 1, wherein


the abrasive particles have mean particle size ranging from 5nm to 500nm, and have a concentration from 0.05 wt.% to 10 wt.%;

the chemical additive (a) has at least six hydroxyl functional groups in its molecular structure and R1, R2, R3, R4 and R5 (Rs in group R1 to R5) selected from (1), and ranges from 0.05 wt.% to 5 wt.%;


the composition has a pH of 3 to 10; and

the abrasive particles have changes of mean particle size MPS(nm) and D99(nm) $\leq 3.0\%$ over shelf time of ≥ 30 days at a temperature ranging from 20 to 60 °C; wherein D99(nm) is a particle size that 99 wt.% of the particles fall on and under.

5. The Chemical Mechanical Polishing(CMP) composition of Claim 4, wherein the polyol molecular unit (b) has $n = 2$ and $m = 1$; and rest of Rs in the group of R1 to R9 are all hydrogen atoms, as shown below:



Maltitol; or



Lactitol;


the solvent is deionized (DI) water; and

the abrasive particles have changes of mean particle size MPS(nm) and D99(nm) $\leq$ 2.0%.

- 5 6. The Chemical Mechanical Polishing(CMP) composition of Claim 1, wherein
the abrasive particles have mean particle size ranging from 5nm to 500nm, and
have a concentration from 0.05 wt.% to 10 wt.%;
the chemical additive (a) has at least six hydroxyl functional groups in its molecular
structure and R1, R2, R3, R4 and R5 (Rs in group R1 to R5) selected from (2),
10 and range from 0.05 wt.% to 5 wt.%;
the composition has a pH of 3 to 10; and
the abrasive particles have changes of mean particle size MPS(nm) and D99(nm)
 $\leq$ 3.0% over shelf time of $\geq$ 30 days at a temperature ranging from 20 to 60 °C;
wherein D99(nm) is a particle size that 99 wt.% of the particles fall on and under.

15

7. The Chemical Mechanical Polishing(CMP) composition of Claim 6, wherein
the polyol molecular unit (b) which has $n = 2$ and $m = 1$; and rest of Rs in the group
of R1 to R14 are all hydrogen atoms, as shown below:



20

Maltotritol;

and the solvent is deionized (DI) water, and

the abrasive particles have changes of mean particle size MPS(nm) and D99(nm) $\leq$ 2.0%.

- 25 8. The Chemical Mechanical Polishing(CMP) composition of Claim 1, wherein

the abrasive particles having mean particle size ranging from 5nm to 500nm and range from 0.05 wt.% to 10 wt.%;

the chemical additive ranges from 0.01 wt.% to 20.0% wt.% and is selected from the group comprising maltitol, lactitol, maltotritol, ribitol, D-sorbitol, mannitol, dulcitol, iditol, D- (-)-Fructose, sorbitan, sucrose, Inositol, glucose, D-arabinose, L-arabinose, L-mannose, D-mannose, L-mannose, meso-erythritol, ribose, beta-lactose, and combinations thereof; and

the composition has a pH of 3 to 10.

9. The Chemical Mechanical Polishing(CMP) composition of Claim 1, wherein the abrasive particles are ceria-coated colloidal silica particles or ceria particles having mean particle size ranging from 5nm to 500nm and range from 0.05 wt.% to 10 wt.%;

the chemical additive ranges from 0.05 wt.% to 5 wt.%, and has at least five hydroxyl functional groups in its molecular structure; and is selected from the group comprising maltitol, lactitol, maltotritol, D-sorbitol, mannitol, dulcitol, iditol, D- (-)-Fructose, sucrose, Inositol, glucose, L-mannose, D-mannose, beta-lactose, and combinations thereof.

the composition has a pH of 3 to 10; and the ceria-coated colloidal silica particles or ceria particles have changes of mean particle size MPS(nm) and $D_{99}(nm) \leq 3.0\%$ over shelf time of ≥ 30 days at a temperature ranging from 20 to 60 °C; wherein $D_{99}(nm)$ is a particle size that 99 wt.% of the particles fall on and under.

10. The chemical mechanical polishing composition of Claim 1, wherein the composition comprises ceria-coated colloidal silica particles or ceria particles; the chemical additive selected from the group consisting of maltitol, lactitol, maltotritol, D-sorbitol, mannitol, dulcitol, D- (-)-Fructose, , beta-lactose, and combinations thereof; and water; and

the ceria-coated colloidal silica particles or ceria particles have changes of mean particle size MPS(nm) and $D_{99}(nm) \leq 2.0\%$ over shelf time of ≥ 30 days at a temperature ranging from 20 to 60 °C; wherein $D_{99}(nm)$ is a particle size that 99 wt.% of the particles fall on and under.

11. The chemical mechanical polishing composition of Claim 1, wherein the composition comprises one selected from the group consisting of from 0.0001 wt.% to 0.05 wt.% of the biocide having active ingredient selected from the group consisting of 5-chloro-2-methyl-4-isothiazolin-3-one, 2-methyl-4-isothiazolin-3-one, and combinations thereof; from 0 wt.% to 1 wt.% of the pH adjusting agent selected from the group consisting of nitric acid, hydrochloric acid, sulfuric acid, phosphoric acid, other inorganic or organic acids, and mixtures thereof for acidic pH conditions; or selected from the group consisting of sodium hydride, potassium hydroxide, ammonium hydroxide, tetraalkyl ammonium hydroxide, organic quaternary ammonium hydroxide compounds, organic amines, and combinations thereof for alkaline pH conditions; and combinations thereof.
12. A method of chemical mechanical polishing (CMP) a semiconductor substrate having at least one surface comprising silicon oxide film, comprising
- (a) providing the semiconductor substrate;
 - (b) providing a polishing pad;
 - (c) providing a chemical mechanical polishing (CMP) composition comprising
 - 0.05 wt.% to 10 wt.% abrasive particles selected from the group consisting of inorganic oxide particles, metal-coated inorganic oxide particles, organic polymer particles, metal oxide-coated organic polymer particles and combinations thereof;
 - 0.01 wt.% to 20.0% wt.% chemical additive;
 - solvent selected from the group consisting of deionized (DI) water, distilled water, and alcoholic organic solvents; and
 - optionally
 - biocide; and
 - pH adjuster;
- wherein
- the composition has a pH of 2 to 12;
 - the inorganic oxide particles are selected from the group consisting of ceria, colloidal silica, high purity colloidal silica, colloidal ceria, alumina, titania, zirconia particles, and combinations thereof;


the metal-coated inorganic oxide particles are selected from the group consisting of ceria-coated inorganic oxide particles selected from the group consisting of ceria-coated colloidal silica, ceria-coated high purity colloidal silica, ceria-coated alumina, ceria-coated titania, ceria-coated zirconia particles and combinations thereof;

the organic polymer particles are selected from the group consisting of polystyrene particles, polyurethane particles, polyacrylate particle, and combinations thereof;

the metal-coated organic polymer particles are selected from the group consisting of ceria-coated organic polymer particles, zirconia-coated organic polymer particles, silica-coated organic polymer particles, and combinations thereof; and

the chemical additive is selected from the group consisting of


(A)a molecular structure (a):



(a)

wherein R_1 , R_2 , R_3 , R_4 and R_5 (R_s in group of R_1 to R_5) are selected from the group consisting of

(1) (i) at least one R in the group of R_1 to R_5 is a polyol molecular unit having a structure shown in (b):



(b);


wherein m or n is independently selected from 1 to 5; and each of R6, R7, R8 and R9 is independently selected from the group consisting of hydrogen, alkyl, alkoxy, organic group with one or more hydroxyl groups, substituted organic sulfonic acid or salt, substituted organic carboxylic acid or salt, organic carboxylic ester, organic amine, and combinations thereof;

and

(ii) each of other Rs in the group of R1 to R5 is independently selected from the group consisting of hydrogen, alkyl, alkoxy, organic group with one or more hydroxyl groups, substituted organic sulfonic acid or salt, substituted organic carboxylic acid or salt, organic carboxylic ester, organic amine, and combinations thereof;

and

(2) (i) at least one R in the group of R1 to R5 is a polyol molecular unit having a structure shown in (b):




(b);

wherein m or n is independently selected from 1 to 5; and each of R6, R7, R8 and R9 is independently selected from the group consisting of hydrogen, alkyl, alkoxy, organic group with one or more hydroxyl groups, substituted organic sulfonic acid or salt, substituted organic

carboxylic acid or salt, organic carboxylic ester, organic amine, and combinations thereof;

(ii) at least one R in the group of R1 to R5 is a six-member ring polyol as shown in (c):




(c);

wherein one of OR in group of OR11, OR12, OR13 and OR14 will be replaced by O in structure (c); and R10 and each of other R in group of R11, R12, R13 and R14 is independently selected from the group consisting of hydrogen, alkyl, alkoxy, organic group with one or more hydroxyl groups, substituted organic sulfonic acid or salt, substituted organic carboxylic acid or salt, organic carboxylic ester, organic amine, and combinations thereof;


and

(iii) each of other Rs in the group of R1 to R5 is independently selected from the group consisting of hydrogen, alkyl, alkoxy, organic group with one or more hydroxyl groups, substituted organic sulfonic acid or salt, substituted organic carboxylic acid or salt, organic carboxylic ester, organic amine, and combinations thereof;


(B) a molecular structure selected from the group consisting of at least one (d), at least one (e), at least one (f), at least one (g), at least one (h) and combinations thereof;




(d)




(e)



(f)



(g)



(h)

wherein n is selected from 3 to 12;

R1, R2, R3, R4, R5, R6, R7, R8, R9, R10, R11, R12, R13, and R14 can be the same or different atoms or functional groups; and each R is

independently selected from the group consisting of hydrogen, oxygen, alkyl,


- alkoxy, organic group with one or more hydroxyl groups, substituted organic sulfonic acid, substituted organic sulfonic acid salt, substituted organic carboxylic acid, substituted organic carboxylic acid salt, organic carboxylic ester, organic amine groups, and combinations thereof; wherein, at least
5 four of them are hydrogen atoms;
- (d)contacting the surface of the semiconductor substrate with the polishing pad and the chemical mechanical polishing composition; and
- (e)polishing the least one surface comprising silicon dioxide film;
- wherein the silicon oxide film is selected from the group consisting of Chemical
10 vapor deposition (CVD), Plasma Enhance CVD (PECVD), High Density Deposition CVD(HDP), spin on silicon oxide film, flowable CVD oxide film, carbon doped oxide film, nitrogen doped oxide film, and combinations thereof.
13. The method of claim 12; wherein the chemical mechanical polishing (CMP)
15 composition comprises
- the abrasive particles having mean particle size ranging from 5nm to 500nm;
- wherein the abrasive particles have changes of mean particle size
MPS(nm) and $D_{99}(nm) \leq 5.0\%$ over shelf time of ≥ 30 days at a
temperature ranging from 20 to 60 °C; wherein $D_{99}(nm)$ is a particle size
20 that 99 wt.% of the particles fall on and under;
- the chemical additive having at least four hydroxyl functional groups in its molecular structure; and
- the chemical mechanical polishing (CMP) composition has a pH of 3 to 10.
- 25 14. The method of claim 12; wherein the chemical mechanical polishing (CMP) composition comprises
- the abrasive particles have mean particle size ranging from 5nm to 500nm;
- wherein the abrasive particles have changes of mean particle size
MPS(nm) and $D_{99}(nm) \leq 5.0\%$ over shelf time of ≥ 30 days at a
30 temperature ranging from 20 to 60 °C; wherein $D_{99}(nm)$ is a particle size that 99 wt.% of the particles fall on and under;

the chemical additive (a) has at least six hydroxyl functional groups in its molecular structure and R1, R2, R3, R4 and R5 (Rs in group R1 to R5) selected from (1), and ranges from 0.05 wt.% to 5 wt.%; and the composition has a pH of 3 to 10.


5

15. The method of claim 14, wherein

the polyol molecular unit (b) in the chemical additive has $n = 2$ and $m = 1$; and rest of Rs in the group of R1 to R9 are all hydrogen atoms, as shown below:



Maltitol; or



Lactitol;

the solvent is deionized (DI) water; and

the abrasive particles have changes of mean particle size MPS(nm) and D99(nm) $\leq 2.0\%$; and

15

ratio of oxide trench dishing rate ($\text{\AA}/\text{min.}$) vs the blanket HDP film removal rate($\text{\AA}/\text{min.}$) is ≤ 0.1 .

16. The method of claim 12; wherein the chemical mechanical polishing (CMP)

5 composition comprises

the abrasive particles having mean particle size ranging from 5nm to 500nm;


the chemical additive has at least six hydroxyl functional groups in its molecular structure and R1, R2, R3, R4 and R5 (Rs in group R1 to R5) selected from (2);

10 the abrasive particles have changes of mean particle size MPS(nm) and D99(nm) $\leq 3.0\%$ over shelf time of ≥ 30 days at a temperature ranging from 20 to 60 $^{\circ}\text{C}$; wherein D99(nm) is a particle size that 99 wt.% of the particles fall on and under; and

the composition has a pH of 3 to 10.

15 17. The method of claim 16, wherein

the polyol molecular unit (b) in the chemical additive has $n = 2$ and $m = 1$; and rest of Rs in the group of R1 to R14 are all hydrogen atoms, as shown below:



Maltotritol;

20 and the solvent is deionized (DI) water, and

the abrasive particles have changes of mean particle size MPS(nm) and D99(nm) $\leq 2.0\%$; and

ratio of oxide trench dishing rate ($\text{\AA}/\text{min.}$) vs the blanket HDP film removal rate($\text{\AA}/\text{min.}$) is ≤ 0.1 .

25

18. The method of claim 12, wherein the chemical mechanical polishing (CMP) composition comprises

The abrasive particles having mean particle size ranging from 5nm to 500nm;
wherein the abrasive particles have changes of mean particle size MPS(nm)
and $D_{99}(nm) \leq 3.0\%$ over shelf time of ≥ 30 days at a temperature ranging
from 20 to 60 °C; wherein $D_{99}(nm)$ is a particle size that 99 wt.% of the
particles fall on and under;

the chemical additive is selected from the group comprising maltitol, lactitol,
maltotritol, ribitol, D-sorbitol, mannitol, dulcitol, iditol, D- (-)-Fructose, sorbitan,
sucrose, Inositol, glucose, D-arabinose, L-arabinose, D-mannose, L-mannose,
meso-erythritol, ribose, beta-lactose, and combinations thereof; and
the composition has a pH of 3 to 1.

19. The method of claim 12; wherein the chemical mechanical polishing (CMP) composition comprises

ceria-coated colloidal silica particles or ceria particles having mean particle size
ranging from 5nm to 500nm;

wherein the ceria-coated colloidal silica particles or ceria particles have
changes of mean particle size MPS(nm) and $D_{99}(nm) \leq 3.0\%$ over shelf time
of ≥ 30 days at a temperature ranging from 20 to 60 °C; wherein $D_{99}(nm)$ is a
particle size that 99 wt.% of the particles fall on and under;

the chemical additive has at least five hydroxyl functional groups in its molecular
structure; and is selected from the group comprising maltitol, lactitol, maltotritol, D-
sorbitol, mannitol, dulcitol, iditol, D- (-)-Fructose, sucrose, ribose, Inositol, glucose.

D-(+)-mannose, beta-lactose, and combinations thereof;
water;

the composition has a pH of 3 to 10.

20. The method of claim 12; wherein the chemical mechanical polishing (CMP) composition comprises

ceria-coated colloidal silica particles or ceria particles having mean particle size
ranging from 5nm to 500nm;

wherein the ceria-coated colloidal silica particles or ceria particles have changes
of mean particle size MPS(nm) and $D_{99}(nm) \leq 2.0\%$ over shelf time of ≥ 30

days at a temperature ranging from 20 to 60 °C; wherein D99(nm) is a particle size that 99 wt.% of the particles fall on and under;
the chemical additive selected from the group consisting of maltitol, lactitol, maltotritol, D-sorbitol, mannitol, dulcitol, D- (-)-Fructose, , beta-lactose, and combinations thereof; and water; and
5 the composition has a pH of 3 to 10.


21. The method of claim 12, wherein the chemical mechanical polishing (CMP) composition comprises one selected from the group consisting of from 0.0001 wt.%
10 to 0.05 wt.% of the biocide having active ingredient selected from the group consisting of 5-chloro-2-methyl-4-isothiazolin-3-one, 2-methyl- -isothiazolin-3-one, and combinations thereof; from 0 wt.% to 1 wt.% of the pH adjusting agent selected from the group consisting of nitric acid, hydrochloric acid, sulfuric acid, phosphoric acid, other inorganic or organic acids, and mixtures thereof for acidic
15 pH conditions; or selected from the group consisting of sodium hydride, potassium hydroxide, ammonium hydroxide, tetraalkyl ammonium hydroxide, organic quaternary ammonium hydroxide compounds, organic amines, and combinations thereof for alkaline pH conditions; and combinations thereof.

20 22. The method of claim 12; wherein the semiconductor substrate further comprises a silicon nitride surface; and removal selectivity of silicon oxide: silicon nitride is ≥ 20 .

23. A system of chemical mechanical polishing (CMP) a semiconductor substrate having at least one surface comprising silicon oxide film, comprising
25 a. the semiconductor substrate;
b. a polishing pad; and
c. a chemical mechanical polishing (CMP) composition comprising
0.05 wt.% to 10 wt.% abrasive particles selected from the group consisting of inorganic oxide particles, metal-coated inorganic oxide particles, organic
30 polymer particles, metal oxide-coated organic polymer particles and combinations thereof;
0.01 wt.% to 20.0% wt.% chemical additive;
solvent selected from the group consisting of deionized (DI) water, distilled water, and alcoholic organic solvents; and

optionally
biocide; and
pH adjuster;
wherein


- 5 the composition has a pH of 2 to 12;
the inorganic oxide particles are selected from the group consisting of ceria,
colloidal silica, high purity colloidal silica, colloidal ceria, alumina, titania, zirconia
particles, and combinations thereof;
the metal-coated inorganic oxide particles are selected from the group
10 consisting of ceria-coated inorganic oxide particles selected from the group
consisting of ceria-coated colloidal silica, ceria-coated high purity colloidal silica,
ceria-coated alumina, ceria-coated titania, ceria-coated zirconia particles and
combinations thereof;
the organic polymer particles are selected from the group consisting of
15 polystyrene particles, polyurethane particles, polyacrylate particle, and
combinations thereof;
the metal-coated organic polymer particles are selected from the group
consisting of ceria-coated organic polymer particles, zirconia-coated organic
polymer particles, silica-coated organic polymer particles, and combinations
20 thereof; and
the chemical additive has at least four hydroxyl functional groups and is selected
from the group consisting of
(A) a molecular structure (a):



(a)

wherein R1, R2, R3, R4 and R5 (Rs in group of R1 to R5) are selected from the group consisting of

(1) (i) at least one R in the group of R1 to R5 is a polyol molecular unit having a structure shown in (b):



(b);


wherein m or n is independently selected from 1 to 5; and each of R6, R7, R8 and R9 is independently selected from the group consisting of hydrogen, alkyl, alkoxy, organic group with one or more hydroxyl groups, substituted organic sulfonic acid or salt, substituted organic carboxylic acid or salt, organic carboxylic ester, organic amine, and combinations thereof;

and

(ii) each of other Rs in the group of R1 to R5 is independently selected from the group consisting of hydrogen, alkyl, alkoxy, organic group with one or more hydroxyl groups, substituted organic sulfonic acid or salt, substituted organic carboxylic acid or salt, organic carboxylic ester, organic amine, and combinations thereof;

and


(2) (i) at least one R in the group of R1 to R5 is a polyol molecular unit having a structure shown in (b):



(b);

wherein m or n is independently selected from 1 to 5; and each of R6, R7, R8 and R9 is independently selected from the group consisting of hydrogen, alkyl, alkoxy, organic group with one or more hydroxyl groups, substituted organic sulfonic acid or salt, substituted organic carboxylic acid or salt, organic carboxylic ester, organic amine, and combinations thereof;

(ii) at least one R in the group of R1 to R5 is a six-member ring polyol as shown in (c):




(c);

wherein one of OR in group of OR11, OR12, OR13 and OR14 will be replaced by O in structure (c); and R10 and each of other R in group of R11, R12, R13 and R14 is independently selected from the group consisting of hydrogen, alkyl, alkoxy, organic group with one or more hydroxyl groups, substituted organic sulfonic acid or salt, substituted organic carboxylic acid or salt, organic carboxylic ester, organic amine, and combinations thereof;


and

(iii) each of other Rs in the group of R1 to R5 is independently selected from the group consisting of hydrogen, alkyl, alkoxy, organic group with one or more hydroxyl groups, substituted organic sulfonic acid or salt, substituted organic carboxylic acid or salt, organic carboxylic ester, organic amine, and combinations thereof;


(B) a molecular structure selected from the group consisting of at least one (d), at least one (e), at least one (f), at least one (g), at least one (h) and combinations thereof;




(d)




(e)



(f)



(g)



(h)

wherein n is selected from 3 to 12;
R1, R2, R3, R4, R5, R6, R7 R8, R9, R10, R11, R12, R13, and R14 can be
the same or different atoms or functional groups; and each R is
independently selected from the group consisting of hydrogen, oxygen, alkyl,
5 alkoxy, organic group with one or more hydroxyl groups, substituted organic
sulfonic acid, substituted organic sulfonic acid salt, substituted organic
carboxylic acid, substituted organic carboxylic acid salt, organic carboxylic
ester, organic amine groups, and combinations thereof; wherein, at least four
of them are hydrogen atoms;
10 wherein
the silicon oxide film is selected from the group consisting of Chemical vapor
deposition (CVD), Plasma Enhance CVD (PECVD), High Density Deposition
CVD(HDP), spin on silicon oxide film, flowable CVD oxide film, carbon doped oxide
film, nitrogen doped oxide film, and combinations thereof; and
15 the at least one surface comprising silicon oxide film is in contact with the polishing
pad and the chemical mechanical polishing composition.


24. The system of claim 23; wherein the chemical mechanical polishing (CMP)
composition comprises
20 the abrasive particles having mean particle size ranging from 5nm to 500nm;
wherein the abrasive particles have changes of mean particle size
MPS(nm) and $D_{99}(nm) \leq 5.0\%$ over shelf time of ≥ 30 days at a
temperature ranging from 20 to 60 °C; wherein D99(nm) is a particle size
that 99 wt.% of the particles fall on and under;
25 the chemical additive having at least four hydroxyl functional groups in its
molecular structure;
the chemical mechanical polishing (CMP) composition has a pH of 3 to 10.

25. The system of claim 23; wherein the chemical mechanical polishing (CMP)
composition comprises
30 the abrasive particles having mean particle size ranging from 5nm to 500nm;


wherein the abrasive particles have changes of mean particle size MPS(nm) and $D_{99}(nm) \leq 5.0\%$ over shelf time of ≥ 30 days at a temperature ranging from 20 to 60 °C; wherein $D_{99}(nm)$ is a particle size that 99 wt.% of the particles fall on and under;

- 5 the chemical additive (a) has at least six hydroxyl functional groups in its molecular structure and R1, R2, R3, R4 and R5 (Rs in group R1 to R5) selected from (1), and ranges from 0.05 wt.% to 5 wt.%; and the composition has a pH of 3 to 10.

- 10 26. The system of claim 25, wherein the polyol molecular unit (b) in the chemical additive has $n = 2$ and $m = 1$; and rest of Rs in the group of R1 to R9 are all hydrogen atoms, as shown below:



Maltitol; or



Lactitol;

the solvent is deionized (DI) water; and

the abrasive particles have changes of mean particle size MPS(nm) and D99(nm) $\leq$ 2.0%.

27. The system of claim 23; wherein the chemical mechanical polishing (CMP)

5 composition comprises

the abrasive particles have mean particle size ranging from 5nm to 500nm;

wherein the abrasive particles have changes of mean particle size

MPS(nm) and D99(nm) $\leq$ 5.0% over shelf time of $\geq$ 30 days at a

temperature ranging from 20 to 60 °C; wherein D99(nm) is a particle size

10 that 99 wt.% of the particles fall on and under;

the chemical additive (a) has at least six hydroxyl functional groups in its molecular structure and R1, R2, R3, R4 and R5 (Rs in group R1 to R5) selected from (2),


and ranges from 0.05 wt.% to 5 wt.%;and

the composition has a pH of 3 to 10

15

28. The system of claim 27; wherein

the polyol molecular unit (b) in the chemical additive has n = 2 and m =1; and rest of Rs in the group of R1 to R14 are all hydrogen atoms, as shown below:



20

Maltotritol;

and the solvent is deionized (DI) water,

the abrasive particles have changes of mean particle size MPS(nm) and D99(nm) $\leq$ 2.0%;

and

ratio of oxide trench dishing rate ($\text{\AA}/\text{min.}$) vs the blanket HDP film removal rate($\text{\AA}/\text{min.}$) is ≤ 0.1 .

29. The system of claim 23; wherein the chemical mechanical polishing (CMP)

5 composition comprises

The abrasive particles having mean particle size ranging from 5nm to 500nm;
wherein the abrasive particles have changes of mean particle size MPS(nm)
and $D99(\text{nm}) \leq 3.0\%$ over shelf time of ≥ 30 days at a temperature ranging
from 20 to 60 $^{\circ}\text{C}$; wherein D99(nm) is a particle size that 99 wt.% of the
10 particles fall on and under;

the chemical additive is selected from the group comprising maltitol, lactitol,
maltotritol, ribitol, D-sorbitol, mannitol, dulcitol, iditol, D-(-)-Fructose, sorbitan,
sucrose, Inositol, glucose, D-arabinose, L-arabinose, D-mannose, L-mannose,
meso-erythritol, ribose, beta-lactose, and combinations thereof; and

15 the composition has a pH of 3 to 10.

30. The system of claim 23; wherein the chemical mechanical polishing (CMP)

composition comprises

20 ceria-coated colloidal silica or ceria particles having mean particle size ranging
from 5nm to 500nm;

wherein the ceria-coated colloidal silica or ceria particles have changes of
mean particle size MPS(nm) and $D99(\text{nm}) \leq 3.0\%$ over shelf time of ≥ 30 days
at a temperature ranging from 20 to 60 $^{\circ}\text{C}$; wherein D99(nm) is a particle size
that 99 wt.% of the particles fall on and under;

25 the chemical additive has at least five hydroxyl functional groups in its molecular
structure; and is selected from the group comprising maltitol, lactitol, maltotritol, D-
sorbitol, mannitol, dulcitol, iditol, D-(-)-Fructose, sucrose, ribose, Inositol, glucose.

D-(+)-mannose, beta-lactose, and combinations thereof;

water;

30 the composition has a pH of 3 to 10.

31. The system of claim 23; wherein the chemical mechanical polishing (CMP)

composition comprises

ceria-coated colloidal silica or ceria particles having mean particle size ranging from 5nm to 500nm;

5 wherein the ceria-coated colloidal silica or ceria particles have changes of mean particle size MPS(nm) and D99(nm) $\leq$ 2.0% over shelf time of $\geq$ 30 days at a temperature ranging from 20 to 60 °C; wherein D99(nm) is a particle size that 99 wt.% of the particles fall on and under;

the chemical additive selected from the group consisting of maltitol, lactitol, maltotritol, D-sorbitol, mannitol, dulcitol, D-(-)-Fructose, beta-lactose, and combinations thereof; and water;

10 the composition has a pH of 3 to 10.

32. The system of claim 23; wherein the chemical mechanical polishing (CMP) composition comprises one selected from the group consisting of from 0.0001 wt.% to 0.05 wt.% of the biocide having active ingredient selected from the group
15 consisting of 5-chloro-2-methyl-4-isothiazolin-3-one, 2-methyl- -isothiazolin-3-one, and combinations thereof; from 0 wt.% to 1 wt.% of the pH adjusting agent selected from the group consisting of nitric acid, hydrochloric acid, sulfuric acid, phosphoric acid, other inorganic or organic acids, and mixtures thereof for acidic pH conditions; or selected from the group consisting of sodium hydride, potassium
20 hydroxide, ammonium hydroxide, tetraalkyl ammonium hydroxide, organic quaternary ammonium hydroxide compounds, organic amines, and combinations thereof for alkaline pH conditions; and combinations thereof.