

The present invention relates to heavy tungsten-nickel-iron alloys with very high mechanical characteristics and a process for the productions of said alloys.

5 The man skilled in the art knows that materials which are intended for the production of balancing weights, screens for the absorption of vibration and λ , α , β , γ rays and projectiles having a high perforation capacity, must be of a relatively substantial specific mass.

10 It is for that reason that, for the production thereof, recourse is had to alloys which are referred to as "heavy alloys", primarily containing tungsten which is homogenously distributed in a metal matrix generally formed by bonding elements such as nickel and iron. In most cases those alloys have an amount of tungsten by weight which is between 90 and 98% and a specific gravity of from 15.6 to 18. They are
15 essentially produced by powder metallurgy, that is to say the components thereof are used in the powder state, compressed to impart the appropriate shape thereto, sintered and stabilized to give them mechanical solidity and possibly subjected to an operation for working and heat treatment thereof in order for them to acquire mechanical
20 characteristics: strength, elongation and hardness, which are suited to the use to which they are to be put.

The teaching of such alloys is set forth for example in US Patent No. 3 979 234 which describes a process for the production of W-Ni-Fe alloy comprising:

25 preparing a homogenous mixture of powders containing by weight 85 - 96% W, the balance being nickel and iron in a Ni/Fe ratio by weight of from 5.5 to 8.2,

compressing the mixture in the form of compacted items,

30 sintering the compacted items in a reducing atmosphere at a temperature of at least 1200°C and below the temperature at which a liquid phase appears for a sufficient period to produce a product with a density of at least 95% of the theoretical density,

heating the product at a temperature which is between 0.1 and 20°C above the temperature at which a liquid phase appears for a period
35 of time sufficient to cause a liquid phase to appear but insufficient to produce deformation of the product,

heating the product under vacuum at between 700 and 1420°C for a

sufficient time to degas it, and

machining it to the desired dimensions, which operation can be preceded by at least one working pass to increase the strength thereof.

Under those conditions, what is obtained is for example a product
5 which, after a working operation which results in a reduction in surface area of 31%, has a breaking strength RM of 1220 MPa, an elastic limit R 0.2 of 1180 MPa, a degree of elongation E of 7.8% and Rockwell C hardness: HRC, of 41.

Those characteristics are sufficient for certain uses but for
10 uses which involve higher levels of loading, they are found to be markedly inadequate as the need is now for levels of breaking strength which are higher than 1600 MPa and which can go up to 2000 MPa.

The present invention provides heavy alloys with very high mechanical characteristics, of a specific gravity of between 15.6 and
15 18, containing between 80 and 99% by weight of tungsten in the form of nodules constituting the α phase as well as nickel and iron in an Ni/Fe ratio by weight which is higher than or equal to 2, performing the bonding function and constituting the γ phase and optionally elements such as molybdenum, titanium, aluminium, manganese, cobalt and rhenium,
20 characterised in that in a direction transverse to the working direction, the α phase is in the form of ellipsoids joined two by two in the neighbourhood of one extremity of their major axes so as to form an acute angle between the said axes, with dislocation cells of dimensions from 0.01 to 1 μm , and the bonding γ phase has a mean free
25 path, defined as the average of the distances which in a given direction separates two successive zones of γ phase, of less than 15 μm .

It is known to the man skilled in the art that tungsten-nickel-iron alloys have a structure formed by nodules of pure tungsten which
30 are more or less spheroidised in the sintering operation, constituting the α phase, said nodules being surrounded by a γ phase composed of the three elements of the alloy which performs the function of bonding between said nodules. However, the applicants have found that, to develop very high mechanical characteristics, the tungsten alloys had
35 to be of a particular structure.

Moreover, from the morphological point of view, if a surface which is transverse to the direction of working is examined on a test

piece obtained from such alloys, it is found that:

the α phase is no longer of a spheroidised shape but is rather in the shape of ellipsoids which are linked together in pairs in the vicinity of one of the ends of their long axis so as to form an acute angle between said axes, that arrangement being more generally referred to as "butterfly wings", and

the bonding γ phase has a mean free path which decreases in proportion to increases in the rupture strength in particular. Thus, below 15 μm , values of higher than 1600 MPa are attained.

Furthermore, the increase in mechanical characteristics beyond a level of 1500 MPa goes through polygonisation of the α phase. As a complementary aspect, a precipitation network in respect of the γ phase is developed in the area of contiguity of the nodules of the α phase.

From the point of view of microstructure, by taking thin slices, the presence is found in the α phase of dislocation cells of dimensions of between 0.01 and 1 μm which decrease in proportion to a rise in the mechanical characteristics of the material. In accordance with that rise, disorientation of the cells relative to each other is also observed. It is thought that it is those cells which give such alloys the plasticity necessary for their deformation. In addition, examination on a testpiece of the surface parallel to the direction of working reveals a fibrous texture which becomes more pronounced in proportion to increasing mechanical characteristics. Those fibres are characterised by a particular orientation which, in accordance with the Miller indices, corresponds to the direction $\langle 110 \rangle$ for the poles $\{110\}$ in the central part of the testpiece.

The invention also concerns a process for the production of alloys having such a structure, in which it is possible to regulate as desired the value of the required mechanical characteristics and in particular to achieve a breaking strength of close to 2000 MPa.

In order to achieve that, the applicants developed treatment of the alloys which makes it possible to promote plastic deformation of the α phase, having regard to the fact that the latter is normally fragile but has a high elastic limit.

The process comprises steps which are already known and which consist of:

using powders of each element of the alloy, each thereof being of a FISHER diameter of between 1 and 15 μm ,

mixing said powders in proportions corresponding to the composition of the desired alloy,

5 compressing said powders in the form of compacted items,

sintering the compacted items at between 1490 and 1650°C for from 2 to 5 hours,

treating the sintered compacted items under vacuum at between 1000 and 1300°C, and

10 subjecting the resulting compacted items to at least one working pass.

However, what characterises that process is that after treatment under vacuum the compacted items are subjected to at least three cycles of operations, each cycle comprising a working step followed by a heat
15 treatment.

Thus, the invention consists of a succession of cycles which are of an increasing number in proportion to the wish to attain structures corresponding to the highest values of the mechanical characteristics involved. Thus three cycles make it possible to attain a level of
20 breaking strength which is between 1400 and 1450 MPa while at the end of four cycles, values of close to 1850 MPa are achieved. Each of those cycles comprises, in the following order, a working step which is effected for example by hammering so as to develop a certain degree of reduction in surface area of the sintered compacted item of between 10
25 and 50% followed by an annealing treatment by putting them in a furnace heated to a temperature of less than 1300°C in an inert atmosphere for 4 to 20 hours.

Preferably in the course of the first two cycles the levels of working are lower and the temperatures are higher than in the course of
30 the subsequent cycles. In the fourth cycle, the appropriate level of working is achieved by effecting at least two successive passes in the hammering apparatus for example before effecting the heat treatment.

The invention can be illustrated by means of the accompanying drawings in which, in respect of an alloy containing by weight 93% of tungsten, 5% of nickel and 2% of iron:
35

Figures 1, 2 and 3 show the structures under a magnification of 200 of transverse sections of testpieces which respectively exhibit a

breaking strength of 1100, 1540 and 1850 MPa,

Figures 4, 5 and 6 show microstructures of facies in respect of rupture under a tensile load, obtained from the same testpieces, under respective degrees of magnification of 1000-1000-2500, and

5 Figures 7, 8 and 9 show microstructures obtained by viewing thin slices under an electron microscope under levels of magnification of 35,000, 30,000 and 60,000 respectively, revealing the specific state of the α phase which makes it possible to achieve the desired characteristics.

10 Referring to Figure 1, shown therein in white is the nodular structure of the tungsten α phase and the bonding γ phase whose mean free path is close to 20 μm .

Figure 2 shows the formation of butterfly wings while the mean free path is reduced to about 10 to 14 μm .

15 In Figure 3, the trend noted in Figure 2 is accentuated and the mean free path is in the range of from 3 to 7 μm .

In Figure 4 the rupture in the alloy is essentially internodular and cupular in regard to the γ phase.

20 In Figures 5 and 6, which correspond to testpieces of higher characteristics than those shown in Figure 4, it is noted that the total rupture mode becomes transnodular with infrequent internodular rupture initiations. At the level of the microstructure of the γ phase states of sub-structures are developed.

25 Figure 7 shows a restoration structure with rearranged cells of a size of from 0.4 to 0.8 μm .

Figure 8 shows the polygonised step, which is necessary in order to go to the highest characteristics.

Figure 9 shows a typical structure of the highest characteristics with development of dislocation microcells of from 0.05 to 0.01 μm .

30 The invention can be illustrated by reference to the following example of use thereof:

Elementary powders of a FISHER diameter of between 1.4 and 10 μm were mixed so as to obtain a product of the following composition by weight: W 93% - Ni 5% - Fe 2%.

35 After isostatic compression under a pressure of 230 MPa, the compacted items, measuring 90 mm in diameter and 500 mm in length, were sintered in a tunnel furnace at a temperature of 1490°C for 5 hours and

then kept under partial vacuum for a period of 25 hours in a furnace heated at between 900 and 1300°C.

The products obtained in that way were then treated in accordance with the invention. The particular conditions under which the cycles were effected as well as the mechanical characteristics R_m (breaking strength), R_{0.2} (resistance to 0.2% of elongation), E (elongation), VH30 (Vickers hardness) and RHc (Rockwell hardness) obtained in the different treatment cycles were set forth in the following table:

Cycle No.	Degree of working %	Heat treatment		R _m in MPa	R _p 0.2 MPa	E%	VH30 Hardness	RHc Hardness
		Temp. in °C	Period in hours					
15	1	10-20		1050	1010	8	400	30
		700/ 1200	4-8	1100	1050	8	420	38
20	2	10-15		1330	1310	5	470	45
		500/ 1100	4-8	1150	1000	20	380	38
25	3	20-50		1400	1320	9	470	40
		500/ 1000	4-8	1450	1400	8	500	44
	4	40-60		1820	1800	5	530	48
		30-50		1840	1870	4	540	49
30		500/ 900	6-20	1850	1810	5	530	48

It is found therefore that the breaking strength increases substantially when the number of cycles increased and that the degree of elongation remains sufficient to permit transformation of the alloy.

CLAIMS

1. Heavy alloys with very high mechanical characteristics, of a specific gravity of between 15.6 and 18, containing between 80 and 99%
5 by weight of tungsten in the form of nodules constituting the α phase as well as nickel and iron in a Ni/Fe ratio by weight which is higher than or equal to 2, performing the bonding function and constituting the γ phase and optionally elements such as molybdenum, titanium, aluminium, manganese, cobalt and rhenium, characterised in that in a
10 direction transverse to the working direction, the α phase is in the form of ellipsoids joined two by two in the neighbourhood of one extremity of their major axes so as to form an acute angle between the said axes, with dislocation cells of dimensions from 0.01 to 1 μm , and the bonding γ phase has a mean free path, defined as the average of the
15 distances which in a given direction separates two successive zones of γ phase, of less than 15 μm .
2. Alloys according to Claim 1 characterised in that the α phase in the working direction has a fibrous texture of a direction $\langle 110 \rangle$.
20
3. Alloys according to Claim 1 characterised in that, for levels of breaking strength of higher than 1500 MPa, the α phase in the working direction is polygonised.
- 25 4. Alloys according to Claim 1 characterised in that the γ phase forms a precipitation network in the area of contiguity of the nodules of the α phase.
5. A process for the production of alloys according to Claim 1
30 comprising:
 using powders of each element of a FISHER diameter of between 1 and 15 μm ,
 mixing said powders in proportions corresponding to the composition of the desired alloy,
35 compressing said powders in the form of compacted items,
 sintering the compacted items at a temperature of between 1490 and 1650°C for from 2 to 5 hours,



treating the sintered compacted items under vacuum at between 1000 and 1300°C, and

subjecting them to at least one working pass,
characterised by subjecting the compacted items after treatment under
5 vacuum to at least three cycles of operations, each cycle comprising a
working step followed by a heat treatment.

6. A process according to Claim 5 characterised in that, in the
course of the first two cycles, the degrees of working are lower and
10 the heat treatment temperatures higher than in the course of the
subsequent cycles.

7. A process according to Claim 6 characterised in that, in the
course of the fourth cycle, the working operation is effected in at
15 least two passes.