

- 1 -

TRANSITION METAL COMPLEXES

Field of the Invention

The present invention relates to transition metal complexes based on certain bis-arylimine pyridine ligands and catalyst systems prepared therefrom, wherein the transition metal complexes and the catalyst systems prepared therefrom are highly soluble in non-polar media, and the use of such transition metal complexes for the dimerization and oligomerization of olefins.

Background of the Invention

Several transition metal complexes based upon bis-imine pyridine ligands have been reported in the art, in particular for use in catalyst systems for the catalysis of ethylene and/or olefin (co-) polymerization and (co-) oligomerization reactions as well as for use in catalyst systems for the catalysis of alpha-olefin dimerization reactions.

In this regard a number of published patent applications describe catalyst systems for the polymerization or oligomerization of 1-olefins, in particular ethylene, which contain nitrogen-containing transition metal compounds. See, for example, the following patent applications which are incorporated herein by reference in their entirety: WO 92/12162, WO 96/27439, WO 99/12981, WO 00/50470, WO 98/27124, WO 99/02472, WO 99/50273, WO 99/51550, EP-A-1,127,987, WO 02/12151, WO 02/06192, WO 99/12981, WO 00/24788, WO 00/08034, WO 00/15646, WO 00/20427, WO 01/58874 and WO 03/000628.

In particular, recently published Shell applications WO01/58874, WO02/00339, WO02/28805 and WO 03/011876, all of which are incorporated herein by reference in their entirety, disclose novel classes of catalysts based on bis-imine pyridine iron compounds which are highly active in the oligomerization of olefins, especially ethylene and which produce linear alpha olefins in the C₆-C₃₀ range with a Schulz-Flory distribution, said linear alpha olefins being of high purity.

10 In co-pending PCT Patent Application No. PCT/EP03/10708 (now published as WO 2004/037415), there is described a catalyst system for the oligomerization of ethylene to linear alpha olefins, wherein the catalyst system comprises:

15 a) one or more bis-arylimine pyridine iron or cobalt catalysts;


b) a first co-catalyst compound which is selected from aluminium alkyls, aluminoxanes, and mixtures thereof; and

20 c) one or more additional co-catalyst compounds which comprises one or more compounds of the formula ZnR'_2 wherein each R', which may be the same or different, is selected from hydrogen, optionally substituted C₁-C₂₀ hydrocarbyl, phenyl, Cl, Br, I, SR'', NR''₂, OH, OR'', CN, NC wherein R'', which within the same molecule may be the same or different, is C₁-C₂₀ hydrocarbyl.

Co-pending PCT Patent Application No. PCT/EP03/10708 (now published as WO 2004/037415) describes bis-arylimine pyridine ligands having the formula below:

30

- 3 -



wherein X is carbon or nitrogen,

n is 0 or 1,

m is 0 or 1,

5 Z is a π -coordinated metal fragment,

R₁-R₅, R₇-R₉ and R₁₂-R₁₄ are each, independently, hydrogen, optionally substituted hydrocarbyl, an inert functional group, or any two of R₁-R₃, R₇-R₉ and R₁₂-R₁₄ vicinal to one another taken together may form a ring; R₆ is hydrogen, optionally substituted hydrocarbyl, an inert functional group, or taken together with R₇ or R₄ to form a ring; R₁₀ is hydrogen, optionally substituted hydrocarbyl, an inert functional group, or taken together with R₉ or R₄ to form a ring; R₁₁ is hydrogen, optionally substituted hydrocarbyl, an inert functional group, or taken together with R₅ or R₁₂ to form a ring; and R₁₅ is hydrogen, optionally substituted hydrocarbyl, an inert functional group, or taken together with R₅ or R₁₄ to form a ring.

20 Disclosed within the examples of co-pending PCT Patent Application No. PCT/EP03/10708 (now published as WO 2004/037415) is the 2-[1-(2,4,6-trimethylphenylimino)ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl]

pyridine iron[III] chloride complex, and catalyst systems consisting of 2-[1-(2,4,6-trimethylphenylimino) ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl] pyridine iron[III] chloride with MAO and 2-[1-(2,4,6-trimethylphenylimino) ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl] pyridine iron[III] chloride with methylaluminoxane (MAO) and Et₂Zn co-catalysts in a toluene solution.

US Patent No. 6,291,733, describes a method of dimerizing alpha-olefins to mostly linear internal olefin dimers using a catalyst composition comprising a bis-arylimine pyridine iron complex and an alkylaluminoxane co-catalyst composition in molar excess. The reaction of this process proceeds rapidly, even at ambient temperatures, and yields a dimerization product rich in linear internal olefin dimers.

The use of a bis-arylimine pyridine cobalt complex and a modified methylaluminoxane (MMAO) co-catalyst in the dimerization of alpha-olefins is described in the article "Tridentate Cobalt Catalysts for Linear Dimerization and Isomerization of α -Olefins" by Brooke L. Small in Organometallics 2003, 22, 3178-3183. The use of a molar excess of the alkylaluminoxane co-catalyst in this reference makes this process commercially less favourable.

Although catalysts based on bis-arylimine pyridine complexes are useful catalyst precursors in polymerization, oligomerization and dimerization processes, they suffer from the disadvantage that they have low solubility in non-polar media, especially at ambient temperatures. The low solubility of bis-arylimine pyridine complexes in non-polar media such as

benzene, toluene and paraffin solvents, especially at ambient temperatures, has several problems attached to it, including difficulty in accurate dosing of the catalyst system into reactors, especially under
5 continuous operation, and damage to the reactor equipment, especially pumps and seals which can be caused by the abrasive action of suspended, non-soluble catalyst particles.


Therefore, there is a need for bis-arylimine pyridine complexes and catalyst systems comprising these
10 complexes which can be used with ease in a continuous process, e.g. continuous polymerization, oligomerization or dimerization process. In particular, there is a need for bis-arylimine pyridine complexes and catalyst systems
15 containing such complexes which are highly soluble in non-polar media, without having a deleterious effect on the catalytic activity displayed by the bis-arylimine pyridine catalyst compositions known in the art.

The present invention provides a transition metal complex based on certain bis-arylimine pyridine ligands
20 and a catalyst system thereof which are highly soluble in non-polar media and display good catalytic activity for continuous polymerization, oligomerization and dimerization processes.

25 Summary of the Invention

In one aspect of the present invention there is provided a transition metal complex which is a bis-arylimine pyridine MX_n complex, comprising a bis-arylimine pyridine ligand having the formula (I) below:

- 6 -



(I)

wherein R₁-R₅, R₇-R₉, R₁₂ and R₁₄ are each,
 independently, hydrogen, optionally substituted
 5 hydrocarbyl, an inert functional group, or any two of
 R₁-R₃ and R₇-R₉ vicinal to one another taken together may
 form a ring, and R₆ is hydrogen, optionally substituted
 hydrocarbyl, an inert functional group, or taken together
 with R₇ or R₄ to form a ring, R₁₀ is hydrogen, optionally
 10 substituted hydrocarbyl, an inert functional group, or
 taken together with R₉ or R₄ to form a ring, R₁₁ is
 hydrogen, optionally substituted hydrocarbyl, an inert
 functional group, or taken together with R₁₂ or R₅ to
 form a ring, R₁₅ is hydrogen, optionally substituted
 15 hydrocarbyl, an inert functional group, or taken together
 with R₁₄ or R₅ to form a ring, provided that R₁₃ and at
 least one of R₁₂ and R₁₄ are independently selected from
 optionally substituted C₁-C₃₀ alkyl, optionally
 substituted C₄-C₃₀ alkyloxy, halogen and optionally
 20 substituted C₅-C₂₀ aryl, or R₁₃ taken together with R₁₂
 or R₁₄ form a ring, or R₁₂ taken together with R₁₁ form a
 ring and R₁₄ taken together with R₁₅ form a ring
 (preferably wherein R₁₃ and at least one of R₁₂ and R₁₄

- 7 -

are independently selected from optionally substituted C₁-C₃₀ alkyl, optionally substituted C₄-C₃₀ alkyloxy and optionally substituted C₅-C₂₀ aryl), and provided that at least one of R₁₂, R₁₃ and R₁₄ is optionally substituted C₄-C₃₀ alkyloxy;


M is a transition metal atom selected from Ti, V, Cr, Mn, Ni, Pd, Rh, Ru, Mo, Nb, Zr, Hf, Ta, W, Re, Os, Ir or Pt; preferably Ti, V, Cr, Mn, Ni, Pd or Pt; more preferably V, Cr, Mn, Ni or Pd; especially Cr;

n matches the formal oxidation state of transition metal atom M; and

X is halide, optionally substituted hydrocarbyl, alkoxide, amide, or hydride.

In another aspect of the present invention, there is provided a transition metal complex which is a bis-arylimine pyridine MX_n complex, comprising a bis-arylimine pyridine ligand having the formula (I) above, wherein R₁₋₁₅ and X are as defined above in relation to formula I and M is a transition metal atom, especially one selected from Fe and Co, wherein the transition metal complex is not 2-[1-(2,4,6-trimethylphenylimino) ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl]pyridine iron (II) chloride complex.

In another aspect of the present invention there is provided a transition metal complex which is a [bis-arylimine pyridine MX_p⁺][NC⁻]_q complex, comprising a bis-arylimine pyridine ligand having the formula (I) below:



(I)

wherein R₁-R₅, R₇-R₉, R₁₂ and R₁₄ are each,
independently, hydrogen, optionally substituted
5 hydrocarbyl, an inert functional group, or any two of
R₁-R₃ and R₇-R₉ vicinal to one another taken together may
form a ring, and R₆ is hydrogen, optionally substituted
hydrocarbyl, an inert functional group, or taken together
with R₇ or R₄ to form a ring, R₁₀ is hydrogen, optionally
10 substituted hydrocarbyl, an inert functional group, or
taken together with R₉ or R₄ to form a ring, R₁₁ is
hydrogen, optionally substituted hydrocarbyl, an inert
functional group, or taken together with R₁₂ or R₅ to
form a ring, R₁₅ is hydrogen, optionally substituted
15 hydrocarbyl, an inert functional group, or taken together
with R₁₄ or R₅ to form a ring, provided that R₁₃ and at
least one of R₁₂ and R₁₄ are independently selected from
optionally substituted C₁-C₃₀ alkyl, optionally
substituted C₄-C₃₀ alkyloxy, halogen and optionally
20 substituted C₅-C₂₀ aryl, or R₁₃ taken together with R₁₂
or R₁₄ form a ring, or R₁₂ taken together with R₁₁ form a
ring and R₁₄ taken together with R₁₅ form a ring
(preferably R₁₃ and at least one of R₁₂ and R₁₄ are

- 9 -

independently selected from optionally substituted C₁-C₃₀ alkyl, optionally substituted C₄-C₃₀ alkyloxy and optionally substituted C₅-C₂₀ aryl), and provided that at least one of R₁₂, R₁₃ and R₁₄ is optionally substituted C₄-C₃₀ alkyloxy;

X is halide, optionally substituted hydrocarbyl, alkoxide, amide, or hydride;

M is a transition metal atom selected from Ti, V, Cr, Mn, Ni, Pd, Rh, Ru, Mo, Nb, Zr, Hf, Ta, W, Re, Os, Ir or Pt; preferably Ti, V, Cr, Mn, Ni, Pd or Pt; more preferably V, Cr, Mn, Ni or Pd; especially Cr; or M is a transition metal atom, particularly Fe or Co;

NC⁻ is a non-coordinating anion; and

p + q matches the formal oxidation state of transition metal atom M.

In another aspect of the invention, there is provided a transition metal complex, which is (a) a bis-arylimine pyridine MX_n complex comprising a bis-arylimine pyridine ligand having the formula (I) above wherein R₁₋₁₅, X and n are as defined and described herein in relation to formula I and M is a transition metal atom, e.g. as described above but preferably Fe, Co or Cr or (b), a [bis-arylimine pyridine MX_p⁺][NC⁻]_q complex comprising a bis-arylimine pyridine ligand having the formula (I) above wherein R₁₋₁₅, X, p, [NC] and q are as defined and described herein in relation to formula (I) and M is a transition metal atom, e.g. as described above but preferably selected from Fe, Co and Cr, provided that in the ligand of formula (I) in said transition metal complex R₈ and at least one of R₇ and R₉ are

- 10 -

independently selected from optionally substituted C₁-C₃₀ alkyl, optionally substituted C₄-C₃₀ alkyloxy, halogen and optionally substituted C₅-C₂₀ aryl, or R₈ taken together with R₇ or R₉ form a ring, or R₇ taken together with R₆ form a ring and R₉ taken together with R₁₀ form a ring (preferably wherein R₈ and at least one of R₇ and R₉ are independently selected from optionally substituted C₁-C₃₀ alkyl, optionally substituted C₄-C₃₀ alkyloxy and optionally substituted C₅-C₂₀ aryl), and provided that at least one of R₇, R₈ and R₉ is optionally substituted C₄-C₃₀ alkyloxy. A ligand of formula I having such a definition of R₇, R₈, R₉ as given in this paragraph is also described herein as one of formula II.

In another aspect of the present invention there is provided a catalyst system comprising (a) one or more of the transition metal complexes which is a bis-arylimine pyridine MX_n complex where the bis-arylimine pyridine is of formula I above in which R₁₋₁₅, X, n are as defined and described herein in relation to formula I and M is a transition metal atom e.g. as described herein in relation to formula I including Fe or Co, or is a [bis-arylimine pyridine MX_p⁺][NC⁻]_q complex wherein the bis-arylimine pyridine is of formula I above in which R₁₋₁₅, X, p, q [NC] are as defined and described herein in relation to formula I and M is a transition metal atom, e.g. as described herein in relation to formula I include Fe or Co, and mixtures thereof and

(b) (i) in the case when a bis-arylimine pyridine MX_n complex is present, (1) a co-catalyst compound capable of abstracting an anion and transferring an

- 11 -

optionally substituted hydrocarbyl or hydride group to the metal atom, or (2) a co-catalyst compound capable of abstracting an anion and a co-catalyst compound capable of transferring an optionally substituted hydrocarbyl or hydride group to the transition metal atom; and/or

5 (b) (ii) in the case where a [bis-arylimine pyridine $\text{MX}_p^+][\text{NC}^-]_q$ complex is present, a co-catalyst compound capable of transferring an optionally substituted hydrocarbyl or hydride group to the transition metal atom;

with the proviso that when the transition metal atom is Fe or Co the catalyst system does not comprise one or more compounds of the formula ZnR'_2 wherein each R' , which may be the same or different, is selected from hydrogen, optionally substituted $\text{C}_1\text{-C}_{20}$ hydrocarbyl, phenyl, Cl, Br, I, SR'' , NR''_2 , OH, OR'' , CN, isocyanide wherein R'' , which within the same molecule may be the same or different, is $\text{C}_1\text{-C}_{20}$ hydrocarbyl, and the catalyst system is not 2-[1-(2,4,6-trimethylphenylimino) ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl] pyridine iron[II] chloride complex with MAO.

or with the proviso that when the transition metal is Fe the catalyst system is not 2-[1-(2,4,6-trimethylphenylimino) ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl] pyridine iron (II) chloride with MAO or 2-[1-(2,4,6-trimethylphenylimino) ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl] pyridine iron (II) chloride with MAO and ZnEt_2 .

In another aspect, there is provided a modified catalyst system of the invention comprising (b) and (a)


one or more of the transition metal complexes which is a bis-arylimine pyridine

MX_n or $[MX_p^+][NC^-]_q$ complex, where X, p, NC and q are as defined and described herein in relation to formula I and M is a transition metal atom e.g. as described herein in relation to formula I including Fe or Co, and R_1 - R_{15} are as defined and described with respect to formula I, provided that R_7 , R_8 and R_9 are as defined above in relation to ligands of formula II.

In another aspect of the present invention, there is provided a dimerization or co-oligomerisation process comprising contacting an olefin feed which is an alpha-olefin comprising at least 3 carbon atoms or a mixture thereof with ethylene, with a catalyst composition comprising:

(a) one or more transition metal complexes selected from:

(i) a bis-arylimine pyridine MX_n complexes, comprising a bis-arylimine pyridine ligand having the formula (I) below:



(I)

wherein R_1 - R_5 , R_7 - R_9 , R_{12} and R_{14} are each, independently, hydrogen, optionally substituted

- 13 -


hydrocarbyl, an inert functional group, or any two of R₁-R₃ and R₇-R₉ vicinal to one another taken together may form a ring, and R₆ is hydrogen, optionally substituted hydrocarbyl, an inert functional group, or taken together with R₇ or R₄ to form a ring, R₁₀ is hydrogen, optionally substituted hydrocarbyl, an inert functional group, or taken together with R₉ or R₄ to form a ring, R₁₁ is hydrogen, optionally substituted hydrocarbyl, an inert functional group, or taken together with R₁₂ or R₅ to form a ring, R₁₅ is hydrogen, optionally substituted hydrocarbyl, an inert functional group, or taken together with R₁₄ or R₅ to form a ring, provided that R₁₃ and at least one of R₁₂ and R₁₄ are independently selected from optionally substituted C₁ - C₃₀ alkyl, optionally substituted C₄ - C₃₀ alkyloxy, halogen and optionally substituted C₅ - C₂₀ aryl, or R₁₃ taken together with R₁₂ or R₁₄ form a ring, or R₁₂ taken together with R₁₁ form a ring and R₁₄ taken together with R₁₅ form a ring (preferably wherein R₁₃ and at least one of R₁₂ and R₁₄ are independently selected from optionally substituted C₁-C₃₀ alkyl, optionally substituted C₄-C₃₀ alkyloxy and optionally substituted C₅-C₂₀ aryl), and provided that at least one of R₁₂, R₁₃ and R₁₄ is optionally substituted C₄-C₃₀ alkyloxy;

M is a transition metal atom; preferably a Group 4 to Group 10 transition metal; preferably Ti, V, Cr, Mn, Fe, Co, Ni, Pd or Pt; more preferably V, Cr, Mn, Fe, Co, Ni or Pd; especially Fe, Co or Cr;

n matches the formal oxidation state of transition metal atom M; and

X is halide, optionally substituted hydrocarbyl, alkoxide, amide, or hydride; and

(ii) a [bis-arylimine pyridine MX_p^+][NC^-] $_q$ complex, comprising a bis-arylimine pyridine ligand having the formula (I) below:



(I)

wherein R_1 - R_5 , R_7 - R_9 , R_{12} and R_{14} are each, independently, hydrogen, optionally substituted hydrocarbyl, an inert functional group, or any two of R_1 - R_3 and R_7 - R_9 vicinal to one another taken together may form a ring, and R_6 is hydrogen, optionally substituted hydrocarbyl, an inert functional group, or taken together with R_7 or R_4 to form a ring, R_{10} is hydrogen, optionally substituted hydrocarbyl, an inert functional group, or taken together with R_9 or R_4 to form a ring, R_{11} is hydrogen, optionally substituted hydrocarbyl, an inert functional group, or taken together with R_{12} or R_5 to form a ring, R_{15} is hydrogen, optionally substituted hydrocarbyl, an inert functional group, or taken together with R_{14} or R_5 to form a ring, provided that R_{13} and at least one of R_{12} and R_{14} are independently selected from optionally substituted $\text{C}_1 - \text{C}_{30}$ alkyl, optionally

substituted C₄-C₃₀ alkyloxy, halogen and optionally substituted C₅-C₂₀ aryl, or R₁₃ taken together with R₁₂ or R₁₄ form a ring, or R₁₂ taken together with R₁₁ form a ring and R₁₄ taken together with R₁₅ form a ring

5 (preferably R₁₃ and at least one of R₁₂ and R₁₄ are independently selected from optionally substituted C₁-C₃₀ alkyl, optionally substituted C₄-C₃₀ alkyloxy and optionally substituted C₅-C₂₀ aryl), and provided that at least one of R₁₂, R₁₃ and R₁₄ is optionally substituted
10 C₄-C₃₀ alkyloxy;

X is halide, optionally substituted hydrocarbyl, alkoxide, amide, or hydride;

M is a transition metal atom; preferably a Group 4 to Group 10 transition metal; preferably Ti, V, Cr, Mn, Fe, Co, Ni, Pd or Pt; more preferably V, Cr, Mn, Fe, Co,
15 Ni or Pd; especially Fe, Co or Cr;

NC⁻ is a non-coordinating anion; and

p + q matches the formal oxidation state of transition metal atom M; and mixtures thereof; and

20 (b) (i) in the case when a bis-arylimine pyridine MX_n complex is present, (1) a co-catalyst compound capable of abstracting an anion and transferring an optionally substituted hydrocarbyl or hydride group to the metal atom, or (2) a co-catalyst compound capable of
25 abstracting an anion and a co-catalyst compound capable of transferring an optionally substituted hydrocarbyl or hydride group to the transition metal atom; and/or

(b) (ii) in the case where a [bis-arylimine pyridine MX_p⁺][NC⁻]_q complex is present, a co-catalyst
30 compound capable of transferring an optionally

- 16 -

substituted hydrocarbyl or hydride group to the transition metal atom.

When the feed olefin is an alpha olefin of at least 3 carbon atoms, the process is a dimerization, but when the feed olefin is a mixture thereof with ethylene it is a co-oligomerization process.

In another aspect of the present invention there is provided an oligomerization process comprising contacting an olefin feed which is ethylene with a catalyst system (also called herein a catalyst) composition comprising

(a) one or more transition metal complexes which is a bis-arylimine pyridine MX_n complex where the bis-arylimine pyridine of formula I above in which R_{1-15} , X , n are as defined and described herein in relation to formula I and M is a transition metal atom e.g. as described herein in relation to formula I including Fe or Co, or is a $[bis\text{-arylimine pyridine } MX_p][NC^-]_q$ complex wherein the bis arylamine pyridine is of formula I above in which R_{1-15} , X , p , q , $[NC]$ are as defined and described herein in relation to formula I and M is a transition metal atom, eg as described herein in relation to formula I (including Fe or Co), in particular in relation to the dimerization process, and mixtures thereof and

(b) (i) in the case when a bis-arylimine pyridine MX_n complex is present, (1) a co-catalyst compound capable of abstracting an anion and transferring an optionally substituted hydrocarbyl or hydride group to the metal atom, or (2) a co-catalyst compound capable of abstracting an anion and a co-catalyst compound capable

- 17 -

of transferring an optionally substituted hydrocarbyl or hydride group to the transition metal atom; and/or

(b)(ii) in the case where a [bis-arylimine pyridine $\text{MX}_p^+][\text{NC}^-]_q$ complex is present, a co-catalyst compound capable of transferring an optionally substituted hydrocarbyl or hydride group to the transition metal atom

with the proviso that when the transition metal atom is Fe or Co the catalyst system does not comprise one or more compounds of the formula ZnR'_2 wherein each R' , which may be the same or different, is selected from hydrogen, optionally substituted $\text{C}_1\text{-C}_{20}$ hydrocarbyl, phenyl, Cl, Br, I, SR'' , NR''_2 , OH, OR'' , CN, NC wherein R'' , which within the same molecule may be the same or different, is $\text{C}_1\text{-C}_{20}$ hydrocarbyl, and the catalyst system is not 2-[1-(2,4,6-trimethylphenylimino) ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl] pyridine iron(II) chloride complex with MAO,

or with the proviso that when the transition metal is Fe the catalyst system is not 2-[1-(2,4,6-trimethylphenylimino) ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl] pyridine iron (II) chloride with MAO or 2-[1-(2,4,6-trimethylphenylimino) ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl] pyridine iron (II) chloride with MAO and ZnEt_2 .

In a modification of this aspect of the present invention there is provided an oligomerization process comprising contacting an olefin feed which is ethylene with the modified catalyst system of the invention.

The transition metal complexes and catalyst systems of the present invention have excellent solubility in

- 18 -

non-polar media and can be used to catalyze a wide variety of oligomerization, polymerization and dimerization reactions.


In another aspect of the present invention, there is provided a solution in non-polar media, in particular a chemically inert non-polar solvent, especially an aromatic hydrocarbon solvent, of at least 5 or 10 mg ml⁻¹ of a transition metal complex which is a bis-arylimine pyridine MX_n or [MX_p⁺][NC⁻]_q complex each comprising a bis-arylimine pyridine complex of formula I as defined and described above wherein each of R₁₋₁₅, X, n, p, NC and q are as defined and described herein, and M is a transition metal, such as one from any of Groups 4 to 10, in particular one selected from Ti, V, Cr, Mn, Fe, Co, Ni, Pd, Rh, Ru, Mo, Nb, Zr, Hf, Ta, W, Re, Os, Ir or Pt, preferably Fe, Co or Cr and especially Co or Fe. A preferred solution is in toluene of at least 10 mg ml⁻¹ especially at least 50 mg ml⁻¹ of the transition metal complex wherein the metal M is iron or cobalt, in particular 2-[1-(2,4,6-trimethylphenylimino) ethyl]-6-[1-4-eicosanoxy-3,5-diphenylphenylimino)ethyl]pyridine iron (II) chloride complex. In a further solution aspect of the present invention there is provided a solution in non-polar media in particular chemically inert non-polar solvents especially an aromatic hydrocarbon solvent, of at least 5 or 10 mg ml⁻¹ of a catalyst system comprising (a) said transition metal complex and component (b) as defined above. The catalyst system solution can be made by mixing solutions of the complex (a) and component (b) and is optionally in the presence or absence of the reactant composition to be dimerized or (co)oligomerized.

- 19 -

The same complex is preferred in the catalyst solution as in the above complex solution of the present invention.

In another aspect of the present invention, the dimerization, oligomerization or co-oligomerization processes of the invention are performed with the catalyst complex, composition or system being in a solution of the present invention, especially in one or more of an aromatic hydrocarbon, such as benzene, toluene or xylene, and an alkene such as 1-hexene, cis/trans 2-hexene or 1-octene.

There is also provided in this invention a bis-arylimine pyridine ligand having the formula (I) below:



(I)

wherein R₁-R₅, R₇-R₉, R₁₂ and R₁₄ are each, independently, hydrogen, optionally substituted hydrocarbyl, an inert functional group, or any two of R₁-R₃ and R₇-R₉ vicinal to one another taken together may form a ring, and R₆ is hydrogen, optionally substituted hydrocarbyl, an inert functional group, or taken together with R₇ or R₄ to form a ring, R₁₀ is hydrogen, optionally substituted hydrocarbyl, an inert functional group, or taken together with R₉ or R₄ to form a ring, R₁₁ is hydrogen, optionally substituted hydrocarbyl, an inert

- 20 -

functional group, or taken together with R₁₂ or R₅ to form a ring, R₁₅ is hydrogen, optionally substituted hydrocarbyl, an inert functional group, or taken together with R₁₄ or R₅ to form a ring, provided that R₁₃ and at least one of R₁₂ and R₁₄ are independently selected from optionally substituted C₁-C₃₀ alkyl, optionally substituted C₄-C₃₀ alkyloxy, halogen and optionally substituted C₅-C₂₀ aryl, or R₁₃ taken together with R₁₂ or R₁₄ form a ring, or R₁₂ taken together with R₁₁ form a ring and R₁₄ taken together with R₁₅ form a ring (preferably wherein R₁₃ and at least one of R₁₂ and R₁₄ are independently selected from optionally substituted C₁-C₃₀ alkyl, optionally substituted C₄-C₃₀ alkyloxy and optionally substituted C₅-C₂₀ aryl), and provided that at least one of R₁₂, R₁₃ and R₁₄ is optionally substituted C₄-C₃₀ alkyloxy;

wherein the bis-arylimine pyridine ligand is not 2-[1-(2,4,6-trimethylphenylimino) ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl] pyridine. Preferably the ligands are of formula II as defined and described above.

Detailed Description of the Invention

The present invention relates to transition metal complexes which comprise a bis-arylimine pyridine ligand having the formula (I) above wherein R₁₋₁₅, are as defined and described with reference to formula I

In one class of complexes R₁₂, R₁₃ and R₁₄ are all independently selected from optionally substituted C₁-C₃₀ alkyl, optionally substituted C₄-C₃₀ alkyloxy, and

optionally substituted C₅-C₂₀ aryl, with the proviso that at least one of R₁₂, R₁₃ and R₁₄ is optionally substituted C₄-C₃₀ alkyloxy.

5 In a preferred embodiment of the invention, R₁₃ and at least one of R₁₂ and R₁₄ are independently selected from optionally substituted C₁-C₃₀ (preferably C₃-₂₅) alkyl, optionally substituted C₄-C₃₀ alkyloxy and optionally substituted C₅-C₂₀ (preferably C₃-₂₅) aryl with the proviso that at least one of R₁₂, R₁₃ and R₁₄ is
10 optionally substituted C₄-C₃₀ alkyloxy.

In one class of bis-arylimine pyridine transition metal complexes, the bis-arylimine pyridine ligand having formula (I) above, is such that R₈ and at least one of R₇ and R₉ are independently selected from optionally
15 substituted C₁-C₃₀ alkyl, optionally substituted C₄-C₃₀ alkyloxy, halogen and optionally substituted C₅-C₂₀ aryl, or R₈ taken together with R₇ or R₉ form a ring, or R₇ taken together with R₆ form a ring and R₉ taken together with R₁₀ form a ring with the proviso that at least one
20 of R₇, R₈ and R₉ is optionally substituted C₄-C₃₀ alkyloxy. Preferably R₈ and at least one of R₇ and R₉ are independently selected from optionally substituted C₄-C₃₀ alkyl, optionally substituted C₄-C₃₀ alkyloxy and optionally substituted C₅-C₂₀ aryl or are independently
25 selected from optionally substituted C₃-₂₅ alkyl, optionally substituted C₄-C₃₀ alkyloxy and optionally substituted C₅-C₆ aryl with the proviso that at least one

of R₇, R₈ and R₉ is optionally substituted C₄-C₃₀ alkyloxy.

In another class of the complexes the ligand of formula I has R₇, R₈ and R₉ all independently selected from optionally substituted C₁-C₃₀ alkyl, optionally substituted C₄-C₃₀ alkyloxy and optionally substituted C₅-C₂₀ aryl with the proviso that at least one of R₇, R₈ and R₉ is optionally substituted C₄-C₃₀ alkyloxy.

It will be immediately apparent to the person skilled in the art, that when R₈ and at least one of R₇ and R₉ are independently selected from optionally substituted C₄-C₃₀ alkyl, optionally substituted C₄-C₃₀ alkyloxy and optionally substituted C₅-C₂₀ aryl with the proviso that at least one of R₇, R₈ and R₉ is optionally substituted C₄-C₃₀ alkyloxy, it is not possible for R₈ to be independently, hydrogen, optionally substituted hydrocarbyl, an inert functional group, or any two of R₇-R₉ vicinal to one another taken together to form a ring.

One type of transition metal complex herein is a bis-arylimine pyridine MX_n complex comprising a bis-arylimine pyridine ligand having the formula (I) defined herein, and wherein:

M is a transition metal atom;

n matches the formal oxidation state of transition metal atom M; preferably n is 1, 2 or 3;

X is halide, optionally substituted hydrocarbyl, alkoxide, amide, or hydride; preferably halide or optionally substituted hydrocarbyl; more preferably halide; especially chlorine.

- 23 -

The bis-arylimine pyridine MX_n complex disclosed herein can be reacted with a non-coordinating anion generating species to form a cationic complex, [bis-arylimine pyridine MX_p^+][NC^-] $_q$ complex comprising a bis-arylimine pyridine ligand having the formula (I) defined herein, and wherein:

NC^- is a non-coordinating anion; and

$p + q$ is 2 or 3, matching the formal oxidation state of transition metal atom M; preferably $p + q$ is 2 or 3.

Like the bis-arylimine pyridine MX_n complex, the cationic complex formed by the reaction of the bis-arylimine pyridine MX_n complex with a non-coordinating anion generating species is advantageously highly soluble in non-polar media, and chemically inert non-polar solvents such as benzene and toluene. Furthermore, when the cationic complex of the present invention is used in a process of the invention of dimerization, co-oligomerization or oligomerization, a lower quantity of the compound (b) capable of transferring an optionally substituted hydrocarbyl or hydride group to the transition metal atom is required.

By the term "non-coordinating anion" is meant an anion which does not substantially coordinate to the metal atom M. Non-coordinating anions (NC^-) that may be suitably employed include bulky anions such as tetrakis [3,5-bis(trifluoromethyl)phenyl]borate ($BArF^-$), $(C_6F_5)_4B^-$, and anions of alkylaluminium compounds including $R_3AlX'^-$, $R_2AlClX'^-$, $RAlCl_2X'^-$, and " $RAlOX'^-$ ", wherein R is hydrogen, optionally substituted hydrocarbyl or an inert functional group, and X' is halide, alkoxide or oxygen.

A preferred non-coordinating anion for use herein is tetrakis [3,5-bis(trifluoromethyl)phenyl]borate (BArF^-).

The term "Hydrocarbyl group" in relation to the R_1 to R_{15} groups of formula (I) above means a group
5 containing only carbon and hydrogen atoms. Unless otherwise stated, the number of carbon atoms is preferably in the range from 1 to 30, especially from 1 to 6. Unless otherwise stated, the hydrocarbyl group may be saturated or unsaturated, aliphatic, cycloaliphatic or
10 cycloaromatic (e.g. phenyl), but is preferably aliphatic. Suitable hydrocarbyl groups include primary, secondary and tertiary carbon atom groups such as those described below.

The phrase "optionally substituted hydrocarbyl" in
15 relation to the R_1 to R_{15} groups of formula (I) above is used to describe hydrocarbyl groups which may optionally contain one or more "inert" heteroatom-containing functional groups. By "inert" it is meant that the
functional groups do not interfere to any substantial
20 degree with the catalytic process in which the transition metal complex may be employed. Non-limiting examples of such inert groups are halides, such as fluoride and chloride, silanes, stannanes, ethers, alkoxides and amines with adequate steric shielding, all well-known to
25 those skilled in the art. Some examples of such groups include methoxy, trimethylsiloxy and eicosanoxy. Said optionally substituted hydrocarbyl may include primary, secondary and tertiary carbon atom groups of the nature described below.

30 The term "inert functional group" in relation to the R_1 to R_{15} groups of formula (I) above means a group other

than optionally substituted hydrocarbyl which is inert under the reaction conditions for any reaction or process in which the transition metal complex may be employed. By "inert" it is meant that the functional group does not interfere to any substantial degree with the catalytic process in which the transition metal complex may be employed. Examples of inert functional groups suitable for use herein include halides, ethers, and amines such as tertiary amines, preferably the inert functional group is a halide, especially fluorine and chlorine.

The term "Primary carbon atom group" as used herein means a $-\text{CH}_2-\text{R}$ group wherein R is selected from hydrogen, an optionally substituted hydrocarbyl, or an inert functional group. Examples of suitable primary carbon atom groups include, but are not limited to, $-\text{CH}_3$, $-\text{C}_2\text{H}_5$, $-\text{CH}_2\text{Cl}$, $-\text{CH}_2\text{OCH}_3$, $-\text{CH}_2\text{N}(\text{C}_2\text{H}_5)_2$ and $-\text{CH}_2\text{Ph}$. Unless otherwise stated, preferred primary carbon atom groups for use herein are those wherein R is selected from hydrogen or a C_1 - C_6 unsubstituted hydrocarbyl, preferably wherein R is hydrogen or a C_1 - C_3 alkyl.

The term "Secondary carbon atom group" as used herein means a $-\text{CH}(\text{R})_2$ group wherein each R is independently selected from an optionally substituted hydrocarbyl or an inert functional group. Alternatively, the two R groups may together represent a double bond moiety, e.g. $=\text{CH}_2$, or a cycloalkyl group. Examples of secondary carbon atom groups include, but are not limited to, $-\text{CH}(\text{CH}_3)_2$, $-\text{CHCl}_2$, $-\text{CHPh}_2$, $-\text{CH}=\text{CH}_2$ and cyclohexyl. Unless otherwise stated, preferred secondary carbon atom groups for use herein are those in which R is a C_1 - C_6 unsubstituted hydrocarbyl, preferably a C_1 - C_3 alkyl.

- 26 -

The term "Tertiary carbon atom group" as used herein means a $-C(R)_3$ group wherein each R is independently selected from an optionally substituted hydrocarbyl or an inert functional group. Alternatively, the three R groups may together represent a triple bond moiety, e.g. $-C\equiv CPh$, or a ring system containing tertiary carbon atoms such as adamantyl derivatives. Examples of tertiary carbon atom groups include, but are not limited to, $-C(CH_3)_3$, $-CCl_3$, $-C\equiv CPh$, 1-Adamantyl and $-C(CH_3)_2(OCH_3)$.

Unless otherwise stated, preferred tertiary carbon atom groups for use herein are those wherein each R is a C_1 - C_6 unsubstituted hydrocarbyl group, preferably wherein each R is a C_1 - C_3 alkyl group, more preferably wherein each R is methyl. In the case wherein each R is a methyl group, the tertiary carbon atom group is tert-butyl.

The rings which may be formed by any two of R_1 - R_3 and R_7 - R_9 vicinal to one another taken together, R_6 taken together with R_7 , R_{10} taken together with R_9 , R_{11} taken together with R_{12} and R_{15} taken together with R_{14} , are preferably optionally substituted C_5 - C_{20} cyclic hydrocarbyl groups, more preferably optionally substituted C_5 - C_{20} cycloaliphatic or aromatic groups, even more preferably optionally substituted C_5 - C_8 cycloaliphatic or aromatic groups, especially a C_6 cycloaliphatic or aromatic group.

The rings which may be formed by R_6 taken together with R_4 , R_9 taken together with R_4 , R_{11} taken together with R_5 and R_{15} taken together with R_5 , are preferably optionally substituted C_6 - C_{20} cyclic hydrocarbyl groups,

more preferably optionally substituted C₆-C₂₀ cycloaliphatic groups, even more preferably optionally substituted C₆-C₈ cycloaliphatic groups, especially a C₆ cycloaliphatic group.

5 The term "optionally substituted C₁-C₃₀ alkyl" in relation to the R₁₂, R₁₃ and R₁₄ groups, and, where applicable, the R₇, R₈ and R₉ groups of formula (I) above means a C₁ to C₃₀ linear or branched alkyl group, which may substituted with one or more "inert" functional
10 groups known to those skilled in the art, in particular a halide, preferably fluorine. Preferred optionally substituted alkyl groups comprise from 3 to 25 carbon atoms, more preferably from 4 to 20 carbon atoms. Preferably, the alkyl group is an unsubstituted alkyl
15 group. Examples of suitable "optionally substituted C₁-C₃₀ alkyl" include octadecyl, tetradecyl, dodecyl, decyl, octyl, hexyl, pentyl, *tert*-butyl and *iso*-propyl, especially *tert*-butyl and *iso*-propyl.

 The term "optionally substituted C₄-C₃₀ alkyloxy" in
20 relation to the R₁₂, R₁₃ and R₁₄ groups, and, where applicable, the R₇, R₈ and R₉ groups of formula (I) above means a C₄-C₃₀ optionally substituted alkyl group which is attached to an oxygen atom, the alkoxy group being attached to the aryl group via the oxygen atom.
25 Preferably, the optionally substituted alkyloxy group comprises from 6 to 30 carbon atoms, more preferably from 8 to 30 carbon atoms, and most preferably from 10 to 25 carbon atoms. Preferably, the alkyloxy group is an unsubstituted alkyloxy group. Examples of suitable
30 "optionally substituted C₄-C₃₀ alkyloxy" include

eicosanoxy (which is preferred), octadecyloxy, hexadecyloxy, tetradecyloxy, dodecyloxy, decyloxy, hexyloxy, pentyloxy, butyloxy and tert-butyloxy, especially eicosanoxy, dodecyloxy, pentyloxy and tert-butyloxy.

The term "optionally substituted C₅-C₂₀ aryl" in relation to the R₁₂, R₁₃ and R₁₄ groups, and, where applicable, the R₇, R₈ and R₉ groups of formula (I) above means an aryl or heteroaryl group, comprising from 5 to 20 ring atoms and wherein one or more of the ring atoms can be substituted with one or more substituents known to those skilled in the art, preferably selected from optionally substituted hydrocarbyl, preferably C₁-C₆ alkyl, preferably methyl, and "inert" functional groups, such as halide. In a heteroaryl group, one or more of the ring atoms is a heteroatom, such as nitrogen, oxygen or sulfur, provided that the heteroatom is inert with regard to the catalytic process in which the transition metal complex is employed. Preferably the heteroaryl groups are aromatic, fully substituted or the heteroatom is fully shielded from the transition metal atom. Preferred heteroaryl groups are 1-pyrrolyl groups. Preferably all of the ring atoms are carbon atoms. Within the term "optionally substituted C₅-C₂₀ aryl" is encompassed mono- and poly-aromatic groups. Preferred optionally substituted C₅-C₂₀ aryl groups comprise from 5 to 10 ring carbon atoms, more preferably 5 or 6 ring carbon atoms. Preferably, the aryl groups are unsubstituted aryl groups, including 1-pyrrolyl groups. Most preferred are optionally substituted phenyl groups, especially phenyl.

The rings which may be formed by R₁₃ taken together with R₁₂ or R₁₄, and, where applicable, R₈ taken together with R₇ or R₉ are preferably optionally substituted C₅-C₂₀ cyclic hydrocarbyl groups, more preferably optionally substituted C₅-C₁₀ groups, even more preferably optionally substituted C₅-C₈ groups, especially C₅ and C₆ cyclic hydrocarbyl groups. Included within the term cyclic hydrocarbyl groups in relation to the rings which may be formed by R₁₃ taken together with R₁₂ or R₁₄, and, where applicable, R₈ taken together with R₇ are cycloaliphatic, polycycloaliphatic, aromatic and polyaromatic groups, preferably cycloaliphatic or aromatic groups.

In one class of transition metal complexes herein, R₁₃ and at least one of R₁₂ and R₁₄ are independently selected from optionally substituted C₄-C₃₀ alkyl, optionally substituted C₄-C₃₀ alkyloxy and optionally substituted C₅-C₂₀ aryl, with the proviso that at least one of R₁₂, R₁₃ and R₁₄ is optionally substituted C₄-C₃₀ alkyloxy, and R₈ and at least one of R₇ and R₉ are independently selected from optionally substituted C₄-C₃₀ alkyl, optionally substituted C₄-C₃₀ alkyloxy and optionally substituted C₅-C₂₀ aryl, with the proviso that at least one of R₇, R₈ and R₉ is optionally substituted C₄-C₃₀ alkyloxy.

In another class of transition metal complexes herein, R₁₂, R₁₃ and R₁₄ are all independently selected from optionally substituted C₄-C₃₀ alkyl, optionally substituted C₄-C₃₀ alkyloxy and optionally substituted

- 30 -

C₅-C₂₀ aryl, with the proviso that at least one of R₁₂, R₁₃ and R₁₄ is optionally substituted C₄-C₃₀ alkyloxy.

In another class of transition metal complexes herein, R₇, R₈, R₉, R₁₂, R₁₃ and R₁₄ are all
5 independently selected from optionally substituted C₄-C₃₀ alkyl, optionally substituted C₄-C₃₀ alkyloxy and optionally substituted C₅-C₂₀ aryl, with the proviso that at least one of R₁₂, R₁₃ and R₁₄ is optionally substituted C₄-C₃₀ alkyloxy, and at least one of R₇, R₈
10 and R₉ is optionally substituted C₄-C₃₀ alkyloxy.

The bis-arylimine pyridine ligand having the formula (I) above, may be either symmetrical or non-symmetrical. The term "symmetrical" is used in relation to the four meta-positions and two para-positions of the two aryl-imino groups and defines these as such that both the
15 substitution pattern and the substituents themselves afford two equally substituted aryl-imino groups.

Preferred transition metal complexes of the present invention comprise ligands according to formula (I), in
20 which the following R groups appear: R₁-R₃ are hydrogen; and/or R₄ and R₅ are methyl, hydrogen, benzyl or phenyl, preferably methyl, phenyl or hydrogen, more preferably methyl.

One preferred class of transition metal complexes of the present invention comprise ligands according to
25 formula (I), in which the following R groups appear: R₁₂ and R₁₄ are independently selected from C₁-C₃₀ alkyl and C₅-C₂₀ aryl, preferably C₅-C₂₀ aryl, more preferably phenyl; R₁₃ is C₄-C₃₀ alkyloxy, preferably C₁₀-C₂₅
30 alkyloxy, more preferably eicosanoxy.

Another preferred class of transition metal complexes of the present invention comprise ligands according to formula (I), in which the following R groups appear: R₁₂ and R₁₄ are independently selected from
5 C₁-C₃₀ alkyl and C₅-C₂₀ aryl, preferably C₅-C₂₀ aryl, more preferably phenyl; R₁₃ is C₄-C₃₀ alkyloxy, preferably C₁₀-C₂₅ alkyloxy, more preferably eicosanoxy; R₆ is selected from C₁-C₃₀ alkyl, preferably C₁-C₁₀ alkyl, more preferably C₃-C₆ alkyl, most preferably *tert*-
10 butyl or *iso*-propyl; R₈ and R₁₀ are hydrogen; and preferably R₇ and R₉ are hydrogen.

Another preferred class of transition metal complexes of the present invention comprise ligands according to formula (I), in which the following R groups appear: R₁₂ and R₁₄ are independently selected from
15 C₁-C₃₀ alkyl and C₅-C₂₀ aryl, preferably C₅-C₂₀ aryl, more preferably phenyl; R₁₃ is C₄-C₃₀ alkyloxy, preferably C₁₀-C₂₅ alkyloxy, more preferably eicosanoxy; R₆, R₈ and R₁₀ are independently selected from C₁-C₃₀ alkyl, preferably C₁-C₁₀ alkyl, more preferably C₁-C₆ alkyl, most preferably methyl, ethyl, *iso*-propyl or *tert*-
20 butyl; and preferably R₇ and R₉ are hydrogen.

Another preferred class of transition metal complexes of the present invention comprise ligands according to formula (I), in which the following R groups appear: R₁₂ and R₁₄ are independently selected from
25 C₁-C₃₀ alkyl and C₅-C₂₀ aryl, preferably C₅-C₂₀ aryl, more preferably phenyl; R₁₃ is C₄-C₃₀ alkyloxy, preferably C₁₀-C₂₅ alkyloxy, more preferably eicosanoxy;

R₇ and R₉ are independently selected from C₁-C₃₀ alkyl, preferably C₁-C₁₀ alkyl, more preferably C₃-C₆ alkyl, most preferably *iso*-propyl or *tert*-butyl; and preferably R₆, R₈ and R₁₀ are hydrogen.

5 Another class of transition metal complexes of the present invention comprise ligands according to formula (I), in which the following R groups appear: R₇ and R₉ are independently selected from C₁-C₃₀ alkyl and C₅-C₂₀ aryl, preferably C₅-C₂₀ aryl, more preferably phenyl; R₈
10 is C₄-C₃₀ alkyloxy, preferably C₁₀-C₂₅ alkyloxy, more preferably eicosanoxy.

Another class of transition metal complexes of the present invention comprise ligands according to formula (I), in which the following R groups appear: R₈
15 independently selected from C₁-C₃₀ alkyl, preferably C₁-C₁₀ alkyl, more preferably C₃-C₆ alkyl, most preferably *iso*-propyl or *tert*-butyl; and preferably R₆, R₇, R₉ and R₁₀ are hydrogen.

In a preferred embodiment, the transition metal
20 complex comprises a ligand according to formula (I), wherein R₁ - R₃ are hydrogen, R₄ and R₅ are methyl, R₆, R₈ and R₁₀ are methyl, R₇, R₉, R₁₁ and R₁₅ are hydrogen, R₁₂ and R₁₄ are phenyl and R₁₃ is eicosanoxy.

In another preferred embodiment, the transition
25 metal complex comprises a ligand according to formula (I), wherein R₁ - R₅ are hydrogen, R₆, R₈ and R₁₀ are methyl, R₇, R₉, R₁₁ and R₁₅ are hydrogen, R₁₂ and R₁₄ are phenyl and R₁₃ is eicosanoxy.

In another preferred embodiment, the transition metal complex comprises a ligand according to formula (I), wherein R₁ - R₃ are hydrogen, R₄ and R₅ are phenyl, R₆, R₈ and R₁₀ are methyl, R₇, R₉, R₁₁ and R₁₅ are hydrogen, R₁₂ and R₁₄ are phenyl and R₁₃ is eicosanoxy.

In another preferred embodiment, the transition metal complex comprises a ligand according to formula (I), wherein R₁ - R₃ are hydrogen, R₄ and R₅ are methyl, R₆ and R₁₀ are fluorine, R₇, R₈, R₉, R₁₁ and R₁₅ are hydrogen, R₁₂ and R₁₄ are phenyl and R₁₃ is eicosanoxy.

In another preferred embodiment, the transition metal complex comprises a ligand according to formula (I), wherein R₁ - R₅ are hydrogen, R₆ and R₁₀ are fluorine, R₇, R₈, R₉, R₁₁ and R₁₅ are hydrogen, R₁₂ and R₁₄ are phenyl and R₁₃ is eicosanoxy.

In another preferred embodiment, the transition metal complex comprises a ligand according to formula (I), wherein R₁ - R₃ are hydrogen, R₄ and R₅ are phenyl, R₆ and R₁₀ are fluorine, R₇, R₈, R₉, R₁₁ and R₁₅ are hydrogen, R₁₂ and R₁₄ are phenyl and R₁₃ is eicosanoxy.

In another preferred embodiment, the transition metal complex comprises a ligand according to formula (I), wherein R₁-R₃ are hydrogen, R₄ and R₅ are methyl, R₆ and R₁₀ are chlorine, R₇, R₈, R₉, R₁₁ and R₁₅ are hydrogen, R₁₂ and R₁₄ are phenyl and R₁₃ is eicosanoxy.

In another preferred embodiment, the transition metal complex comprises a ligand according to formula (I), wherein R₁-R₅ are hydrogen, R₆ and R₁₀ are chlorine,

R₇, R₈, R₉, R₁₁ and R₁₅ are hydrogen, R₁₂ and R₁₄ are phenyl and R₁₃ is eicosanoxy.

In another preferred embodiment, the transition metal complex comprises a ligand according to formula
5 (I), wherein R₁-R₃ are hydrogen, R₄ and R₅ are phenyl, R₆ and R₁₀ are chlorine, R₇, R₈, R₉, R₁₁ and R₁₅ are hydrogen, R₁₂ and R₁₄ are phenyl and R₁₃ is eicosanoxy.

In another preferred embodiment, the transition metal complex comprises a ligand according to formula
10 (I), wherein R₁-R₃ are hydrogen, R₄ and R₅ are methyl, R₆, R₁₀, R₁₁ and R₁₅ are hydrogen, R₇, R₉, R₁₂ and R₁₄ are phenyl and R₈ and R₁₃ is eicosanoxy.

In another preferred embodiment, the transition metal complex comprises a ligand according to formula
15 (I), wherein R₁-R₅ are hydrogen, R₆, R₁₀, R₁₁ and R₁₅ are hydrogen, R₇, R₉, R₁₂ and R₁₄ are phenyl and R₈ and R₁₃ is eicosanoxy.

In another preferred embodiment, the transition metal complex comprises a ligand according to formula
20 (I), wherein R₁-R₃ are hydrogen, R₄ and R₅ are phenyl, R₆, R₁₀, R₁₁ and R₁₅ are hydrogen, R₇, R₉, R₁₂ and R₁₄ are phenyl and R₈ and R₁₃ is eicosanoxy.

In another preferred embodiment, the transition metal complex comprises a ligand according to formula
25 (I), wherein R₁-R₃ are hydrogen, R₄ and R₅ are methyl, R₆ is tert-butyl, R₇, R₈, R₉, R₁₀, R₁₁ and R₁₅ are hydrogen, R₁₂ and R₁₄ are phenyl and R₁₃ is eicosanoxy.

In another preferred embodiment, the transition metal complex comprises a ligand according to formula
30 (I), wherein R₁-R₅ are hydrogen, R₆ is tert-butyl, R₇,

R₈, R₉, R₁₀, R₁₁ and R₁₅ are hydrogen, R₁₂ and R₁₄ are phenyl and R₁₃ is eicosanoxy.

In another preferred embodiment, the transition metal complex comprises a ligand according to formula (I), wherein R₁ - R₃ are hydrogen, R₄ and R₅ are phenyl, R₆ is tert-butyl, R₇, R₈, R₉, R₁₀, R₁₁ and R₁₅ are hydrogen, R₁₂ and R₁₄ are phenyl and R₁₃ is eicosanoxy.

In another preferred embodiment, the transition metal complex comprises a ligand according to formula (I), wherein R₁-R₃ are hydrogen, R₄ and R₅ are methyl, R₇, and R₉ are iso-propyl, R₆, R₈, R₁₀, R₁₁ and R₁₅ are hydrogen, R₁₂ and R₁₄ are phenyl and R₁₃ is eicosanoxy.

In another preferred embodiment, the transition metal complex comprises a ligand according to formula (I), wherein R₁ - R₅ are hydrogen, R₇, and R₉ are iso-propyl, R₆, R₈, R₁₀, R₁₁ and R₁₅ are hydrogen, R₁₂ and R₁₄ are phenyl and R₁₃ is eicosanoxy.

In another preferred embodiment, the transition metal complex comprises a ligand according to formula (I), wherein R₁-R₃ are hydrogen, R₄ and R₅ are phenyl, R₇, and R₉ are iso-propyl, R₆, R₈, R₁₀, R₁₁ and R₁₅ are hydrogen, R₁₂ and R₁₄ are phenyl and R₁₃ is eicosanoxy.

In another preferred embodiment, the transition metal complex comprises a ligand according to formula (I), wherein R₁-R₃ are hydrogen, R₄ and R₅ are methyl, R₇ is iso-propyl, R₁₀ is methyl, R₆, R₉, R₁₁ and R₁₅ are hydrogen, R₁₂ and R₁₄ are phenyl and R₈ and R₁₃ is eicosanoxy.

In another preferred embodiment, the transition metal complex comprises a ligand according to formula

(I), wherein R₁ - R₅ are hydrogen, R₇ is iso-propyl, R₁₀ is methyl, R₆, R₉, R₁₁ and R₁₅ are hydrogen, R₁₂ and R₁₄ are phenyl and R₈ and R₁₃ is eicosanoxy.

5 In another preferred embodiment, the transition metal complex comprises a ligand according to formula (I), wherein R₁-R₃ are hydrogen, R₄ and R₅ are phenyl, R₇ is iso-propyl, R₁₀ is methyl, R₆, R₉, R₁₁ and R₁₅ are hydrogen, R₁₂ and R₁₄ are phenyl and R₈ and R₁₃ is eicosanoxy.

10 In another preferred embodiment, the transition metal complex comprises a ligand according to formula (I), wherein R₁-R₃ are hydrogen, R₄ and R₅ are methyl, R₆, R₈ and R₁₀ are methyl, R₇, R₉, R₁₁ and R₁₅ are hydrogen, R₁₂ and R₁₄ are fluorine and R₁₃ is eicosanoxy.

15 In another preferred embodiment, the transition metal complex comprises a ligand according to formula (I), wherein R₁-R₅ are hydrogen, R₆, R₈ and R₁₀ are methyl, R₇, R₉, R₁₁ and R₁₅ are hydrogen, R₁₂ and R₁₄ are fluorine and R₁₃ is eicosanoxy.

20 In another preferred embodiment, the transition metal complex comprises a ligand according to formula (I), wherein R₁-R₃ are hydrogen, R₄ and R₅ are phenyl, R₆, R₈ and R₁₀ are methyl, R₇, R₉, R₁₁ and R₁₅ are hydrogen, R₁₂ and R₁₄ are fluorine and R₁₃ is eicosanoxy.

25 In another preferred embodiment, the transition metal complex comprises a ligand according to formula (I), wherein R₁-R₃ are hydrogen, R₄ and R₅ are methyl, R₆, R₈ and R₁₀ are methyl, R₇, R₉, R₁₁ and R₁₅ are hydrogen, R₁₂ and R₁₄ are chlorine and R₁₃ is eicosanoxy.

In another preferred embodiment, the transition metal complex comprises a ligand according to formula (I), wherein R₁-R₅ are hydrogen, R₆, R₈ and R₁₀ are methyl, R₇, R₉, R₁₁ and R₁₅ are hydrogen, R₁₂ and R₁₄ are chlorine and R₁₃ is eicosanoxy.

In another preferred embodiment, the transition metal complex comprises a ligand according to formula (I), wherein R₁-R₃ are hydrogen, R₄ and R₅ are phenyl, R₆, R₈ and R₁₀ are methyl, R₇, R₉, R₁₁ and R₁₅ are hydrogen, R₁₂ and R₁₄ are chlorine and R₁₃ is eicosanoxy.

In another preferred embodiment, the transition metal complex comprises a ligand according to formula (I), wherein R₁-R₃ are hydrogen, R₄ and R₅ are methyl, R₆, R₁₀, R₁₁ and R₁₅ are hydrogen, R₇, R₉, R₁₂ and R₁₄ are fluorine and R₈ and R₁₃ is eicosanoxy.

In another preferred embodiment, the transition metal complex comprises a ligand according to formula (I), wherein R₁-R₅ are hydrogen, R₆, R₁₀, R₁₁ and R₁₅ are hydrogen, R₇, R₉, R₁₂ and R₁₄ are fluorine and R₈ and R₁₃ is eicosanoxy.

In another preferred embodiment, the transition metal complex comprises a ligand according to formula (I), wherein R₁-R₃ are hydrogen, R₄ and R₅ are phenyl, R₆, R₁₀, R₁₁ and R₁₅ are hydrogen, R₇, R₉, R₁₂ and R₁₄ are fluorine and R₈ and R₁₃ is eicosanoxy.

In another preferred embodiment, the transition metal complex comprises a ligand according to formula (I), wherein R₁-R₃ are hydrogen, R₄ and R₅ are methyl, R₆, R₁₀, R₁₁ and R₁₅ are hydrogen, R₇, R₉, R₁₂ and R₁₄ are chlorine and R₈ and R₁₃ is eicosanoxy.

In another preferred embodiment, the transition metal complex comprises a ligand according to formula (I), wherein R₁-R₅ are hydrogen, R₆, R₁₀, R₁₁ and R₁₅ are hydrogen, R₇, R₉, R₁₂ and R₁₄ are chlorine and R₈ and R₁₃ is eicosanoxy.

In another preferred embodiment, the transition metal complex comprises a ligand according to formula (I), wherein R₁ - R₃ are hydrogen, R₄ and R₅ are phenyl, R₆, R₁₀, R₁₁ and R₁₅ are hydrogen, R₇, R₉, R₁₂ and R₁₄ are chlorine and R₈ and R₁₃ is eicosanoxy.

In another preferred embodiment, the transition metal complex comprises a ligand according to formula (I), wherein R₁ - R₃ are hydrogen, R₄ and R₅ are methyl, R₆, R₉, R₁₂ and R₁₅ are hydrogen, R₇ and R₁₄ are iso-propyl, R₁₀ and R₁₁ are methyl and R₈ and R₁₃ is eicosanoxy.

In another preferred embodiment, the transition metal complex comprises a ligand according to formula (I), wherein R₁-R₅ are hydrogen, R₆, R₉, R₁₂ and R₁₄ are hydrogen, R₇ and R₁₅ are iso-propyl, R₁₀ and R₁₁ are methyl and R₈ and R₁₃ is eicosanoxy.

In another preferred embodiment, the transition metal complex comprises a ligand according to formula (I), wherein R₁-R₃ are hydrogen, R₄ and R₅ are phenyl, R₆, R₉, R₁₂ and R₁₅ are hydrogen, R₇ and R₁₄ are iso-propyl, R₁₀ and R₁₁ are methyl and R₈ and R₁₃ is eicosanoxy.

The present invention also relates to a catalyst system comprising:

(a) one or more transition metal complexes defined herein; and

(b) a co-catalyst compound (1) or (2) as defined and described herein

5 The catalyst system of the present invention may also comprise one or more additional co-catalyst compounds as optional component (c).

 The purpose of co-catalyst compound(s) (b) is to form an activated catalyst system.

10 A co-catalyst compound capable of abstracting an anion (X^- group) and transferring an optionally substituted hydrocarbyl or hydride group to the transition metal atom (M), preferably at a temperature in the range of -100°C to $+300^\circ\text{C}$, is selected from
15 alkylaluminium compounds such as alkylaluminumoxane and alkylaluminium halides. Preferred compounds of this type are methylaluminumoxane (MAO) and modified methylaluminumoxane (MMAO).

 A co-catalyst compound capable of transferring an
20 optionally substituted hydrocarbyl or hydride group to the transition metal atom (M), preferably at a temperature in the range of -100°C to $+300^\circ\text{C}$, is selected from alkylaluminium compounds such as alkyl aluminumoxanes, alkyl lithium compounds, Grignards, alkyl tin and alkyl
25 zinc compounds, such as compounds of the formula ZnR'_2 wherein each R' , which may be the same or different, is selected from hydrogen, optionally substituted $\text{C}_1\text{-C}_{20}$ hydrocarbyl, phenyl, Cl, Br, I, SR'' , NR''_2 , OH, OR'' , CN, NC (isocyanide) wherein R'' , which within the same
30 molecule may be the same or different, is $\text{C}_1\text{-C}_{20}$ hydrocarbyl. Preferably, R' is $\text{C}_1\text{-C}_{20}$ hydrocarbyl, more

preferably C₁-C₂₀ alkyl, even more preferably C₁-C₆ alkyl. Suitable alkyl groups include methyl, ethyl, propyl, butyl, and the like. It is especially preferred that the R' group is a C₁-C₃ alkyl, especially ethyl.

5 Preferred compound of this type are methylaluminoxane (MAO) and modified methylaluminoxane (MMAO).

A co-catalyst compound capable of abstracting an anion (X⁻ group) from the transition metal atom (M), preferably at a temperature in the range of -100°C to
10 +300°C, is selected from strong neutral Lewis acids such as SbF₅, BF₃ and Ar₃B, wherein Ar is a strong electron-withdrawing aryl group such as C₆F₅ or 3,5-(CF₃)₂C₆H₃ or from salts with non-coordinating anions (NC⁻) such as tetrakis [3,5-bis(trifluoromethyl)-phenyl]borate (BArF⁻),
15 (C₆F₅)₄B⁻, and anions of alkylaluminium compounds including R₃AlX'⁻, R₂AlClX'⁻, RAlCl₂X'⁻, and "RAlOX'⁻", wherein R is hydrogen, optionally substituted hydrocarbyl or an inert functional group, and X' is halide, alkoxide or oxygen. A preferred salt with a non-coordinating anion
20 for use herein is sodium tetrakis [3,5-bis(trifluoromethyl)-phenyl]borate (Na⁺ BArF⁻).

Additional co-catalyst compounds (c), which may be used in addition to co-catalyst compound(s) (b), include, but are not necessarily limited to, neutral Lewis donor
25 molecules.

The term "neutral Lewis donor molecule" as used in herein means a compound which may suitably act as a Lewis base, such as ethers, amines, sulphides and organic nitriles, for example, triethylamine or 2,6-di-tert-butylpyridine.
30

The ligands and transition metal complexes of the present invention may be prepared using the chemical processes and equivalent processes to those illustrated in the examples of the present invention and the
5 references therein, as well as the processes known from WO01/58874, WO02/00339, WO02/28805 and WO 03/011876 and the references incorporated therein.

The catalyst system of the present invention may be formed by mixing together the transition metal complex or
10 a mixture of a transition metal salt and the appropriate bis-arylimine pyridine ligand of formula (I), co-catalyst compound(s) (b), and optionally one or more additional co-catalyst compounds (c), in any order.

Conveniently, the preparation of the catalyst system
15 of the present invention may be performed in the presence of the reaction mixture or in the presence of a chemically inert solvent which may be polar or non-polar. Preferably, the catalyst system of the present invention is prepared in the presence of the reaction mixture or in
20 the presence of a chemically inert non-polar solvent, more preferably in the presence of a chemically inert non-polar solvent.

The use of a chemically inert non-polar solvent in the preparation of the catalyst system of the present
25 invention may be desired for ease of handling, storage and use of the catalyst system, in particular for accurate dosing of the catalyst composition, especially during continuously operated reaction processes. Examples of suitable chemically inert non-polar solvents
30 include o-,m- or p-xylene, toluene, benzene, pentane, isopentane, heptane, cyclohexane and isooctane, preferably the solvent is toluene, isopentane,

- 42 -

cyclohexane and isooctane, especially toluene and isooctane.

In one embodiment, the catalyst system of the present invention is formed by combining a solution of the transition metal complex dissolved in a chemically inert non-polar solvent with a solution of the co-catalyst compound(s) (b) and optionally additional co-catalyst compound(s) (c) in a chemically inert non-polar solvent. The combining of these two separate solutions may be performed either in the presence or the absence of the reactant composition.

Alternatively, the catalyst system of the present invention is formed by combining a solution comprising a mixture of a transition metal salt and a bis-arylimine pyridine ligand of formula (I) dissolved in a chemically inert non-polar solvent with a solution of the co-catalyst compound(s) (b) and optionally additional co-catalyst compound(s) (c) in a chemically inert non-polar solvent. The combining of these two separate solutions may be performed either in the presence or the absence of the reactant composition.

In another embodiment, the catalyst system of the present invention is formed by combining a solution of the transition metal bis-arylimine pyridine complex in a chemically inert non-polar solvent, with the co-catalyst compound(s) (b) and optionally additional co-catalyst compound(s) (c), which are present in the reaction media.

Alternatively, the catalyst system of the present invention is formed by combining a mixture of a transition metal salt and a bis-arylimine pyridine ligand of formula (I) in a chemically inert non-polar solvent, with the co-catalyst compound(s) (b) and optionally

additional co-catalyst compound(s) (c) which are present in the reaction media.

In another embodiment, the catalyst system of the present invention is prepared by combining all the components of the catalyst system in a chemically inert non-polar solvent.

In another embodiment, the catalyst system of the present invention is prepared by combining all the components of the catalyst system in the reaction media.

The bis-arylimine ligands of formula (I), the transition metal complexes, and the catalyst systems of the present invention are highly soluble in non-polar media, such as non-polar solvents, non-polar reactant compositions and non-polar product compositions.

By the term "highly soluble", it is meant that the specific component (e.g. bis-arylimine pyridine ligand or bis-arylimine pyridine transition metal complex) will form a clear and stable solution in non-polar media at ambient temperatures. Preferably, it is meant that the component has a solubility of at least 1 mg ml⁻¹, e.g. at least 5 mg ml⁻¹, more preferably a solubility of at least 10 mg ml⁻¹, e.g. at least 25 mg ml⁻¹, most preferably at least 50 mg ml⁻¹ e.g. at least 75 mg ml⁻¹, especially at least 100 mg ml⁻¹, at ambient temperatures. Typically, the solubility of the components will be less than 5 g ml⁻¹.

The term "clear and stable solution" in the context of the present invention, means a solution having dissolved particles with diameters between 0.1 and 1 nm, which cannot be made visual by microscopic or ultramicroscopic techniques and cannot be separated by

(ultra) filtration or dialysis, or a colloidal solution, having particles with diameters between 0.1 and 0.001 μm , which do not show sedimentation.

In the context of the present invention, the term
5 "ambient temperatures" means any temperature or temperature range within the range wherein the lower temperature is at least $-20\text{ }^{\circ}\text{C}$, more preferably at least $0\text{ }^{\circ}\text{C}$ and most preferably at least $10\text{ }^{\circ}\text{C}$, and the upper temperature is at most $120\text{ }^{\circ}\text{C}$, more preferably at most 50
10 $^{\circ}\text{C}$ and most preferably at most $40\text{ }^{\circ}\text{C}$.

The solution of the invention is in a non-polar medium e.g. a chemically inert non-polar solvent. The solubility of the specific component (e.g. the bis-arylimine pyridine ligand, bis-arylimine pyridine
15 transition metal complex or catalyst system comprising it) is as described particularly above, preferably at least 5, 10 or 25 mg ml^{-1} , such as at least 50 or 75 mg ml^{-1} , especially at least 100 mg ml^{-1} . Examples of the non-polar media are given herein, while classes of the
20 chemically inert non-polar solvents are the inert solvents that may be used for the co-oligomerization or oligomerization mentioned herein, namely alkanes (e.g. of 5-8 carbon atoms), alkenes (e.g. of 5-8 carbon atoms especially 1-hexene, cis/trans 2-hexene or 1-octene),
25 cycloalkanes (e.g. of 5-7 carbon atoms) and aromatic hydrocarbons (e.g. of 6-8 carbon atoms), and more particularly those named above as chemically inert non polar solvents, especially toluene, benzene or a xylene.

Examples of non-polar reactant compositions include
30 alpha olefin compositions, such as ethylene, propylene and $\text{C}_4\text{-C}_{12}$ linear and branched alpha olefins, which may optionally include impurities such as internal olefins,

such as C₄-C₁₂ linear and branched internal olefins, C₂-C₁₂ paraffins and the like. The non-polar product compositions are the resultant compositions produced from the polymerization, co-polymerization, oligomerization, co-oligomerization or dimerization or alpha-olefins using the catalyst system of the present invention, and may optionally include unreacted feed olefin.

The catalyst systems of the present invention are particularly useful when incorporated in the following reactions:

polymerization or oligomerization;
co-polymerization or co-oligomerization;
trimerization; and
dimerization.

The catalyst systems of the present invention are particularly useful for the polymerization or oligomerization of ethylene, the co-polymerization or co-oligomerization of ethylene and an alpha-olefin, and the dimerization of alpha-olefins having at least 3 carbon atoms under continuous process conditions.

In one preferred process of the present invention, the catalyst system of the present invention is employed for the oligomerization of ethylene.

In another preferred process of the present invention, the catalyst system of the present invention is employed in the dimerization of alpha-olefins.

The catalyst system of the present invention can be used for polymerization and oligomerization reactions when ethylene or propene is used as the feed olefin.

The term "feed olefin" used in the context of the present invention relates to the repeating unit(s) which may combine when brought into contact with the catalyst

system of the present invention under polymerization, co-polymerization, oligomerization, co-oligomerization, trimerization or dimerization conditions.

5 The catalyst systems of the present invention can be used for co-polymerization and co-oligomerization reactions when ethylene and an alpha-olefin having at least 3 carbon atoms are used as the feed olefins, or propene and an alpha-olefin having at least 4 carbon atoms are used as the feed olefin.

10 The catalyst systems of the present invention can be used for dimerization reactions when an alpha-olefin having at least 3 carbon atoms is used as the feed olefin, especially the dimerization of 1-butene (e.g. present in Raffinate II) to octene.

15 The dimerization reaction of the present invention includes the formation of dimers of more than one alpha-olefin having at least 3 carbon atoms, wherein the alpha-olefins in the feed olefin do not have the same number of carbon atoms.

20 When propene is used as the feed olefin in the dimerization reaction of the present invention, the dimer product olefin may be an alpha-olefin. If an alpha-olefin is produced in the dimerization of propene, the alpha-olefin product olefin may subsequently be dimerized
25 by another propene feed olefin, which may result in the formation of another alpha-olefin dimer product which may subsequently be dimerized, or the alpha-olefin produced in the dimerization of propene may dimerize with any other alpha-olefin present, which is not propene, and
30 form an internal olefin product which can not be dimerized further.

A preferred feed olefin used in the co-polymerization, co-oligomerization and dimerization reactions is an alpha-olefin which has at least 4 carbon atoms. The feed olefin used for the co-polymerization, co-oligomerization and dimerization reactions preferably has at most 20 carbon atoms, more preferably at most 12 carbon atoms, most preferably at most 8 carbon atoms and especially at most 6 carbon atoms. The feed olefin of the present invention can be linear or branched. Preferably the feed olefin is linear. Preferably, the feed olefin used in the co-polymerization, co-oligomerization and dimerization reactions of the present invention is selected from propene, 1-butene, 1-pentene and 1-hexene, and mixtures thereof.

The feed olefins used in the co-polymerization, co-oligomerization and dimerization reactions of the present invention may form part of a reactant composition. Said reactant composition may optionally comprise other linear or branched alpha-olefins, linear or branched internal olefins, linear or branched paraffins and other chemically inert components such as solvents.

In one embodiment of the present invention, the feed olefin composition is an olefin composition which comprises a distillation fraction of an olefin composition, comprising alpha-olefins, internal olefins and paraffins boiling in the same temperature range, for example a raffinate II composition which is primarily composed of 1-butene and 2-butene.

The oligomerization and/or co-oligomerization reactions of the present invention may be conveniently carried out using the following conditions.

A quantity of the catalyst system of the present invention is usually employed in the oligomerization or co-oligomerization reaction mixture so as to contain from 10^{-4} to 10^{-9} gram atom of transition metal atom M per mole of ethylene or ethylene and α -olefin feed olefin having at least 3 carbon atoms mixture to be reacted.

The oligomerization or co-oligomerization reaction may be most conveniently conducted over a range of temperatures from -100°C to $+300^{\circ}\text{C}$, preferably in the range of from 0°C to 200°C , and more preferably in the range of from 50°C to 150°C .

The oligomerization or co-oligomerization reaction may be conveniently carried out at a pressure of 0.01 to 15 MPa (0.1 to 150 bar(a)), more preferably 1 to 10 MPa (10 to 100 bar(a)), and most preferably 1.5 to 5 MPa (15 to 50 bar(a)).

The optimum conditions of temperature and pressure used for a particular catalyst system to maximise the yield of oligomer or co-oligomer, and to minimise the competing reactions such as dimerization and polymerization can be readily established by one skilled in the art.

The conditions of temperature and pressure are preferably selected to yield a product slate with a Schulz-Flory K-factor within the range of from 0.40 to 0.90, most preferably in the range of from 0.60 to 0.80. In the present invention, polymerization is deemed to have occurred when a product slate has a K-factor greater than 0.9.

The oligomerization or co-oligomerization reaction can be carried out in the gas phase or liquid phase, or

- 49 -

mixed gas-liquid phase, depending upon the volatility of the feed olefin and product olefins.

5 The oligomerization or co-oligomerization reaction may be carried out in the presence of an inert solvent which may also be the carrier for the catalyst and/or feed olefin. Suitable solvents include alkanes, alkenes, cycloalkanes, and aromatic hydrocarbons. For example, solvents that may be suitably used according to the present invention include heptane, isooctane,
10 cyclohexane, benzene, toluene, and xylene.

Reaction times of from 0.1 to 10 hours have been found to be suitable, dependent on the activity of the catalyst. The reaction is preferably carried out in the absence of air or moisture.

15 The oligomerization or co-oligomerization reaction may be carried out in a conventional fashion. It may be carried out in a stirred tank reactor, wherein olefin and catalyst or catalyst precursors are added continuously to a stirred tank and the feed olefin, product olefin,
20 catalyst, and catalyst are removed from the stirred tank with the product separated and the unused feed olefin and optionally the catalyst recycled back to the stirred tank.

Alternatively, the reaction may be carried out in a
25 batch reactor, wherein the catalyst precursors or catalyst system, and feed olefin are charged to an autoclave, and after being reacted for an appropriate time, product is separated from the reaction mixture by conventional means, such as distillation.

30 After a suitable reaction time, the oligomerization or co-oligomerization reaction can be terminated by rapid

- 50 -

venting of the ethylene in order to deactivate the catalyst system.

The resulting alpha olefins have a chain length of from 4 to 100 carbon atoms, preferably 4 to 30 carbon atoms, and most preferably from 4 to 20 carbon atoms.

Product olefins can be recovered, suitably by distillation, and further separated as desired by distillation techniques dependent on the intended end use of the olefins.

The soluble transition metal complexes and compositions thereof of the type described herein, have been found to be particularly useful in dimerization of alpha-olefins having 3 carbon atoms or more, the co-oligomerization of said alpha olefin and ethylene and in the oligomerization of ethylene, in each case particularly, with the transition metal complexes and catalyst systems in solution, especially in aromatic hydrocarbon solvents such as toluene.

In the transition metal complexes used in the above dimerization reaction, the R₁-R₁₅ substituents on the bis-arylimine ligand of formula (I), X and NC⁻ are as defined hereinabove.

In preferred transition metal complexes used in the dimerization reaction of the present invention, M is selected from any Group 4 to Group 10 transition metal. In one embodiment of the dimerization process of the present invention, M is selected from Ti, V, Cr, Mn, Fe, Co, Ni, Pd or Pt; more preferably V, Cr, Mn, Fe, Co, Ni or Pd; especially Fe, Co or Cr.

In another embodiment of the dimerization process of the present invention, M is selected from Ti, V, Cr, Mn, Ni, Pd, Rh, Ru, Mo, Nb, Zr, Hf, Ta, W, Re, Os, Ir or Pt,

- 51 -

preferably Ti, V, Cr, Mn, Ni, Pd or Pt, more preferably V, Cr, Mn, Ni or Pd, especially Cr.

In another embodiment of the dimerization process of the present invention, M is selected from Fe or Co.

5 Currently used processes for ethylene oligomerization produce alpha-olefins yields with undesirably large quantities of low molecular weight olefins, which has limited value. In addition, the Fischer-Tropsch process for the production of
10 hydrocarbons produces a certain amount of low value lower olefins, also of limited value (e.g. Raffinate II - a butene composition comprising 1-butene). Therefore processes which convert these fractions into higher value products, such as higher molecular weight linear olefins
15 (e.g. octene) are desired (i.e. dimerization).

The dimerization reactions of the present invention are particularly suitable for any C₃ to C₁₂ alpha-olefin, especially propene, 1-butene, 1-pentene and 1-hexene and compositions containing said alpha-olefins (e.g.
20 Raffinate II which comprises 1-butene and 2-butene).

The dimerization reaction of the present invention may be conveniently carried out using the following conditions.

A quantity of the catalyst system of the present
25 invention is usually employed in the dimerization reaction mixture so as to contain from 10⁻³ to 10⁻⁹ gram atom of transition metal atom M per mole of feed olefin having at least 3 carbon atoms mixture to be reacted.

The dimerization reaction may be most conveniently
30 conducted over a range of temperatures from -100°C to +200°C, preferably in the range of from -50°C to 150°C, more preferably in the range of from -10°C to 120°C, most

preferably from 10°C to 100°C, especially from 20°C to 90°C.

The dimerization reaction may be conveniently carried out at a pressure of 0.01 to 15 MPa (0.1 to 150 bar(a)), more preferably 0.1 to 10 MPa (1 to 100 bar(a)), and most preferably 0.1 to 5 MPa (1 to 50 bar(a)).

The optimum conditions of temperature and pressure used for a particular catalyst system to maximise the yield of linear dimers, and to minimise the competing reactions such as isomerization of the feed olefin can be readily established by one skilled in the art.

The dimerization reaction can be carried out in the gas phase or liquid phase, or mixed gas-liquid phase, depending upon the volatility of the feed olefin and product olefins.

The dimerization reaction may be carried out in the presence of an inert solvent which may also be the carrier for the catalyst system and/or feed olefin. Suitable solvents include alkanes, alkenes, cycloalkanes, and aromatic hydrocarbons. For example, solvents that may be suitably used according to the present invention include heptane, isooctane, cyclohexane, benzene, toluene, and xylene.

Reaction times of from 0.1 to 10 hours have been found to be suitable, dependent on the activity of the catalyst. The reaction is preferably carried out in the absence of air or moisture.

The dimerization reaction may be carried out in a conventional fashion. It may be carried out in a stirred tank reactor, wherein the feed olefin and catalyst system or catalyst precursors are added continuously to a stirred tank and the feed olefin and catalyst system are

removed from the stirred tank with the product olefin, which may then be separated, and optionally the unused feed olefin and/or the catalyst system are recycled back to the stirred tank.

5 Alternatively, the reaction may be carried out in a batch reactor, wherein the catalyst system or the catalyst system precursors, and feed olefin are charged to an autoclave, and after being reacted for an appropriate time, product is separated from the reaction
10 mixture by conventional means, such as distillation.

 After a suitable reaction time, the dimerization reaction can be terminated by exposure of the catalyst composition to air or starving the reaction of feed olefin.

15 The product olefins produced by the dimerization process of the present invention preferably comprise at least 6 carbon atoms and at most 30 carbon atoms, more preferably at most 20 carbon atoms, and most preferably 16 carbon atoms. In one aspect of the dimerization
20 process of the present invention, the product olefin is a linear olefin which comprises from 6 to 12 carbon atoms, preferably hexenes, octenes, decenes and dodecenes, especially octenes.

 Product olefins can be recovered suitably by
25 distillation and further separated as desired by distillation techniques dependent on the intended end use of the olefins.

 The invention is illustrated in the following Examples.

ExamplesGeneral Procedures and Characterisation

All chemicals used in preparations were purchased from Aldrich and used without further purification unless mentioned otherwise.

5 All the operations with the catalyst systems were carried out under nitrogen atmosphere. All solvents used were dried using standard procedures.

Anhydrous toluene (99.8% purity) was dried over 4Å molecular sieves (final water content of about 3 ppm).
10 Isooctane (2,4,4-trimethylpentane, 99.8% purity) was dried by prolonged nitrogen purge, followed by passage over 4Å molecular sieves (final water content of about 1 ppm). Anhydrous heptane (99.8% purity) was dried by passage over 4Å molecular sieves (final water content of
15 about 1 ppm).

Ethylene (99.5% purity) was purified over a column containing 4Å molecular sieves and BTS catalyst (BASF) in order to reduce water and oxygen content to <1 ppm.
Propene (99.0% purity) and 1-butene (grade 2.0, i.e.
20 99.0% purity) were purchased from Hoek Loos N.V., Dieren, The Netherlands, 1-pentene (99% purity) from Aldrich and 1-hexene (>99% purity) from Shell Chemicals were used without further purification.

The oligomers obtained were characterised by Gas
25 Chromatography (GC), in order to evaluate oligomer distribution using a HP 5890 series II apparatus and the following chromatographic conditions:

Column: HP-1 (cross-linked methyl siloxane), film
thickness = 0.25µm, internal diameter = 0.25 mm, length
30 60 m (by Hewlett Packard); injection temperature: 325°C; detection temperature: 325°C; initial temperature: 40°C

- 55 -

for 10 minutes; temperature programme rate:
10.0°C/minute; final temperature: 325°C for 41.5 minutes;
internal standard: n-hexylbenzene.

5 Response factors for the even and odd linear α -
olefins, for the internal hexenes: *cis*- and *trans*-2-
hexene, and *cis*- and *trans*-3-hexene, and for the branched
hexenes: 3-methyl-1-pentene and 2-ethyl-1-butene,
relative to n-hexylbenzene (internal standard) were
determined using a standard calibration mixture. The
10 response factors of the branched and internal heptenes
and dodecenes were assumed to be equal to the
corresponding even and odd linear α -olefins.

15 In case of ethylene oligomerization, the yields of
the C₄-C₃₀ olefins were obtained from the GC analysis,
from which the K-factor and the theoretical yield of C₄-
C₁₀₀ olefins, i.e. total oligomerization product (Total
Product), were determined by regression analysis, using
the C₆-C₂₈ data.

20 In case of oligomerization or dimerization of alpha-
olefins, or co-oligomerization of ethylene and alpha-
olefins, the yields of the branched and internal, even
and odd olefins were determined by the same GC-method.

25 The relative amounts of the linear 1-hexene amongst
all hexene isomers, the relative amount of 1-heptene
amongst all heptene isomers, the relative amount of 1-
decene amongst all decene isomers, and the relative
amount of 1-dodecene amongst all dodecene isomers found
from the GC analysis is used as a measure of the
selectivity of the catalyst towards linear alpha-olefin
30 formation.

- 56 -


The NMR data was obtained at room temperature with a Varian 300 MHz or 400 MHz apparatus.

The practical solubility of the transition metal complexes was determined at ambient temperature in the inert atmosphere of the dry box.

1 mg of solid complex was contacted with 0.5 ml of benzene-D6 in an NMR-tube (5 mm external diameter) and gently swirled. If, after 1 minute of contact between the solid complex and the solvent under swirling or shaking, it does not result in a coloured solution and the solid remains deposited, further solvent is added stepwise to a final volume of 1.0 ml. If the solvent does not become coloured and the solid remains deposited even after stepwise increase of the volume of benzene-D6 to 1.0 ml and standing at ambient temperature for 24 hours, the complex is categorised as having a solubility <1 mg/ml. If the solution becomes coloured and 1 mg of the complex dissolves in about 1 ml of solvent it is categorised as having a solubility of ca. 1 mg/ml. Likewise, for higher solubility of complexes the amount of complex is increased to 10 mg or to 100 mg and the practical solubility is estimated by stepwise (0.1-ml steps) increase of benzene-D6, starting from 0.5 ml. The solubility of the complexes was confirmed in toluene at room temperature, which yielded results similar to that of benzene-D6. The solubility of these transition metal complexes was confirmed by the possibility to measure their NMR-spectra. Deposit formation upon standing for 24 hour and also on some occasions upon centrifugation (at 2500 rpm during 30 minutes) was checked and shown to be absent for the complexes categorized as having a solubility of at least 10 mg/ml.

TRANSITION METAL COMPLEX AND CATALYST PREPARATIONExample 1 (Comparative)

The 2-[1-(2,4,6-trimethylphenylimino) ethyl]-6-[1-(4-*tert*-butylphenylimino)ethyl] pyridine iron[III] chloride complex (1) was prepared according to the method disclosed in WO02/28805 and has the formula below:




(A)

Its solubility in toluene or benzene-D₆ is <1 mg/ml at 20°C.

Example 2 (Comparative)

The 2-[1-(2,4,6-trimethylphenylimino) ethyl]-6-[1-(3,5-di-*tert*-butylphenylimino)ethyl] pyridine iron[III] chloride complex which was prepared according to the method described below:

Preparation of 2-[1-(2,4,6-trimethylphenylimino) ethyl]-6-[1-(3,5-di-*tert*-butylphenylimino)ethyl]pyridine, (B)




(B)

2-[1-(2,4,6-trimethylphenylimino)ethyl]-6-acetylpyridine (1.3 g, 4.64 mmol), prepared according to the method disclosed in WO02/28805, and 3,5-di-*tert*-butylaniline (1 g, 4.87 mmol) were dissolved in 100 ml of toluene. To this solution, 4Å molecular sieves were added. After standing for 2 days the mixture was

filtered. The solvent was removed in vacuo. The residue was washed with methanol and crystallised from ethanol. Yield 1.1 g (51%) of 2-[1-(2,4,6-trimethylphenylimino)ethyl]-6-[1-(3,5-di-tert-butylphenylimino)ethyl]pyridine.

5 $^1\text{H-NMR}$ (CDCl_3) δ 8.43 (d, 1H, Py- H_m), 8.37 (d, 1H, Py- H_m), 7.87 (t, 1H, Py- H_p), 7.16 (t, 1H, ArH), 6.89 (s, 2H, ArH), 6.69 (d, 2H, ArH), 2.42 (s, 3H, Me), 2.29 (s, 3H, Me), 2.22 (s, 3H, Me), 2.01 (s, 6H, Me), 1.33 (s, 18H, Bu^t).

Preparation of 2-[1-(2,4,6-trimethylphenylimino)ethyl]-6-[1-(3,5-di-tert-butylphenylimino)ethyl]pyridine iron[II] chloride complex, (C)



10

(C)

In an inert atmosphere a solution of 400 mg diimine (0.855 mmol) in 20 ml dichloromethane was added to 100 mg FeCl_2 (0.789 mmol) in 30 ml dichloromethane. The mixture was stirred for 16 hours. A small amount of precipitate was removed by centrifugation. Pentane (40 ml) was added to the solution. The blue precipitate was isolated by filtration and dried in vacuo. Yield 0.420 g (90%) of iron complex **C**.

20 $^1\text{H-NMR}$ (Cl_2CDCl_2 , broad signals) δ 78.6 (1H, Py- H_m), 76.8 (1H, Py- H_m), 29.7 (1H, Py- H_p), 20.9 (3H, Me), 18.3 (6H, Me), 15.2 (2H, ArH), 0.7 (18H, Bu^t), -4.1


- 59 -

(3H, MeC=N), -11.5 (1H, ArH), -15.6 (2H, o-ArH), -30.7 (3H, MeC=N).

Its solubility in toluene or benzene-D₆ is estimated at <1 mg/ml at 20°C.


5 Examples 3 - 10

Alternatively, the catalysts used in the experiments below were 2-[1-(2,4,6-trimethylphenylimino) ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl] pyridine iron[III] dichloride complex, 2-[1-(2,4,6-trimethylphenylimino)ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl]pyridine cobalt[II] dichloride complex, 2-[1-(2,4,6-trimethylphenylimino)ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl]pyridine cobalt[III] chloride tetrakis[3,5-bis(trifluoromethyl)phenyl] borate, 2-[1-(2,4,6-trimethylphenylimino) ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl] pyridine chromium[III] trichloride complex, 2,6-bis [1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl]pyridine iron[II] dichloride complex, 2,6-bis[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl]pyridine cobalt[II] dichloride complex, 2,6-bis[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl]pyridine chromium[III] trichloride complex and 2-[1-(2-tert-butylphenylimino)ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl]pyridine cobalt[II] chloride complex, which were prepared according to the methods described below:

Preparation of 4-hydroxy-3,5-diphenylacetanilide

To 4-hydroxy-3,5-diphenylaniline (4 g, 15.3 mmol) in 30 ml of ethanol was added 1.6 ml of acetic anhydride. The reaction was stirred for 16 hours. The resulting mixture was poured into water. The pink product (6 g) was isolated by filtration, washed with water, dried and used without further purification.


$^1\text{H-NMR}$ (CDCl_3 , selected data) δ 5.31(s, OH), 2.16 (s, Me).

Preparation of 4-eicosanoxy-3,5-diphenylacetanilide

A mixture of 4-hydroxy-3,5-diphenylacetanilide (6 g), 1-bromoeicosane and 10 g potassium carbonate was refluxed in acetone (70 ml) for 16 hours. The reaction mixture was poured into water. The product was isolated by filtration, washed with water and dried. Crystallisation from pentane yielded 7.2 g of 4-eicosanoxy-3,5-diphenylacetanilide as a white solid.

$^1\text{H-NMR}$ (CDCl_3 , selected data) δ 3.13(t, CH_2O), 2.17 (s, Me).


- 61 -

Preparation of 4-eicosanoxy-3,5-diphenylaniline

To 4-eicosanoxy-3,5-diphenylacetanilide (7.2 g) was added 24 g NaOH in 30 ml H₂O and 40 ml ethanol. The resulting mixture was refluxed for 16 hours. The reaction mixture was poured on ice. The product was isolated by filtration and washed with water. Crystallisation from ethanol yielded 5.9 g (10.9 mmol) of 4-eicosanoxy-3,5-diphenylaniline as a white solid.

¹H-NMR (CDCl₃) δ 7.27-7.63 (m, 10H, ArH), 6.67 (s, 2H, ArH), 3.60 (br s, 2H, NH₂), 3.09 (t, 2H, CH₂O), 0.8-1.4 (m, 39H, alkyl).

Preparation of 2-[1-(2,4,6-trimethylphenylimino) ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl]pyridine, (D)



(D)

2-[1-(2,4,6-trimethylphenylimino)ethyl]-6-acetylpyridine (3 g, 10.7 mmol), prepared according to the method disclosed in WO02/28805, and 4-eicosanoxy-3,5-diphenylaniline (5.8 g, 10.7 mmol) were dissolved in 200 ml of toluene. To this solution, 4Å molecular sieves were added. After standing for 1 day the mixture was filtered. The solvent was removed in vacuo. The residue was


- 62 -

crystallised from cold ethanol. The product, **D**, was isolated as a yellow treacle (6.5 g, 8.1mmol, 76%) after drying at 60 °C in vacuo.

¹H-NMR (CDCl₃) δ 8.45 (d, 1H, Py-H_m), 8.37 (d, 1H, Py-H_m), 7.89 (t, 1H, Py-H_p), 7.67 (d, 4H, ArH), 7.1-7.5 (m, 16H, ArH), 6.90 (s, 2H, ArH), 6.86 (s, 2H, ArH), 3.19 (t, 2H, CH₂O), 2.51 (s, 3H, Me), 2.29 (s, 3H, Me), 2.22 (s, 3H, Me), 2.01 (s, 6H, Me), 0.8-1.4 (m, 39H, alkyl).

Example 3

Preparation of 2-[1-(2,4,6-trimethylphenylimino) ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl]pyridine iron[III] dichloride complex, (**E**)



(**E**)


In an inert atmosphere a solution of 5 g above-described diimine (**D**) in 20 ml dichloromethane was added to 788 mg FeCl₂ in 30 ml dichloromethane. The mixture was stirred for 16 hours. The solution was filtrated, and the solvent was removed in vacuo. The resulting green blue product was washed with pentane, isolated by filtration and dried in vacuo. Yield 5g (86%) of iron complex **E**.

¹H-NMR (CD₂Cl₂, broad signals, selected data) δ 81.4 (1H, Py-H_m), 80.5 (1H, Py-H_m), 21.1 (3H, Me), 17.3 (6H, Me), 16.0 (2H, ArH), 0.21 (3H, Me), -13.8 (2H, ArH), -30.4 (3H, Me).

Its solubility in toluene or benzene-D₆ is estimated at ca. 50 mg/ml at 20°C.

Example 4

Preparation of 2-[1-(2,4,6-trimethylphenylimino)ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl]pyridine cobalt[II] dichloride complex, (F)



(F)

5

In an inert atmosphere a solution of 1.44 g (1.79 mmol) diimine **D**, (Mes/Sol20), in 10 ml dichloromethane was added to 220 mg CoCl₂ (1.69 mmol) in 10 ml dichloromethane. The mixture was stirred for 16 hours. After filtration the solution was concentrated by removing part of the solvent in vacuo. The product was precipitated from the resulting solution (~5ml) by addition of 15 ml pentane. The yellow brown solid was isolated by centrifugation, washed with pentane and dried in vacuo. Yield 1.25 g (79%) of cobalt complex **F**.

10

15

¹H-NMR (CD₂Cl₂, broad signals, selected data) δ 106.5 (1H, Py-H_m), 105.6 (1H, Py-H_m), 12.8 (1H, Py-H_p), 11.8 (3H, Me), 3.4 (2H), 2.9 (4H), 0.1 (2H), -0.2 (2H), -0.7 (2H), -1.5 (2H), -1.8 (2H), -2.4 (2H), -10.5 (3H, Me), -16.6 (6H, Me), -60.9 (2H, ArH).


20

Its solubility in toluene or benzene-D₆ is estimated at 50 mg/ml at 20°C.

Its solubility in toluene or benzene-D₆ is estimated at ca. 50 mg/ml at 20°C.

Example 4

Preparation of 2-[1-(2,4,6-trimethylphenylimino)ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl]pyridine cobalt[III] dichloride complex, (F)



(F)

5

In an inert atmosphere a solution of 1.44 g (1.79 mmol) diimine **D**, (Mes/Sol20), in 10 ml dichloromethane was added to 220 mg CoCl₂ (1.69 mmol) in 10 ml dichloromethane. The mixture was stirred for 16 hours. After filtration the solution was concentrated by removing a part of the solvent in vacuo. The product was precipitated from the resulting solution (~5ml) by addition of 15 ml pentane. The yellow brown solid was isolated by centrifugation, washed with pentane and dried in vacuo. Yield 1.25 g (79%) of cobalt complex **F**.

10

15

20

¹H-NMR (CD₂Cl₂, broad signals, selected data) δ 106.5 (1H, Py-H_m), 105.6 (1H, Py-H_m), 12.8 (1H, Py-H_p), 11.8 (3H, Me), 3.4 (2H), 2.9 (4H), 0.1 (2H), -0.2 (2H), -0.7 (2H), -1.5 (2H), -1.8 (2H), -2.4 (2H), -10.5 (3H, Me), -16.6 (6H, Me), -60.9 (2H, ArH).

Its solubility in toluene or benzene-D₆ is estimated at 50 mg/ml at 20°C.

Example 5


Preparation of 2-[1-(2,4,6-trimethylphenylimino)ethyl]-
6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl]
pyridine cobalt[III] chloride tetrakis[3,5-
bis(trifluoromethyl)phenyl] borate, (G)

In an inert atmosphere a 313 mg (0.353 mmol) of sodium tetrakis[3,5-bis(trifluoromethyl)phenyl]borate (ABCR GmbH & Co, Karlsruhe, Germany) was added to a solution of 330 mg (0.353 mmol) cobalt complex **F** in 20 ml toluene. The solution was stirred for 1 hour at room temperature. After removing the precipitate by centrifugation, the solvent was removed in vacuo. The resulting oil was washed three times with pentane. After drying in vacuo, the product was isolated as a yellowish solid (560 mg, 90%).

Its solubility in toluene or benzene-D₆ is estimated at ca. 10 mg/ml at 20°C.

Example 6

Preparation of 2-[1-(2,4,6-trimethylphenylimino) ethyl]-
6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl]
pyridine chromium[III] trichloride complex, (H)

**(H)**


In an inert atmosphere a solution of 439 mg (0.54 mmol) diimine **D** in 10 ml dichloromethane was added to 195 mg (0.52 mmol) chromium[III] chloride tetrahydrofuran complex, CrCl₃(THF)₃ in 10 ml dichloromethane. The mixture was stirred for 4 hours. The solution was

filtrated. The solution was concentrated (5ml) by removing solvent vacuo. Pentane (20 ml) was added. The resulting green precipitate was washed with pentane and dried in vacuo. Yield 0.4g (80%) of the chromium complex,

5 **H.**

Its solubility in toluene or benzene-D₆ is estimated at ca. 1 mg/ml at 20°C.

Preparation of 2,6-bis[1-(4-eicosanoxy-3,5-diphenylphenylimino) ethyl]pyridine, (**J**)



(**J**)

10

Diacetylpyridine (1.43 g, 8.77 mmol) and 4-eicosanoxy-3,5-diphenylaniline (9.5 g, 17.53 mmol) were dissolved in 400 ml of toluene. To this solution, 4Å molecular sieves were added. After standing for 1 week, further 4Å molecular sieves were added and the mixture was filtered. Most of the solvent was removed in vacuo. On standing a red precipitate was formed. The product, **J**, was isolated (5.52 g, 51%).


15

¹H-NMR (CDCl₃) δ 8.35 (d, 2H, Py-H_m), 7.88 (t, 1H, Py-H_p), 7.66 (d, 8H, ArH), 7.3-7.5 (m, 12H, ArH), 6.86 (s, 4H, ArH), 3.19 (t, 4H, CH₂O), 2.50 (s, 6H, Me), 0.8-1.4 (m, 39H, alkyl).

20

Example 7

Preparation of 2,6-bis[1-(4-eicosanoxy-3,5-diphenylphenylimino) ethyl]pyridine iron[II] dichloride complex, (K)

**(K)**


In an inert atmosphere a solution of 4g (3.3 mmol) diimine **J** in 20 ml dichloromethane was added to 419 mg (3.3 mmol) FeCl₂ in 20 ml dichloromethane. The mixture was stirred for 48 hours. The purple blue solution was filtrated. The solvent was removed in vacuo. The resulting dark oily product was washed with pentane and dried in vacuo. Yield 3.5g (79%) of the iron complex **K**.

¹H-NMR (C₆D₆, broad signals, selected data) δ 70.5 (2H, Py-H_m), -13.4 (4H, ArH), -26.2 (6H, Me).

Its solubility in toluene or benzene-D₆ is estimated at ca. 100 mg/ml at 20°C.

Example 8

Preparation of 2,6-bis[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl]pyridine cobalt[III] dichloride complex, (L)

**(L)**


In an inert atmosphere a solution of 40 mg (33 μ mol) diimine **J** in 2 ml dichloromethane was added to 4 mg CoCl_2 . The mixture was stirred for 5 hours. The solution was filtrated. The solvent was removed in vacuo. The product was washed with pentane and dried in vacuo. Yield 25 mg of the cobalt complex **L**.

$^1\text{H-NMR}$ (C_6D_6 , broad signals, selected data) δ 103 (2H, Py- H_m), -10 (6H, Me), -50 (4H, ArH).

Its solubility in toluene or benzene- D_6 is estimated at ca. 100 mg/ml at 20°C.

Example 9

Preparation of 2,6-bis[1-(4-eicosanoxy-3,5-diphenylphenylimino) ethyl]pyridine chromium[III] trichloride complex, (**M**)




(**M**)

In an inert atmosphere a solution of 0.84 g (0.92 mmol) diimine **J** in 10 ml dichloromethane was added to 0.25 g (0.66 mmol) $\text{CrCl}_3(\text{THF})_3$ in 10 ml dichloromethane. The mixture was stirred for 4 hours. The solution was filtrated. The solution was concentrated (5ml) by removing solvent vacuo. Pentane (20 ml) was added. The resulting green precipitate was washed with pentane and dried in vacuo. Yield 0.6g (84%) of the chromium complex **M**.

Its solubility in toluene or benzene- D_6 is estimated at ca. 50 mg/ml at 20°C.

Preparation of 2-[1-(2-tert-butylphenylimino)ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl]pyridine, (N)




(N)

2-[1-(2-tert-butylphenylimino)ethyl]-6-acetylpyridine (487 mg, 1.65 mmol), prepared according to the method described in WO 02/28805, and 4-eicosanoxy-3,5-diphenylaniline (900 mg, 1.65 mmol) were dissolved in 50 ml of toluene. To this solution, 4Å molecular sieves were added. After standing for 1 day the mixture was filtered. The solvent was removed in vacuo. The residue was crystallised from ethanol. The product **N** was isolated as an yellow solid (600 mg, 0.73 mmol, 44%).

¹H-NMR (CDCl₃) δ 8.38 (dd, 2H, Py-H_m), 7.90 (t, 1H, Py-H_p), 6.5-7.7 (m, 16H, ArH), 3.21 (t, 2H, CH₂O), 2.52 (s, 3H, Me), 2.40 (s, 3H, Me), 1.37 (s, 9H, t-Bu), 0.8-1.35 (m, 39H, alkyl).

Example 10

Preparation of 2-[1-(2-tert-butylphenylimino)ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl]pyridine cobalt[III] chloride complex, (O)




In an inert atmosphere a solution of 300 mg (0.365 mmol) diimine **N** in 10 ml dichloromethane was added to 40 mg CoCl_2 (0.308 mmol) in 5 ml dichloromethane. The mixture was stirred for 16 hours. After filtration the solution was concentrated by removing part of the solvent in vacuo. The product formed a jelly after addition of 10 ml pentane to the resulting solution (~2ml). A yellowish brown solid was isolated by centrifugation, washing with pentane and drying in vacuo. Yield 234 mg (80%) of the cobalt complex **O**.

$^1\text{H-NMR}$ (C_6D_6 , broad signals, selected data) δ 113 (1H, Py- H_m), 112 (1H, Py- H_m), 18 (1H, Py- H_p), -10.8 (9H, t-Bu), -56.0 (2H, ArH), -85.6 (1H, ArH).

Its solubility in toluene or benzene- D_6 is estimated at ca. 50 mg/ml at 20°C.

Example 11 (Comparative)


Preparation of 4-hydroxy-2-methylacetanilide



5.0 g (40.6 mmol) 4-hydroxy-2-methylaniline was taken up in 120 ml ethanol to give a cloudy, pale orange suspension. To the stirred mixture was added dropwise 4.0


ml (4.3 g, 42.3 mmol) acetic anhydride, causing the suspension to dissolve. The solution was left stirring overnight. All volatiles were subsequently removed under reduced pressure at 80 °C, followed by rapid washing with 100 ml water, followed by drying under vacuum. 3.85 g (58 % yield) light brown solid recovered.

Preparation of 4-eicosanoxy-2-methylaniline



1.51 g (9.1 mmol) 4-hydroxy-2-methylacetanilide was dissolved in 100 ml acetone. To this was added 6.54 g (45 mmol, 5 eq.) potassium carbonate, and the resulting suspension stirred vigorously. To this was added 3.65 g (10.1 mmol) 1-bromoeicosane, and the reaction mixture was then heated to reflux for 22 hours. After cooling to room temperature, 500 ml deionised water was added and the solution stirred vigorously. The suspension was filtered under vacuum, and the white solid formed was dried under vacuum at 75 °C overnight. 3.72 g of the product (a white powder) was recovered (92 % yield).


Preparation of 4-eicosanoxy-2-methylaniline



9.22 g (0.02 mol) 4-eicosanoxy-2-methylacetanilide was slurried in a solution of 18.3 g (0.45 mol) sodium hydroxide in 30 ml water and 40 ml ethanol. Under

stirring it was heated to reflux and kept refluxing for 40 hours. The resulting two-phase liquid system was cooled and poured over 500 ml crushed ice, and stirred. Filtration of the white solid product and washing with 2
 5 × 25 ml deionised water afforded a product, which was dried in the vacuum oven (5.4 g, 67 % yield).


Preparation of 2,6-bis[1-(4-eicosanoxy-2-methylphenylimino)ethyl]pyridine



10.0 g (25 mmol) 4-eicosanoxy-2-methylaniline was reacted under stirring with 2.3 g (14 mmol) 2,6-
 10 diacetylpyridine in the presence of 29 g 4Å molecular sieves in 250 ml of refluxing toluene for 20 h. Subsequently the compound was filtered while hot, and volatiles removed from residue under reduced pressure. It
 15 was then washed with hot ethanol (300 ml) to give a yellow solid, which was dried in the vacuum oven (9.1 g, 69 % yield).

¹H-NMR (CDCl₃ after dissolving by heating) δ 8.37 (d, 2H, Py-H_m), 7.86 (t, 1H, Py-H_p), 6.82 (d, 2H, ArH), 6.75 (dd, 2H, ArH), 6.61 (d, 2H, ArH), 3.95 (t, 4H, CH₂O), 2.36 (s, 6H, Me), 2.12 (s, 6H, Me), 1.78 (m, 4H),
 20 1.0-1.6 (m, 68H), 0.88 (t, 6H, Me).

Preparation of 2,6-bis[1-(4-eicosanoxy-2-methylphenylimino)ethyl]pyridine iron[III] chloride complex




110 mg (0.12 mmol) 2,6-bis[1-(4-eicosanoxy-2-methylphenylimino)ethyl]pyridine was reacted under stirring with 35 mg (0.28 mmol) FeCl₂ in 10 ml dichloromethane in the dry box for 16 hours at ambient temperature. The resulting green suspension was centrifuged, and the supernatant decanted. Volatiles were then removed under reduced pressure to afford a green powder (54 mg, 42 % yield).

¹H-NMR (CD₂Cl₂, broad signals, selected data) δ 78.2 (2H, Py-H_M), 39 and 31 (1H, Py-H_P), 19.5 and 16.8 (6H, MeAr), 40.9 and 41.2 (2H, ArH), -22.7 and -26.1 (6H, Me).

Its solubility in toluene or benzene-D₆ is estimated at <1 mg/ml at 20°C.

Example 12

Preparation of 2,6-bis[1-(2-methyl-4-eicosanoxy-5-isopropylphenylimino)ethyl]pyridine




The title compound was prepared by condensation of 2-methyl-4-eicosanoxy-5-isopropylaniline with 2,6-

diacetylpyridine in the presence of 4Å molecular sieves in refluxing toluene for 20 hours, similarly to the preparation of 2,6-bis[1-(4-eicosanoxy-2-methylphenylimino)ethyl]pyridine, described above.

5 To that end 2-methyl-4-hydroxy-5-isopropylaniline (available from Specs, Delftechpark 30, 2628 XH Delft, The Netherlands) was converted to 2-methyl-4-eicosanoxy-5-isopropylaniline by acetylation of the amino group, followed by alkylation of the hydroxy group by reaction
10 with 1-bromoeicosane and finally by removal of the acetyl group of amide functional group, similarly to the above-described preparation of 4-eicosanoxy-2-methylaniline.

$^1\text{H-NMR}$ (CDCl_3) δ 8.38 (d, 2H, Py- H_m), 7.85 (t, 1H, Py- H_p), 6.72 (s, 2H, ArH), 6.56 (s, 2H, ArH), 3.95 (t, 4H, CH_2O), 3.15 (m, 2H, CH), 2.36 (s, 6H, Me), 2.11 (s, 6H, Me), 1.78 (m, 4H), 1.2-1.6 (m), 1.2 (d, Me), 0.88 (t, 6H, Me).

Preparation of 2,6-bis[1-(2-methyl-4-eicosanoxy-5-isopropylphenylimino)ethyl]pyridine iron (II) dichloride



20 The iron complex was prepared from 2,6-bis[1-(2-methyl-4-eicosanoxy-5-isopropylphenylimino)ethyl]pyridine and FeCl_2 in dichloromethane.


$^1\text{H-NMR}$ (CD_2Cl_2 , broad signals, selected data) δ 75.9 (2H, Py- H_m), 42.0 and 41.2 (1H, Py- H_p), 21.3 and 20.2 (6H, MeAr), -12.4 and -20.9, (2H, ArH), -26.0 (6H, Me).

After removing the CD_2Cl_2 the product is soluble in C_6D_6 : ^1H -NMR (very broad signals, selected data) δ 65 (Py- H_m), 23 (MeAr), -37 (Me).

5 Its solubility in toluene or benzene- D_6 is estimated at ca. 10 mg/ml at 20°C .

Example 13 (Comparative)


Preparation of 4-propoxy-3,5-diphenylacetanilide



10 A mixture of 4-hydroxy-3,5-diphenylacetanilide (3.45g), 1-bromopropane (1.4g) and 4.8 g potassium carbonate was refluxed in acetone (50 ml) for 16 hours. The reaction mixture was poured into water. The product was isolated by filtration, washed with water and dried. Yield 3.8 g of 4-propoxy-3,5-diphenylacetanilide.

15 ^1H -NMR (CDCl_3) δ 7.1-7.7(m, ArH) 3.10(t, 2H, CH_2O), 2.14 (s, Me), 1.16 (m, 2H, CH_2), 0.49 (t, 3H, Me).

Preparation of 4-propoxy-3,5-diphenylaniline




20 To 4-propoxy-3,5-diphenylacetanilide (3.8 g) was added 22.5 g NaOH in 30 ml H_2O and 40 ml ethanol. The resulting mixture was refluxed for 16 hours. The reaction

mixture was poured on ice. The product was isolated as an oil after washing with water.

¹H-NMR (CDCl₃) δ 7.3-7.7 (m, 10H, ArH), 6.68 (s, 2H, ArH), 3.61 (br s, 2H, NH₂), 3.06 (t, 2H, CH₂O), 1.13 (m, 2H, CH₂), 0.48 (t, 3H, Me).


Preparation of 2-[1-(2,4,6-trimethylphenylimino)ethyl]-6-[1-(4-propoxy-3,5-diphenylphenylimino)ethyl]pyridine



2-[1-(2,4,6-trimethylphenylimino)ethyl]-6-acetylpyridine (387 mg, 1.38 mmol) and 4-propoxy-3,5-diphenylaniline (440 mg, 1.45 mmol) were dissolved in 50 ml of toluene. To this solution, 4Å molecular sieves were added. After standing for 1 day the mixture was filtered. The solvent was removed in vacuo. The residue was crystallised from cold ethanol. The product was isolated as a yellow treacle (700 mg) and used as such.

¹H-NMR (CDCl₃) δ 8.45 (d, 1H, Py-H_m), 8.37 (d, 1H, Py-H_m), 7.89 (t, 1H, Py-H_p), 7.68 (d, 4H, ArH), 7.1-7.5 (m, 16H, ArH), 6.90 (s, 2H, ArH), 6.87 (s, 2H, ArH), 3.17 (t, 2H, CH₂O), 2.52 (s, 3H, Me), 2.30 (s, 3H, Me), 2.23 (s, 3H, Me), 2.02 (s, 6H, Me), 1.20 (m, 2H, CH₂), 0.54 (t, 3H, Me).

Preparation of 2-[1-(2,4,6-trimethylphenylimino)ethyl]-6-[1-(4-propoxy-3,5-diphenylphenylimino)ethyl]pyridine cobalt[II] chloride complex




In an inert atmosphere a solution of 675 mg diimine in 20 ml dichloromethane was added to 140 mg CoCl_2 in 10 ml dichloromethane. The mixture was stirred for 16 hours. The solution was filtrated. The solvent was removed in vacuo. The resulting brown product was washed with pentane, isolated by filtration and dried in vacuo. Yield 700 mg of cobalt complex.

$^1\text{H-NMR}$ (CD_2Cl_2 , broad signals, selected data) δ 103.0 (1H, Py- H_m), 98.5 (1H, Py- H_m), -18.1 (6H, ArMe), -62.8 (2H, ArH).

Its solubility in toluene or benzene- D_6 is estimated at <1 mg/ml at 20°C.

Example 14 (Comparative)

Preparation of 2-[1-(2,4,6-trimethylphenylimino)ethyl]-6-[1-(4-hydroxy-3,5-diphenylphenylimino)ethyl]pyridine




The title compound was prepared by condensation of 4-hydroxy-3,5-diphenylaniline with 2-[1-(2,4,6-trimethylphenylimino)ethyl]-6-acetylpyridine, prepared according to the method disclosed in W002/28805, in toluene, using 4Å molecular sieves, similarly to the

above-described preparation of 2-[1-(2,4,6-trimethylphenylimino)ethyl]-6-[1-(4-propoxy-3,5-diphenylphenylimino)ethyl]pyridine.

¹H-NMR (CD₂Cl₂) δ 8.43 (d, 1H, Py-H_m), 8.35 (d, 1H, Py-H_m), 7.90 (t, 1H, Py-H_p), 7.62 (d, 4H, ArH), 7.50 (t, 4H, ArH), 7.42 (m, 2H, ArH), 6.89 (s, 2H, ArH), 6.83 (s, 2H, ArH), 2.52 (s, 3H, Me), 2.28 (s, 3H, Me), 2.21 (s, 3H, Me), 1.98 (s, 6H, Me).

Preparation of 2-[1-(2,4,6-trimethylphenylimino)ethyl]-6-[1-(4-hydroxy-3,5-diphenylphenylimino)ethyl]pyridine iron (II) dichloride



10

The iron complex was prepared from 2-[1-(2,4,6-trimethylphenylimino)ethyl]-6-[1-(4-hydroxy-3,5-diphenylphenylimino)ethyl]pyridine and FeCl₂ in dichloromethane.

15

¹H-NMR (CD₂Cl₂, broad signals, selected data) δ 82.6 (1H, Py-H_m), 82.3 (1H, Py-H_m), 21.0 (3H, Me), 18.5 (6H, Me), -4.0 (3H, Me), -18 (2H, ArH), -31.3 (3H, Ar).

Its solubility in toluene or benzene-D₆ is estimated at <1 mg/ml at 20°C.

20

Co-catalysts

The first co-catalyst compound used in the dimerization or oligomerization experiments below was sodium tetrakis[3,5-bis(trifluoromethyl)phenyl]borate

(NaBArF) purchased from ABCR GmbH & Co in Karlsruhe, Germany and was used as such to transform the soluble transition metal pyridine-diimine catalyst precursor to a cationic transition metal catalyst complex, either by
5 separate preparation as described above or by in-situ preparation just prior to addition of an aluminium alkyl or aluminoxane.

The second or solely applied co-catalyst used in the experiments below was selected from:

10 modified methyl aluminoxane (MMAO) wherein about 25% of the methyl groups are replaced with isobutyl groups. MMAO-3A in heptane ([Al] = 6.42%wt), available from AKZO-NOBEL Chemicals B.V., Amersfoort, The Netherlands;

15 methyl aluminoxane (MAO) in toluene, supplied under the tradename Eurecen AL 5100/10T, batch: B7683; [Al] = 4.88%wt, TMA = 35.7 wt%(calculated), molecular mass = 900 g/mol and [Al] = 4.97% wt) supplied by Witco GmbH, Bergkamen, Germany; and

20 trimethylsilylmethyl lithium, $\text{Me}_3\text{SiCH}_2\text{Li}$, 1.0 M solution in pentane from Aldrich.

Examples 15 - 23

Catalyst system preparation for (co)-oligomerization in a batch autoclave

In a Braun MB 200-G dry box the transition metal complex, 2-[1-(2,4,6-trimethylphenylimino)ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl] pyridine iron
25 [II] chloride complex, 2,6-bis[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl]pyridine chromium [III] trichloride or 2,6-bis[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl]pyridine iron [II] dichloride
30 (typically about 22.5 μmol) in the presence or absence of an approximately equimolar amount of sodium tetrakis[3,5-

bis[trifluoromethyl]phenyl] borate (NaBArF) (see Table 1), was placed in a glass bottle and sealed by a septum. Toluene (typically about 10 ml) was added. Part of these solutions were used in the oligomerization reaction.

5 Ethylene (co)-oligomerizations in a 0.5-litre batch autoclave

Oligomerization experiments were performed in a 0.5 litre steel autoclave equipped with jacket cooling with a heating/cooling bath (ex. Julabo, model no. ATS-2) and a turbine/gas stirrer and baffles.

In order to remove traces of water from the reactor, it was evacuated overnight at <10 Pa, and 70°C. The reactor was scavenged by introducing 250 ml toluene, MAO (0.3 g solution) and subsequent stirring at 70°C under nitrogen pressure of 0.4–0.5 MPa for 30 min. The reactor contents were discharged via a tap in the base of the autoclave. The reactor was evacuated to 0.4 kPa and loaded with approximately 125 ml 1-butene and/or 1-pentene and/or toluene (see Table 1), heated to 40 °C and pressurised with ethylene to the pressure indicated in Table 1.

Whilst stirring, an amount of MAO-solution (see Table 1) was added to the reactor with the aid of toluene (the total volume injected was 12 ml: the MAO-solution diluted with toluene to 4 ml was injected and the injector system was rinsed twice with 4 ml toluene) and the stirring at 800 rpm was continued for 30 minutes.

0.20 µmol of the catalyst system prepared as described above was introduced into the stirred reactor using an injection system with the aid of toluene (the total volume injected was 12 ml: the catalyst solution diluted with toluene to 4 ml was injected and the

injector system was rinsed twice with 4 ml toluene). The initial loading of the reactor was about 150 ml alpha-olefin and/or toluene.

5 The addition of the catalyst system resulted in an exotherm (generally some 5°C), which generally reached a maximum within 1 minute and was followed by establishment of the temperature and pressure indicated in Table 1.

10 After consuming the desired volume of ethylene, the oligomerization was stopped by rapid venting of the ethylene, decanting the product mixture into a collection bottle using a tap in the base of the autoclave. Exposure of the mixture to air resulted in rapid deactivation of the catalyst.

15 After addition of n-hexylbenzene (0.5-3.5 g) as internal standard to the crude product, the amount of the C₄-C₃₀ olefins and purity of C₆, C₁₀ and C₁₂ olefins was determined by gas chromatography. The Schulz-Flory K-factor and its standard error were determined from the amounts of C₆-C₂₈ olefins by regression analysis, as
20 described in detail in WO 01/58874. From the Schulz-Flory K-factor the total amount of C₄-C₁₀₀ olefins is calculated to compensate for losses in particularly the volatile 1-butene during product isolation. The experimental data is reported in Table 1.

25 In the case of using chromium catalysts a similarly equipped 1-litre steel autoclave has been used, loaded (similarly to the above-described procedure for the 0.5-litre autoclave) with 300 ml of toluene, a MAO-solution and also n-hexylbenzene (as an internal standard), at the
30 start of the (co)-oligomerization or (co)-polymerization reaction and subsequently maintained at the conditions, described in Table 1.

After consuming the desired amount of ethylene the reactor was rapidly cooled to room temperature to minimise evaporation of the volatile products, particularly the butenes. The reaction was stopped by rapid venting of the ethylene and decanting the product mixture into a collection bottle using a tap in the base of the autoclave. Exposure of the mixture to air resulted in rapid deactivation of the catalyst. Since the reactions with ethylene have been carried out in the presence of an internal standard (n-hexylbenzene) and the products have been analysed by the above-described gas chromatographic (GC) method immediately after their isolation, a more reliable amount of the volatile butenes can be established without having to use regression analysis of the higher olefins, a method which can be used in the case of a Schulz-Flory distribution of olefins.

The experimental data is provided in Table 1 below.

TABLE 1: Ethylene (co)-oligomerizations in a 0.5-litre autoclave using soluble
2-[1-(2,4,6-trimethylphenylimino)ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)
ethyl]pyridine iron [II] catalyst systems (at 0.20 μmol Fe[II]) or similar soluble
transition metal catalyst systems.

Example No. (* = comparative example)	Co-catalyst		Process Conditions		Productivity			Distribution	AO Selectivity		
	NaBARF μmol (eq)	MAO μmol (eq)	Temp $^{\circ}\text{C}$	Pressure bar(a)	Yield C ₄ -C ₁₀₀ (GC) g	Final [AO] %wt	TON (TON on Al) $\text{molC}_2^-/\text{molM}$		1-C ₆ %wt	1C ₁₀ %wt	1-C ₁₂ %wt
Example 15*	0 (0)	305 (1502)	70	16	53.7	31.1	9.4*E+06 (6300)	0.67 (0.01)	99.5	98.4	97.8
Example 16	0.211 (1.06)	303 (1515)	70	16	52.4	30.9	9.3*E+06 (6200)	0.68 (0.01)	99.6	98.5	98.0
Example 17	0.201 (1.05)	195 (970)	70	16	18.0	12.8	3.2*E+06 (3300)	0.67 (0.01)	99.8	99.4	99.1
Example 18 a)	0 (0)	1200 (621)	70	13	45.8 (incl. PE = 70mg)	16	0.90*E+06	b)	30.4 b)	b)	
Example 19 a)	2.12 (1.06)	1210 (605)	70	16	19.9 (incl. PE = 3.3g)	7	0.36*E+06	c)	50.6 c)	c)	
Example 20* just ethene	0 (0)	(2100)	50	7	103.2	46	12.5*E+06	0.73 (0.03)	98.8 d)	96.8 d)	95.9 d)

Example 21 e)	0 (0)	(2000)	50	7	Even: 80.2 Odd: 51.9	68	12.7*E+06	Even: 0.68 (0.04) Odd: 0.66 (0.03)	97.7 f) 66.0 g)	92.0 f) g)	90.6 f) g)
Example 22 h)	0 (0)	(2000)	50	7	106.8	67	12.4*E+06	0.71 (0.05)	90.0 i)	85.0 i)	85.0 i)
Example 23 j)	0 (0)	(2400)	50	7	33.2	80	3.5*E+06	0.15 (0.16)	39.0 k)	16.8 k)	n.d.

- a) Ethylene oligomerization using 2.0 μmol 2,6-bis[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl]pyridine chromium [III] trichloride in 1-litre autoclave, initially loaded with 300 ml toluene, MAO and n-hexylbenzene (ISTD).
- b) Largely dimerization: butenes = 92.8wt (consisting of 1-butene = 97.5, trans 2-butene = 1.5 and cis 2-butene = 1.1wt); hexenes = 7.0wt (consisting of 1-hexene = 30.4, 3-methyl-1-pentene = 1.4, 2-ethyl-1-butene = 64.2 and internal hexenes = 3.4wt), decenes <0.1wt and polyethylene (PE) <0.2wt (on total product, including polyethylene).
- c) Largely dimerization: butenes = 70.5wt (consisting of 1-butene = 97.7, trans 2-butene = 1.4 and cis 2-butene 1.0wt); hexenes = 9.0wt (consisting of 1-hexene = 50.6, 3-methyl-1-pentene = 0.9, 2-ethyl-1-butene = 46.0 and internal hexenes = 2.6wt), decenes = 1.1wt and polyethylene (PE) = 16.4wt (on total product, including polyethylene).
- d) Hexenes: 1-hexene = 98.8, 3-methyl-1-pentene = 0.9, 2-ethyl-1-butene = 0.1 and internal hexenes = 0.2wt; branched C₁₀ = 2.9, internal C₁₀ = 0.3, branched C₁₂ = 3.9 and internal C₁₂ = 0.1wt.
- e) Co-oligomerization of 1-pentene and ethylene using 150 ml of 1-pentene/toluene in a ratio of 1.04 v/v, instead of toluene and 30 μmol 2-[1-(2,4,6-trimethylphenylimino)ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl]pyridine iron [II] dichloride.

- f) Hexenes: 1-hexene = 97.7, 3-methyl-1-pentene = 1.6, 2-ethyl-1-butene = 0.2 and internal hexenes = 0.4wt; branched C₁₀ = 6.8, internal C₁₀ = 1.3, branched C₁₂ = 8.5 and internal C₁₂ = 0.9wt.
- g) Heptenes: 1-heptene = 66.0, 3-methyl-1-hexene = 29.2 and 2-ethyl-1-pentene = 3.8, internal heptenes = 1.1wt; 1-nonene = 56.8, 1-undecene = 61.6 and 1-tridecene = 58.8wt.
- h) Co-oligomerization of 1-butene and ethylene using 150 ml of 1-butene/toluene in a ratio of 0.79 v/v, instead of toluene and 30 μ mol 2-[1-(2,4,6-trimethylphenylimino)ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl]pyridine iron [II] dichloride.
- i) Hexenes: 1-hexene = 90.0, 3-methyl-1-pentene = 8.3, 2-ethyl-1-butene = 0.2 and internal hexenes = 1.3wt; branched C₁₀ = 12.8, internal C₁₀ = 2.2, branched C₁₂ = 14.1 and internal C₁₂ = 0.9wt.
- j) Co-oligomerization of 1-butene and ethylene using 150 ml of 1-butene/toluene in a ratio of 6.67 v/v, instead of toluene and 34 μ mol 2,6-bis[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl]pyridine iron [II] dichloride.
- k) Hexenes: 1-hexene = 39.0, 3-methyl-1-pentene = 3.3, 2-ethyl-1-butene = 36.2 and internal hexenes = 19.0wt; branched C₁₀ = 77.0 and internal C₁₀ = 6.2wt.

Upon replacing a minute quantity (approximately 1.05 equivalents based on moles of transition metal, or about 0.21 μmol) of the MAO co-catalyst (generally present in about 300 μmol) with a transition metal complex cation
5 generating compound, such as sodium tetrakis[3,5-bis[trifluoromethyl]phenyl] borate (NaBArF), the selectivity towards linear alpha olefins (as measured by the %wt 1-C₆⁼, 1-C₁₀⁼ and 1-C₁₂⁼ of the respective C₆, C₁₀ and C₁₂ fractions) is at least on a par with the
10 experiments performed in the absence of NaBArF (see examples 15 - 17).

On addition of NaBArF, the selectivity towards linear alpha olefins based upon the total olefin yield remains at least on a par with that of the experiments
15 without NaBArF addition, as is clear from the yield of C₄-C₁₀₀ oligomers and the turnover number (TON = the amount of moles of ethylene converted per mol of Fe) (see examples 15 and 16).

The Schulz-Flory K-factor and its standard error²³
20 remain the same for the experiments performed both in the presence and the absence of NaBArF. The standard error, which is a measure for deviation from a genuine Schulz-Flory distribution, described in WO 01/58874, is very low, indicating that no tail of heavy olefins (C₃₀-C₁₀₀)
25 are being formed in either case.

It can also be seen that use of a reduced amount of MAO co-catalyst with NaBArF does not detrimentally affect the selectivity of the catalyst towards linear alpha-olefins (see examples 15 - 17).

30 Another advantage of the soluble transition metal catalyst precursors is that by using transition metal complex cation generating compounds, such as NaBArF,

alternative compounds capable of transferring a hydrocarbyl or hydride group to MAO or MMAO can be employed easily, such as any suitable compounds known to those skilled in the art, for example RLi , R_2Zn or R_3Al .

5 The ethylene oligomerization and/or polymerization, using soluble Cr[III] catalysts in the presence or absence of NaBARf are also summarised in Table 1 (examples 18 and 19). It is noted that in the absence of NaBARf the soluble chromium complex gives rise to largely
10 dimer formation (1-butene >90%wt of the total product) at a turnover number (TON) about one order of magnitude lower than for similar Fe[II] catalysts. The 1-hexene content of the hexenes is low (30.4%wt); the predominant product being 2-ethyl-1-butene. A small amount (70 mg) of
15 polyethylene (PE) is formed as well (in two repeat experiments the amounts of PE were 31 and 91 mg, respectively, whereas the relative amount of dimers remained constant).

 In the presence of 1 equivalent of NaBARf the same
20 Cr[III] complex also gave largely dimer formation (1-butene is 69%wt of the total product) at a somewhat lower TON. The 1-hexene content of the hexenes was higher (50.6%wt); a large by-product also being 2-ethyl-1-butene. Furthermore, a large amount (3.3 g; 16.4%wt) of
25 high molecular weight polyethylene (PE) is formed. Differential Scanning Calorimetry (DSC) of the PE showed a melting point of 127°C . Upon repeat of the experiment the product contained less (12.4%wt) high molecular weight polymer (DSC m.p. = 129°C).

30 The co-oligomerization of α -olefins, such as 1-pentene and 1-butene, and ethylene, using soluble Fe[II] catalysts in the presence or absence of NaBARf are summarised in Table 1 (examples 20 - 23). In example 21,

39%wt of the product consists of odd-numbered olefins, which indicates that 1-pentene is co-oligomerised under the conditions employed.

Upon the use of the symmetrical soluble Fe[II] catalyst **K** (Example 23), a catalyst with a low k-factor (low propagation) the product spectrum was surprisingly different from that of catalyst **E**. Contrary to the catalyst systems comprising iron complex **E**, when catalyst systems comprising the symmetrical iron complex **K** are used, a relatively large amount of 1-butene undergoes 1,2-insertion into iron-ethyl, believed to be leading to 2-ethyl-1-butene formation.

Examples 24 - 31

Catalyst system preparation for dimerization in a batch autoclave

In a Braun MB 200-G dry box, the 2-[1-(2,4,6-trimethylphenylimino)ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl]pyridine cobalt[III] chloride tetrakis[3,5-bis(trifluoromethyl)phenyl] borate, the 2-[1-(2,4,6-trimethylphenylimino)ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl]pyridine cobalt[III] dichloride complex or the 2-[1-(2-tert-butylphenylimino)ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl]pyridine cobalt[III] dichloride complex, in the presence or absence of an approximately equimolar amount of sodium tetrakis[3,5-bis(trifluoromethyl)phenyl] borate (NaBArF) (typically about 50 μmol - see Table 2), was placed in a glass bottle sealed by a septum. Toluene (typically about 10 ml) was added. The resulting mixture was stirred for at least a half of hour. Part of these

solutions were used in the dimerization experiments below.

Alpha-olefin dimerizations in a 0.5-litre batch autoclave

The dimerization experiments were performed in a 0.5 litre steel autoclave equipped with jacket cooling with a heating/cooling bath (ex. Julabo, model no. ATS-2) and a turbine/gas stirrer and baffles.

In order to avoid traces of water, the reactor was kept under nitrogen pressure (0.5 MPa) at room temperature. Prior the experiment the reactor was scavenged by introducing 250 ml toluene, MAO (0.3 g solution) and subsequent stirring at 70°C under nitrogen pressure of 0.5-0.6 MPa for 30 min. The reactor contents were discharged via a tap in the base of the autoclave. The reactor was evacuated to 0.4 kPa and cooled to 20°C. After which it was loaded with 120 ml 1-butene (grade 2.0, Hoek Loos) and the reactor was heated to 30°C.

Under stirring, the MAO-solution (minimum 210 mg) was then added to the reactor with the aid of toluene (the MAO-solution was injected, the injector was subsequently rinsed twice, bringing the total volume injected was 10 ml) and the stirring at 800 rpm was continued for 60 minutes.

The required amount (50 μmol) of the catalyst solution, preparation of which is described above, was introduced into the stirred reactor using an injection system, after that the injector was rinsed three times with 3-4 ml toluene (total contents of reactor 150 ml).

The addition of the catalyst system resulted in a small exotherm (generally 3-8°C), which was easily absorbed by the thermostat bath, bringing the reactor back to the initial conditions.

After about 2 hours, the experiment was stopped by decanting the product mixture into a collection bottle using a tap in the base of the autoclave. Exposure of the mixture to air resulted in rapid deactivation of the catalyst.

After addition of n-hexylbenzene (0.5-3.5 g), as internal standard, to the crude product, the amount and purity of C₄, C₈ and C₁₂ olefins was determined by gas chromatography.

The results of the alpha olefin, mainly 1-butene, dimerization experiments are given in Table 2 and in the detailed descriptions below.

On one occasion 1-pentene was used in a small-scale dimerization experiment at ambient temperature and pressure in a nitrogen atmosphere in a stirred vessel in the dry box (see Table 2, example 30 and the detailed description of the Example 30). Activation (by alkylation) of the cationic cobalt complex, can also be achieved in-situ by stepwise activation of the cobalt cationic complex by 1 equivalent of NaBARf, followed by addition of 1 equivalent of trimethylsilylmethyl lithium, Me₃SiCH₂Li, instead of MAO or MMAO. This demonstrates that the catalyst can be activated without MAO or MMAO.

Example 30 (see Table 2): Reaction of 1-pentene catalysed by an activated cationic Co[III] complex G

In an inert atmosphere (in dry box) in a stirred vessel at ambient temperature, 1-pentene (4.6 g; 65.7 mmol) was dimerised to a mixture of linear cis and trans 3-decene and 4-decene (2.8%wt 2-propyl-1-heptene is the main branched impurity), using 11.3 µmol cationic Co[III] catalyst, 2-[1-(2,4,6-trimethylphenylimino)ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl]pyridine cobalt[III] chloride tetrakis[3,5-

bis[trifluoromethyl)phenyl] borate, activated by addition of 1 equivalent of $\text{Me}_3\text{SiCH}_2\text{Li}$ (alkylation), instead of MAO. 1-Pentene was converted to linear cis/trans 3-decenes and 4-decenes (2.8%wt 2-propyl-1-heptene is the
5 main branched impurity) and cis/trans 2-pentene in about equal amounts. The results are summarised in Table 2.

The products were analysed by GC and NMR and the results are given in Table 2.

TABLE 2: Alpha olefin dimerization experiments in 0.5-litre autoclave using soluble 2-[1-(2,4,6-trimethylphenylimino)ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl]pyridine cobalt[III] catalyst systems (at 50 μ mol cobalt[III]) or similar soluble transition metal catalyst systems.

Example No. (* = comparative example)	Co-catalyst		Process Conditions		Productivity			TON (Al) $\frac{2 \times \text{mol C}_8}{\text{mol Al}}$	TON (Co) $\frac{2 \times \text{mol C}_8}{\text{mol Co}}$	Selectivity	$\frac{\text{Linear } 2+3-\text{C}_8}{2-\text{C}_4} = \frac{\text{on all C}_8}{\text{C}_8}, \text{ \%wt}$	$\frac{2+3-\text{C}_8}{2-\text{C}_4} = \frac{\text{(Dimers)}}{\text{(Isomers)}} \text{ g/g}$
	NaBARF $\mu\text{mol (eq)}$	(M)MAO $\mu\text{mol (eq)}$	Temp °C	Press bar (a)	Yield C ₈ -C ₃₂ (GC) g	Conversion of C ₄ to C ₈ %						
Example 24* (Lit) a)	0	~6500 (~600)	30	-	26.0	19	36000	<50	85	71	-	
Example 25* (Lit) b)	0	10600 (500)	30	-	153	50.2	10500	200	82	70	>20 b)	
Example 26* (Lit) c)	0	26500 (500)	30	-	96.7	39	32000	65	99	97	0.70	
Example 27* d)	0	25018 (502)	30	3.0	15.1	22.4	5300	11	99	92	0.46	
Example 28	48.8 (1.00)	487 (10)	30	3.4	19.5	29.0	7100	710	>99	97	0.96	
Example 29	53.0 (1.04)	1205 (24)	30	3.0	25.7	38.2	9000	380	>99	96	0.97	
Example 30 e)	11.3 (1.0)	e)	20	1	1.2 e)	26 e)	1500 e)	1500 e)	>99 e)	97 e)	e)	

Example 31 f)	48.0 (1.04)	1146 (24)	30	3.0	12.0	17.8	4400	185	99	98	3.24
------------------	----------------	--------------	----	-----	------	------	------	-----	----	----	------

- a) Using 10.9 μmol 2,6-bis[1-(2-methylphenylimino)ethyl]pyridine iron[II] chloride complex and MAO according to B.L. Small, E.J Baralt, A.J. Marcucci, US 6,291,733 B1 of 18th September 2001.
- b) Using 21.2 μmol 2,6-bis[1-(2-methylphenylimino)ethyl]pyridine iron[II] chloride complex and MAO according to B.L. Small, Organometallics 2003, 22, 3178-3183; in this case the dimer/isomer ratio is replaced by the oligomer/isomer ratio.
- c) Using 53.1 μmol 2,6-bis[1-(2-methylphenylimino)ethyl]pyridine cobalt[II] chloride complex and MAO according to B.L. Small, Organometallics 2003, 22, 3178-3183.
- d) In a preceeding experiment it was observed that stepwise addition of MAO (1200-16000 μmol), followed by an additional 17 μmol soluble Co[II] catalyst precursor did not initiate dimerization; dimerization only started after addition to this system of 4.6 μmol of the cationic Co[II] catalyst system, 2-[1-(2,4,6-trimethylphenylimino)ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino) ethyl]pyridine cobalt[II] chloride tetrakis[3,5-bis(trifluoromethyl)phenyl] borate.
- e) On a small scale, using 1-pentene and 2-[1-(2,4,6-trimethylphenylimino)ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino) ethyl]pyridine cobalt[II] chloride tetrakis[3,5-bis(trifluoromethyl)phenyl] borate (cationic Co[II] complex), activated by addition of 1 equivalent of $\text{Me}_3\text{SiCH}_2\text{Li}$ (alkylation), instead of MAO. 1-Pentene was converted to linear cis/trans 3- and 4-decenes (2.8%wt 2-propyl-1-heptene is the main branched impurity) and cis/trans 2-pentene in about equal amounts.
- f) Using 48 μmol of the alternate toluene-soluble Co [II] catalyst system, derived from the 2-[1-(2-tert-butylphenylimino)ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino) ethyl]pyridine cobalt[II] dichloride complex, (o).


From these examples it is clear that upon the use of soluble cationic transition metal complexes, which are formed by stepwise activation of the neutral transition metal complex by addition of a stoichiometric amount of NaBARF, subsequently followed by activation with a relatively small amount of MAO or MMAO, a higher TON on aluminium (MAO) is obtained in comparison to a transition metal complex activated MAO or MMAO alone (see Examples 26 and 28). The soluble Co[II] catalysts have a selectivity to dimers relative to higher oligomers, which is on a par with the non-soluble catalysts described in the literature (see Table 2, Example 29 and comparative Example 26). The same is true for the head-to-head dimerization selectivity, which affords linear dimers. It is noted that selectivities towards linear dimer formation are much higher for Co[II] catalysts than for Fe[II].

We have surprisingly found that the use of a soluble cobalt[III] cationic catalyst, either prepared separately or prepared *in-situ*, enhances the selectivity towards dimers over that of double bond shift (isomerisation), in comparison with the Co[II] catalysts activated by addition of a large excess of MMAO as described in the literature (see Table 2, examples 26, 28 and 29).

Use of the soluble catalyst system derived from 2-[1-(2-*tert*-butylphenylimino)ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl]pyridine cobalt[III] dichloride complex (**0**) by *in-situ* addition of 1 equivalent of NaBARF (Table 2, example 31), results in a significantly higher selectivity towards linear dimer formation (less isomerisation of 1-butene to 2-butenes) compared to the Co[II] catalyst of Example 26, which is described in the literature.

C L A I M S

1. A transition metal complex which is a bis-arylimine pyridine MX_n complex, comprising a bis-arylimine pyridine ligand having the formula (I) below:



(I)

5
wherein R_1 - R_5 , R_7 - R_9 , R_{12} and R_{14} are each,
independently, hydrogen, optionally substituted
hydrocarbyl, an inert functional group, or any two of
 R_1 - R_3 and R_7 - R_9 vicinal to one another taken together may
10 form a ring, and R_6 is hydrogen, optionally substituted
hydrocarbyl, an inert functional group, or taken together
with R_7 or R_4 to form a ring, R_{10} is hydrogen, optionally
substituted hydrocarbyl, an inert functional group, or
taken together with R_9 or R_4 to form a ring, R_{11} is
15 hydrogen, optionally substituted hydrocarbyl, an inert
functional group, or taken together with R_{12} or R_5 to
form a ring, R_{15} is hydrogen, optionally substituted
hydrocarbyl, an inert functional group, or taken together
with R_{14} or R_5 to form a ring, provided that R_{13} and at
20 least one of R_{12} and R_{14} are independently selected from
optionally substituted C_1 - C_{30} alkyl, optionally

substituted C₄-C₃₀ alkyloxy, halogen and optionally substituted C₅-C₂₀ aryl, or R₁₃ taken together with R₁₂ or R₁₄ form a ring, or R₁₂ taken together with R₁₁ form a ring and R₁₄ taken together with R₁₅ form a ring, and
5 provided that at least one of R₁₂, R₁₃ and R₁₄ is optionally substituted C₄-C₃₀ alkyloxy;

M is a transition metal atom selected from Ti, V, Cr, Mn, Ni, Pd, Rh, Ru, Mo, Nb, Zr, Hf, Ta, W, Re, Os, Ir or Pt;

10 n matches the formal oxidation state of the transition metal atom M; and

X is halide, optionally substituted hydrocarbyl, alkoxide, amide, or hydride.

2. A transition metal complex which is a
15 [bis-arylimine pyridine MX_p⁺][NC⁻]_q complex, comprising a bis-arylimine pyridine ligand, X and M each as defined in claim 1

NC⁻ is a non-coordinating anion; and

p + q matches the formal oxidation state of the
20 transition metal atom M.

3. A transition metal complex according to claim 1 or 2, wherein R₁₂, R₁₃ and R₁₄ are all independently selected from optionally substituted C₁-C₃₀ alkyl, optionally substituted C₄-C₃₀ alkyloxy and optionally
25 substituted C₅-C₂₀ aryl with the proviso that at least one of R₁₂, R₁₃ and R₁₄ is optionally substituted C₄-C₃₀ alkyloxy.

4. A transition metal complex according to claim 1 or 2, wherein R₁₃ and at least one of R₁₂ and R₁₄ are
30 independently selected from optionally substituted C₃-C₂₅

alkyl, optionally substituted C₄-C₃₀ alkyloxy and optionally substituted C₅-C₆ aryl with the proviso that at least one of R₁₂, R₁₃ and R₁₄ is optionally substituted C₄-C₃₀ alkyloxy.

5 5. A transition metal complex according to any one of claims 1 to 4, wherein R₈ and at least one of R₇ and R₉ are independently selected from optionally substituted C₁-C₃₀ alkyl, optionally substituted C₄-C₃₀ alkyloxy, halogen and optionally substituted C₅-C₂₀ aryl, or R₈
10 taken together with R₇ or R₉ form a ring, or R₇ taken together with R₆ form a ring and R₉ taken together with R₁₀ form a ring with the proviso that at least one of R₇, R₈ and R₉ is optionally substituted C₄-C₃₀ alkyloxy.

15 6. A transition metal complex according to any one of claims 1 to 4 wherein R₇, R₈ and R₉ are all independently selected from optionally substituted C₁-C₃₀ alkyl, optionally substituted C₄-C₃₀ alkyloxy and optionally substituted C₅-C₂₀ aryl with the proviso that at least one of R₇, R₈ and R₉ is optionally substituted C₄-C₃₀
20 alkyloxy.

7. A transition metal complex according to claim 5, wherein R₈ and at least one of R₇ and R₉ are independently selected from optionally substituted C₃-C₂₅ alkyl, optionally substituted C₄-C₃₀ alkyloxy and
25 optionally substituted C₅-C₆ aryl with the proviso that at least one of R₇, R₈ and R₉ is optionally substituted C₄-C₃₀ alkyloxy.

8. A transition metal complex according to any one of claims 1 to 7 wherein said optionally substituted C₄-30 alkyloxy group is an eicosanoxy group.
9. A transition metal complex according to any one of
5 claims 1 to 8 wherein M is Cr.
10. A bis-arylimine pyridine ligand having the formula (I) as defined in claim 1 wherein R₁-15 are as defined in any one of claims 1 to 8 and wherein the bis-arylimine pyridine ligand is not 2-[1-(2,4,6-trimethylphenylimino) ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl] pyridine.
11. A bis-aryliminio pyridine ligand having the formula I as defined in claim 1, wherein R₁-6 and R₁₀-15 are as defined in any one of claims 1 to 4 and R₇-R₉ are as
15 defined in any one of claims 5 to 8.
12. A transition metal complex which is a bis-arylimine pyridine MX_n complex, comprising a bis-arylimine pyridine ligand having the formula (I) as defined in claim 1 wherein, R₁-15, X and n are as defined in any of claims
20 1-8 and M is a transition metal selected from Fe and Co and wherein the transition metal complex is not 2-[1-(2,4,6-trimethylphenylimino) ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl] pyridine iron (II) chloride complex.
13. A transition metal complex which is a [bis-arylimine
25 pyridine MX_p⁺][NC⁻]_q complex, comprising a bis-arylimine pyridine ligand having the formula (I) as defined in claim 1 wherein R₁-15, X, p, q, NC are as defined in any one of claims 2-7, and M is a transition metal selected
30 from Fe and Co.

14. A transition metal complex according to claim 12 or 13 wherein R₇-R₉ are as defined in any one of claims 5 to 8.
15. A solution in non polar media particularly a
5 chemically inert non polar solvent, of at least 10 mg ml⁻¹ of a transition metal complex which is a bis-arylimine pyridine MX_n complex or a [bis-arylimine pyridine MX_p⁺][NC⁻]_q complex, each comprising a bis-arylimine pyridine ligand of formula I as defined in
10 claim 1 wherein each of R₁-R₁₅ is defined in any one of claims 1 to 8, X and n are as defined in claim 1 and p, NC and q are as defined in claim 2, and M is a transition metal.
16. A solution according to claim 15 in toluene of at
15 least 50 mg ml⁻¹ of the transition metal complex wherein the metal M is iron or cobalt, in particular 2-[1-(2,4,6-trimethylphenylimino) ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl] pyridine iron (II) chloride complex.
- 20 17. A catalyst system comprising:
(a) one or more transition metal complexes according to any one of claims 1 to 9; and mixtures thereof; and
(b) (i) in the case when a bis-arylimine pyridine
25 MX_n complex is present, (1) a co-catalyst compound capable of abstracting an anion and transferring a hydrocarbyl or hydride group to the transition metal atom, or (2) a co-catalyst compound capable of abstracting an anion and a co-catalyst compound
30 capable of transferring a hydrocarbyl or hydride group to the transition metal atom; and/or

(b) (ii) in the case where a [bis-arylimine pyridine $\text{MX}_p^+][\text{NC}^-]_q$ complex is present, a co-catalyst compound capable of transferring a hydrocarbyl or hydride group to the transition metal atom.

5 18. A catalyst system comprising:

(a) one or more transition metal complexes selected from:

10 (i) a bis-arylimine pyridine MX_n complex, comprising a bis-arylimine pyridine ligand having the formula (I) as defined in claim 1, wherein R_{1-15} , X and n are as defined in any one of claims 1 to 8 and M is a transition metal selected from Fe and Co, and

15 (ii) a [bis-arylimine pyridine $\text{MX}_p^+][\text{NC}^-]_q$ complex, comprising a bis-arylimine pyridine ligand having the formula (I) as defined in claim 1 wherein R_{1-15} , X, p, q, and NC are as defined in any one of claims 2 to 8 and M is a transition metal selected from Fe and Co, and

20 (b) (i) in the case when a bis-arylimine pyridine MX_n complex is present, (1) a co-catalyst compound capable of abstracting an anion and transferring a hydrocarbyl or hydride group to the transition metal atom, or (2) a co-catalyst compound capable of abstracting an anion and a co-catalyst compound capable of transferring a hydrocarbyl or hydride group to the transition metal atom; and/or

25 (b) (ii) in the case where a [bis-arylimine pyridine $\text{MX}_p^+][\text{NC}^-]_q$ complex is present, a co-catalyst compound capable of transferring a hydrocarbyl or hydride group to the transition metal atom;

30

with the proviso that when the transition metal atom is Fe or Co the catalyst system does not comprise one or more compounds of the formula ZnR'_2 wherein each R' , which may be the same or different, is selected from hydrogen, optionally substituted C_1 - C_{20} hydrocarbyl, phenyl, Cl, Br, I, SR'' , NR''_2 , OH, OR'' , CN, NC wherein R'' , which within the same molecule may be the same or different, is C_1 - C_{20} hydrocarbyl, and the catalyst system is not 2-[1-(2,4,6-trimethylphenylimino) ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl] pyridine iron[III] chloride complex with MAO,

or with the proviso that when the transition metal is Fe, the catalyst system is not 2-[1-(2,4,6-trimethylphenylimino) ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl] pyridine iron[III] chloride complex with MAO or 2-[1-(2,4,6-trimethylphenylimino) ethyl]-6-[1-(4-eicosanoxy-3,5-diphenylphenylimino)ethyl] pyridine iron[III] chloride complex with MAO and $ZnEt_2$.

19. A catalyst system according to claim 17 and 18 wherein said bis-aryliminopyridine ligand is as defined in claim 11.

20. A catalyst system according to any one of claims 17-19 wherein co-catalyst compound(s) (b) is selected from alkyl aluminium, aluminoxane and mixtures thereof.

21. A solution in a non polar medium or chemically inert non polar solvent containing at least 10 mg ml^{-1} of a catalyst system, comprising (a) at least one transition metal complex as defined in claim 15 or 16 and (b) a co-catalyst compound as defined in claim 17.

22. A dimerization or co-oligomerization process comprising contacting a feed olefin, which is an alpha-olefin comprising at least 3 carbon atoms or an alpha-olefin comprising 3 carbon atoms and ethylene, with a catalyst system comprising (a) one or more transition metal complex selected from a transition metal complex which is a bis-arylimine pyridine MX_n complex, a [bis-arylimine pyridine MX_p^+][NC^-] $_q$ complex, each comprising a bis-arylimine pyridine ligand having the formula (I) as defined in any of claims 1 to 8 wherein R_{1-15} , X and n are as defined in any one of claims 1 to 8 and p, NC and q are as defined in claim 2 and M is a transition metal; and mixtures thereof, and
- (b) (i) in the case when a bis-arylimine pyridine MX_n complex is present, (1) a co-catalyst compound capable of abstracting an anion and transferring a hydrocarbyl or hydride group to the transition metal atom, or (2) a co-catalyst compound capable of abstracting an anion and a co-catalyst compound capable of transferring a hydrocarbyl or hydride group to the transition metal atom; and/or
- (b) (ii) in the case where a [bis-arylimine pyridine MX_p^+][NC^-] $_q$ complex is present, a co-catalyst compound capable of transferring a hydrocarbyl or hydride group to the transition metal atom.
23. A process according to claim 22 wherein M is Fe, Co or Cr.
24. An oligomerization process comprising contacting a feed olefin which is ethylene with a catalyst system as defined in claim 17 or 18.
25. A process according to any one of claims 22-24 wherein in the bis-arylimine pyridine of formula I as

defined in claim 1, R₇, R₈ and R₉ are as defined in any one of claims 5-8.

26. A process according to any one of claims 22-25, wherein co-catalyst compound(s) (b) is selected from
5 alkyl aluminium, aluminoxane and mixtures thereof.

27. A process according to any one of claims 22-26 wherein the catalyst system is in a solution as claimed in claim 21.