



(51) International Patent Classification:
C08L 3/02 (2006.01) **C08L 3/04** (2006.01)

(21) International Application Number:
PCT/AU2009/000979

(22) International Filing Date:
31 July 2009 (31.07.2009)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
2008903922 31 July 2008 (31.07.2008) AU

(71) Applicant (for all designated States except US): **TRIS-TANO PTY LTD** [AU/AU]; Unit 18, 35 Dunlop Road, Mulgrave, Victoria 3170 (AU).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **CHANGPING, Chen** [CN/CN]; SD9 Wuyi Garden, Jiangning District, Nanjing, Jiangsu (CN). **SCHEIRS, John** [AU/AU]; 3 Esplanade Lane, Edithvale, Victoria 3196 (AU).

(74) Agents: **TOZER, Ramon Dean** et al.; Davies Collison Cave, 1 Nicholson Street, Melbourne, Victoria 3000 (AU).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: COMPOSITIONS COMPRISING THERMOPLASTIC STARCH

(57) Abstract: The invention relates to a composition comprising very low density polyethylene having a density of less than 0.905g/cm³, ethylene acrylic acid copolymer and thermoplastic starch and/or the constituent components thereof.

