

Description

BACKGROUND OF THE INVENTION

5 Field of the Invention

This invention relates to a polythiol compound, and an optical material and optical product comprising same. The polythiol compound of this invention is used, e.g. as a useful material for an optical material. The optical material produced from the above polythiol compound, provided by this invention, exhibits a high
 10 refractive index and low dispersion or has excellent optical properties, and it is preferred for use in optical products such as a plastic lens, a prism, an optical fiber, a substrate for data reading and storage, a colored filter, an infrared absorbing filter, etc.

Further, it is usable in ornament such as a cup, a flower vase, etc., owing to a high refractive index which the material has as a characteristic.

15

Description of Prior Art

Being light-weighted, unbreakable to a certain degree and easy to dye as compared with glass, plastic has been recently used for an optical purpose, e.g. for producing various lenses. For this reason, polyethylene glycol bisallylcarbonate (CR-39) and polymethyl methacrylate (PMMA) are generally used as a plastic material. Since, however, these plastic materials have a refractive index of not more than 1.50, a lens formed of such a plastic material is required to have a large thickness when the degree is increased. As a result, undesirably, not only the advantage of the light-weight of plastic is lost, but also aesthetic appearance of spectacles of such a material is poor. In particular, when a concave lens is formed of such a material, the peripheral thickness of the lens increases, and birefringence and chromatism undesirably take place. It is therefore desired to develop a plastic material which can take advantage of the properties of plastic having low specific gravity or permit a smaller thickness of a lens, and which has low chromatism, a high refractive index and low dispersion. As a material for such purposes, JP-A-63-46213 discloses a polymer of tetrachloro-m-xylylenedithiol or 1,3,5-trimercaptobenzene with a diisocyanate compound. JP-A-64-26622 discloses a polymer of pentaerythritoltetrakisithiopropionate with a diisocyanate compound. Further, JP-A-63-309509 discloses a polymer of pentaerythritoltetrakisithiopropionate with a vinyl compound.

However, the thiol compound disclosed in the above JP-A-63-46213 has a low Abbe's number although it has a high refractive index, and a polymer produced therefrom also has defects in that it has a low Abbe's number and poor weatherability. And, the thiol compounds disclosed in JP-A-64-26622 and JP-A-63-309509 have a low refractive index although they have a large Abbe's number, and polymers produced therefrom have defects in that they have a low refractive index and inferior heat resistance.


Summary of the Invention

It is therefore an object of this invention to provide a novel thiol compound which can overcome the above defects, and novel optical material and product produced from it as a starting material.

This invention has been made to achieve the above object, and the novel thiol compound of this invention has the formula [1].

45

50



wherein X is $-(CH_2CH_2S)n_2-H$, n_1 is an integer of 1 to 5 and n_2 is an integer of 0 to 2.

55

The novel optical material of this invention comprises a polymer obtained by polymerizing a component (A) which at least contains a polythiol compound (a_1) and a component (B) which contains at least one member of a compound (b_1) having at least two vinyl groups per molecule, a compound (b_2) having at least two iso(thio)cyanate groups per molecule and a compound (b_3) having at least one vinyl group and at least

one iso(thio)cyanate group per molecule. In addition, the above "iso(thio)cyanate group" means both an isocyanate group and a thiocyanate group.

BRIEF EXPLANATION OF THE DRAWINGS

Figs. 1 and 2 are a $^1\text{H-NMR}$ spectrum chart and an IR spectrum chart of the polythiol compound obtained in Example 1, respectively.


DETAILED DESCRIPTION OF THE INVENTION

This invention will be detailed hereinafter.

The novel polythiol compound of this invention has a characteristic feature in that it has a 1,4-dithian ring which is a cyclic sulfide, as is shown in the above formula [1]. The 1,4-dithian ring increases the refractive index and Abbe's number of a polythiol compound. Therefore, this polythiol compound used for the production of a polymer increases the refractive index and Abbe's number of the polymer. The 1,4-dithian ring in a polythiol compound is rigid. Therefore, the polythiol compound used for the production of a polymer impart the polymer with high heat resistance and excellent mechanical properties.



In the formula [1], n_1 is limited to an integer of 1 to 5, and n_2 is limited to an integer of 0 to 2. The reasons therefor are as follows. When n_1 is 0, a polymer produced from the polythiol compound is fragile and its impact resistance is degraded. On the other hand, when n_1 exceeds 6, the polythiol compound has a reduced refractive index, and undesirably, a polymer produced therefrom is liable to have not only a reduced refractive index but also degraded heat resistance. Further, when n_2 is not less than 3, a polymer produced from the polythiol compound undesirably has degraded heat resistance.

The polythiol compound of this invention can be synthesized according to a method shown in the following scheme, e.g. when it is a compound of the formula [1] in which X is a hydrogen atom ($n_2 = 0$), and $n_1 = 1$.



That is, a diallyldisulfide is reacted with bromine, and, a resulting cyclic dimerized compound with bromine atoms is reacted with a thiourea to form an isothiuronium salt. This salt is hydrolyzed with an aqueous sodium hydroxide solution and then acidified with hydrochloric acid, whereby the intended polythiol compound can be obtained.

- 5 The following are examples of the polythiol compound of the formula [1] other than the polythiol compound of which the production process is described above and in which X is a hydrogen atom ($n_2 = 0$), and $n_1 = 1$.



- 30 The optical material comprising the polythiol compound of the above formula [1], provided by this invention, is explained below. This optical material comprises a polymer obtained by polymerizing a component (A) which at least contains a polythiol compound (a_1) and a component (B) which contains at least one member of a compound (b_1) having at least two vinyl groups per molecule, a compound (b_2) having at least two iso(thio)cyanate groups per molecule and a compound (b_3) having at least one vinyl group and at least one iso(thio)cyanate group per molecule. Since the compound (a_1) of the formula [1],
- 35 contained in the component (A), is detailed above, an explanation thereof is omitted here.

- In order to improve physical properties, etc., of the polymer as required, the component (A) may contain one or more compounds (a_2) having mercapto group(s) and/or hydroxy group(s) in such a manner that the total number of the mercapto and hydroxy groups per molecule is not less than 2, in addition to the
- 40 compound (a_1) of the formula [1]. Specific examples of the compound (a_2) are trimethylolpropane, 1,2-ethanedithiol, 1,3-propanedithiol, tetrakis(mercaptomethyl)methane, pentaerythritoltetrakis(mercaptopropionate), pentaerythritoltetrakis(mercaptoacetate), 2-mercaptoethanol, 2,3-dimercaptopropanol, 1,2-dihydroxy-3-mercaptopropane, 4-mercaptophenol, 1,2-benzenedithiol, 1,3-benzenedithiol, 1,4-benzenedithiol, 1,3,5-benzenetriol, 1,2-dimercaptomethylbenzene, 1,3-dimercaptomethylbenzene, 1,4-dimercaptomethylbenzene,
- 45 1,3,5-trimercaptomethylbenzene, toluene-3,4-dithiol and 4,4'-dihydroxyphenylsulfide.

The amount of the compound (a_1) of the formula [1] based on the total amount of the component (A) is 0.1 to 100 mol%, preferably 10 to 100 mol%.

- Specific examples of the compound (b_1) containing vinyl groups, contained in the component (B), are divinylbenzene, ethyleneglycoldi(meth)acrylate, trimethylolpropanetri(meth)acrylate, urethane-modified
- 50 (meth)acrylates, epoxy-modified (meth)acrylates and polyester-modified (meth)acrylates. These modified acrylates contain at least two (meth)acryloxy groups per molecule. (In addition, the above "(meth)acrylate" stands for both of an acrylate and a methacrylate, and the "(meth)acryloxy group stands for both of an acryloxy group and a methacryloxy group.)

- Specific examples of the compound (b_2) containing iso(thio)cyanate groups, contained in, the component (B), are xylylenediiso(thio)cyanate, 3,3'-dichlorodiphenyl-4,4'-diiso(thio)cyanate, 4,4'-diphenylmethanediiso(thio)cyanate, hexamethylenediiso(thio)cyanate, 2,2',5,5'-tetrachlorodiphenyl-4,4'-diiso(thio)cyanate and tolylenediiso(thio)cyanate. Further, examples of the compound (b_2) having at least one cyclohexyl ring are bis(iso(thio)cyanatomethyl)cyclohexane, bis(4-iso(thio)cyanatocyclohexyl)methane, bis(4-
- 55

iso(thio)cyanatomethylcyclohexyl)methane; cyclohexanediiiso(thio)cyanate, isophoronediiiso(thio)cyanate, 2,5-bis(iso(thio)cyanatomethyl)bicyclo[2,2,2]octane, 2,5-bis(iso(thio)cyanatomethyl)bicyclo[2,2,1]heptane, 2-iso(thio)cyanatomethyl-3-(3-iso(thio)cyanatopropyl)-5-iso(thio)cyanatomethyl-bicyclo[2,2,1]-heptane, 2-iso(thio)cyanatomethyl-3-(3-iso(thio)cyanatopropyl)-6-iso(thio)cyanatomethylbicyclo[2,2,1]heptane, 2-iso(thio)cyanatomethyl-2-[3-iso(thio)cyanatopropyl]-5-iso(thio)cyanatomethyl-bicyclo[2,2,1]-heptane, 2-iso(thio)cyanatomethyl-2-(3-iso(thio)cyanatopropyl)-6-(2-iso(thio)cyanatomethyl)-bicyclo[2,2,1]-heptane, 2-iso(thio)cyanatomethyl-3-(3-iso(thio)cyanatopropyl)-6-(2-iso(thio)cyanatoethyl)-bicyclo[2,2,1]-heptane, 2-iso(thio)cyanatomethyl-3-(3-iso(thio)cyanatopropyl)-6-(2-iso(thio)cyanatoethyl)-bicyclo[2,2,1]heptane, 2-iso(thio)cyanatomethyl-2-(3-iso(thio)cyanatopropyl)-5-(2-iso(thio)cyanatoethyl)-bicyclo[2,2,1]-heptane, and 2-iso(thio)cyanatomethyl-2-(3-iso(thio)cyanatopropyl)-6-(2-iso(thio)cyanatoethyl)-bicyclo[2,2,1]heptane.

Further, examples of the compound (B₃) containing vinyl and iso(thio)cyanate groups, contained in the component (B), are 2-(meth)acryloxyethyliso(thio)cyanate and (meth)acryloyliso(thio)cyanate.

When the component (B) contains vinyl group(s), it is desirable that all of the polymeric functional groups of the component (A) are mercapto groups. When the component (A) contains a hydroxy group, the polymerization degree of the polymer cannot be increased, and the resultant polymer is liable to exhibit low mechanical properties.

For the production of the optical material of this invention, monomers other than the above components (A) and (B) may be used as required.

Further, in order to improve weatherability, additives such as a UV absorber, an antioxidant, a color inhibitor, a fluorescent dye, etc., may be incorporated as required. And, a catalyst for improving polymerization reactivity may be also incorporated as required. For example, an organic peroxide, an azo compound and a basic catalyst are effective to improve the reactivity between a mercapto group and a vinyl group. An organotin compound and an amine compound are effective to improve the reactivity between a mercapto or hydroxy group and an iso(thio)cyanate group.

The following is one embodiment of the production of the optical material using the polythiol compound of this invention.

A homogeneous mixture of the above components (A) and (B), additive and catalyst is heated and cured by a known casting polymerization method, i.e. the homogeneous mixture is casted into a mold assembly formed of a combination of a pair of glass or metal molds and a resinous gasket, heated and cured. In this case, in order to make it easy to takeout a molded resin, the mold may be preliminary subjected to mold releasing treatment or a mold releasing agent may be incorporated into the mixture of the components (A) and (B). The polymerization temperature differs depending upon compounds used. In general, it is between -20°C and +150°C, and the polymerization time is 0.5 to 72 hours. The optical material of this invention is easily dyeable with a usual dispersion dye in water or an organic solvent, and in this case, a carrier may be added or the dye may be heated in order to ease the dyeing.

The optical material obtained as above is desirably usable as an optical product such as a plastic lens, etc., although it shall not be limited thereto.

[Examples]

This invention will be explained specifically hereinbelow by reference to Examples, which, however, shall not limit this invention.

(Evaluation of properties)

Those polythiol compounds and polymers produced therefrom which were obtained in Examples and polymers obtained in Comparative Examples were evaluated on physical properties as follows.

Refractive index (n_D) and Abbe's number (ν_D):

Abbe's refractometer 3T supplied by Atagoshia was used for the measurement.

Appearance:

Observed by the eyes.

Weatherability:

The hue of a plastic lens which had been set at a weatherometer provided with a sunshine carbon arc lamp for 200 hours was compared with that of a lens which remained intact. The evaluation was made on the basis of ratings of no change (o), and yellowing (x).

Heat resistance:

TMA measurement was carried out with a TMA apparatus supplied by Rigakusha by using a 0.5 mm ϕ pin under a load of 10 gf, and heat resistance was evaluated on the basis of a peak temperature of a chart obtained at a temperature elevation rate of 10 °C/min.

Optical strain:

Observed by the eyes according to the Schlielen method. No strain is indicated as O, and the presence of strain, as x.

Example 1

Preparation of 2,5-dimercaptomethyl-1,4-dithian as a polythiol compound of this invention (a compound of formula [1] in which X=H ($n_2=0$), and $n_1=1$)

25.0 Grams (0.157 mol) of bromine was added dropwise to a solution of 22.9 g (0.57 mol) of diallyldisulfide in 780 ml of dichloromethane at -78 °C over 1 hour. And, the temperature of the resultant mixture was elevated up to -20 °C, and the mixture was stirred at said temperature for 8 hours. Then, dichloromethane was removed under reduced pressure. To the remaining residue there were added 100 ml of ethanol and 23.9 g (0.314 mol) of thiourea, and the resultant mixture was refluxed for 1.5 hours. A precipitate formed was recovered by filtration, washed with ethanol several times and dried. The precipitate was dispersed in 73 ml of water, and while the resultant dispersion was refluxed under nitrogen atmosphere, 64.2 g of a 15 % sodium hydroxide aqueous solution was added dropwise over 1 hour. Thereafter, the resultant mixture was further refluxed for 1 hour. The resultant reaction mixture, after cooled, was acidified with 6N-hydrochloric acid and subjected to extraction with benzene. Benzene was removed from the resultant extract under reduced pressure, and the remainder was distilled at 2×10^{-2} mmHg to give 22.6 g of a fraction having a boiling point of 121.5 °C (yield 68 %). This fraction had a refractive index of 1.846 and Abbe's number of 35.2. Analysis results for determining the structure of this novel polythiol compound are as follows.

Elemental Analysis			
	C	H	S
Theoretical (%)	33.9	5.68	60.4
Found (%)	33.8	5.80	60.0

¹H-NMR (solvent: CDCl₃, internal reference substance: TMS)
 δ (ppm) = 1.62 (t, 1H)
 2.88-3.14 (m, 5H)

IR

2545 cm⁻¹ (ν_{SH} of thiol)

In addition, Fig. 1 shows a ¹H-NMR spectrum chart of the above novel polythiol compound, and Fig. 2 shows an IR spectrum chart thereof.

Example 2

Preparation of 2,5-bis(2-mercaptoethylthiomethyl)-1,4-dithian as a polythiol compound of this invention (a compound of formula [1] in which $X = CH_2CH_2SH$ ($n_2 = 1$), and $n_1 = 1$)

21.2 Grams (0.1 mol) of the 2,5-dimercaptomethyl-1,4-dithian obtained in Example 1 was dissolved in 58.7 g of a 15 % sodium hydroxide aqueous solution. To the mixture was added a solution prepared by dissolving 18.0 g (0.3 mol) of thirane in 200 ml of benzene in the presence of 100 mg of benzyltrimethylammonium chloride. And, the resultant mixture was allowed to react at room temperature for 12 hours. Then, at 0 °C, while the mixture was stirred, a concentrated hydrochloric acid was added until the pH of a water phase became 1, a benzene phase was separated, the remainder was washed with water, and benzene was distilled off to give 24.6 g of an intended product, 2,5-bis(2-mercaptoethylthiomethyl)-1,4-dithian (yield 74 %).

Example 3

Preparation of 2,5-bis(3-mercaptopropyl)-1,4-dithian as a polythiol compound of this invention (a compound of formula [1] in which $X = H$ ($n_2 = 0$), and $n_1 = 3$)

25.0 Grams (0.157 mol) of bromine was added to a solution of 22.9 g (0.157 mol) of diallyldisulfide in 780 ml of dichloromethane at -78 °C over 1 hour. And, the temperature of the mixture was elevated up to -20 °C, the mixture was stirred at said temperature for 8 hours, and then, dichloromethane was removed under reduced pressure. 300 Milliliters of dry tetrahydrofuran was added to the residue, the resultant mixture was cooled to -10 °C, and while the mixture was stirred, 329 ml of a 1.0 M-tetrahydrofuran solution of vinylmagnesium bromide was added dropwise. Thereafter, the mixture was stirred at 0 °C for 2 hours and at room temperature for 12 hours. The reaction mixture was poured into water and subjected to extraction with benzene, and benzene was distilled off under reduced pressure. Then, the resultant residue was dissolved in 200 ml of benzene, and while hydrogen sulfide was blown into the mixture, the mixture was allowed to react at room temperature for 4 hours. Thereafter, benzene was distilled off under reduced pressure to give 25.7 g of an intended product, 2,5-bis(3-mercaptopropyl)-1,4-dithian (yield 61 %).

Example 4

Production of optical material of this invention

A mixture of 0.1 mol of 2,5-dimercaptomethyl-1,4-dithian (indicated as S-1 in Table 1), 0.1 mol of m-xylylenediisocyanate (indicated as XDI in Table 1) and 1×10^{-5} mol of dibutyltin dilaurate (indicated as DBTDL in Table 1) was homogeneously stirred, and injected into a glass mold assembly for forming a lens. The mixture was polymerized under heat at 50 °C for 10 hours, then at 60 °C for 5 hours, and further at 120 °C for 3 hours to give a polymer having a lens form. Table 1 shows various physical properties of the polymer. As shown in Table 1, the polymer of this Example 4 was colorless and transparent, and it had a very high refractive index (n_D) of 1.66 and a high Abbe's number of 32 (low dispersion). Further, this polymer had excellent weatherability and heat resistance (97 °C), and it was free from optical strain.

Examples 5-21

Production of other optical materials of this invention

The procedure of Example 4 was repeated except that monomer compositions shown in Table 1 were used and that the polymerization conditions were suitably changed, whereby polymers having a lens form were obtained. Table 1 shows various physical properties of these polymers as well as those of the polymer obtained in Example 4. As shown in Table 1, the polymers of Examples 5 to 21 were also colorless and transparent, and they also had a very high refractive index (n_D) of 1.58 to 1.66 and a high Abbe's number of 32 to 43 (low dispersion). Further, these polymers had excellent weatherability and heat resistance (94 to 128 °C), and they were free from optical strain.

In particular, the polymers obtained in Examples 4 to 10 and 20 to 21 had an Abbe's number of 32 to 38, and these polymers had a higher refractive index, as high as 1.62 to 1.66, than conventional polymers having an Abbe's number in such a range.

Further, the polymers obtained in Examples 11 to 19 had a refractive index of 1.58 to 1.62, and these polymers had a higher Abbe's number, as high as 38 to 43, than conventional polymers having a refractive index in such a range.

5 Comparative Example 1

A mixture of 0.1 mol of pentaerythritoltetrakis-mercaptopropionate (indicated as PETMP in Table 1), 0.2 mol of m-xylylenediisocyanate (indicated as XDI in Table 1) and 1×10^{-4} mol of dibutyltin dilaurate (indicated as DBTDL in Table 1) was homogeneously stirred, and injected into a glass mold assembly for forming a lens. The mixture was polymerized under heat at 50 °C for 10 hours, then at 60 °C for 5 hours, and further at 120 °C for 3 hours to give a polymer having a lens form. Table 1 shows various physical properties of the polymer. As shown in Table 1, the polymer of this Comparative Example was colorless and transparent, and exhibited no optical strain. However, this polymer had a n_D^{20} of as low as 1.59/36, and its heat resistance was as inferior as 86 °C.

15

Comparative Examples 2 and 3

The procedure of Comparative Example 1 was repeated except that monomer compositions shown in Table 1 were used, whereby polymers having a lens form were obtained. Table 1 shows various physical properties of these polymers as well as those of the polymers obtained in Examples 4 to 21 and those of the polymer obtained in Comparative Example 1. As shown in Table 1, the polymer of this Comparative Example 2 had a high refractive index of 1.67 and good heat resistance (94 °C). However, this polymer had inferior weatherability and exhibited optical strain. The polymer of Comparative Example 3 was colorless and transparent, and it exhibited no optical strain and had good weatherability. However, this polymer had a refractive index of as low as 1.53, and the heat resistance thereof was as inferior as 65 °C.

25

30

35

40

45

50

55

Table 1 (No. 1)


Example No.	Component A (mol)	Component B (mol)	Polymerization catalyst (mol)	n_D / n_D Appearance	Heat resistance and 97	Weatherability	Optical strain
4	S-1 (0.1)	XDI (0.1)	DBTDL (1×10^{-5})	1.66/32 Colorless and transparent	97	○	○
5	S-1/4-MP (0.1/0.03)	XDI (0.13)	DBTDL (4×10^{-4})	1.64/34	121	○	○
6	S-4/PETMA/DHPS (0.1/0.04/0.01)	IPDI/TDI (0.17/0.02)	DBTDL (1×10^{-4})	1.62/37	98	○	○
7	S-2/TMP/DMB (0.15/0.06/0.1)	DPMDI (0.34)	DBTDL (2×10^{-4})	1.64/36	101	○	○
8	S-1/EDT (0.1/0.01)	EDMA (0.11)	ADVN (1×10^{-3})	1.64/35	94	○	○
9	S-1/PETMP (0.1/0.02)	DVB (0.14)	ADVN (1.5×10^{-3})	1.63/34	103	○	○
10	S-1 (0.125)	MEI/XDI (0.1/0.1)	ADVN/DBTDL ($2 \times 10^{-3}/1 \times 10^{-5}$)	1.62/38	128	○	○
11	S-1 (0.1)	H6-XDI (0.1)	DMTDCI (1×10^{-4})	1.62/38	108	○	○
12	S-1/PETMA (0.06/0.02)	H6-XDI (0.10)	DBTDCI (4×10^{-4})	1.60/40	118	○	○
13	S-2 (0.1)	H6-MDI (0.1)	DMTDCI (2×10^{-4})	1.61/40	98	○	○
14	S-1/PETMP (0.08/0.01)	H6-XDI/H6-MDI (0.08/0.02)	DBTDCI (1.5×10^{-4})	1.60/40	121	○	○

Table 1 (No. 2)


Example No.	Component A (mol)	Component B (mol)	Polymerization catalyst (mol)	η_{sp}/c	Appearance	Heat Resistance (°C)	Weatherability	Optical strain
15	S-1/PETMP (0.35/0.075)	H6-XDI (0.5)	DMTDCI (1×10^{-4})	1.60/40	Colorless and transparent	108	○	○
16	S-1/1,2-DHB (0.1/0.015)	H6-XDI (0.115)	DBTDL (3×10^{-5})	1.61/39	"	100	○	○
17	S-1/TG (0.1/0.02)	H6-XDI (0.13)	DBTDL (3×10^{-5})	1.59/42	"	109	○	○
18	S-2/PETMA (0.06/0.02)	H6-XDI (0.1)	DMTDCI (1×10^{-5})	1.60/40	"	103	○	○
19	S-4/PETMA (0.08/0.01)	H6-XDI (0.1)	DMTDCI (1×10^{-5})	1.58/43	"	100	○	○
20	S-2/PETMA (0.06/0.02)	XDI (0.1)	DBTDL (1×10^{-5})	1.65/32	"	101	○	○
21	S-4/PETMA (0.08/0.01)	XDI (0.1)	DBTDL (1×10^{-5})	1.65/33	"	97	○	○
Comparative Example No.								
1	PETMP (0.1)	XDI (0.2)	DBTDL (1×10^{-4})	1.59/36	Colorless and transparent	86	○	○
2	1,3,5-TMB (0.2)	XDI (0.3)	DBTDL (1.5×10^{-4})	1.67/28	Yellowish	94	×	×
3	PETMP (0.1)	DAPE (0.2)	ADVN (2×10^{-3})	1.53/52	Colorless and transparent	65	○	○

Abbreviations in Table 1


S - 1 :



S - 2 :



S - 4 :



XDI:	m-xylylenediisocyanate
EDT:	ethanediol
PETMA:	pentaerythritoltetrakismercaptopacetate
EDMA:	ethylene glycol dimethacrylate
PETMP:	pentaerythritoltetrakismercaptopropionate
DVB:	divinylbenzene
4-MP:	4-mercaptophenol
TMP:	trimethylpropane
1,2-DHB:	1,2-dihydroxybenzene
DMB:	1,3-dimercaptobenzene
TG:	3-mercapto-1,2-dihydroxypropane
DPMDI:	diphenylmethanediisocyanate
DHPS:	4,4'-dihydroxyphenylsulfide
IPDI:	isophoronediiisocyanate
H6-XDI:	1,3-bis(isocyanatemethyl)cyclohexane
H6-MDI:	bis(4-isocyanatecyclohexyl)methane
MEI:	2-methacryloxyethylisocyanate
TDI:	tolylenediisocyanate
DBTDL:	dibutyltin dilaurate
DMTDCI:	dimethyltin dichloride
DBTDCI:	dibutyltin dichloride
ADVNI:	azobisdimethylvaleronitrile
1,3,5-TMB:	1,3,5-trimercaptobenzene
DAPE:	diallylidene-pentaerythritol

The novel polythiol compound of this invention has a high refractive index and a high Abbe's number due to its 1,4-dithian ring, and it is easily polymerizable with at least one member of a compound having at least two vinyl groups per molecule, a compound having at least two iso(thio)cyanate groups per molecule and a compound having at least one vinyl group and at least one iso(thio)cyanate group per molecule to give a polymer. The optical material of this invention comprising the above polymer has a high refractive


index and a high Abbe's number and also has excellent heat resistance, weatherability and transparency due to a 1,4-dithian ring contained in its main chain. Therefore, the optical material of this invention is suitably usable as a lens for spectacles, a camera, etc., a prism, an optical fiber, a recording medium substrate for use in an optical disk, a magnetic disk, etc., and an optical product such as a colored filter, a UV absorbing filter, etc.

Further, the above material is also usable in ornament utilizing its characteristic high refractive index such as a cup, a flower vase, etc.

Claims




10 Claims for the following Contracting States : CH, DE, FR, GB, IT, LI, NL, SE

1. A polythiol compound having the formula [1]



wherein X is $-(CH_2CH_2S)_{n_2}-H$, n_1 is an integer of 1 to 5 and n_2 is an integer of 0 to 2.

25 2. A polythiol compound according to claim 1, which is selected from the group consisting of the compounds represented by the formulae:




index and a high Abbe's number and also has excellent heat resistance, weatherability and transparency due to a 1,4-dithian ring contained in its main chain. Therefore, the optical material of this invention is suitably usable as a lens for spectacles, a camera, etc., a prism, an optical fiber, a recording medium substrate for use in an optical disk, a magnetic disk, etc., and an optical product such as a colored filter, a UV absorbing filter, etc.

Further, the above material is also usable in ornament utilizing its characteristic high refractive index such as a cup, a flower vase, etc.

Claims




Claims for the following Contracting States : CH, DE, FR, GB, IT, LI, NL, SE

1. A polythiol compound having the formula [1]




wherein X is $-(CH_2CH_2S)_{n_2}-H$, n_1 is an integer of 1 to 5 and n_2 is an integer of 0 to 2.

2. A polythiol compound according to claim 1, which is selected from the group consisting of the compounds represented by the formulae:






3. An optical material comprising a polymer obtained by polymerizing:
a component (A) which at least contains a polythiol compound (a_1) having the formula [1],



15 wherein X is $-(CH_2CH_2S)_{n_2}-H$, n_1 is an integer of 1 to 5 and n_2 is an integer of 0 to 2, and
a component (B) which contains at least one member of a compound (b_1) having at least two vinyl
groups per molecule, a compound (b_2) having at least two iso(thio)cyanate groups per molecule and a
compound (b_3) having at least one vinyl group and at least one iso(thio)cyanate group per molecule.

- 20 4. An optical material according to claim 3, wherein the polythiol compound is selected from the group
consisting of the compounds represented by the formulae:




- 50 5. An optical material according to claim 3, wherein the component (A) contains, together with the
compound (a_1), a compound (a_2) which has mercapto group(s) and/or hydroxy group(s) in such a
manner that the total number of the mercapto and hydroxy groups per molecule is not less than 2.
- 55 6. An optical material according to claim 3 or 5, wherein the compound (b_2) has at least one cyclohexyl
ring.
7. An optical product comprising an optical material recited in any one of claims 3 to 6.



8. An optical product according to claim 7, which is a plastic lens.


Claims for the following Contracting State : ES

1. A process for the preparation of a polythiol compound having the following formula:



wherein a diallylsulfide is reacted with bromine and the resulting cyclic dimerized compound with bromine atoms is reacted with a thiourea to form an isothiuronium salt, which is then hydrolyzed with an aqueous sodium hydroxide solution and then acidified with hydrochloric acid to obtain the intended polythiol compound.


2. A process for producing an optical material which comprises the polymerization of a component (A) which at least contains a polythiol compound (a₁) having the formula [1],




[1]

wherein X is $-(CH_2CH_2S)n_2-H$, n_1 is an integer of 1 to 5 and n_2 is an integer of 0 to 2, and a component (B) which contains at least one member of a compound (b₁) having at least two vinyl groups per molecule, a compound (b₂) having at least two iso(thio)cyanate groups per molecule and a compound (b₃) having at least one vinyl group and at least one iso(thio)cyanate group per molecule.


3. A process according to claim 2, wherein the polythiol compound is selected from compounds represented by the formulae:



(S-1)




(S-2)



(S-4)




4. A process according to claim 2, wherein the component (A) contains, together with the compound (a₁), a compound (a₂) which has mercapto group(s) and/or hydroxy group(s) in such a manner that the total number of the mercapto and hydroxy groups per molecule is not less than 2.
5. A process according to claims 2 or 4, wherein the compound (b₂) has at least one cyclohexyl ring.
6. An optical material comprising a polymer obtained by polymerizing:
a component (A) which at least contains a polythiol compound (a₁) having the formula [1]:




[1]

wherein X is $-(CH_2CH_2S)_{n_2}-H$, n_1 is an integer of 1 to 5 and n_2 is an integer of 0 to 2, and a component (B) which contains at least one member of a compound (b₁) having at least two vinyl groups per molecule, a compound (b₂) having at least two iso(thio)cyanate groups per molecule and a compound (b₃) having at least one vinyl group and at least one iso(thio)cyanate group per molecule.


7. An optical material according to claim 6, wherein the polythiol compound is selected from the group consisting of the compounds represented by the formulae:



(S-1)



(S-2)



(S-4)


8. An optical material according to claim 6, wherein the component (A) contains, together with the compound (a₁), a compound (a₂) which has mercapto group(s) and/or hydroxy group(s) in such a manner that the total number of the mercapto and hydroxy groups per molecule is not less than 2.
9. An optical product according to claims 6 or 8, wherein the compound (b₂) has at least one cyclohexyl ring.
10. An optical product according to claim 9, which is a plastic lens.



Patentansprüche

Patentansprüche für folgende Vertragsstaaten : CH, DE, FR, GB, IT, LI, NL, SE


1. Polythiol-Verbindung mit der Formel [1]




[1]

worin $X-(CH_2CH_2S)_{n_2}-H$ ist, n_1 eine Ganzzahl von 1 bis 5 ist und n_2 eine Ganzzahl von 0 bis 2 ist.


2. Polythiol-Verbindung gemäß Anspruch 1, welche ausgewählt ist aus der Gruppe bestehend aus Verbindungen der Formeln:




(S-1)



(S-2)



(S-4)


3. Optisches Material, umfassend ein Polymer, das erhalten wird durch Polymerisieren von:
einer Komponente (A), die mindestens eine Polythiol-Verbindung (a_1) mit der Formel [1] enthält,

[1]


worin $X-(CH_2CH_2S)_{n_2}-H$ ist, n_1 eine Ganzzahl von 1 bis 5 ist und n_2 eine Ganzzahl von 0 bis 2 ist und
einer Komponente (B), welche mindestens einen Vertreter aus einer Verbindung (b_1) mit mindestens zwei Vinyl-Gruppen pro Molekül, einer Verbindung (b_2) mit mindestens zwei Iso(thio)cyanat-Gruppen pro Molekül und einer Verbindung (b_3) mit mindestens einer Vinyl-Gruppe und mindestens einer Iso(thio)cyanat-Gruppe pro Molekül enthält.




4. Optisches Material gemäß Anspruch 3, worin die Polythiol-Verbindung ausgewählt wird aus der Gruppe bestehend aus den Verbindungen der Formeln:



(S-1)



(S-2)




(S-4)

5. Optisches Material gemäß Anspruch 3, wobei die Verbindung (A) zusammen mit der Verbindung (a₁) eine Verbindung (a₂) mit Mercapto-Gruppe(n) und/oder Hydroxy-Gruppe(n) in einer solchen Weise enthält, daß die Gesamtzahl der Mercapto- und Hydroxy-Gruppe(n) pro Molekül nicht weniger als 2 beträgt.
6. Optisches Material gemäß Anspruch 3 oder 5, worin die Verbindung (b₂) mindestens einen Cyclohexylring hat.
7. Optisches Produkt, umfassend ein optisches Material gemäß einem der Ansprüche 3 bis 6.
8. Optisches Produkt gemäß Anspruch 7, das eine Plastiklinse ist.

Patentansprüche für folgenden Vertragsstaat : ES


1. Verfahren zur Herstellung einer Polythiol-Verbindung mit der folgenden Formel:



wobei ein Diallylsulfid mit Brom umgesetzt wird und die resultierende cyclische dimerisierte Verbindung mit Bromatomen mit einem Thioharnstoff unter Bildung eines Isothiuroniumsalzes umgesetzt wird, welches dann mit einer wäßrigen Natronlauge hydrolysiert und dann mit Salzsäure angesäuert wird, so daß die gewünschte Polythiol-Verbindung erhalten wird.

2. Verfahren zur Herstellung eines optischen Materials, umfassend die Polymerisation einer Verbindung (A), die mindestens eine Polythiol-Verbindung (a₁) mit der Formel [1] enthält:







[1]

worin X $-(\text{CH}_2\text{CH}_2\text{S})_{n_2}-\text{H}$ ist, n_1 eine Ganzzahl von 1 bis 5 ist und n_2 eine Ganzzahl von 0 bis 2 ist, und einer Komponente (B), die mindestens einen Vertreter aus einer Verbindung (b_1) mit mindestens zwei Vinyl-Gruppen pro Molekül, einer Verbindung (b_2) mit mindestens zwei Iso(thio)cyanat-Gruppen pro Molekül und einer Verbindung (b_3) mit mindestens einer Vinyl-Gruppe und mindestens einer Iso(thio)cyanat-Gruppe pro Molekül enthält.


3. Verfahren gemäß Anspruch 2, wobei die Thiol-Verbindung ausgewählt ist aus Verbindungen der Formeln:



(S-1)




(S-2)



(S-4)

4. Verfahren gemäß Anspruch 2, wobei die Komponente (A) zusammen mit der Verbindung (a_1) eine Verbindung (a_2) mit Mercapto-Gruppe(n) und/oder Hydroxy-Gruppe(n) in einer solchen Weise enthält, daß die Gesamtzahl der Mercapto- und Hydroxy-Gruppe(n) pro Molekül nicht weniger als 2 beträgt.
5. Verfahren gemäß Ansprüchen 2 oder 4, worin die Verbindung (b_2) mindestens einen Cyclohexyrling aufweist.
6. Optisches Material, umfassend ein Polymer, das erhalten wird durch Polymerisieren von:
einer Komponente (A), die mindestens eine Polythiol-Verbindung (a_1) mit der Formel [1] enthält,




[1]




worin $X-(CH_2CH_2S)_{n_2}-H$ ist, n_1 eine Ganzzahl von 1 bis 5 ist und n_2 eine Ganzzahl von 0 bis 2 ist und einer Komponente (B), die mindestens einen Vertreter aus einer Verbindung (b_1) mit mindestens zwei Vinyl-Gruppen pro Molekül, einer Verbindung (b_2) mit mindestens zwei Iso(thio)cyanat-Gruppen pro Molekül und einer Verbindung (b_3) mit mindestens einer Vinyl-Gruppe und mindestens einer Iso(thio)cyanat-Gruppe pro Molekül enthält.


7. Optisches Material gemäß Anspruch 6, worin die Polythiol-Verbindung ausgewählt wird der Gruppe bestehend aus Verbindungen der Formeln:



(S-1)



(S-2)




(S-4)

8. Optisches Material gemäß Anspruch 6, worin die Komponente (A) zusammen mit der Verbindung (a_1) eine Verbindung (a_2) mit Mercapto-Gruppe(n) und/oder Hydroxy-Gruppe(n) in einer solchen Weise enthält, daß die Gesamtzahl der Mercapto- und Hydroxy-Gruppe(n) pro Molekül nicht weniger als 2 beträgt.
9. Optisches Produkt gemäß Ansprüchen 6 oder 8, worin die Verbindung (b_2) mindestens einen Cyclohexyrling aufweist.
10. Optisches Produkt gemäß Anspruch 9, welches eine Plastiklinse ist.

Revendications

Revendications pour les Etats contractants suivants : CH, DE, FR, GB, IT, LI, NL, SE




1. Polythiol répondant à la formule [1]:




dans laquelle X est $-(CH_2CH_2S)_{n_2}-H$, n_1 est un entier de 1 à 5 et n_2 est un entier de 0 à 2.



2. Polythiol selon la revendication 1, qui est choisi parmi les composés représentés par les formules:






3. Matériau optique comprenant un polymère obtenu en polymérisant:
un composant (A) qui contient au moins un polythiol (a_1) de formule [1]:



dans laquelle X est $-(CH_2CH_2S)n_2-H$, n_1 est un entier de 1 à 5 et n_2 est un entier de 0 à 2 et
un composant (B) qui contient au moins un composé choisi parmi un composé (b_1) ayant au moins 2 groupes vinyliques par molécule, un composé (b_2) ayant au moins 2 groupes iso(thio)cyanates par molécule et un composé (b_3) ayant au moins un groupe vinyle et au moins un groupe iso(thio)cyanate par molécule.

4. Matériau optique selon la revendication 3, dans lequel le polythiol est choisi parmi les composés représentés par les formules:






5. Matériau optique selon la revendication 3, dans lequel le composant (A) contient, en même temps que le composé (a₁), un composé (a₂) qui a un ou des groupes mercapto et/ou un ou des groupes hydroxyles de telle manière que le nombre total des groupes mercapto et des groupes hydroxyles par molécule ne soit pas inférieur à 2.
6. Matériau optique selon la revendication 3 ou 5, dans lequel le composé (b₂) a au moins un noyau cyclohexyle.
7. Produit optique comprenant un matériau optique selon l'une quelconque des revendications 3 à 6.
8. Produit optique selon la revendication 7 qui est une lentille plastique.

Revendications pour l'Etat contractant suivant : ES


1. Procédé pour fabriquer un polythiol répondant à la formule suivante:



dans lequel on fait réagir un disulfure de diallyle avec le brome et on fait réagir le composé dimérisé cyclique résultant ayant des atomes de brome avec une thiourée pour former un sel d'isothiuronium, qui est ensuite hydrolysé par une solution aqueuse d'hydroxyde de sodium et ensuite acidifié par l'acide chlorhydrique pour obtenir le polythiol recherché.

2. Procédé pour fabriquer un matériau optique qui comprend la polymérisation d'un composant (A) qui contient au moins un polythiol (a₁) répondant à la formule [1]:






[1]


dans laquelle X est un groupe $-(\text{CH}_2\text{CH}_2\text{S})_{n_2}-\text{H}$, n_1 est un entier de 1 à 5 et n_2 est un entier de 0 à 2 et

un composant (B) qui contient au moins un composé choisi parmi un composé (b_1) ayant au moins 2 groupes vinytes par molécule, un composé (b_2) ayant au moins 2 groupes iso(thio)cyanates par molécule et un composé (b_3) ayant au moins un groupe vinyle et au moins un groupe iso(thio)cyanate par molécule.


3. Procédé selon la revendication 2, dans lequel le polythiol est choisi parmi les composés représentés par les formules suivantes:



(S-1)



(S-2)




(S-4)

4. Procédé selon la revendication 2, dans lequel le composant (A) contient, en même temps que le composé (a_1), un composé (a_2) qui a un ou des groupes mercapto et/ou un ou des groupes hydroxyles de telle manière que le nombre total des groupes mercapto et des groupes hydroxyles par molécule ne soit pas inférieur à 2.

5. Procédé selon la revendication 2 ou 4, dans lequel le composé (b_2) a au moins un noyau cyclohexyle.

6. Matériau optique comprenant un polymère obtenu en polymérisant:
un composant (A) qui contient au moins un polythiol (a_1) de formule [1]:




[1]




dans laquelle X est un groupe $-(CH_2CH_2S)_{n_2}-H$, n_1 est un entier de 1 à 5 et n_2 est un entier de 0 à 2 et

un composant (B) qui contient au moins un composé choisi parmi un composé (b_1) ayant au moins 2 groupes vinyliques par molécule, un composé (b_2) ayant au moins 2 groupes iso(thio)cyanates par molécule et un composé (b_3) ayant au moins un groupe vinyle et au moins un groupe iso(thio)cyanate par molécule.


7. Matériau optique selon la revendication 6, dans lequel le polythiol est choisi parmi les composés représentés par les formules:



(S-1)



(S-2)



(S-4)

8. Matériau optique selon la revendication 6, dans lequel le composant (A) contient en même temps que le composé (a_1), un composé (a_2) qui a un ou des groupes mercapto et/ou un ou des groupes hydroxyles de telle manière que le nombre total des groupes mercapto et des groupes hydroxyles par molécule ne soit pas inférieur à 2.

9. Produit optique selon la revendication 6 ou 8, dans lequel le composé (b_2) a au moins un noyau cyclohexyle.

10. Produit optique selon la revendication 9 qui est une lentille plastique.

