

DESCRIPTION

Title of the Invention: FOAMING AGENT COMPOSITION FOR
CIVIL ENGINEERING-CONSTRUCTION MATERIALS

Field of the Invention

[0001]

The present invention relates to a foaming agent composition for civil engineering-construction materials capable of forming bubbles that are applied to a civil engineering-construction material and have excellent stability.

Background of the Invention

[0002]

Bubbles are mixed in building materials such as mortar, concrete, cement milk, gypsum, ceramic porous materials, bricks, refractories and lightweight embankments mainly for the purpose of weight reduction. In addition, in a bubble shield method, bubbles are used for reduction of excavating resistance and abrasion of cutter heads and improvement of workability in excavated soil transportation operation. In addition, bubbles are also used for the purpose of excavation. A foaming agent is used for generating such bubbles that are used for civil engineering-construction materials.

[0003]

JP-A 2003-313060 discloses a foaming agent for a hydraulic composition that contains an alkyl ether sulfate salt having a hydrocarbon group with 8 to 18 carbons and an alcohol with 8 to 18 carbons at a specific weight ratio.

[0004]

JP-A 2015-168929 discloses a bubble shield method in which a foaming agent aqueous solution in which a hydrophobic film agent is made soluble with a water-soluble solvent and an anionic surfactant is further mixed is foamed at an expansion ratio of 10 to 50 to form bubbles, and the bubbles are injected into soil and sand on the working face and soil and sand in a chamber of a shield boring machine to form bubble-mixed soil.

Summary of the Invention

[0005]

The present invention provides a foaming agent composition for civil engineering-construction materials capable of forming bubbles that are applied to a civil engineering-construction material and have excellent stability.

[0006]

The present invention relates to a foaming agent composition for civil engineering-construction materials containing an anionic surfactant (A) [hereinafter, referred to as component (A)], a surfactant aid (B)

[hereinafter, referred to as component (B)], and a water-insoluble or slightly water-soluble nonionic surfactant (C) [hereinafter, referred to as component (C)].

[0007]

According to the present invention, provided is a foaming agent composition for civil engineering-construction materials capable of forming bubbles that are applied to a civil engineering-construction material and have excellent stability.

Bubbles that are used in the field of civil engineering-construction materials are required to be stable until the bubbles are mixed with a civil engineering-construction material. In addition, the bubbles are mixed with an inorganic material such as soil and sand or hydraulic powder, and therefore required to be stable when mixed with such a material. The foaming agent composition for civil engineering-construction materials of the present invention is capable of forming stable bubbles that meet these requirements.

Embodiments of the Invention

[0008]

<Foaming agent composition for civil engineering-construction materials>

[Component (A)]

Component (A) is an anionic surfactant. The anionic surfactant is preferably water-soluble. Here, "being

water-soluble" means that the solubility in 100 g of water at 25°C is 1.0 g or more. The solubility is preferably 2 g or more, more preferably 3 g or more from the viewpoint of improvement of solubility and the viewpoint of efficiently developing surface-active performance. Component (A) is, for example, an anionic surfactant having an alkyl group or alkenyl group with 8 or more and 22 or less carbons from the viewpoint of improvement of foamability.

The anionic surfactant having an alkyl group or alkenyl group with 8 or more and 22 or less carbons is, for example, one or more selected from alkyl or alkenyl sulfonic acids having an alkyl group or alkenyl group with 8 or more and 22 or less carbons, alkyl or alkenyl sulfates having an alkyl group or alkenyl group with 8 or more and 22 or less carbons, olefin sulfonic acids whose olefin has 8 or more and 22 or less carbons, polyoxyalkylene alkyl or alkenyl ether sulfates having an alkyl group or alkenyl group with 8 or more and 22 or less carbons, polyoxyalkylene alkyl or alkenyl ether carboxylic acids having an alkyl group or alkenyl group with 8 or more and 22 or less carbons, and salts thereof from the viewpoint of improvement of foamability and availability.

The anionic surfactant having an alkyl group or alkenyl group with 8 or more and 22 or less carbons is preferably one or more selected from alkyl or alkenyl

sulfates having an alkyl group or alkenyl group with 8 or more and 22 or less carbons, olefin sulfonic acids whose olefin has 8 or more and 22 or less carbons, polyoxyalkylene alkyl or alkenyl ether sulfates having an alkyl group or alkenyl group with 8 or more and 22 or less carbons, and salts thereof from the viewpoint of improvement of foamability and availability.

Examples of the salt of the anionic surfactant include alkali metal salts such as sodium salts and potassium salts, ammonium salts and organic ammonium salts.

[0009]

The polyoxyalkylene alkyl or alkenyl ether sulfate (hereinafter, also referred to as AES) having an alkyl group or alkenyl group with 8 or more and 22 or less carbons is preferably one having an oxyalkylene group having an average number of added moles of 0.5 or more and 50 or less from the viewpoint of improvement of foamability and water solubility. Examples of the oxyalkylene group include an oxyethylene group, an oxypropylene group, and groups obtained by block and/or random addition thereof, and an oxyethylene group is preferable from the viewpoint of water solubility.

From the viewpoint of water solubility and formation of fine bubbles, the number of carbons in the alkyl group or alkenyl group in the AES is 8 or more and 22 or less,

preferably 10 or more, more preferably 12 or more, and preferably 16 or less, more preferably 14 or less.

From the viewpoint of formation of stable bubbles, the AES has an average number of moles of added oxyalkylene group of 0.5 or more and 50 or less, preferably 1 or more, and preferably 25 or less, more preferably 15 or less, further preferably 10 or less, furthermore preferably 5 or less, furthermore preferably 3 or less.

[0010]

The polyoxyalkylene alkyl or alkenyl ether carboxylic acid (hereinafter, also referred to as an ether carboxylic acid) having an alkyl group or alkenyl group with 8 or more and 22 or less carbons is preferably one having an oxyalkylene group having an average number of added moles of 0.5 or more and 50 or less from the viewpoint of improvement of foamability and water solubility. Examples of the oxyalkylene group include an oxyethylene group, an oxypropylene group, and groups obtained by block and/or random addition thereof, and an oxyethylene group is preferable from the viewpoint of water solubility.

From the viewpoint of water solubility and formation of fine bubbles, the number of carbons in the alkyl group or alkenyl group in the ether carboxylic acid is 8 or more and 22 or less, preferably 10 or more, more

preferably 12 or more, and preferably 22 or less, more preferably 18 or less.

From the viewpoint of formation of stable bubbles, the ether carboxylic acid has an average number of moles of added oxyalkylene group of 0.5 or more and 50 or less, preferably 1 or more, and preferably 25 or less, more preferably 15 or less, further preferably 10 or less, furthermore preferably 5 or less, furthermore preferably 1 or less.

[0011]

Component (A) is more preferably a polyoxyalkylene alkyl or alkenyl ether sulfate having an alkyl group or alkenyl group with 8 or more and 22 or less carbons, or a salt thereof from the viewpoint of water solubility, stability in hard water, foamability and safety.

[0012]

[Component (B)]

Component (B) is a surfactant aid. A surfactant aid has low surface-active performance in itself, but improves the surface-active performance of component (A) when used in combination with component (A).

Component (B) is, for example, a hydrocarbon derivative having 8 or more and 22 or less carbons. Here, examples of the hydrocarbon derivative include higher alcohols and higher fatty acids.

Component (B) is preferably water-insoluble or slightly water-soluble from the viewpoint of formation of

stable bubbles. Here, "being water-insoluble or slightly water-soluble" means that the solubility in 100 g of water at 25°C is 0.1 g or less. The solubility is preferably 0.05 g or less, more preferably 0.01 g or less from the viewpoint of efficiently improving surface-active performance.

In addition, the melting point of component (B) is preferably higher than the melting point of component (C) described later from the viewpoint of formation of stable bubbles. The melting point of component (B) is preferably 5°C or higher, more preferably 10°C or higher, further preferably 15°C or higher.

[0013]

Component (B) is preferably one or more compounds selected from monohydric alcohols having 8 or more and 22 or less carbons and fatty acids having 8 or more and 22 or less carbons from the viewpoint of formation of stable bubbles.

From the viewpoint of water insolubility, bubble stability, safety and improvement of stiffness of bubble films, the number of carbons in the monohydric alcohol or the fatty acid is 8 or more and 22 or less, preferably 10 or more, more preferably 12 or more, and preferably 16 or less, more preferably 14 or less.

Examples of the monohydric alcohol having 8 or more and 22 or less carbons include octanol, decanol, dodecanol, tetradecanol, hexadecanol and octadecanol, and

decanol, dodecanol, tetradecanol, hexadecanol and octadecanol are more preferable from the viewpoint of formation of more stable bubbles. Two or more of these alcohols may be used in combination.

Examples of the fatty acid having 8 or more and 22 or less carbons include octanoic acid, decanoic acid, dodecanoic acid, tetradecanoic acid and hexadecanoic acid. Two or more of these fatty acids may be used in combination.

[0014]

From the viewpoint of water insolubility, bubble stability, compatibility with component (A) and product liquidity, component (B) is preferably a monohydric alcohol having 8 or more, further 10 or more, further 12 or more and 22 or less, further 16 or less, further 14 or less carbons.

[0015]

[Component (C)]

Component (C) is a water-insoluble or slightly water-soluble nonionic surfactant. For component (C), "being water-insoluble or slightly water-soluble" means that the solubility in 100 g of water at 25°C is 0.1 g or less. The solubility is preferably 0.05 g or less, more preferably 0.01 g or less from the viewpoint of efficiently improving surface-active performance.

In addition, the melting point of component (C) is preferably lower than the melting point of component (B)

described above from the viewpoint of formation of stable bubbles. The melting point of component (C) is preferably lower than 5°C, more preferably 3°C or lower.

[0016]

The water-insoluble or slightly water-soluble nonionic surfactant as component (C) is, for example, a nonionic surfactant having an alkyl group or alkenyl group with 5 or more and 22 or less carbons. The nonionic surfactant having an alkyl group or alkenyl group with 5 or more and 22 or less carbons is, for example, a polyether compound and/or a polyol.

[0017]

Examples of the polyether compound having an alkyl group or alkenyl group with 5 or more and 22 or less carbons include polypropylene glycol monoalkyl ethers, poly(propylene/ethylene) glycol monoalkyl ethers, polypropylene glycol fatty acid esters and poly(propylene/ethylene) glycol fatty acid esters.

A polyether compound having an alkyl group or alkenyl group with 8 or more and 22 or less carbons is preferable from the viewpoint of improvement of bubble stability and improvement of bubble stiffness.

[0018]

The polyether compound is preferably one that has one alkyl group with 8 or more and 22 or less, preferably 18 or less carbons and that has an average number of moles of added oxyalkylene group of 1 or more, preferably

2 or more, more preferably 3 or more and 10 or less, preferably 8 or less, more preferably 7. The oxyalkylene group is preferably a polyether compound having a large amount of an oxypropylene group from the viewpoint of improvement of water insolubility. Specifically, the ratio of the average number of moles of added oxypropylene group to the average number of moles of all added oxyalkylene groups is preferably 50% or more.

From the viewpoint of formation of stable bubbles, the polyether compound having an oxypropylene group is preferably a polypropylene glycol monoalkyl ether having one alkyl group with 8 or more and 22 or less carbons, more preferably a polypropylene glycol monoalkyl ether that has one alkyl group with 8 or more and 22 or less carbons and that has an average number of moles of added oxypropylene of 1 or more and 10 or less.

[0019]

In addition, examples of the polyol having an alkyl group or alkenyl group with 5 or more and 22 or less carbons include glyceryl ethers, 1,2-diols such as 1,2-dodecanediol and 1,2-tetradecanediol, glycerin fatty acid esters, sorbitan fatty acid esters, alkyl glucosides and sucrose fatty acid esters. Among them, preferable are glyceryl ethers having an alkyl group or alkenyl group with 5 or more and 22 or less carbons, more preferable are glyceryl ethers having an alkyl group with 5 or more and 22 or less carbons, and further preferable are alkyl

monoglyceryl ethers having one alkyl group with 5 or more and 22 or less carbons from the viewpoint of improvement of bubble stability and improvement of bubble stiffness.

[0020]

The number of carbons in the alkyl group or alkenyl group bonded to a polyol, particularly a glyceryl ether is 5 or more, preferably 8 or more from the viewpoint of improvement of water insolubility, and 22 or less, preferably 18 or less from the viewpoint of blending stability.

[0021]

From the viewpoint of improvement of bubble stability and improvement of bubble stiffness, component (C) is preferably one or more water-insoluble or slightly water-soluble nonionic surfactants selected from polypropylene glycol monoalkyl ethers that have one alkyl group with 8 or more and 22 or less carbons and that have an average number of moles of added oxypropylene of 1 or more and 10 or less, and alkyl monoglyceryl ethers having one alkyl group with 5 or more and 22 or less carbons.

From the viewpoint of improvement of bubble stability and improvement of bubble stiffness, component (C) is more preferably one or more water-insoluble or slightly water-soluble nonionic surfactants selected from alkyl monoglyceryl ethers having one alkyl group with 5 or more and 22 or less carbons.

[0022]

In Patent Document 2, a hydrophobic film agent such as a higher alcohol is made water-soluble with a water-soluble solvent, but because the water-soluble solvent is water-soluble, it is poor in power of dissolving a higher alcohol or the like having high hydrophobicity in a water-coexistent product, and thus, for making the hydrophobic film agent soluble, it is necessary to add a large amount of the water-soluble solvent in the product, resulting in impairment of foam stability that is essential during generation of bubbles.

On the other hand, component (C) for use in the present invention has a hydrophobic group and a hydrophilic group in the molecule, and has a property of being hardly dissolved in both water and oil, and therefore when blended in a system including component (A) and component (B), component (C) is easily arranged at a micellar interface, so that component (B) can be stably blended, and further, an effect of improving foamability and bubble stiffness is exhibited.

[0023]

[Composition etc.]

From the viewpoint of obtaining sufficient foamability, the foaming agent composition for civil engineering-construction materials of the present invention contains component (A) in an amount of preferably 60% by mass or more, more preferably 70% by mass or more, further preferably 75% by mass or more, and

preferably 95% by mass or less, more preferably 93% by mass or less, further preferably 90% by mass or less provided that the total of component (A), component (B) and component (C) is 100% by mass.

[0024]

From the viewpoint of bubble stability, the foaming agent composition for civil engineering-construction materials of the present invention contains component (B) in an amount of preferably 2.5% by mass or more, more preferably 3% by mass or more, further preferably 5% by mass or more, and preferably 20% by mass or less, more preferably 16% by mass or less, further preferably 13% by mass or less provided that the total of component (A), component (B) and component (C) is 100% by mass.

[0025]

From the viewpoint of foaming enhancement and solubility of component (B), the foaming agent composition for civil engineering-construction materials of the present invention contains component (C) in an amount of preferably 2.5% by mass or more, more preferably 3% by mass or more, further preferably 5% by mass or more, and preferably 20% by mass or less, more preferably 16% by mass or less, further preferably 13% by mass or less provided that the total of component (A), component (B) and component (C) is 100% by mass.

[0026]

From the viewpoint of bubble stability, the mass ratio of component (B) to component (A), $(B)/(A)$ in the foaming agent composition for civil engineering-construction materials of the present invention is preferably 0.03 or more, more preferably 0.06 or more, further preferably 0.08 or more, and preferably 0.20 or less, more preferably 0.18 or less, further preferably 0.15 or less.

[0027]

Preferably, the foaming agent composition for civil engineering-construction materials of the present invention contains water. The foaming agent composition for civil engineering-construction materials of the present invention is, for example, a foaming agent composition for civil engineering-construction materials containing component (A), component (B), component (C) and water. The foaming agent composition for civil engineering-construction materials of the present invention contains water in an amount of preferably 30% by mass or more, preferably 40% by mass or more, more preferably 50% by mass or more, further preferably 60% by mass or more, and preferably 95% by mass or less, more preferably 90% by mass or less, further preferably 85% by mass or less. In foaming agent composition for civil engineering-construction materials containing component (A), component (B), component (C) and water, the content of the total of component (A), component (B) and

component (C) may be 5% by mass or more and 70% by mass or less.

When the foaming agent composition for civil engineering-construction materials of the present invention, which contains component (A), component (B), component (C) and water, is prepared, it is preferable that component (A) is dissolved in water in advance, and the solution is mixed with component (B) and component (C) from the viewpoint of solubility of component (B) in water.

[0028]

The foaming agent composition for civil engineering-construction materials of the present invention may optionally contain a thickener, a chelating agent, a heavy metal scavenger, a surfactant, a rust inhibitor, a preservative, a colorant, a perfume, a defoaming agent, a solvent, a dispersant, a coagulant, a water-soluble polymer and so on. For the above, those that do not correspond to component (A), component (B) and component (C) are used.

[0029]

Examples of the civil engineering-construction material that is targeted by the foaming agent composition for civil engineering-construction materials of the present invention include lightweight milk (bubble milk and air milk), lightweight mortar (cellular mortar and air mortar), lightweight concrete (cellular concrete

and air concrete), back-filling materials, inside-filling materials, building concrete blocks, ALC (lightweight cellular concrete), grout materials, ceramic porous materials, bricks, refractories, lightweight embankments and pumping mortar. It is expected that functions such as weight reduction, improvement of fluidity, heat insulating properties, heat resistance, imparting of viscosity and control of fluidity will be imparted by mixing of bubbles in these civil engineering-construction materials.

[0030]

The foaming agent composition of the present invention may be, for example, a foaming agent composition for hydraulic compositions. Specifically, the foaming agent composition of the present invention may be a foaming agent composition for gypsum slurry. In the foaming agent composition for hydraulic compositions such as a foaming agent composition for gypsum slurry, component (A) is preferably an alkyl or alkenyl sulfate having an alkyl group or alkenyl group with 8 or more and 22 or less carbons.

[0031]

In addition, the foaming agent composition of the present invention may be, for example, a foaming agent composition for lightweight hydraulic compositions, such as lightweight milk (bubble milk and air milk),

lightweight mortar (cellular mortar and air mortar), and lightweight concrete (cellular concrete and air concrete).

Preferably, the foaming agent composition for hydraulic compositions is used as an aqueous solution containing component (A), component (B) and component (C) at a concentration of 0.05% by mass or more and 2.0% by mass or less in total (calculated based on the form of solid content). The total content of component (A), component (B) and component (C) in the aqueous solution is more preferably 0.1% by mass or more and more preferably 1.5% by mass or less, furthermore preferably 1.0% by mass or less.

The method for producing a hydraulic composition is preferably a method in which such a foaming agent composition is foamed, so that a hydraulic substance is blended as froth to perform blending and weight reduction because bubbles are uniformly entrained. A diluted aqueous solution of the foaming agent composition or foaming agent may be formed, and directly kneaded into paste, slurry, mortar or concrete having cement or gypsum as a hydraulic substance. The method for adding the foaming agent composition of the present invention to the hydraulic composition is not limited, and the method for frothing the diluted aqueous solution of the foaming agent composition is also not limited. In addition, as the hydraulic composition using the foaming agent composition of the present invention, a hydraulic

composition containing cement, gypsum or a mixture thereof is suitable, and examples thereof include cement paste having a reduced weight, lightweight mortar, lightweight concrete and gypsum boards. The density (apparent density) of the hydraulic composition is preferably 0.5 to 2 (g/cm³).

[0032]

The present invention provides a bubble-containing hydraulic composition for civil engineering-construction materials that contains froth obtained by foaming a liquid composition containing the foaming agent composition for civil engineering-construction materials of the present invention and water, and a hydraulic composition.

In addition, the present invention provides a bubble-containing hydraulic composition for civil engineering-construction materials that contains a hydraulic powder, water, an anionic surfactant (A), a surfactant aid (B) and a water-insoluble or slightly water-soluble nonionic surfactant (C).

The mass ratio of water to hydraulic powder in the bubble-containing hydraulic composition for civil engineering-construction materials is preferably 0.1 or more, more preferably 0.15 or more, and preferably 1.0 or less, more preferably 0.8 or less. The hydraulic powder is composed of cement, gypsum or the like, and preferably includes cement. The bubble-containing hydraulic

composition for civil engineering-construction materials may contain a fine aggregate and/or a coarse aggregate. The bubble-containing hydraulic composition for civil engineering-construction materials may contain an admixture agent or admixture material known in the art.
[0033]

The present invention provides a method for producing a bubble-containing hydraulic composition for civil engineering-construction materials, the method including step 1 and step 2:

<step 1>

obtaining froth by foaming a liquid composition containing the foaming agent composition for civil engineering-construction materials of the present invention and water; and

<step 2>

mixing the froth obtained in step 1 with a hydraulic composition containing hydraulic powder and water.

The bubble-containing hydraulic composition for civil engineering-construction materials described above can be prepared by this production method. In step 1, the expansion ratio of the liquid composition is preferably 5 or more, more preferably 10 or more, and preferably 100 or less, more preferably 80 or less, depending on a use of the hydraulic composition, etc. In step 2, the froth is mixed in an amount of preferably 5% by volume or more, more preferably 10% by volume or more,

and preferably 100% by volume or less, more preferably 80% by volume or less relative to the amount of the hydraulic composition, depending on a use of the hydraulic composition, etc. In this production method, an admixture agent or admixture material known in the art can be mixed in step 1 and/or step 2.

[0034]

In addition, the present invention provides a method for producing a bubble-containing hydraulic composition for civil engineering-construction materials in which a hydraulic powder, water, an anionic surfactant (A), a surfactant aid (B), and a water-insoluble or slightly water-soluble nonionic surfactant (C) are mixed to prepare a hydraulic composition containing bubbles. The bubble-containing hydraulic composition for civil engineering-construction materials described above can be prepared by this production method.

[0035]

The present invention provides a bubble-containing gypsum slurry for civil engineering-construction materials that contains froth obtained by foaming a liquid composition containing the foaming agent composition for civil engineering-construction materials of the present invention and water, and gypsum.

In addition, the present invention provides a bubble-containing gypsum slurry for civil engineering-construction materials containing gypsum, water, an

anionic surfactant (A), a surfactant aid (B) and a water-insoluble or slightly water-soluble nonionic surfactant (C).

The mass ratio of water to gypsum in the bubble-containing gypsum slurry for civil engineering-construction materials is preferably 40% by mass or more, more preferably 50% by mass or more, and preferably 90% by mass or less, more preferably 80% by mass or less. The bubble-containing gypsum slurry for civil engineering-construction materials is suitable for gypsum boards.

[0036]

As gypsum, any of neutralized gypsum with high quality, phosphogypsum as a byproduct of phosphoric acid, flue-gas-desulfurized gypsum generated in thermal power generation, natural gypsum containing various impurities and clay, and mixtures thereof can be used.

Clay contained in gypsum is mainly composed of a water-containing silicate mineral (hereinafter, referred to as a clay mineral) having a layered structure, and examples of the clay mineral contained as a particulate mineral in the clay include kaolin minerals (kaolinite, dickite and nacrite), serpentines (lizardite, antigorite and chrysotile), mica clay minerals (illite, sericite, glauconite and celadonite), chlorite, vermiculite and smectites (montmorillonite, beidellite, nontronite, saponite and hectorite).

[0037]

Examples of the gypsum include anhydrous gypsum, hemihydrate gypsum and dihydrate gypsum. As raw material gypsum, natural gypsum, or chemical gypsum such as neutralized gypsum or byproduct gypsum can be used singly, or a mixture of two or more thereof can be used. The main chemical gypsum is, for example, phosphogypsum, fluorogypsum, titanium gypsum or flue-gas-desulfurized gypsum. In addition, the raw material gypsum may contain recycled gypsum. The recycled gypsum may be recycled gypsum that is recovered from any of waste gypsum boards generated in a gypsum board manufacturer itself, waste gypsum boards generated during new construction and during dismantling, and the like. The present invention can be suitably used for any of the raw material gypsums, and produces an excellent effect for blends of the raw material gypsums at various ratios.

In the present invention, additives to be used for gypsum boards etc. can be used. These additives include general-purpose water-reducing agents, defoaming agents, foam stabilizers, hardening adjusting agents, water repellents, adhesives and retarders, and further, glass fiber, carbon fiber, waste paper, virgin pulp or the like is added as reinforcing fiber, or a gypsum board is also prepared together with perlite, foamed styrene or the like as a lightweight aggregate.

[0038]

The present invention provides a method for producing a bubble-containing gypsum slurry for civil engineering-construction materials, the method including step 1 and step 2:

<step 1>

obtaining froth by foaming a liquid composition containing the foaming agent composition for civil engineering-construction materials of the present invention and water; and

<step 2>

mixing the froth obtained in step 1 with a gypsum slurry containing gypsum and water.

The gypsum slurry for civil engineering-construction materials described above can be prepared by this production method. Step 1 and step 2 can be carried out in conformity to the method for producing the bubble-containing hydraulic composition for civil engineering-construction materials described above.

[0039]

In addition, the foaming agent composition of the present invention may be, for example, a foaming agent composition for a bubble shield method. In the foaming agent composition for a bubble shield method, component (A) is preferably an alkyl or alkenyl sulfate having an alkyl group or alkenyl group with 8 or more and 22 or less carbons.

Preferably, the foaming agent composition for a bubble shield method is used as an aqueous solution containing component (A), component (B) and component (C) at a concentration of 0.05% by mass or more and 2.0% by mass or less in total (calculated based on the form of solid content). The total content of component (A), component (B) and component (C) in the aqueous solution is more preferably 0.1% by mass or more, and more preferably 1.5% by mass or less, furthermore preferably 1.0% by mass or less.

[0040]

The foaming agent composition for a bubble shield method according to the present invention is used with bubbles injected to an excavation surface (excavation soil wall) at the time of carrying out a shield method. As a method for injecting bubbles, for example, a method can be used in which bubbles are jetted from a nozzle with pressure applied by a pump, but the method for injecting bubbles is not limited to a specific method.

[0041]

Hereinafter, a specific method for using the foaming agent composition for a bubble shield method according to the present invention will be described.

The foaming agent composition of the present invention, preferably an aqueous solution containing component (A), component (B) and component (C) at the above-described concentration is prepared, and foamed.

Next, foamed bubbles are sprayed to the excavation surface (excavation soil wall), the inside of a shield machine chamber or the inside of a screw conveyor, and kneaded with excavated soil and sand to perform excavation.

As a method for generating bubbles, component (A), component (B) and component (C) (when the components are powder, they are dissolved in water at an arbitrary concentration in advance), and water are transferred to a foaming agent composition mixing tank by respective exclusive pumps, and diluted aqueous solution diluted to an arbitrary concentration is prepared in the foaming agent composition mixing tank. Next, a drag (a bead-like article, torus-shaped article, column-shaped article or metallic scrubbing brush-like article is commonly used) is placed in a pipe, and compressed air and the diluted aqueous solution prepared as described above are simultaneously fed into the pipe containing the drag (generally referred to as a foaming pipe), so that a turbulent flow is produced to foam the diluted aqueous solution.

As a method for spraying bubbles, for example, a method can be used in which bubbles are jetted from an inlet of a shield machine to an excavation surface, the inside of a chamber, a screw conveyor or the like with pressure applied by a pump.

When the foaming agent composition for a bubble shield method according to the present invention is used, the previously prepared foaming agent composition of the present invention can be diluted with water by, for example, preferably 10 times or more, more preferably 20 or more, further preferably 50 or more, and preferably 500 times or less, more preferably 400 times or less, further preferably 200 times or less at a work site. Here, in view of the dilution ratio, the concentration of each component in the foaming agent is set to a high concentration (e.g. 10 to 500 times the concentration after dilution) so that the total content of component (A), component (B) and component (C) in the aqueous solution after dilution falls within a predetermined range.

In addition, a foaming agent composition prepared by mixing component (A), component (B), component (C) and water at a construction site as necessary can also be used as a foaming agent aqueous solution to be foamed.

The total concentration of component (A), component (B) and component (C) in the aqueous solution is preferably 0.2% by mass or more, more preferably 0.25% by mass or more, further preferably 0.4% by mass or more, furthermore preferably 0.5% by mass or more, and preferably 10% by mass or less, more preferably 5% by mass or less, further preferably 2% by mass or less, furthermore preferably 1% by mass or less. This

concentration may be applied to an aqueous solution of other foaming agent composition for use in the present invention. In addition, the concentration of an aqueous solution of other foaming agent composition for use in the present invention may be applied to the above-described aqueous solution.

The expansion ratio at the time of use is preferably 5 or more, and preferably 30 or less, more preferably 20 or less from the viewpoint of securing foam stability for effectively fluidizing soil and sand. The expansion ratio means a ratio of the air volume to the volume of the diluted aqueous solution of the foaming agent composition, and for example, an expansion ratio of 10 means that 9 parts by volume of air is kneaded with 1 part by volume of the aqueous solution to foam the aqueous solution to 10 parts by volume. Here, the volume of air is a volume under pressure applied to the ground or mountain to be excavated. Thus, in accordance with the Boyle's law ($PV = P'V'$), the amount of air supplied under atmospheric pressure is changed according to pressure.

[0042]

In addition, in the bubble shield method according to the present invention, the injection ratio of foam is preferably 10% or more, more preferably 15% or more, and preferably 50% or less, more preferably 30% or less. Here, the "injection ratio" means a volume of foam

injected into 1 part by volume of the ground or mountain to be excavated, and an injection ratio of 15% means that 0.15 parts by volume of foam is injected into 1 part by volume of the ground or mountain.

[0043]

A further example of the present invention will be shown below. The matters described in the foaming agent composition for civil engineering-construction materials of the present invention, the bubble-containing hydraulic composition for civil engineering-construction materials and the method for production thereof according to the present invention, and the bubble-containing gypsum slurry for civil engineering-construction materials and the method for production thereof according to the present invention can be applied to the following invention directly or with modifications appropriately made according to respective fields.

[0044]

The present invention provides a bubble-containing soil composition for civil engineering-construction materials that contains froth obtained by foaming a liquid composition containing the foaming agent composition for civil engineering-construction materials of the present invention and water, and soil.

[0045]

The present invention provides a bubble-containing soil composition for civil engineering-construction

materials containing soil, water, an anionic surfactant (A), a surfactant aid (B) and a water-insoluble or slightly water-soluble nonionic surfactant (C).

[0046]

The present invention provides a method for producing a bubble-containing soil composition for civil engineering-construction materials, the method including step 1 and step 2:

<step 1>

obtaining froth by foaming a liquid composition containing the foaming agent composition for civil engineering-construction materials of the present invention and water; and

<step 2>

kneading soil with froth obtained in step 1.

[0047]

The present invention provides a method for producing a foaming agent composition for civil engineering-construction materials in which an anionic surfactant (A), a surfactant aid (B) and a water-insoluble or slightly water-soluble nonionic surfactant (C) are mixed.

[0048]

The present invention provides use of a composition containing an anionic surfactant (A), a surfactant aid (B) and a water-insoluble or slightly water-soluble

nonionic surfactant (C) as a foaming agent composition for civil engineering-construction materials.

[0049]

The present invention provides a method for stabilizing froth for civil engineering-construction materials in which a surfactant aid (B) and a water-insoluble or slightly water-soluble nonionic surfactant (C) are used together with an anionic surfactant (A) when producing froth for civil engineering-construction materials from the anionic surfactant (A) and water.

[0050]

The present invention provides an excavation method in which froth obtained by foaming a liquid composition containing the foaming agent composition for civil engineering-construction materials of the present invention and water is supplied to excavate the ground.

[0051]

The present invention provides a method for treating excavated soil in which froth obtained by foaming a liquid composition containing the foaming agent composition for civil engineering-construction materials of the present invention and water is supplied to excavate the ground, a mixture of excavated soil and froth is taken out from an excavation site, and a defoaming agent is then added to the mixture to reduce the volume of the mixture.

Examples

[0052]

<Example 1 and Comparative Example 1>

(1) Preparation of foaming agent composition

Component (A), component (B) and component (C) shown in Table 1 were mixed with water at 70°C at a mass ratio shown in Table 2 so that the total content of these components was 20% by mass. Thereafter, the resulting mixture was stirred still at 70°C for 1 hour, confirmed to be homogeneous, and then cooled to room temperature (20°C) to obtain a foaming agent composition.

In Table 1-1, POE is an abbreviation for polyoxyethylene, and the numbers in parentheses are average numbers of moles of added oxyethylene group.

Components (A) in Table 1-1 all had a solubility of 1.0 g or more in 100 g of water at 25°C.

Components (B) in Table 1-2 all had a solubility of 0.1 g or less in 100 g of water at 25°C, and a melting point of 5°C or higher.

In addition, C-1 to C-4 in Table 1-3 all had a solubility of 0.1 g or less in 100 g of water at 25°C, and a melting point of lower than 5°C.

In addition, C'-1 in Table 1-3 was mixed with water at 25°C at an arbitrary ratio. It is to be noted that in Table 1-3, C'-1, which does not correspond to component (C), is shown in the column of component (C) for the sake of convenience.

[0053]

(2) Evaluation of appearance

The obtained foaming agent composition was left standing at room temperature (20°C) for 24 hours, and the appearance thereof was then visually confirmed, and evaluated in accordance with the following criteria. The results are shown in Table 2.

Homogeneous: The foaming agent composition is free from delamination of components and floating or sedimentation of precipitates, and looks the same throughout visually. The same applies when the foaming agent composition is cloudy.

Separated: The foaming agent composition suffers from floating or sedimentation of precipitates, is shown to be heterogeneous visually, and cannot be evenly collected.

[0054]

(3) Evaluation of foam stability

A diluted aqueous solution of a foaming agent composition, which consisted of 1 part by mass of a foaming agent composition containing component (A), component (B) and component (C) in an amount of 20% by mass in terms of a total content (balance: water), and of 99 parts by mass of water, was foamed using a pump type foam discharge vessel (vessel for Biore U Foam Hand Soap (Kao Corporation), expansion ratio: 12 based on the measured value). A graduated cylinder with a cap was filled with 200 mL of generated bubbles, and then left

standing, drainage amount d [mL] was measured after 60 minutes, the degree of foam stability was determined from the following formula, and foam stability was evaluated. It is meant that the higher the value of the degree of foam stability is, the more excellent the stability of foam is. The test was conducted at an ambient temperature of 20°C. The results are shown in Table 2.

$$\text{Degree of foam stability} = (1 - d/16.7) \times 100 \text{ [\%]}$$

[0055]

[Table 1]

Table 1-1

Component (A)	
Symbol	Name
A-1	POE (2) sodium alkyl (dodecyl/tetradecyl = 75/25 (mass ratio)) sulfate
A-2	POE (3) sodium dodecyl sulfate
A-3	A-1/A-2=1/1 (mass ratio)
A-4	POE (23) sodium oleyl sulfate
A-5	Triethanolamine dodecyl sulfate
A-6	Sodium olefin (C14-16) sulfonate ^{*1}

* 1 LIPOLAN LB-440 (manufactured by Lion Corporation)

Table 1-2

Component (B)	
Symbol	Name
B-1	Tetradecanol
B-2	Dodecanol
B-3	Tetradecanol/dodecanol = 1/1 (mass ratio)
B-4	Tetradecanoic acid

Table 1-3

Component (C)	
Symbol	Name
C-1	2-ethylhexyl glyceryl ether
C-2	Pentyl glyceryl ether
C-3	Isodecyl glyceryl ether
C-4	Polyoxypropylene (average number of added moles: 3) octyl ether
C'-1	Diethylene glycol monobutyl ether

[0056]

[Table 2]

		Foaming agent composition						Appearance	Degree of foam stability (%)
		Component			Content (% by mass)* ¹				
		(A)	(B)	(C)	(A)	(B)	(C)		
Example	1-1	A-1	B-1	C-1	79	12	9	Homogeneous	52
	1-2	A-1	B-1	C-1	80	11	9	Homogeneous	49
	1-3	A-1	B-1	C-1	86	5	9	Homogeneous	40
	1-4	A-1	B-1	C-1	82	9	9	Homogeneous	46
	1-5	A-1	B-1	C-1	84	7	9	Homogeneous	43
	1-6	A-2	B-1	C-1	82	9	9	Homogeneous	43
	1-7	A-2	B-1	C-1	84	7	9	Homogeneous	43
	1-8	A-1	B-1	C-4	82	9	9	Homogeneous	46
	1-9	A-3	B-1	C-1	82	9	9	Homogeneous	46
	1-10	A-4	B-2	C-2	82	9	9	Homogeneous	43
	1-11	A-5	B-3	C-4	82	9	9	Homogeneous	46
	1-12	A-6	B-4	C-3	82	9	9	Homogeneous	46
Comparative Example	1-1	A-1	—	C-1	90	0	10	Homogeneous	1
	1-2	A-1	B-1	—	90	10	0	Separated	28
	1-3	A-1	B-1	C'-1	82	9	9	Separated	31
	1-4	A-1	B-1	C'-1	77	8	15	Homogeneous	4

*1 Content (% by mass) provided that the total of component (A), component (B) and component (C) is 100% by mass

[0057]

The results in Table 2 show that the foaming agent composition of the present invention has excellent foamability and preparation stability.

[0058]

<Example 2 and Comparative Example 2>

Effects of the foaming agent compositions prepared in Example 1 and Comparative Example 1 were evaluated when they were used for air milk.

Among materials shown in Table 3, water and ordinary portland cement were put in a vessel, and then stirred by a hand mixer. After the resulting mixture was confirmed to be homogeneous, the foaming agent composition was then added, and the resulting mixture was further stirred and mixed for 1 minute to prepare air milk. The density and the flow value of the air milk were measured by the methods described below. In addition, the state of depression of the surface of the air milk was evaluated by the following method. The results are shown in Table 4.

[0059]

(1) Density

A stainless cup having an inner volume of 400 cm³ was filled with air milk, and the density was calculated from the mass.

(2) Flow value

Air milk was put in cylinder having an inner diameter of 8 cm and a height of 8 cm, and the diameter after drainage was measured.

(3) Depression of surface

Air milk was put in a mold for a strength measurement test sample, which had an inner diameter of 5 cm and a height of 10 cm, and the state of the air milk was observed at 20°C after 24 hours.

[0060]

[Table 3]

Material	Mass [g]
Water	500
Ordinary portland cement	500
Foaming agent composition	7.5

[0061]

[Table 4]

		Foaming agent composition							Air milk		
		Type	Component			Content (% by mass)*1			Flow [mm]	Density [g/cm ³]	Depression of surface
			(A)	(B)	(C)	(A)	(B)	(C)			
Example	2-1	Example 1-1	A-1	B-1	C-1	79	12	9	250	0.75	Not observed
	2-2	Example 1-6	A-2	B-1	C-1	82	9	9	255	0.78	Not observed
	2-3	Example 1-10	A-4	B-2	C-2	82	9	9	265	0.81	Not observed
	2-4	Example 1-11	A-5	B-3	C-4	82	9	9	263	0.80	Not observed
	2-5	Example 1-12	A-6	B-4	C-3	82	9	9	259	0.79	Not observed
Comparative Example	2-1	Comparative Example 1-1	A-1	—	C-1	90	0	10	500	1.45	Observed
	2-2	Comparative Example 1-4	A-1	B-1	C'-1	79	6	15	430	1.38	Observed

*1 Content (% by mass) provided that the total of component (A), component (B) and component (C) is 100% by mass

[0062]

The results in Table 4 show that by using the foaming agent composition of the present invention, stable foam is introduced, and therefore a moderate flow and density are imparted to air milk, resulting in production of air milk that enables construction as designed.

[0063]

<Example 3 and Comparative Example 3>

(1) Production of gypsum slurry

Water added with a water-reducing agent was added to a mixture of burnt gypsum and dihydrate gypsum, and the resulting mixture was stirred for 10 seconds at a high speed by a hand mixer. Thereafter, froth was added to gypsum slurry in an amount shown in Table 5, and the resulting mixture was stirred for 20 seconds at a high speed by a hand mixer.

Here, Mighty 150 (Kao Corporation) was used as the water-reducing agent.

In addition, the blending of the gypsum slurry was as shown in Table 5.

In addition, the froth was produced in the following manner: 300 mL of an aqueous solution containing a foaming agent composition, which had a composition shown in Table 6, at a concentration shown in Table 7 was put in a 1 L vessel, and shaken for 1 minute.

Components (A) in Table 6 all had a solubility of 1.0 g or more in 100 g of water at 25°C.

Components (B) in Table 6 all had a solubility of 0.1 g or less in 100 g of water at 25°C, and a melting point of 5°C or higher.

Components (C) in Table 6 all had a solubility of 0.1 g or less in 100 g of water at 25°C, and a melting point of lower than 5°C. It is to be noted that the

numbers in parentheses for components (C) in Table 6 are average numbers of moles of added oxypropylene group.

[0064]

(2) Evaluation

The obtained gypsum slurry was put in a mold for a columnar test sample, which had a diameter of 5 cm and a height of 10 cm. The gypsum slurry was left standing at room temperature for 30 minutes, and then dried at 60°C for 4 hours, and mass of the hardened test sample was measured, and the density was calculated. It is meant that the smaller the density is, the larger the amount of bubbles mixed in the hardened product is, i.e. the smaller the loss of bubbles during hardening is. The results are shown in Table 7.

[0065]

[Table 5]

Burnt gypsum (g)	Dihydrate gypsum (g)	Water (g)	Froth (mL)	Water-reducing agent (% by mass relative to burnt gypsum)
250	25	150	400	1

[0066]

[Table 6]

Foaming agent composition				
Symbol	Composition (% by mass)			
	Component (A)	Component (B)	Component (C)	Water
	Sodium decyl sulfate	Tetradecanol	Polyoxypropylene (3) octyl ether	
a-1	29			71
a-2	29	1.5	1.5	68
a-3	29	3	3	65

[0067]

[Table 7]

		Foaming agent composition		Test sample density (g/mL)
		Type	Concentration in aqueous solution for froth (% by mass)	
Comparative Example	3-1	a-1	0.2	0.777
	3-2	a-1	0.3	0.640
Example	3-1	a-2	0.2	0.530
	3-2	a-2	0.3	0.430
	3-3	a-3	0.2	0.440
	3-4	a-3	0.3	0.400

[0068]

<Example 4>

(1) Production of mortar

Mortar of blend A or blend B in Table 8 was prepared using the following materials.

<Materials>

Cement: ordinary portland cement (density: 3.16 g/cm³)

Admixture material: silica fume (density: 2.2 g/cm³)

Fine aggregate (ordinary sand): land sand from Kimitsu (surface-dry density: 2.61 g/cm³)

Fine aggregate (lightweight aggregate): artificial lightweight aggregate (true density: 0.69 g/cm³, average particle size: 250 μ m)

Admixture agent: high-performance AE water-reducing agent Mighty 21VS (manufactured by Kao Corporation)

Foaming agent composition: some of foaming agent compositions prepared in Example 1
[0069]

The water-bonding material ratio (W/B) was 20%. The water-bonding material ratio (W/B) is a mass ratio of water (W) to bonding material (B), and the bonding material includes ordinary portland cement and silica fume. The fine aggregate included ordinary sand and a lightweight aggregate. The amount of the foaming agent composition added was as shown in Table 9. In Table 9, the amount of the foaming agent composition added is shown as % by mass relative to the total of component (A), component (B) and component (C) in the foaming agent composition to the bonding material. In addition, the foaming agent composition was blended as a part of kneading water.

[0070]

For kneading and mixing the blended materials, a revolution-rotation type mortar mixer was used. Cement and silica fume were dry-kneaded for 30 seconds, Water was then added, the resulting mixture was kneaded for 120 seconds, a fine aggregate was put in, and the resulting mixture was then further kneaded for 120 seconds to prepare mortar containing bubbles.

[0071]

(2) Evaluation

In accordance with JIS A 1108, the mortar was taken in a mold, and removed from the mold after 24 hours, and the air content, the specific gravity and the strength of the hardened product were measured. The results are shown in Table 9.

The air content of the hardened product was determined by calculation from the specific gravity.

The specific gravity of the hardened product was calculated from the mass of the test sample in air and the volume of the test sample.

The strength of the hardened product was measured using a compression testing machine.

[0072]

[Table 8]

			Mortar	
			Blend A	Blend B
Blend material (g)	Water (W)		202	160
	Bonding material (B)	Cement (C)	911	718
		Silica fume (SF)	101	79
	Fine aggregate (S)	Ordinary sand	1214	—
		Lightweight aggregate	—	399
	Admixture agent (SP)	High-performance AE water-reducing agent	30.4	27.9
	Foaming agent composition	Example 1-1	Amount shown in Table 9	—
		Example 1-11	—	Amount shown in Table 9
W/B (%)			20	20

[0073]

[Table 9]

		Amount of foaming agent composition added (% by mass *1)	Hardened product of mortar		
			Air content (%)	Specific gravity	Compression strength (MPa)
Example 4-1-1	Mortar blend A	0.0	9.5	2.21	16.9
Example 4-1-2		0.2	25.6	1.82	10.7
Example 4-1-3		0.6	30.0	1.69	8.1
Example 4-1-4		1.0	32.7	1.64	7.0
Example 4-2-1	Mortar blend B	0.0	12.7	1.19	8.5
Example 4-2-2		0.2	41.4	0.79	4.5
Example 4-2-3		0.6	47.5	0.71	5.0
Example 4-2-4		1.0	58.1	0.57	3.4

*1 % by mass of the total of component (A), component (B) and component (C) relative to bonding material (cement and silica fume)

CLAIMS

1. A foaming agent composition for civil engineering-construction materials comprising an anionic surfactant (A), a surfactant aid (B) and a water-insoluble or slightly water-soluble nonionic surfactant (C).
2. The foaming agent composition for civil engineering-construction materials according to claim 1, wherein the anionic surfactant (A) is an anionic surfactant having an alkyl group or alkenyl group with 8 or more and 22 or less carbons.
3. The foaming agent composition for civil engineering-construction materials according to claim 1 or 2, wherein the anionic surfactant (A) is one or more selected from alkyl or alkenyl sulfonic acids having an alkyl group or alkenyl group with 8 or more and 22 or less carbons, alkyl or alkenyl sulfates having an alkyl group or alkenyl group with 8 or more and 22 or less carbons, olefin sulfonic acids whose olefin has 8 or more and 22 or less carbons, polyoxyalkylene alkyl or alkenyl ether sulfates having an alkyl group or alkenyl group with 8 or more and 22 or less carbons, polyoxyalkylene alkyl or alkenyl ether carboxylic acids having an alkyl group or alkenyl group with 8 or more and 22 or less carbons, and salts thereof.

4. The foaming agent composition for civil engineering-construction materials according to any one of claims 1 to 3, wherein the surfactant aid (B) is a hydrocarbon derivative with 8 or more and 22 or less carbons.

5. The foaming agent composition for civil engineering-construction materials according to any one of claims 1 to 4, wherein the surfactant aid (B) is one or more compounds selected from monohydric alcohols with 8 or more and 22 or less carbons, and fatty acids with 8 or more and 22 or less carbons.

6. The foaming agent composition for civil engineering-construction materials according to any one of claims 1 to 5, wherein the surfactant aid (B) is a monohydric alcohol with 8 or more and 22 or less carbons.

7. The foaming agent composition for civil engineering-construction materials according to any one of claims 1 to 6, wherein the water-insoluble or slightly water-soluble nonionic surfactant (C) is a nonionic surfactant having an alkyl group or alkenyl group with 5 or more and 22 or less carbons.

8. The foaming agent composition for civil engineering-construction materials according to any one of claims 1

to 7, wherein the water-insoluble or slightly water-soluble nonionic surfactant (C) is a polyether compound and/or polyol having an alkyl group or alkenyl group with 5 or more and 22 or less carbons.

9. The foaming agent composition for civil engineering-construction materials according to any one of claims 1 to 8, wherein the water-insoluble or slightly water-soluble nonionic surfactant (C) is a glyceryl ether having an alkyl group or alkenyl group with 5 or more and 22 or less carbons.

10. The foaming agent composition for civil engineering-construction materials according to any one of claims 1 to 9, wherein the anionic surfactant (A) is contained in an amount of 60% by mass or more and 95% by mass or less provided that the total of (A), (B) and (C) is 100% by mass.

11. The foaming agent composition for civil engineering-construction materials according to any one of claims 1 to 10, wherein the surfactant aid (B) is contained in an amount of 2.5% by mass or more and 20% by mass or less provided that the total of (A), (B) and (C) is 100% by mass.

12. The foaming agent composition for civil engineering-construction materials according to any one of claims 1 to 11, wherein the water-insoluble or slightly water-soluble nonionic surfactant (C) is contained in an amount of 2.5% by mass or more and 20% by mass or less provided that the total of (A), (B) and (C) is 100% by mass.

13. The foaming agent composition for civil engineering-construction materials according to any one of claims 1 to 12, wherein a mass ratio of (B) to (A), $(B)/(A)$, is 0.03 or more and 0.20 or less.

14. The foaming agent composition for civil engineering-construction materials according to any one of claims 1 to 13, comprising water.

15. A bubble-containing hydraulic composition for civil engineering-construction materials comprising: froth obtained by foaming a liquid composition containing the foaming agent composition for civil engineering-construction materials according to any one of claims 1 to 14 and water; and a hydraulic composition.

16. A bubble-containing hydraulic composition for civil engineering-construction materials comprising a hydraulic powder, water, an anionic surfactant (A), a surfactant

aid (B) and a water-insoluble or slightly water-soluble nonionic surfactant (C).

17. A bubble-containing hydraulic composition for civil engineering-construction materials, comprising the following step 1 and step 2:

<step 1>

obtaining froth by foaming a liquid composition containing the foaming agent composition for civil engineering-construction materials according to any one of claims 1 to 14 and water; and

<step 2>

mixing the froth obtained in step 1 with a hydraulic composition containing a hydraulic powder and water.

18. A method for producing a bubble-containing hydraulic composition for civil engineering-construction materials, wherein a hydraulic powder, water, an anionic surfactant (A), a surfactant aid (B) and a water-insoluble or slightly water-soluble nonionic surfactant (C) are mixed to prepare a hydraulic composition containing bubbles.

19. A bubble-containing gypsum slurry for civil engineering-construction materials comprising: froth obtained by foaming a liquid composition containing the foaming agent composition for civil engineering-

construction materials according to any one of claims 1 to 14 and water; and gypsum.

20. A bubble-containing gypsum slurry for civil engineering-construction materials comprising gypsum, water, an anionic surfactant (A), a surfactant aid (B) and a water-insoluble or slightly water-soluble nonionic surfactant (C).

21. A method for producing a bubble-containing gypsum slurry for civil engineering-construction materials, the method comprising the following step 1 and step 2:

<step 1>

obtaining froth by foaming a liquid composition containing the foaming agent composition for civil engineering-construction materials according to any one of claims 1 to 14 and water; and

<step 2>

mixing the froth obtained in step 1 with a gypsum slurry containing gypsum and water.

22. A bubble-containing soil composition for civil engineering-construction materials comprising: froth obtained by foaming a liquid composition containing the foaming agent composition for civil engineering-construction materials according to any one of claims 1 to 14 and water; and soil.

23. A bubble-containing soil composition for civil engineering-construction materials comprising soil, water, an anionic surfactant (A), a surfactant aid (B) and a water-insoluble or slightly water-soluble nonionic surfactant (C).

24. A method for producing a bubble-containing soil composition for civil engineering-construction materials, the method comprising the following step 1 and step 2:

<step 1>

obtaining froth by foaming a liquid composition containing the foaming agent composition for civil engineering-construction materials according to any one of claims 1 to 14 and water; and

<step 2>

kneading soil with the froth obtained in step 1.

25. A method for producing a foaming agent composition for civil engineering-construction materials, wherein an anionic surfactant (A), a surfactant aid (B) and a water-insoluble or slightly water-soluble nonionic surfactant (C) are mixed.

26. Use of a composition containing an anionic surfactant (A), a surfactant aid (B) and a water-insoluble or slightly water-soluble nonionic surfactant

(C) as a foaming agent composition for civil engineering-construction materials.

27. A method for stabilizing froth for civil engineering-construction materials, wherein a surfactant aid (B) and a water-insoluble or slightly water-soluble nonionic surfactant (C) are used together with an anionic surfactant (A) when producing froth for civil engineering-construction materials from the anionic surfactant (A) and water.