

A BACKPLATELESS SILICON MICROPHONE

FIELD OF THE INVENTION

The invention relates to a sensing element of a silicon condenser microphone and a method for making the same, and in particular, to a silicon microphone structure without a dedicated backplate that has perforated plates attached directly to a movable diaphragm.

BACKGROUND OF THE INVENTION

The silicon based condenser microphone also known as an acoustic transducer has been in a research and development stage for more than 20 years. Because of its potential advantages in miniaturization, performance, reliability, environmental endurance, low cost, and mass production capability, the silicon microphone is widely recognized as the next generation product to replace the conventional electret condenser microphone (ECM) that has been widely used in communication, multimedia, consumer electronics, hearing aids, and so on. Of all the silicon based approaches, the capacitive condenser type of microphone has advanced the most significantly in recent years. The silicon condenser microphone is typically comprised of two basic elements which are a sensing element and a pre-amplifier IC device. The sensing element is basically a variable capacitor constructed with a movable compliant diaphragm, a rigid and fixed perforated backplate, and a dielectric spacer to form an air gap between the diaphragm and backplate. The pre-amplifier IC device is basically configured with a voltage bias source (including a bias resistor) and a source follower preamplifier.

Although there have been numerous embodiments of the variable capacitor on silicon substrates, each prior art example includes a dedicated backplate in the construction of the microphone sensing element. Table 1 lists typical examples which employ various materials in the fabrication of a microphone sensing element.

Table 1. List of Prior Art for Silicon Condenser Microphones

Author/ Inventor	Year	Diaphragm	Backplate	Dielectric Spacer	Ref.
Hohm	1986	Nitride with metal	Silicon	Nitride	1
Bergqvist	1990	Silicon	Glass	Oxide	2
Kuhnel	1991	Nitride with Al	Silicon with Al	Oxide/Nitride	3
Scheeper	1992	PECVD Silicon rich Nitride (Au as metal)	Silicon	PECVD Si rich Nitride	4
Bernstein	1993	Silicon (typical)	Nickel (typical)	Oxide/Nitride	5
Bergqvist	1994	Silicon (1 st wafer)	Silicon (2 nd wafer)	Thermal Oxide	6
Zou	1996	Polysilicon	Silicon	Nitride+Oxide	7
Loeppert	1996	Polysilicon	Composite Silicon Nitride-Metal (or Polysilicon)	Silicon Nitride	8
Pedersen	1997	Polyimide with metal	Polyimide with metal	Polyimide + Oxide	9
Rombach	2000	Polysilicon	Polysilicon	Nitride+Oxide	10
Brauer	2001	Polysilicon	Silicon	Oxide	11
Loeb	2001	Composite (oxide- poly+metal+polymer)	Silicon	Oxide + Nitride	12

The references in Table 1 are the following: (1) D. Hohm and G. Hess, "A Subminiature Condenser Microphone with Silicon Nitride Membrane and Silicon Backplate", J. Acoust. Soc. Am., Vol. 85, pp. 476 - 480 (1989); (2) J. Bergqvist et al., "A New Condenser Microphone in Silicon", Sensors and Actuators, A21-23 (1990), pp. 123 -125; (3) W. Kuhnel et al., "A Silicon Condenser Microphone with Structured Backplate and Silicon Nitride Membrane", Sensors and Actuators A, Vol. 30, pp. 251 – 258 (1991); (4) P. Scheeper et al., "Fabrication of Silicon Condenser Microphones Using Single Wafer Technology", J. Microelectromech. Systems, Vol. 1, No. 3, pp. 147

– 154 (1992); (5) U.S. Patent No. 5,146,435 and U.S. Patent No. 5,452,268; (6) J. Bergqvist et al., “A Silicon Microphone Using Bond and Etch-back Technology”, *Sensors and Actuators A*, Vol. 45, pp. 115 – 124 (1994); (7) Zou, Quanbo, et al., “Theoretical and Experimental Studies of Single Chip Processed Miniature Silicon Condenser Microphone with Corrugated Diaphragm”, *Sensors and Actuators A*, Vol. 63, pp. 209 – 215 (1997); (8) U.S. Patent No. 5,490,220 and U.S. Patent No. 4,870,482; (9) M. Pedersen et al., “A Silicon Microphone with Polyimide Diaphragm and Backplate”, *Sensors and Actuators A*, Vol. 63, pp. 97 – 104 (1997); (10) P. Rombach et al., “The First Low Voltage, Low Noise Differential Condenser Silicon Microphone”, *Eurosensor XIV, The 14th European Conference on Solid State Transducers*, Aug. 27-30, 2000, pp. 213 – 216; (11) M. Brauer et al., “Silicon Microphone Based on Surface and Bulk Micromachining”, *J. Micromech. Microeng.*, Vol. 11, pp. 319 – 322 (2001); (12) PCT Patent Application No. WO 01/20948 A2.

The inclusion of a dedicated backplate in the microphone sensing element normally leads to manufacturing complications due to its special definitions in material and processing method. The required masking levels as well as the processing issues relating to overlay and spacing between the diaphragm and backplate normally result in a complex and high cost fabrication.

Therefore, an improved structure for a silicon microphone is needed that enables the fabrication process to be simplified at a reduced cost. In particular, a novel design for the variable capacitor component is desirable so that fewer masking levels are needed to produce a microphone sensing element with improved performance.

SUMMARY OF THE INVENTION

One objective of the present invention is to provide a microphone sensing element that does not include a dedicated backplate component.

A further objective of the present invention is to provide a simplified method for fabricating a microphone sensing element.

These objectives are achieved with a microphone sensing element which in its most basic embodiment features a movable diaphragm that is supported at its edges or corners by mechanical springs that are anchored to a conductive substrate through rigid pads. Each pad is disposed on a dielectric layer which acts as a spacer to define an air gap between the diaphragm and substrate. Attached to the sides of the diaphragm are perforated plates made from the same material layer as the diaphragm, pads, and mechanical springs. One or more of the pads have an overlying first electrode which is an island of a conductive metal material that is connected by wiring to external circuitry. A second electrode of the same material composition is formed on the conductive substrate and is wired to complete a variable capacitor circuit. In one embodiment (SOI version), the diaphragm, perforated plates, pads, and mechanical springs are coplanar and are made from the same silicon layer and the dielectric spacer is an oxide layer. Both the diaphragm and perforated plates may be rectangular in shape. The perforated plates are positioned between adjacent mechanical springs. Perforations preferably comprise multiple rows and columns of holes. An air gap exists in the dielectric spacer layer between the substrate and the perforated plates and a back hole is formed in the substrate below the diaphragm so that a sound signal has a free path to the diaphragm and thereby induces vibrations in the diaphragm. The diaphragm, mechanical springs,

and perforated plates move up and down (perpendicular to the substrate) in a concerted motion during a vibration. This movement results in a capacitance change between the first and second electrodes which can be converted into an output voltage.

In a second embodiment wherein a silicon oxide layer such as tetraethyl orthosilicate (TEOS) is used as a sacrificial layer, the diaphragm, mechanical springs, pads, and perforated plates are all made from a thin polysilicon (poly 2) layer. The diaphragm with attached perforated plates may have bottom reinforcements that project below the bottom surface of the diaphragm that is aligned over a back hole in the substrate. The diaphragm may be square with four corners and four sides and with a perforated plate affixed to each side. Each of the four mechanical springs is formed in a lengthwise direction along a plane that passes through the center and a corner of the diaphragm and has two ends wherein one end is attached to the diaphragm and the other end is connected to a poly 2 anchor pad. Optionally, the mechanical springs are attached to the sides of the diaphragm and the perforated plates are affixed to the corners and portions of the adjoining diaphragm sides. The anchor pad or pad also serves as an electrical connection point. To reduce parasitic capacitance between the poly 2 anchor pad and the conductive substrate, the poly 2 anchor pad may not be coplanar with the diaphragm and may be raised away from the substrate by adding one or more dielectric oxide layers between the substrate and anchor pad. Another polysilicon (poly 1) pad may be interposed between the poly 2 anchor pad and the substrate to serve as an etch stop layer for oxide trench etching. A poly 2 filled trench in the shape of a wall continuously surrounds the inner edges of the interposed poly 1 pad. Vertical sections of the poly 2 anchor pad form a continuous ring around the edge of the poly 1 anchor

pad and thereby protect the oxide layer beneath the poly 1 anchor pad from being etched away in a release process. The oxide layer between the interposed poly 1 pad and substrate is protected with another dielectric layer made of silicon nitride or the like that can resist or delay the oxide release etching used to form the air gap. To further reduce parasitic capacitance, a plurality of mesh patterned deep trenches filled with oxide may be formed in the conductive silicon substrate wherever they are overlaid by the mechanical springs and their anchor pads.

In a third embodiment, the diaphragm has four attached perforated plates and four mechanical springs that connect the diaphragm at its corners to four pads (anchor pads) as in the second embodiment. However, the mechanical springs, pads, and diaphragm are coplanar and made from the same polysilicon layer which is a first distance from the substrate. The diaphragm may have bottom reinforcements as in the second embodiment. However, each mechanical spring is anchored to a horizontal section of a base element that is supported by a vertical section comprised of sidewalls that have a top, bottom, and width. The base element is preferably made of silicon rich silicon nitride (SRN) that fills four trenches to form four sidewalls arranged in a square or rectangular ring. The horizontal section of the SRN base is formed on a pad which in one embodiment is an extension of a mechanical spring. Thus, the diaphragm and its attached perforated plates are suspended over an air gap and a back hole in the substrate. A first electrode may be non-planar and formed on the top of a horizontal section and adjacent pad. A second electrode is formed on the substrate.

A fourth embodiment is shown that is a modification to the first embodiment in which a corner or edge support for the mechanical springs is replaced by a "center support"

configuration. A dielectric spacer layer that functions as a center rigid anchor pad is formed on the substrate below the center of the diaphragm and supports four mechanical springs that overlap on one end below a first electrode. The other ends of the mechanical springs are connected to the edge of the diaphragm. Each mechanical spring may have a rectangular shape with a lengthwise direction along one of two perpendicular planes that intersect at the center of the diaphragm and are perpendicular to the substrate. Along the lengthwise direction on either side of the mechanical springs are slots that separate the mechanical spring from the diaphragm. The back hole has four sections wherein one section is formed below each diaphragm quadrant defined by the two intersecting planes. The thickness of the dielectric spacer layer defines the thickness of the air gap between the diaphragm and substrate.

The present invention is also a simple method of fabricating a microphone sensing element that requires fewer masks than most of the conventional silicon condenser microphones having a dedicated backplate. An exemplary process sequence involves forming a dielectric spacer layer on a conductive substrate such as doped silicon. The dielectric spacer layer may be comprised of silicon oxide. A membrane film that may be doped silicon or polysilicon is then formed on the dielectric spacer layer. Next, a hardmask comprised of one or more layers that will subsequently be used for fabricating a back hole is formed on the back side of the substrate. A first photo mask is employed to generate one or more vias in the membrane film that extend through the dielectric spacer layer to contact the substrate. After a conductive layer which may be a composite of two or more metals is deposited on the front side, a second photo mask is used to remove the conductive layer except for one or more islands on the membrane

layer that are first electrodes and an island in one or more vias on the substrate that are second electrodes. Another photo mask is then employed to etch holes in portions of the membrane layer to define the perforated plates and form openings that define the edges of the perforated plates, mechanical springs, and pads. A fourth photo mask is used to etch an opening in the hard mask on the backside that allows KOH etchant or a deep RIE etch in a subsequent step to form a back hole in the substrate below the diaphragm. Finally, an etchant during a timed release step removes a portion of the dielectric spacer layer between the diaphragm and back hole to create an air gap so that the diaphragm becomes suspended over the air gap and the underlying back hole.

The simplest fabrication method to form the basic silicon microphone structure involves silicon-on-insulator (SOI) wafers. Those skilled in the art will appreciate that other fabrication methods including wafer-to-wafer bonding methods and polysilicon surface micromachining can be used to form the other embodiments or embodiments similar to those described herein.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a top view depicting a diaphragm with adjoining perforated plates and springs that terminate in pads according to one embodiment of the present invention.

FIG. 2 is a cross-sectional view showing the variable capacitor design for a microphone sensing element according to one embodiment of the present invention.

FIGS. 3 – 8 are cross-sectional views which illustrate a process flow involving four photo mask steps that form a microphone sensing element according to a first embodiment of the present invention.

FIG. 9 is a cross-sectional view illustrating a microphone sensing element according to a second embodiment of the present invention.

FIG. 10 is a top view of a microphone sensing element with a corner support and reinforcements according to the second embodiment.

FIG. 11 is an enlarged top view of a portion of the microphone sensing element depicted in FIG. 10.

FIG. 12 is a top view of a microphone sensing element with an edge support and reinforcements according to the second embodiment.

FIG. 13 is a top view of a microphone sensing element with a center support according to a fourth embodiment of the present invention.

FIG. 14 is a cross-sectional view of the microphone sensing element in FIG. 13.

FIG. 15 is a cross-sectional view showing a microphone sensing element according to a third embodiment of the present invention.

FIG. 16 is an oblique view and FIG. 17 is a cross-sectional view of a base element according to the third embodiment.

FIG. 18 is a top view of the microphone sensing element depicted in FIG. 15.

DETAILED DESCRIPTION OF THE INVENTION

The present invention is a sensing element for a capacitive condenser type of microphone that can readily be made with existing semiconductor materials and silicon micromachining processes. The figures are not necessarily drawn to scale and the relative sizes of various elements in the structures may be different than in an actual device. The present invention is based on the discovery that a high performance

microphone sensing element may be constructed without a dedicated backplate component. A microphone working capacitance is achieved with a conductive substrate having a back hole formed therein and with perforated plates affixed to a movable diaphragm above the substrate. The diaphragm may be connected to mechanical springs attached to rigid anchor pads on a dielectric spacer layer disposed on the substrate.

Referring to FIG. 1, a first embodiment of the microphone sensing element according to the present invention is depicted. The microphone sensing element **10** is constructed on a substrate **11** such as silicon which preferably has low resistivity. Optionally, the substrate **11** may be glass with a conductive layer formed thereon. The microphone sensing element **10** is based on a membrane film that is fabricated into diaphragm, mechanical springs, perforated plates, and pads. In the exemplary embodiment, there is an essentially square, planar diaphragm **13a** made of silicon, polysilicon that may be doped, Au, Ni, Cu, or other metal materials. Alternatively, the diaphragm may have a rectangular or circular shape. The diaphragm **13a** is supported at each of its four corners by mechanical springs **13b** which are made of the same material and have the same thickness as the diaphragm. The mechanical springs **13b** have a length **a**, a width **b**, and are formed along a plane that passes through the diaphragm center **e** and a corner. Each mechanical spring **13b** may have a rectangular, "U", or "L" shape that terminates in an anchor pad hereafter referred to as a pad **13c** that is comprised of the same material and has the same thickness as the diaphragm **13a**. For an illustrative purpose, the pads **13c** are shown as essentially square with a width and length **c** that is typically greater than the width **b** of the mechanical springs.

However, the pads **13c** may also have a rectangular shape or have rounded edges. In one embodiment, each mechanical spring **13b** is connected to a side of a pad **13c**.

The pads **13c** are anchored to the substrate **11** through a dielectric layer **12** that serves as a spacer so that the diaphragm **13a** and perforated plates **13d** are suspended over an air gap and a back hole (not shown) through which a sound signal may pass to induce a vibration in the diaphragm. In one aspect, the dielectric layer **12** is comprised of silicon oxide. This embodiment encompasses an SOI approach wherein the membrane film is comprised of silicon and the dielectric layer **12** is silicon oxide. Optionally, the dielectric layer **12** may be made of other dielectric materials used in the art and may be a composite with a plurality of layers therein.

Another important feature of the present invention is that a perforated plate **13d** which is rectangular in shape is adjoined to each side of the diaphragm **13a**. The perforated plate **13d** has a lengthwise dimension equal to or less than the length of the diaphragm side to which it is attached, a width that is less than its lengthwise dimension, and has the same composition and thickness as the diaphragm **13a**. Perforations consist of holes **19** that may be arranged in multiple columns and rows. The holes are needed to allow air ventilation and thus reduce the air damping in the narrow air gap (not shown) during vibrations.

There is a contact or first electrode **18a** comprised of metal layers like Cr/Au above each pad **13c** that serves as a connecting point to external wiring. Additionally, there are one or more second electrodes **18b** with the same composition as a first electrode located on the front side of the substrate **11**. A first electrode and second electrode are connected by wiring (not shown) to form a variable capacitor circuit. Again, for an

illustrative purpose, the first and second electrodes **18a**, **18b** are shown as square in shape although rounded corners or rectangular shapes may be adopted. A first electrode **18a** is smaller in length and width than the width **c** of a pad **13c** to allow for some overlay error in processing. Optionally, the first and second electrodes **18a**, **18b** may be a single or composite layer comprised of Al, Ti, Ta, Ni, Cu, or other metal materials.

The first embodiment is further illustrated in a cross-sectional view in FIG. 2 that is obtained from the cross-section along the dashed line **23 – 23** (FIG. 1). The variable capacitor circuit **24** is shown between first electrode **18a** and second electrode **18b**. There is a back hole **26** with sloping sidewalls that is aligned below the diaphragm **13a** in the substrate **11** and an air gap **28** in the spacer (dielectric layer **12**) that separates the perforated plates **13d** and mechanical springs **13b** from the substrate. Optionally, the back hole **26** may have vertical sidewalls. Through the back hole **26**, a sound signal **25** impinging on the bottom of the diaphragm **13a** induces a vibration **27** in the diaphragm, attached perforated plates **13a**, and mechanical springs **13b** which move in a concerted motion perpendicular to the substrate. In addition to the microphone sensing element **10**, it is understood that a silicon condenser microphone is comprised of a voltage bias source (including a bias resistor) and a source follower preamplifier but these components are not shown in order to simplify the drawing and direct attention to the key features of the present invention. The vibration **27** induced by a sound signal **25** will cause a change in capacitance in the variable capacitor circuit **24** that is converted into a low impedance voltage output by the source follower preamplifier.

A second embodiment of a sensing element in a backplateless silicon microphone according to the present invention is shown in FIGS. 9 – 12. The view in FIG. 9 is from a cross-section along the dashed line **47** as illustrated in the top view in FIG. 10. Note that the dashed line **47** is not linear in order to intersect all of the key features in the drawing. Referring to FIG. 9, a microphone sensing element **30** is based on a substrate **31** that is preferably a silicon wafer polished on front and back sides and having a (100) crystal orientation and a 0.01-0.02 ohm-cm resistivity. Optionally, the substrate is comprised of glass with a conductive layer thereon. To reduce the parasitic capacitance, regions on the front side of the substrate **31** that are overlaid by mechanical springs **41c** and pads **41d** have trenches **32** filled with an oxide layer **33** that also overlays the substrate. The oxide layer **33** and an overlying first polysilicon (poly 1) layer **34** form a stack in the shape of an island that covers the trenches **32** and a portion of the substrate **31** around the trenches also known as isolation trenches. From a top view (FIG. 10), the silicon nitride layer **36** as well as the underlying oxide layer and poly 1/oxide stack (not shown) supports each of the pads **41d** that anchor mechanical springs **41c** and a diaphragm **41b** with attached perforated plates **41e**.

Returning to FIG. 9, there is a thermal oxide layer **35** disposed on the front side of substrate **31** and on the poly 1/oxide stack above the trenches **32**. Above the thermal oxide layer **35** is a low pressure chemical vapor deposition (LPCVD) silicon nitride layer **36**. The silicon nitride layer **36** serves to protect the underlying thermal oxide layer **35** and the oxide layer **33**. On the back side of substrate **31** is a similar stack comprised of LPCVD silicon nitride layer **36b** on thermal oxide layer **35b**. An oxide layer **37** that may be comprised of low temperature oxide (LTO), LPCVD tetraethyl orthosilicate (TEOS),

plasma enhanced (PE) CVD oxide, or phosphosilicate glass (PSG) is disposed on portions of the LPCVD silicon nitride layer **36**.

Vertical sections of a rigid semiconductor layer preferably made of polysilicon are formed in the dielectric spacer stack comprised of thermal oxide layer **35**, silicon nitride layer **36**, and oxide layer **37** and contact the substrate **31** or the poly 1 layer **34** in certain regions outside the periphery of the diaphragm **41b**. In one embodiment, the vertical sections are polysilicon filled trenches **38a**, **38b**, **40**.

To reduce parasitic capacitance between the pad **41d** and substrate **31**, the pad **41d** may not be coplanar with the diaphragm **41b** and may be raised away from the substrate (compared with the diaphragm) by inserting a dielectric layer which in this case is oxide layer **33** on certain regions of the substrate **31**. Furthermore, the poly 1 layer **34** is interposed between the oxide layer **33** and thermal oxide layer **35** to serve as an etch stop to protect the oxide layer **33** when etching the trench **38b** through the thermal oxide layer **35** and oxide layer **37**. As a result, the filled trench **38b** continuously surrounds the edge of the poly 1 layer **34**. Note that portions of the oxide layer **37**, silicon nitride layer **36**, and thermal oxide layer **35** below the pad **41d** and horizontal section **41a** are completely enclosed within the filled trench **38a** and within filled trench **38b** and thereby the enclosed oxide layers **35**, **37** are protected from an etch that is applied to form the air gap **48** in a release step. Additionally, the oxide layer **33** below the poly 1 layer **34** is protected by the silicon nitride layer **36** that can resist or delay the oxide etching in the release step.

From a top perspective in FIG. 10, trench **38a** may have a square or rectangular shape that forms a continuous ring around the second electrode **45** and encloses a

portion of the dielectric spacer stack below the second electrode. Likewise, trench **38b** (not shown) has a square or rectangular shape that surrounds a first electrode **44**. A first electrode **44** may be disposed on the horizontal section of each pad **41d** above a portion of the silicon nitride layer **36** over the poly1/oxide stack. One or more second electrodes **45** are formed on the horizontal section **41a**. First and second electrodes may be a single layer or composite layer comprised of conductive materials such as Cr, Au, Al, Ti, Ta, Ni or Cu. Trench **40** forms a continuous wall that in one embodiment has a square ring shape which surrounds the diaphragm **41a**, pads **41d**, mechanical springs **41b**, and perforated plates **41e**. Filled trench **38a** and an overlying horizontal layer are comprised of a second polysilicon (poly 2) layer and form the rigid polysilicon layer **41a**. Filled trench **38b** is used to support a horizontal section of the rigid polysilicon layer otherwise known as pad **41d**. In other words, there is a horizontal section **41a** of the rigid polysilicon layer disposed on the vertical sections **41a**. Moreover, each pad **41d** is connected by vertical sections **41d** to an underlying poly1 layer **34**.

In an enlarged view of one pad area shown in FIG. 11, the filled trench **38b** is covered by pad **41d** and is shown as dashed lines. The filled trench **38b** surrounds a portion of the dielectric spacer stack below the first electrode **44**. It is understood that there is a filled trench **38b** also referred to as vertical sections **41d** below each pad **41d**.

Returning to FIG. 9, the horizontal section **41a** is coplanar with the diaphragm **41b** and perforated plates **41e** and has the same thickness as the diaphragm, perforated plates, mechanical springs **41c**, and pads **41d**. There is a back hole **46** formed in the substrate **31** that is surrounded by the back side hardmask stack comprised of silicon nitride layer **36b** and oxide layer **35b**. Although the back hole is shown with sloping

sidewalls as a result of silicon anisotropic etching like KOH etching, the back hole may also have vertical sidewalls as a result of silicon deep reactive ion etching (DRIE). In either case, the opening in the front side has a width that is smaller than the length of a diaphragm side.

The diaphragm **41b**, perforated plates **41e**, and mechanical springs **41c** are suspended over an air gap **48**. The air gap **48** is between the perforated plates **41e** and silicon nitride layer **36**. The diaphragm **41b**, perforated plates **41e**, and mechanical springs **41c** may have reinforcements **39** along their bottom sides that project downward toward substrate **31**. Reinforcements **39** are preferably employed when the diaphragm **41b** is thin (about 1 micron thick) and are not necessary when the diaphragm thickness is greater than about 3 microns. Note that the openings **43** separate the horizontal sections **41f** of the poly 2 layer from the perforated plates **41e** and pads **41d**. There is a trench **49** with a ring shape in the horizontal section **41f** of the poly 2 layer that isolates the horizontal section **41a** below the second electrode **45**.

The perspective in FIG. 10 shows one embodiment of how the perforated plates **41e**, pads **41d**, and mechanical springs **41c** are positioned around the diaphragm **41b** in a so called "corner support" configuration. A mechanical spring **41c** may be attached at one end to a corner of the diaphragm **41b** and extends outward along a plane that passes through the center of the diaphragm. The mechanical spring **41c** may also have a reinforcement **39** (outline shown by dashed lines below the diaphragm) and may have a length and width that are similar those of the mechanical spring **13b** described in the first embodiment. Furthermore, the reinforcements **39** may also be applied to the bottom surfaces of the perforated plates **41e** and mechanical springs **41c** because a

thin polysilicon layer (about 1 micron thick) is too compliant. The reinforcements **39** may comprise a ring that is concentric with the diaphragm shape and is formed on the bottom surface of the diaphragm near its edge. The top opening of the back hole **46** is indicated by dashed lines since it is below the diaphragm **41b**. A pad **41d** that has a mechanical spring **41c** attached may have a similar shape and size to that of pad **13c** described earlier. A first electrode **44** which has a length and width smaller than the length and width of pad **41d** may be disposed on one or more of the four pads.

In one aspect, the diaphragm **41b** has essentially a square shape. A perforated plate **41e** is adjoined to each side of the diaphragm **41b** and has a rectangular shape with a lengthwise dimension that is equal to or less than the length of a diaphragm side and a width that is less than its lengthwise dimension. Perforations (holes) **42** are preferably arranged in multiple rows and columns and may have a square, rectangular, or circular shape as mentioned in the first embodiment. Surrounding the three unattached sides of the perforated plates **41e** and pads **41d** are the openings **43** which expose the silicon nitride layer **36** above the substrate **31** and separate the perforated plates and pads from the horizontal sections **41f**. Reinforcements **39** help to strengthen the diaphragm **41b** and in one embodiment are arranged like spokes radiating from the center of the diaphragm. Although eight reinforcements are depicted, those skilled in the art will appreciate that other reinforcement designs involving various patterns are equally feasible.

The second embodiment has an advantage over the first embodiment in that the reinforcement ring **39** around the top opening of the back hole **46** prevents acoustic leakage through the air gap **48** (as shown in FIG. 9) and helps to avoid stiction.

Furthermore, parasitic capacitance is controlled in at least three ways. First, there are isolation trenches **32** filled with a dielectric layer in the substrate below the pads and the mechanical springs. Second, the filled trench **38b** that encloses the dielectric spacer stack below the pads **41d** provides protection for the oxide layers **35**, **37** and thus allows a smaller pad width than in the previous embodiment. Third, the distance between the pads and substrate is increased because of the insertion of the poly 1/oxide stack above the oxide filled trenches.

A third embodiment of a microphone sensing element according to the present invention is shown in FIGS. 15 – 18. The view in FIG. 15 is from a cross-section along the dashed line **70** in the top view depicted in FIG. 18. Note that the dashed line **70** is not linear in order to intersect all of the key features in the drawing. Referring to FIG. 15, a microphone sensing element **50** is based on a substrate **51** that is preferably a low resistivity silicon wafer polished on front and back sides. There is a thermal oxide layer **52** disposed on a portion of the front side of substrate **51** and above the thermal oxide layer is an LPCVD silicon nitride layer **53**. On an adjacent portion of substrate **51** is a second electrode **63**. The second electrode is comprised of a Cr/Au composite layer or is a single layer or composite layer comprised of Al, Ti, Ta, Ni, Cu, or other metal materials.

The back side of substrate **51** has a stack of layers in which a thermal oxide layer **52b** is disposed on the substrate and a silicon nitride layer **53b** is formed on the thermal oxide layer. A back hole **68** is formed in the substrate **51** wherein the opening in the front side is smaller than the opening in the back side when the back hole is formed by KOH etching. Alternatively, the back hole **68** may have vertical sidewalls as explained

previously in the second embodiment. The back hole **68** extends vertically (perpendicular to the substrate) through thermal oxide layer **52b** and silicon nitride layer **53b** on the back side and also extends essentially vertical from the front side of the substrate through the thermal oxide layer **52** and silicon nitride layer **53** to form an upper edge **69** that preferably has a square shape (not shown) when seen from a top view.

An important feature is that an SRN base having horizontal and vertical sections **61a**, **61b**, respectively, is formed on, within, and below each pad **58c**. The horizontal section **61a** serves as an electrical connection base while the vertical sections **61b** provide a rigid support for the pad **58c**. A horizontal section **61a** is disposed on the pad **58c** and preferably has a square shape which is centered above the vertical sections. Vertical sections **61b** are comprised of a ring shaped trench **60** that has four walls and is filled with the SRN layer that encloses a dielectric spacer stack (not shown) comprised of a lower thermal oxide layer **52**, a middle LPCVD silicon nitride layer **53**, and an upper PSG layer **56**. In a preferred embodiment, the trench **60** for each SRN base has four sections that intersect in a square shape although a rectangular or circular shape is also acceptable.

Referring to FIG. 16, an oblique view of the SRN base and surrounding elements in FIG. 15 has the first electrode **62** intentionally removed to show the relative size of the horizontal section **61a** of the SRN base on the pad **58c**. Note that the pad **58c** is actually an extension of the mechanical spring **58b** and may have a larger width than the mechanical spring. The horizontal section **61a** has a width **r** while the width **s** of a vertical section **61b** of the SRN base is generally smaller than **r**.

Referring to FIG. 17, the front section of the trench **60** has been removed to reveal the side walls (trench **60**) filled with SRN layer **61b** having a width v and the dielectric spacer stack between the side walls. A back section of trench **60** lies behind the dielectric spacer stack and SRN base **61b** and is not visible in this view. Trench **60** has a bottom that contacts the substrate **51** and has a lower portion that is formed in the thermal oxide layer **52** and silicon nitride layer **53**. The pad **58c** forms an overhang and extends away from the SRN base **61b** and opposite the mechanical spring **58b** by a distance n .

It is understood that a total of four SRN bases with horizontal sections **61a** and vertical sections **61b** are formed a similar distance from the edge **69** on substrate **51** and support the four pads **58c** (FIG. 18). The horizontal sections **61a** are not visible in FIG. 18 as they are completely covered by the first electrodes **62**. Thus, the four mechanical springs **58b** which are attached to the four pads **58c** and the diaphragm **58a** which is connected to the four mechanical springs are suspended above the back hole (not shown).

Returning to FIG. 15, there is an air gap **71a** having a thickness t_3 between the pad **58c** and the silicon nitride layer **53**. Above the horizontal section **61a** is a first electrode **62** with a similar thickness and composition as the second electrode **63**. The first electrode **62** preferably has a square shape when viewed from the top and covers the horizontal section and a portion of the pad **58c** but does not extend to the edge of the pad. The first electrode **62** may be non-planar with an inner portion (upper level) resting on the horizontal section **61a** while an outer portion formed on the pad **58c** is at a lower level. There is a middle portion of the first electrode disposed **62** along the side of the

horizontal section **61a** that connects the aforementioned inner and outer portions. A perforated plate **58d** with holes **64** adjoining a side of the diaphragm **58c** is separated from the silicon nitride layer **53** by the air gap **71b** which has the thickness t_3 . The pad **58c**, mechanical spring **58b**, perforated plate **58d** and the diaphragm **58a** are coplanar, have the same thickness, and are comprised of the same material which is preferably polysilicon although other semiconductor materials may be used.

There may be reinforcements **67** on the bottom surface of the diaphragm **58a** that project downward toward the back hole **66** and the substrate **51**. Reinforcements may not be necessary in an embodiment wherein the diaphragm is comprised of a polysilicon layer having a thickness of about 3 microns or greater. Although three reinforcements are depicted, a plurality of reinforcements **67** may be employed in a variety of designs including a spoke like pattern with an outer ring as illustrated previously for reinforcements **39** in the second embodiment. The reinforcements **67** are an integral part of the diaphragm **58a** and have the same composition as the diaphragm.

From a top view in FIG. 18, an exemplary embodiment depicts the orientation of the mechanical springs **58b** relative to the perforated plates **58d** and diaphragm **58a**. A mechanical spring **58b** extends outward from each corner of the diaphragm along a plane that passes through a corner and the center point **72** of the diaphragm. Each mechanical spring **58b** may have a rectangular shape with a lengthwise dimension along a plane that passes through a corner and center of the diaphragm. Optionally, the mechanical springs may have a "U" or "L" shape and may be attached to the center of each side of the diaphragm according to the "edge configuration" as appreciated by

those skilled in the art. A mechanical spring **58b** connects to a pad **58c** proximate to a first electrode **62**. The position and number of second electrodes **63** may vary but at least one second electrode is located on the substrate **51** in the vicinity of a first electrode **62**. Perforations (holes) **64** are preferably arranged in multiple rows and columns and may have a square, rectangular, or circular shape. Note that a perforated plate has a lengthwise dimension about equal to or less than the length of a diaphragm side and has a width that may be less than its lengthwise dimension.

The advantage of the third embodiment is that the SRN base serves as an anchor for a pad and overlying first electrode and thereby eliminates the need for a poly 1/oxide stack adopted in the second embodiment. Furthermore, no filled trenches are required for reducing substrate parasitic capacitance. However, the drawback is that formation of the SRN base is achieved with additional material deposition and etch processes.

All three embodiments anticipate a configuration wherein mechanical springs are attached to the center of each side of the diaphragm and a perforated plate is attached to adjacent sides of a diaphragm around a corner. In the exemplary embodiment depicted in FIG. 12 which is a modification of the second embodiment, the mechanical springs **41c** are attached to the center of each side of the diaphragm **41b** and a perforated plate **41e** is attached to adjacent sides of the diaphragm around a corner. This so called "edge support" configuration is identical to the previously described "corner support" approach except that the mechanical springs and perforated plate elements attached to the diaphragm are shifted along the edge (side) of the diaphragm by a distance equal to one half of the lengthwise dimension of a diaphragm side. Obviously, the pads connected to the ends of the mechanical springs and any

reinforcements on the bottom surfaces of the perforated plates and mechanical springs would also shift accordingly.

A fourth embodiment of a microphone sensing element according to the present invention is depicted in FIGS. 13 – 14 and is based on a “center support” configuration that is a modification of the first embodiment. However, those skilled in the art will appreciate that the second and third embodiments could also be modified to encompass a “center support” configuration. It is understood that the fourth embodiment relates to the microphone sensing element **10** and the composition of the various elements therein was described previously.

Referring to FIG. 13, a perforated plate **13d** is adjoined to each of four sides of the diaphragm **13a** as in the corner support approach described previously. However, in the exemplary embodiment, the mechanical springs **13b** are positioned within the diaphragm. A first pair of mechanical springs **13b** is formed along a plane **X-X'** that bisects the sides of the diaphragm **13a** and passes through the center of the diaphragm. The first pair of mechanical springs **13b** may have a rectangular shape with a lengthwise direction along the plane **X-X'** and are supported at one end by the dielectric spacer layer **12** and are connected to the edge of the diaphragm on the other end. A second pair of mechanical springs **13b** is formed along a plane **Y-Y'** that is perpendicular to the plane **X-X'** and passes through the center of the diaphragm and bisects the other two sides of the diaphragm. The second pair of mechanical springs have the same shape as the first pair of mechanical springs but with a lengthwise direction along the plane **Y-Y'** and are formed above the dielectric spacer layer on one end and on the other end are connected to the edge of the diaphragm **13a**. Note that

the four mechanical springs **13b** are coplanar with each other and with the diaphragm and overlap in a region above the dielectric spacer layer **12**. There is a rectangular slot **29** formed along each side of a mechanical spring so that the sides of the mechanical springs are separated from the diaphragm. The two rectangular slots **29** in each diaphragm quadrant disposed at right angles to each other are connected by small collar slots adjacent to the overlap region of the mechanical springs **13b**.

The dielectric spacer layer **12** has a thickness t_5 and may be a single or composite layer comprised of one or more oxide layers, silicon nitride layers, or other dielectric layers. Furthermore, the dielectric spacer layer **12** may have a circular or square shape and has a width w_2 .

Another important feature of the fourth embodiment is that the back hole **26** is comprised of four sections. There is one section of back hole formed in each quadrant of the substrate defined by the planes **X-X'** and **Y-Y'**. From a top down view, one back hole section is below the lower right quadrant of the diaphragm **13a** while the other three sections of back hole **26** are located below the upper right, upper left, and lower left quadrants of the diaphragm, respectively. A first electrode **18a** is disposed on the overlap region of the four mechanical springs above the dielectric spacer layer **12** while a second electrode **18b** is formed on the substrate **11** outside the periphery of the diaphragm **13a** and perforated plates **13d**.

Referring to FIG. 14, a cross-sectional view is shown that is taken along the plane **23-23** in FIG. 13. The plane **23-23** is not linear in order to intersect all of the key features in the microphone sensing element **10**. The dielectric spacer layer **12** is formed on a portion of substrate **11** as in the first embodiment. When a sound signal **25**

impinges on the diaphragm **13a** through the back holes **26**, a vibration **27** is induced wherein the diaphragm, mechanical springs **13b**, and perforated plates **13d** move up and down in a concerted motion. Note that only one rigid anchor pad below the center of the diaphragm is necessary in this approach. Although the back hole **26** is shown with vertical sidewalls, sloped sidewalls may be used, instead. The rectangular slots **29** should be at a certain distance away from the back holes **26** and should have a minimum width so as to prevent acoustic leakage from the diaphragm **13a**. In other words, a rectangular slot should not be formed above a back hole.

This embodiment has the advantages of the first embodiment but also provides additional advantages in that fewer pads are required and there is less parasitic capacitance. Furthermore, the center support allows symmetric relaxing of any intrinsic stress and the fabrication process employed for the second and third embodiments may be used as well for the fourth embodiment.

All four embodiments of the microphone sensing element have a similar advantage over prior art in that the resulting silicon microphone has no dedicated backplate and thus can be produced at a lower cost than heretofore achieved. Furthermore, a microphone sensing element according to the present invention can exhibit good performance that is similar to results obtained from prior art microphone sensing elements with a dedicated backplate feature.

The present invention is also a method of forming a previously described silicon microphone sensing element. In one process sequence illustrated in FIGS. 3 – 8, a method of forming the first embodiment as represented in FIG. 1 is provided that requires only four photomasks. The cross-sections in FIGS. 3 – 8 were obtained along

a non-linear cut which is in the same position relative to the substrate **11** as the dashed line **23 – 23** in FIG. 1.

Referring to FIG. 3, an exemplary process sequence for fabricating the microphone sensing element **10** involves forming a dielectric spacer layer **12** by a conventional oxidation or deposition methods on a substrate **11** such as doped silicon that is polished on both of its front and back sides. The dielectric spacer layer may be comprised of silicon oxide. A membrane film **13** that may be doped silicon or polysilicon is then formed on the dielectric spacer layer **12**. Those skilled in the art will appreciate that the membrane film **13** and dielectric spacer layer **12** could also be formed directly by a well known wafer bonding process. In an SOI approach where the dielectric spacer layer **12** is silicon oxide and the membrane film **13** is doped silicon, substrate **11** and the silicon layer **13** are provided with a resistivity of < 0.02 ohm-cm.

Next, a hardmask comprised of one or more layers that will subsequently be used for fabricating a back hole is formed on the back side of the substrate. In one embodiment, the back side hard mask is comprised of a thermal oxide layer **15** grown by a well known LPCVD method on the substrate **11** and a silicon nitride layer **16** deposited by an LPCVD method on the thermal oxide layer. Note that the thermal oxide/silicon nitride hard mask is simultaneously grown on the membrane film **13** but is subsequently removed by well known wet chemical or dry etching methods.

A first photo mask is employed to generate one or more vias **17** in the membrane film **13** that extend through the dielectric spacer layer **12** to contact the substrate. For example, in an SOI approach a reactive ion etch or plasma etch may be used to transfer the openings in a photoresist layer through a silicon membrane film **13** followed by a

wet buffered oxide etch (BOE) to remove the exposed dielectric spacer layer (oxide) **12** and extend the vias **17** to the substrate.

Referring to FIG. 4, a conductive layer **18** is formed on the membrane film **13** and in the via **17** by using conventional methods. The conductive layer **18** may be a single layer or a composite layer comprised of Cr, Au, Al, Ti, Ta, Ni, Cu, or other metal materials. A second photomask is employed to selectively etch the conductive layer **18** to define a first electrode **18a** on the membrane film **13** and a second electrode **18b** in a via **17**. There are four pads **13c** (FIG. 1) and a first electrode **18a** may be formed on each pad. Furthermore, there may be a plurality of second electrodes **18b** formed on the substrate **11**.

Referring to FIG. 5, the membrane film **13** is selectively etched with a third photomask to form holes **19** in sections of the membrane film that will become perforated plates **13d**. Although only one perforated plate **13d** is shown, there are typically four perforated plates formed per diaphragm. Additional openings **20** are produced by the same membrane film etch step and are used to separate a microphone sensing element **10** from an adjacent silicon layer and to define the pads **13c**, mechanical springs **13b**, perforated plates **13d** and a diaphragm **13a** as previously described.

Referring to FIG. 6, an opening **21** is formed on the back side of the substrate **11** by employing a fourth photomask to selectively remove portions of the silicon nitride layer **16** and thermal oxide layer **15** by an etch process known to those skilled in the art. The opening **21** is aligned below the diaphragm **13a**. From a bottom view (not shown), the

opening **21** is in the shape of a square which will define a back hole in the substrate in the following step.

Referring to FIG. 7, the substrate **11** is etched with a standard process involving a KOH solution to form a back hole **22**. Due to the silicon crystal structure in the silicon substrate **11**, sloping sidewalls are generated in which the width of the back hole **22** on the back side is larger than the width of the back hole on the front side. An important feature is that the width of the back hole on the front side must be smaller than the width of the diaphragm **13a**. In an alternative embodiment (not shown), a plasma etch or deep RIE (DRIE) process may be used to form a back hole **22** with vertical sidewalls.

Referring to FIG. 8, the back side hard mask comprised of silicon nitride layer **16** and thermal oxide layer **15** is removed by a known method. Conventional processing then follows in which the substrate is diced to physically separate microphone sensing elements from each other. There is a final release step in which a portion of the dielectric spacer layer **12** is removed. In the SOI embodiment, an oxide layer **12** is removed by a timed etch involving a buffered HF solution, for example. The oxide layer **12** is removed with proper control so that the regions below the pads **13c** can be kept and thereby serve to anchor the pads to the substrate. The diaphragm **13a** is attached to the pad **13c** by a mechanical spring **13b**. The diaphragm **13a**, mechanical springs **13b**, pads **13c**, and perforated plates **13d** are coplanar and all are comprised of a similar thickness of the membrane film. Although a rectangular shaped mechanical spring **13b** is shown (FIG. 1), other configurations such as a "U" shape or "L" shape are acceptable as appreciated by those skilled in the art.

It is understood that in addition to the microphone sensing element **10**, a silicon microphone is also comprised of a voltage bias source, a source follower preamplifier, and wiring to connect the first and second electrodes to complete a variable capacitor circuit. However, these features are not shown in order to simplify the drawings and direct attention to the key components of the present invention. The resulting silicon microphone has a simpler fabrication sequence than prior art methods which include a dedicated backplate construction. Furthermore, the method of the present invention is less expensive to practice in manufacturing since fewer photomasks are required.

While this invention has been particularly shown and described with reference to, the preferred embodiments thereof, it will be understood by those skilled in the art that various changes in form and details may be made without departing from the spirit and scope of this invention.

We claim:

1. A method of forming a microphone sensing element without a dedicated backplate component, comprising:

- (a) providing a substrate having a front side and a back side wherein a stack comprised of a lower dielectric spacer layer and an upper membrane film is formed on said front side and a hardmask is disposed on said back side;
- (b) forming a plurality of vias in said upper membrane film that extend through the lower dielectric spacer layer to contact said front side of the substrate;
- (c) forming a plurality of first electrodes at certain locations on said upper membrane film and a second electrode in one or more of said vias;
- (d) etching said upper membrane film to form openings that define a diaphragm and a perforated plate that adjoins each side or corner of the diaphragm, a mechanical spring having two ends that is connected on one end to the diaphragm and on the other end to a pad, and a pad that anchors each mechanical spring to the lower dielectric spacer layer;
- (e) etching an opening in said hardmask and a back hole in the substrate that are aligned below said diaphragm; and
- (f) removing a portion of said lower dielectric spacer layer in a release step to form an air gap between the diaphragm and the back hole.

2. The method of claim 1 wherein said substrate is comprised of silicon with a low resistivity and said membrane film is comprised of doped silicon or doped polysilicon having a low resistivity.

3. The method of claim 2 wherein the lower dielectric spacer layer is comprised of phosphosilicate glass (PSG), a thermal oxide, a tetraethyl orthosilicate (TEOS) layer, or a low temperature oxide.

4. The method of claim 1 wherein said hardmask is comprised of a thermal oxide layer, a low pressure CVD (LPCVD) silicon nitride layer, or is a composite layer comprised of both of the aforementioned layers.

5. The method of claim 1 wherein said first and second electrodes are comprised of a Au/Cr composite layer, or are a single or composite layer comprised of Al, Ti, Ta, Ni, Cu, or other metal materials.

6. The method of claim 1 wherein said diaphragm is essentially square and each side has a first length, and a perforated plate has a lengthwise dimension equal to or less than the first length and a width that is less than said lengthwise dimension.

7. The method of claim 1 wherein the holes in the perforated plate have a square, rectangular, or circular shape and are formed during the etching of said upper membrane film.

8. The method of claim 1 wherein a mechanical spring has a rectangular shape, a "U" shape, or an "L" shape from a top view.

9. The method of claim 1 wherein a mechanical spring has a first width and a pad has an essentially square shape and a width dimension that is equal to or greater than said first width.

10. The method of claim 6 wherein etching the back hole in the substrate is performed with a KOH etch and said back hole has sloped sidewalls in which an

opening on the back side has a larger width than an opening on the front side and the opening in the front side has a smaller width than the length of said diaphragm side.

11. The method of claim 6 wherein etching the back hole is performed with a deep RIE (DRIE) etch and said back hole has vertical sidewalls and a width that is smaller than the length of said diaphragm side.

12. The method of claim 1 wherein a certain location of a first electrode is on a pad.

13. The method of claim 1 wherein a first photomask is used for step (b), a second photomask is used for step (c), a third photomask is used for step (d), and a fourth photomask is employed for etching an opening in the hardmask in step (e).

14. The method of claim 1 wherein said membrane film is planar and the diaphragm, mechanical springs, and pads are coplanar and have an equivalent thickness.

15. A microphone sensing element without a dedicated backplate component, comprising:

- (a) a substrate having front and back sides with a back hole formed therein;
- (b) a dielectric spacer layer formed on the front side of the substrate;
- (c) a diaphragm with a first thickness, a center, four sides having a length, and four corners that is aligned above said back hole;
- (d) a rectangular perforated plate with a first thickness and a plurality of holes therein which adjoins each side or corner of the diaphragm, said perforated plate has lengthwise and widthwise dimensions and is suspended above an air gap that overlies the substrate;
- (e) a mechanical spring attached to each corner of said diaphragm wherein each mechanical spring has a first thickness, length, width, and two ends in which one

end is attached to a corner of the diaphragm and a second end is connected to a pad; and

(f) a pad connected to each mechanical spring, said pad has a first thickness, four sides, a length and width, and is formed on the dielectric spacer layer, said pad serves to anchor the mechanical springs and diaphragm which vibrate up and down (perpendicular to the substrate) in response to a sound signal that passes through the back hole and air gap.

16. The microphone sensing element of claim **15** further comprised of a first electrode formed on one or more pads, and one or more second electrodes formed on the substrate wherein a first electrode and a second electrode are connected to form a variable capacitor circuit.

17. The microphone sensing element of claim **16** wherein a first electrode and a second electrode are comprised of a Au/Cr composite layer, or are a single or composite layer comprised of Al, Ti, Ta, Ni, Cu, or other metal materials

18. The microphone sensing element of claim **15** wherein the diaphragm, mechanical springs, pads, and perforated plates are coplanar and comprised of silicon, polysilicon, Au, Cu, Ni, or other metal materials.

19. The microphone sensing element of claim **15** wherein said back hole has an opening in the front side of said substrate that has a first width which is less than the length of said diaphragm side and wherein the back hole has an opening in the back side of the substrate with a second width that is equal to or greater than the first width.

20. The microphone sensing element of claim **15** wherein a mechanical spring has a rectangular, "U", or "L" shape and a lengthwise direction along a plane that passes through the center and a corner of the diaphragm.

21. The microphone sensing element of claim **15** wherein a mechanical spring is attached to a side of a pad.

22. The microphone sensing element of claim **15** wherein the diaphragm has a square or rectangular shape.

23. The microphone sensing element of claim **15** wherein the dielectric spacer layer is comprised of a thermal oxide, a low temperature oxide, a TEOS layer, or a PSG layer.

24. The microphone sensing element of claim **15** wherein the substrate is comprised of either doped silicon having a low resistivity or glass having a conductive layer formed thereon.

25. A microphone sensing element without a dedicated backplate, comprising:

- (a) a substrate having front and back sides with a back hole formed therein;
- (b) a dielectric spacer stack formed on the front side of the substrate;
- (c) a diaphragm having a first thickness, a center, four corners, four sides with a length, and a bottom surface that is aligned above the back hole;
- (d) a rectangular perforated plate with a first thickness and a plurality of holes therein which adjoins each side or corner of the diaphragm, said perforated plate has lengthwise and widthwise dimensions and is suspended above an air gap formed in the dielectric spacer layer;

(e) a mechanical spring attached to each corner or side of said diaphragm wherein each mechanical spring has a first thickness, length, width, and two ends in which one end is attached to the diaphragm at a first distance above the substrate and a second end is connected to a pad at a second distance above the substrate wherein the second distance is greater than the first distance; and

(f) a pad comprised of a horizontal section of a semiconductor layer connected to each mechanical spring which is supported by rigid vertical sections of the semiconductor layer, said pad has a first thickness, four sides, a length and first width and said vertical sections have a depth and second width.

26. The microphone sensing element of claim **25** wherein the diaphragm, perforated plates, mechanical springs, and the semiconductor layer are comprised of a doped polysilicon layer.

27. The microphone sensing element of claim **25** further comprised of a dielectric stack comprised of a thermal oxide layer on the back side and a LPCVD silicon nitride layer formed on thermal oxide layer, and wherein the dielectric spacer stack formed on the front side is comprised of a lower thermal oxide layer, a middle LPCVD silicon nitride layer, and an upper oxide layer.

28. The microphone sensing element of claim **25** wherein the substrate is comprised of doped silicon having a low resistivity or is glass having a conductive layer formed thereon.

29. The microphone sensing element of claim **25** further comprised of a first electrode formed on one or more pads at said second distance from the substrate and a

second electrode disposed on one or more horizontal sections of the polysilicon layer formed said first distance from the substrate.

30. The microphone sensing element of claim **29** wherein a first electrode and a second electrode have an essentially square shape and are comprised of a Au/Cr composite layer, or are a single or composite layer comprised of Al, Ti, Ta, Ni, Cu, or other metal materials.

31. The microphone sensing element of claim **27** wherein said back hole has a front side opening with a first width that extends through said dielectric spacer stack and a back side opening with a second width that extends through said dielectric stack, said second width is equal to or larger than the first width.

32. The microphone sensing element of claim **25** wherein a mechanical spring has a rectangular, "U", or "L" shape and a lengthwise direction along a plane that passes through the center of the diaphragm.

33. The microphone sensing element of claim **29** wherein said vertical sections of the semiconductor layer are comprised of filled ring shaped trenches wherein a first trench surrounds the dielectric spacer stack below the first electrode and is formed on a stack comprised of an upper polysilicon layer and a lower thermal oxide layer in a first region and a second trench surrounds the dielectric spacer stack below a second electrode and contacts the substrate.

34. The microphone sensing element of claim **33** wherein the polysilicon/thermal oxide stack in the first region is formed on a portion of the substrate that has oxide filled trenches that together with the polysilicon/thermal oxide stack serve to reduce the parasitic capacitance between the pads and the substrate.

35. The microphone sensing element of claim **25** further comprised of reinforcements affixed to the bottom surface of the diaphragm which are comprised of the same material as in the diaphragm.

36. A microphone sensing element without a dedicated backplate, comprising:

- (a) a substrate having front and back sides with a back hole formed therein;
- (b) a dielectric spacer stack formed on the front side of the substrate;
- (c) a diaphragm with a first thickness, a center, four corners, four sides having a length, and a bottom surface that is aligned above the back hole;
- (d) a rectangular perforated plate with a first thickness and a plurality of holes therein which adjoins each side or corner of the diaphragm, said perforated plate has lengthwise and widthwise dimensions and is suspended above an air gap formed in the dielectric spacer stack;
- (e) a mechanical spring attached to each corner of said diaphragm wherein each mechanical spring has a first thickness, length, first width, and two ends in which one end is attached to the diaphragm and a second end is connected to a pad that serves as an electrical connection point;
- (f) a pad having a first thickness, four sides, a length and first width that is connected to each mechanical spring and is supported by a rigid base element; and
- (g) a base element in the form of a continuous wall comprised of four filled trenches wherein each filled trench has lengthwise and widthwise dimensions, a thickness, and a top and bottom wherein the bottom contacts the substrate and the top connects to a pad, said base element surrounds the dielectric spacer stack below each pad.

37. The microphone sensing element of claim **36** wherein the diaphragm, perforated plates, mechanical springs, and pads are coplanar and are comprised of polysilicon.

38. The microphone sensing element of claim **37** further comprised of polysilicon reinforcements formed on the bottom surface of the diaphragm.

39. The microphone sensing element of claim **36** wherein the substrate is comprised of doped silicon having a low resistivity.

40. The microphone sensing element of claim **36** further comprised of a dielectric stack comprised of a thermal oxide layer on the back side and an LPCVD silicon nitride layer on the thermal oxide layer and wherein the dielectric spacer stack is comprised of a lower thermal oxide layer, an LPCVD silicon nitride layer on the thermal oxide layer, and a PSG layer on the LPCVD silicon nitride layer.

41. The microphone sensing element of claim **36** further comprised of a first electrode formed on one or more base elements and one or more second electrodes disposed on the substrate wherein a first electrode is partially overlaid on an adjoining region of a pad.

42. The microphone sensing element of claim **41** wherein a first electrode and a second electrode are comprised of a Au/Cr composite layer, or are a single or composite layer comprised of Al, Ti, Ta, Ni, Cu, or other metal materials.

43. The microphone sensing element of claim **36** wherein said base element is comprised of a silicon rich silicon nitride (SRN) layer.

44. The microphone sensing element of claim **40** wherein said back hole has a front side opening with a first width that extends through the thermal oxide layer and LPCVD silicon nitride layer on the front side and a back side opening with a second width that

extends through the dielectric stack, said second width is greater than or equal to the first width and said first width is less than the length of a diaphragm side.

45. The microphone sensing element of claim **36** wherein a mechanical spring has a rectangular, "U", or "L" shape and a lengthwise direction along a plane that passes through the center and a corner of the diaphragm.

46. A microphone sensing element without a dedicated backplate, comprising:

(a) a substrate having front and back sides with a back hole formed therein, said back hole has four sections wherein one section is formed in each quadrant divided by first and second planes that are perpendicular to each other and to the substrate;

(b) a diaphragm having a first thickness, a center, edge, four corners, four sides with a length, and a bottom surface that is formed above the back hole in each of said quadrants and over an air gap formed between said bottom surface and the substrate;

(c) a dielectric spacer layer having a thickness and width formed on the front side of the substrate and below the center of said diaphragm;

(d) a rectangular perforated plate with a first thickness and a plurality of holes therein which adjoins each side of the diaphragm, said perforated plate is suspended above an air gap that overlies the substrate;

(e) a first pair of mechanical springs with two sides and two ends having a lengthwise dimension formed along the first plane, said mechanical springs are coplanar with the diaphragm and separated from the diaphragm by a slot along each side and wherein one end is formed on the dielectric spacer layer and a second end is attached to the edge of the diaphragm; and

(f) a second pair of mechanical springs with two sides and two ends having a lengthwise dimension formed along the second plane, said mechanical springs are coplanar with the diaphragm and separated from the diaphragm by a slot along each side and wherein one end is formed on the dielectric spacer layer and a second end is attached to the edge of the diaphragm and wherein said ends on the dielectric spacer layer form an overlap region with the ends of the first pair of mechanical springs on the dielectric spacer layer.

47. The microphone sensing element of claim **46** wherein the substrate is comprised of doped silicon having a low resistivity or glass having a conductive layer formed thereon, and the diaphragm, mechanical springs, and perforated plates are comprised of doped silicon, doped polysilicon, or other semiconductor materials.

48. The microphone sensing element of claim **46** further comprised of a first electrode formed on the overlap region of the mechanical springs above the dielectric spacer layer and a second electrode formed on the substrate outside the perforated plates or diaphragm.

49. The microphone sensing element of claim **46** wherein the mechanical springs are not formed over the back hole sections.

50. The microphone sensing element of claim **46** wherein the air gap has a thickness that is defined by the thickness of the dielectric spacer layer.

51. The microphone sensing element of claim **46** wherein the first and second electrodes are comprised of a Au/Cr composite layer or are a single layer or composite layer comprised of Al, Ti, Ta, Ni, Cu, or other metal materials.

52. The microphone sensing element of claim **46** wherein the dielectric spacer layer is a single or composite layer comprised of oxide, silicon nitride, or other dielectric materials.

53. The microphone sensing element of claim **46** wherein said diaphragm is essentially square or rectangular and a perforated plate has a lengthwise dimension equal to or less than the length of said diaphragm and a width that is less than said lengthwise dimension.