Claims

[Claim 1]

A block copolymer composition for a viscous adhesive comprising:

a component (a): 50 mass% or more and 90 mass% or less of a non-hydrogenated block copolymer having a number average molecular weight of 10,000 or more and 60,000 or less, comprising a polymer block (A) mainly including a vinyl aromatic monomer unit and a polymer block (B) mainly including a conjugated diene monomer unit; and

a component (b): 10 mass% or more and 50 mass% or less of a non-hydrogenated block copolymer having a number average molecular weight of more than 120,000 and 200,000 or less, comprising a polymer block (A) mainly including a vinyl aromatic monomer unit and a polymer block (B) mainly including a conjugated diene monomer unit;

a content of the vinyl aromatic monomer unit in the component (a) and the component (b) of the block copolymer composition being 25 to 50 mass%;

the composition having a 15 mass% toluene solution viscosity of 10 to 40 mPa•s; and

a number average molecular weight ratio of the component (b) to the component (a) being 2.0 to 4.0.

[Claim 2]

The block copolymer composition for the viscous adhesive according to claim 1, wherein