

ABSTRACT

One object of the present invention is to provide a production method for powder that can produce powder which can suppress foaming of a melt and can produce a molded-article with good conductivity and appearance by melt-molding, the present

5 invention provides a production method for powder containing a composite resin (2, 21, 22, 23) containing a thermomelttable resin (2a) and a conductive filler (2b), wherein the production method comprises: a dispersion preparing step in which a raw material powder containing the thermomelttable resin (2a), the conductive filler (2b), a dispersion medium in which the raw material powder and the conductive filler (2b) are dispersed,

10 and a dispersant (3) for dispersing the conductive filler (2b) in the dispersion medium are mixed to prepare the dispersion: an intermediate powder recovering step in which the dispersion medium is removed from the dispersion and recovering an intermediate powder containing the composite resin (2, 21, 22, 23) and the dispersant (3); and a dispersant removing step in which the dispersant (3) is removed from the intermediate

15 powder.