

Transmission lubricant

The present invention relates to lubricants for
5 transmission systems and wind power plants wherein the
transmission system comprises a lubricant containing
polyalkyl(meth)acrylates. In addition, the present
invention describes polyalkyl(meth)acrylates and processes
for preparation thereof and use thereof as lubricants in
10 transmission systems.

Decreasing global mineral oil reserves and discussions
about a rising carbon dioxide content in the earth's
atmosphere are causing increasing interest in alternative
15 energies. More particularly, systems for utilization of
wind energy are gaining increasing importance.

These systems comprise, as well as further components,
particularly transmission systems, which are subject to
20 extreme stress. For instance, not only are extremely high,
highly varying torques transmitted, but these systems are
also subject to significant temperature changes.

Furthermore, these systems and hence the transmission
systems present therein should have a low maintenance
25 requirement, since the economic viability thereof would
otherwise be greatly impaired or they would be unviable.

Due to this profile of requirements, transmission systems
for wind power plants differ very greatly from other
30 transmission systems which are used in plant and vehicle
construction. These differences are manifested particularly
in the lubricants too, which are used for these
transmission systems.

While automobiles typically in - based on operating performance - have relatively short oil change intervals, which can be conducted in a standard manner in any workshop, oil changes for wind power plants are associated with a high level of cost, time and material, since the oil has to be conveyed from the base to the pod, and the used oil has to leave the pod in the reverse direction. Moreover, the amount of oil is large and is up to 1500 liters according to the plant size. An additional factor is that the oil change leads to an interruption in power generation. In addition, it should be ensured that a transmission system does not fail since exchange thereof at a great height above the surface of the earth is very expensive, and a replacement is often available only after long wait times or laborious repair. For these reasons, high-performance transmission oils used preferentially for wind power plants are those which retain their function over a long period and can be used over a large temperature range. In addition, the power loss caused by the transmission oil should be at a minimum.

Other industrial transmission systems likewise profit from transmission oils with long lifetime, even in the cases in which the oil change is less inconvenient per se, or the stresses are typically more homogeneous than in wind power plants. The advantage of lower shutdown times and of better protection for the transmission system, and also of the costs for the oil change owing to the high amount of transmission oil, also applies in industrial transmission applications outside wind power.

For these reasons, it is customary to operate transmission systems for wind power plants using lubricants based on

specific polyalphaolefins (PAOs). Such lubricants are detailed, for example, in WO 2007/145924 A1. These lubricants generally comprise two base oils of different viscosity.

5

The known lubricants have a useable profile of properties. However, the provision of a lubricant with an improved profile of properties is a constant task.

10 In view of the prior art, it is thus an object of the present invention to provide a lubricant for transmission systems with an improved profile of properties.

For example, the lubricant should have an improved seal
15 compatibility, more particularly compared to polyalphaolefins. In addition, the lubricant should exhibit improved flow characteristics at low temperatures. Furthermore, the lubricant should have an enhanced viscosity index without any associated decrease in the
20 service life of the lubricant.

Especially the lubricants detailed in WO 2007/145924 A1 comprise relatively large amounts of expensive PAOs, the preparation of which is complex and which have a high
25 viscosity. The second base component of the lubricants described is a PAO grade with a lower viscosity and is much less expensive. It is therefore a particular task to substitute the amount or grade of the relatively more expensive component with less expensive alternatives.

30

In addition, the wear and fatigue of the transmission systems should be minimized as far as possible by the lubricant. At the same time, the lubricant should minimize

the power loss, i.e. lead to a low coefficient of friction, in order to increase the efficiency of the plant.

Furthermore, the lubricant should be compatible with many additives, although, to improve compatibility, if possible, only minor additives, and ideally no additional additives, should be necessary since they are associated with further costs.

10 These objects, and further objects which are not stated explicitly but are immediately derivable or discernible from the connections discussed herein by way of introduction, are achieved by a lubricant for a transmission system having all features of claim 1.

15 Appropriate modifications of the inventive lubricants are protected in the dependent claims referring back to claim 1. With regard to the polyalkyl(meth)acrylates, processes for preparation thereof and use thereof and the wind power plants, claims 9, 20, 28 and 29 are a solution to the
20 problems.

The present invention accordingly provides a lubricant for a transmission system, which is characterized in that it comprises at least 30% by weight of
25 polyalkyl(meth)acrylate.

The present invention further provides a polyalkyl(meth)acrylate for use in lubricants, comprising
a) 0 to 25% by weight of repeat units derived from
30 (meth)acrylates of the formula (I)



in which R is hydrogen or methyl and R¹ is an alkyl radical having 1 to 5 carbon atoms,

- b) 50 to 100% by weight of repeat units derived from (meth)acrylates of the formula (II)



- 5 in which R is hydrogen or methyl and R² is an alkyl radical having 6 to 15 carbon atoms, and

- c) 0 to 50% by weight of repeat units derived from (meth)acrylates of the formula (III)



- 10 in which R is hydrogen or methyl and R³ is an alkyl radical having 16 to 40 carbon atoms, which is characterized in that the polyalkyl(meth)acrylate has a weight-average molecular weight in the range from 3000 to 25 000 g/mol and
- 15 a polydispersity in the range from 1.1 to 2.5, and the repeat units of the formula (II) are a mixture of linear and branched radicals where 5 to 80% of the R² radicals are branched, based on the weight of the repeat units of the formula (II).

It is thus possible in an unforeseeable manner to provide a lubricant for a transmission system with an improved profile of properties.

- 5 For example, the lubricant exhibits improved seal compatibility, more particularly compared to polyalphaolefins. In addition, the lubricant has improved flow characteristics at low temperatures. Furthermore, the lubricant has an enhanced viscosity index without any
- 10 associated decrease in the service life of the lubricant. More particularly, the shear stability is excellent, and the outstanding rheological properties of the lubricant should be taken into account.
- 15 Furthermore, the lubricant can be provided relatively inexpensively. At the same time, the amount of relatively inexpensive components, particularly of low-viscosity base oils, can be kept high without any unacceptable impairment of the further properties, particularly the shear
- 20 stability, the low-temperature flowability or the viscosity index.

Moreover, the lubricant can be produced from inexpensive base materials on the industrial scale without any

25 associated investments in expensive plants or danger to the environment.

In addition, wear and fatigue of the transmission systems can be greatly minimized by the lubricant. A distinction is

30 typically drawn between two groups of faults at metallic surfaces of transmission systems, especially at gearings and roller bearings:

1. Wear resulting from continuous surface material removal or scuffing as a result of abrupt material removal after surface wear of both friction partners.
- 5 2. Fatigue which becomes visible through gray staining (surface fatigue, micro-pitting) or craters (sub-surface fatigue, pitting). This damage is caused by material flaking off or breaking out owing to cracks, which are caused 20-40 μm or 100-500 μm below the
10 surface by shear stresses in the metal lattice.

The types of damage mentioned are commonly known for gearings and roller bearings, and are described in detail, for example, in the publications "Gears - Wear and Damage
15 to Gear Teeth", ISO DIN 10825 and "Wälzlagerschäden" [Damage to roller bearings], Publ. No. WL 82 102/2 DA from FAG (Schaeffler KG), Schweinfurt 2004.

Furthermore, the low coefficient of friction of the
20 inventive lubricant can keep the power loss of the transmission system extremely low.
Moreover, the lubricant is compatible with many additives, and barely any, if any, additives are needed to improve compatibility.

25 Surprisingly, a polyalkyl(meth)acrylate particularly preferred for achievement of the properties detailed above can be prepared very inexpensively, the preparation being possible preferentially without the use of particular
30 solvents and within a relatively short time.

The present invention describes a lubricant for a transmission system. Lubricants, especially lubricant oils,

serve to reduce friction and wear, and for force transmission, cooling, vibration damping, sealing action and corrosion protection. In this context, transmission oils are typically distinguished from other lubricant oils, which can serve, for example, for lubrication of engines. Typically, these differences are manifested particularly in the additives added, and transmission oils in many cases have higher proportions of antiwear and extreme pressure additives compared to motor oils.

10

The inventive lubricant comprises at least 30% by weight, preferably at least 40% by weight and more preferably at least 45% by weight of polyalkyl(meth)acrylates.

15

Polyalkyl(meth)acrylates are polymers by which polymerization of alkyl(meth)acrylates can be obtained. The expression "(meth)acrylates" encompasses methacrylates and acrylates and mixtures of the two. These monomers are widely known.

20

Polyalkyl(meth)acrylates comprise preferably at least 40% by weight, more preferably at least 60% by weight, especially preferably at least 80% by weight and most preferably at least 90% by weight of repeat units derived from alkyl(meth)acrylates.

25

Polyalkyl(meth)acrylates of particular interest include those which preferably have a weight-average molecular weight M_w in the range from 3000 to 25 000 g/mol,

30

preferably 5000 to 20 000 g/mol, more preferably 10 000 to 18 000 g/mol and most preferably 13 000 to 15 000 g/mol.

The number-average molecular weight M_n may preferably be in the range from 2500 to 20 000 g/mol, more preferably 5000 to 17 500 g/mol and most preferably 7000 to 13 000 g/mol.

- 5 Further appropriate polyalkyl(meth)acrylates are those whose polydispersity index M_w/M_n is in the range from 1.1 to 2.5, more preferably in the range from 1.4 to 1.9 and most preferably in the range from 1.5 to 1.8. The number-average and weight-average molecular weights can be
10 determined by known processes, for example gel permeation chromatography (GPC), preferably using a PMMA standard.

Preferred polyalkyl(meth)acrylates comprise

- a) 0 to 25% by weight, especially up to 20% by weight and
15 more preferably up to 15% by weight of repeat units derived from (meth)acrylates of the formula (I)



in which R is hydrogen or methyl and R^1 is an alkyl radical having 1 to 5 carbon atoms,

- b) 50 to 100% by weight, especially at least 70% by weight
20 and more preferably at least 80% by weight of repeat units derived from (meth)acrylates of the formula (II)



in which R is hydrogen or methyl and R^2 is an alkyl radical having 6 to 15 carbon atoms, and

- c) 0 to 50% by weight, preferably up to 30% by weight and more preferably up to 20% by weight of repeat units derived from (meth)acrylates of the formula (III)



5 in which R is hydrogen or methyl and R³ is an alkyl radical having 16 to 40 carbon atoms.

In a particular embodiment, an inventive polyalkyl(meth)acrylate may preferably at least 0.1% by weight and more preferably at least 0.5% by weight of repeat units derived from (meth)acrylates of the formula (I).

15 In a particular embodiment, an inventive polyalkyl(meth)acrylate may comprise at least preferably 0.1% by weight and more preferably at least 1% by weight of repeat units derived from (meth)acrylates of the formula (III).

20 The polyalkyl(meth)acrylates can preferably be obtained by free-radical polymerization. Accordingly, the proportion by weight of the respective repeat units that these polymers have is calculated from the proportions by weight of corresponding monomers used for preparation of the polymers.

25

Examples of (meth)acrylates of the formula (I) include linear and branched (meth)acrylates which derive from saturated alcohols, such as methyl (meth)acrylate, ethyl (meth)acrylate, n-propyl (meth)acrylate, isopropyl

(meth)acrylate, n-butyl (meth)acrylate, tert-butyl (meth)acrylate and pentyl (meth)acrylate; and cycloalkyl (meth)acrylates such as cyclopentyl (meth)acrylate.

5

The (meth)acrylates of the formula (II) include especially linear and branched (meth)acrylates which derive from saturated alcohols, such as hexyl (meth)acrylate, 2-ethylhexyl (meth)acrylate, heptyl (meth)acrylate, 2-tert-butylheptyl (meth)acrylate, octyl (meth)acrylate, 3-isopropylheptyl (meth)acrylate, nonyl (meth)acrylate, decyl (meth)acrylate, undecyl (meth)acrylate, 5-methylundecyl (meth)acrylate, dodecyl (meth)acrylate, 2-methyldodecyl (meth)acrylate, tridecyl (meth)acrylate, 5-methyltridecyl (meth)acrylate, tetradecyl (meth)acrylate, pentadecyl (meth)acrylate; (meth)acrylates which derive from unsaturated alcohols, for example oleyl (meth)acrylate; cycloalkyl (meth)acrylates such as cyclohexyl (meth)acrylate, 3-vinylcyclohexyl (meth)acrylate, bornyl (meth)acrylate.

Examples of monomers of the formula (III) include linear and branched (meth)acrylates which derive from saturated alcohols, such as hexadecyl (meth)acrylate, 2-methylhexadecyl (meth)acrylate, 2-methylpentadecyl (meth)acrylate, 2-ethyltetradecyl (meth)acrylate, 2-propyltridecyl (meth)acrylate, 2-butyldodecyl (meth)acrylate, 2-methylhexadecyl (meth)acrylate, 2-pentyldodecyl (meth)acrylate, 2-hexyldecyl (meth)acrylate, 2-hexylundecyl (meth)acrylate, n-heptadecyl (meth)acrylate, 5-isopropylheptadecyl (meth)acrylate, 4-tert-butyloctadecyl (meth)acrylate, 5-ethyloctadecyl (meth)acrylate,

- 3-isopropyloctadecyl (meth)acrylate, octadecyl (meth)acrylate, nonadecyl (meth)acrylate, eicosyl (meth)acrylate, cetyleicosyl (meth)acrylate, stearyleicosyl (meth)acrylate, docosyl (meth)acrylate and/or
- 5 eicosyltetratratriacontyl (meth)acrylate; cycloalkyl (meth)acrylates such as 2,4,5-tri-t-butyl-3-vinylcyclohexyl (meth)acrylate, 2,3,4,5-tetra-t-butylcyclohexyl (meth)acrylate.
- 10 Alkyl (meth)acrylates with a long-chain alcohol radical, especially components (II) and (III), can be obtained, for example, by reacting (meth)acrylates and/or the corresponding acids with long-chain fatty alcohols, generally forming a mixture of esters, for example
- 15 (meth)acrylates with various long-chain alcohol radicals. These fatty alcohols include Oxo Alcohol® 7911, Oxo Alcohol® 7900, Oxo Alcohol® 1100; Alfol® 610, Alfol® 810, Lial® 125 and Nafol® products (Sasol); C13-C15-Alkohol (BASF); Epal® 610 and Epal® 810 (Afton); Linevol® 79,
- 20 Linevol® 911 and Neodol® 25 (Shell); Dehydad®, Hydrenol® and Lorol® products (Cognis); Acropol® 35 and Exxal® 10 (Exxon Chemicals); Kalcol® 2465 (Kao Chemicals).

- The weight ratio of alkyl (meth)acrylates of the formula
- 25 (III) to the (meth)acrylates of the formula (II) may be within a wide range. The weight ratio of monomers of the formula (III) having 16 to 40 carbon atoms in the alcohol radical to the monomers of the formula (II) having 6 to 15 carbon atoms in the alcohol radical is preferably less than
- 30 5:1, especially less than 1:1, more preferably less than 1:5 and more preferably less than 1:10. In a particular aspect of the present invention, the weight ratio of

monomers of the formula (III) having 16 to 40 carbon atoms in the alcohol radical to the monomers of the formula (II) having 6 to 15 carbon atoms in the alcohol radical may be less than 1:100, and, in preferred embodiments, the polymer
5 does not comprise any monomers of the formula (III) having 16 to 40 carbon atoms in the alcohol radical.

Surprising advantages can be achieved especially with polyalkyl(meth)acrylate for use in lubricants which have a
10 weight-average molecular weight in the range from 3000 to 25 000 g/mol and a polydispersity in the range from 1.1 to 2.5. A further feature of these polyalkyl(meth)acrylates is that the repeat units of the formula (II) are a mixture of linear and branched radicals where 5 to 80%, preferably 10
15 to 65%, of the R^2 radicals are branched, based on the weight of the repeat units of the formula (II).

Particularly advantageously, it is especially possible to use polyalkyl(meth)acrylates wherein the units derived from
20 repeat units of the formula (II) are a mixture of linear and branched radicals where the proportion by weight of the branched R^2 radicals having 9 to 11 carbon atoms is higher than the proportion by weight of the linear R^2 radicals having 9 to 11 carbon atoms.

25 Polyalkyl(meth)acrylates of further interest include those wherein the repeat units of the formula (II) are a mixture of linear and branched radicals where the proportion by weight of the linear R^2 radicals having 12 to 15 carbon
30 atoms is preferably higher than the proportion by weight of the branched R^2 radicals having 12 to 15 carbon atoms.

In addition, surprising advantages can be achieved by polyalkyl(meth)acrylates which are characterized in that the repeat units of the formula (II) are a mixture of branched and linear radicals where the weight ratio of
5 branched to linear R^2 radicals is in the range from 60:40 to 20:80.

In a further embodiment, preference is given to lubricants comprising polyalkyl(meth)acrylates wherein the repeat
10 units of the formula (II) have a high proportion of branched R^2 radicals having 10 to 15 carbon atoms. The ratio of branched to linear R^2 radicals may more preferably be in the range from 70:30 to 50:50, preferably 60:40 to 65:35, the repeat units of the formula (II) having at least
15 50% by weight and preferably at least 70% by weight of R^2 radicals having 13 to 15 carbon atoms, based on the proportion of repeat units of the formula (II).

In addition, particular preference is given to
20 polyalkyl(meth)acrylates wherein the repeat units of the formula (II) are a mixture of R^2 radicals with a different number of carbon atoms, the proportion by weight of R^2 radicals having 12 to 15 carbon atoms being greater than the proportion by weight of R^2 radicals having 7 to 11
25 carbon atoms.

The proportions of repeat units of the formula (II) with the respective carbon numbers and the isomerism thereof can be determined by customary processes with reference to the
30 monomers which are used for preparation of the polymers. These include particularly gas chromatography (GC).

- In addition, it is possible with preference to use polyalkyl(meth)acrylates having repeat units of the formula (II) where at least 50% by weight, especially 70% by weight and more preferably 90% by weight of the repeat units of the formula (II) having a branched R^2 radical have at least one branch at one of positions 2 to 5, preferably at position 2, based on the weight of the repeat units of the formula (II) having a branched R^2 radical.
- 10 The alkyl (meth)acrylates of the polyalkyl(meth)acrylates of the present invention may, in this context, have a short-chain or long-chain branch. In a particular aspect of the present invention, preference is given to using polyalkyl(meth)acrylates whose repeat units of the formula
- 15 (II) are a mixture of branched radicals, the mixture comprising repeat units with methyl branches and with ethyl branches. In addition, it is also possible to use polyalkyl(meth)acrylates whose repeat units of the formula (II) are a mixture of branched radicals, the mixture
- 20 comprising repeat units with propyl branches and with longer-chain branches, especially butyl or pentyl branches. Particular preference is given here especially to polyalkyl(meth)acrylates which contain both methyl, ethyl, propyl branches and longer-chain branches in the repeat
- 25 units of the formula (II).

The type of branch and the position of the branch can be measured by means of NMR processes with reference to the monomers which are used for preparation of the polymers. It

30 is possible here to conduct and evaluate especially ^{13}C and ^1H NMR measurements. Valuable pointers can be found especially in "Determination of the Oligomer Distribution in Ethoxylated Linear and Branched Alkanols using ^{13}C -NMR",

Li Yang et al. Eur. Polym. J. Vol. 33 (2), 143 (1997) and
"Quantitative assessment of Alkyl Chain Branching in
Alcohol-Based Surfactants by Nuclear Magnetic Resonance",
J. Duynhoven, A. Leika and P.C. van der Hoeven, J. of
5 Surfactants and Detergents Vol 8 (1), 73 (2005). For
clarification, it should be pointed out that butyl branches
cannot be distinguished from pentyl or hexyl branches by
means of the NMR methods detailed, and so the term "longer-
chain branch" includes not only the butyl branches but also
10 pentyl or hexyl branches.

In addition, the monomer mixture for preparation of the
polyalkyl(meth)acrylates for use in accordance with the
invention may comprise monomers copolymerizable with the
15 (meth)acrylates of the formulae (I), (II) and/or (III).
These include
aryl (meth)acrylates such as benzyl methacrylate or
phenyl methacrylate, where the aryl radicals may in each
case be unsubstituted or up to tetrasubstituted;
20 styrene, substituted styrenes having an alkyl substituent
in the side chain, for example α -methylstyrene and
 α -ethylstyrene, substituted styrenes having an alkyl
substituent on the ring, such as vinyltoluene and p-
methylstyrene, halogenated styrenes, for example
25 monochlorostyrenes, dichlorostyrenes, tribromostyrenes and
tetrabromostyrenes;
maleic acid and maleic acid derivatives, for example maleic
monoesters, maleic diesters, maleic anhydride, methylmaleic
anhydride, maleimide, methylmaleimide;
30 itaconic acid and itaconic acid derivatives, for example
itaconic monoesters, itaconic diesters and itaconic
anhydride;

fumaric acid and fumaric acid derivatives, for example fumaric monoesters, fumaric diesters and fumaric anhydride; 1-alkenes, especially 1-butene, 1-pentene, 1-hexene, 1-heptene, 1-octene, 1-nonene, 1-decene, 1-undecene, 1-dodecene, 1-tridecene, 1-tetradecene and 1-pentadecene.

In a particular embodiment, it is especially possible to use dispersing monomers.

Dispersing monomers have long been used for functionalization of polymeric additives in lubricant oils and are therefore known to those skilled in the art (cf. R.M. Mortier, S.T. Orszulik (eds.): "Chemistry and Technology of Lubricants", Blackie Academic & Professional, London, 2nd ed. 1997). It is appropriately possible to use particularly heterocyclic vinyl compounds and/or ethylenically unsaturated, polar ester or amide compounds of the formula (IV)



in which R is hydrogen or methyl, X is oxygen, sulfur or an amino group of the formula -NH- or -NR^a-, in which R^a is an alkyl radical having 1 to 10 and preferably 1 to 4 carbon atoms, R⁴ is a radical which comprises 2 to 50, especially 2 to 30 and preferably 2 to 20 carbon atoms and has at least one heteroatom, preferably at least two heteroatoms, as dispersing monomers.

Examples of dispersing monomers of the formula (IV) include aminoalkyl (meth)acrylates, aminoalkyl (meth)acrylamides,

hydroxylalkyl (meth)acrylates, heterocyclic (meth)acrylates and/or carbonyl-containing (meth)acrylates.

The hydroxyalkyl (meth)acrylates include

- 5 2-hydroxypropyl (meth)acrylate,
- 3,4-dihydroxybutyl (meth)acrylate,
- 2-hydroxyethyl (meth)acrylate,
- 3-hydroxypropyl (meth)acrylate,
- 2,5-dimethyl-1,6-hexanediol (meth)acrylate and
- 10 1,10-decanediol (meth)acrylate.

Carbonyl-containing (meth)acrylates comprise, for example,

- 2-carboxyethyl (meth)acrylate,
- carboxymethyl (meth)acrylate,
- 15 N-(methacryloyloxy)formamide,
- acetonyl (meth)acrylate,
- mono-2-(meth)acryloyloxyethyl succinate,
- N-(meth)acryloylmorpholine,
- N-(meth)acryloyl-2-pyrrolidinone,
- 20 N-(2-(meth)acryloyloxyethyl)-2-pyrrolidinone,
- N-(3-(meth)acryloyloxypropyl)-2-pyrrolidinone,
- N-(2-(meth)acryloyloxy pentadecyl)-2-pyrrolidinone,
- N-(3-(meth)acryloyloxyheptadecyl)-2-pyrrolidinone and
- N-(2-(meth)acryloyloxyethyl)ethyleneurea.
- 25 2-acetoacetoxyethyl (meth)acrylate

The heterocyclic (meth)acrylates include 2-(1-

- imidazolyl)ethyl (meth)acrylate,
- oxazolidinylethyl (meth)acrylate,
- 30 2-(4-morpholinyl)ethyl (meth)acrylate,
- 1-(2-methacryloyloxyethyl)-2-pyrrolidone,
- N-methacryloylmorpholine,
- N-methacryloyl-2-pyrrolidinone,

N-(2-methacryloyloxyethyl)-2-pyrrolidinone,
N-(3-methacryloyloxypropyl)-2-pyrrolidinone.

The aminoalkyl (meth)acrylates include especially

- 5 N,N-dimethylaminoethyl (meth)acrylate,
N,N-dimethylaminopropyl (meth)acrylate,
N,N-diethylaminopentyl (meth)acrylate,
N,N-dibutylaminohexadecyl (meth)acrylate.

- 10 In addition, it is possible to use aminoalkyl
(meth)acrylamides as dispersing monomers, such as
N,N-dimethylaminopropyl(meth)acrylamide.

- In addition, it is possible to use phosphorus-, boron-
15 and/or silicon-containing (meth)acrylates as dispersing
monomers, such as

- 2-(dimethylphosphato)propyl (meth)acrylate,
2-(ethylenephosphito)propyl (meth)acrylate,
dimethylphosphinomethyl (meth)acrylate,
20 dimethylphosphonoethyl (meth)acrylate,
diethyl (meth)acryloylphosphonate,
dipropyl (meth)acryloylphosphate,
2-(dibutylphosphono)ethyl (meth)acrylate,
2,3-butylene(meth)acryloylethyl borate,
25 methyldiethoxy(meth)acryloylethoxysilane,
diethylphosphatoethyl (meth)acrylate.

- The preferred heterocyclic vinyl compounds include
2-vinylpyridine, 3-vinylpyridine, 4-vinylpyridine, 2-
30 methyl-5-vinylpyridine, 3-ethyl-4-vinylpyridine, 2,3-
dimethyl-5-vinylpyridine, vinylpyrimidine, vinylpiperidine,
9-vinylcarbazole, 3-vinylcarbazole, 4-vinylcarbazole,
1-vinylimidazole, N-vinylimidazole, 2-methyl-1-

vinylimidazole, N-vinylpyrrolidone, N-vinylpyrrolidine,
3-vinylpyrrolidine, N-vinylcaprolactam,
N-vinylbutyrolactam, vinyloxolane, vinylfuran,
vinylthiophene, vinylthiolane, vinylthiazoles and
5 hydrogenated vinylthiazoles, vinyloxazoles and hydrogenated
vinyloxazoles.

The particularly preferred dispersing monomers include
especially ethylenically unsaturated compounds comprising
10 at least one nitrogen atom, these being selected with
particular preference from the above-detailed heterocyclic
vinyl compounds and/or aminoalkyl (meth)acrylates,
aminoalkyl(meth)acrylamides and/or heterocyclic
(meth)acrylates.

15 The proportion of comonomers can be varied according to the
end use and profile of properties of the polymer. In
general, this proportion may be in the range from 0 to 30%
by weight, preferably 0.01 to 20% by weight and more
20 preferably 0.1 to 10% by weight. Especially the proportion
of 1-alkenes can preferably be limited to proportions of up
to 30% by weight, preferably up to 20% by weight and more
preferably up to 10, particularly preferred embodiments of
polyalkyl(meth)acrylates for use in accordance with the
25 invention not having any repeat units derived from 1-
alkenes.

The aforementioned ethylenically unsaturated monomers can
be used individually or as mixtures. It is additionally
30 possible to vary the monomer composition during the
polymerization of the main chain in order to obtain defined
structures, for example block copolymers or graft polymers.

The preparation of the polyalkyl esters from the above-described compositions is known per se. For instance, these polymers can be obtained especially by free-radical polymerization, and also related processes, for example

5 ATRP (= Atom Transfer Radical Polymerization) or RAFT (= Reversible Addition Fragmentation Chain Transfer).

The ATRP process is known per se. This reaction regime is described, for example, by J.-S. Wang, et al., J. Am. Chem.

10 Soc., vol. 117, p. 5614-5615 (1995), by Matyjaszewski, Macromolecules, vol. 28, p. 7901-7910 (1995). In addition, patent applications WO 96/30421, WO 97/47661, WO 97/18247, WO 98/40415 and WO 99/10387 disclose variants of the above-described ATRP.

15 In addition, the inventive polymers can be obtained, for example, via RAFT methods too. This method is explained in detail, for example, in WO 98/01478 and WO 2004/083169, to which explicit reference is made for the purposes of the

20 disclosure.

In addition, the inventive polymers are obtainable by NMP processes (nitroxide-mediated polymerization), which are described in US 4581429 inter alia.

25 One comprehensive description, more particularly with further references, of these methods is given in K. Matyjaszewski, T. P. Davis, Handbook of Radical Polymerization, Wiley Interscience, Hoboken 2002, to which

30 explicit reference is made for the purposes of the disclosure.

The free-radical polymerization of the ethylenically unsaturated compounds can be effected in a manner known per se. Customary free-radical polymerization is described inter alia in Ullmann's Encyclopedia of Industrial
5 Chemistry, Sixth Edition.

In the context of the present invention, the polymerization is initiated using at least one polymerization initiator for free-radical polymerization. These include the azo
10 initiators widely known in the specialist field, such as 2,2'-azobisisobutyronitrile, 2,2'-azobis(2,4-dimethylvaleronitrile) and 1,1-azobiscyclohexanecarbonitrile, organic peroxides such as dicumyl peroxide, diacyl peroxides such as dilauroyl
15 peroxide, peroxydicarbonates such as diisopropyl peroxydicarbonate, peresters such as tert-butyl peroxy-2-ethylhexanoate, and the like.

Polymerization initiators of very particular suitability for the purposes of the present invention include especially the following compounds:
20 methyl ethyl ketone peroxide, acetylacetone peroxide, dilauroyl peroxide, tert-butyl per-2-ethylhexanoate, ketone peroxide, tert-butyl peroctoate, methyl isobutyl ketone peroxide, cyclohexanone peroxide, dibenzoyl peroxide, tert-butyl peroxybenzoate, tert-butyl peroxyisopropylcarbonate,
25 2,5-bis(2-ethylhexanoylperoxy)-2,5-dimethylhexane, tert-butyl peroxy-2-ethylhexanoate, tert-butyl peroxy-3,5,5-trimethylhexanoate, dicumyl peroxide, 1,1-bis(tert-butylperoxy)cyclohexane, 1,1-bis(tert-butylperoxy)-3,3,5-trimethylcyclohexane, cumyl hydroperoxide, tert-butyl
30 hydroperoxide, bis(4-tert-butylcyclohexyl) peroxydicarbonate, 2,2'-azobisisobutyronitrile, 2,2'-azobis(2,4-dimethylvaleronitrile), 1,1-azobiscyclohexanecarbonitrile, diisopropyl peroxydicarbonate, tert-amyl peroxy-pivalate,

di(2,4-dichlorobenzoyl) peroxide, tert-butyl peroxy-pivalate, 2,2'-azobis(2-amidinopropane) dihydrochloride, di(3,5,5-trimethylhexanoyl) peroxide, dioctanoyl peroxide, didecanoyl peroxide, 2,2'-azobis(N,N'-dimethyleneiso-
5 butyramidine), di(2-methylbenzoyl) peroxide, dimethyl 2,2'-azobisisobutyrate, 2,2'-azobis(2-methylbutyronitrile), 2,5-dimethyl-2,5-di(2-ethylhexanoylperoxy)hexane, 4,4'-azobis(cyanopentanoic acid), di(4-methylbenzoyl) peroxide, dibenzoyl peroxide, tert-amyl peroxy-2-ethylhexanoate,
10 tert-butyl peroxy-2-ethylhexanoate, tert-butyl peroxyisobutyrate and mixtures of the aforementioned polymerization initiators.

According to the invention, very particular preference is
15 given to polymerization initiators having a half-life of 1 hour at a temperature in the range from 25°C to 200°C, preferably in the range from 50°C to 150°C, especially in the range from 50°C to 100°C. In addition, peroxidic polymerization initiators, especially tert-butyl
20 peroctoate, are very particularly suitable for the present purposes.

According to the embodiment, it is also possible to use various polymerization initiators. If various initiator
25 species are used, they are preferably added separately in successive steps, in which case the polymerization initiator added later should appropriately have a higher half-life than the polymerization initiator added beforehand.

30 In preferred processes, the at least one polymerization initiator for the free-radical polymerization is added in at least two steps. The polymerization initiator can be

added in each step in undiluted form or in diluted form, preferably dissolved in a solvent, especially in the form of a 10% by weight to 50% by weight solution in at least one mineral oil and/or a polyalphaolefin.

5

In a first embodiment of this preferred process, the polymerization initiator can preferably be added all at once in the first step. However, it has also been found to be very particularly appropriate to meter in the
10 polymerization initiator in the first step, preferably continuously, especially with a constant metering rate.

In the second step, the polymerization initiator, in a first embodiment of this preferred process, is preferably
15 added all at once. Alternatively, however, it is also preferable to meter in the polymerization initiator in the second step, preferably continuously, especially with a constant metering rate. In a very particularly preferred embodiment of this process, the polymerization initiator
20 can be metered in continuously in the first and in the second step, favorably with a constant metering rate in each case, the mean metering rate of the second step preferably being greater than the mean metering rate of the first step. The ratio of the mean metering rate of the
25 second step to the mean metering rate of the first step is preferably greater than 1.2:1, preferably in the range from 1.2:1 to 10:1, more preferably greater than 1.5:1, even more preferably greater than 2:1, especially greater than 3:1.

30 The amount of polymerization initiator added in the second step is preferably greater than the amount added in the first step, in which case, in the second step, based on the total weight of the polymerization initiator added in the

first step, preferably at least 120%, appropriately 120% to 1000%, more preferably at least 150% and especially 150% to 500% of the amount of polymerization initiator added in the first step is added.

5

The second step is preferably commenced at a time at which 0.01 to 50.0%, appropriately 10.0 to 40.0% and especially 15.0 to 35.0% by weight of the total amount of the polymerization initiator added during the first step is yet
10 to be consumed.

For the purposes of the present invention, it has been found to be very particularly appropriate to add the polymerization initiator in at least three steps, in which
15 case, in the third step, more initiator is added than in the first step and than in the second step. In the third step, the polymerization initiator is appropriately added all at once. Alternatively, it is also preferable to meter in the polymerization initiator in the third step,
20 preferably continuously, especially with a constant metering rate. In a very particularly preferred embodiment of the present invention, the polymerization initiator is metered in continuously in the first, in the second and in the third step, favorably with a constant metering rate in
25 each case, the mean metering rate of the third step preferably being greater than the mean metering rate of the second step, and the mean metering rate of the second step preferably being greater than the mean metering rate of the first step. The ratio of the mean metering rate of the
30 third step to the mean metering rate of the second step is preferably greater than 1.2:1, preferably in the range from 1.2:1 to 10:1, more preferably greater than 1.5:1, even

more preferably greater than 2:1, especially greater than 3:1.

More preferably, the amount of polymerization initiator
5 added in the third step is preferably greater than the
amount added in the second step, in which case, in the
third step, based on the total weight of the polymerization
initiator added in the second step, preferably at least
120%, appropriately 120% to 1000%, more preferably at least
10 150% and especially 150% to 500% of the amount of
polymerization initiator added in the second step is added.

The third step is preferably commenced at a time at which
0.01 to 50.0%, appropriately 10.0 to 40.0% and especially
15 15.0 to 35.0% by weight of the total amount of the
polymerization initiator added during the second step is
yet to be consumed.

This proportion of as yet unconsumed polymerization
20 initiator can be determined in a manner known per se or
calculated on the basis of the parameters known per se, for
example the decomposition constant of the polymerization
initiator, the temperature profile during the
polymerization, the addition profile. For metered addition
25 at constant rate at a constant temperature, for example,
the following equation applies as an approximation:

$$I_{ss}/I_{\Sigma} = 1/(k_d t_{\Sigma})$$

where the ratio I_{ss}/I_{Σ} denotes the proportion of the as yet
unconsumed polymerization initiator based on the total
30 amount of the polymerization initiator added during the
second step, where k_d is the decomposition constant of the
polymerization initiator and where t_{Σ} is the duration of
metered addition.

In a particularly preferred embodiment, the polymerization initiator can be added in more than three steps, in which case, from the fourth step, in each subsequent step, more polymerization initiator is added than in the immediately
5 preceding step and the polymerization initiator is added all at once or metered in continuously, preferably at constant metering rate.

For preparation of the polymers for use in accordance with
10 the invention, it has been found to be very particularly favorable to meter in the polymerization initiator with a constantly rising metering rate. This corresponds to an addition of constantly rising amounts of polymerization initiator in an infinite number of steps.

15 The process detailed above allows a rapid and extremely effective polymerization of ethylenically unsaturated compounds and leads to polymers with comparably low residual monomer contents. Nevertheless, it has
20 occasionally been found to be extremely favorable to provide further initiation toward the end of the reaction in order to lower the residual monomer content of the reaction mixture still further. Further initiation is preferably provided at a time at which at least 75.0% by
25 weight, appropriately at least 90.0% by weight and especially at least 95.0% by weight of the total amount of the polymerization initiator added during the last step has been consumed. Preference is given to metering in a further
30 0.1% by weight to 100.0% by weight, especially 5.0% by weight to 50.0% by weight, of polymerization initiator, based on the total amount of polymerization initiator added beforehand.

The total amount of initiator is preferably in the range from 0.5 to 1% and more preferably in the range from 0.6 to 0.8% by weight, based on the weight of the monomers.

- 5 The process can be performed either in the presence or in the absence of a chain transferer. The chain transferers used may be typical species described for free-radical polymerizations, as known to those skilled in the art.
- 10 The sulfur-free molecular weight regulators include, for example, without any intention that this should impose a restriction, dimeric α -methylstyrene (2,4-diphenyl-4-methyl-1-pentene), enol ethers of aliphatic and/or cycloaliphatic aldehydes, terpenes, β -terpinene,
- 15 terpinolene, 1,4-cyclohexadiene, 1,4-dihydronaphthalene, 1,4,5,8-tetrahydronaphthalene, 2,5-dihydrofuran, 2,5-dimethylfuran and/or 3,6-dihydro-2H-pyran, preference being given to dimeric α -methylstyrene.
- 20 The sulfur-containing molecular weight regulators used may preferably be mercapto compounds, dialkyl sulfides, dialkyl disulfides and/or diaryl sulfides. The following polymerization regulators are mentioned by way of example: di-n-butyl sulfide, di-n-octyl sulfide, diphenyl sulfide,
- 25 thiodiglycol, ethylthioethanol, diisopropyl disulfide, di-n-butyl disulfide, di-n-hexyl disulfide, diacetyl disulfide, diethanol sulfide, di-t-butyl trisulfide and dimethyl sulfoxide. Compounds used with preference as molecular weight regulators are mercapto compounds, dialkyl
- 30 sulfides, dialkyl disulfides and/or diaryl sulfides. Examples of these compounds are ethyl thioglycolate, 2-ethylhexyl thioglycolate, pentaerythritol tetrathio-glycolate, cysteine, 2-mercaptoethanol, 1,3-mercapto-

propanol, 3-mercaptopropane-1,2-diol, 1,4-mercaptobutanol, mercaptoacetic acid, 3-mercaptopropionic acid, thioglycolic acid, mercaptosuccinic acid, thioglycerol, thioacetic acid, thiourea and alkyl mercaptans such as n-butyl mercaptan, n-
5 hexyl mercaptan, t-dodecyl mercaptan or n-dodecyl mercaptan. Polymerization regulators used with particular preference are mercapto alcohols and mercapto carboxylic acids. In the context of the present invention, very particular preference is given to the use of n-dodecyl
10 mercaptan and tert-dodecyl mercaptan as chain transferers.

In a particular aspect of the present invention, it is possible to use mixtures of molecular weight regulators, preferred mixtures comprising especially sulfur-containing
15 regulators such as the abovementioned mercaptan derivatives and sulfur-free regulators such as terpinolene, terpinene and derivatives thereof, and suitable transition metal complexes. More preferably, it is possible to use mixtures of abovementioned n-dodecyl mercaptan, tert-dodecyl
20 mercaptan and terpinolene as chain transferers.

The molecular weight regulators are used preferably in amounts of 0.05 to 10% and especially 1 to 6% by weight and more preferably 2 to 4.5% by weight, based on the monomers
25 used in the polymerization.

Further information can be found by the person skilled in the art in the specialist literature, especially the publications H. Rausch-Puntigam, T. Völker „Acryl- und
30 Methacrylverbindungen" [Acrylic and Methacrylic Compounds] Springer, Heidelberg, 1967; Houben-Weyl „Methoden der organischen Chemie" [Methods of Organic Chemistry] Vol. XIV/1, p. 66ff., Georg Thieme, Heidelberg, 1961 and

Kirk-Othmer "Encyclopedia of Chemical Technology" Vol. 1, p. 296ff., J. Wiley, New York, 1978.

Processes of particular interest are especially those in which a majority of the monomers is initially charged and the polymerization initiators, as explained above, are added in several steps over the polymerization time. Preferably, at least 50% by weight, especially at least 60% by weight, more preferably at least 80% by weight and most preferably at least 90% by weight of the monomers can be initially charged in a reactor. Subsequently, the initiators mentioned can be added at the polymerization temperature. The regulators may either be initially charged or added with the initiator, the regulators being initially charged in preferred processes. Particular preference here is given to processes in which at least 50% by weight, especially at least 60% by weight, more preferably at least 80% by weight and most preferably at least 90% by weight of the molecular weight regulators are initially charged in a reactor.

The polymerization can be performed at standard pressure, reduced pressure or elevated pressure. The polymerization temperature is also uncritical. In general, however, it is in the range of -20° - 200°C , preferably 20° - 180°C and more preferably 60° - 150°C . In the case of performance of a free-radical polymerization, higher polymerization temperatures may be preferable; for instance, the polymerization temperature in the case of stepwise addition of the initiator may preferably be in the range from 20 to 180°C , more preferably 60 to 150°C . Particular preference is given here especially to processes in which the polymerization is performed at a temperature in the range

from 0 to 30°C above the initiator temperature at which the half-life of the initiator is 30 minutes.

The polymerization can be performed with or without
5 solvent. The term "solvent" should be understood here in a broad sense. The solvents to be used include hydrocarbon solvents, for example aromatic solvents such as toluene, benzene and xylene, saturated hydrocarbons, for example cyclohexane, heptane, octane, nonane, decane, dodecane,
10 which may also be present in branched form. These solvents can be used individually or else as a mixture. Particularly preferred solvents are mineral oils, natural oils and synthetic oils, and mixtures thereof.

15 In a preferred embodiment, the proportion of solvent can be kept low, preferred embodiments of the process according to the invention having the feature that, after the polymerization has ended, there is no need to remove solvent from the composition, for example by distillation,
20 in order to obtain a useable polymer mixture. Accordingly, the proportion of solvent which is used overall is preferably in the range from 0 to 30% by weight, more preferably 0.5 to 10% by weight and most preferably in the range from 1 to 8% by weight. The solvent here may
25 especially serve for dissolution of the initiator added over the course of the reaction.

The measures detailed above, especially the stepwise addition of the initiator to a reactor comprising
30 relatively large amounts of the monomers, can give surprising advantages. One of these is more particularly that the reaction can be performed without any great amounts of solvents. If only a small amount of 1-alkenes is

used for preparation of the polyalkyl(meth)acrylates, a distillation for removal of solvents and/or residual monomers can be dispensed with. This allows the reaction to be conducted very inexpensively. It is surprisingly possible to obtain, more particularly, very narrow molecular weight distributions with a low polydispersity index without any need to use costly processes such as ATRP. In addition, the reaction time and initiator consumption can be minimized.

10

The proportion of the polyalkyl(meth)acrylates for use in accordance with the invention in the lubricant is at least 30% by weight, especially 35% by weight, more preferably at least 40% by weight and most preferably at least 45% by weight, based on the total weight of the lubricant.

15

As well as the polyalkyl(meth)acrylate to be used obligatorily, preferred lubricants for a transmission system may comprise at least one further base oil.

20

The preferred base oils include especially mineral oils, synthetic oils and natural oils.

Mineral oils are known per se and commercially available.

25

They are generally obtained from mineral oil or crude oil by distillation and/or refining and optionally further purification and finishing processes, the term mineral oil including in particular the higher-boiling fractions of crude or mineral oil. In general, the boiling point of mineral oil is higher than 200°C, preferably higher than 300°C, at 5000 Pa. The production by low-temperature carbonization of shale oil, coking of bituminous coal, distillation of brown coal with exclusion of air, and also

30

hydrogenation of bituminous or brown coal is likewise possible. Accordingly, mineral oils have, depending on their origin, different proportions of aromatic, cyclic, branched and linear hydrocarbons.

5

An improved class of mineral oils (reduced sulfur content, reduced nitrogen content, higher viscosity index, lower pour point) results from hydrogen treatment of the mineral oils (*hydroisomerization, hydrocracking, hydrotreatment, hydrofinishing*). In the presence of hydrogen, this essentially reduces aromatic components and builds up naphthenic components.

Synthetic oils include organic esters, for example diesters and polyesters, polyalkylene glycols, polyethers, synthetic hydrocarbons, especially polyolefins, among which preference is given to polyalphaolefins (PAOs), silicone oils and perfluoroalkyl ethers. In addition, it is possible to use synthetic base oils originating from *gas to liquid* (GTL), *coal to liquid* (CTL) or *biomass to liquid* (BTL) processes. They are usually somewhat more expensive than the mineral oils, but have advantages with regard to their performance.

25 Natural oils are animal or vegetable oils, for example neatsfoot oils or jojoba oils.

Base oils for lubricant oil formulations are divided into groups according to API (American Petroleum Institute).
30 Mineral oils are divided into group I (non-hydrogen-treated) and, depending on the degree of saturation, sulfur content and viscosity index, into groups II and III (both

hydrogen-treated). PAOs correspond to group IV. All other base oils are encompassed in group V.

5 These base oils may also be used as mixtures and many are commercially available.

Particularly preferred lubricants of the present invention comprise at least one polyalphaolefin (PAO) or a group III oil having a kinematic viscosity measured at 100°C in the
10 range from 3.0 to 10.0 mm²/s, preferably in the range from 5.5 to 9.0 mm²/s and more preferably in the range from 7.5 to 8.5 mm²/s (ASTM D 445). In a further embodiment, preference is given to lubricants which comprise a polyalphaolefin (PAO) or a group III oil having an at 100°C
15 kinematic viscosity in the range from 3.0 to 5.5 mm²/s and more preferably 3.5 to 5 mm²/s.

Further lubricants of particular interest are those which comprise at least one group III mineral oil. Surprising
20 advantages can be achieved especially by lubricants which comprise at least one pour point improver and at least one group III mineral oil having a kinematic viscosity KV₁₀₀ in the range from 3 to 10 mm²/s and more preferably 5.5 to 9 mm²/s, measured at 100°C according to ASTM D 445.
25 Preference is given to using poly(alkyl)methacrylates together with a group III mineral oil as a pour point improver.

The proportion of further base oils, especially of
30 polyalphaolefins and/or group III mineral oils, may be at least 10% by weight, more preferably at least 35% by weight and most preferably at least 45% by weight, based on the total weight of the lubricant.

As well as the aforementioned components, a lubricant oil composition may comprise further additives. These additives include DI additives (dispersants, detergents, defoamers, corrosion inhibitors, antioxidants, antiwear and extreme pressure additives, friction modifiers), pour point improvers (more preferably based on polyalkyl(meth)acrylate having 1 to 30 carbon atoms in the alcohol group), and/or dyes.

10

In addition, the lubricant oil compositions detailed here may, as well as the inventive polymers, also be present in mixtures with conventional VI improvers. These include especially hydrogenated styrene-diene copolymers (HSDs, US 4 116 917, US 3 772 196 and US 4 788 316 to Shell Oil Company), especially based on butadiene and isoprene, and also olefin copolymers (OCPs, K. Marsden: "Literature Review of OCP Viscosity Modifiers", Lubrication Science 1 (1988), 265), especially of the poly(ethylene-co-propylene) type, which may often also be present in N/O-functional form with dispersing action, or PAMAs, which are usually present in N-functional form with advantageous booster properties as a dispersant, antiwear additive and/or friction modifier (DE 1 520 696 to Rohm and Haas, WO 2006/007934 to RohMax Additives).

25

Compilations of VI improvers and pour point improvers for lubricant oils, especially motor oils, are detailed, for example, in T. Mang, W. Dresel (eds.): "Lubricants and Lubrication", Wiley-VCH, Weinheim 2001; R. M. Mortier, S. T. Orszulik (eds.): "Chemistry and Technology of Lubricants", Blackie Academic & Professional, London 1992;

30

or J. Bartz: "Additive für Schmierstoffe" [Additives for Lubricants], Expert-Verlag, Renningen-Malmsheim 1994.

Appropriate dispersants include poly(isobutylene) derivatives, e.g. poly(isobutylene)succinimides (PIBSIs);

5 ethylene-propylene oligomers with N/O functionalities.

The preferred detergents include metal-containing compounds, for example phenoxides; salicylates; thio-phosphonates, especially thiopyrophosphonates, thio-

10 phosphonates and phosphonates; sulfonates and carbonates.

As metals, these compounds may comprise especially calcium, magnesium and barium. These compounds may be used preferably in neutral or overbased form.

15 Of particular interest are additionally defoamers, which are in many cases divided into silicone-containing and silicone-free defoamers. The silicone-containing antifoams include linear poly(dimethylsiloxane) and cyclic poly(dimethylsiloxane). The silicone-free defoamers which
20 may be used are in many cases polyethers, for example poly(ethylene glycol), polyacrylates or tributyl phosphate.

In a particular configuration, the inventive lubricant oil compositions may comprise corrosion inhibitors. These are

25 in many cases divided into antirust additives and metal passivators/deactivators. The antirust additives used may, inter alia, be sulfonates, for example petroleum sulfonates or (in many cases overbased) synthetic alkylbenzenesulfonates, e.g. dinonylnaphthenesulfonate;
30 carboxylic acid derivatives, for example lanolin (wool fat), oxidized paraffins, zinc naphthenates, alkylated succinic acids, 4-nonylphenoxyacetic acid, amides and imides (N-acylsarcosine, imidazoline derivatives); amine-

- neutralized mono- and dialkyl phosphates; morpholine; dicyclohexylamine or diethanolamine. The metal passivators/deactivators include benzotriazole, tolyltriazole, 2-mercaptobenzothiazole, dialkyl-
- 5 2,5-dimercapto-1,3,4-thiadiazole; N,N'-disalicylideneethylenediamine, N,N'-disalicylidenepropylenediamine; zinc dialkyldithiophosphates and dialkyl dithiocarbamates.
- 10 A further preferred group of additives is that of antioxidants. The antioxidants include, for example, phenols, for example 2,6-di-tert-butylphenol (2,6-DTB), butylated hydroxytoluene (BHT), 2,6-di-tert-butyl-4-methylphenol, 4,4'-methylenebis(2,6-di-tert-butylphenol);
- 15 aromatic amines, especially alkylated diphenylamines, N-phenyl-1-naphthylamine (PNA), polymeric 2,2,4-trimethyldihydroquinone (TMQ); compounds containing sulfur and phosphorus, for example metal dithiophosphates, e.g. zinc dithiophosphates (ZnDTPs), "OOS triesters" =
- 20 reaction products of dithiophosphoric acid with activated double bonds from olefins, cyclopentadiene, norbornadiene, α -pinene, polybutene, acrylic esters, maleic esters (ashless on combustion); organosulfur compounds, for example dialkyl sulfides, diaryl sulfides, polysulfides,
- 25 modified thiols, thiophene derivatives, xanthates, thioglycols, thioaldehydes, sulfur-containing carboxylic acids; heterocyclic sulfur/nitrogen compounds, especially dialkyldimercaptothiadiazoles, 2-mercaptobenzimidazoles; zinc and methylenebis(dialkyl dithiocarbamate); organophos-
- 30 phorus compounds, for example triaryl and trialkyl phosphites; organocopper compounds and overbased calcium- and magnesium-based phenoxides and salicylates.

The preferred antiwear (AW) and extreme pressure (EP) additives include phosphorus compounds, for example trialkyl phosphates, triaryl phosphates, e.g. tricresyl phosphate, amine-neutralized mono- and dialkyl phosphates, 5 ethoxylated mono- and dialkyl phosphates, phosphites, phosphonates, phosphines; compounds containing sulfur and phosphorus, for example metal dithiophosphates, e.g. zinc C₃₋₁₂dialkyldithiophosphates (ZnDTPs), ammonium dialkyldithiophosphates, antimony dialkyldithiophosphates, 10 molybdenum dialkyldithiophosphates, lead dialkyldithiophosphates, "OOS triesters" = reaction products of dithiophosphoric acid with activated double bonds from olefins, cyclopentadiene, norbornadiene, α -pinene, polybutene, acrylic esters, maleic esters, 15 triphenylphosphorothionate (TPPT); compounds containing sulfur and nitrogen, for example zinc bis(amyldithiocarbamate) or methylenebis(di-n-butyl dithiocarbamate); sulfur compounds containing elemental sulfur and H₂S-sulfurized hydrocarbons (diisobutylene, 20 terpene); sulfurized glycerides and fatty acid esters; overbased sulfonates; chlorine compounds or solids such as graphite or molybdenum disulfide.

A further preferred group of additives is that of friction 25 modifiers. The friction modifiers used may include mechanically active compounds, for example molybdenum disulfide, graphite (including fluorinated graphite), poly(trifluoroethylene), polyamide, polyimide; compounds which form adsorption layers, for example long-chain 30 carboxylic acids, fatty acid esters, ethers, alcohols, amines, amides, imides; compounds which form layers through tribochemical reactions, for example saturated fatty acids, phosphoric acid and thiophosphoric esters, xanthogenates,

sulfurized fatty acids; compounds which form polymer-like layers, for example ethoxylated dicarboxylic acid partial esters, dialkyl phthalates, methacrylates, unsaturated fatty acids, sulfurized olefins or organometallic

5 compounds, for example molybdenum compounds (molybdenum dithiophosphates and molybdenum dithiocarbamates MoDTCs) and their combinations with ZnDTPs, copper-containing organic compounds.

10 Some of the compounds detailed above may fulfill multiple functions. ZnDTP, for example, is primarily an antiwear additive and extreme pressure additive, but also has the character of an antioxidant and corrosion inhibitor (here: metal passivator/deactivator).

15

The additives detailed above are described in more detail, inter alia, in T. Mang, W. Dresel (eds.): "Lubricants and Lubrication", Wiley-VCH, Weinheim 2001; R.M. Mortier, S.T. Orszulik (eds.): "Chemistry and Technology of Lubricants".

20

In addition to high compatibility with further additives, the inventive polymers and the lubricants are notable for a multitude of favorable properties. Therefore, it is surprisingly possible to provide lubricants which

25 preferably feature a low proportion of ester oils.

Particularly preferred lubricants comprise at most 10% by weight and especially at most 5% by weight of ester oils. Most preferably, the inventive lubricants may not comprise any detectable amounts of ester oils. Ester oils are known
30 in the specialist field and feature a molecular weight of at most 800 g/mol.

Preferred lubricants have a viscosity measured according to ASTM D 445 at 40°C in the range from 200 to 2000 mm²/s, especially 250 to 1000 mm²/s, more preferably in the range from 300 to 800 mm²/s. The kinematic viscosity KV₁₀₀

5 measured at 100°C according to ASTM D 445 is preferably at least 30 mm²/s, more preferably at least 35 mm²/s and most preferably at least 37 mm²/s. Accordingly, preferred lubricants correspond to ISO viscosity grades (ISO VG) ISO 220, ISO 320, ISO 460, ISO 680 and ISO 1000.

10

The use of the inventive polymers, however, is not limited to the preferred lubricants detailed above; instead, they may also find use in other applications, especially other lubricants.

15

In a particular aspect of the present invention, preferred lubricant oil composition have a viscosity index determined according to ASTM D 2270 in the range from 100 to 400, more preferably in the range from 130 to 350 and most preferably

20

The present lubricant oils have a very high shear stability, and one way of determining this is by the tapered roller bearing (KRL) test to CEC L45-T-93. For

25 instance, preferred lubricants after 20 hours at load 5000N, an oil temperature of 60°C and a speed of 1475/min⁻¹ exhibit a decrease in viscosity of at most 8%.

25

In an appropriate modification, the permanent shear

30 stability index (PSSI) according to ASTM D2603 Ref. B (ultrasound treatment for 12.5 minutes) may be less than or equal to 35, more preferably less than or equal to 20. It is advantageously also possible to obtain lubricant oil

compositions which have a permanent shear stability index (PSSI) according to DIN 51381 (30 cycles of a Bosch pump) of at most 5, preferably at most 2 and most preferably at most 1.

5

Also surprisingly high is the seal compatibility of the present lubricants. For instance, the change in volume is preferably at most 0 to +10%, measured after 168 h and 1000 h at a temperature of 100°C with an SRE NBR 28/SX

10 elastomer according to DIN ISO 1817. In the case of use of a 72 NBR 902 or 75 FKM 585 elastomer, a change in the specimen volume of at most -2 to +5% is preferably found, measured after 168 h and 1000 h at a temperature of 100°C according to DIN ISO 1817. In the case of use of a

15 75 FKM 170055 elastomer, a change in the specimen volume of at most -2 to +5% is preferably likewise found, measured after 168 h and 1000 h at a temperature of 130°C according to DIN ISO 1817.

20 The change in the Shore hardness in the case of use of the inventive lubricant is preferably likewise very small. The change in the Shore A hardness is preferably between -10 and +5 Shore A points, measured after 168 h and 1000 h at a temperature of 100°C with an SRE NBR 28/SX elastomer

25 according to DIN ISO 1817. In the case of use of a 72 NBR 902 or 75 FKM 585 elastomer, a change in the Shore A hardness of less than or equal to ± 5 Shore A points is preferably found, measured after 168 h and 1000 h at a temperature of 100°C according to DIN ISO 1817. In the case

30 of use of a 75 FKM 170055 elastomer, a change in the Shore A hardness of less than or equal to ± 5 Shore A points is preferably likewise found, measured after 168 h and 1000 h at a temperature of 130°C according to DIN ISO 1817.

In addition, the elastomers, after contact with the inventive lubricant, preferably have relatively constant stress-strain characteristics. For instance, the tensile strength measured according to DIN 53504 after contact with the lubricant at 100°C for 168 h and 1000 h (DIN ISO 1817) preferably decreases by at most 30%, this value applying especially to the elastomer SRE NBR 28/SX. In the case of use of a 72 NBR 902 or 75 FKM 585 elastomer, the tensile strength measured according to DIN 53504 after contact with the lubricant at 100°C for 168 h and 1000 h (DIN ISO 1817) preferably decreases by at most 50%. In the case of use of a 75 FKM 170055 elastomer, the tensile strength measured according to DIN 53504 after contact with the lubricant at 130°C for 168 h and 1000 h (DIN ISO 1817) preferably likewise decreases by at most 50%.

In addition, the tensile strain at break measured according to DIN 53504 after contact with the lubricant at 100°C for 168 h and 1000 h (DIN ISO 1817) preferably decreases by at most 40%, this value applying especially to the elastomer SRE NBR 28/SX. In the case of use of a 72 NBR 902 or 75 FKM 585 elastomer, the tensile strain at break measured according to DIN 53504 after contact with the lubricant at 100°C for 168 h and 1000 h (DIN ISO 1817) preferably decreases by at most 60%. In the case of use of a 75 FKM 170055 elastomer, the tensile strength measured according to DIN 53504 after contact with the lubricant at 130°C for 168 h and 1000 h (DIN ISO 1817) preferably likewise decreases by at most 60%.

In addition, the present lubricants exhibit excellent flowabilities at low temperatures. For example, the

viscosity measured at -26°C according to ASTM D2983 may preferably be at most 150 000 mPas, preferably at most 100 000 mPas and more preferably at most 70 000 mPas.

- 5 In addition, the pour point (PP) according to ASTM D97 of preferred lubricants may assume values of less than or equal to -30°C, preferably less than or equal to -35°C and more preferably less than or equal to -45°C.
- 10 The present lubricants counteract material fatigue and wear surprisingly strongly, and so the lifetime of transmission systems can be increased. This finding can be confirmed by various methods.
- 15 For instance, especially SRV tests exhibit a surprisingly low wear factor measured according to DIN 51834-4 (load: 300N, stroke length: 1200 µm, frequency: 50 Hz, duration: 3 h). For instance, preferred lubricants at a temperature of 60°C achieve a wear factor of preferably at most
- 20 1200 mm³/10⁶, especially at most 1100 mm³/10⁶ and more preferably 1000 mm³/10⁶. At 110°C, preferred lubricants attain a wear factor of preferably at most 650 mm³/10⁶, especially at most 550 and more preferably 500 mm³/10⁶.
- 25 In addition, the present lubricants have surprising advantages according to micropitting tests described in US 2009-0093384 A1, filed October 3, 2007 at the US Patent Office (USPTO) with application number 11/866,696. Preferred lubricants do not exhibit any failure with regard
- 30 to micropitting at a load stage of at least 8, especially at least 9 and more preferably at least 10, measured by the method detailed in FVA Information Sheet "Micropitting", No. 54 / I-IV, published by the Forschungsvereinigung

Antriebstechnik e.V., Lyoner Strasse 18, D-60528
Frankfurt/Main.

The present lubricants can be used especially as
5 transmission oil. In this context, the lubricants are
especially suitable for transmission systems which are used
in wind power plants, axial transmission systems and
vehicle transmission systems, especially marine
transmission systems. Transmission systems for wind power
10 plants may preferably comprise spur gear and/or planetary
transmission systems, preference being given especially to
spur gear transmission systems with 2 to 3 spur gear
stages, planetary transmission systems with 1 planetary
stage and 2 spur gear transmission systems, and planetary
15 transmission systems with 2 planetary stages and 1 spur
gear transmission system, in order to transmit the high
forces which bear on the transmission systems. These wind
power plants may preferably have a power of at least 50 kW,
especially at least 300 kW and most preferably at least
20 2300 kW, and the rotor torque may preferably be at least
8000 Nm, especially at least 100 000 Nm and more preferably
at least 1 300 000 Nm.

The present invention is to be illustrated hereinafter by
25 examples and comparative examples, without any intention
that this should impose a restriction.

Examples and comparative examples

30 *General method for preparation of the polymers*

A 1 liter 4-neck round-bottom flask equipped with a
precision glass stirrer (in saber form) and precision glass
stirrer sleeve (operated at 150 revolutions per minute),

thermometer and reflux condenser was initially charged with 760.0 g of a monomer mixture whose composition is shown in table 1, for example consisting of C12-C15-alkyl methacrylates for example 2, together with 14.06 g of
5 dodecyl mercaptan and 14.06 g of tert-dodecyl mercaptan and 32.4 g of the mineral oil Nexbase 3020 as a solvent. The temperature was adjusted to 110°C. Thereafter, 1.9 g of tert-butyl per-2-ethylhexanoate dissolved in 7.60 g of Nexbase 3020 (20% solution) were metered in within three
10 hours, with addition of 5% of the amount specified within the first hour, 25% within the second hour and 70% within the third hour. 120 minutes and 180 minutes thereafter, another 1.52 g each time of tert-butyl per-2-ethylhexanoate are added. The total reaction time is 6 hours.

15

The weight-average molecular weight M_w and the polydispersity index PDI of the polymers were determined by GPC. The measurements were effected in tetrahydrofuran at 35°C against a polymethylmethacrylate calibration curve
20 from a set of ≥ 25 standards (Polymer Standards Service or Polymer Laboratories), the M_{peak} of which had a homogeneous logarithmic distribution over the range from $5 \cdot 10^6$ to $2 \cdot 10^2$ g/mol. A combination of six columns (Polymer Standards Service SDV 100Å / 2× SDV LXL / 2× SDV 100Å /
25 Shodex KF-800D) was used. To record the signal, an RI detector (Agilent 1100 Series) was used.

Table 1: Properties of the polymers used

Polymer	Monomer composition (weight ratio)	Mw [g/mol]	PDI (Mw/Mn)
Example 1	LIMA 100	13400	1.66
Example 2	LIMA - LMA 20 - 80	14400	1.68
Example 3	LIMA - LMA 40 - 60	14200	1.68
Example 4	IDMA - LMA 20 - 80	14500	1.70
Example 5	iC ₁₃ MA - LMA 20 - 80	14300	1.69
Example 6	IDMA - C ₁₃ -C ₁₅ MA 20 - 80	13700	1.68

LMA: alkyl methacrylate having 12 to 14 carbon atoms in the alkyl radical, the alkyl radical being a mixture comprising predominantly linear radicals (proportion of linear radicals approx. 98% by weight; proportion of C₁₂ approx. 73% by weight; proportion of C₁₄ approx. 25% by weight)

IDMA: alkyl methacrylate having about 10 carbon atoms in the alkyl radical, the alkyl radical being a mixture comprising predominantly branched radicals (proportion of branched radicals approx. 98% by weight; proportion of C₁₀ approx. 89.9% by weight; proportion of C₁₁ approx. 4.6% by weight)

- 5 LIMA: alkyl methacrylate having 12 to 15 carbon atoms in the alkyl radical, the alkyl radical being a mixture comprising branched and linear radicals (proportion of C₁₂ branched: approx. 12% by weight and C₁₂ linear: approx. 11.3% by weight; proportion of C₁₃ branched: approx. 17.3% by weight and C₁₃ linear: approx. 13.5% by weight; proportion of C₁₄ branched: approx. 15.7% by weight and C₁₄ linear: approx. 11.9% by weight; proportion of C₁₅ branched: approx. 9.8% by weight and C₁₅ linear: approx. 6.2% by weight; proportion of methyl branching approx. 14%, proportion of ethyl branching approx. 10%, proportion of propyl branching approx. 10%, proportion of longer-chain branching, especially butyl and higher, approx. 17%, based on the sum of linear and branched radicals)
- 10
- 15 iC₁₃MA alkyl methacrylate having about 13 carbon atoms in the alkyl radical, the alkyl radical being predominantly branched (proportion of C₁₃ branched: approx. 99% by weight)
- 20
- 25 C₁₃-C₁₅MA alkyl methacrylate having 13 to 15 carbon atoms in the alkyl radical, the alkyl radical being a mixture comprising branched and linear radicals (proportion of C₁₃ branched: approx. 35.6% by weight and C₁₃ linear: approx. 30.7% by weight; proportion of C₁₅ branched: approx. 16.9% by weight and C₁₅ linear: approx. 13.9% by weight)
- 30 The proportions of linear and branched radicals were determined by means of GC and ¹³C and ¹H NMR. The ¹³C spectra were conducted at 30°C using standard pulse sequences for quantitative determination of ¹³C signals,

more particularly with selection of a relaxation time of 10s and use of broadband decoupling to suppress nuclear Overhauser effects. To improve the signal-noise ratio (S/N ratio), at least 1000 scans were conducted.

5

The ^{13}C NMR data obtained were processed by mathematical methods in order to optimize the S/N ratio (line broadening of 3 Hz). The ^{13}C NMR signals were assigned by 2D NMR experiments, taking into account the influences of the incremental chemical shifts of the ^{13}C signals. The integrals of the following ^{13}C signal areas were used to calculate the isomer distribution:

10

Substructure	Chemical shift of the ^{13}C signal
unbranched n-alkanol	62.93 ppm (C1)
2-methyl-1-alkanol	69.30 ppm (C1), 16.68 ppm (C1, side chain)
2-ethyl-1-alkanol	65.23 ppm (C1), 42.12 ppm (C2)
2-propyl-1-alkanol	20.10 ppm (C2, side chain), 40.43 ppm (C2)
2-butyl+* -1-alkanol	65.61 ppm (C1) includes 2-propyl (C1),
*butyl and >C4 chains	40.64 ppm (C2)

15 The signal areas were normalized to 100% in order to obtain the isomer distribution of the alcohols in percent.

The results were checked by means of ^1H NMR:

Substructure	Chemical shift of the ^1H signal
unbranched n-alkanol	3.61 ppm (2H, t)
2-methyl-1-alkanol	3.37 ppm (1H, B component of the ABX system)
all other branched alkanols	3.50 ppm (2H, d)

In addition, the degree of branching was checked via by evaluation of the signal areas of the α -methyl groups

5 (0.88 ppm) and of the α -CH₂ groups (3.3-3.7 ppm).

Application studies

The properties of the polymers obtained were tested using
10 lubricant compositions which comprised 2.65% by weight of additive (Hitec® 307) and a polyalphaolefin (PAO 8). The amounts of PAO and of polymer added up to 97.35% by weight. Table 1 reports only the proportion of polymer, and the lubricants were adjusted to a kinematic viscosity of
15 320 mm²/s at 40°C (KV₄₀). The kinematic viscosities KV₄₀ and KV₁₀₀ measured at 40°C and 100°C respectively were determined according to ASTM D 445. The viscosity index VI was found according to ASTM D 2270. The pour point was measured according to ASTM D97. The low-temperature
20 flowability at -26°C was determined according to ASTM D2983 (Brookfield; BF). The results obtained are shown in table 2. The Brookfield viscosity was determined by two measurements, and the arithmetic mean is reported.

Table 2

Application	Amount of polymer [% by wt.]	KV ₄₀ [mm ² /s]	KV ₁₀₀ [mm ² /s]	VI	Pour point [°C]	BF -26°C [mPas]
1	Example 1 48.1	321.1	36.90	163	-39	62000
2	Example 2 48.2	319.1	37.08	165	-33	62000
3	Example 3 48.2	316.2	36.87	165	-36	57500
4	Example 4 46.0	319.4	36.38	162	-39	67000
5	Example 5 47.1	320.7	36.53	162	-39	65000
6	Example 6 46.2	321.0	36.06	159	-42	70000

In addition, tests were conducted to show the influence of the second base oil. For this purpose, various lubricants
5 were produced, the composition and properties of which are described in table 3. The test methods were detailed above, and all proportions are based on % by weight.

Table 3

Lubricant	7	8	9	10
Constituents				
Polymer according to Example 1	61.0	51.0		
Polymer according to Example 2			57.0	47.0
Hitec 307	2.65	2.65	2.65	2.65
PAO 4	36.35		40.35	
PAO 8		46.35		50.35
Test results				
KV ₄₀ [°C]	318.2	315.4	316.3	323.9
KV ₁₀₀ [°C]	38.44	36.78	37.45	36.27
VI	172	165	168	159
Pour point [°C]	-45	-45	-33	-39
BF -26°C [mPas]	60000	62000	57000	71000

To study seal compatibility, the lubricant composition detailed in application 8 comprising about 51% by weight of polymer according to example 1 and 46.35% by weight of PAO 8 was used. The test data were obtained according to

DIN 53521 and DIN 53505. The data obtained are shown in table 4.

5 Table 4: Seal compatibility of the lubricant detailed in application 8

Time [h]	Temp. [°C]	Elastomer	Tensile strength [%]	Strain [%]	Hardness [Shore A points]	Change in volume [%]
168	100	SRE NBR 28/SX	-3.6	-21	-2	+3.6
168	100	72 NBR 902	+0.8	+1.6	+1	-1.5
168	100	75 FKM 585	-6.9	+5.3	0	+0.3
168	130	75 FKM 170055	-12	+5.3	0	+1.5
1000	100	SRE NBR 28/SX	-23	-67	+6	+8.3
1000	100	72 NBR 902	-13	-57	+4	+5.8
1000	100	75 FKM 585	-10	-0.9	0	+0.7
1000	130	75 FKM 170055	-13	+3.2	0	+3.3

In addition, the improvement in wear through an inventive composition was studied. For this purpose, a lubricant comprising about 51.2% by weight of polymer according to

example 1, 2.65% by weight of Hitec 307 and 46.15% by weight of PAO 8 was produced and subjected to an SVR test according to DIN 51834-4. In the case of a measurement at 60°C, the lubricant had a wear factor of 987 at a wear diameter of 608 μm (60°C, 300N, 1200 μ , 50 Hz, 3 h). In the case of a measurement at 110°C, the wear factor was 472 at a wear diameter of 655 μm (110°C, 300N, 1200 μ , 50 Hz, 3 h). The coefficient of friction was 0.072.

10 In addition, a test of formation of gray staining was conducted with an instrument from PCS Instruments (PCS Micropitting rig). This involved operating three rollers against one another with different loads using a lubricant. The speed on the contact surfaces is approx. 3.5 m/s, and
15 three load stages are typically selected. For instance, the rollers are run first at 1.1 GPa for one hour, then at 1.4 GPa for one hour and finally at 1.7 GPa for two hours. The roller wear caused by the load is determined after each stage. The test was conducted at 60°C and 90°C with the
20 lubricant detailed above in application 4 (46.0 by weight of polymer according to Example 4, 51.35 PAO 8). The comparative example selected was a customary formulation composed of different PAOs which are used in wind power plants.

Table 5: Results of the micropitting test

Weight loss of the rollers [mg]			
at 90°C			
Time [h]	1	2	4
Comparative lubricant 1	0.5	5.7	6
Lubricant according to application 4	0.6	1.1	2.1

Weight loss of the rollers [mg]			
at 60°C			
Time [h]	1	2	4
Comparative lubricant 1	0.2	1.4	1.4
Lubricant according to application 4	0.1	0.2	0.6

Claims

1. A lubricant for a transmission system, characterized
in that the lubricant comprises at least 30% by weight of
5 polyalkyl(meth)acrylate.
2. The lubricant as claimed in claim 1, characterized in
that the lubricant comprises a polyalphaolefin (PAO) having
a kinematic viscosity KV_{100} in the range from 3 to 10 mm^2/s ,
10 measured at 100°C according to ASTM D 445.
3. The lubricant as claimed in claim 1 or 2,
characterized in that the lubricant comprises at least one
pour point improver and at least one group III mineral oil
15 having a kinematic viscosity KV_{100} in the range from 3 to
10 mm^2/s , measured at 100°C according to ASTM D 445.
4. The lubricant as claimed in at least one of the
preceding claims, characterized in that the
20 polyalkyl(meth)acrylate has a weight-average molecular
weight in the range from 3000 to 25 000 g/mol.
5. The lubricant as claimed in at least one of the
preceding claims, characterized in that the lubricant has a
25 kinematic viscosity KV_{100} of at least 30 mm^2/s , measured at
100°C according to ASTM D 445.
6. The lubricant as claimed in at least one of the
preceding claims, characterized in that the
30 polyalkyl(meth)acrylate comprises
 - a) 0 to 25% by weight of repeat units derived from
(meth)acrylates of the formula (I)



in which R is hydrogen or methyl and R¹ is an alkyl radical having 1 to 5 carbon atoms,

- b) 50 to 100% by weight of repeat units derived from (meth)acrylates of the formula (II)



- 5 in which R is hydrogen or methyl and R² is an alkyl radical having 6 to 15 carbon atoms, and

- c) 0 to 50% by weight of repeat units derived from (meth)acrylates of the formula (III)



- 10 in which R is hydrogen or methyl and R³ is an alkyl radical having 16 to 40 carbon atoms.

7. The lubricant as claimed in claim 6, characterized in that the proportion of repeat units derived from (meth)acrylates of the formula (II) is at least 70% by weight.
- 15

8. The lubricant as claimed in at least one of the preceding claims, characterized in that the polyalkyl(meth)acrylate has repeat units derived from dispersing monomers.
- 20

9. A polyalkyl(meth)acrylate for use in lubricants, comprising

- a) 0 to 25% by weight of repeat units derived from (meth)acrylates of the formula (I)



5 in which R is hydrogen or methyl and R¹ is an alkyl radical having 1 to 5 carbon atoms,

- b) 50 to 100% by weight of repeat units derived from (meth)acrylates of the formula (II)



10 in which R is hydrogen or methyl and R² is an alkyl radical having 6 to 15 carbon atoms, and

- c) 0 to 50% by weight of repeat units derived from (meth)acrylates of the formula (III)



15 in which R is hydrogen or methyl and R³ is an alkyl radical having 16 to 40 carbon atoms, characterized in that the polyalkyl(meth)acrylate has a weight-average molecular weight in the range from 3000 to 25 000 g/mol and

a polydispersity in the range from 1.1 to 2.5, and the repeat units of the formula (II) are a mixture of
20 linear and branched radicals where 5 to 80% of the R²

radicals are branched, based on the weight of the repeat units of the formula (II).

10. A polyalkyl(meth)acrylate as claimed in claim 9,
5 characterized in that the repeat units of the formula (II) are a mixture of linear and branched radicals where 10 to 65% of the R^2 radicals are branched, based on the weight of the repeat units of the formula (II).
- 10 11. A polyalkyl(meth)acrylate as claimed in claim 9 or 10, characterized in that the polyalkyl(meth)acrylate has a weight-average molecular weight in the range from 5000 to 15 000 g/mol.
- 15 12. A polyalkyl(meth)acrylate as claimed in at least one of claims 9 to 11, characterized in that the polyalkyl(meth)acrylate has a polydispersity in the range from 1.4 to 1.9.
- 20 13. A polyalkyl(meth)acrylate as claimed in at least one of claims 9 to 12, characterized in that the repeat units of the formula (II) are a mixture of linear and branched radicals where the proportion by weight of the branched R^2 radicals having 9 to 11 carbon atoms is
25 higher than the proportion by weight of the linear R^2 radicals having 9 to 11 carbon atoms.
14. A polyalkyl(meth)acrylate as claimed in at least one of claims 9 to 13, characterized in that the repeat units
30 of the formula (II) are a mixture of linear and branched radicals where the proportion by weight of the linear R^2 radicals having 12 to 15 carbon atoms is

higher than the proportion by weight of the branched R^2 radicals having 12 to 15 carbon atoms.

- 5 15. A polyalkyl(meth)acrylate as claimed in at least one of claims 9 to 14, characterized in that the repeat units of the formula (II) are a mixture of branched and linear radicals where the weight ratio of branched to linear R^2 radicals is in the range from 60:40 to 20:80.
- 10 16. A polyalkyl(meth)acrylate as claimed in at least one of claims 9 to 15, characterized in that the repeat units of the formula (II) are a mixture of R^2 radicals with a different number of carbon atoms, the proportion by weight of R^2 radicals having 12 to 15 carbon atoms
15 being greater than the proportion by weight of R^2 radicals having 7 to 11 carbon atoms.
- 20 17. A polyalkyl(meth)acrylate as claimed in at least one of claims 9 to 16, characterized in that the repeat units of the formula (II) are a mixture of linear and branched radicals where at least 50% by weight of the repeat units of the formula (II) having a branched R^2 radical have a branch at the 2 position.
- 25 18. A polyalkyl(meth)acrylate as claimed in at least one of claims 9 to 17, characterized in that the repeat units of the formula (II) are a mixture of branched radicals, the mixture comprising repeat units with methyl branches and with ethyl branches.
- 30 19. A polyalkyl(meth)acrylate as claimed in at least one of claims 9 to 18, characterized in that the repeat units of the formula (II) are a mixture of branched radicals,

the mixture comprising repeat units with propyl branches and with longer-chain branches.

- 5 20. A process for preparing polyalkyl(meth)acrylates as claimed in at least one of claims 9 to 19, characterized in that a composition comprising at least one (meth)acrylate of the formula (II) is free-radically polymerized.
- 10 21. The process as claimed in claim 20, characterized in that the polymerization is effected using at least one chain transferer.
- 15 22. The process as claimed in claim 21, characterized in that the polymerization is effected using at least two chain transferers.
- 20 23. The process as claimed in claim 21 or 22, characterized in that the polymerizable composition comprises 2 to 4.5% by weight of chain transferer, based on the weight of the monomers.
- 25 24. The process as claimed in at least one of claims 20 to 23, characterized in that at least 60% by weight of the monomers are initially charged.
- 30 25. The process as claimed in at least one of claims 20 to 24, characterized in that the initiator is added in at least two steps, less initiator being added in the first step than in the subsequent steps.
26. The process as claimed in at least one of claims 20 to 25, characterized in that the proportion of solvent

during the polymerization is in the range from 0.5 to 10% by weight.

27. The process as claimed in at least one of claims 20 to 26, characterized in that the polymerization is performed at a temperature in the range from 0 to 30°C above the initiator temperature at which the half-life of the initiator is 30 minutes.
28. The use of polyalkyl(meth)acrylates as lubricants in transmission systems, characterized in that the polyalkyl(meth)acrylate has a weight-average molecular weight in the range from 3000 to 25 000 g/mol.
29. A wind power plant comprising at least one transmission system comprising a lubricant containing a polyalkyl(meth)acrylate, characterized in that the lubricant comprises at least 30% by weight of polyalkyl(meth)acrylate.