

"GETTER SYSTEM FOR PURIFYING THE WORK ATMOSPHERE IN THE
PROCESSES OF PHYSICAL VAPOR DEPOSITION"

DESCRIPTION

5

The present invention relates to a getter system for purifying the work atmosphere in the processes of physical vapor deposition.

The deposition processes of thin layers of metallic or ceramic materials from suitable vapors or plasmas are more and more widely used in the industry, and are
10 generally referred to in the field by the English term "Physical Vapor Deposition", or by its acronym PVD. These processes are used e.g. in the semiconductor field for depositing a number of layers, that are then selectively removed for obtaining the integrated circuits, or in the compact disc industry for forming the reflecting layer of aluminum.

15 In all these processes a high purity is required for the used gases. In particular, in the semiconductor production, impurities in process gases result in microflaws in the electronic devices, and the smaller the size of the devices, the greater the effect of such flaws on the working of such devices. Owing to the constant trend of reduction of the average size of these devices, it is necessary to
20 use a process gas more and more pure in order to reduce the scrap percentage.

The use of getter materials combined with conventional pumps for purifying gases upstream with respect to the PVD processes is by now a common practice in the industry. However, the purity control of inlet gases in the production lines is not sufficient, since the impurities may enter in the work atmosphere resulting from
25 the degassing of the materials forming the walls or other parts of the chamber. In particular, some processes such as the deposition of aluminium or titanium nitride layers may result in contamination. These depositions are made by the technique known by the English term "sputtering", wherein a flat surface of a "target", consisting of the material to be deposited, is eroded due to the impact of ions of
30 heavy atoms (generally Ar^+ ions) accelerated by a suitable electric field; the

particles removed from the target surface are deposited in form of thin layers onto the substrate of semiconductor material, being generally arranged parallel with respect to the target surface. The gases in the target, e.g. mechanically included in the structure of the material during its production, are discharged during the sputtering process, thus resulting in a high concentration of impurities in the work area. The most common among the impurities are H₂O, H₂, CO, CO₂ and CH₄, and their concentration may range, depending upon the specific features of each process, from about 1 to 100 ppm.

Laid-open patent applications WO 96/13620, WO 96/17171, EP 693626 and WO 97/17542 refer to the gas purifying with getter pumps arranged inside the PVD chambers. These applications disclose getter pumps being arranged inside the chambers in portions far from the work areas. The main advantage obtained by using these pumps *in situ* is the reduction of the dead times being necessary to bring the level of impurities below a predetermined value, after every opening of the chamber, e.g. for maintenance operations.

However, these systems do not solve, or solve only partially, the problem due to the impurities in the work area during the PVD operations, since this area is defined by screens acting so as to prevent the target material from being deposited onto undesired portions of the chamber, such as e.g. feedthroughs, openings for connecting the chamber to gas lines, etc.. These screens have the side-effect of greatly reducing the gas conductance between the work area and the remaining volume of the chamber, thus producing two different gaseous atmospheres inside the process chamber, so that the sorption of the impurities in the work area by the aforementioned *in situ* getter pumps is negligible. Thus, the problem of an effective purifying of the work atmosphere during the PVD process and of the resulting contamination of the layers deposited onto a support by these processes is not yet solved.

The object of the present invention is to provide a getter system for purifying the gaseous atmosphere in the work area in the processes of physical vapor deposition.

This object is achieved according to the present invention by a getter system formed of one or more essentially planar getter devices being inserted inside the work area of a process chamber for physical vapor deposition, in such an arrangement that said getter devices are essentially parallel and spaced apart with
5 respect to the screens defining said work area and the space between the getter devices and the screens is connected to the work area, said getter devices being such that at least the surface facing the screens is made of getter material.

The invention will be hereinafter described with reference to the drawings, wherein:

10 - Figure 1 shows in diagrammatic form a process chamber for physical vapor deposition;

- Figure 2 shows in outline the positioning of the getter system inside the process chamber of Figure 1;

- Figures 3 and 4 show some embodiments of a first type of getter devices
15 which may be used in the system of the invention;

- Figure 5 shows a possible getter system of the invention formed of devices of Figure 3;

- Figure 6 shows a possible alternative embodiment of a second type of getter devices which may be used in the system of the invention;

20 - Figure 7 shows another possible getter system of the invention formed of devices of Figure 6.

Referring to Figure 1, a process chamber is diagrammatically shown for the production of integrated devices. A chamber 10 is formed of a housing 11 defining a space 12 isolated from the atmosphere. The chamber has connected thereto a
25 pumping system for its evacuation, which is generally indicated in Figure as 13, and at least a feeding line for the process gas, which is generally indicated as 14. Inside chamber 10 there are a target 15, being generally shaped as a disk or a short cylinder and made of material 16 to be deposited as a thin layer; a support 17 carrying a housing 18 for a substrate 19 made of a semiconductor material
30 (generally silicon), to have the thin layer of material 16 deposited thereon; finally,

there are screens 20, 20', ... (only two are shown in the Figure). Screens 20, 20', ... divide space 12 in two areas, a work area 21 and an area 22 having therein the auxiliary structures of PVD process, such as the electric connections or the inlets of the gas feeding lines; areas 21 and 22 contact one another only through a small conductance 23 at the edge of the screens. There is a wide variety of modifications to the simple scheme outlined above. For example, work area 21 may be square-, rectangular- or cylindrical-shaped; anyway, generally the screens are essentially planar and inserted inside chamber 10 with the polygonal arrangement being the most suitable to define the desired geometry in the work area. Target 15 may be made of a forerunner of material 16 to be deposited onto substrate 19, or may be part of a system of multiple targets, which is used in some cases for allowing the sequential deposition of layers of different materials without having to open the chamber. Support 17 may be generally shifted in a vertical direction for bringing substrate 19 to the working position, while housing 18 is generally heated in order to keep substrate 19 at a temperature being optimal for obtaining a thin layer with good homogeneity properties; this temperature, depending upon material 16, generally ranges from about 100 to 500 °C.

The getter pumps of the known technique are arranged in various positions inside chamber 10, anyhow always in area 22, and thus they are practically isolated from the gaseous atmosphere of area 21 due to the small conductance between areas 21 and 22.

On the contrary, according to the present invention, the getter system is arranged inside area 21 and thus is in an effective position for sorbing the impurities in this area.

In particular, the getter system according to the invention is formed of essentially planar getter devices which are fastened to the screens so that they are essentially parallel with respect to the screens, there is a space between screens and getter devices and such a space is connected to work area 21; furthermore, the getter devices must be fastened to the screens so as to have at least the surface facing the screens made of getter material.

Figure 2 shows in outline the arrangement of the getter system of the invention inside a PVD process chamber. A getter system 24 is essentially parallel with respect to screens 20, 20', ... and it defines a space 25 between said screens and system 24. System 24 is formed of getter devices 26, 26', ... ; the Figure does not show the means for fastening devices 26, 26' to screens 20, 20', ... , since such means are different depending upon the specific type of used getter devices, as hereinafter described. Getter system 24 has a surface 27 facing work area 21 and a surface 28 facing screens 20, 20', ... ; at least surface 28 must be made of a getter material 29. System 24 may be arranged around the work area so as to sweep an angle smaller than 360° , but preferably it wholly encloses the work area, thus increasing the available surface of getter material and the efficiency of the impurity sorption. As previously said, whatever the geometry of the work area may be, generally the screens are essentially planar, as well as getter devices 26, 26', ... forming the system according to the invention. Should the getter system sweep an angle smaller than 360° around work area 21, it may consist only of a single getter device. However, as previously said, the getter system preferably sweeps a 360° angle around the work area, being in this case formed of several getter devices, and generally of at least as many getter devices as the screens.

Space 25 must be connected to area 21. The condition of the connection between space 25 and area 21 may be complied with in many ways, e.g. by such getter devices that surface 27 is continuous and there is conductance between area 21 and space 25 at areas 30, 30' indicated in Figure 2. However, the required condition is preferably complied with by getter devices 26, 26', ... shaped or arranged so that surface 27 is discontinuous; in particular, it has been found that the best efficiency in removing impurities from area 21 is obtained when the surface 27 being effective, i.e. the sum of the surfaces facing area 21 for all the getter devices, is a fraction of the available surface for a continuous getter system 24 ranging from 70 to 99%, and preferably from 80 to 95%. The discontinuities of surface 27 may be in form of through-holes in devices 26, 26' or of void spaces between adjacent devices; both these possibilities are shown in the Figure, the

discontinuities being indicated as 31, 31', In both cases, the discontinuities may have a regular or an irregular shape, and be regularly or irregularly arranged on the available surface; for example, in case of holes on the surface of a single getter device, they may be square- or round-shaped, or irregularly shaped, and be
5 arranged on the surface of the getter device network-like or random; in case of spacings between adjacent getter devices, the shape and the arrangement of the discontinuities depend upon whether devices 26, 26', ... are regularly arranged on the available surface or not. Generally, regular shapes and arrangements of the discontinuities are preferred, both on single getter devices and between adjacent
10 devices, in that more suitable for an automated production of getter system 24 and allowing an easier control of the aforementioned condition for the ratio between effective surface and available surface for system 24. Mixed configurations are obviously possible, wherein single getter devices have holes and adjacent getter devices are spaced apart from one another.

15 The distance between getter system 24 and screens 20, 20', ... mainly depends upon the overall size of area 21 and the distances between adjacent getter devices and/or the size of the holes on said devices. Generally, the distance between getter system and screens ranges from 1 mm to 5 cm; within these limits, said distance is generally smaller in small-sized PVD-chambers, in order to prevent
20 the getter system from affect the processes occurring in the work area; moreover, said distance increases upon increasing of the distances between adjacent getter devices and/or of the size of the holes on said devices.

A wide variety of getter materials may be used for producing devices 26, 26', ... , including metals such as Zr, Ti, Nb, Ta, V, alloys between these metals or
25 alloys of these metals and one or more elements selected among Cr, Mn, Fe, Co, Ni, Al, Y, La and rare earths, such as binary alloys Ti-V, Zr-V, Zr-Fe and Zr-Ni or ternary alloys Zr-Mn-Fe or Zr-V-Fe, or mixture of the aforementioned metals and alloys. The getter materials most commonly used are the alloy having weight composition Zr 84% - Al 16%, manufactured and sold by the Company SAES
30 GETTERS (Milan, ITALY) under the tradename St 101[®]; the alloy having weight

composition Zr 70% - V 24.6% - Fe 5.4%, manufactured and sold by the Company SAES GETTERS under the tradename St 707TM, or mechanical mixtures of these two alloys and Zr or Ti; these mixtures are preferred due to their good mechanical properties, in particular with respect to the particle loss.

5 Getter devices 26, 26', ... may be bodies made only of getter material, obtained by powder sintering, or may consist of getter material deposited, according to a variety of techniques, onto a metal support.

 The production of sintered bodies from powders is known in the field of powder metallurgy, and it generally comprises the steps of compressing the
10 powders in a suitable mold and heating the clotted powders until a partial melting of the surface of the powder grains is obtained. Modifications to the method in order to obtain bodies having specific features, e.g. being highly porous, are disclosed e.g. in US patent 5324172 and in patent application EP-A-719609, both in the name of the applicant, and in patent application EP-A-765012. Figures 3 and
15 4 show getter devices of this type. Device 35 of Figure 3 is rectangular-shaped, and has at its ends through-holes 36, 36', provided for the use of members such as screws and bolts for fastening the device to the screens at the desired distance; it is obviously possible to use other means for fastening the device to the screens, such as e.g. a metal member having integrated therein a frame for retaining the getter
20 body and suitable spacers which may be fastened to the screens; device 40 of Figure 4 is essentially square-shaped and has a series of through-holes 31, 31', ... allowing an easy connection between work area 21 and space 25, as previously mentioned. During the PVD process, the surface facing area 21 is covered by material 16 to be deposited as a thin layer on substrate 19, whereas surface 28 is
25 active for sorbing impurities.

 Since planar sintered bodies having side dimensions far greater than their thickness are complex to manufacture and have a low mechanical strength, when using these bodies for the getter system of the invention, this latter is preferably formed of a relatively great number of getter devices, each having a surface
30 considerably smaller than the screen having them fastened thereto. An arrangement

of this kind is represented in Figure 5, which shows a portion of a screen 20 having fastened thereto a plurality of devices 26, 26', 26'', ... of type 35; devices 26, ..., are fastened to the screen through suitable mounting members 37, 37', also acting as spacers.

5 Getter devices 26, 26', ... may be also made of getter material deposited onto a metal support. Devices of this type may be produced according to a variety of techniques. A first way is the cold lamination of the getter material powders onto the metal support, according to a technique well known in the field of powders metallurgy. Another way is to spray a suspension of getter particles in a suitable
10 solvent onto the metal support kept hot, such as disclosed in patent application WO 95/23425, to be referred to as for the details of this technique. Furthermore, the metal support may be covered by getter material particles by the electrophoretic technique; as for the details of this technique, patent US 5242559 must be referred to. Finally, the deposition of powders of getter material onto the
15 metal support may be obtained by screen printing technique, such as disclosed in PCT published patent application WO 98/03987. The support may be made of any metal capable of withstanding temperatures of about 600 °C, which may be necessary for the activation of the getter material, and preferably not being ferromagnetic, in order to avoid interferences with the magnetic fields sometimes
20 used in the PVD processes. The use of steel or nickel-chromium alloys is preferred. The thickness of the support may vary within a wide range, and it generally ranges from 0.1 to 1 mm; out of mechanical stability, the thickness of the support preferably increases upon increasing of the side dimensions of getter device 26. The thickness of the getter material deposit 29 in device 26 may vary within a wide
25 range, but, out of production expediency and mechanical stability of the deposit, this thickness generally ranges from about 20 to 500 µm. In this case the getter devices are mounted onto the screens so that the surface of getter material faces these latter. Unlike the aforementioned case, wherein the getter system is formed of sintered bodies, when the getter devices are obtained by depositing the getter
30 material onto a metal support, the system is preferably formed of a relatively small

number of such devices, each having a surface similar to that of the screen having them fastened thereto, so that one, or two at the most, of such devices are fastened to each screen. The production of devices of this type, having a relatively large surface, is easy and allows to spare times and costs both in manufacturing the
5 getter devices and in fastening them to the screens.

Figure 6 shows a possible embodiment of getter devices obtained by depositing getter material onto a metal support. Device 60 is formed of an essentially planar metal support 61 having deposited on a surface 62 thereof getter material 29 (the Figure shows only a partial covering made of getter material); the
10 device has a plurality of holes 31, 31', ... ; support 61 has preferably distortions, such as e.g. lifted edges 63, 63' shown in the Figure or similar members, acting as spacers between the device and the screen having the device fastened thereto. As previously mentioned, holes 31, 31', ... may be regular-shaped or not, and may be arranged on support 61 as a regular network or not, the first way being preferred
15 for an easier automated production. A possible way of assembling a screen of a PVD chamber and a getter device being part of a system according to the invention is represented in Figure 7, showing a screen 20 having fastened thereto a single device 26 of type 60; device 26 may be fastened to the screen through suitable mechanical mounting members, such as screws, or through welding spots 70, 70',
20 ..., on edge 63 of the getter device.

The getter devices require for their working an activation, generally consisting in the heating, by a variety of means, at temperatures of at least 300 °C. This operation may be made during the preparatory steps of the chamber working, such as e.g. the heating of the whole chamber for degassing the walls and obtaining
25 a better resulting vacuum. Otherwise, the getter device activation may be obtained during the operations of material deposition onto disposable substrates, carried out for cleaning the surface of target 15, which are generally polluted before every deposition step; these operations generally result in a heating of the chamber sufficient to the getter activation.

30 By the getter system of the invention, another advantage is obtained in case

the material to be deposited (16) is titanium. Titanium, deposited as thin layers, is well known as a getter material. During the titanium deposition in the chambers for physical vapor deposition, some metal is deposited also onto the walls of the work area, including the screens. In particular, this thin layer sorbs the hydrogen in the
5 work atmosphere, and, due to this sorption, first swells and then comes off from the surfaces upon which it is in form of metal microlayers; these could reach the substrate being processed, thus affecting its quality and contributing to the scrap percentage. On the contrary, by the system of the invention the hydrogen is preferably sorbed by the getter material, thus overcoming the drawback occurring
10 in the common chambers for physical vapor deposition.



CLAIMS

1. A getter system (24) for purifying the gaseous atmosphere of the work area (21) in the processes of physical vapor deposition, formed of one or more
5 essentially planar getter devices (26, 26', ... ; 35; 40; 60) inserted inside said area in such an arrangement that said getter devices are essentially parallel and spaced apart with respect to the screens (20, 20', ...) which define said work area and that the space (25) between the getter devices and the screens is connected to the work area, said getter devices being such that at least the surface (28) facing the screens
10 is made of getter material (29).
2. A getter system according to claim 1, wherein the occupation fraction of the surface (27) of the getter devices facing the work area ranges from 70 to 99% of the available surface.
3. A getter system according to claim 2, wherein said occupation fraction
15 is obtained by arranging in the work area the getter devices so as not to contact one another.
4. A getter system according to claim 2, wherein said occupation fraction is obtained by using getter devices having a discontinuous surface.
5. A getter system according to claim 2, wherein said occupation fraction
20 is obtained by arranging in the work area getter devices having a discontinuous surface so as not to contact one another.
6. A getter system according to claim 2, wherein said occupation fraction ranges from 80 to 95%.
7. A getter system according to claim 1, wherein the distance between the
25 getter devices and the screens ranges from 1 mm to 5 cm.
8. A getter system according to claim 1, wherein the getter material is selected among the metals Zr, Ti, Nb, Ta, V, the alloys between said metals, the alloys of said metals and one or more metals selected among Cr, Mn, Fe, Co, Ni, Al, Y, La and rare earths, the mixtures of said metals and said alloys.
- 30 9. A getter system according to claim 8, wherein the getter material is the



alloy having weight composition Zr 84% - Al 16%.

10. A getter system according to claim 8, wherein the getter material is the alloy having weight composition Zr 70% - V 24.6% - Fe 5.4%.

11. A getter system according to claim 8, wherein the getter material is a mixture of the alloy having weight composition Zr 84% - Al 16% and a metal selected among Zr and Ti.

12. A getter system according to claim 8, wherein the getter material is a mixture of the alloy having weight composition Zr 70% - V 24.6% - Fe 5.4% and a metal selected among Zr and Ti.

13. A getter system according to claim 1, wherein the getter devices are made only of getter material (35; 40).

14. A getter system according to claim 13, wherein said getter bodies are obtained by powder sintering.

15. A getter system according to claim 1, wherein the getter devices are formed of a getter material deposit onto a support (61) made of a metal capable of withstanding thermal treatments up to 600 °C.

16. A getter system according to claim 15, wherein the metal making up the support is not ferromagnetic.

17. A getter system according to claim 15, wherein the support is made of steel.

18. A getter system according to claim 15, wherein the support is made of a nickel-chromium alloy.

19. A getter system according to claim 15, wherein the getter material is deposited onto the metal support by cold lamination.

20. A getter system according to claim 15, wherein the getter material is deposited onto the metal support by spray technique.

21. A getter system according to claim 15, wherein the getter material is deposited onto the metal support by electrophoretic technique.

22. A getter system according to claim 15, wherein the getter material is deposited onto the metal support by screen printing technique.



23. A getter system according to claim 15, wherein the support has a thickness ranging from 0.1 to 1 mm.

24. A getter system according to claim 15, wherein the deposit of getter material has a thickness ranging from 20 to 500 μm .

"GETTER SYSTEM FOR PURIFYING THE WORK ATMOSPHERE IN THE
PROCESSES OF PHYSICAL VAPOR DEPOSITION"

ABSTRACT

5

A system is disclosed formed of one or more getter devices in form of sintered bodies of getter powders or deposits of getter material onto a metal support, to be arranged in the work area of process chambers for the deposition of thin layers of metallic or ceramic materials from vapors or plasmas for purifying the

10


gaseous atmosphere contained in that area.

THIS SHEET HAS BEEN
REPLACED

This Sheet Has Been Replaced



Fig. 1




This Sheet Has Been Replaced



THIS SHEET HAS BEEN
REPLACED

Fig. 2



This Sheet Has Been Replaced



THIS SHEET HAS BEEN
REPLACED

Fig. 3





Fig. 4




This Sheet Has Been Replaced



THIS SHEET HAS BEEN
REPLACED

Fig. 5




This Sheet Has Been Replaced



THIS SHEET HAS BEEN
REPLACED

Fig. 6




This Sheet Has Been Replaced



THIS SHEET HAS BEEN
REPLACED

Fig. 7




This Sheet Has Been Replaced



THIS SHEET HAS BEEN
REPLACED

THIS SHEET HAS BEEN
REPLACED



- 14 -

"GETTER SYSTEM FOR PURIFYING THE WORK ATMOSPHERE IN THE
PROCESSES OF PHYSICAL VAPOR DEPOSITION"

ABSTRACT


5

A system is disclosed formed of one or more getter devices in form of
sintered bodies of getter powders or deposits of getter material onto a metal
support, to be arranged in the work area of process chambers for the deposition of
thin layers of metallic or ceramic materials from vapors or plasmas for purifying the
10 gaseous atmosphere contained in that area.

Figure 2

This Sheet Has Been Replaced






~~THIS SHEET HAS BEEN
REPLACED~~

06 MAY 1999

-2-

Fig. 2



~~THIS SHEET HAS BEEN
REPLACED~~

RÉPLACEMENT SHEET

06 MAY 1999

13

Fig. 4





Fig. 3




~~THIS SHEET HAS BEEN
REPLACED~~

06 MAY 1999

-4-

Fig. 5




~~THIS SHEET HAS BEEN
REPLACED~~

06 MAY 1999


-5-

Fig. 6



~~THIS SHEET HAS BEEN
REPLACED~~

Fig. 7





TEXT OF THE ABSTRACT

GETTER SYSTEM FOR PURIFYING THE WORK ATMOSPHERE IN THE PROCESSES OF PHYSICAL VAPOR DEPOSITION

A system is disclosed formed of one or more getter devices (24) in form of sintered bodies of getter powders or deposits of getter material (29) onto a metal support, to be arranged in the work area of process chambers for the deposition of thin layers of metallic or ceramic materials from vapors or plasma for purifying the gaseous atmosphere contained in that area.

Figure 2.

REPLACEMENT SHEET

10 APR 2000