# CLAIMS

1. An asphalt composition comprising asphalt, a thermoplastic elastomer, and a polyester, wherein

the polyester comprises 50 mol% or more of an aliphatic dicarboxylic acid compound based on the carboxylic acid component,

the polyester has a softening point of 90°C or higher and 140°C or lower and a glass transition point of 40°C or higher and 80°C or lower, and

a ratio of the polyester is 1 part by mass or more and 17 parts by mass or less based on 100 parts by mass of the asphalt.

2. The asphalt composition according to claim 1, wherein the polyester comprises an alcohol component-derived structural unit containing 60 mol% or more of an alkylene oxide adduct of bisphenol A and a carboxylic acid component-derived structural unit.

3. The asphalt composition according to any of claim 1 or 2, wherein the polyester has a hydroxyl value of 2 mgKOH/g or more and 30 mgKOH/g or less.

4. The asphalt composition according to any of claims 1 to 3, wherein the thermoplastic elastomer is at least one selected from the group consisting of a styrene/butadiene block copolymer, a styrene/butadiene/styrene block copolymer, a styrene/butadiene random copolymer, a styrene/isoprene block copolymer, a styrene/isoprene/styrene block copolymer, a styrene/isoprene random copolymer, an ethylene/vinyl acetate copolymer, and an ethylene/acrylic acid ester copolymer.

5. The asphalt composition according to any of claims 1 to 4, wherein the thermoplastic elastomer is at least one selected from the group consisting of a styrene/butadiene block copolymer, a styrene/butadiene/styrene block copolymer, a styrene/butadiene random copolymer, a styrene/isoprene block copolymer, a styrene/isoprene/styrene block copolymer, and a styrene/isoprene random copolymer.

6. An asphalt mixture comprising the asphalt composition according to any of claims 1 to 5 and an aggregate.

7. A method for producing an asphalt mixture, comprising a step of mixing a heated aggregate, asphalt, a thermoplastic elastomer, and a polyester, wherein

the polyester comprises 50 mol% or more of an aliphatic dicarboxylic acid compound based on the carboxylic acid component,

the polyester has a softening point of 90°C or higher and 140°C or lower and a glass transition point of 40°C or higher and 80°C or lower, and

a ratio of the polyester is 1 part by mass or more and 17 parts by mass or less based on 100 parts by mass of the asphalt.

8. The method for producing an asphalt mixture according to claim 7, wherein in the mixing step,

(i) the asphalt and the thermoplastic elastomer are added to and mixed with the heated aggregate, and then, the polyester is added and mixed; or

(ii) the asphalt, the thermoplastic elastomer, and the polyester are simultaneously added to and mixed with the heated aggregate.