


A PROCESS FOR THE PREPARATION OF POLY-ALFA-GLUTAMIC ACID AND DERIVATIVES THEREOF

Field of the invention

The present invention relates to a process for the preparation of poly- α -glutamic acid and derivatives thereof.

Background of the invention

5 Poly- α -glutamic acid of formula (I)



(I)

is currently used as drug delivery system, for example for the preparation of conjugates with a wide variety of drugs containing a primary or secondary amino group as well as primary, secondary or tertiary hydroxy groups. The conjugation can occur directly or through a suitable linker, for example an amino acid or a hydroxyacid. See, for example, EP0932399, Advanced Drug Delivery Reviews, Volume 54, Issue 5, 2002, Pages 695-713 and Journal of Controlled Release, Volume 74, Issues 1-3, 2001, Pages 243-247.


15 Poly- α -glutamic acid can be synthesized by polymerisation of suitably protected glutamic acid. US 3,635,909 discloses, *inter alia*, the polymerisation of D-glutamic acid- γ -(*tert*-butyl)ester N-carboxy anhydride in a 1,2-dichloroethane/1,4-dioxane mixture using sodium 4-methyl-2-pyrrolidone as initiator.

20 Description of the invention

The present disclosure shows that appropriate choice of the solvent and

of the initiator allows the control of the molecular weight of poly- α -glutamic acid prepared from tertiary γ -esters of α -glutamic acid N-carboxy anhydride. Accordingly, in one aspect the invention relates to a process for the preparation of poly- α -glutamic acid (I)

5




wherein n is an integer comprised between 60 and 310, so that the poly- α -glutamic acid has a molecular weight ranging from 8,000 to 40,000 Da, preferably from 10,000 to 35,000 Da, more preferably from 13,000 to 16,000 Da, and with a polydispersity index usually ≤ 2 , preferably ≤ 1.5 ,

10

said process comprising:

- a. the polymerisation of a tertiary γ -ester of α -glutamic acid N-carboxy anhydride of formula (II)

15




wherein R is selected from *t*-butyl, 1,1-dimethylpropyl- and 1,1-dimethylbutyl- and is preferably a *t*-butyl group

either in water or in an organic solvent selected from tetrahydrofuran (THF), 1,4-dioxane, dimethylformamide (DMF), 1,4-dioxane/DMF and 1,4-dioxane/tetrahydrofuran mixtures with an initiator selected from

20

potassium *tert*-butoxide (*t*-BuOK), sodium methoxide (MeONa), diisopropylethylamine, 1,8-diazabicyclo[5,4,0]undec-7-ene (DBU), 4-dimethylaminopyridine (DMAP), glutamic acid dimethyl ester, and glutamic acid- γ -*tert*-butyl ester, to give a compound of formula (III)



(III)

wherein *n* and *R* are as defined above and *R'* is hydrogen when the initiator is selected from diisopropylethylamine, 1,8-diazabicyclo[5,4,0]undec-7-ene (DBU), 4-dimethylaminopyridine (DMAP), glutamic acid dimethyl ester and glutamic acid- γ -*tert*-butyl ester or a *t*-butyl or methyl group when the initiator is *t*-BuOK and MeONa respectively followed by

b. acid hydrolysis of the ester groups.

Throughout the specification, the symbol * indicates a chiral center and the term glutamic acid comprises both the L- and D- form, either as pure isomers or as racemic mixture.

Step a) is usually carried out at a temperature ranging from 10 to 50°C, with a concentration of the γ -ester of α -glutamic acid N-carboxy anhydride ranging from 0.1 to 0.3 M. According to a preferred embodiment, the process is carried out using 1,4-dioxane as the solvent and DBU as the initiator.

The molar ratio of γ -ester of α -glutamic acid N-carboxy anhydride to initiator usually ranges from 2 to 25; the molar ratio of γ -ester of α -glutamic acid N-carboxy anhydride to α -glutamic acid γ -ester is 100.

Step b) can be carried out using any reagent conventionally used for the removal of *tert*-butyl esters, as exemplified by those described in "Protective

groups in organic synthesis" Third edition, Theodora W. Greene and Peter G. M. Wuts, a Wiley-Interscience publication- John Wiley & Sons, Inc, page 406-408 and references therein. Preferred conditions include trifluoroacetic acid (TFA), formic acid and water/formic acid mixtures at a temperature ranging
5 from 20 to 60°C; TFA is used in amount of 100 v/w, while formic acid and water/formic acid mixtures are used in amounts ranging from 20 to 50 v/w.


The process of the invention is suitable for preparing both the D and L form of poly- α -glutamic acids, in particular the L form. Moreover, the poly- α -glutamic acids prepared according to the invention can be easily converted
10 into their acidic or basic salts by reaction with inorganic acids, such as hydrochloric acid, hydrobromic acid, sulphuric acid, nitric acid, perchloric acid or with inorganic bases such as alkaline or alkaline-earth metal hydroxides and ammonium hydroxide.

The process of the invention provides poly- α -glutamic acid with a
15 weight average molecular weight (M_w) determined by Gel Permeation Chromatography combined with Multi Angle Laser Light Scattering detection, ranging within the values defined above, preferably between 13,000 and 16,000 Da and with a polydispersity index ≤ 1.5 . This is particularly advantageous, since the procedures disclosed in the literature, through
20 different γ -protecting groups (such as benzyl, methyl or ethyl; see Polymer monographs, Volume 9: H. Block, Poly(γ -benzyl-L-glutamate) and other glutamic acid containing polymers. Edited by B. Huglin, University of Salford), afford materials of uncontrolled and very high molecular weight, which often require chromatographic separation to isolate poly- α -glutamic
25 acids having a desired molecular weight range.

Moreover, the process of the invention allows to avoid spontaneous formation of a pyroglutamic ester at the amino terminus, which usually occurs during polymerisation using, for example, γ -benzyl, γ -methyl or γ -ethyl

glutamic acid ester N-carboxy anhydride. In fact, currently available poly- α -glutamic acids exhibit either a pyroglutamic terminus, or an amino terminus or a mixture thereof. Suppression of formation of a pyroglutamic terminus is achieved in particular when a compound of formula (II) wherein R is a *t*-butyl group is used as the starting material. Poly- α -glutamic acids γ -esters with a free amino terminus can thus be reacted either with stoichiometric amounts of pyroglutamic acid or with other suitable acids, so as to achieve 100% conversion into the desired N-capped poly- α -glutamic acid.


Accordingly, in another aspect the present invention provides also a process for the preparation of poly- α -glutamic acid derivatives of formula (IV)




wherein n is as defined above and R₁CO- is selected from:

(C₁-C₁₀)alkylcarbonyl; (C₄-C₈)cycloalkylcarbonyl;
 (C₂-C₆)carboxyalkylcarbonyl; (C₆-C₁₀)arylcarbonyl; (C₆-C₁₀)aryl(C₁-C₁₀)alkylcarbonyl;
 (C₁-C₁₀)alkyl(C₆-C₁₀)arylcarbonyl;
 (C₅-C₁₀)heteroarylcarbonyl and (C₅-C₁₀)heteroaryl(C₁-C₁₀)alkylcarbonyl wherein the heteroaromatic ring contains one or more nitrogen, oxygen or sulphur atoms; D- or L-natural and non-natural amino acid residues

said process comprising reacting a compound of formula (III)



obtained according to step a) above with a carboxylic acid $R_1\text{COOH}$ in the presence of a dehydrating agent, or with an activated carboxylic acid, such as an acyl chloride $R_1\text{COCl}$ or an anhydride $(R_1\text{CO})_2\text{O}$, wherein $R_1\text{CO-}$ is as defined above, to give a compound of formula (V)



(V)

and hydrolysing the compound of formula (V) to a compound of formula (IV).

In the compounds of formula (IV) and (V):

preferred $(\text{C}_1\text{-C}_{10})$ alkylcarbonyl are acetyl and butyryl;

10 preferred $(\text{C}_4\text{-C}_8)$ cycloalkylcarbonyl are cyclopropylcarbonyl, cyclobutanecarbonyl, cyclohexylcarbonyl;

preferred $(\text{C}_2\text{-C}_6)$ carboxyalkylcarbonyl is succinyl;

preferred $(\text{C}_6\text{-C}_{10})$ aryl carbonyl are benzoyl, 1-naphthoyl, 2-naphthoyl;

15 preferred $(\text{C}_6\text{-C}_{10})$ aryl $(\text{C}_1\text{-C}_{10})$ alkylcarbonyl are phenylacetyl and phenylbutyryl;

preferred $(\text{C}_1\text{-C}_{10})$ alkyl $(\text{C}_6\text{-C}_{10})$ arylcarbonyl are *o*-, *m*- and *p*-tolyl;

preferred $(\text{C}_5\text{-C}_{10})$ heteroarylcarbonyl are nicotinoyl, N-methylpyrrole-3-carbonyl, 3-thiophenecarbonyl and 3-quinolinecarbonyl;

preferred $(\text{C}_5\text{-C}_{10})$ heteroaryl $(\text{C}_1\text{-C}_{10})$ alkylcarbonyl is 3-pyridyl acetyl;

20 preferred D- or L-natural amino acid residues are those deriving from glycine, alanine, valine, leucine, isoleucine, serine, threonine, lysine, pyroglutamic acid, phenylalanine, tryptophan and cysteine;

25 preferred non-natural amino acid residues are those deriving from β -alanine, α,α -dimethylglycine, α -phenylglycine, homophenylalanine, 3-amino-3-(4-methylphenyl)propionic acid, and

2-(1-aminocyclopentyl)acetic acid.

The reaction between compound (III) and the acid $R_1\text{COOH}$ is carried out in the presence of a dehydrating agent commonly used in peptide chemistry, like carbodiimides, such as dicyclohexylcarbodiimide and diisopropylcarbodiimide, uronium salts, such as 2-1*H*-7-azabenzotriazol-1-yl-1,1,3,3-tetramethyl uronium hexafluorophosphate methanaminium (HATU), 2-(1*H*-benzotriazol-1-yl)-1,1,3,3-*N,N,N',N'*-tetramethyluronium-hexafluorophosphate (HBTU) and 2-(1*H*-6-chlorobenzotriazol-1-yl)-1,1,3,3-*N,N,N',N'*-tetramethyluronium-hexafluorophosphate (HCTU), phosphonium salts, such as benzotriazol-1-yl-*oxy*tris(pyrrolidino)phosphonium hexafluorophosphate (PyBOP), and the like. When a natural or non-natural amino acid is used as the capping agent, its amino group is preferably protected by a suitable protecting group, preferably the *t*-butoxycarbonyl protecting group. Subsequent acidic hydrolysis of the N-capped poly- α -glutamic acid- γ -ester as described in step b) above then provides the N-capped poly- α -glutamic acid. If desired, the compounds of formula (IV) can be converted into their acidic or basic salts by reaction with inorganic acids, such as hydrochloric acid, hydrobromic acid, sulphuric acid, nitric acid, perchloric acid or with inorganic bases such as alkaline or alkaline-earth metal hydroxides and ammonium hydroxide.

The compounds of formula (IV) and (V) are disclosed as another aspect of the present invention.

A particularly preferred embodiment is a compound of formula (IV) wherein $R_1\text{CO}$ is a D- or L-pyroglutamic acid residue and the content of the N-terminus free amine is lower than 1% w/w, preferably lower than 0.2% w/w.


The process described above for the preparation of a compound of formula (IV) has general applicability, that is to say that, further to a carboxylic acid $R_1\text{COOH}$, or an activated carboxylic acid, such as an acyl

chloride $R_1\text{COCl}$ or an anhydride $(R_1\text{CO})_2\text{O}$, any compound able to react with the $-\text{NH}_2$ terminus can be used for the reaction with the compound of formula (III). Examples of such compounds are aldehydes, ketones, α,β -unsaturated ketones, sulfonyl chlorides and nitriles, which can be reacted with compound (III) according to methods known to the skilled chemist. According to a further embodiment of the invention either the carboxylic acid, or activated carboxylic acid, or anhydride, or compound able to react with the $-\text{NH}_2$ terminus may also bear at least a group, such as a hydroxy, an amino or a thio group, which can be further functionalised with a moiety suitable for modulating the pharmacokinetic properties of poly- α -glutamic acid. Therefore, another aspect of the present invention is also a poly- α -glutamic acid substituted at the $-\text{NH}_2$ terminus with a group which is able to be further functionalised with a moiety suitable for modulating the pharmacokinetic properties of poly- α -glutamic acid.

The invention will be hereinafter illustrated in greater detail in the following examples.

EXAMPLE 1

Step a - Preparation of L- α -Glu-NCA- γ -tBu ester



40.17 g of triphosgene (0.135 mol; phosgene/ L-Glu- γ -tBu ester 2.74/1) and 862.5 mL of THF were placed under nitrogen into a 1 L jacketed reactor, equipped with mechanical stirrer. The reactor was thermostated at 20°C and the mixture was stirred until complete dissolution of triphosgene (a few minutes are necessary), thereafter 30 g of L- α -Glu- γ -tBu ester (0.148 mol)


were added in a single portion and quite rapidly. The resulting suspension was allowed to react for 2 hours at 20°C. At the beginning exothermicity was observed ($\approx 4^\circ\text{C}$), then the solid dissolved as the reaction proceeded: after about 30 min a clear solution was obtained.

5 At the end of the reaction the solvent was evaporated under reduced pressure, keeping the jacket temperature not higher than 20°C: the distillation was quite tumultuous. The distillation was continued until a dense and oily residue was obtained, without solids (about 80 mL of residue expected). At the end of the distillation 750 mL of n-heptane were dropped in over about 15 min
10 and the mixture was stirred under nitrogen at 20/23 °C for 1 hour until complete crystallization of the product. Usually, crystallisation begins after addition of 150 mL of n-heptane.

The resulting pure white solid was filtered on buchner funnel and washed with 3×90 mL of n-heptane, then dried in the oven under dynamic
15 vacuum at 20/25 °C for no longer than 20 hours. The solid must be used as soon as possible and must be stored under static vacuum in the presence of silica gel.

Starting from 30 g of L- α -Glu- γ -tBu ester, 23.3 g of L- α -Glu-NCA- γ -tBu ester were obtained (68.8 % yield).

20 **Step b - Polymerization of α -L-glutamic acid- γ -(*tert*-butyl)ester N-carboxy anhydride) (NCA) to poly- α -L-glutamic acid- γ -(*tert*-butyl)ester.**



1,8-Diazabicyclo[5.4.0]undec-7-ene free base (DBU; MW 152.24;
25 585 mg, 3.84 mmol) was dissolved in 1,4-dioxane (5 mL from the total


amount) in few minutes.

In a 1 L jacketed glass reactor 1,4-dioxane (550 mL) and α -L-glutamic acid- γ -(*tert*-butyl)ester N-carboxy anhydride (NCA) (22 g, 96 mmol; NCA/DBU = 25) were mixed at 25°C until dissolution was complete.

5 The resulting solution was added very quickly with the previously prepared DBU solution. A precipitate instantly appeared and low exothermicity was observed (about 3°C).

The mixture was stirred for 4 hours, then water (1100 mL) was slowly poured in over 30 to 40 minutes. After a further 30 minutes stirring at 25°C
10 the precipitated solid was collected by filtration and washed with water (3 x 50 mL). The recovered white solid was then dried under vacuum at 40°C to yield 16.4 g of pure material, t-BuPG (92% recovery; $DP_n = 137.2$, number average degree of polymerisation; $M_n = 25,400$ Da, number average molecular weight from $^1\text{H-NMR}$).

15 **Step c - Hydrolysis of poly- α -L-glutamic acid- γ -(*tert*-butyl)ester to poly- α -L-glutamic acid**



Solid poly- α -L-glutamic acid- γ -(*tert*-butyl)ester (4 g) was suspended in
20 formic acid 99% (80 mL, 20 volumes) under nitrogen atmosphere in a 100 mL jacketed glass reactor. The mixture was stirred at 60°C for 5 hours. After about a 30-minute heating the suspension turned into solution, then a solid began to precipitate.

Most of the formic acid was then removed by distillation under reduced
25 pressure ($P = 15$ torr; internal temperature always below 60°C). The residual

formic acid was evaporated off by azeotropic distillation with toluene (2 x 40 mL; T<40°C).

The resulting residue was suspended in water (40 mL) and the mixture was cooled to 3 - 5°C, then 30% w/w NaOH was carefully added to reach pH
5 8. Once the pH was stable at 23 - 25°C, the resulting solution was filtered through a 0.22 µm microfilter.

The clear solution was acidified by means of sulphuric acid up to pH 2.5, then the resulting suspension was stirred for 2 hours. The precipitated solid was filtered off and dried under vacuum (30°C overnight). A white cake
10 was recovered (2.7 g) with a $M_w = 13,900$ Da and polydispersity 1.04 (GPC - MALLS).

EXAMPLE 2

α-L-glutamic acid-γ-(*tert*-butyl)ester N-carboxy anhydride (3.95 g, 17.2 mmol) was dissolved, under nitrogen stream, in THF (100 mL) to reach a
15 concentration of 0.039 g/mL (0.17 M). The stirring speed was set to 800 rpm.

Then DBU (105 mg, A/I=25) was added by a syringe very quickly and the mixture was stirred for 4 hours at 22-23°C. A slight exotherm was observed soon after addition of the initiator.

Afterwards, the reaction mixture was concentrated to dryness and the
20 residue was rinsed with fresh 1,4-dioxane (100 mL). Two volumes of water were then added to the reaction mixture which was stirred for 30 minutes. The precipitated solid was collected, washed with water and dried under vacuum at 40°C for at least 12 hours.

2.85 g of poly-α-L-glutamic acid-γ-(*tert*-butyl)ester (90% recovery) as
25 a white powder with $M_n = 34,100$ Da and $DP_n = 184$ (by $^1\text{H-NMR}$) were obtained.

The resulting poly-α-L-glutamic acid-γ-(*tert*-butyl)ester was then hydrolysed in hot 99% HCOOH according to the procedure described in step c

of Example 1, furnishing about 1.7 g of poly- α -L-glutamic acid (84% recovery) with $M_w = 25,700$ and polydispersity = 1.2, $n \approx 100$ according to Gel Permeation Chromathography coupled with Multi Angle Laser Light Scattering analysis.

5 **EXAMPLE 3**

GENERAL PROCEDURE FOR THE POLYMER CAPPING REACTION

A typical poly- α -L-glutamic acid- γ -(*tert*-butyl)ester, obtained according to an experimental procedure herein described (see Example 1 and 2), contains about 1% moles of free amino groups at the N-terminus, as determined by ^1H -
10 NMR analysis. This percentage was used to calculate the molar equivalents of the suitable acid to add to poly- α -L-glutamic acid- γ -(*tert*-butyl)ester for its capping reaction.

Poly- α -L-glutamic acid- γ -(*tert*-butyl)ester was dissolved in THF (20 mL/g) then a catalytic amount of 4-dimethylaminopyridine (DMAP; about
15 5-10% moles with respect to the added acid) was added. The suitable acid (10 molar equivalents) was added to the previous mixture and diisopropylcarbodiimide (DIPC, 30-50% molar excess with respect to the acid added) was dropwise added in about 10 min. The solution was stirred for 2 hours.

Two volumes of water were then added and the resulting mixture was
20 stirred for 30 min. The precipitated solid consisting of N-acyl-poly- α -L-glutamic acid- γ -(*tert*-butyl)ester was collected and then suspended in formic acid (20 volumes). After stirring at 60°C for 2 h, two volumes of water were added and the resulting mixture was stirred for 30 min. The precipitated solid was removed by filtration, washed with water and dried under vacuum (30°C,
25 overnight) to yield a suitably N-capped poly- α -L-glutamic acid (N-acyl-poly-L- α -glutamic acid).

Example 3a

Poly- α -L-glutamic acid- γ -(*tert*-butyl)ester (1 g, 0.054 mmol) was

dissolved in THF (20 mL) and catalytic DMAP (8 mg, 0.07 mol) was added. Then N-BOC-L-Phenylalanine (180 mg, 0.7 mmol) was added to the mixture and immediately after DIPC (160 μ L, 1 mmol) was dropwise added. The resulting solution was stirred for about two hours then water (2 volumes) was added and a white precipitate formed immediately. The suspension was stirred for 30 min and filtered, then the white powdered solid was suspended in formic acid (18 mL). The resulting mixture was stirred for 2 h at 60°C and formic acid was removed by distillation at reduced pressure ($P = 15$ torr) followed by azeotropic distillation with toluene (2 x 10 mL of toluene) under slight vacuum (Lakhanpal M.L.; Mandal H.G.; Lal G.; Indian J. Chem, 13, 1309 (1975)). The solid residue was dissolved in aqueous NaHCO_3 and the resulting solution was ultrafiltered through a 5,000 Da cutoff membrane. The retentate was concentrated to about 30 mL and acidified with sulphuric acid until pH 2 – 2.5. The precipitated material was stirred for 30 min and recovered by filtration yielding, after drying under vacuum (30°C, overnight), the corresponding N-terminus phenylalanine-capped poly- α -L-glutamic acid, i.e. N-phenylalanyl-poly- α -L-glutamic acid (530 mg, 84% recovery). The ^1H -NMR was consistent with the proposed structure.

The N-terminal free amine content (clearly detectable at the poly- α -L-glutamic acid- γ -(*tert*-butyl)ester stage) was no longer detectable by ^1H -NMR analysis or by analysis following derivatisation with *o*-phthalaldehyde.

$M_w = 13,300$ polydispersity = 1.16 as determined by GPC-MALLS analysis.

Example 3b

Poly- α -L-glutamic acid- γ -(*tert*-butyl)ester (1 g, 0.054 mmol) was dissolved in THF (40 mL) and DMAP (42 mg, 0.34 mmol) was added. Then L-pyroglutamic acid (44 mg, 0.34 mmol) was added to the mixture and immediately after DIPC (106 μ L, 0.7 mmol) was dropwise added. The

resulting solution was stirred for about two hours then water (2 volumes) was added and a white precipitated formed immediately. The suspension was stirred for 30 min, then filtered and the recovered white powder was suspended in formic acid (18 mL). The resulting mixture was stirred for 2 h at
5 60°C and formic acid was removed by distillation at reduced pressure ($P = 15$ torr) followed by azeotropic distillation with toluene (2 x 10 mL of toluene) under slight vacuum. The solid residue was dissolved in aqueous NaHCO_3 and the resulting solution was ultrafiltered through a 5,000 Da cutoff membrane. The retentate was concentrated to about 30 mL and acidified by means of
10 sulphuric acid until pH 2 – 2.5. The precipitated material was stirred for 30 min and recovered by filtration yielding, after drying under vacuum (30°C, overnight), the corresponding N-terminus pyro-L-glutamic-capped poly- α -L-glutamic acid (400 mg, 64% recovery). The ^1H -NMR was consistent with the proposed structure and the free amine (clearly detectable at the poly- α -L-glutamic acid- γ -(*tert*-butyl)ester stage) was no longer detectable by ^1H -NMR
15 or *o*-phthalaldehyde analysis.

Example 3c

Naphthalen-2-yl-acetic acid (19.7 mg, 0.106 mmol) and N-methyl morpholine (23.7 mg, 25.7 μL , 0.234 mmol) were dissolved in CH_2Cl_2
20 (10 mL) and the mixture was cooled at 0°C.

Chlorotripyrrolidinophosphonium hexafluorophosphate (PyClop, 0.106 mmol, 44.7 mg) was added to the mixture and the resulting solution was stirred for about 1 hour, then poly- α -L-glutamic acid - γ -(*tert*-butyl)ester was added quickly ($n \approx 100$; 1g, 0.054 mmol) and the reaction was stirred for
25 additional 5 hours after the removal of the cooling bath. The solvent was evaporated under reduced pressure. The crude material was dissolved again in THF (10 mL) and water (2 volumes) was added. The resulting suspension was stirred for 30 min, then it was filtered and the recovered white powder was

suspended in formic acid (18 mL). The resulting mixture was stirred for 2 h at 60°C. The mixture was cooled down and formic acid was removed by distillation at reduced pressure ($P = 15$ torr) followed by azeotropic distillation with toluene (2 x 10 mL each). The solid residue was dissolved in aqueous NaHCO_3 and the resulting solution was ultrafiltered through a 5000 Da cutoff membrane. The retentate was concentrated to about 30 mL and acidified by means of sulfuric acid until pH 2 – 2.5. The precipitated material was stirred for 30 min and recovered by filtration yielding, after drying under vacuum (30°C, overnight), the corresponding N-(Naphthalen-2-yl-acetyl)-poly- α -L-glutamic acid (570 mg, 82% recovery). The $^1\text{H-NMR}$ was consistent with the proposed structure and the free amine (clearly detectable at the poly- α -L-glutamic acid- γ -(*tert*-butyl)ester stage) was no longer detectable by $^1\text{H-NMR}$ or *o*-phthalaldehyde analysis.

Example 3d

Naphthalen-2-yl-acetic acid (31.7 mg, 0.17 mmol), TEA (3.5 mg, 4.7 μL , 0.034 mmol) and *N,N'*-disuccinimidyl carbonate (DSC, 43.6 mg, 0.17 mmol), were dissolved in a 1:1 mixture of $\text{CH}_2\text{Cl}_2/\text{CH}_3\text{CN}$ (2 mL) and the resulting mixture was stirred at room temperature for 2 hours. The mixture was dropwise added to a poly- α -L-glutamic acid- γ -(*tert*-butyl)ester ($n \approx 100$; 1 g, 0.054 mmol) solution in CH_2Cl_2 (10 mL) and the resulting solution was stirred overnight. The solvent was then removed under reduced pressure and the crude material was processed in the same way as described in the Example 3C.

The recovered solid, after drying under vacuum (30°C, overnight), furnished the corresponding N-(Naphthalen-2-yl-acetyl)-poly- α -L-glutamic acid (612 mg, 88% recovery). The $^1\text{H-NMR}$ was consistent with the proposed structure and the free amine (clearly detectable at the poly- α -L-glutamic acid- γ -(*tert*-butyl)ester stage) was no longer detectable by $^1\text{H-NMR}$ or

o-phthalaldehyde analysis.

Example 3e

Poly- α -L-glutamic acid- γ -(*tert*-butyl)ester ($n \approx 100$; 1 g, 0.054 mmol) was dissolved in THF (20 mL) and catalytic DMAP (8 mg, 0.07 mmol) was added. Then 2-thiophenebutyric acid (119 mg, 0.7 mmol) was added to the mixture and immediately after DIPC (160 μ L, 1 mmol) was dropwise added. The resulting solution was stirred for about two hours then water (2 volumes) was added and a white precipitate formed immediately. The suspension was stirred for 30 min and filtered, then the white powdered solid was suspended in formic acid (18 mL). The resulting mixture was stirred for 2 h at 60°C and formic acid was removed by distillation at reduced pressure ($P = 15$ torr) followed by azeotropic distillation with toluene (2 x 10 mL of toluene) under slight vacuum. The solid residue was dissolved in aqueous NaHCO_3 and the resulting solution was filtered on a fiberglass filter (0.2 μ m). The filtrate was acidified with H_2SO_4 2N until pH 2 – 2.5. The precipitated material was stirred for 30 min and recovered by filtration yielding, after drying under vacuum (30°C, overnight), the corresponding N-terminus 2-thiophenebutyryl-capped poly- α -L-glutamic acid, i.e. N-(2-thiophenebutyryl)-poly- α -L-glutamic acid (480 mg, 76% recovery). The ^1H -NMR was consistent with the proposed structure.


The N-terminal free amine content (clearly detectable at the poly- α -L-glutamic acid- γ -(*tert*-butyl)ester stage) was no longer detectable by ^1H -NMR analysis or by analysis following derivatisation with *o*-phthalaldehyde.

$M_w = 13,300$, polydispersity = 1.12 as determined by GPC-MALLS analysis.

According to a very similar procedure, N-(2-thiophenepropanoyl)-poly- α -L-glutamic acid and N-(2-thiophenepentanoyl)-poly- α -L-glutamic acid, were also obtained.

CLAIMS


1. A process for the preparation of poly- α -glutamic acid of formula (I)



wherein the symbol * indicates a chiral center n is between 60 and 310, so that the poly- α -glutamic acid has a molecular weight ranging from 8,000 to 40,000 Da


said process comprising the steps of:

- a) polymerisation of a tertiary γ -ester of α -glutamic acid N-carboxy anhydride of formula (II)



wherein the symbol * is as defined above and R is selected from *t*-butyl, 1,1-dimethylpropyl and 1,1-dimethylbutyl

in water or in an organic solvent selected from: tetrahydrofuran, 1,4-dioxane, dimethylformamide, 1,4-dioxane/DMF and 1,4-dioxane/tetrahydrofuran mixture with an initiator selected from potassium *tert*-butoxide, sodium methoxide, diisopropylethylamine, 1,8-diazabicyclo[5,4,0]undec-7-ene, dimethylaminopyridine and L-glutamic acid- γ -*tert*-butylester, to give a compound of formula (III)



(III)

wherein * and R are as defined above and R' is hydrogen when the initiator is selected from diisopropylethylamine, 1,8-diazabicyclo[5,4,0]undec-7-ene, 4-dimethylaminopyridine, glutamic acid dimethyl ester and glutamic acid- γ -*tert*-butyl ester or R' is a *t*-butyl or methyl group when the initiator is potassium *tert*-butoxide and sodium methoxide respectively and

followed by

- 10 b) acid hydrolysis of the γ - and α -ester groups to give a compound of formula (I).
2. The process according to claim 1 wherein the solvent is 1,4-dioxane and the initiator is 1,8-diazabicyclo[5,4,0]undec-7-ene.
3. The process according to claim 1 or 2 wherein the temperature ranges
- 15 from 10 to 50°C.
4. The process according to any one of claims 1 to 3 wherein the concentration of the tertiary γ -ester of α -glutamic acid N-carboxy anhydride ranges from 0.1 to 0.3 M.
5. The process according to any one of claims 1 to 4 wherein step b) is
- 20 carried out in an acid selected from trifluoroacetic acid, formic acid and water/formic acid mixtures at a temperature ranging from 20 to 60°C.
6. The process according to any one of claims 1 to 5 wherein R is *t*-butyl.
7. The process according to any one of claims 1 to 6 wherein the molecular weight of the poly- α -glutamic acid (I) ranges from 13,000 to
- 25 16,000 Da and the polydispersity index is ≤ 1.5 .