

Description

This invention relates to the manufacture of foundry moulds and cores and to moulding compositions useful therein. More particularly, the invention relates to the use of highly condensed potassium alkali phenolic resins in the binders for the moulds and cores.

Phenol-formaldehyde (PF), phenol-formaldehyde/furfuryl alcohol-formaldehyde condensation products, catalysed with strong acid catalysts, such as phosphoric acid, sulphuric acid and paratoluene sulphuric acid and the like, are well known as binders for sand in the production of cold-setting foundry moulds and cores. Aromatic sulphonic acids are more commonly employed than all other types but have the disadvantage that pungent fumes of sulphur dioxide are evolved on thermal decomposition.

UF/FA condensation products contain nitrogen which can form ammonia on thermal decomposition and this tends to neutralise the sulphur dioxide. However, nitrogen in the binder can react with certain metals, such as, for example, grey and nodular irons and steel, resulting in the formation of small bubbles in the final casting, a defect known in the foundry industry as "pinholing". The employment of UF/FA binders is consequently restricted.

Phosphoric acid may be employed as a catalyst but tends to build up on the sand on repeated attrition reclamation and this reduces the refractoriness of the sand. Phosphoric acid is also incompatible with PF/FA condensation products and, as a result, the moulds and cores produced exhibit poor bond strengths.

In the foundry moulding art the use of aqueous highly alkaline phenol-aldehyde resins as binders for sand has not been developed because they tend to produce weak cores. It is known in other fields that the curing of phenol-formaldehyde resins can be catalysed by esters. The application of this to foundry moulds and cores has been suggested in Japanese Patent publication (Kokai) No. 130627/1975 and our earlier specifications G.B. 2059972A and EPA 0027333. Whilst these Specifications show that foundry cores and moulds having adequate strength and strength increase with time can be made they require the use of relatively high proportions of resin which is costly and makes recovery of the sand, after casting, more difficult.

The present invention is based on the discovery that the use of highly condensed phenol-formaldehyde resins can give moulds and cores which have adequate strength and strength increase at much lower levels of resin. The use of such highly condensed resins in making foundry moulds and cores has not been considered practicable, heretofore.

The present invention accordingly provides a method of making a foundry mould or core which comprises mixing granular refractory material with a binder which comprises:

1. from 0.25 to 2.5% by weight of the granular refractory material of an aqueous solution, having a solids content of from 50 to 75% by weight, of a potassium alkali phenol-formaldehyde resin having the following characteristics:

a) a weight average molecular weight ($\bar{M}_w$) of from 700 to 2000;

b) a formaldehyde:phenol molar ratio of from 1.2:1 to 2.6:1; and

c) a KOH:phenol molar ratio of from 0.5:1 to 1.2:1;

2. from 0.05 to 3% by weight on the weight of the resin solution of at least one silane; and
3. from 20 to 110% by weight on the weight of the resin solution of at least one ester active to catalyse curing of the resin; forming the mixture and allowing the mixture to set by curing of the resin in the binder.

The moulding composition comprising the mixture of granular refractory material and binder as set out above is believed to be novel and, accordingly, forms part of the invention.

The granular refractory materials used in the present invention may be any of the refractory materials commonly employed in the foundry industry for the production of moulds and cores, such as silica sand, quartz, chromite sand, zircon or olivine sand. The compositions of the invention have the particular advantage that the difficulties commonly associated with the bonding of sands of alkaline reaction, such as olivine and chromite, or beach sands containing shell fragments, and which arise from neutralisation or partial neutralisation of the acid catalyst used in conventional systems, are completely overcome, since in this invention the resin binder is cured under alkaline conditions. The invention is, therefore, of particular utility where it is necessary or desirable to employ alkaline sands.

The nature of the phenol-formaldehyde resin used is a most important feature of the present invention. There are several features of the resin which are important. Since the present invention is directed to cold set techniques, the resin binder will be used as an aqueous solution of the resin. The solids content of the aqueous solution is in the range 50 to 75% by weight. Solids contents below 50% are not used because they contain too much water which reduces the effectiveness of the binder. Solids contents above 75%, are not used because the viscosity becomes too high.

The phenol-formaldehyde resins used in this invention have a weight average molecular weight ($\bar{M}_w$) of from 700 to 2000 and preferably from 800 to 1700. Resins with $\bar{M}_w$ less than 700, such as were used in our earlier GB-A-2059972, give products which are relatively weaker or require significantly more resin to achieve similar strengths. Resins with $\bar{M}_w$ greater than 2000 are either not adequately water soluble within the range of KOH contents used in the invention or precipitate out of solution or cause the solution to gel before the resin has cured adequately yielding products with poor strength.

Optimum results may not be obtained within the broad $\bar{M}_w$ range at the extreme limits of the ranges of KOH:phenol and formaldehyde:phenol molar ratios, especially at the lower end of the KOH:phenol ratio.

We have obtained satisfactory results showing the advantage of the invention throughout the 800 to 1700 M_w range. We have, to date, obtained optimum results using resins having M_w greater than 950.

The resins used in this invention are potassium alkaline phenol-formaldehyde resins by which is meant that the alkali in the resin is potassium alkali. This alkali can be present in the resin during manufacture or, more usually, post added to resin as KOH, preferably in aqueous solution of suitable strength. The alkalinity of the resin is expressed in terms of its KOH content and specifically by the molar ratio of KOH to the phenol in the resin. Other alkalis are not expressly excluded and may be present in minor amounts but will not be specifically added because they slow curing of the resin and give products having lower strength. We have found that substituting the KOH used in the invention by an equimolar amount of NaOH gives cores which typically have half the strength after 1 hour and only achieve two thirds the strength after 24 hours of cores made using KOH as the alkali.

The molar ratio of KOH:phenol in the resin solution is in the range 0.5:1 to 1.2:1 and preferably 0.6:1 to 1.2:1. At ratios less than 0.5 the speed of cure and product strength are much reduced. The reasons for this are not entirely clear but it seems probable that at such low ratios the resin tends to be insoluble or precipitates from solution during curing. Also we believe that a relatively high KOH:phenol ratio increases the concentration of phenolate type anions which enhances activity of the resin to curing by cross-linking. Ratios higher than 1.2 are not used because the excess KOH makes the resins hazardous to handle and inhibits curing by oversolubilizing the resin and/or reducing the effect of ester catalysis. The use of KOH:phenol ratios lower than 0.6 is not preferred with resins having M_w less than 800 because the speed of cure and product strength is below optimum.

The resins used have a formaldehyde to phenol molar ratio of from 1.2:1 to 2.6:1. Lower ratios are not used because lower strengths are obtained in use. Higher ratios are not used because they are either of low molecular weight, or are excessively crosslinked, or contain undesirably high levels of unreacted formaldehyde. Especially, within the preferred limits of this ratio suitable highly condensed resins, with low levels of unreacted formaldehyde and high reactivity can be obtained.

It is a subsidiary aspect of this invention that the resin used satisfies the following criteria:

- a) M_w from 800 to 1700;
- b) KOH:phenol molar ratio of from 0.6:1 to 1.2:1 and
- c) formaldehyde:phenol molar ratio of from 1.2:1 to 2.6:1.

The curing catalyst used in the invention is an ester. Suitable esters include low molecular weight lactones e.g. γ -butyrolactone, propiolactone and ϵ -caprolactone, and esters of short and medium chain e.g. C_1 to C_{10} alkyl mono- or polyhydric alcohols, with short or medium chain e.g. C_1 to C_{10} carboxylic acids especially acetic acid. We have obtained very good results using triacetin (glyceryl triacetate) as the catalyst.

The amount of catalyst used is in the range 20 to 110%, preferably 25 to 40% by weight on the weight of resin solution used, corresponding approximately to 10 to 80% by weight on the weight of solid resin in the solution. The optimum in any particular case will depend on the ester chosen and the properties of the resin. The mechanism of catalysis is not certain but we believe that it involves the initial nucleophilic attack by anionic sites in the resin on the ester which activates the resin to crosslinking reactions in the presence of the alkali.

A silane is included in the mixture to improve product strength. Amounts as low as 0.05% by weight on the weight of resin solution provide a significant improvement in strength. Increasing the amount of silane gives greater improvements in strength up to about 0.6% by weight on the resin solution. Higher silane concentrations are not preferred because of added cost. Further, because the silane typically used is γ -aminopropyltriethoxy silane which contains nitrogen, use of excess silane may increase the risk of pinholing defects and for these reasons amounts in excess of 3% by weight on the resin solution are not used.

The following Examples illustrate the invention.

The techniques used in the Examples are described below:

Manufacture of phenol formaldehyde resin solutions

100% Phenol was dissolved in 50% aqueous KOH in an amount corresponding to the desired KOH:phenol molar ratio (from 0.5 to 1.2). The solution was heated to reflux and 50% aqueous formaldehyde was added slowly, whilst maintaining reflux, in an amount corresponding to the desired formaldehyde:phenol molar ratio (1.6, 1.8 or 2.0). The reaction mixture was maintained under reflux until it attained a pre-determined viscosity corresponding to the desired value of M_w . (If desired the solids content can be adjusted by distillation, but this is not usually necessary. This is a further advantage of the invention. In some cases minor amounts of KOH solution were added to adjust the KOH:phenol ratio, but this would not be necessary in full scale production). The resin solution was cooled to 40°C and 0.4% by weight on the weight of the resin solution of γ -aminopropyl triethoxy silane was added.

Testing of resins

- a) viscosity—measured using an Ostwald (U-tube) viscometer at 25°C.
- b) Solids content—measured by heating a weighed sample (2.0 ± 0.1 g) in an air circulating oven for 3 hrs. at 100°C.

c) molecular weight ($\bar{M}_w$)—measured using gel permeation chromatography. Samples were prepared by precipitating resin from the resin solution by adding H_2SO_4 ; separating, washing and drying the precipitate and dissolving it in tetrahydrofuran.

5 Preparation of test foundry cores

1 kg of the selected sand was charged to a Fordath laboratory coremixer. The ester catalyst was added and mixed for 1 min and the resin solution was then added. Mixing was continued for 1 min and the mixture then quickly discharged into the test moulds. One sample was rammed into a waxed paper cup which was squeezed by hand to assess the bench life and when setting had occurred. Other samples were
10 formed into 5×5 cm cylindrical test cores by the standard method recommended by I.B.F. working party P. The test cores were placed in a standard atmosphere, 20°C; 50% relative humidity, and samples were tested for compression strength 1 hr, 2 hr, 4 hr and 24 hr after manufacture. All compression test cores were made within 2 minutes of discharge of the mix.

In the Examples tests designated with a letter (tests A to F) are comparative tests outside the invention,
15 tests designated with a number (1 to 22) are of the invention.

Example 1

This Example illustrates the effect of phenol-formaldehyde resin $\bar{M}_w$ on core performance.

Test cores were made from the following starting materials *phenol-formaldehyde resin solution*

20 $\bar{M}_w$ —variable—see Table 1

Formaldehyde:phenol molar ratio 2:1

KOH:phenol molar ratio 0.85:1

Solids 64% by weight

Amount 1.5% by weight on sand.

25 Sand—Chelford 50

Silane 0.4% by weight on resin solution of γ -aminopropyltriethoxysilane.

Catalyst 30% by weight on resin solution of triacetin (0.45% on sand).

The values of $\bar{M}_w$ and test results are set out in Table 1. Tests A and B are of resins outside the $\bar{M}_w$ range
30 of this invention. The results show that the benefit of the invention is obtained within a restricted range of $\bar{M}_w$.

TABLE 1

Test No.	A	1	2	3	4	5	6	B
35 $\bar{M}_w$	560	718	849	966	1050	1217	1320	$\infty^{(3)}$
Viscosity (cSt)	—	81	111	144	167	321	364	501
Bench life (mins)	65	23	19	16	14 ⁽²⁾	10	10	2
40 Set time (mins)	180	32	28	22	22 ⁽²⁾	16	15	3
45 Compression strength (kPa) ⁽¹⁾								
1 hr	0	690	1580	2070	2050 ⁽²⁾	2465	2415	0
2 hr	0	1950	2765	2960	2685 ⁽²⁾	3000	3000	0
50 4 hr	0	2860	3200	3520	2750 ⁽¹⁾	3300	3300	0
24 hr	1480	4785	4800	5000	4650 ⁽²⁾	4400	4400	800

⁽¹⁾ "0" figures for Compression strength mean that the resin had not set at the test time or the core was soft.

55 ⁽²⁾ average of 2 runs.

⁽³⁾ " ∞ " means that $\bar{M}_w$ is >2000 and was too high to measure by the method used.

Example 2

Example 1 was repeated using resins having a lower KOH:phenol molar ratio.

60 Phenol-formaldehyde resin solution

$\bar{M}_w$ —variable—see Table 2

KOH:phenol molar ratio 0.65:1

formaldehyde:phenol molar ratio 2:1

65 Solids 66% by weight

Amount 1.5% by weight on sand.

Sand—Chelford 50

Silane 0.4% by weight on resin solution of γ -aminopropyltriethoxysilane.

Catalyst 30% by weight on resin solution of triacetin. The values of $\bar{M}_w$ and test results are set out in Table 2. The results are similar to those of Example 1. The result of Test No. 7 could be improved using γ -butyrolactone as the catalyst.

TABLE 2

Test No.	7	8	9	10
$\bar{M}_w$	718	849	966	1050
Viscosity (cSt)	107	202	320	405
Bench life (mins)	35	24	18	15
Set time (mins)	70	40	30	26
Compression strength (kPa)				
1 hr	0	740	1085	1285
2 hr	590	1600	1875	2200
4 hr	1085	2350	2650	2900
24 hr	3000	4400	4350	5000

Example 3

This Example illustrates the use of different levels of and different catalysts and gives a comparison with the system of U.K. Specification 2059972.

TABLE 3

Test No.	11	12	C ⁽³⁾
$\bar{M}_w$	966	966	560
Viscosity (cSt)	144	144	ca 70
KOH:phenol	0.85	0.85	0.52
formaldehyde:phenol	2	2	1.8
Solids (%)	64	64	68.1
Amount of binder (%) ⁽¹⁾	1.4	1.33	2.1
Catalyst ⁽²⁾	γ -Bu	TAc	γ -Bu
Amount of catalyst (%)	30	25	32
Bench life (mins)	3	18	5
Set time (mins)	5	24	8
Compression strength (kPa)			
1 hr	2320	1725	1725
2 hr	2950	2765	2450
4 hr	3300	3500	3350
24 hr	4500	5000	4800

Test C is Example 6 of U.K. 2059972

⁽¹⁾ Amount of binder is solids content of binder including resin alkali and catalyst as % by weight on sand

⁽²⁾ γ -Bu= γ -butyrolactone. TAc=triacetin.

⁽³⁾ For Test C the data are based on the resin solution i.e. the combination of the 6 parts of "resin" and the 2.4 parts of 50% KOH solution.

Example 4

This Example illustrates the effect of variation of the KOH:phenol molar ratio.

Phenol-formaldehyde resin solution

$\bar{M}_w$ 966

formaldehyde:phenol molar ratio 2:1

KOH:phenol molar ratio-variable—see Table 4.

Solids 64% by weight

Amount varies to maintain solid organic resin to sand ratio—see Table 4.

Sand—Chelford 50

Silane 0.4% by weight on resin solution of γ -aminopropyltriethoxysilane.

Catalyst 30% by weight on resin solution of triacetin. The results are set out in Table 4.

TABLE 4

Test No.	13	14	15	16	17
KOH:phenol molar ratio	0.34	0.51	0.68	0.85	1.02
Wt. % resin solution on sand	1.33	1.41	1.5	1.59	1.67
Bench life (mins)	30	18	15	12	9
Set time (mins)	100	29	23	19	15
Compression strength (kPa)					
1 hr	0	890	2070	2615	2465
2 hr	200	1625	2715	3305	3110
4 hr	440	2220	3355	3550	3395
24 hr	1875	3995	5032	4537	4271

25 Example 5

This Example further illustrates the variation of KOH:phenol molar ratio at lower formaldehyde:phenol (f:phenol) molar ratios and values of $\bar{M}_w$. The results are set out in Table 5. In all cases the resin solution was used at 1.5% by weight on the sand and including 0.4% by weight on the resin solution of γ -aminopropyltriethoxy silane. The catalyst was triacetin 30% by weight on the resin solution.

TABLE 5

Test No.	D	18	E	19	F	20	21	22
$\bar{M}_w$	650	800	720	950	650	900	1100	1603
Viscosity (cSt)	191	276	478	460	600	414	277	350
Solids (%)	62.7	63.2	63.2	66.1	65.4	66.2	60.2	58
f:phenol ratio	1.8	1.8	1.8	1.8	1.6	1.6	1.6	1.6
KOH:phenol ratio	0.46	0.79	0.46	0.79	0.45	0.79	0.79	0.75
Bench life (mins)	60	14	35	10	45	20	12	11
Set time (mins)	220	20	90	16	120	35	18	15
Compression strength (kPa)								
1 hr	0	2465	0	2515	0	1235	1875	2270
2 hr	0	3100	350	3300	150	2200	2860	3060
4 hr	150	3350	790	3300	350	2800	3300	3500
24 hr	1240	4500	2660	4000	2150	4000	4600	4685

60 Claims

1. A foundry moulding composition comprising

(a) a granular refractory material;

(b) from 0.25 to 2.5% based on the weight of the refractory material of an aqueous solution of a potassium alkali phenol-formaldehyde resin, which aqueous solution has a solids content of from 50 to 75% by weight, the resin having a weight average molecular weight ($\bar{M}_w$) of from 700 to 2000, a

TABLE 4

Test No.	13	14	15	16	17
KOH:phenol molar ratio	0.34	0.51	0.68	0.85	1.02
Wt. % resin solution on sand	1.33	1.41	1.5	1.59	1.67
Bench life (mins)	30	18	15	12	9
Set time (mins)	100	29	23	19	15
Compression strength (kPa)					
1 hr	0	890	2070	2615	2465
2 hr	200	1625	2715	3305	3110
4 hr	440	2220	3355	3550	3395
24 hr	1875	3995	5032	4537	4271

Example 5

This Example further illustrates the variation of KOH:phenol molar ratio at lower formaldehyde:phenol (f:phenol) molar ratios and values of $\bar{M}_w$. The results are set out in Table 5. In all cases the resin solution was used at 1.5% by weight on the sand and including 0.4% by weight on the resin solution of γ -aminopropyltriethoxy silane. The catalyst was triacetin 30% by weight on the resin solution.

TABLE 5

Test No.	D	18	E	19	F	20	21	22
$\bar{M}_w$	650	800	720	950	650	900	1100	1603
Viscosity (cSt)	191	276	478	460	600	414	277	350
Solids (%)	62.7	63.2	63.2	66.1	65.4	66.2	60.2	58
f:phenol ratio	1.8	1.8	1.8	1.8	1.6	1.6	1.6	1.6
KOH:phenol ratio	0.46	0.79	0.46	0.79	0.45	0.79	0.79	0.75
Bench life (mins)	60	14	35	10	45	20	12	11
Set time (mins)	220	20	90	16	120	35	18	15
Compression strength (kPa)								
1 hr	0	2465	0	2515	0	1235	1875	2270
2 hr	0	3100	350	3300	150	2200	2860	3060
4 hr	150	3350	790	3300	350	2800	3300	3500
24 hr	1240	4500	2660	4000	2150	4000	4800	4685

Claims

1. A foundry moulding composition comprising
 - (a) a granular refractory material;
 - (b) from 0.25 to 2.5% based on the weight of the refractory material of an aqueous solution of a potassium alkali phenol-formaldehyde resin, which aqueous solution has a solids content of from 50 to 75% by weight, the resin having a weight average molecular weight ($\bar{M}_w$) of from 700 to 2000, a



formaldehyde:phenol molar ratio of from 1.2:1 to 2.6:1 and a KOH:phenol molar ratio of from 0.5:1 to 1.2:1;

(c) at least one silane in an amount of from 0.05 to 3% by weight based on the weight of the resin solution; and

5 (d) as curing agent, at least one ester in an amount of from 20 to 110% by weight based on the weight of the resin solution.

2. A composition according to claim 1, wherein the refractory material is silica sand, quartz, chromite sand, zircon, olivine sand, beach sands containing shell fragments or mixtures thereof.

3. A composition according to either claim 1 or claim 2, wherein the resin has a $\bar{M}_w$ of from 800 to 1700.

10 4. A composition according to claim 3, wherein the resin has a $\bar{M}_w$ of from 950 to 1700.

5. A composition according to any one of claims 1 to 4, wherein the molar ratio of KOH:phenol in the resin is from 0.6:1 to 1.2:1.

6. A composition according to any one of claims 1 to 5, wherein the ester curing agent is present in an amount of from 25 to 40% by weight based on the weight of the resin solution.

15 7. A composition according to any one of claims 1 to 6, wherein the ester is a lactone selected from γ -butyrolactone, propiolactone and ϵ -caprolactone.

8. A composition according to any one of claims 1 to 6, wherein the ester is an ester of a 1—10C alkyl mono- or polyhydric alcohol with a 1—10C carboxylic acid.

9. The composition according to claim 8, wherein the ester used as curing agent is glycerol triacetate
20 (triacetin).

10. A method of making a foundry mould or core which method comprises mixing a granular refractory material with a binder which comprises:—

1) from 0.25 to 2.5% by weight of the granular refractory material of an aqueous solution having a solids content of from 50 to 75% by weight, of a potassium alkali phenolformaldehyde resin, having the
25 following characteristics:—

a) a weight average molecular weight ($\bar{M}_w$) of from 700 to 2000;

b) a formaldehyde:phenol molar ratio of from 1.2:1 to 2.6:1; and

c) a KOH:phenol molar ratio of from 0.5:1 to 1.2:1;

2) from 0.05 to 3% by weight of the resin solution of at least one silane; and

30 3) from 20 to 110% by weight of the resin solution of at least one ester active to catalyse curing of the resin; forming the mixture and allowing the mixture to set by curing of the resin in the binder.

11. A method according to claim 10, wherein the refractory material is silica sand, quartz, chromite sand, zircon, olivine sand, beach sands containing shell fragments or mixtures thereof.

12. A method according to either claim 10 or claim 11, wherein the resin has a $\bar{M}_w$ of from 800 to 1700.

35 13. A method according to claim 12, wherein the resin has a $\bar{M}_w$ of from 950 to 1700.

14. A method according to any one of claims 10 to 13, wherein the molar ratio of KOH:phenol in the resin is from 0.6:1 to 1.2:1.

15. A method according to any one of claims 10 to 14, wherein the ester curing agent is present in an amount of from 25 to 40% by weight based on the weight of the resin solution.

40 16. A method according to any one of claims 10 to 15, wherein the ester is a lactone selected from γ -butyrolactone, propiolactone and ϵ -caprolactone.

17. A method according to any one of claims 10 to 15, wherein the ester is an ester of a 1—10C alkyl mono- or polyhydric alcohol with a 1—10C carboxylic acid.

18. A method according to claim 17, wherein the ester is glycerol triacetate.

Patentansprüche

1. Giessereiformmasse, welche

(a) ein körniges feuerfestes Material;

50 (b) von 0,25 bis 2,5%, bezogen auf das Gewicht des feuerfesten Materials, einer wässrigen Lösung eines Kalium-alkalischen Phenol-Formaldehyd-Harzes, wobei diese wässrige Lösung einen Feststoffgehalt von 50 bis 75 Gew.% aufweist, das Harz ein durchschnittliches molekulares Gewichtsmittel ($\bar{M}_w$) von 700 bis 2.000 besitzt, das molare Verhältnis von Formaldehyd:Phenol 1,2:1 bis 2,6:1 und das molare Verhältnis von KOH:Phenol von 0,5:1 bis 1,2:1 geht;

55 (c) mindestens ein Silan in einer Menge von 0,05 bis 3 Gew.%, bezogen auf das Gewicht der Harzlösung; und

(d) als Härter mindestens einen Ester in einer Menge von 20 bis 110 Gew.%, bezogen auf das Gewicht der Harzlösung, umfasst.

2. Formmasse nach Anspruch 1, dadurch gekennzeichnet, dass das feuerfeste Material
60 Siliziumdioxidsand, Quarz, Chromitsand, Zircon, Olivinsand, Sand von Stränden, der Schalenfragmente enthält, oder Gemische derselben darstellt.

3. Formmasse gemäss Anspruch 1 oder 2, dadurch gekennzeichnet, dass das Harz ein $\bar{M}_w$ von 800 bis 1.700 aufweist.

4. Formmasse gemäss Anspruch 3, dadurch gekennzeichnet, dass das harz ein $\bar{M}_w$ von 950 bis 1.700
65 aufweist.



5. Formmasse gemäss einem oder mehreren der Ansprüche 1 bis 4, dadurch gekennzeichnet, dass das Molverhältnis von KOH:Phenol in dem Harz von 0,6:1 bis 1,2:1 beträgt.

6. Formmasse gemäss einem oder mehreren der Ansprüche 1 bis 5, dadurch gekennzeichnet, dass der Ester, der als Härtemittel verwendet wird, in einer Menge von 25 bis 40 Gew.%, bezogen auf das Gewicht der Harzlösung, vorliegt.

7. Formmasse gemäss einem oder mehreren der Ansprüche 1 bis 6, dadurch gekennzeichnet, dass der Ester ein Lacton aus der Gruppe γ -Butyrolacton, Propiolacton und ϵ -Caprolacton darstellt.

8. Formmasse gemäss einem oder mehreren der Ansprüche 1 bis 6, dadurch gekennzeichnet, dass der Ester ein Ester eines C_{1-10} -alkylmono- oder -polyhydri-schen Alkohols mit einer C_{1-10} -Carbonsäure darstellt.

9. Formmasse gemäss Anspruch 8, dadurch gekennzeichnet, dass der als Härtemittel verwendete Ester Glycerin-triacetat (Triacetin) darstellt.

10. Verfahren zur Herstellung von Giessereiformen oder -kernen, gekennzeichnet durch Mischen eines körnigen feuerfesten Materials mit einem Binder, der

(1) von 0,25 bis 2,5 Gew.%, bezogen auf das körnige feuerfeste Material, einer wässrigen Lösung mit einem Feststoffgehalt von 50 bis 75 Gew.% eines Kalium-alkalischen Phenol-Formaldehyd-Harzes, das die folgenden Charakteristiken aufweist:

(a) ein durchschnittliches molekulares Gewichtsmittel ($\bar{M}_w$) von 700 bis 2.000;

(b) ein Molverhältnis von Formaldehyd:Phenol von 1,2:1 bis 2,6:1; und

(c) ein Molverhältnis von KOH:Phenol von 0,5:1 bis 1,2:1;

(2) von 0,05 bis 3 Gew.%, bezogen auf die Harzlösung, mindestens eines Silans; und

(3) von 20 bis 110 Gew.%, bezogen auf die Harzlösung, mindestens eines aktiven Esters, um die Härtung des Harzes zu katalysieren, umfasst; Formen des Gemisches und Aushärten des Gemisches durch Härtung des Harzes im Binder.

11. Verfahren gemäss Anspruch 10, dadurch gekennzeichnet, dass als feuerfestes Material Siliziumdioxidsand, Quarz, Chromitsand, Zircon, Olivinsand, Sand von Stränden, der Schalenfragmente enthält, oder Gemische derselben verwendet wird.

12. Verfahren gemäss Anspruch 10 oder 11, dadurch gekennzeichnet, dass das Harz ein $\bar{M}_w$ von 800 bis 1.700 aufweist.

13. Verfahren gemäss Anspruch 12, dadurch gekennzeichnet, dass das Harz ein $\bar{M}_w$ von 950 bis 1.700 aufweist.

14. Verfahren gemäss einem oder mehreren der Ansprüche 10 bis 13, dadurch gekennzeichnet, dass das Molverhältnis von KOH:Phenol im Harz 0,6:1 bis 1,2:1 beträgt.

15. Verfahren gemäss einem oder mehreren der Ansprüche 10 bis 14, dadurch gekennzeichnet, dass der als Härtungsmittel verwendete Ester in einer Menge von 25 bis 40 Gew.%, bezogen auf das Gewicht der Harzlösung, vorliegt.

16. Verfahren gemäss einem oder mehreren der Ansprüche 10 bis 15, dadurch gekennzeichnet, dass der Ester ein Lacton aus der Gruppe γ -Butyrolacton, Propiolacton und ϵ -Caprolacton darstellt.

17. Verfahren gemäss einem oder mehreren der Ansprüche 10 bis 15, dadurch gekennzeichnet, dass der Ester einen Ester eines C_{1-10} -alkyl-mono- oder -polyhydri-schen Alkohols mit einer C_{1-10} -Carbonsäure darstellt.

18. Verfahren gemäss Anspruch 17, dadurch gekennzeichnet, dass als Ester Glycerintriacetat verwendet wird.

Revendications

1. Composition de moulage de fonderie comprenant:

a) une matière réfractaire granulée;

b) entre 0,25 et 2,5% rapportés au poids de la matière réfractaire d'une solution aqueuse d'une résine phénol-formaldéhyde alcaline par du potassium, cette solution ayant une teneur en solides entre 50 et 75% en poids, la résine ayant un poids moléculaire moyen en poids ($\bar{M}_w$) compris entre 700 et 2000, un rapport molaire formaldéhyde/phénol entre 1,2/1 et 2,6/1 et un rapport molaire KOH/phénol entre 0,5/1 et 1,2/1;

c) au moins un silane en une quantité comprise entre 0,05 et 3% en poids, rapportée au poids de la solution de la résine; et

d) en tant qu'agent durcissant, au moins un ester en une quantité comprise entre 20 et 110% en poids, rapportée au poids de la solution de résine.

2. Composition selon la revendication 1, caractérisée en ce que la matière réfractaire est du sable de silice, du quartz, du sable de chromite, du zircon, du sable d'olivine, un sable de plage contenant des débris de coquillages ou un mélange de ceux-ci.

3. Composition selon la revendication 1 ou 2, caractérisée en ce que la résine présente un $\bar{M}_w$ compris entre 800 et 1700.

4. Composition selon la revendication 3, caractérisée en ce que la résine présente un $\bar{M}_w$ compris entre 950 et 1700.

5. Composition selon l'une quelconque des revendications 1 à 4, caractérisée en ce que le rapport molaire KOH/phénol dans la résine est compris entre 0,6/1 et 1,2/1.

6. Composition selon l'une quelconque des revendications 1 à 5, caractérisée en ce que l'ester utilisé



comme agent durcissant est présent en une quantité comprise entre 25 et 40% en poids rapportée au poids de la solution de résine.

7. Composition selon l'une quelconque des revendications 1 à 6, caractérisée en ce que l'ester est une lactone choisie parmi la γ -butyrolactone, la propiolactone et l' ϵ -caprolactone.

5 8. Composition selon l'une quelconque des revendications 1 à 6, caractérisée en ce que l'ester est un ester d'un alcool mono- ou polyhydrique d'alkyle C_1-C_{10} avec un acide carboxylique C_1-C_{10} .

9. Composition selon la revendication 8, caractérisée en ce que l'ester utilisé comme agent durcissant est le triacétate de glycérol (triacétine).

10. Procédé de fabrication d'un moule ou d'un noyau de fonderie, dans lequel on mélange une matière

réfractaire granulée avec un liant comprenant:
1) entre 0,25 et 2,5% rapportés au poids de la matière réfractaire granulée, d'une solution aqueuse ayant une teneur en solides entre 50 et 75% en poids d'une résine phénol-formaldéhyde alcaline par du potassium, présentant les caractéristiques suivantes:

a) un poids moléculaire moyen en poids (M_w) entre 700 et 2000

15 b) un rapport formaldéhyde/phénol entre 1,2/1 et 2,6/1; et

c) un rapport molaire KOH/phénol entre 0,5/1 et 1,2/1;

2) entre 0,05 et 3% rapportés au poids de la solution de résine d'au moins un silane; et

3) entre 20 et 110% rapportés au poids de la solution de résine d'au moins un ester ayant une activité catalytique sur le durcissement de la résine; on forme le mélange et on permet au mélange de se figer

20 grâce au durcissement de la résine dans le liant.

11. Procédé selon la revendication 10, caractérisé en ce que la matière réfractaire est du sable de silice, du quartz, du sable de chromite, du zircon, du sable d'olivine, un sable de plage contenant des débris de coquillages ou un mélange de ceux-ci.

12. Procédé selon la revendication 10 ou 11, caractérisé en ce que la résine présente un M_w compris

25 entre 800 et 1700.

13. Procédé selon la revendication 12, caractérisé en ce que la résine présente un M_w entre 950 et 1700.

14. Procédé selon l'une quelconque des revendications 10 à 13, caractérisé en ce que le rapport molaire KOH/phénol dans la résine est compris entre 0,6/1 et 1,2/1.

15. Procédé selon l'une quelconque des revendications 10 à 14, caractérisé en ce que l'ester utilisé

30 comme agent durcissant est présent en une quantité comprise entre 25 et 40% en poids, rapportée au poids de la solution de résine.

16. Procédé selon l'une quelconque des revendications 10 à 15, caractérisé en ce que l'ester est une lactone choisie parmi la γ -butyrolactone, la propiolactone et l' ϵ -caprolactone.

17. Procédé selon l'une quelconque des revendications 10 à 15, caractérisé en ce que l'ester est un

35 ester d'un alcool mono- ou polyhydrique d'alkyle C_1-C_{10} avec un acide carboxylique C_1-C_{10} .

18. Procédé selon la revendication 17, caractérisé en ce que l'ester est le triacétate de glycérol.

40

45

50

55

60

65

