



159159

1

PLASTERBOARD COMPRISING AT LEAST ONE FACING PAPER WITH A
COATING SLIP CONTAINING PLASTIC PIGMENTS, COATING SLIP, AND
APPERTAINING MANUFACTURING PROCESS

Technical field

This invention relates to the general technical field of construction materials and in particular to that relating to the manufacture of prefabricated plasterboard comprising a plaster body and at least one exterior facing paper or cardboard coated with a coating slip or rendering.

This invention relates to plasterboard comprising at least one facing paper forming the exterior of the board, the facing paper on which a coating slip is deposited being designed to improve the visual effect of the plasterboard and/or to make possible the installation of wallpaper directly on the facing paper and on the coating slip previously deposited on said paper.

This invention also relates to the coating slip or rendering properly speaking designed to be spread or deposited on the facing paper.

This invention also relates to a manufacturing process for plasterboard comprising at least one facing paper forming the exterior of the plasterboard, a process in which a coating slip or rendering is deposited on the facing paper.

Finally, this invention also relates to a novel use of compounds that are involved in the composition of coating slips or renderings as whitening agents in a coating slip for facing paper designed for plasterboard.



Prior art

Plasterboard or panelling is well-known and traditionally realised from a body or core of gypsum plaster which is deposited, in general by pouring, between
5 two cardboard paper supports ensuring both the mechanical maintenance or framework of the plaster as well as its exterior facing on its outer surfaces.

The fabrication of plaster panelling of this sort is well-known and in particular described in patent EP-
10 A 0 521 804 by the same applicant, and which can be referred to if need be.

In this previous patent, provision is also made to deposit, on the exterior surface of the facing paper, a coating slip with the purpose in particular of ensuring a
15 proper aesthetic appearance of the outer layer of the facing paper by avoiding in particular its yellowing, and by ensuring for it a proper homogeneity of white colour without for all that negatively affecting the manufacturing of the paper, its performance over time and its strength
20 qualities, in particular mechanical.

Nevertheless, a search is constantly being made to obtain plasterboard possessing facing papers presenting good aesthetic properties of their outer layers while being of low cost.

25 One of the means contemplated consists in realising the facing paper by means of materials presenting a low cost and therefore of quality inferior to the materials, in particular the fibres, used previously. Now, recourse to fibres of reduced quality, in general fibres obtained from

recycled paper, has the disadvantage of leading to a facing paper that is darker and less homogeneous in its mass and in its overall hue. The reduction in cost of the base paper, if it actually leads to an appreciable reduction in the cost of the plasterboard, nevertheless has the negative consequence of leading to the production of a paper presenting an external visual appearance that is darker and less homogeneous. On the whole the plaster panelling obtained therefore presents diminished aesthetic qualities.

10 Restoration of whiteness to paper that is obtained of lower quality has also been contemplated, by increasing the proportion of whitening agent in the coating slip for the paper. Such an inclusion, in addition to the fact that its economic significance is debatable, is not directly
15 envisioned because it is accompanied by a reduction in the porosity of the coated paper, which has the tendency to reduce the evaporation of water during the setting of the plaster. Consequently, this increases drying time, which in this way reduces the productivity of manufacturing and
20 therefore renders this solution unacceptable.

In other respects, the reduction in the drying properties of the paper, i.e., the increase in the value of Gurley porosity (NF ISO 5636-5) of the paper, is also expressed by risks of detachment of the paper when the
25 plasterboard is manufactured or by the appearance of blisters.

Disclosure of the invention

The objectives assigned to the invention consequently aim at remedying the various disadvantages enumerated

already and at offering a novel plasterboard as well as a novel coating slip and a novel manufacturing process for plasterboard which, although of reduced manufacturing cost, presents excellent properties of finish and visual appearance, in particular of whiteness, while being easy to manufacture and preserving its integrity over time.

Another object of the invention aims at providing a novel plasterboard and a novel manufacturing process pertaining to it, as well as a novel coating slip that makes it possible to efficaciously obtain a particularly homogeneous visual effect of this plasterboard.

The objects assigned to the invention are attained by means of plasterboard comprising at least one facing paper forming the exterior of the plasterboard, and a coating slip deposited on said facing paper characterised in that the coating slip contains plastic pigments as whitening agents.

The objects assigned to the invention are also attained by means of a coating slip designed to be coated on the upper layer of a facing paper for plasterboard characterised in that it contains plastic pigments as whitening agents.

The objects assigned to the invention are also attained by means of a manufacturing process for plasterboard comprising at least one facing paper forming the exterior of the board on which a coating slip is deposited on the upper surface of the facing paper characterised in that a coating slip is deposited that contains plastic pigments as whitening agents.

Finally, the objects assigned to the invention are attained by means of a novel use of plastic pigments as whitening agents in a coating slip for facing paper designed for plasterboard.

5

Best mode of carrying out the invention

Other objects and advantages of the invention will appear in more detail upon reading of the description which follows, given purely in an illustrative and non-restrictive way.

10 This invention has for object a plasterboard formed from a body or core of plaster poured within appropriate fittings, between two exterior frames formed, as a general rule, of sheets of paper or cardboard, thus taking care of both the exterior facing of the plasterboard and its
15 supporting framework.

Such plasterboard is traditionally used as construction material and is used to form partitions or ceilings, or to form linings, in particular insulation.

20 The manufacture of these boards is generally realised through a set of standard operations involving, as is well known by those skilled in the art, a pouring of plaster on one of the facing papers, then the installation of the second facing paper, and then finally the drying of the board leading to a heavy evaporation of water and to the
25 production of the final construction board after setting.

The overall steps in manufacture are well described in patent EP-0 521 804 which can be referred to if necessary.

In the case of this invention, the plasterboard as set forth in the invention presents at least one facing paper

forming the exterior of the board and more preferably two facing papers arranged on both sides of the plaster body.

The facing paper used is, more preferably, a multi-layered paper that can for example be formed by stacking
5 two or more layers, and in particular two to nine layers without the number of layers being restrictive.

In a particularly advantageous way, the facing paper of plasterboard as set forth in the invention will be formed by a succession of two layers, it being understood
10 that within the meaning of the invention use can also be made of a stacking of three or five layers without exiting the framework of the invention.

The characteristics of the paper, given below in a by no means restrictive way, such as for example its grammage
15 (NFQ03-019), or its thickness (NFQ03-016), its water absorption properties, whether it is a matter of its properties for absorption of water on the surface in contact with the sheet of plaster or Cobb three minutes (NFQ03-014), or of its properties for absorption of water
20 on the exterior surface or Cobb three minutes (NFQ03-014), its permeability to air (GURLEY porosity - NFISO-5636-5), its resistance to breakdown measured according to standard (NFQ03-004), its inter-fold strength, its elongation under water measured after one minute at 23°C in the transverse
25 direction (NFQ03-063), etc. are adapted to withstand the presence and evaporation of water as well as the various manufacturing operations.

By way of non-restrictive examples, the grammage of the base paper is to be between 100 and 250 g/m², and
30 preferentially, it is to be between 160 and 200 g/m², and

in a still more preferential way, it is to be between 180 and 200 g/m².

In a general way, the production of a low-cost plasterboard, compared to the usual plasterboards, involves the use of low-cost facing paper, which correlatively implies recourse to fibres of reduced quality leading in the end to paper of overall colour that is darker and for example of the order of 50 to 70 ISO (ISO 2469/2470), and, for example, of the order of 60.

To best advantage, the upper layer of the facing paper designed to form the exterior of the plasterboard, and which will therefore be the visible surface of the board will be realised from a mixture of bleached or semi-bleached recycled fibres such as white clippings or outdated office paper. The papers, references and nomenclatures of the papers cited in patent EP-0521804, by the same applicant, are fully applicable here (group C and in particular C7 to C9 and C11, C12, C14 to C19).

The upper layer can also be realised from recycled unprinted office paper or from newsprint. By way of information, other usable fibres or pulps might be bleached or semi-bleached virgin cellulose fibres such as chemical-mechanical fibres, thermomechanical fibres or thermomechanical chemical fibres.

The base grammage of the upper layer can be approximately within the range of 20 - 90 g/m² and preferentially between approximately 30 to 50 g/m². Quite obviously, and as is known to those skilled in the art, the grammage of the upper layer of the facing paper will play a very important role in the production of the final

whiteness of the paper and those skilled in the art will adapt the grammage of the upper layer in terms of the grammage and properties of the other layers, as well as in terms of the properties of the coating slip. In a non-restrictive way, the whiteness of the upper layer is to be between 65 to 68 ISO.

The layer of paper that is in contact with the plaster (gypsum) will be to best advantage made from old corrugated cardboard, or from recovered raw material originating in household use and including for example packaging for liquids, or similar types of fibres, or a mixture of these fibres that can give the required solidity and porosity to these layers.

The upper facing surface or upper ply of the paper, which makes up the exposed surface of the plasterboard, is designed to accept a coating slip that will confer superior aesthetic qualities on this surface and in particular one or more qualities chosen from among:

- a surface with confirmed and homogeneous whiteness;
- a surface that does not yellow with use or only with difficulty, in particular on account of UV radiation;
- a surface that precludes the subsequent application of a primer;
- a surface easy to clean;
- a surface that makes possible the installation and especially the removal of wallpaper without degradation of the layer of paper, and which in particular makes possible the successive removal of several layers of paper without major degradation;

-a surface that does not require being painted immediately after installation of the plaster board or panelling.

5 The coating slip is in a position to fulfil the already stated objectives without degrading the qualities and functions of the paper in relation to its role as framework and for the draining of water during drying of the plaster.

10 The coating slip can be deposited to best advantage in a proportion of approximately 25 to 30 g/m², its application being quite obviously dependent on the degree of initial whiteness of the paper; the whiter the base paper, the less the application of the coating slip need be. The degree of whiteness of the coated paper, i.e.,
15 coated with the coating slip, can to best advantage have an ISO gloss index between 75 and 85 and to best advantage between 78 and 80.

The application of the coating slip is to be carried out according to the usual techniques used in the field
20 such as by air knife or by roller or by blade or by spraying or other means, or by a combination of one or more of these techniques well-known to those skilled in the art and referenced for example in patent EP-A-0 521 804.

As set forth in the invention, the plasterboard
25 comprising at least one facing paper forming the exterior of the plasterboard as well as a coating slip deposited on the facing paper comprises a coating slip that contains plastic pigments as whitening agents.

The application of plastic pigments through the
30 coating slip proved in fact to give or restore a good

degree of whiteness to the facing paper, and this in a homogeneous fashion without for all that it being possible to observe an appreciable drop in the porosity of the paper corresponding to an elevated Gurley value.

5 This turned out to be surprising because the use of plastic pigments in coating slips designed for facing papers for plasterboard wasn't known, and a negative effect as far as paper porosity is concerned could certainly be expected.

10 Now, it turned out on the contrary that whiteness could be given or restored to the facing paper and this even in situations in which the facing paper is of a relatively dark colour, because it is possible, without fear of significantly negative side-effects as far as
15 porosity is concerned, to incorporate elevated levels of plastic pigments in the coating slip.

 Quite obviously, the invention also relates to a coating slip containing plastic pigments as whitening agents.

20 To best advantage, the coating slip set forth in the invention and/or the plasterboard comprising at least one facing paper on which a coating slip is deposited is to be such that the coating slip contains at least 5% by weight of plastic pigments.

25 It is recognized that advantageous industrial effects have been perceptibly obtained from 5% by weight of plastic pigments in the coating slip, even if, as far as improvement of paper whiteness is concerned, an effect can be obtained at a lower level.

To best advantage, the coating slip and the plasterboard comprising the facing paper on which the coating slip is deposited contain between 5 and 40% by weight of plastic pigments, and more preferably between 15 and 25% by weight of plastic pigments.

As mentioned already, the coating slip is to be applied in the proportion of approximately 10 g/m² to 45 g/m², and more preferably in the proportion of approximately 20 to 30 g/m², and in an even more preferential way, in a proportion of 25 to 30 g/m².

The plastic pigments, also designated as organic pigments as opposed to inorganic pigments such as clay, talc or calcium carbonate for example, are synthetic polymeric latexes whose vitreous transition point is sufficiently high so as to give to these latexes one or more non-film-forming properties making it possible for the particles composing this type of latex to remain separate.

The plastic pigments or organic pigments that can be used in the coating slip set forth in the invention can be chosen from among plastic pigments available on the market, and in particular from among plastic pigments with filled particles or with hollow particles. To best advantage, the plastic pigments will be formed from hollow particles, i.e., comprising a free internal volume.

By way of non-restrictive example, the plastic pigments used in the coating slip can be plastic pigments sold under the ROPAQUE (registered trademark) HP-1055 brand name available from the ROHM & HAAS company, or plastic pigments corresponding to the ROPAQUE (registered trademark) BC-643 brand of the same manufacturer. Other

compounds can quite obviously be used without for that reason exiting the overall framework of the invention.

The plastic pigments are to be included and mixed in a coating slip containing in addition to the plastic pigments:

-at least 25% and preferably at least approximately 30% of fillers, more preferably of calcium carbonate, and more preferably at approximately 44%,

-a quantity of water,

-a dispersing agent,

-a defoamer agent,

-at least 8% of binder (more preferably styrene-butadiene and more preferably at approximately 16%),

-an insolubilising agent, more preferably an epoxy-aliphatic resin,

-a biocide, more preferably an organo-sulfurated/nitrogenous agent (organosulphur/azotee).

By way of inorganic filler, it is possible to use, in place of calcium carbonate, any equivalent filler such as for example calcium sulphate dihydrate in any form.

As a binder, it is essentially possible to use synthetic binders, and in particular synthetic latexes (styrene-butadiene or styrene-acrylic in particular). Thus, in place of styrene-butadiene or in combination with it, it can is obviously conceivable to use other synthetic latexes and, more generally, all polymeric materials customarily employed, and for example synthetic polymeric materials such as polyvinyl acetates and polymers of acrylic monomers as well as polymeric materials of natural origin, such as, speaking non-restrictively, amylaceous polymers, modified

or not, casein-type proteins or a mixture of synthetic polymeric materials and polymeric materials of natural origin.

To best advantage, the proportion of synthetic binders
5 can be significantly increased in the coating slip compared to coating slips known to prior art.

Thus, plasterboard according to the invention will comprise a binder formed of a synthetic latex or a combination of synthetic latexes, the binder(s) being
10 preferentially included in the coating slip, in the proportion of at least 10% and more preferably at least 12% by weight.

To best advantage, the synthetic latex(es) are included in the proportion of at least 15% by weight in the
15 coating slip.

Finally, the binder is to best advantage to be made of styrene-butadiene included in the proportion of approximately 15 to 16% by weight in the coating slip (table 2).

20 This addition, significantly higher than standard percentages of addition, improves the resistance of the coated paper to sanding and therefore of the plasterboard without, surprisingly, the observation, as might have been expected, of a corresponding closure of the paper leading
25 to a prolongation of the drying time. Moreover, the performance of jointing renderings on plasterboards comprising a paper coated with a coating slip comprising that high a proportion of latex, is not affected and is at least comparable to the performance on known plasterboards.

In addition to the components already indicated, the coating slip may contain secondary components that may or may not be present in the coating slip.

5 In this way, the coating slip may additionally contain titanium dioxide, acting as filler, in the proportion of 10% by weight.

The coating slip may also contain a pH agent, for example sodium hydroxide, for example in the proportion of less than 1% by weight in the coating slip.

10 The coating slip may also contain ammonium as a fluidifier. The ammonium can be included at a very low level.

Finally, the coating slip may additionally contain oxidised maize starch acting as a binder, as a supplement
15 to the styrene-butadiene, more preferably in the proportion of approximately 15% by weight.

Example 1 of realisation

Table 2 below gives an example of practical
20 realisation of a coating slip in accordance with the invention.

The values in column 9 relating to "fractions" expresses the composition of the coating slip such as is traditionally used in the field, as percentage of the dry
25 matter of the component as a function of the value of the dry matter of the pigment, whose reference is given as being equal to 100.

In the case in which there are several types of pigments in the coating slip, the sum of their relative
30 values is also indicated as being the 100 reference and the

values of the other components of the coating slip is calculated as a function of this.

In this case, the plastic pigment therefore represents 20% of the dry extract of the total of the three fillers used, which is in total 193.769 kg (sum of the dry matter of the totality of the fillers in the composition), which corresponds to approximately 13% by weight of plastic pigments referred to the totality of the dry formulation.

As filler, the coating slip contains approximately 44% calcium carbonate and approximately 16% styrene-butadiene as binder.

The plastic pigment (Ropaque HP-1055) is composed of polymeric pigments of acrylic styrene with particles on the order of 1.0 micrometers in diameter with a 55% void volume.

The coating slip was deposited by an air knife system after addition after addition of a supplementary quantity of water in order to reduce the viscosity of the coating slip, for example on the order of 80 litres on a facing paper presenting the characteristics shown in table 1 below.

The deposition was done in the proportion of approximately 29 g/m².

The values shown in table 1 were obtained in accordance with the standards in force, namely:

- porosity: (Gurley value) NF ISO 5636-5
- Cobb: ISO 535,
- Dennison test: TAPPI 459,

-colour measurements: in accordance with standard T527 OM94 (TAPPI), the colour system being expressed according to the CIE L*, a*, b* system.

Study of the results shows that the measured colour indices of the coated paper were significantly elevated, whereas the porosity of the paper remained within acceptable values since the porosity (Gurley value) of the paper went from 67.4 s/100 ml (uncoated paper) to 137.8 s/100 ml (coated paper).

10 The initial value of whiteness of the paper, which was 84.27 (the value 0 corresponds to black and the value 100 to perfectly white) went, for its part, to 89.23.

The other representative values of the colour measurement a* for grey and b* for blue were also
15 distinctly improved.

It consequently turned out that inclusion of a plastic pigment whitening agent in the coating slip and the application of this coating slip to a base paper specifically designed for plasterboard and produced from
20 fibres of reduced quality, for example unbleached recycled fibres, makes it possible to give, efficaciously and inexpensively, a good degree of whiteness to the facing paper of plasterboard. This addition can be made without
25 in particular its qualities and properties of porosity, and this even at the elevated quantities of addition that can be required in the case of particularly dark base papers. It is therefore not only possible to restore whiteness to the facing paper, but also to do so efficaciously.

30

Example 2 (Table 3)

This example does not differ practically from example 1, the composition of the coating slip being unchanged, only certain trade names of products having changed and
5 having come from different suppliers (and therefore with different references) for calcium carbonate, and the binder (oxidised maize starch). The other conditions are essentially unchanged with respect to example 1.

The results shown in table 5 for this example 2 also
10 show a significant elevation in the whiteness of the paper after coating and of the plasterboard. The paper used presents a grammage of 195 g/m² and the coating slip was deposited in the proportion of 30 g/m² according to the procedure already described.

15

Example 3 (Table 4)

Essentially speaking, the composition of the coating slip is similar to that of examples 1 and 2, except for the binder content, since the oxidised maize starch was omitted
20 as well as the associated component, namely sodium hydroxide (fluidifier) which proportions were reduced. The proportions of the other components remained essentially identical in this coating slip.

This coating slip was coated according to the
25 procedure already described in the proportion of 23 g/m² on a base paper with grammage on the order of 195 g/m². The addition of plastic pigments contributes to the significant increase in the whiteness of the paper as shown in Table 5.

Finally, the results shown in table 5 are also
30 interesting in their comparative character between examples

2 and 3 because the measurements carried out originate in batches of identical papers and identical plasterboards on which the coating slips of examples 2 and 3 were coated. The regulatory effect of oxidised maize starch on the
5 whiteness of the paper is then noticed, this regulatory effect being particularly clear indeed on the gloss of the coated paper.

Example 4 (Table 6)

10 In this example, the addition of plastic pigments has been greatly reduced, and it only represents 4.15% (5 parts) by weight of the coating slip. In spite of this reduced level of addition, it is possible to observe (Table 7) a significant elevation in the whiteness of the coated
15 paper and of the plasterboard produced, thus marking the preponderant effect of the plastic pigments. The heavy reduction in the content of plastic pigments also explains the low gloss value in relation to the high filler content.

20 Trials of capacity for painting

) Trials of application of paint were also conducted on coated paper by means of "FASTOATIN" acrylic paint from the TOLLENS company.

The application of paint proved to be particularly
25 easy and the level of covering was very good. After drying, the area having undergone application is appreciably whiter than the facing paper of the plasterboard, the overall result being excellent. No particular problem in application of the second layer was noted, the results
30 still being excellent.

Trials on detachment and removal of wallpaper

Trials for the purpose of evaluating the strength and the maintenance of integrity of the facing paper during
5 removal and detachment of wallpaper were also conducted.

The paper used was a standard wallpaper from CASTORAMA.

Surface active agent: PERFAX from HENKEL.

Dilution of the product: 40 ml for 4 l of water.

10 The adhesive used was an ordinary "Métylan" (registered trademark) adhesive from HENKEL.

The initial attempt at detaching and stripping the paper showed that the surface active agent had the tendency to act rapidly on the plasterboard.

15 It is also possible to proceed by spraying the surface active agent.

In all cases, it proved to be almost impossible to damage or harm the facing paper of the plasterboard.

20 After an initial removal of the wallpaper, the gluing of a second layer of wallpaper was carried out, under the same conditions as the first operation.

Stripping of this second layer also did not pose any particular problem, the facing paper still reacting rapidly and very well to the surface active agent, in such a way
25 that it was still possible to withdraw this second layer of paper extremely easily. The only two areas of degradation of the facing paper were caused by the damage created by the stripping knife used for the operation.

30 Trials of resistance to sanding

Trials on the mechanical resistance to sanding by the facing paper were carried out on standard plasterboards as controls and on plasterboards fitted with facing paper in accordance with the invention and on which a coating slip
5 was deposited in accordance with the invention.

The results show that the two plasterboards lost essentially the same weight through mechanical erosion, namely approximately 0.2 g. In other respects their behaviour was essentially identical.

10 The entire set of these trials clearly shows, in addition to the good whiteness obtained with the use of plastic pigments, that the mechanical properties of overall strength of the paper are preserved.

The invention also relates to a manufacturing process
15 for plasterboard comprising at least one facing paper forming the exterior of the plasterboard on which a coating slip is deposited on the upper surface of the facing paper.

The manufacturing process set forth in the invention is characterised in that a coating slip containing plastic
20 pigments is deposited in the capacity of a whitening agent.

To best advantage, the coating slip contains at least 5% by weight of plastic pigments.

Preferentially, the manufacturing process set forth in the invention is characterised in that the coating slip
25 applied contains between 5 and 40% by weight of plastic pigments, and more preferably between 15 and 25% by weight of pigments.

To best advantage, the application of the coating slip is carried out in the proportion of 10 to 45 g/m², more
30 preferably in the proportion of approximately 20 to 30

g/m², and even more preferably in the proportion of 25 to 30 g/m².

Even more preferably, an application of coating slip on the order of approximately 29 g/m² is carried out.

5 Application of the coating slip is handled according to one of the techniques already mentioned.

 According to the process of the invention, the binder is formed from a synthetic latex or a combination of synthetic latexes, the binder(s) being incorporated in the
10 coating slip in the proportion of at least 12% by weight.

 According to the process of the invention, the synthetic latex(es) are incorporated in the coating slip in the proportion of at least 15% by weight, the binder being more preferably styrene-butadiene.

15 Within the meaning of the invention, the expression "*manufacturing process for plasterboard*" comprises not only the industrial manufacturing steps for the plasterboard, essentially involving the pouring of the plaster within its frame and the drying of the plasterboard, and also the
20 steps prior to manufacture of the frame corresponding to the manufacture of the facing paper(s).

 Application of the coating slip can therefore take place indifferently during any of these steps.

 The manufacturing process set forth in the invention
25 is finally characterized in that the application of the coating slip is handled before the operation of pouring the plaster core or after the formation of the plasterboard.

 Before pouring the plaster, the paper can be coated with the coating slip on the same production line or on
30 another completely independent production line, indeed in

another manufacturing plant where the paper is manufactured.

The coating of the paper can thus take place at the stage of manufacture of the paper, well before the assembly
5 process of the plasterboard properly speaking, including the pouring of the plaster.

The coating operation can in fact take place on the paper support ensuring the mechanical maintenance of the plasterboard before or essentially during the pouring of
10 the gypsum plaster core and therefore before the industrial drying of the plasterboard. Application of the coating slip can also take place after the pouring operation, once the plasterboard is formed, before the industrial drying or even after the industrial drying, but during the industrial
15 manufacturing process.

Finally, this invention relates to a novel use of plastic pigments as whitening agents in a coating slip for facing paper designed for plasterboard. The use of such pigments was not in fact known in coating slips for the
20 specifically intended application, namely deposition on papers used during the manufacture of plasterboard.

Possibility of industrial application

The invention finds its industrial application in the manufacture of plasterboards comprising at least one facing
25 paper, in the manufacture of coating slips designed to be coated on the facing papers, in the manufacturing processes for plasterboards comprising at least one facing paper and in the use of plastic pigments as whitening agents in a coating slip for facing paper in a plasterboard.

TABLE 1

Environmental conditions of the trial: 23°C/50%RH

Paper type: Paper coated with coating slip as set forth in
5 the invention

		Uncoated paper	Coated paper	Plasterboard	Plasterboard
				Plant 1	Plant 2
Paintability					Good
Wallpaper removal	twice				Good
Sanding resistance	strong			0.2 g	0.2 g
Colour Measurements	L	84.27	89.23	88.17	
	a*	0.60	0.00	-0.15	
	b*	2.35	1.65	4.28	
	YI	5.47	3.33	8.48	
Gloss	85° angle	2.8	6.9	7.1	6.4
Grammage	g/m ²	192.0	221.0		
Density	kg/m ³	711.0	762.0		
Porosity	sec/100ml	67.4	137.8		
Cobb(60)	top	32	14		6
Dennison Pick test	top	17	15		13

TABLE 2
Example 1 of the realisation of a coating slip composition

Half Batch	Product Name	Chemical Composition	Function	Form	DM %	Weight (kg) of dry matter	Total weight DM + liquid fraction	Parts	%
1	Water	Water		Liquid			80		
2	EW902	Calciumcarbonate	Filler	Dispersion	75	126.0	168	65.03	43.94
3	Dispex N-40		Dispersing agent	Liquid	40	0.48	1.2	0.25	0.16
4	Titanium dioxide	Titanium Dioxide	Filler	Powder	99	29.0	29.3	14.97	10.11
5	Etingal S	Phosphorics Esters	Defoamer	Liquid	100	0.3	0.3	0.15	0.10
6	NaOH	Sodiumhydroxide	Fluidifier / PH agent	Powder	100	2.60	2.60	1.34	0.90
7	Ropaque	Plastic Pigment	Filler	Liquid	28.5	38.76	1.36	20.00	13.51
8	Ammonia	Ammonia	Fluidifier	Liquid	20	0.01	0.07	0.01	0.003
9	Amilys 108P	Oxidised Maize Starch	Binder	Powder	85	43.0	50.0	22.19	14.99
10	Latexia305	Styrene-butadiene	Binder	Liquid	50	45	90	23.22	15.69
11	Basocoll OV	Aliphatic Epoxy Resin	Insolubiliser / Crosslinker	Liquid	100	0.80	0.80	0.41	0.27
12	Surfasept 440	Organosulphur/Azotee	Biocide	Liquid	45	0.77	1.70	0.40	0.26
Total						286.7	560.0	148.0	99.933
DM							640.0	44.6	

TABLE 3
Example 2 : Coating Colour Formulation

	Product Name	Chemical Composition	Function	Supplier	Form	Dry Solids %	Dry Amount Addition kg	Addition As is. Kg	Parts	%
1	Water	Water			Liquid			140		
2	Carbital 90-P	Calciumcarbonate	Filler	AGS-BMP	Dispersion	75	252.0	336	65.03	43.939
3	Dispex N-40		Dispersing agent		Liquid	40	0.96	2.4	0.25	0.169
4	Titanium Dioxide	Titanium Dioxide	Filler		Powder	99	58.0	58.6	14.97	10.115
5	Etingal S	Phosphoric Esters	Defoamer	BASF	Liquid	100	0.6	0.6	0.15	0.101
6	NaOH	Sodiumhydroxide	Fluidifier / PH agent	ENI Chem	Powder	100	5.20	5.20	1.34	0.905
7	Ropaque	Plastic Pigment	Filler	Rohm & Haas	Liquid	28.5	77.52	272	20.00	13.513
8	Ammonia	Ammonia	Fluidifier	Langlois Chemie	Liquid	20	0.03	0.14	0.01	0.007
9	Stabilys D029	Oxidised Maize Starch	Binder	Roquette	Powder	86	86.0	100.0	22.19	14.993
10	Latexia 305	Styrene-butadiene	Binder	Latexia	Liquid	50	90	180	23.22	15.689
11	Basocoll OV	Aliphatic Epoxy Resin	Insolubiliser / Crosslinker	BASF	Liquid	100	1.60	1.60	0.41	0.277
12	Surfasept 440	Organosulphur / Azotee	Biocide	Nalco	Liquid	45	1.53	3.40	0.39	0.263
Total							573.5	1099.9	148.0	100.000
Dry Content								1239.0	46.3	

TABLE 4
Example 3 : Coating Colour Formulation

Half Batch	Product Name	Chemical Composition	Function	Supplier	Form	Dry Solids %	Dry Amount Addition kg	Addition As is. Kg	Parts	%
1	Water	Water			Liquid			50		
2	Carbital 90-P	Calciumcarbonate	Filler	AGS-BMP	Dispersion	75	126.0	168	65.03	52.233
3	Dispex N-40		Dispersing agent		Liquid	40	0.48	1.2	0.25	0.201
4	Titanium Dioxide	Titanium Dioxide	Filler		Powder	99	29.0	29.3	14.97	12.024
5	Etingal S	Phosphoric Esters	Defoamer	BASF	Liquid	100	0.3	0.3	0.15	0.120
6	NaOH	Sodiumhydroxide	Fluidifier	ENI Chem	Powder	100	0.15	0.15	0.08	0.064
7	Ropaque	Plastic Pigment	Filler	Rohm & Haas	Liquid	28.5	38.76	136	20.00	16.064
8	Ammonia	Ammonia	Fluidifier	Langlois Chemie	Liquid	20	0.01	0.07	0.01	0.008
9	Latexia 305	Styrene-butadiene	Binder	Latexia	Liquid	50	45	90	23.22	18.651
10	Basocoll OV	Aliphatic Epoxy Resin	Insolubiliser/Crosslinker	BASF	Liquid	100	0.80	0.80	0.41	0.329
11	Surfasept 440	Organosulphur/Azotee	Biocide	Nalco	Liquid	45	0.77	1.70	0.39	0.313
Total							241.3	477.5	124.5	100.000
Dry Content								527.5	45.7	

TABLE 5

		Example 2	Example 2	Example 3	Example 2	Example 3
		Basepaper	Coated Paper	Coated Paper	Plasterboard	Plasterboard
Jointing Compound Adhesion					Good	Very Good
Paintability					Good	Poor
Wallpaper Removal	Two times				Good	Good
Sanding Resistance	Good/Poor				Good	Average
Colour Measurements	L	82.39	87.96	91.73	88.49	90.96
	a*	1.14	0.23	-0.11	-0.10	-0.23
	b*	0.71	0.08	0.08	3.42	1.25
	YI	2.52	0.36	0.07	6.81	2.29
Loss	Angle de 85°	4.80	12.20	29.30	8.40	41.90
Whiteness after painting 1	L				94.66	94.55
UV-Test 12 hours	L				88.25	90.91
	YI	4.29	2.00	0.89	7.63	2.93
Porosity	sec/100 ml	61,6 - 63,9	262,5 - 227	248 - 203		
Cobb (60)	1 minute Top	20-21-20	10-9,5-9	4-4-3	4-6-6	2-3-3
Drop Test	min/sec				2h	> 2h 30
Dennison Pick test	Top	19	15	< 8	13	15

TABLE 6
Example 4: Coating Colour Formulation

	Product Name	Chemical Composition	Function	Supplier	Form	Dry Solids %	Dry Amount Addition kg	Addition As is. Kg	Parts	%
1	Water	Water			Liquid			50		
2	Dispex N-40		Dispersing agent		Liquid	40	0.8	2	0.41	0.340
3	Carbital 90-P	Calciumcarbonate	Filler	Minerys	Liquid	75	39	52	20.14	16.686
4	Durcal 10	Calciumcarbonate	Filler	OMYA	Powder	100	116.0	116	59.89	49.619
5	Titanium Dioxide	Titanium Dioxide	Filler		Powder	99	29.0	29.3	14.97	12.403
6	Etingal S	Phosphoric Esters	Defoamer	BASF	Liquid	100	0.3	0.3	0.15	0.124
7	NaOH	Sodiumhydroxide	Fluidifier	ENI Chem	Powder	100	0.20	0.20	0.10	0.083
8	Ropaque	Plastic Pigment	Filler	Rohm & Haas	Liquid	28.5	9.69	34	5.00	4.142
9	Ammonia	Ammonia	Fluidifier	Langlois Chemie	Liquid	20	0.02	0.1	0.01	0.008
10	Soya Protein	Soya Protein	Crosslinker	Du Pont	Powder	90	7.74	8.6	4.00	3.314
11	Water	Water			Liquid			40.0		
12	Latexia 305	Styrene-butadiene	Binder	Latexia	Liquid	50	29	58	14.97	12.403
13	Basocoll OV	Aliphatic Epoxy Resin	Insolubiliser/Crosslinker	BASF	Liquid	100	1.10	1.10	0.57	0.472
14	Surfasept 440	Organosulphur/Azotee	Biocide	Nalco	Liquid	45	0.77	1.70	0.39	0.323
15	Silicone RE 29	Polysiloxane	Hydrophobiser	Witco	Liquid	43	0.19	0.45	0.10	0.083
Total							233.8	393.8	120.7	100.000
Dry Content								423.8	55.2	

TABLE 7
Example 4

		Basepaper	Coated paper	Boards
Paintability				Good
Sanding Resistance	Good/Poor		Good	Good
Colour Measurements	L	84.86	88.35	88.03
	a*	0.47	-0.10	-0.36
	b*	0.13	0.40	4.12
	YI	0.67	0.73	8.00
Gloss	Angle de 85°	4.3	1.8	2.6
UV-Test 12 hours	Colours L		88.22	87.88
	a*		-0.25	-0.57
	b*		1.24	4.97
	YI		2.33	9.52
Basis Weight	gsm	199	232	
Density	kg/m3	743	787.0	
Porosity	sec/100 ml	178	>1999	
Cobb (60)	1 minute Top	26/ 25,6/ 25,8	3,5/ 3,5/ 5,2	11,5/ 13,4/ 11,9
Dennison Pick test	Top	19	13	13

CLAIMS

1. Plasterboard comprising at least one facing paper forming the exterior of the plasterboard and a coating slip deposited on said facing paper, characterised in that the coating slip contains plastic pigments as whitening agents.

5

2. Plasterboard as claimed in claim 1 characterised in that the coating slip contains at least 5% by weight of plastic pigments.

10 3. Plasterboard as claimed in claim 2 characterised in that the coating slip contains between 5% and 40% by weight of plastic pigments, and more preferably between 15 and 25% by weight of plastic pigments.

15 4. Plasterboard as claimed in claim 3 characterised in that the coating slip contains approximately 13% by weight of plastic pigments.

20 5. Plasterboard as claimed in one of claims 1 to 4 characterised in that the coating slip is applied in the proportion of approximately 10 to 45 g/m², and more preferably in the proportion of approximately 20 to 30 g/m².

25 6. Plasterboard as claimed in one of the preceding claims characterised in that the plastic pigments are chosen from among plastic pigments with filled particles or with hollow particles.

7. Plasterboard as claimed in one of the preceding claims characterised in that the coating slip contains, in addition to the plastic pigments:

- 5 -at least 25% fillers, more preferably calcium carbonate, and more preferably at approximately 44%;
- a sufficient quantity of water;
- a dispersing agent;
- a defoamer;
- 10 -at least 8% of binder;
- an insolubilising agent, more preferably an aliphatic epoxy resin;
- a biocide, more preferably an organo-sulfurated/nitrogenous agent (organosulphur/azotee).

15

8. Plasterboard as claimed in claim 7 characterised in that the binder is formed from a synthetic latex or from a combination of synthetic latexes, the binder(s) being incorporated in the coating slip in the proportion of at least 10% and more preferably of at least 12% by weight.

20

9. Plasterboard as claimed in claim 8 characterised in that the synthetic latex(es) are incorporated in the proportion of at least 15% by weight in the coating slip.

25

10. Plasterboard as claimed in claim 8 or 9 characterised in that the binder is composed of styrene-butadiene.

11. Plasterboard as claimed in one of claims 7 to 10 characterised in that the coating slip additionally

30

contains titanium dioxide in the proportion of approximately 10% by weight.

12. Plasterboard as claimed in one of claims 7 to 11
5 characterised in that the coating slip additionally contains sodium hydroxide.

13. Plasterboard as claimed in one of claims 7 to 12
10 characterised in that the coating slip additionally contains ammonium.

14. Plasterboard as claimed in one of claims 7 to 13
characterised in that the coating slip additionally contains oxidized maize starch, more preferably in the
15 proportion of approximately 15% by weight.

15. Coating slip designed to be coated on the upper layer of a facing paper of a plasterboard characterised in that it contains plastic pigments as whitening agents.

20 16. Coating slip as claimed in claim 15 characterised in that the coating slip contains at least 5% by weight of plastic pigments.

25 17. Coating slip as claimed in claim 16 characterised in that the coating slip contains between 5% and 40% by weight of plastic pigments, and more preferably between 15 and 25% by weight of plastic pigments.

18. Coating slip as claimed in claim 17 characterised in that the coating slip contains approximately 13% by weight of plastic pigments.

5 19. Coating slip as claimed in one of claims 15 to 18 characterised in that the plastic pigments are chosen from among plastic pigments with filled particles or with hollow particles.

10 20. Coating slip as claimed in one of claims 15 to 19 characterised in that the coating slip contains, in addition to the plastic pigments:

-at least 25% fillers, more preferably calcium carbonate, and more preferably approximately 44%;

15 -a sufficient quantity of water;

-a dispersing agent;

-a defoamer;

-at least 8% binder;

-an insolubilising agent, more preferably an aliphatic epoxy resin;

20 -a biocide, more preferably an organo-sulfurated/nitrogenous agent (organosulphur/azotee).

21. Coating slip as claimed in claim 20 characterised in
25 that the binder is formed from a synthetic latex or a combination of synthetic latexes, the binder(s) being incorporated in the coating slip in the proportion of at least 10% by weight and more preferably at least 12%.

22. Coating slip as claimed in claim 21 characterised in that synthetic latex(es) are incorporated in the proportion of at least 15% by weight in the coating slip.

5 23. Coating slip as claimed in claim 21 or 22 characterised in that the binder is composed of styrene-butadiene.

24. Coating slip as claimed in one of claims 20 to 23 characterised in that the coating slip additionally
10 contains titanium dioxide in the proportion of approximately 10% by weight.

25. Coating slip as claimed in one of claims 20 to 24 characterised in that the coating slip additionally
15 contains sodium hydroxide.

26. Coating slip as claimed in one of claims 20 to 25 characterised in that the coating slip additionally contains ammonium.

20

27. Coating slip as claimed in one of claims 20 to 26 characterised in that the coating slip additionally contains oxidised maize starch, more preferably in the proportion of approximately 15% by weight.

25

28. Manufacturing process for plasterboard comprising at least one facing paper forming the exterior of the plasterboard on which a coating slip is deposited on the upper surface of the facing paper characterised in that a

coating slip is deposited containing plastic pigments as whitening agents.

29. Manufacturing process as claimed in claim 28
5 characterised in that the coating slip contains at least 5% by weight of plastic pigments.

30. Manufacturing process as claimed in claim 29
10 characterised in that the coating slip contains between 5% and 40% by weight of plastic pigments, and more preferably between 15 and 25% by weight of plastic pigments.

31. Manufacturing process as claimed in one of claims 28 to
15 30 characterised in that the application of the coating slip is done in the proportion of 10 to 45 g/m², more preferably in the proportion of approximately 20 to 30 g/m².

32. Manufacturing process as claimed in one of claims 28 to
20 31 characterised in that the application of the coating slip is taken care of before the operation of the pouring of the plaster core or after the formation of the plasterboard.

25 33. Process as claimed in claim 32 characterised in that the coating of the paper takes place at the stage of manufacture of the paper.

30 34. Use of plastic pigments as whitening agents in a coating slip for facing paper designed for plasterboard.