

**GLASS SUBSTRATE FOR INFORMATION RECORDING MEDIUM AND
INFORMATION RECORDING MEDIUM**

ABSTRACT

A glass substrate for information recording medium, said glass substrate being composed of an alminosilicate glass containing 60-75 % by mass of SiO_2 , 5-18 % by mass of Al_2O_3 , 3-10 % by mass of Li_2O , 3-15 % by mass of Na_2O and 0.5-8 % by mass of ZrO_2 relative to the entire glass components. The glass substrate for information recording medium contains neither As (arsenic) nor Sb (antimony), while containing at least one substance selected from the group consisting of SO_3 (sulfurous acid), F (fluorine), Cl (chlorine), Br (bromine) and I (iodine), as a refining agent. The molar ratio of the total amount of the refining agent to the amount of Al_2O_3 is within the range of 0.02-0.20.