Fabrication method for thin layers containing microcomponents

The invention concerns producing microcomponents from a thin layer on a substrate and processing this thin layer/substrate combination.

The expression "thin layer" conventionally means a layer whose thickness is usually from a few tens of angstrom units to several micrometers. The substrate to which the invention relates can be an initial or intermediate substrate and can be "demountable", i.e. intended to be separated from this thin layer.

There is an increasing requirement to be able to produce microcomponents to be integrated onto supports other than those used to fabricate them.

Examples that may be cited are microcomponents on plastics material or flexible substrates. Here the term "microcomponent" means any wholly or partially processed electronic or optoelectronic device or any sensor (for example any chemical, mechanical, thermal, biological or biochemical sensor).

A layer transfer method can be used to integrate such microcomponents onto flexible supports.

There are many other examples of applications in which layer transfer techniques may be suitable for integrating microcomponents or layers onto a support that is unsuitable for their fabrication a priori. In the same line of thinking, these layer transfer techniques are also very useful when it is required to isolate a thin layer, with or without microcomponents, from its original substrate, for example by separating or eliminating the latter. Also in the same line of thinking, turning over a thin layer combined with transferring it onto another support provides engineers with a valuable degree of freedom to design structures that would otherwise be impossible. Thin films can be separated and turned over

for example to produce buried structures such as buried capacitors for dynamic random access memories (DRAM) in which, unusually, the capacitors are first formed and then transferred onto another silicon substrate before fabricating the remainder of the circuits on this new substrate. Another example concerns the processing of dual gate transistor structures. The first gate of a CMOS transistor is produced on a substrate using a conventional technology and then transferred and turned over onto a second substrate to produce the second gate and finish the transistor; the first gate is therefore buried in the structure (see for example K. Suzuki, T. Tanaka, Y. Tosaka, H. Horie and T. Sugii, "High-Speed and Low-Power n+-p+ Double-Gate SOI CMOS", IEICE Trans. Electron., vol. E78-C, 1995, pages 360 to 367).

The requirement to isolate a thin layer from its original substrate is encountered in the field of light-emitting diodes (LED), for example, as reported in the following documents, for example: W.S. Wong et al., Journal of Electronic Materials, page 1409, vol. 28, No. 12, 1999, and I. Pollentier et al., page 1056, SPIE vol. 1361, "Physical Concepts of Materials for Novel Optoelectronic Device Applications I", 1990. Here one of the aims is improved control of extraction of the light emitted. Another aim relates to the fact that in this particular example the sapphire substrate used for the epitaxial stack is bulky a posteriori, in particular because of its electrically insulative nature, and this prevents making electrical contact to its rear face. It therefore seems now to be desirable to be able to dispense with this sapphire substrate, the use of which was advantageous in the phase of growing the material.

An identical situation is encountered in the field of applications associated with telecommunications and microwaves, for example. In this case, it is preferable

for the microcomponents to be finally integrated onto a support having a high resistivity, typically at least several kohm.cm. However, a highly resistive substrate is not necessarily available at the same cost and with the same quality as the standard substrates usually employed. In the case of silicon, for example, note the availability of 200 and 300 mm diameter silicon wafers of standard resistivity, whereas for resistivities in excess of 1 kohm·cm, what is available with a 200 mm diameter is highly unsuitable and there is nothing available at all with a 300 mm diameter. One solution is to process the microcomponents on standard substrates and then, during the final steps, to transfer a thin layer containing the microcomponents onto an insulative substrate such as glass, quartz or sapphire.

From a technical point of view, the major benefit of these transfer operations is that they decorrelate the properties of the layer in which the microcomponents are formed from those of the layer providing the final support, as a result of which these operations are beneficial in many other cases also.

The cases may further be cited in which the substrate which is advantageous for processing the microcomponents is excessively costly. In the case of silicon carbide, for example, which offers the best performance (higher temperatures of use, significantly improved maximum powers and frequencies of use, and so on), but whose cost is very high compared to silicon, it would be beneficial to transfer a thin layer from the high-cost substrate (here silicon carbide) onto the low-cost substrate (here silicon) and recover the residue of the high-cost substrate for reuse, possibly after recycling. The transfer operation can take place before, during or after the processing of the microcomponents.

These techniques can also be beneficial in all

fields in which obtaining a thin substrate is important for the final application. Power applications may be cited in particular, for reasons associated with the evacuation of heat (which improves as the thickness of the substrate is reduced), or because the electrical current must sometimes pass through the thickness of the substrates, incurring losses that, to a first approximation, are proportional to the thickness through which this current passes. Microchip card applications may also be cited, in which thin substrates are required for reasons of flexibility. Similarly, applications intended for processing 3D circuits and stacked structures may also be cited.

For all these applications (which are cited by way of example), circuit processing is carried out on thick or standard thickness substrates, with the advantages, firstly, of good mechanical resistance to the various technology steps and, secondly, of conforming to the standards relating to their processing on some kinds of production equipment. It is therefore necessary to carry out a thinning operation prior to the final application.

Various techniques can be used to transfer layers from one support to another support. The techniques described in 1985 by T. Hamaguchi et al., Proc. IEDM 1985, p. 688 may be cited, for example. Although these techniques are of great benefit because they transfer a layer from one substrate to another substrate, they necessarily consume the basic substrate (which is destroyed during the course of the process), and cannot transfer a thin film homogeneously unless a stop layer is present, i.e. a layer forming an inhomogeneity in the material of the substrate.

Of the prior art transfer methods that recover the thin film after transfer, it is also possible to use methods of transferring thin layers of materials

containing (or not) all or part of a microcomponent. Some of these methods are based on creating a weak buried layer in a material by introducing one or more gaseous species. In this connection, see the documents US-A-5374564 (or EP-A-533551), US-A-6020252 (or EP-A-807970), FR-A-2767416 (or EP-A-1010198), FR-A-2748850 (or EP-A-902843), or FR-A-2773261 (or EP-A-963598), which describe these methods. They are generally used with the objective of detaching the whole of a film from an original substrate in order to transfer it onto a support. The thin film obtained can then contain a portion of the original substrate. These films can be used as active layers for processing electronic or optical microcomponents.

In particular, these methods enable the substrate to be reused after separation, as only very little of these substrates is consumed during each cycle. The thickness removed is frequently only a few microns, while the substrates are typically several hundred microns thick. It is thus possible to obtain, in particular in the method disclosed in the document US-A-6020252 (or EP-A-807970), substrates that are similar to substrates that are "demountable" (i.e. detachable substrates) with the aid of a mechanical stress. This particular method is based on implantation to form a buried weak area in which the cut is made during the final transfer.

Other methods, based on the lift-off principle, also separate a thin layer from the remainder of its original support, again without necessarily consuming the latter. These methods generally employ chemical etching to selectively etch an intermediate buried layer, possibly associated with mechanical forces. This type of method is widely used to transfer III-V elements onto different types of support (cf. C. Camperi et al., IEEE Transaction and Photonics Technology, vol. 3 No. 12,

1991, page 1123). As explained in a paper by P. Demeester et al., Semicond. Sci. Technol. 8, 1993, pages 1124 to 1135, the transfer, which generally takes place after an epitaxial step, can take place before or after processing the microcomponents (it is known as preprocessing or postprocessing, respectively).

Of the methods using a (pre-existing) buried layer that is mechanically weaker than the remainder of the substrate to obtain localized separation at this buried layer, the ELTRAN® process may be cited (Japanese Patent Publication Number 07302889). In this case, a stack based on monocrystalline silicon is locally weakened by forming an area of porous silicon. Another similar case exploits the presence of a buried oxide in the case of a silicon on insulator (SOI) structure, however conventional the latter may be (i.e. even if processed without seeking to achieve any particular demountable effect). If this structure is stuck sufficiently strongly to another substrate and a high stress is applied to the structure, localized fracture can be obtained, preferentially in the oxide, leading to cutting at the scale of the entire substrate. An example of this is described in PHILIPS Journal of Research, Vol. 49 No. 1/2, 1995, pages 53 to 55. Unfortunately, this fracture is difficult to control and necessitates high mechanical stresses, which is not without risk of breaking the substrates or damaging the microcomponents.

The advantage of such weak buried layer methods is the ability to process layers based on crystalline materials (Si, SiC, InP, AsGa, $LiNbO_3$, $LiTaO_3$, etc.) in a range of thicknesses from a few tens of angstrom units (Å) to several micrometers (μm), with very good homogeneity. Greater thicknesses are also accessible.

The techniques of transferring layers (with or without microcomponents) based on producing demountable

substrates by forming an intermediate layer or weakened interface (whether the weakened interface is obtained by implanting species, forming a porous area, or any other means) run up against problems relating to unintentional delamination if processing prior to the intentional separation is too aggressive.

An object of the invention is to combine reliably the imperative easy separation, at the required time, and the imperative ability, where necessary, to withstand the application of mechanical or heat treatments necessary for processing all or some electronic, optical or acoustical microcomponents or sensors, or to withstand epitaxial steps, without causing premature separation or delamination.

A more general object of the invention is to provide a combination of a thin layer on a substrate, this layer being connected to this substrate by an intermediate layer or an interface having an easily controlled mechanical strength.

According to the document FR 2748851, a demountable substrate of the above kind can be produced by introducing a gaseous species (for example hydrogen). The implanted dose must be chosen so that thermal annealing does not induce any deformation or exfoliation of the surface. Depending on the mechanical forces that can be applied and/or the tool used to induce the separation between the surface layer and the remainder of the substrate, the weakening achieved in the implanted area may prove insufficient. It may then be beneficial to weaken further the implanted area.

The method described in the document FR 2773261 also produces a demountable substrate, thanks to the presence of a buried layer of inclusions used as a trapping layer in the substrate. After various treatments, for example processing of electronic

microcomponents, this localizes, preferably in this trapping layer, sufficient quantities of gaseous species that can contribute to the final separation of the thin surface layer delimited by the area of inclusions and the surface of the substrate. This separation step can include heat treatment and/or the application of mechanical stress to the structure.

The use of this technique can encounter limitations, in particular with regard to the reintroduction of gaseous species into the surface layer after the fabrication of some or all of the microcomponents, which may be undesirable for processing some types of microcomponents.

In the method disclosed in French application No. 0006909, the introduction of a controlled dose of implanted species firstly weakens the buried area (or even overweakens it) and secondly evacuates the gas afterwards, in order to limit a pressure effect in the event of a rise in temperature. There is therefore no deformation or exfoliation of the surface during high-temperature technology steps. This technique necessitates rigorous control of the implantation conditions (dose, temperature, etc.). It may therefore prove beneficial to be able to relax the constraints relating to a narrow technology window.

The document FR 2758907 proposes local introduction of gaseous species after processing the microcomponents in the surface layer of the substrate. The introduction of these species leads to the formation of a discontinuous buried layer of microcavities that can contribute to the fracture after fastening the treated substrate to a support substrate. Thus the substrate is weakened after processing the various microcomponent fabrication technology steps. The accessible size of the areas to be masked (which correspond to the active areas

of the microcomponents) may prove to be a limitation, depending on the intended applications. For example, this technique is difficult to use for microcomponent sizes from a few tens of microns to a few hundred microns. Moreover, depending on the microcomponent production technology used, the thickness of the active layer, i.e. the layer incorporating the microcomponents, can be as much as several microns. The introduction of gaseous species at a great depth (by dedicated implanters or by accelerators), with adequate protection of the areas by masking, can then prove difficult.

To eliminate these various drawbacks, the invention proposes a method for fabricating, by means of a substrate, thin layers containing microcomponents, said method being noteworthy in that it includes in particular the following steps for each layer:

a) localized implantation of at least one gaseous species in said substrate in line with a plurality of implantation areas defined on the surface of the substrate, degrading of this surface of the substrate during the step b) being prevented by an appropriate choice of the implantation depth and the geometry of said implantation areas,

b) processing microcomponents in the surface layer of the substrate delimited by the implantation depth, and

c) separating the substrate into two parts, one part containing said surface layer containing said microcomponents and the other part containing the remainder of the substrate.

Here the term "degradation" means any surface deformation (for example in the form of blisters) or any exfoliation of the surface layer that could compromise the correct execution of the step b).

Thus, according to the invention, there are areas protected from implantation and areas subjected to the

implantation of said gaseous species, the shapes, dimensions and distribution of these implantation areas being chosen to prevent any deformation of the surface of the substrate exceeding an amplitude of, say, a few tens of angstrom units, during the step of processing the microcomponents. Account is therefore taken, in particular, of the stiffness of the surface layer (which may consist of a stack of several layers of materials), the implantation conditions, and subsequent treatments up to separation of said thin layer.

The method according to the invention processes a demountable substrate including buried areas weakened by the presence of microcavities and/or microcracks (thus locally separating the surface layer from the remainder of the substrate), and areas that have not been weakened, or that have been only slightly weakened, so that the surface layer remains fastened to the substrate. Localized areas are obtained in this way in which the surface layer separates easily from the substrate because of the presence in these areas of these microcavities and/or microcracks.

An important advantage of the invention is that the lateral confinement of these buried weak areas prevents significant deformation of the surface layer in the form of blisters or exfoliation. The technology window for the implanted doses is widened compared to the prior art methods, because localized implantation in confined areas limits the lateral extension of microcracks.

Moreover, the surface of the substrate obtained is compatible with standard technology steps, such as lithography operations or the production of microcomponents. In particular, the weakened substrate obtained is compatible with high-temperature treatments, for example thermal oxidation or gas-phase or liquid-phase epitaxy.

After these varied technological steps have been processed, the presence of areas locally separating the surface layer from the substrate produces a deep fracture between this surface layer and the substrate.

Said implantation areas can conveniently be openings in a mask placed on the surface of the substrate.

Said gaseous species can comprise hydrogen ions, for example, or ions of at least one rare gas, or a mixture of such ions.

It will be noted that the fabrication method according to the invention can comprise, before the step a), a supplementary step of introducing at least one gaseous species, this at least one supplementary introduction being effected with no mask on the surface of the substrate. Here, and hereinafter, the term "introduction" refers to conventional techniques such as ion implantation, for example, thermally activated diffusion or plasma diffusion. A substrate that has been treated by supplementary introduction before implantation in the step a) is regarded as a substrate to which the method of the invention as succinctly described hereinabove is applied.

In accordance with preferred features, such supplementary introduction with no mask on the substrate can be processed between the steps a) and b).

Thanks to these provisions, a buried area is obtained delimiting a surface layer that is more or less weakened, since some areas have undergone two implantations, for example, whereas other areas have undergone only one. The doses of ions introduced during these implantations can be such that their sum corresponds to an average dose which, in the case of implantation over the whole of the surface of the substrate, would cause the appearance of blisters after

heat treatment. It must be remembered that the geometry of the areas that have undergone double implantation prevents the appearance of such blisters and therefore degradation of the surface of the substrate. This embodiment can in particular be favorable during the step of separating the surface layer from the remainder of the substrate (step c)), and obtain such separation by less stressful treatments.

According to other preferred features, the fabrication method according to the invention comprises, before or during the step b), a step during which the implanted area is overweakened, for example by appropriate heat treatment or by depositing particular thin layers inducing mechanical stresses. Here the term "overweakened" means a state of greater weakness of the implanted area, to reduce the stresses to be used at the time of final separation.

Thanks to this provision, the structural defects generated by implanting gaseous species increase in the implanted areas, which increases the weakness of these buried local areas. A high weakening threshold can be reached in these areas by judiciously choosing the dimensions of the implantation patterns, without this causing significant surface deformation or exfoliation.

It is to be noted that the optional steps of overweakening the implanted areas can be processed entirely or partly during microcomponent fabrication steps provided that the temperature and duration sequences are carefully chosen.

According to other preferred features, the fabrication method according to the invention comprises, between the step b) and the step c), a supplementary step of introducing at least one gaseous species. This supplementary introduction of at least one gaseous species can be effected with the aid of a mask defining

implantation areas of this at least one gaseous species, for example.

Thanks to this provision, the buried area is weakened, with the aim of facilitating subsequent detachment of the surface layer from the substrate.

This detachment (step c)) can be effected by means of heat treatment and/or by applying mechanical stresses.

Another aspect of the invention concerns a thin layer containing microcomponents, said thin layer being noteworthy in that it is fabricated by any of the methods succinctly described hereinabove. If necessary, this layer is transferred to a support, which may be flexible or rigid.

Other aspects and advantages of the invention will become apparent on reading the following detailed description of particular embodiments provided by way of non-limiting example. This description refers to the accompanying drawings, in which:

- figure 1 is a diagrammatic view of a substrate provided with masking means,
- figure 2 shows the first step of a method of fabricating layers according to the invention,
- figure 3 is a diagrammatic view of the substrate after removing the mask according to the invention,
- figure 4 is a diagrammatic view of the substrate after a second step of a method of fabricating layers according to the invention,
- figure 5 shows the individual transfer of a microcomponent to a support substrate,
- figure 6 shows the transfer to a "handle" support of a layer according to the invention containing microcomponents, and
- figure 7 shows the individual transfer of a microcomponent to a final support from a "handle" support.

The principal steps of fabricating a layer conforming to one embodiment of the invention are described.

Figure 1 shows the initial preparation of a substrate 1. This preparation consists of defining the areas to be implanted by processing a mask 2 delimiting, on the surface of a substrate 1, non-masked areas (that are subsequently implanted) and masked areas (that are not implanted).

This mask can be produced by applying a layer of resin to the substrate 1 lithographically or by applying any other surface layer (for example a layer of oxide) to the substrate 1 by successive lithography and etching steps. The masking can equally well be effected by placing a grid on the surface of the substrate 1 during the implantation step. This masking grid can be at the level of a diaphragm disposed between the beam of ions to be implanted and the target substrate. The above masking means have been described by way of example, but other masking means may be suitable.

A judicious choice of the shapes and the dimensions of the masked areas is of primary importance for the correct processing of subsequent steps. The implantation step creates a discontinuous buried area including specific defects (platelets, microcavities and/or microbubbles) due to the introduction of the ions. The step of defining the areas to be implanted allows for the properties of the substrate, the properties of the different composition or material layer or layers on the surface of the substrate 1, and the implantation conditions.

The stiffness properties and the thickness of the surface layer to be produced condition the dimensions and the spacing of the areas to be implanted. The latter are established so that the growth of microcavities and

microcracks in the implanted areas, such as could occur during heat treatment, for example, lead:

- neither to a vertical relaxation of the surface layer, by formation of blisters, with an amplitude exceeding a few tens of angstrom units,

- nor to total or partial interaction between different locally implanted areas of such a kind as to cause lifting or exfoliation of all or part of the surface layer.

In this way it is possible to maintain the surface of the surface layer free of any significant degradation, with locally weakened buried areas.

Depending on the type of masking effected (oxide mask on the substrate, grid placed on the surface of the substrate during implantation, or grid placed on the path of the beam of ions during implantation), the effective lateral dimensions (in the plane of the surface of the substrate) of the buried areas that have been subjected to ion implantation depend on the Gaussian profiles of implantation. This means that a sharp edge of the mask on the surface is not rigorously reproduced in the implanted buried layer. Dispersion of the ions as they penetrate into the material induces a significant widening of the implanted area. It is therefore necessary to take account of this phenomenon in order to define the dimensions of the masked and non-masked areas correctly.

On the other hand, the dimensions of the implanted areas must be sufficient for easy separation of the surface layer at the end of the process.

Trials carried out by the inventors have shown that the total surface area of the implantation areas generally represents between approximately 1/3 and approximately 5/6 of the surface area of the substrate 1. Moreover, a linear dimension of the implantation areas is preferably from approximately 0.1 times to approximately

10 times the target thickness for the surface layer in the case of a silicon substrate. In the case of a more rigid material, this dimension can be significantly greater, for example of the order of 50 times.

For example, an implantation mask can be used incorporating 10 μm × 10 μm for example square openings separated by for example 5 μm masked areas. Another example of an implantation mask has non-masked areas in the form of lines whose dimensions are for example 5 μm × 100 μm, the lines being spaced from each other by for example 5 μm.

The first step of this embodiment, shown in **figure 2**, therefore consists of introducing at least one gaseous species such as hydrogen and/or a rare gas in ionic form into the substrate 1.

The substrate 1 consequently has a set of buried areas 3 that have been subjected to implantation of gaseous species, these areas 3 being separated from each other by areas 4 in which the original masking has prevented the introduction of gaseous species. Thus the substrate 1 comprises a discontinuous buried layer made up of defects 3 such as platelets, microcavities, microbubbles or microcracks. The lateral confinement of the microcracks 3 prevents their expansion or relaxation degrading the surface of the substrate 1.

The implantation energy of the gaseous species controls the thickness of the surface layer 5 delimited by the implanted layer and the surface of the substrate 1.

One application example is implanting hydrogen ions at an energy from 150 to 250 keV and at a dose from approximately 10^{16} to approximately 10^{17} H^+/cm^2.

The mask is then removed, leaving the surface of the substrate 1 entirely bare, as shown in **figure 3.**

In a variant of the method according to the

invention, this is followed by a second implantation of ions of the same species or of different species from the first implantation: the openings in the original mask are therefore subjected to a second implantation, while the initially masked areas are submitted to a first implantation. This second implantation increases the density and/or the size of the defects in the previously implanted areas and induces the formation of buried defects in the initially masked areas. The dose introduced during the second implantation must be relatively low, i.e. it must not form blisters or cause exfoliation after annealing at a moderate temperature (from approximately 450°C to approximately 600°C). It is preferably carried out at an energy of 180 keV and at a dose of 4×10^{16} H^+/cm^2, for example.

There is then, at depth, a buried area comprising a greater or lesser quantity of gaseous species and therefore a greater or lesser density of microcavity defects. The areas that were submitted only to the second implantation are therefore less weakened than the doubly implanted areas, but establish the continuity of the buried weak area.

The development of the weak areas 3 created by one or more implantations of gaseous species, as described hereinabove, depends on the implantation conditions and on any treatment effected after implantation. These optional treatments aim to overweaken the local implanted areas 3 and to induce the growth of microcavities in these areas. To this end, heat treatment at a temperature of the order of 450 to 475°C may be applied for a few minutes, for example.

During a second step of this embodiment of the invention, shown in **figure 4**, the substrate weakened in this way can then be subjected to heat treatment, deposition or epitaxy steps, or other treatment for

producing electronic and/or optical microcomponents and/or sensors 6, without risk of degrading the surface.

Thus, if necessary, the substrate can be subjected to epitaxy operations. A 5 μm epitaxial layer can be used to produce CMOS-type microcomponents using conventional techniques, for example. A 50 μm epitaxial layer can be used to produce photovoltaic cells, for example.

The third and final step of this embodiment of the invention consists of separating the surface layer 5 containing the microcomponents 6 from the remainder of the substrate 1. Depending on the conditions under which the first two steps are carried out, this separation can be carried out either by means of heat treatment, by judicious application of mechanical stresses to the structure, or by a combination of heat treatment and mechanical stresses.

In a variant of the invention, before proceeding to this separation, supplementary local introduction of at least one gaseous species in areas identical to or different from the implantation areas used for the first step of this embodiment can be effected with the aim of facilitating subsequent separation of the surface layer from the substrate.

This addition of gaseous species can be effected by implantation in the areas already weakened or constitute a continuous weakened buried area by implantation in initially masked areas underneath which the substrate is not weakened much or at all. The implantation energy is then chosen so that the implanted species reach the depth of the areas weakened by the initial implantation steps, allowing for changes of thickness occurring during the production of the microcomponents on the layer 5.

A moderate dose of the order of 6×10^{16} H^+ ions/cm^2 is preferably implanted whereby separation is obtained for a heat treatment at a temperature from 400 to 500°C.

Let it be noted that the conditions for using this variant depend on:

- the size of the microcomponents (it may be necessary to prevent the implanted ions crossing active areas of the microcomponents), and/or

- the sensitivity of the microcomponents to ion implantation, regardless of their size, if the microcomponents are not degraded by having ions pass through them or at least some parts of the microcomponents are not sensitive to the ions.

In particular, to process this supplementary implantation, appropriate masking can be used, different, of course, from the masking used in the first step of this embodiment.

The step of separating the surface layer 5 containing the microcomponents 6 from the remainder of the substrate 1 can include heat treatment (furnace and/or local heating and/or laser beam, etc.) and/or the application of mechanical stresses such as a sprayed jet of fluid (gas, liquid) and/or the insertion of a blade in the weakened area and/or applying traction, shear or bending stresses to the substrate 1. For example, heat treatment at approximately 450°C can be applied for 30 minutes to separate the surface layer 5 from the initial substrate.

This separation can yield a self-supporting layer or the surface layer 5 can be transferred onto a support substrate 7, for example using the molecular adhesion technique or adhesive substances. This support 7 stiffens the layer 5 transferred from the weakened substrate, in particular for transportation and/or finishing steps.

Moreover, as shown in **figure 5**, the demountable substrate can be prepared beforehand so that each microcomponent 6 can be taken off individually. This technique is disclosed in the application FR 2781925.

A variant of the transfer step to the final support can comprise an intermediate step of transferring the surface layer 5 from the weakened substrate onto a "handle" support 8, as shown in **figure 6**. The microcomponents 6 can then be selectively or non-selectively transferred to a final support 9, as shown in **figure 7**.

The final support 7 or 9 can be of silicon, plastics material, or glass, for example, and can be flexible or rigid.

After separating and transferring the surface layer 5, the remainder of the weakened substrate can be recycled either as an initial substrate or, possibly, as a support.

CLAIMS

1. A method for fabricating, by means of a substrate (1), thin layers (5) containing microcomponents (6), characterized in that it includes in particular the following steps for each layer (5):

a) localized implantation of at least one gaseous species in said substrate (1) in line with a plurality of implantation areas defined on the surface of the substrate (1), degrading of this surface of the substrate (1) during the step b) being prevented by an appropriate choice of the implantation depth and the geometry of said implantation areas,

b) processing microcomponents (6) in the surface layer (5) of the substrate (1) delimited by the implantation depth, and

c) separating the substrate (1) into two parts, one part containing said surface layer (5) containing said microcomponents (6) and the other part containing the remainder of the substrate (1).

2. A fabrication method according to claim 1, characterized in that said implantation areas are defined by a mask (2) placed on the surface of the substrate (1).

3. A fabrication method according to claim 1 or claim 2, characterized in that said gaseous species comprises hydrogen ions, or ions of at least one rare gas, or a mixture of such ions.

4. A fabrication method according to any preceding claim, characterized in that the total surface area of the implantation areas represents from approximately 1/3 to approximately 5/6 of the surface area of the substrate (1).

5. A fabrication method according to any preceding claim, characterized in that a linear dimension of the implantation areas is from approximately 0.1 times to

approximately 50 times the thickness of said surface layer (5).

6. A fabrication method according to any preceding claim, characterized in that it comprises, before the step a) and/or between the step a) and the step b), at least one supplementary step of introducing at least one gaseous species, this at least one supplementary introduction being effected with no mask on the surface of the substrate (1).

7. A fabrication method according to any preceding claim, characterized in that, before or during the step b), the implanted area is overweakened.

8. A fabrication method according to any preceding claim, characterized in that it comprises, between the step b) and the step c), a supplementary step of introducing at least one gaseous species.

9. A fabrication method according to claim 8, characterized in that said supplementary introduction of at least one gaseous species is effected with the aid of a mask defining implantation areas of this at least one gaseous species.

10. A fabrication method according to any preceding claim, characterized in that said step c) includes heat treatment and/or applying mechanical stresses.

11. A fabrication method according to claim 10, characterized in that applying said mechanical stresses entails the use of a fluid jet and/or the insertion of a blade in the implanted area and/or applying traction, shear or bending stresses to the substrate (1).

12. A fabrication method according to claim 10, characterized in that said heat treatment comprises heating in a furnace and/or local heating and/or heating with a laser.

13. A fabrication method according to any of

claims 1 to 12, characterized in that a surface (7) is applied to the substrate (1) before or during the step c) to serve as a support for said surface layer (5) after it is separated from the substrate (1).

14. A fabrication method according to any of claims 1 to 12, characterized in that a "handle" support (8) is applied to the substrate (1) before or during the step c), the microcomponents (6) then being selectively or non-selectively transferred to a final support (9).

15. A thin layer (5) containing microcomponents (6), characterized in that it is fabricated by means of a method according to any of claims 1 to 14.

16. A thin layer (5) according to claim 15, characterized in that it is transferred onto a flexible or rigid support (7, 8, 9).