

Virus scaffold for self-assembled, flexible and light lithium battery

This application claims priority to U.S. Provisional Application No. 60/620,522, filed October 19, 2004, the entire contents of which are incorporated
5 herein by reference.

Field of the Invention

This invention pertains to production of electrodes for rechargeable lithium-ion batteries using a biological template.

Background of the Invention

10 The increasing demand for portable devices is driving the development of small, rechargeable batteries with high energy density. Lithium-ion batteries are the system of choice owing to their higher specific energy (100-150 Wh/kg), higher specific power (150-250 W/kg) and longer lifespan (> 1000 cycles) in comparison to other types of batteries. These advantages result from the battery's high voltage (2.4 -
15 4.6 V) and the high theoretical capacity density of the lithium carrier ion (3862 Ah/kg). The performance of a lithium-ion battery is heavily influenced by the intercalation materials used in its anode and cathode.(1) The intrinsic properties of the intercalation material determine the cell's voltage, capacity, and stability, which in turn determines the individual cycle-life and total lifetime of the battery.

20 Carbonaceous compounds (e.g., graphite and coke) have been widely used as anode materials in lithium-ion batteries because their electrochemical potentials are similar to that of lithium metal and because, unlike lithium metal anodes, they do not form dendrites. Most of the known lithium/transition metal oxides [LiMO_2 (M: Co, Fe, Mn, Ni ...)] and nanotubes, for example carbon and TiO_2 nanotubes, (2,3) have
25 been studied for use as cathode materials.

Layered lithium nickel dioxide (LiNiO_2) was one of the first lithium-metal oxides considered (4) as a cathode material because of its favorable specific capacity. However, it was found that the layered crystalline structure of delithiated Li_xNiO_2 would collapse after the exothermic oxidation of the organic electrolyte. The collapse

of the layered structure results in accumulation of lithium atoms on the electrode/electrolyte interface. The accumulated lithium atoms form dendrites, which penetrate the separators and create a short circuit inside the battery that can cause an explosion. On the other hand, the crystalline structure of delithiated lithium cobalt dioxide (Li_xCoO_2) is more stable than that of Li_xNiO_2 . LiCoO_2 is widely used in commercial lithium-ion batteries; however, the capacity of Li_xCoO_2 (~150mAh/g) is smaller than that of Li_xNiO_2 (~250mAh/g).

To improve the capacity and stability of intercalation materials, several routes have been investigated. For example, lithium-metal oxides have been doped with inert di-, tri- or tetravalent cationic elements (e.g. Ti and Mg). These elements substitute for Ni or Co and stabilize the layered structure of the intercalation materials. However, this $\text{LiM}_{1-x}\text{Ti}_{x/2}\text{Mg}_{x/2}\text{O}_2$ (M:Co or Ni) phase (5) is difficult to synthesize. Another approach employs chimie douce (soft chemistry) to synthesize the layered lithium manganese dioxide (LiMnO_2) phase. However, the layered phase is structurally unstable and transitions to an unstable spinel, $\text{Li}_x\text{Mn}_2\text{O}_4$, during use.(6) While electrochemically attractive, these materials exhibit limited cycling life and storage capacity.

Tuning the morphology or texture of lithium-intercalated materials to produce porous, high surface area composites presents an alternative strategy for improving electrode capacities and stabilities. For example, electrodes fabricated from mesoporous vanadium oxide (V_2O_5) were reported to have capacities up to 100 % greater than electrodes of polycrystalline non-porous V_2O_5 powder.(7)

Still, it is desirable to have an electrode material for lithium ion batteries that exhibits improved capacity and stability.

Summary of the Invention

The present invention provides a variety of compositions that include a metal oxide, films and batteries comprising one or more of the compositions, and methods of making the same.

In one aspect, the invention provides a metal oxide coordinated to a first peptide, the first peptide exhibiting an affinity for a reduced form of the metal. In

certain embodiments of the invention the metal comprises a transition metal, e.g., cobalt, vanadium, nickel, manganese, iron, cadmium, tungsten, chromium, zirconium, titanium, scandium, yttrium, copper, calcium, aluminum, barium, beryllium, magnesium, and strontium. In certain embodiments of the invention the metal oxide
5 is an oxidized metal nanoparticle. In certain embodiments of the invention the metal oxide can intercalate lithium ions.

In certain embodiments of the invention the first peptide includes carboxylated amino acids. In a particular embodiment the sequence of the first peptide is AEEEEED and the metal is cobalt. The peptide may be part of a virus.

10 In certain aspects of the invention, the composition further includes a second peptide that selectively binds a predetermined metal selected from copper, nickel, gold, silver, platinum, and palladium. In a particular embodiment of these aspects of the invention the sequence of the second peptide may be LKAHLPPSRLPS and the predetermined metal may be gold.

15 The composition that includes a second peptide that selectively binds a predetermined metal may further comprise the predetermined metal. The predetermined metal may be, e.g., between about 1% and about 30% of the metal coordinated to a protein coat of the virus. In some embodiments the predetermined metal is between about 15% and about 30% of the metal coordinated to a protein coat
20 of the virus. In certain embodiments of the invention a first portion of a predetermined coat protein on the virus includes the first peptide, and a second portion of the predetermined coat protein includes the second peptide. The first peptide may be part of a first predetermined coat protein, and the second peptide may be part of a second predetermined coat protein.

25 In another aspect, the invention provides a composition produced by steps that include: (i) providing a first peptide exhibiting an affinity for metal ions; (ii) coordinating a metal to the first peptide; and (iii) oxidizing the coordinated metal to form a crystallite of the metal oxide. In certain embodiments of the invention the crystallite has a size between 2 nm and 1000 nm. In certain embodiments of this
30 aspect of the invention, providing a first peptide includes providing a population of

virus displaying the first peptide. The invention further provides the foregoing composition, wherein substantially all the virus is removed from the composition.

In another aspect, the invention provides a film that includes any of the aforementioned compositions. The film may, e.g., exhibit long range order or short range
5 order. In certain embodiments of the invention the film does not exhibit long range order. In certain embodiments of the invention the film does not exhibit short range order. The film may be between about 10 nm and about 10 μ m thick.

In another aspect, the invention provides a lithium ion battery that includes: (i)
10 an electrolyte; and (ii) a lithium accumulation layer disposed adjacent to the electrolyte, the lithium accumulation layer that includes any of the afore-mentioned compositions. The battery may further include an electrode material adjacent to the lithium accumulation layer, wherein the lithium accumulation layer is disposed between the electrode material and the electrolyte. The electrolyte may be a solid or a fluid.

15 In another aspect, the invention provides a method of producing a thin film, the method including steps of: (i) providing a plurality of nanotubes, the nanotubes comprising a virus to which a metal oxide is coordinated; and (ii) casting the plurality into a film. In certain embodiments of this method, providing a plurality of nanotubes includes: (i) providing a population of virus comprising a first peptide exhibiting an
20 affinity for metals; (ii) coordinating a metal to the first peptide; and (iii) oxidizing the coordinated metal to form a crystallite of the metal oxide disposed about the virus.

Brief Description of the Drawing

The invention is described with reference to the several figures of the drawing, in which,

25 Figure 1 is a transmission electron microscopy image of virus-based Co_3O_4 nanotubes;

Figure 2A is a graph showing the variation in specific capacity with cycling of an electrochemical cell including a thin film of cobalt oxide nanoparticles according to an embodiment of the invention.

Figure 2B is a graph showing the variation in voltage with cycling of an electrochemical cell including a thin film of cobalt oxide nanoparticles according to an embodiment of the invention.

Figure 3A is a transmission electron micrograph of a thin film of cobalt
oxide/gold nanoparticles according to an embodiment of the invention.

Figure 3B is a graph showing the variation in specific capacity with cycling of an electrochemical cell including a thin film of cobalt oxide/gold nanoparticles according to an embodiment of the invention.

Detailed Description of Certain Preferred Embodiments

M13 bacteriophage contains about 2700 copies of a major coat protein, pVIII protein, which are longitudinally assembled along the virus's DNA. Moreover, several copies of minor coat proteins (pIII, pVI, pVII, and pIX proteins) are assembled at the two ends of the virus. This unique periodic, uniform structure is genetically controlled. Therefore, we can use this particular property of M13
bacteriophage to create tailor-made nanostructure electrode materials that exhibit improved structural stability and higher capacity.

In one embodiment, the major coat protein of M13 bacteriophage is genetically engineered to specifically bind to metal ions or nanoparticles. Metal oxide nanotubes are synthesized using this engineered virus template. Due to the anisotropic structure of bacteriophage, the virus-based metal oxide nanotubes self-assemble into a mesoporous nanocrystalline film. Intercalation of lithium through and between the virus-based nanotubes, as well as their high specific surface area, can greatly increase the capacity of the films for lithium ions. Furthermore, the highly oriented helical major coat proteins of M13 virus promote the structural stability of individual virus-based nanotubes, increasing the total life of lithium-ion batteries incorporating them. Other viruses, such as f1, fd, and tobacco mosaic virus (TMV) may also be employed in embodiments of the invention.

Mesoporous thin films for lithium ion batteries

Films produced using virus based metal/oxide nanotubes according to an
embodiment of the invention may be used in all parts of a lithium-ion battery. A

lithium-ion battery employs lithium ions as a charge carrier in the battery, completing the circuit traversed by electrons circulating from the battery to a load. In some prior art batteries, lithium ions are inserted in intercalation layers, e.g., graphite layers, in the anode of the battery. As the battery discharges, the lithium ions leave the cathode and traverse the electrolyte to the anode. When the battery is charged, the lithium ions leave the anode and travel back across the electrolyte to the cathode.

The stability of the crystalline microstructure of the electrodes determines the lifespan of a lithium-ion battery. The long-range order of virus-based nanotubes and the stiffness of bacteriophage itself provide good mechanical properties to virus-based films. In addition, both the proteins and the nanotubes themselves stabilize virus-based thin films against fatigue. As discussed above, delithiated lithium-transition metal oxides may collapse. The intercalation of lithium ions in metal oxides causes them to expand; diffusion of the lithium ions out of the oxide during the reverse cycle allows the expanded oxide to relax and contract. This repeated volume change can cause a solid oxide material to crack.

In contrast, because the nanotubes are not affixed to one another, they can shift within the film to accommodate lithium ions that are incorporated into the cathode film during battery discharge and to accommodate the volume change resulting from the ejection of those lithium ions as the battery is charged. Likewise, the flexible protein chains in the virus coat can also shift to accommodate lithium ions in the cathode film without causing permanent cracks in the nanotube. In addition, the flexibility of the proteins and the malleability of the film may also promote diffusion of the lithium ions through the film. The highly oriented helical major proteins of M13 can stabilize the microstructure because of the layered crystalline structure regulated by the proteins and their strong binding affinity for metal oxides.

Synthesis of a virus-based metal oxide nanotube.

M13 is a filamentous phage (~880nm long and 6nm in diameter) whose capsid includes several proteins (pI-pVIII). At one end of the M13 virus, there are approximately five copies each of pII and pIX. The other end has about five copies each of pIII and pVI. The wild-type M13 virus coat includes about 2700 copies of

major coat protein pVIII, which are stacked in units of five in a helical array. The various proteins may be genetically modified to have a specific peptide motif that can bind and organize nanomaterials. Because the amino acid sequence of this motif is genetically linked to the virus DNA and contained within the virus capsid, exact genetic copies of the virus scaffold can be created easily and quickly reproduced by infection into bacterial hosts. In one embodiment, glutamic acid and aspartic acid, which contain carboxylic acid sidechains, are genetically expressed in the pVIII protein and used to bind various metal ions via chelation. An exemplary peptide sequence is AEEEEED (SEQ ID:1) ("sequence E4") Longer sequences, including 5 to 25 amino acids or more, for example, 5 to 10, 10 to 15, 15-20, or 20-25 amino acids, may also be employed. The terminal amino acids on either end of the peptide may be carboxylated or not; however, it may be preferable that the peptide not include amino acids that would interfere with the interaction of the peptide and the metal. The ratio of glutamate to aspartate in the peptides may range from 100% glutamate to 100% aspartate. Alternatively or in addition, an inert peptide sequence may be coupled to the carboxylated peptide sequence, or a peptide that is selective for some other material may be coupled to the carboxylated peptide. The carboxylate enhancement may be expressed on all the pVIII chains (100% display) or may be partially displayed using various techniques for modifying bacteriophage genomes well known to those skilled in the art.(9) Alternatively or in addition, the carboxylate enhancement may be expressed on one of the other coat proteins, e.g., pIII.

Variation of the degree of carboxylate expression may modify the conformation and crystalline structure of the virus-based nanotubes. In addition, variation of the number of carboxylate groups or different mixtures of aspartic acid and glutamic acid residues may also influence the microstructure of the oxide. The affinity of the desired metal or its oxide for the modified virus may be optimized using the phage display library techniques described in US20030073104, published April 17, 2003, the contents of which are incorporated herein by reference. Phage display is a combinatorial technique in which a 'random library' of viruses is exposed to a substrate of interest. In some embodiments, the random library includes roughly 10^{11} viruses that have each been uniquely modified, representing about 10^9 variations.

The modification may take the form of an additional amino acid sequence which is expressed on one of the coat proteins of the viral assembly. Peptides containing various amounts of carboxylate and ratios of aspartate and glutamate may be tested for their affinity to a metal or oxide surface.

5 As used herein, the term "peptide" denotes a string of at least two amino acids linked together by peptide bonds. Peptide may refer to an individual peptide or a collection of peptides. Peptides may contain only natural amino acids, although non-natural amino acids (i.e., compounds that do not occur in nature but that can be incorporated into a polypeptide chain) and/or amino acid analogs as are known in the art may alternatively be employed. Also, one or more of the amino acids in a peptide
10 may be modified, for example, by the addition of a chemical entity such as a carbohydrate group, a phosphate group, a farnesyl group, an isofarnesyl group, a fatty acid group, a linker for conjugation, functionalization, or other modification, etc. In one embodiment, the modifications of the peptide lead to a more stable peptide (e.g.,
15 greater half-life in vivo). These modifications may include cyclization of the peptide, the incorporation of D-amino acids, etc. None of the modifications should substantially interfere with the desired activity of the peptide.

Lithium ion batteries often exhibit a decay in voltage after repeated recharging cycles. This reduces the lifetime of the battery, as the capacity of the battery may not
20 provide a reasonable battery life or sufficient power after a certain number of charges. One possible contributor to this effect is the irreversible binding of lithium ions to each other and to impurities at the cathode and anode of the battery. In some batteries, a solid electrolyte interface is disposed between the electrode, especially graphite anodes, and the electrolyte to prevent migration of the lithium ions to the
25 electrode. Where the ions do not migrate all the way to the electrode, the circuit may be maintained by conducting electrons from the electrode to a solid electrolyte interface material.

The use of phage display provides a method to co-locate both ionic and electronic conductors. In one embodiment, a peptide sequence that selectively binds
30 an electronic conductor may be incorporated into the protein coat of the virus. For example, biopanning may be used to identify a peptide sequence that is selective for a

desired catalyst, e.g., copper, gold, silver, nickel, platinum, palladium, etc. An exemplary peptide that selectively binds gold is LKAHLPPSRLPS (SEQ ID:2). This peptide may be expressed on a different coat protein than the modified coat protein that binds the metal oxide. Alternatively or in addition, the peptide may be expressed
5 on a portion of the same coat protein (e.g., pVIII) on which the peptide for the metal oxide is expressed. In some embodiments, biopanning using a library of variations in one coat protein is used to identify a peptide sequence for which a polynucleotide is engineered such that the peptide is expressed in a different coat protein.

This is not to say that peptide sequences selective for the metal oxide and the
10 electronic conductor are expressed on the very same protein molecule, rather that both peptides show up in the region of the virus where the particular coat protein is found. For example, some copies of the pVIII protein may include a peptide selective for the electronic conductor, while others include a peptide selective for the metal oxide. Techniques for expressing two separate engineered peptide sequences on the same
15 virus are discussed in Nam, et al., *Nanoletters*, 2004, Vol. 4(1):23-27, the entire contents of which are incorporated herein by reference. Briefly, a phagemid system (Kay, et al., *Phage Display of Peptides and Proteins: A laboratory Manual*; Academic Press: San Diego, 1996, the entire contents of which are incorporated herein by reference), is employed, using a plasmid separate from the already
20 engineered-M13 plasmid to express the catalyst-selective peptide-coat protein fusion. The DNA from the phagemid are packaged into viruses as well as the engineered-M13 plasmid, allowing further copies of the virus to be reproduced later if desired. In some embodiments, at most about 20-30% of the major coat proteins or between zero and five copies of the minor coat proteins such as pIX exhibit the catalyst-selective
25 peptide sequence.

The resulting virus, expressing either one type or two types of modified peptides, may then be used to nucleate nanoparticles of the metal oxide, with or without an electronic conductor. Nanoparticles and nanotubules may be produced at room temperature, in contrast to the elevated temperatures ($> 150^{\circ}\text{C}$) required for
30 some prior art techniques. In one embodiment, the pVIII-engineered M13 virus is incubated with a metal salt precursor, for example, cobalt chloride, at a concentration

between about 1mM and about 5mM. Metal ions in solution are chelated by the carboxylic acid ligands. Chelated metal ions are then oxidized by adding a basic solution such as sodium hydroxide (NaOH), at, for example, between about 10mM and about 100mM. Alternatively, metallic nanoparticles may be nucleated and grown
5 on the virus major coat proteins by adding between about 5mM and about 10mM of a reducing agent such as sodium borohydride (NaBH₄) or hydrazine (N₂H₂) to a metal salt solution in which the virus is suspended. The virus is fully coated with nanoparticles, forming a metallic nanotube. Because the metallic materials in nanostructures are very reactive, the metallic nanotube is easily oxidized in an
10 aqueous solution or in air to produce a nanotube composed of crystalline metal oxide nanoparticles. In another embodiment, the virus scaffold may be removed from the nanotubes, for example, using enzymes or solvents that disrupt or lyse the viral proteins without disturbing the ceramic phase.

The production conditions may be altered to modify the nanostructure of the
15 oxide nanoparticles. The size of the nanoparticles varies roughly with temperature. Smaller particles may be produced by decreasing the temperature while larger particles may be produced by increasing temperature. The viral system is stable from about 4°C to about 80°C; other templates, e.g., peptides, nucleic acids, etc., will be stable in different temperature ranges. Particles may range in diameter from about 2
20 nm across to about a micron across, for example, between 2 nm and 100 nm, between 100 nm and 500 nm, or between 500 nm and 1000 nm.

The same chemistry may be employed to chelate the electronic conductor to the engineered virus, simply by using a salt of the electronic conductor to the solution in which the metal ion is attached to the virus or using a separate solution. The
25 electronic conductor may be reduced if necessary. Alternatively or in addition, the virus may be incubated with a colloidal solution of nanoparticles of the electronic conductor. Regardless of the proportion of the appropriate peptide in the virus, the proportion of the electronic conductor to the transition metal oxide may be adjusted by adjusting the concentration of the conductor or its salt in solution or modifying the
30 incubation time.

In either embodiment, the diameter of the nanotubes may be adjusted by manipulating the amount of carboxylated amino acids expressed on the coat protein and/or the molar ratio of the metallic ion precursor to the basic reactant or reduction agent. This ratio also determines the uniformity, size and crystal structure of the nanoparticles on these nanotubes.

In another embodiment, alternative metal oxides, such as Mn_2O_4 or V_2O_5 , may be formed into nanotubes using the techniques described herein. Other metals that may be used to produce nanotubes according to embodiments of the invention include transition metals, for example, nickel, iron, cadmium, tungsten, chromium, zirconium, titanium, scandium, yttrium, copper, etc. In some embodiments, non-transition metal oxides may be formed into nanotubes. Exemplary metals that may be exploited for use with the invention include but are not limited to calcium, aluminum, barium, beryllium, magnesium, and strontium. All of these may be produced using the same engineered viruses, or biopanning may be employed to identify peptides that are even more selective for the particular metal or metal oxide. Alternatively or in addition, mixed metal oxides may be produced by incubating engineered phage in solutions including salts of more than one metal.

Figure 1 shows transmission electron microscopy images of Co_3O_4 nanotubes grown on an M13 virus scaffold at room temperature according to Example 1. As shown in this figure, regular oxide nanoparticles are uniformly coated on M13 virus, resulting in metal oxide nanotubes. The electron diffraction pattern indicates that the oxide phase is Co_3O_4 . Nanotubes produced according to certain embodiments of the invention may be as small as 2-3 nm. An exemplary sample of Co_3O_4 nanotubes exhibited a surface area of about $140 \text{ m}^2/\text{g}$. In contrast, cobalt oxide particles formed without any virus or with wild type M13 virus are irregularly shaped and significantly larger than the nanotubes and include a mixture of Co, CoO, and Co_3O_4 .

Self-assembly of nanotubes into a mesoporous thin film

The nanotubes described above may be cast as thin films ranging from about 10 nanometers to about 100 microns, for example, between about 10 nm and about 100 nm, between about 100 nm and about 1 micron, between about 1 micron and

about 10 micron, or between about 10 micron and about 100 micron. for use in lithium-ion batteries. U.S. Patent Publication No. 20030073104, the contents of which are incorporated herein by reference, provides exemplary methods of casting films. Films may be cast by simply allowing a solution of the virus to dry, leaving the viral film behind. Films may have a thickness from about 1 micron to about 100 microns, which may be controlled by using a larger or smaller amount of viral suspension in a given area. The nanotubes may exhibit short-or long-range order in the films, for example, as a liquid crystal phase, depending on the concentration of phage in the original solution. In some embodiments, between about 10^{14} phage/mL to about 10^{14} phage/microliter solutions are employed. The degree of order increases with concentration. M13 bacteriophage exhibits long-range order in liquid crystalline phases due to its unique anisotropic and monodisperse characteristics. Previously, Belcher, et al., have shown that pIII engineered virus suspended in ZnS precursor solution to form viral ZnS nanocrystals contained liquid crystalline suspensions.(8) Although ZnS nanocrystals are linked to pIII proteins at one end of the virus, the long, rod-shaped virus retains its liquid crystalline behavior and can be cast into virus-based thin films with controlled thickness.

Depending on the solvent, the virus concentration, the ionic strength of the solution and, for cobalt oxide and other magnetic materials, the applied external magnetic field, various liquid crystalline phases such as smectic, cholesteric and nematic phases can be achieved. Lower concentrations result in a nematic phase, while progressively higher concentrations result in cholesteric and smectic phases. When the concentration of the virus-based nanotubes in the solution is lower than the critical concentration to form the nematic phase, the nanotubes will not form a liquid crystal phase in cast films. The particular liquid crystalline phase of a nanotube solution will affect the mesoporosity, mesostructure and the mechanical properties of films cast from the solution. All these parameters influence the capacity, lifespan, energy density, and stability of virus-based thin film electrodes.

In some embodiments, it is not necessary that the nanotubes assemble into liquid crystals. Cast films of randomly oriented nanotubes can still exhibit the surface area and mechanical properties needed to produce robust, efficient batteries.

Nanotubes fabricated by specific nucleation on engineered virus spontaneously evolve into a self-supported hybrid mesoporous thin film. The spacing between nanotubes, microstructure, and thickness of the film can be regulated by the casting conditions, such as concentration, temperature, pressure and magnetic field. In an alternative embodiment, engineered virus is first cast as a film and then metallized. The film is suspended in solution as described above and a metal or metal nanoparticles chelated to the virus and then oxidized. The cohesion of phage may prevent the film from dissolving in the solution. The film may be arbitrarily thick so long as it does not interfere with the transfer of electrons to and from the ionic charge carriers and across the multiple cells of a battery. One skilled in the art will recognize that the thickness of the film may be optimized to maintain the physical integrity of the film without excessively increasing the internal resistance of batteries incorporating the film.

In an alternative embodiment, the engineered virus are assembled into a film before coordinating the metal oxide and any conductor to the virus. In this embodiment, the film is cast using a solution of the virus, following which the film is processed under the same conditions as the virus to bind the electron conductor and form the metal oxide. Gentle agitation may be used to maintain the uniformity of solutions in which the film is immersed to improve reaction times.

Use of Thin Films

As discussed above, viral films produced according to an embodiment of the invention may be employed in batteries. Li-ion batteries often employ a graphite anode, a liquid or polymer electrolyte, and a cathode that can accumulate lithium ions, such as a transition metal oxide, e.g., cobalt oxide, vanadium oxide, or nickel oxide. In prior art batteries, the lithium ions intercalate themselves between oxide layers. The metal oxide films produced according to various embodiments of the present invention may also accumulate lithium ions through intercalation. As described above, the mobility of the particles within the film allows the film to accumulate and discharge lithium ions without cracking. Without being limited by any particular hypothesis, it is also thought that the lithium ions are additionally accumulated by the film via deposition of lithium oxide on the surfaces of the nanotubes through standard

electrochemical mechanisms, e.g., through the oxidation of lithium and the reduction of cobalt or other oxidized metals in the films. The high surface area of the nanotubes within the film provides additional reaction sites for lithium ions, thereby increasing the capacity of an electrode including the film.

5 One skilled in the art will also recognize that thin films according to an embodiment of the invention may also be employed in the anode of Li-ion batteries. The composition of the particular metal oxide may be selected with reference to the electrochemical potential of the material used at the cathode, whether it is another virus based thin film or some other material. In general, the materials for the anode
10 and cathode of the battery are selected such that, when the battery is discharging, the oxidation of lithium at the anode and its reduction at the cathode is energetically favored, while the reverse reactions are energetically favored during recharging. Any of the transition metal and non-transition metal oxides described above may be used to form films for use on the anode side of a lithium ion battery. Some exemplary
15 materials include cobalt, nickel, chromium, and manganese. Of course, the anode and cathode materials may be optimized with respect to one another to achieve a desired difference in redox potential between the two sides of the cell.

 Whether or not the virus-based films exhibit short- or long-range order (or none), they also exhibit mesoporosity defined by gaps between regions of more
20 densely packed virus. This mesoporous microstructure can improve the energy capacity of a battery. A large surface area in the inner and outer walls of virus-based nanotubes may facilitate lithium deposition and intercalation, increasing the capacity of the battery without requiring an increase in size. Moreover, the mesopores can serve as electrolyte channels for faster transportation of the lithium ions to the interior
25 surfaces of the electrode, improving the kinetics of both charging and discharging and reducing the internal resistance of a battery employing the film. In fact, effective uptake and release of cations by oxide nanotubes was investigated and intercalation of lithium ions in high capacity nanotubes was reported (3). The interface between nanotubes in the virus-based film may also act as an intercalation site. These unique
30 characteristics of this mesoporous film can greatly improve the battery capacity.

Thin films produced according to an embodiment of the invention may be used with batteries incorporating both solid electrolytes and liquid electrolytes. The flexibility and high surface area/volume ratio of the films may also facilitate the production of smaller batteries in different configurations. The films may be
5 produced in various shapes, such as cylinder, disc, prism and belt. Alternatively or in addition, thin films according to an embodiment of the invention may be coated onto electrode materials such as platinum, silver, or copper, which materials may be used to conduct current to the thin films from another part of a circuit. The electrode material substrate may be solid or a mesh, especially where a conductive material is
10 included in the film. The virus-based thin film electrode is flexible and ductile and exhibits high capacity and specific energy density. Despite the continuing miniaturization of cell phones and laptop computers, the largest and heaviest component of portable devices continues to be their batteries. Thin films according to an embodiment of the invention may be used to create smaller, more flexible, lighter
15 batteries for smaller devices.

Two purposes served by the electrodes in a battery are electron conduction and providing a site for the oxidation or reduction of the ionic charge carrier (e.g., lithium). Where nanotubes are produced incorporating both oxides and electron conductors, the film may be cast on a more traditional electrode material (e.g.,
20 graphite) for use as a solid electrolyte interface layer or may themselves be used as the electrodes. It may be desirable to use metallic leads to connect the various cells in the battery.

Use of peptides to create Li-ion batteries

In another embodiment, peptides unconnected from viruses may be used to
25 produce metal oxide layers for use in batteries. For example, carboxylated peptide sequences may be immobilized as a monolayer on an electrode material and used to support the formation of a metal oxide layer. In one embodiment, the carboxylated peptide is coupled to an alkanethiol or a polycysteine peptide. Thiolated molecules readily attach to many metals, including gold and nickel. See Whitesides,
30 Proceedings of the Robert A. Welch Foundation 39th Conference On Chemical

Research Nanophase Chemistry, Houston, Tex., pages 109-121 (1995). Alternatively, peptides including the carboxylated sequence and a sequence that selectively binds the desired substrate be used to coat an electrode material. Some exemplary sequences that are selective for particular substrates have been reported, for example, in Sarikaya, et al., *Nature Materials*, (2003) Vol. 2, pp577-585, the entire contents of which are incorporated herein by reference. Others may be identified using the biopanning techniques described above.

In another embodiment, free peptides may be used to form metal oxide nanoparticles. For example, peptides may be synthesized using Fmoc-based solid phase synthesis and electrochemical techniques may be used to form metal oxide nanoparticles whose structure is regulated by the peptides. In one embodiment, an electrochemical cell is constructed using the material whose oxide is being formed as the anode and cathode in anolyte and catholyte compartments separated from the electrolyte by a glass frit. An NaCl solution, for example, about 1M, is used as the electrolyte. The peptide is added to the electrolyte at low concentration, e.g., 10-15 nM. The cell is operated galvanically at low current, e.g., about 10 mA, for a short time, e.g., 1 min to generate metal ions. See Dai, et al., "Electrochemical and Biomimetic Synthesis and Organization of Hybrid Protein-Inorganic Nanostructures," *JACS*, (2005) 10.1021/ja055499h, the contents of which are incorporated herein by reference.

Examples

Co₃O₄ nanotubes were prepared by incubating virus engineered to express sequence E4 in the pVIII coat in an aqueous cobalt chloride solution between 1 and 10 mM at a pH greater than 4, e.g., pH 6, for 30 min at room temperature to chelate cobalt ions to the carboxylated peptide fusions. Sodium borohydride was used to reduce the cobalt ions to cobalt metal, which oxidized spontaneously in water to form monodisperse, crystalline cobalt oxide nanotubes. The nanotubes were formed into films and disposed on platinum electrodes. The electrode was used to prepare a Li ion battery using a lithium metal foil was employed as the anode. A CelgardTM 2400 film saturated with 1M LiPF₆ in ethylene carbonate and dimethyl carbonate (1:1 by

volume) was used as the electrolyte. The battery was cycled between 3 and 0.01V using MACCOR automated test equipment. The capacity of the battery and the voltage delivered by the battery are shown in Figures 2A and 2B

5 Nanotubes incorporating both cobalt oxide and gold were prepared by displaying a gold binding peptide (LKAHLPPSRLPS) (SEQ ID:2) on the E4 phage using a phagemid system. The gold binding peptide was present in about 20% of the pVIII proteins of the E4 phage. A solution of 5nm gold particles was obtained from Ted Pella and incubated with the engineered virus for about two hours. The phage were then processed as above to produce gold-cobalt oxide nanotubes. The phage
10 were cast into films from a 10^{14} phage/mL solution and formed into batteries as described above. A TEM micrograph of the resulting film is shown in Figure 3A. The variation in capacity with cycling for a Li-ion cell incorporating the film is plotted in Figure 3B.

References

- 15 1) J.-M. Tarascon and M. Armand, "Issue and challenges facing rechargeable lithium batteries", *Nature* **414**, 359-367 (2001).
- 2) G. Che, B. B. Lakshmi, E. R. Fisher and C. R. Martin, "Carbon nanotube membranes for electrochemical energy storage and production", *Nature* **393**, 346-349 (1998).
- 20 3) Y. Zhou, L. Cao, F. Zhang, B. He, H. Li, "Lithium insertion into TiO₂ nanotube prepared by the hydrothermal process, *J. Electrochem. Soc.* **150**, A1246-A1249 (2003).
- 4) J. R. Dahn, U. Von Sacken, M. W. Juzkow, H. Al-Janaby, "Rechargeable LiNiO₂/carbon cells", *J. Electrochem. Soc.* **138**, 2207-2211 (1991).
- 25 5) G. Yuan, M.V. Yakovleva, W.B. Ebner, "Novel LiNi_{1-x}Ti_x/2Mgx/2O₂ compounds as cathode materials for safer lithium-ion batteries", *Electrochem. Solid State Lett.* **1**, 117-119 (1998),
- 6) B. Ammundsen, et al., in *Proc. Int. Symp. Electrochem. Soc.* Vol. 99-24, 57-67 (ECS, Pennington, NJ, 2000).

7) W. Donga, D. R. Rolison, B. Dunn, "Electrochemical properties of high surface area vanadium oxides aerogels", *Electrochem. Solid State Lett.* **3**, 457-459 (2000).

8) J. Ni, S.-W. Lee, J. M. White, A. M. Belcher, "Molecular orientation of a
5 ZnS-nanocrystal-modified M13 virus on a silicon substrate", *J. Polym. Sci. part B: Polym. Phys.* **42**, 629-635 (2004).

9) C. Mao, et al., *Proc. Natl. Acad. Sci. U.S.A.* **100**, 6946 (2003).

Other embodiments of the invention will be apparent to those skilled in the art from a consideration of the specification or practice of the invention disclosed herein.

10 It is intended that the specification and examples be considered as exemplary only, with the true scope and spirit of the invention being indicated by the following claims.

What is claimed is:

- 1 1. A composition comprising:
2 a metal oxide coordinated to a first peptide, the first peptide exhibiting an
3 affinity for a reduced form of the metal.
- 4 2. The composition of claim 1, wherein the metal comprises a transition metal.
- 5 3. The composition of claim 1, wherein the metal is selected from cobalt,
6 vanadium, nickel, manganese, iron, cadmium, tungsten, chromium, zirconium,
7 titanium, scandium, yttrium, copper, calcium, aluminum, barium, beryllium,
8 magnesium, and strontium.
- 9 4. The composition of claim 1, wherein the metal oxide is an oxidized metal
10 nanoparticle.
- 11 5. The composition of claim 1, wherein the metal oxide can intercalate lithium
12 ions.
- 13 6. The composition of claim 1, wherein the first peptide includes carboxylated
14 amino acids.
- 15 7. The composition of claim 6, wherein the sequence is AEEEEED and the metal
16 is cobalt.
- 17 8. The composition of claim 1, wherein the peptide is part of a virus.
- 18 9. The composition of claim 8, further comprising a second peptide that
19 selectively binds a predetermined metal selected from copper, nickel, gold,
20 silver, platinum, and palladium.
- 21 10. The composition of claim 9, wherein the second peptide is LKAHLPPSRLPS
22 and the predetermined metal is gold.
- 23 11. The composition of claim 9, further comprising the predetermined metal.

- 1 12. The composition of claim 11, wherein the predetermined metal is between
2 about 1% and about 30% of the metal coordinated to a protein coat of the
3 virus.
- 4 13. The composition of claim 12, wherein the predetermined metal is between
5 about 15% and about 30% of the metal coordinated to a protein coat of the
6 virus.
- 7 14. The composition of claim 9, wherein a first portion of a predetermined coat
8 protein on the virus includes the first peptide, and wherein a second portion of
9 the predetermined coat protein includes the second peptide.
- 10 15. The composition of claim 9, wherein the first peptide is part of a first
11 predetermined coat protein, and wherein the second peptide is part of a second
12 predetermined coat protein.
- 13 16. A composition produced by the steps of:
14 providing a first peptide exhibiting an affinity for metal ions;
15 coordinating a metal to the first peptide; and
16 oxidizing the coordinated metal to form a crystallite of the metal oxide.
- 17 17. The composition of claim 16, wherein the metal comprises a transition metal.
- 18 18. The composition of claim 16, wherein the metal is one or more of cobalt,
19 vanadium, nickel, manganese, iron, cadmium, tungsten, chromium, zirconium,
20 titanium, scandium, yttrium, copper, calcium, aluminum, barium, beryllium,
21 magnesium, and strontium.
- 22 19. The composition of claim 16, wherein the crystallite has a size between 2 nm
23 and 1000 nm.
- 24 20. The composition of claim 16, wherein providing a first peptide comprises
25 providing a population of virus displaying the first peptide.

- 1 21. The composition of claim 20, wherein substantially all the virus is removed
2 from the composition.
- 3 22. The composition of claim 20, wherein the population of virus also comprises a
4 second peptide that selectively binds one or more of copper, nickel, gold,
5 silver, platinum, and palladium.
- 6 23. The composition of claim 22, wherein the second peptide is LKAHLPPSRLPS
7 and the second peptide selectively binds gold.
- 8 24. The composition of claim 22, further comprising coordinating a transition
9 metal selected from copper, nickel, gold, silver, platinum, and palladium to the
10 second peptide.
- 11 25. The composition of claim 24, wherein the transition metal selected from
12 copper, nickel, gold, silver, platinum, and palladium is between about 1% and
13 about 30% of the metal in the composition.
- 14 26. The composition of claim 16, wherein the first peptide includes carboxylated
15 amino acids.
- 16 27. The composition of claim 26, wherein the sequence is AEEEEED and the
17 transition metal is cobalt.
- 18 28. A film comprising the composition of claim 1 or 16.
- 19 29. The film of claim 28, wherein the film exhibits long range order or short range
20 order.
- 21 30. The film of claim 28, wherein the film does not exhibit long range order.
- 22 31. The film of claim 28, wherein the film does not exhibit short range order.
- 23 32. The film of claim 28, wherein the film is between about 10 nm and about 10
24 μm thick.

- 1 33. A lithium ion battery, comprising:
2 an electrolyte;
3 a lithium accumulation layer disposed adjacent to the electrolyte, the lithium
4 accumulation layer comprising the composition of claim 1 or 16.
- 5 34. The battery of claim 33, further comprising an electrode material adjacent to
6 the lithium accumulation layer, wherein the lithium accumulation layer is
7 disposed between the electrode material and the electrolyte.
- 8 35. The battery of claim 33, wherein the electrolyte is a solid or a fluid.
- 9 36. A method of producing a thin film, comprising:
10 providing a plurality of nanotubes, the nanotubes comprising a virus to which
11 a metal oxide is coordinated; and
12 casting the plurality into a film.
- 13 37. The method of claim 36, wherein providing a plurality of nanotubes
14 comprises:
15 providing a population of virus comprising a first peptide exhibiting an
16 affinity for metals;
17 coordinating a metal to the first peptide; and
18 oxidizing the coordinated metal to form a crystallite of the metal oxide
19 disposed about the virus.
- 20 38. The method of claim 37, wherein the first peptide comprises carboxylated
21 amino acids.
- 22 39. The method of claim 38, wherein the first peptide is AEEEEED and the
23 transition metal oxide is Co_3O_4 .
- 24 40. The method of claim 37, wherein the population of virus further comprises a
25 second peptide that selectively binds one or more of copper, nickel, gold,
26 silver, platinum, and palladium, and wherein providing a plurality of

- 1 nanotubes further comprises coordinating one or more of copper, nickel, gold
2 gold, silver, platinum, and palladium to the second peptide.
- 3 41. The method of claim 40, wherein the second peptide is LKAHLPPSRLPS and
4 the second peptide selectively binds gold.
- 5 42. The method of claim 37, further comprising removing substantially all the
6 virus from the nanotubes.
- 7 43. The method of claim 36, wherein the film is between about 10 nm and about
8 10 μ m thick.
- 9