

COMBINATION OF BLOOD AND OF BIPHASIC CALCIUM PHOSPHATE
CERAMIC PARTICLES

5 The subject of the invention is a novel biomaterial containing coagulated blood or coagulated bone marrow aspirate, and biphasic calcium phosphate ceramic particles, and a method for its preparation and its use for the manufacture of an implant allowing bone tissue regeneration.

10

The reconstruction of loss of bone substance, mainly of trauma and more rarely tumor origin, is one of the great difficulties encountered by orthopedic surgeons. Small size defects, from "narrow" pseudarthrosis (defect of consolidation of a fracture where the loss of substance is virtual) to bone loss of 5-6 cm, are most often the subject of an autologous transplant of spongy or corticospongy bone tissue removed from the iliac crest (gold standard). Large size defects (≥ 6 cm) require much more cumbersome procedures, vascularized bone transfers or Masquelet technique. Nevertheless, the quantity of available autologous bone is limited, bone consolidation remains uncertain and these various techniques mainly result in post-operative complications at the site of removal of the transplant.

Various biomaterials available in clinical practice make it possible to avoid, in theory, the disadvantages of autologous transplantation. Unfortunately, none of them rivals the results of bone transplantation and they never allow the reconstruction of loss of large size substance.

35 The majority of the bone substitutes currently studied combine biomaterials with mesenchymal stem cells obtained from bone marrow after several weeks of selection and cell culture *in vitro*. This approach is

cumbersome and expensive, which limits the clinical benefits.

5 L. Okazaki et al., Clin. Oral Impl. Res., **16**, 2005,
236-243 describe implants containing either
demineralized bone powder or coagulated blood. Several
authors have studied the combination of blood with
synthetic biomaterials: J. Schmid et al., Clin. Oral
Impl. Res. 1997:**8**:75-8 describe implants containing
10 demineralized bovine bone powder and blood. A. Chevrier
et al., Osteoarthritis and Cartilage (2007), **15**,
316-327, describe implants containing a solution of
polymer containing chitosan in a glycerol phosphate
buffer and blood which coagulates in situ. B. Wallkamm
15 et al., Clin. Oral Imp. Res., **14**, 2003, 734-742
describe implants containing blood and a polylactic
acid derivative (Polyfibre® or Polyfoam®). Yildirim M.
et al., Clin. Oral Impl. Res., 2000, **11**, 217-219
describe implants containing bovine apatite and venous
20 blood. The document US 2008/0014279 describes a
biomaterial consisting of a granular material coated
with a polymer gel, and which may be mixed with any
sort of liquid, in particular blood, in order to form a
paste which is applied using a spatula or a syringe to
25 the site where the bone defect has to be filled in. The
document WO 02/068010 describes a composite material
containing bone marrow, this material comprising a
biocompatible and porous implantable matrix and a
coagulated material, such as a coagulate of bone
30 marrow, blood, plasma.

However, none of these implantable materials described
in the prior art is free of disadvantages:

35 Materials requiring the culture of bone marrow cells
before combining with a support (demineralized bone,
synthetic polymer or the like) take a long time to use
and require collecting bone marrow from the individual
to be treated several weeks before fitting the implant,

which multiplies the procedures and the risks associated therewith.

5 Biomaterials combining a support and noncoagulated blood do not allow an implant to be constructed.

While the combination of some support materials with coagulated blood has been proposed, the results obtained are not always satisfactory, in particular
10 because the method does not allow the production of a homogeneous biomaterial.

Such materials resulting from the combination of a support and coagulated or noncoagulated blood have up
15 until now been used in maxillofacial surgery where the problems of bone consolidation are less critical, but they have hardly or not at all been used in the repair of diaphyseal bones.

20 In the case of WO 02/068010, the method taught consists in using a support material consisting of porous demineralized bone in the form of granules having a minimum size of at least 1 mm, combined with demineralized cortical bone fibers of at least 5 mm,
25 and with a coagulated material, preferably derived from bone marrow. All the examples proposed comprise bone marrow cells.

The invention makes it possible to overcome the
30 disadvantages of the prior art, and in particular, it makes it possible to obtain an implantable biomaterial from a synthetic support, which is therefore easy to produce with constant and homogeneous properties, and coagulated blood, without the need to use culture
35 steps, this material having excellent biocompatibility, allowing rapid reconstruction of bone tissue. The invention also allows the production of a bone of excellent quality in terms of hardness and vascularization. In addition, the method for

manufacturing this biomaterial is simple, easy to carry out, does not require multiple procedures on the individual to be treated, is inexpensive compared to the prior art methods.

5

The biomaterial of the invention is in the form of a paste which comprises at least a biphasic calcium phosphate in the form of granules, substantially homogeneously mixed with coagulated blood.

10

The biphasic calcium phosphate, BCP, is used in numerous medical and dental applications. Biphasic calcium phosphate was first described as a bone repair material by Nery EB et al., J. Periodontol. 1992 Sept., **63(9)**: 729-35. BCP consists of a mixture of hydroxyapatite (HA) $\text{Ca}_{10}(\text{PO}_4)_6(\text{OH})_2$ and beta-tricalcium phosphate ($\text{Ca}_3(\text{PO}_4)_2$) (β -TCP). Its bioactivity and its bioresorbability may be controlled by the proportion of its constituent hydroxyapatite and β -TCP.

20

Biomaterials containing BCP have the advantage, compared to other synthetic biomaterials, of promoting osteogenesis.

25 BCP has been the subject of numerous studies: Fellah B.H. et al., J. Mater. Sci.: Mater. Med. (2007), **18**, 287-294, have shown that the choice of a particle size of less than 20 μm promotes the inflammatory response of tissues, which could explain the fact that this
30 particle size is particularly favorable to osteogenesis, as observed by Malard O. et al., J. Biomed. Mater. Res., **46(1)**, 1999, 103.

Mankani M.H. et al., Biotechnology and Bioengineering, **72(1)**, 2001, 96-107, have by contrast shown that
35 calibrated BCP particles having a size ranging from 100 to 250 μm were those which caused the most bone reconstruction when they are combined with cultured bone marrow cells, while no bone formation was observed

below 44 μm , and that good results are obtained with particles of up to 2 mm in size.

5 Trojani C. et al., *Biomaterials*, **27**, 2006, 3256-3264, have shown that good osteoinduction could be obtained by the implantation of a BCP/hydrogel of Si-hydroxypropylmethyl cellulose composite material to which cultured bone marrow cells have been added, with calibrated BCP particles of 40 to 80 μm .

10

The latter two methods nevertheless require a step of collecting bone marrow cells and their culture.

The present invention is based on the following facts:

- 15 - the observation by the inventors that BCP was endowed with anticoagulant properties,
- the observation by the same inventors that a BCP with a chosen particle size combined with coagulated blood, or with a coagulated bone marrow aspirate, makes
20 it possible to obtain very good osteogenesis and leads to a bone tissue of very satisfactory quality, with the aid of a method of great simplicity compared with those of the prior art.

25 The first subject of the invention is therefore the combination of a particular BCP defined below with coagulated blood or with a coagulated bone marrow aspirate. Advantageously, this combination is in the form of a malleable homogeneous paste.

30

This paste may be manipulated in order to adapt it to the size and shape of the defect to be filled in, while being careful not to apply excessive pressure to it which would damage or destroy its three-dimensional
35 structure.

The BCP used in the present invention has a particle size of between 40 and 500 μm , preferably between 40 and 400 μm , more preferably still between 40 and

300 μm , and advantageously between 80 and 200 μm .

The BCP used in the invention consists of a high-temperature sinter that is ground and calibrated, for example by sieving, as granules having a chosen diameter. Advantageously, the BCP used in the invention comprises hydroxyapatite and β -tricalcium phosphate in an HA/ β -TCP weight/weight ratio of between 5/95 and 95/5, preferably between 30/70 and 80/20, advantageously between 40/60 and 60/40.

Advantageously, this is porous BCP, with pore sizes ranging from 50 nm to 150 μm , preferably from 1 μm to 50 μm .

The granules or powder of tricalcium phosphate and hydroxyapatite may be obtained in accordance with the methods described by Bouler et al., J Biomed Mater Res, 1996, **32**, 603-609; Bouler et al., J Biomed Mater Res, 2000, **51**, 680-684; Obadia et al., J Biomed Mater Res, 2006, **80(B)**, 32-42. They are commercially available from the company GRAFTYS SARL.

If the prior art methods are applied to the BCP granulate, that is to say if BCP is mixed with a blood sample for example, blood coagulate is not obtained because BCP is endowed with anticoagulant properties. According to the method of the invention, BCP is mixed with a blood sample collected beforehand over an anticoagulant or collected without anticoagulant and brought immediately into contact with BCP in a donor compatible with the recipient of the biomaterial, and then at least one coagulating agent is added to the mixture with stirring. Preferably, the coagulating agent is a calcium derivative. Advantageously, the calcium-based coagulating agent is chosen from biocompatible calcium salts such as CaCl_2 , $\text{Ca}(\text{NO}_3)_2$, $\text{Ca}(\text{AcOEt})_2$, CaSO_4 .

Among the other coagulating agents which can be used for carrying out the invention, thrombin may be mentioned. The mixing of BCP, blood, or marrow aspirate, and coagulating agent is continued during the
5 entire coagulating step and is of an intensity suitable for allowing the formation of a homogeneous mixture of granules or particles of BCP and coagulated blood, or of coagulated marrow, and in particular the maintaining of BCP particles in suspension. If this stirring is
10 excessive or not sufficiently vigorous, it does not allow the production of a homogeneous mixture. A person skilled in the art can visually control the formation of a homogeneous mixture.

15 In addition to BCP, the composition of the biomaterial may comprise optional additives such as: polymers, ceramic particles, pharmaceutical molecules, the conditions for using these materials being: their biocompatibility, the absence of a negative effect on
20 the biomaterial setting reaction. Such additives which are well known to a person skilled in the art are intended to modify the rheology of the biomaterial, its behavior *in vivo* (hardness, resorption, osteogenesis) or to act on the appearance of infections or
25 inflammatory phenomena (antibiotics, anti-infectives, anti-inflammatory agents).

It may also be possible to envisage introducing into the biomaterial of the invention active ingredients,
30 such as therapeutic molecules, such as molecules intended to prevent or treat a pathology chosen for example from: a cancer, osteoporosis.

It is also possible to introduce natural or synthetic
35 growth factors into the biomaterial of the invention. It is also possible to envisage the presence of biomarkers or contrast agents which promote the visualization, by medical imaging, of the resorption of the biomaterial and its fate in the body.

It is possible to envisage introducing into the biomaterial of the invention adipose tissue, or any other tissue or cell preparation, collected from the
5 patient for whom the biomaterial is intended, this tissue or this preparation having been suspended beforehand in blood or in plasma or in physiological saline. Among the tissue or cell preparations, there
10 may be mentioned adipose tissue, platelets, bone marrow cells.

It is also possible to envisage the presence of BCP with a different particle size, but preferably in a small quantity, advantageously $< 5\%$ by weight/total
15 weight of BCP because it has been observed that controlling the particle size allowed better formation of bone tissue (more rapid, better quality), and good resorption.

20 According to the method of the invention, the BCP is placed in a cavity of a closed and sterile container such as the inner cavity of a syringe. Blood or bone marrow aspirate, collected beforehand from a donor compatible with the recipient, is introduced into this
25 container.

If the collected blood or bone marrow aspirate has to be stored for a period of more than a few seconds (5 to 10 seconds), it is immediately mixed after its
30 collection with an anticoagulant in order to avoid its premature coagulation. The blood from the donor may for example be collected directly in a tube containing the appropriate quantity of anticoagulant agent.

35 The anticoagulant may be a chelator of calcium ions, such as for example sodium citrate, but also heparin for example.

The mixture of BCP and blood or bone marrow is prepared

in the following preferred proportions:

from 10 to 90% by weight of BCP relative to the volume
of blood (or of bone marrow), preferably from 50 to
5 90%, and more preferably still from 60 to 80%, in g/ml.

Advantageously, the blood is collected from the
recipient themselves so as to ensure as much as
possible the biocompatibility of the implant. According
10 to one variant of the invention, the blood is replaced
by a product derived from blood, such as plasma.
Preferably, whole blood is used. In the entire
application, including the claims, when the word blood
is used, it includes in its definition blood-derived
15 products such as plasma.

Preferably, in the implementation of the invention,
blood or plasma is used whose collection does not
require a surgical procedure.

20 According to one variant of the invention, the blood
may be collected with the aid of a syringe in whose
body the BCP and optionally additives have been placed
beforehand.

25 After a first mixing of the BCP and the blood, the
coagulating agent is also added to the mixture, for
example by aspiration with the aid of the syringe if
such a device is used.

30 The closed container containing the BCP, the blood and
the coagulating agent is immediately stirred, so as to
allow the formation of a homogeneous material. For
example, if the mixture is prepared in a tube or in the
35 body of a syringe, the container is placed in a rotary
shaker whose speed is set according to the particle
size of the BCP, such that the BCP particles remain in
suspension while the coagulation occurs. According to
one variant of the invention, the stirring may be

produced by magnetic beads combined with a magnetic stirrer.

5 According to a preferred variant of the invention, the closed container containing the mixture of BCP, blood and coagulating agent is allowed to stand during the blood coagulation phase so as to allow the BCP to sediment and to form an implant saturated with BCP.

10 At the end of this step, the mixture is in the form of a homogeneous malleable paste containing a three-dimensional network of fibrin entrapping blood particles, plasma and other molecules that have been introduced into the composition.

15 According to the type of device that was used for the preparation of the biomaterial of the invention, the latter may then be applied with the aid of means which are most suited to the location where a bone defect has
20 to be filled in:

With the aid of a tool such as a spatula without however disrupting the three-dimensional organization of the implant, or with the aid of the syringe or of
25 another cylindrical device whose end would have been cut beforehand in order to form an opening suited to the rheology of the biomaterial of the invention.

Accordingly, another subject of the invention is a
30 method for the manufacture of a biomaterial, this method comprising at least the following steps:

- (i) mixing a BCP in the form of granules whose size is between 40 and 500 μm with blood, or with a
35 bone marrow aspirate, in a proportion ranging from 10 to 90% by weight of BCP per volume of blood or marrow,
- (ii) adding to the mixture of step (i) at least one coagulating agent in a sufficient quantity to cause the coagulation (of the blood or of the marrow),

(iii) mixing under conditions promoting the homogenization of the BCP while the coagulation occurs.

As has already been mentioned, in the method of the invention, steps (i) to (iii) may be carried out in the inner cavity of a syringe or in a tube closed at its ends. The coagulating agent may be chosen from calcium derivatives, such as those which were listed above, or from other coagulating agents such as thrombin for example.

The subject of the invention is also a method for filling in a bone defect, this method comprising the steps listed above and additionally comprising a step of applying the biomaterial obtained in step (iii) in the space where a bone defect has been observed. This method may additionally comprise tissue incision and suture steps.

Depending on the size and configuration of the bone defect, the filling in by the biomaterial of the invention may be associated with an osteosynthesis which makes it possible to confer on the affected tissue the mechanical strength required while the bone reconstruction is in progress at the site of implantation of the biomaterial of the invention.

As the inventors observed, the implantation of the biomaterial of the invention made it possible to induce the formation of bone tissue within a short period (a few weeks), this bone tissue being quite abundantly vascularized.

By contrast, it was observed that the implantation of a biomaterial obtained by the same method with a BCP having a particle size of less than 40 μm did not make it possible to obtain the formation of bone tissue of sufficient quality and within satisfactory periods. The implantation of a biomaterial obtained by the same

method with a BCP having a particle size greater than 500 μm leads to an implant whose resorbability is lower.

- 5 Another subject of the invention consists of a kit for carrying out the method of the invention, this kit comprising the combination of a BCP having a particle size of between 40 and 500 μm , preferably between 40 and 400 μm , advantageously between 40 and 300 μm and
10 more preferably still of 80 to 200 μm , with at least one coagulating agent. Preferably, the coagulating agent is derived from calcium. Advantageously, the coagulating agent is CaCl_2 .
- 15 The quantity of coagulating agent is calculated in order to compensate for the anticoagulant effect of BCP and optionally of the anticoagulant agent which is combined with the blood collected.
- 20 The concentration of coagulating agent in the mixture of blood and BCP should be preferably between 1 and 50 mM, more preferably still between 3 and 35 mM, in particular in the case where the coagulating agent is based on calcium. The coagulating agent should be
25 preferably added as an aqueous solution so as not to exceed 2 volumes of solution of coagulating agent by weight of BCP in ml/g.

The concentration of the solution of coagulating agent
30 may vary so as to respect these two constraints, and when using preferably a solution of coagulating agent having a concentration of less than 120 mM, in particular when the coagulating agent is a calcium salt.

35

If the blood is collected over anticoagulant, the effect of the anticoagulant agent and the effect of the biomaterial should be compensated for.

For example, for blood collected over sodium citrate under conventional conditions (of the trademark Vacurette®, available from the company Greiner Bio-One, or of the trademark Vacutainer®, available from the company Becton Dickinson) and in the proportions of 50 mg of BCP and 100 µl of blood, we add 1/5th of the final volume (that is 20 µl) of a calcium solution at 80 mM (final concentration 13.3 mM). The concentration of the solution may be up to 120 mM. Above, there may be an excess of calcium, which again inhibits the coagulation.

If the blood is not collected over an anticoagulant, the blood is collected directly over the biomaterial and the calcium is added in a second instance. In this case, it is possible to add 1/5th of the blood volume of an aqueous solution of calcium salt having a concentration ranging from 12 mM to 60 mM approximately.

20

Such a combination may be in the form of a sterile kit comprising:

- (a) a device comprising a sterile inner cavity in which the BCP is placed,
- 25 (b) a sterile reservoir containing the coagulating agent.

The reservoir (b) may be part of the device (a) or may be a separate entity such as a tube or a bottle from which the coagulating agent may be removed and transferred to the inner cavity of the device (a), or a syringe allowing the injection of the coagulating agent into the cavity where the BCP is placed.

35 Advantageously, the device (a) comprises means allowing the introduction of blood into the inner cavity: for example means allowing the collection of a blood sample either directly from an individual, or from a reservoir, or means allowing the injection of a blood

sample into the inner cavity so as to allow mixing with the BCP. It is possible to envisage that the blood collected is directly introduced into the cavity comprising the BCP or that it is collected in the reservoir where the anticoagulant is placed and then the whole is transferred into the cavity where the BCP is present. In the case where a bone marrow aspirate is used, provision is made for a means for aspiration of the bone marrow.

The inner cavity of the device (a) has a size allowing the introduction therein of the quantity of blood or marrow necessary to produce the biomaterial of the invention, as well as the other constituents of the mixture such as: coagulating agent, active ingredients, tissue or cell preparations.

Also advantageously, the device (a) comprises means allowing the application of the biomaterial in the zone where a bone defect has been observed.

Such a device may consist of a cylindrical device such as a tube or a syringe as is illustrated in the experimental section.

It is also possible to envisage using a device such as the one described in WO 02/068010 comprising a tube in which the BCP is stored, into which the blood and the coagulating agent are injected and to which a piston may be fitted so as to release the biomaterial once it has been formed.

It is also possible to envisage using a device of the Vacutainer® type, that is to say tubes under vacuum to which a syringe is fitted which makes it possible to collect a predetermined quantity of blood, these tubes being preconditioned with BCP in their inner cavity.

Another subject of the invention consists of an

implantable biomaterial comprising a BCP in the form of granules whose size has been defined above, dispersed substantially homogeneously in a three-dimensional network of blood proteins or in a network of bone marrow proteins.

Advantageously, this biomaterial comprises a BCP as defined above and a coagulate of blood (or marrow) proteins in the form of a substantially homogeneous mixture having the appearance of a malleable paste.

The expression malleable paste is understood to mean a material which itself does not flow, as would a liquid, but whose mechanical strength is sufficiently low to be able to be molded under the effect of pressure exerted manually by an individual, in particular with the aid of an instrument such as a spatula or the piston of a syringe.

Such a biomaterial may be used for the manufacture of a bone implant, whether this involves filling in a fracture, a loss of substance of trauma or tumor origin, a defect following a surgical procedure, or helping to fit a prosthesis.

The biomaterial may be introduced, as illustrated in the examples, by a surgical procedure in the zone where a bone defect needs to be filled in. After incision, the biomaterial is implanted and the incision is closed again.

The biomaterial of the invention may be combined with an osteosynthesis of greater mechanical strength, so as to allow the stability of the assembly while awaiting the colonization of the deficient zone by the bone tissues.

It is possible to envisage combining it with a prosthesis. Coating the prosthesis with the biomaterial

of the invention makes it possible to promote the implantation of living bone tissue in or around the prosthesis.

- 5 The biomaterial of the invention may also be used *in vitro* or *ex vivo* as support for the production of bone tissue:

Indeed, the culture of bone cells around this
10 biomaterial makes it possible to produce a bone tissue that can be subsequently implanted.

Another subject of the invention is the use *in vitro* or *ex vivo* of a biomaterial as described above for
15 producing a bone implant.

It is possible, according to the invention, to culture bone cells on the biomaterial of the invention in a mold having the shape of the implant which it is
20 desired to manufacture. The culture of cells under these conditions makes it possible to obtain a biocompatible implant having the appropriate shape and dimensions.

25 **EXPERIMENTAL SECTION**

Figures

Figure 1: Formation of bone tissue by an implant of coagulated blood around BCP particles.

- 30 Cross sections of implants stained with HES after 4 weeks of implantation at a subcutaneous (A and C) and intramuscular (B and D) site.

Scale: A and B: 500 μ m

35 C and D: 50 μ m

White arrows: osteoblasts

Black arrows: osteocytes

Black arrowheads: blood vessels

White arrowheads: osteoclasts

Figure 2: Section of blood/BCP implants after 4 weeks of implantation.

- 5 (A): hybridization with immune serum showing the
brown color of osteocalcin in the cytoplasm of cells
(white arrow)
 (B): hybridization with nonimmune serum - scale:
10 μ m
10 (C): Goldner stain - scale: 50 μ m
 Black arrows: vessels and osteocytes.

Figure 3: Scanning electron microscopy of 4-week-old blood/BCP implants

- 15 (A) collagen matrix in the intergranular space -
scale: 10 μ m
 (B) magnification of (A) - scale: 1 μ m
 (C) two osteoclasts attached to the granules with
2 to 3 visible nuclei - scale: 10 μ m
20 (D) functional capillary - scale: 10 μ m

Figure 4: Scanning electron microscopy of implants

- (A) BCP/coagulated blood
 (B) BCP/coagulated plasma
25 Scale: 1 μ m

Figure 5: Formation of bone tissue from BCP/plasma implants after 4 weeks of implantation

- Subcutaneous sites (A, C)
30 Intramuscular sites (B, D)
 Scale: 500 μ m (A, B)
 50 μ m (C, D)

- Figure 6: Comparison of the osteogenic properties of
35 the biomaterial prepared from blood of C57BL/6 mice (A,
B) and human blood (C, D) combined with BCP
microparticles (40-80 μ m), after subcutaneous
implantation in nude-type immunosuppressed mice.
Observation at low (A, C) and high (B, D)

magnification.

Scales: 100 μ m.

Figure 7: Influence of the size of the BCP microparticles on bone formation after subcutaneous implantation in mice. Implants were prepared from the blood of C57BL/6 mice combined with BCP in the form (A) of a large quantity of fine dust having a size of less than 40 μ m mixed with particles of 80-200 μ m; (B) of particles of 40-80 μ m; (C, D) of particles of 80-200 μ m; (E, F) of particles of 200-500 μ m. Figures D and F correspond to views at higher magnification of the implants C and E respectively. Scales 100 μ m.

Figure 8: Implants prepared from 100 μ l of C57BL/6 mouse blood and increasing quantities of microparticles of BCP 40-80 μ m: (A) 10 mg, (B) 30 mg, (C) 50 mg and (D) 70 mg. Scale: 100 μ m.

Figure 9: X-rays in dogs - implants prepared from coagulated whole blood around calibrated BCP microparticles (80-200 μ m): (A) BCP/blood with a ratio of 50%, the microparticles being maintained in suspension in the blood during the coagulation phase (method No. 1); (B) BCP at maximum concentration in the blood, the microparticles sedimenting during the coagulation (method No. 2). The white arrows indicate the presence of a radiotransparent line between the diaphyseal ends and the implant.

Figure 10: Implantation in BEAGLE dogs. Post-operative x-rays. (A) to the left, the implant consists of BCP alone. (B) to the right, it consists of the BCP/blood mixture with a maximum ratio of BCP according to method 2 of preparation of the implants.

1. Principle:

This is an instant procedure, carried out in an operating room. It consists in mixing, in the body of a

polypropylene syringe, BCP particles and autologous whole blood (50% w/v) collected over an anticoagulant that is a chelator of calcium ions. The addition of CaCl_2 makes it possible to initiate the coagulation.

5 The syringe is then placed for 10 minutes at room temperature on a rotary mixer, which makes it possible to maintain the BCP particles in suspension in the blood during the course of the coagulation. A homogeneous distribution of the particles in the

10 coagulated blood is thus obtained. The end of the syringe is then cut and the implant pushed out of the syringe with the aid of the piston and placed at the site of implantation.

15 Results obtained in animals (C57BL/6 mice):

The implantation of the biomaterial at the ectopic site (subcutaneous and intramuscular) demonstrates its osteo-inductive properties, with implants that are completely colonized by a mineralized immature bone

20 tissue that is very richly vascularized after 4 weeks.

2. Materials and methods

2.1. Particles of biphasic calcium phosphate:

The biphasic calcium phosphate (BCP) biomaterial is

25 composed of 60% hydroxyapatite (HA ; $\text{Ca}_{10}(\text{PO}_4)_6(\text{OH})_2$) and 40% tricalcium phosphate (TCP ; $\text{Ca}_3(\text{PO}_4)_2$). The calibrated BCP particles between 80 and 200 microns were supplied by the company GRAFTYS SARL (Aix-en-Provence, France). The particles were sterilized by

30 heating at 180°C for two hours.

2.2. Preparation of the implants and surgical procedure:

- Subcutaneous implantation in mice

35 The experiments were performed in accordance with the regulations of the Direction of Veterinary Services (Direction des Services Vétérinaires) and authorized by the Regional Ethics Committee for Animal Experimentation (Comité Régional d'Ethique pour

l'Expérimentation Animale (CREEA)). Whole blood is collected over sodium citrate (anticoagulation) by intracardiac puncture from anesthetized ten-week-old C57BL/6 mice. For some experiments, the plasma was
5 prepared from whole blood by centrifugation at 1800 g for 15 minutes.

Method 1: The implants are prepared by mixing 100 µl of whole blood (or plasma) with 50 mg of BCP particles in
10 a 1 ml syringe. The activation of coagulation is then obtained by adding 20 µl of a 1% CaCl₂ solution. During the period of coagulation (5 to 10 minutes), the syringe is placed on a roller of the New Brunswick tissue culture roller type, model TC-7 M1053-4005).
15 This allows a rotational movement of the syringe on itself and maintenance of the BCP particles in suspension in the clot. After cutting the end of the syringe, the implants are pushed out of the syringe by means of the piston and implanted subcutaneously (SC)
20 or intramuscularly (IM) in C57BL/6 mice.

Method 2: The implants are prepared with a maximum concentration of particles and therefore a maximum BCP/blood ratio. For that, the BCP/blood/calcium
25 mixture is maintained in a fixed position for the duration of the coagulation so as to allow the microparticles to sediment naturally in the blood. It is thought that a maximum concentration of microparticles in the coagulated blood is thus
30 obtained.

The subcutaneous implants were placed under the skin in a dorsal position and the intramuscular implants were placed in each thigh between the muscle masses after
35 dissection. At each of the sites (SC and IM), it is checked that no bleeding was induced during the implantation.

In each implantation experiment, the C57BL/6 mice are

anesthetized by inhalation of 4% isoflurane. Two SC implants and two IM implants are placed for each mouse. In some experiments, each mouse received a blood/BCP implant and a plasma/BCP implant at each site. After 4 to 8 weeks, the animals are sacrificed by inhalation of CO₂ and the implants removed for analysis.

- Implantation at a bone site in rats

The protocol which we applied in rats was approved by the regional ethics committee for animal experimentation (NCA/2007/12-06). These preliminary experiments were carried out at the central animal house (Animalerie Centrale) of the Nice faculty of medicine.

15

We used a model of loss of femoral diaphyseal, interruptive, segmental, bone substance of critical size (6 mm) combined with plate-screw osteosynthesis, a model developed in our laboratory. We operate on a single femur per rat, the loss of substance is filled in with our biomaterial, autologous whole blood/BCP (80-200 µm). The rats are monitored clinically (absence of pain, deambulation, general condition) and radiologically by photographs at D0, D7, D15, D30, D45, D60 and D90. At the end of the third month, the animals are sacrificed, the femurs are collected and, after ablation of the osteosynthesis material, the bones are fixed in formalin before being embedded in methyl methacrylate resin and histological study.

30

During the first procedures, the implants were made to the size of the bone defect, with a proportion of particles of 50% weight/volume, that is 75 mg of BCP per 150 µl of whole blood collected from the animal pre-operatively. The coagulation is initiated by the addition of 15 µl of 2% CaCl₂ and the homogenization is produced by continuous rotation until coagulation is obtained so as to maintain the BCP particles in suspension in the blood and ensure the homogeneity of

35

the biomaterial.

- *Implantation at a bone site in BEAGLE dogs*

This is a model of loss of calibrated cylindrical
5 cavitary bone substance of critical size in the region
of the lateral femoral condyles, produced on adult dogs
of the Beagle breed. For each dog, the 2 femoral
condyles were tackled. Whole blood (3.5 ml) is
collected at the beginning of the procedure, by
10 puncture in the region of the jugular vein of the
animal and is used to prepare the biomaterial.
Cylindrical bone loss of 8x10 mm is produced in the
region of each external femoral condyle and the bone
sequestra are carefully removed by washing with
15 physiological saline and aspiration.

Each animal received two implants of different
composition but prepared so as to completely fill in
the defect created, that is to say:

20 On the one hand, the biomaterial to be tested consists
of a mixture of BCP (80-200 μ m) and blood with a ratio
of 50% weight/volume or 330 mg of BCP and 660 μ l of
whole blood. The BCP particles are maintained in
25 suspension during the coagulation by rotation of the
syringe which served to prepare the mixture.

On the other hand, BCP alone is implanted, moisturized
in physiological saline, that is 660 mg, occupying the
30 same volume as the controlateral implant.

The duration of the experiment is 8 weeks.

Post-operative x-rays were taken immediately and at the
35 end of the experiment at the ENVN.

2.3. Histological analysis:

The dissected implants are fixed for 24 hours in a 10%
buffered formalin solution. Each implant is then cut

into three pieces which are decalcified or not in a 10% (w/v) ethylenediaminetetraacetic acid (EDTA) solution for 24 hours at room temperature and then embedded in paraffin. Sections of 4 μm are prepared, 5 deparaffinized, moisturized and stained with hematoxylin, erythrosin, saffron (HES). The sections are then examined by optical microscopy using a Zeiss Axioskop microscope. The photos are taken with an AxioCam HRC color camera (Zeiss, Le Pecq, France). In 10 order to quantify the surface areas occupied by the fibrillar bone, on the one hand, and by the BCP particles, on the other hand, each image of implant was subdivided into three zones having a surface area equal to 0.6 mm^2 along the median axis of the implant. In 15 each of these three zones, the area occupied by the fibrillar bone tissue was measured using the AxioVision Rel.4.6 software. This analysis was carried out for three SC implants and three IM implants. The number of vessels and osteoclasts was evaluated in these same 20 zones by counting the capillaries and the multinucleated giant cells respectively under the light microscope (100X) by two different observers. The density of osteoclasts and vessels is expressed per mm^2 in the form of a mean $\pm$ standard deviation. The 25 statistical test used is the Student's T test. The significance was defined for a p value of less than 0.05.

2.4. Goldner staining:

30 Sections of nondecalcified implants having a thickness of 7 μm were stained by the Goldner's Trichrome method which makes it possible to evaluate the mineralization of bone tissue and to distinguish the mineralized tissue (in blue/green) from the nonmineralized osteoid 35 tissue (in red). Briefly, the deparaffinized sections are rehydrated and then incubated in the presence of Weigert's hematoxylin for 20 min, rinsed with running water and differentiated in the presence of 1% acid alcohol, washed with running water for 5 min and then

rinsed with distilled water. The sections are then stained by incubating in a solution of xylydine Ponceau/acid fuchsin/azophloxin/acetic acid for 5 min, rinsed in 1% acetic acid, incubated in the presence of phosphomolybdic acid/orange G for 20 min, rinsed in 1% acetic acid, stained in the presence of light green/acetic acid for 5 minutes, washed in 1% acetic acid for 5 minutes, dried and mounted in Entellan mounting medium (Merck, Darmstadt, Germany).

10

2.5 Immunohistochemistry of murine osteocalcin

We used an immunopurified polyclonal antibody to mouse osteocalcin, directed against a synthetic peptide corresponding to amino acids 1-20 of the N-terminal end of the protein (Alexis Biochemicals, Lausanne, Switzerland). Briefly, 7 μ m sections in paraffin were deparaffinized, rehydrated in ethanol, washed in PBS and incubated for 30 minutes in the presence of 0.3% H₂O₂ in PBS. After two washes in PBS, the slides were incubated in the presence of 1.5% goat serum (blocking buffer) for 30 min. After washing in PBS, incubation in the presence of a biotin-labeled antibody to rabbit immunoglobulins and the procedure for visualization with peroxidase were performed using the ABC labeling kit (sc-2118, Santa Cruz, CA, USA). The sections were then incubated in the presence of peroxidase substrate for 10 min and the cellular nuclei stained with hematoxylin for 3 min. After dehydration, the mounting is performed in Entellan mounting fluid (Merck). The controls are produced by incubating the slides in the presence of blocking buffer.

30

2.6. Scanning electron microscopy

The implants consisting of coagulated blood/BCP or coagulated plasma/BCP, before and after four weeks of implantation, were fixed for 12 hours at 4°C in a buffered glutaraldehyde solution. The samples were then washed and incubated in the presence of 30% glycerol for 1 h and then frozen in liquid nitrogen and

35

fractured. After dehydration in the presence of increasing concentrations of ethanol, they were immersed in hexamethyldisilazane (Sigma-Aldrich, L'isle d'Abeau Chesnes, France) for 5 min and then dried at room temperature. They were then fixed on aluminum supports and then coated with a layer of gold-palladium (Polaron E5100, UK). The examination was then performed using a scanning electron microscope of the JEOL 6700F type (Japan).

10

3. Results

3.1. Macroscopic and microscopic analysis of the subcutaneous and intramuscular implants of coagulated blood/BCP.

15 The implantation of coagulated blood in the absence of BCP particles did not allow the formation of bone tissue. After four weeks, only a small quantity of fibrous tissue was found at the site of implantation.

20 Dissection and macroscopic examination of the implants of coagulated blood around BCP particles after 4 and 8 weeks made it possible to observe their firm consistency and the presence of numerous small vessels at their surface. No inflammation of the host tissue was observed.

Histological analysis of the paraffin sections of blood/BCP implants after 4 weeks of implantation revealed a complete and reproducible colonization of the entire interparticle space by immature bone tissue in close contact with the BCP both for the SC (Fig. 1A) and IM (Fig. 1B) implants. Examination at higher magnification suggests that the collagen matrix is more mature at the IM site (Fig. 1D) than at the SC site (Fig. 1C). To evaluate the quantity of fibrillar bone developed in the interparticle space, the ratio between the areas occupied by the bone tissue and the areas occupied by the BCP was calculated as described under Materials and Methods. This made it possible to show a

30
35

significant difference between the SC and IM sites with $49.63 \pm 5.08\%$ of bone tissue in the IM implants and $42 \pm 8.33\%$ in the SC implants ($n = 9$, $p = 0.035$). All these results show that the interparticle space is completely colonized in both SC and IM sites, but that the quantity of tissue developed is significantly greater in the IM implants.

At each of the sites, we observed the presence of numerous vessels within the collagenic matrix, homogeneously distributed in all the implants (Fig. 1C, D, black arrowheads). Their count revealed a significant difference between the IM and SC implants with a mean of 61.4 ± 10.2 vessels/mm² and 51.10 ± 10 /mm² respectively ($n = 9$; $p = 0.045$). We also observed numerous multinucleated giant cells attached to the BCP particles (white arrowheads). These cells are identical to those which we identified as being osteoclasts in previous work (Trojani C. et al., Biomaterials, 27, 2006, 3256-3264). Their count revealed a mean of 88.51 ± 14.60 osteoclasts/mm² in the IM implants and 93.13 ± 14.40 /mm² in the SC implants, a difference that is not statistically significant. The high resorption capacity of these cells is strongly suggested by the presence of microparticles and intercytoplasmic fragmentation crystals, by the irregularity of the contour of some BCP particles, their degradation texture with a lower and heterogeneous density. Finally, we observed the presence of cubic osteoblasts aligned at the surface of the BCP particles (Fig. 1C and insert, Fig. 5C, white arrows) and of numerous cells of the osteocyte type embedded in the collagen matrix (Fig. 1D, 2B, 3A, B black arrows). The mature osteoblast phenotype of these cells was demonstrated by the intracytoplasmic immunohistological detection of osteocalcin (Fig. 2A). Furthermore, all the implants were positive after Goldner's staining after 4 weeks of implantation, indicating that this neoformed tissue is mineralized (Fig. 2C).

Analysis of the 4-week IM implants by scanning electron microscopy made it possible to observe (Fig. 3) the microporosity of the BCP particles, the collagen matrix
5 filling the interparticle spaces, the presence of functional capillaries containing erythrocytes (Fig. 3A, D, white arrow) and osteoclasts attached to the BCP granules (Fig. 3C, black arrows). Furthermore, it confirmed the presence of star-shaped cells of the
10 osteocyte type possessing numerous extensions radiating in all directions, embedded in the collagen matrix and surrounded by a pericellular space of the osteoplast type (Fig. 3A insert, 3B).

15 The results obtained after 8 weeks of implantation did not reveal any significant difference with the 4-week implants. All the SC and IM implants are completely colonized by immature bone exhibiting the same histological characteristics.

20

3.2. Macroscopic and microscopic analysis of the SC and IM implants of coagulated plasma/BCP:

In order to analyze the respective role of the plasma and the blood cells in the bone neoformation, we
25 implanted in parallel for each mouse and at each site (SC and IM) an implant of coagulated blood/BCP and an implant of coagulated plasma/BCP.

The structure of the fibrin network of the two types of
30 implant, coagulated blood/BCP and coagulated plasma/BCP, was analyzed by scanning electron microscopy. This showed that the fibrin mesh obtained with the coagulated blood was larger than that observed with the coagulated plasma (Fig. 4A, B). As expected,
35 the red blood cells and the platelets are the predominant cells observed in the implants of coagulated blood/BCP. The preservation of their shape and their structure demonstrates good viability (Fig. 4A), which indicates that the mixture of blood and BCP

particles has no deleterious effect on the blood cells.

Dissection and macroscopic examination of the implants of coagulated plasma/BCP after 4 and 8 weeks showed
5 similar characteristics to those of the implants of coagulated blood/BCP, that is to say a firm consistency and numerous visible surface vessels (results not shown). Histological analysis after 4 weeks showed that the SC implants were all about 80% colonized (Fig. 5A)
10 by neoformed bone. Analysis of the IM implants showed complete colonization in 75% of cases (Fig. 5B) and in 25% of cases, the presence of a small central zone of more fibrous and loose tissue (result not shown). At each of the sites, the neoformed fibrillar bone tissue
15 exhibited the same characteristics as those of the tissue obtained in the implants of coagulated blood/BCP (Fig. 5C, 5D). In conclusion, these results demonstrate that the use of whole blood makes it possible to obtain complete colonization of the implants at both sites.
20 The combination of coagulated plasma and BCP particles produces an incomplete colonization.

*3.3 Macroscopic and microscopic analysis of implants composed of coagulated human blood and 40-80 μ m BCP
25 particles, after subcutaneous implantation in immunosuppressed mice.*

We analyzed the bone formation induced by the biomaterial prepared from coagulated human blood around 40-80 μ m BCP particles after implantation in nude-type
30 immunosuppressed mice. In parallel, in the same animals, we implanted the biomaterial prepared from blood from C57BL/6 mice in order to compare, in the same recipient animal, the bone formation induced by mouse blood and that produced by human blood. After 6
35 weeks of implantation, the implants were collected, fixed and the histological analysis was carried out as previously described.

Even before the histological study, we observed the

quite unusual hardness of the implants prepared from human blood while the implants of mouse blood had a more elastic consistency.

5 Histological analysis of the murine implants revealed an immature bone tissue of equivalent quality to that found during the previous experiments carried out in a syngenic system (implantation of C57BL/6 mouse blood in C57BL/6 mice). We observed a highly vascularized
10 collagenic fibrillar tissue in which bone cells, osteoblasts, osteocytes and osteoclasts can be identified (Fig. 6A, 6B).

Histological analysis of the human implants gave very
15 different results with colonization by a mature bone tissue. The bone cells are fewer, in favor of osteocytes. The supporting tissue exhibits an organization into better structured, aligned and more dense collagen fibers, having within it hematopoiesis
20 plates characterized by the presence of immature hematopoietic cells such as erythroblasts and adipocytes (Fig. 6C, 6D). The hardness of these implants upon cutting suggested that this tissue was highly mineralized. We therefore obtained a mature
25 lamellar bone tissue.

The difference in maturity of the bone tissues obtained after implantation of the human and murine bloods could result from different properties of the blood of these
30 two species, properties linked to the cellular composition and/or to the protein composition, to growth factors, to soluble factors and to the fibrin network. Experiments will be carried out to try to understand the mechanisms involved.

35

Comparison of our results with those of the literature showed that the mature bone tissue which we obtained from human blood was very similar to the one described by several groups after implantation of human

mesenchymal stromal cells (MSC) selected, amplified and differentiated *ex vivo* into osteoblasts and then combined with BCP powder and subcutaneously implanted into immunosuppressed mice.

5

All these results are therefore very promising for clinical application.

10 3.4 Influence of the particle size of BCP on bone formation

We tested 4 forms of BCP, three microparticle forms calibrated respectively between 40 and 80 μm , 80 and 200 μm and 200 and 500 μm , and a mixture of particles of 80-200 μm and of fine dust of much less than 40 μm in size, the proportion of fine dust being 40% by weight relative to the total weight of the mixture. Implants were prepared under the conditions already described, from C57BL/6 mouse blood and from each of these forms of BCP. Bone formation was analyzed after 8 weeks of subcutaneous implantation in syngenic C57BL/6 mice.

The results of figure 7 illustrate that the implants consisting of 80-200 μm microparticles very reproducibly produce the best colonization by an immature bone tissue having the characteristics already described (Fig. 7C, 7D). The presence of BCP dust (size of less than 40 μm) mixed with the 80-200 μm BCP microparticles is extremely deleterious for bone formation as shown in figure 7A. Indeed, colonization of the implants is observed which always remains strictly limited to the peripheral crown. The implants consisting of 40-80 μm grains produce good colonization but less reproducibly than the 80-200 μm implants. Indeed, inexplicably, a central colonization defect is sometimes observed as shown in figure 7B. Finally, the implants consisting of 200-500 μm grains are always colonized but by a more fibrous and loose tissue of a less satisfactory quality (Fig. 7E, 7F).

These results demonstrate that, in our biomaterial, the 80-200 μm granulosity is more favorable to bone formation at an ectopic site.

5

3.5 Determination of the optimal BCP/blood ratio for bone-reconstruction

It is possible to incorporate into our biomaterial variable quantities of BCP microparticles for the same volume of blood. The determination of the ideal ratio was an important step in its development. Several experiments for implantation at a subcutaneous site in mice, and preliminary experiments carried out at a bone site in Wistar rats and in Beagle dogs allowed us to specify the best BCP/blood ratios.

15

3.5.1. Implantation at a subcutaneous ectopic site in mice

We prepared implants consisting of a fixed quantity of blood (100 μl), a fixed quantity of CaCl_2 (10 μl) and an increasing quantity of 40-80 μm BCP microparticles: 10 mg, 30 mg, 50 mg and 70 mg, that is BCP/blood ratios of 10, 30, 50 and 70% weight/volume. The BCP particles were maintained in suspension in the blood during coagulation by rotating on a roller (method 1). These implants had equivalent sizes at the time of implantation, with respective volumes of: 112, 116, 120 and 124 μl .

25

As shown in figure 8, after 4 weeks of implantation, we observed that the final size of the implants was proportional to the initial weight of BCP incorporated, and that all the implants had an equivalent particle density. Moreover, the colonization by immature bone tissue was the same regardless of the BCP/blood ratio.

35

These results show that the homogeneous dispersion of the grains in the initial implant, obtained by rotation of the syringes during coagulation, is not maintained

over time. On the contrary, a phenomenon of packing of the particles occurs which is probably linked to the natural degradation of the fibrin gel *in vivo*. As this packing results in the same concentration of grains for a given volume, regardless of the initial ratio, it seems logical that the osteoinduction phenomenon is the same.

The experiments subsequently carried out at a bone site confirmed these results.

3.5.2. *Implantation at a bone site in rats*

We operate on a single femur per rat, the loss of substance is filled in with our biomaterial, autologous whole blood/BCP (80-200 μm). The rats are monitored clinically (absence of pain, deambulation, general condition) and radiologically by photographs at D0, D7, D15, D30, D45, D60 and D90. At the end of the third month, the animals are sacrificed, the femurs are collected and, after ablation of the osteosynthesis material, the bones are fixed in formalin before being embedded in methyl methacrylate resin and histological study.

During the first procedures, the implants were made to the size of the bone defect, with a proportion of particles of 50% weight/volume, that is 75 mg of BCP per 150 μl of whole blood collected from the animal pre-operatively. The coagulation is initiated by the addition of 15 μl of 2% CaCl_2 and the homogenization is produced by continuous rotation until coagulation is obtained so as to maintain the BCP particles in suspension in the blood and ensure the homogeneity of the biomaterial.

We observed very reproducibly and from the first x-ray photographs at D7, the appearance of a radiotransparent line between the bone surfaces and the implant (fig. 9A), reflecting an absence of cohesion between

the biomaterial and the diaphyseal sections. When the BCP is at maximum concentration in the blood, the microparticles sedimenting during the coagulation (method No. 2), a satisfactory cohesion between the biomaterial and the diaphyseal sections is observed (figure 9B).

3.5.3. Comparison of the results obtained with the two methods for preparing the implants

10 In rats (Fig. 9B) and in dogs (Fig. 10A and 10B) at a bone site, the x-ray analyses showed, with this new protocol, the absence of shrinkage of the implants on the x-rays of the front and the absence of a line on the x-rays of the side. In mice at an ectopic site, we
15 did not observe differences in the results on bone formation.

3.5.4. Discussion:

In the case of a bone implantation of a sedimented biomaterial (method 2), there is no reduction in the
20 dimensions of the implant, as we can observe on the x-rays taken on rats and dogs, and if it was correctly fitted, in close contact with the bone, it benefits from the osteoconduction and osteoinduction phenomena
25 in an optimum fashion.

Claims:

1. A method for the manufacture of a biomaterial comprising a BCP in the form of granules dispersed substantially homogeneously in a three-dimensional network of blood proteins or in a network of bone marrow proteins, this method comprising at least the following steps:
(i) mixing a biphasic calcium phosphate, or BCP, in the form of granules whose size is between 40 and 500 μm with blood, or with a bone marrow aspirate, in a proportion ranging from 10 to 90% by weight of BCP per volume of blood or marrow, in g/ml,
(ii) adding to the mixture of step (i) at least one coagulating agent in a sufficient quantity to cause the coagulation of the blood or of the marrow.
2. The method as claimed in claim 1, in which the coagulating agent based on calcium is chosen from: biocompatible calcium salts and preferably CaCl_2 .
3. The method as claimed in either of the preceding claims, in which the blood was collected beforehand from a donor compatible with the recipient for whom the biomaterial is intended.
4. The method as claimed in any one of the preceding claims, in which the blood was collected beforehand from the recipient for whom the biomaterial is intended.
5. The method as claimed in any one of the preceding claims, which further comprises the step (iii)a) in which the mixture obtained at step (ii) containing the BCP, the blood and the coagulating agent is allowed to stand during the blood coagulation phase so as to allow the BCP to sediment and to form an implant saturated with BCP.
6. The method as claimed in any one of claims 1 to 4, which

further comprises the step of

(iii)b) mixing under conditions promoting the homogenization of the BCP while the coagulation occurs.

7. The method as claimed in any one of the preceding claims, in which steps (i) to (iii)a) or (iii)b) are carried out in the inner cavity of a syringe or in a tube closed at its ends.
8. The method as claimed in any one of the preceding claims, which comprises mixing from 50 to 90% by weight of BCP relative to the volume of blood in g/ml, preferably from 60 to 80%.
9. A biomaterial obtained by the method as claimed in any one of claims 1 to 8, comprising a BCP in the form of granules having a size of between 40 and 500 μm and coagulated blood or coagulated marrow.
10. The biomaterial as claimed in claim 9, in the form of a malleable homogeneous paste.
11. The biomaterial as claimed in either of claims 9 and 10, in which the BCP granules have a size ranging from 80 to 200 μm .
12. The biomaterial as claimed in any one of claims 9 to 11, in which the BCP contains hydroxyapatite (HA) and β -tricalcium phosphate (β -TCP) in an HA/ β -TCP weight/weight ratio of between 5/95 and 95/5.
13. The biomaterial as claimed in any one of claims 9 to 12 and additionally comprising at least one additive chosen from: polymers, ceramic particles, pharmaceutical molecules, growth factors, natural or synthetic, biomarkers, contrast agents, tissue or cell preparations.

14. The biomaterial as claimed in any one of claims 9 to 13, for its use as implant in a method for filling in a bone defect.
15. A combination of a biomaterial as claimed in any one of claims 9 to 14 with an osteosynthesis.
16. A kit when used for carrying out the method as claimed in any one of claims 1 to 8, this kit comprising:
the combination of a BCP having a particle size of between 40 and 500 μm with a coagulating agent derived from calcium,
wherein the quantity of coagulating agent is calculated in order to compensate for the anticoagulant effect of BCP which is combined with the blood.
17. The kit when used as claimed in claim 16, in which the coagulating agent is CaCl_2 .
18. The kit when used as claimed in either of claims 16 and 17, which comprises:
(a) a device comprising a sterile inner cavity in which the BCP is placed,
(b) a sterile reservoir comprising the coagulating agent.
19. The kit when used as claimed in any one of claims 16 to 18, in which the device (a) comprises means allowing the introduction of blood into the inner cavity.
20. The kit when used as claimed in any one of claims 16 to 19, in which the device (a) comprises means allowing the application of the biomaterial in the zone where a bone defect has been observed.
21. The kit when used as claimed in any one of claims 16 to 20, in which the device (a) consists of a syringe.

22. The use of a biomaterial as claimed in any one of claims 9 to 15 *in vitro* or *ex vivo* as support for the production of bone tissue.
23. The use of a biomaterial as claimed in any one of claims 9 to 15 *in vitro* or *ex vivo* for producing a bone implant.