


Means for protecting technical materials

The application relates to the use of the compound 1-(2-chloro-5-pyridylmethyl)-2-cyanoiminothiazolidine (thiacloprid) as a microbicide for protecting industrial materials against attack and destruction by insects. The compound thiacloprid is known from EP-
5 A 235 725, where it is described as being suitable for protecting plants.

The present application provides the use of thiacloprid of the formula (I)



its metal salts or acid addition compounds as microbicide for protecting industrial materials against attack and destruction by insects.

- 10 The pyridine derivative may not only be present in the form of the free base but also in the form of a metal salt complex or as acid addition salt. Preferred metal salts are salts of metals of the II. to IV. main group and the I. and II. and the IV. to VII. transition group of the Periodic Table of the Elements, examples which may be mentioned being copper, zinc, manganese, magnesium, tin, iron, calcium, aluminium, lead, chromium, cobalt and nickel.
- 15 Suitable anions of the salts are those which are preferably derived from the following acids: hydrohalic acids, such as, for example, hydrochloric acid and hydrobromic acid, furthermore phosphoric acid, nitric acid and sulphuric acid.

The metal salt complexes of the pyridine derivative can be obtained in a simple manner by customary processes, for example by dissolving the metal salt in an alcohol, for example
20 ethanol, and adding it to the thiacloprid. Metal salt complexes can be isolated in a known manner, for example by filtration, and, if appropriate, be purified by recrystallization.

To prepare acid addition salts of the pyridine derivative, preference is given to using the following acids: the hydrohalic acids, such as, for example, hydrochloric acid and hydrobromic acid, in particular hydrochloric acid, furthermore phosphoric acid, nitric acid,
25 sulphuric acid, mono- and bifunctional carboxylic acids and hydroxycarboxylic acids, such as, for example, acetic acid, propionic acid, 2-ethylhexanoic acid, butyric acid, mandelic

acid, oxalic acid, succinic acid, 2-hydroxyethanedicarboxylic acid, maleic acid, fumaric acid, tartaric acid, citric acid, salicylic acid, sorbic acid, lactic acid, and also sulphonic acids, such as, for example, p-toluenesulphonic acid, p-decylphenylsulphonic acid, p-dodecylphenylsulphonic acid, 1,4-naphthalenedisulphonic acid, alkanesulphonic acids,
5 benzoic acid and optionally substituted benzoic acids.

The acid addition salts of the compounds can be obtained in a simple manner by customary methods of forming salts, for example by dissolving a compound in a suitable inert solvent and adding the acid, for example hydrochloric acid, and be isolated in a known manner, for example by filtration, and, if appropriate, be purified by washing with an inert organic
10 solvent.

Surprisingly, the compound of the formula (I) has a particularly high insecticidal activity against wood- and plastic-destroying insects, such as, for example,

A: Hymenoptera:

Sirex juvencus

15 Urocerus augur

Urocerus gigas

Urucerus gigas taignus

B: Beetles:

Anobium punctatum

20 Apate monachus

Bostrychus capucins

Chlorophores pilosus

Dendrobium pertinex

Dinoderus minutus

25 Ernobius mollis

Heterobostrychus brunneus

Hylotrupes bajulus

Lyctus africanus

Lyctus Brunneus

30 Lyctus linearis

Lyctus planicollis

- Lyctus pubescens*
Minthea rugicollis
Priobium carpini
Ptilinur pecticornis
5 *Sinoxylon spec.*
Trogoxylon aequale
Trypto dendron spec.
Xestobium rufovillosum
Xyleborus spec.
- 10 C: Termites:
Coptotermes formosanus
Cryptotermes brevis
Heterotermes indicola
Kalotermes flavicollis
15 *Mastotermes darwiniensis*
Reticulitermes flavipes
Reticulitermes lucifugus
Reticulitermes santonensis
Zootermopsis nevadensis
- 20 The amount of active compound (I) to be employed depends on the nature and the occurrence of the insects and the material to be protected. During application, the optimum amount employed can in each case be determined by test series. However, it is generally sufficient to employ from 0.00005 to 1% by weight, preferably from 0.0005 to 0.1% by weight, of the active compound (I), based on the material to be protected.
- 25 The insecticides employed in the protection of wood to date – organophosphorus esters (for example phoxim, chlorpyrifos), synthetic pyrethroids (for example permethrin, cyfluthrin, bifenthrin), IGRs (insect growth inhibitors; for example flufenoxuron, fenoxycarb), nitroimines (for example clothianidin, imidacloprid) – have at least one of the following disadvantages:
- 30 a) generally weak activity
b) activity gaps

- c) high acute toxicity
- d) poor weather persistence, for example against leaching
- e) unbalanced activity spectrum

Surprisingly, it has now been found that the active compound of the formula (I), having
5 relatively low acute toxicity, has a particularly high insecticidal activity both against wood-
destroying beetles and against wood- and plastic-destroying termites. Furthermore, it has
been found, unexpectedly, that, after highly intensive leaching tests according to the
European standard test method EN 84, the high activity is not reduced.

The active compound of the formula (I) can be used as such, in the form of concentrates or
10 in the form of generally customary formulations, such as powders, granules, solutions,
suspensions, emulsions or pastes.

The formulations mentioned can be prepared in a manner known per se, for example by
mixing the active compound of the formula (I) with at least one solvent or diluent,
emulsifier, dispersant and/or binder or fixative, water repellent, if appropriate, desiccants
15 and UV stabilizers and, if appropriate, dyes and pigments and other processing auxiliaries.

Suitable solvents or diluents are organochemical solvents or solvent mixtures and/or a
polar organic solvent or solvent mixtures and/or an oily or oil-like organochemical solvent
or solvent mixture and/or water comprising, if appropriate, an emulsifier and/or wetting
agents. Preferred for use as customary water-insoluble oily or oil-like solvents with low
20 volatility are the respective mineral oils/mineral oil-containing solvent mixtures or their
aromatic fractions. White spirit, petroleum and alkylbenzenes may be mentioned as being
preferred, and additionally spindle oil and monochloronaphthalene. The boiling ranges of
these slowly evaporating solvents (solvent mixtures) are in the range of from more than
about 170°C to at most 350°C.

25 To some extent, the slowly evaporating oily or oil-like solvents described above may be
replaced by more volatile organochemical solvents.

To prepare a composition for protecting wood, part of the solvent or solvent mixture
described above is preferably replaced by a polar organochemical solvent or solvent
mixture. Here, preference is given to using solvents which contain hydroxyl groups, ester

groups, ether groups or mixtures of these functionalities. Esters and glycol ethers may be mentioned by way of example. According to the invention, binders are to be understood as being: synthetic resins which can be diluted in water and/or dissolved, dispersed or emulsified in organochemical solvents, binding drying oils, for example those based on
5 acrylate resins, vinyl resins, polyester resins, polyurethane resins, alkyd resins, phenol resins, hydrocarbon resins, silicone resins. The binder used can be employed as a solution, an emulsion or a dispersion. Preference is given to using mixtures of alkyd resins and drying vegetable oil. Particularly preferred are alkyd resins having an oil content between 45 and 70%.

10 Some or all of the binder mentioned may be replaced by a fixative (mixture) or a plasticizer (mixture). The purpose of these additives is to prevent evaporation of the active compounds and crystallization and/or precipitation. Preferably, they replace from 0.01 to 30% of the binder (based on 100% of the binder employed).

The plasticizers are from the chemical classes of the phthalic esters, such as dibutyl
15 phthalate, dioctyl phthalate or benzyl butyl phthalate, phosphoric esters, such as tributyl phosphate, adipic esters, such as di-(2-ethylhexyl) adipate, stearates, such as butyl stearate and amyl stearate, oleates, such as butyl oleate, glycerol ethers or higher-molecular-weight glycol ethers, glycerol esters and p-toluenesulphonic esters.

Fixatives are based chemically on polyvinyl alkyl ethers such as, for example, polyvinyl
20 methyl ether, or ketones such as benzophenone and ethylenebenzophenone.

A preferred solvent or diluent is water, if appropriate in a mixture with one or more of the abovementioned solvents or diluents, emulsifiers and dispersants.

The active compound of the formula (I) or the compositions or concentrates comprising it are preferably employed for protecting wood and timber products and also plastics against
25 attack and destruction by insects, in particular in the protection of tropical wood.

In the context of the present invention, the term "wood" is meant to include solid wood, wood products and wood composites, such as, for example, round timber, cut timber, construction timber, wooden beams, railway sleepers, bridge components, jetties, wooden vehicles, boxes, pallets, containers, telephone poles, wooden fences, wood cladding,
30 windows and doors made of wood, plywood, particle board, joiners' articles, or wood

products which, quite generally, are used in the construction of houses or in joinery.

"Plastics" are to be understood as meaning, in particular, polyvinyl chloride (PVC), polystyrene, polyurethane, polyethylene, polypropylene and polyesters.

Particularly effective protection of wood can be achieved by employing industrial
5 impregnation processes, for example vacuum, double vacuum or pressure processes.

If appropriate, the active compound of the formula (I) can be employed in combination with at least one other active compound from the group of the insecticides or the fungicides, to widen the activity spectrum or to achieve particular effects, such as, for example, additional protection against wood-destroying fungi. Mixing partners preferred
10 for this purpose are, for example, the following compounds from the group of the fungicides:

sulphenamides, such as dichlofluanid, tolylfluanid, folpet, fluorfolpet;

benzimidazoles, such as carbendazim, benomyl, fuberidazole, thiabendazole or salts thereof;

15 thiocyanates, such as thiocyanatomethylthiobenzothiazole, methylene bithiocyanate;

quaternary ammonium compounds and guanidines, such as benzalkonium chloride, benzyldimethyltetradecylammonium chloride, benzyldimethyldodecylammonium chloride, dichlorobenzyldimethylalkylammonium chloride, didecyldimethylammonium chloride, dioctyldimethylammonium chloride, N-hexadecyltrimethylammonium chloride,

20 didecylmethylpoly(oxyethyl)ammonium propionate;

morpholine derivatives, such as tridemorph, fenpropimorph, azoles, such as cyproconazole, ipconazole, epoxyconazole, fluquinconazole, triadimefon, triadimenol, bitertanol, tebuconazole, propiconazole, azaconazole, hexaconazole, prochloraz, bromuconazole, metconazole, penconazole, clotimazole, climbazole, imizalil, iodine derivatives, such as
25 diiodomethyl-o-tolylsulphone, 3-iodo-2-propynyl-n-butyl carbamate, 3-iodo-2-propynyl-n-hexyl carbamate, 3-iodo-2-propynylcyclohexyl carbamate, 3-iodo-2-propynylphenyl carbamate, phenol derivatives, such as tribromophenol, tetrachlorophenol, 3-methyl-4-chlorophenol, dichlorophene, o-phenylphenol, 2-benzyl-4-chlorophenol;

isothiazolinones, such as N-methylisothiazolin-3-one, 5-chloro-N-methylisothiazolin-3-

- one, 4,5-dichloro-N-octylisothiazolin-3-one, N-octylisothiazolin-3-one, benzisothiazolinones, 4,5-trimethylene-N-methylisothiazol-3-one;
- methoxyacrylates, such as azoxystrobin, trifloxystrobin;
- pyridines, such as 1-hydroxy-2-pyridinthione (and their Na, Fe, Mn, Zn salts), tetrachloro-4-methylsulphonylpyridine;
- metal soaps, such as tin naphthenate, copper naphthenate, zinc naphthenate, tin octoate, copper octoate, zinc octoate, tin 2-ethylhexanoate, copper 2-ethylhexanoate, zinc 2-ethylhexanoate, tin oleate, copper oleate, zinc oleate, tin phosphate, copper phosphate, zinc phosphate, tin benzoate, copper benzoate, zinc benzoate;
- 10 Metal salts and oxides, such as tributyltin oxide, Cu_2O , CuO , ZnO , CuSO_4 , CuCl_2 , copper borates, copper fluorosilicates, sodium dichromate, potassium dichromate, copper hydroxycarbonate; tris-N-(cyclohexyldiazeniumdioxy)aluminium, N-(cyclohexyldiazeniumdioxy)tributyltin and potassium salts, bis-N-(cyclohexyldiazeniumdioxy)copper;
- 15 dialkyl dithiocarbamates, such as Na and Zn salts of dialkyl dithiocarbamates, tetramethylthiuram disulphide;
- nitriles, such as 2,4,5,6-tetrachloroisophthalidinitrile;
- benzothiazoles, such as 2-mercaptobenzothiazole;
- benzothiophenes, such as bethoxazin;
- 20 quinolines, such as quinoxifen, 8-hydroxyquinoline and their Cu salts;
- boron compounds, such as boric acid, boric esters, borax.

Possible insecticides which may be mentioned are;

- acetamiprid, allethrin, alpha-cypermethrin, beta-cyfluthrin, bifenthrin, bioallethrin, 4-chloro-2-(2-chloro-2-methylpropyl)-5-[(6-iodo-3-pyridinyl)methoxy]-3(2H)-pyridazinone (CAS-RN: 120955-77-3), chlorfenapyr, chlorpyrifos, clothianidin, cyfluthrin, cyhalothrin, 25 cypermethrin, deltamethrin, ethofenprox, fenoxycarb, fipronil, flufenoxuron, hexaflumuron, imidacloprid, nitenpyram, permethrin, pyriproxifen, silafluofen,

tebufenozide, thiamethoxam, tralomethrin, triflumuron.

Preference is given to active compound combinations with the following insecticides:

alpha-cypermethrin, bifenthrin, chlorfenapyr, clothianidin, cyfluthrin, cypermethrin, deltamethrin, fipronil, imidacloprid, permethrin, thiamethoxam.

- 5 Particular preference is given to active compound combinations with the following insecticides:

alpha-cypermethrin, bifenthrin, chlorfenapyr, cypermethrin, fipronil, imidacloprid, permethrin, thiamethoxam.

Particularly preferred mixing partners are:

- 10 azaconazole, cyproconazole, fluquinconazole, hexaconazole, propiconazole, tebuconazole, triadimenol, triadimefon, imazalil, prochloraz, dichlofluanid, tolylfluanid, thiabendazole, fenpropimorph, tridemorph, bethoxazin, thiocyanatomethylthiobenzothiazole, benzalkonium chloride, didecyldimethylammonium chloride, didecylmethylpoly(oxyethyl)ammonium propionate, 3-iodo-2-propynylbutyl carbamate,
15 trifloxystrobin.

Especially preferred mixing partners are:

cyproconazole, fluquinconazole, tebuconazole, triadimefon, prochloraz, tolylfluanid, bethoxazin, benzalkonium chloride, didecyldimethylammonium chloride, didecylmethylpoly(oxyethyl)ammonium propionate, 3-iodo-2-propynylbutyl carbamate.

- 20 The insecticidal compositions or concentrates used according to the invention for protecting industrial materials, in particular wood and plastics, comprise from 0.00001 to 20% by weight, preferably from 0.0001 to 5% by weight, particularly preferably from 0.001 to 1% by weight, of at least one insecticidally active compound, 50 to 100% by weight, preferably 80 to 100% by weight, particularly preferably 90 to 100% by weight and
25 very particularly preferably 98 to 100% by weight of the insecticidally active compound being the active compound of the formula (I).

The compositions according to the invention may comprise at least one further active compound from the group of the abovementioned fungicides in an amount of from 0.01 to

40% by weight, preferably from 0.05 to 25% by weight.

Using the compositions according to the invention, it is possible, in an advantageous manner, to replace the insecticidal compositions available to date by more effective compositions. They have good stability and, in an advantageous manner, a broad activity
5 spectrum.

Examples

Example 1 (composition for impregnation)

0.025% of thiacloprid, 0.6% of tebuconazole, 2.67% of alkyd resin, 96.705% of toluene

Example 2 (primer)

- 5 0.01% of thiacloprid, 0.45% of dichlofluanid, 10% of alkyd resin, 6% of Dowanol DPM,
83.54% of white spirit

Example 3 (emulsifiable concentrate)

0.5% of thiacloprid, 5% of tebuconazole, 35% of Texanol, 32% of emulsifier, 27.5% of cyclohexanone

Table 1: Comparative activity thresholds against termites (EN 117) and wood-destroying beetles (EN 46), tested according to European standard test methods

Test insect	thiacloprid	cyfluthrin	fenoxycarb
<i>Reticulitermes santonensis</i> (termite)			
EN 117 1) (without stress)			
EN 117 (with EN 84 ²)	< 1 g/m ³ < 1 g/m ³	n.t. 10 - 20 g/m ³	ineffective against termites
<i>Hylotrupes bajulus</i> (house longhorn beetle)			
EN 46 3) (without stress)	< 0.01 g/m ²	< 0.006 g/m ²	0.005 g/m ²
EN 46 (with EN 84)	< 0.01 g/m ²	< 0.006 g/m ²	0.050 g/m ²

1) EN 117 Wood preservative; determination of the activity threshold against *Reticulitermes santonensis* De Feytaud (laboratory test)


2) EN 84 Wood preservative; accelerated ageing of treated wood prior to biological testing - leaching stress

3) EN 46 Wood preservative; determination of the prophylactic effect on egg larvae of *Hylotrupes bajulus* (L.) (laboratory test)

4) EN 73 Wood preservative; accelerated ageing of treated wood prior to biological testing - evaporation stress

Patent claims

1. Use of the compound of the formula (I)



- 5 its metal salts or acid addition compounds as insecticide for protecting industrial materials against attack and/or destruction by insects.
2. Use according to Claim 1, characterized in that the industrial materials that are protected are wood, wood composites, timber products and plastics.
3. Compositions for protecting industrial materials, which compositions comprise a compound of the formula (I) according to Claim 1 or metal salts or acid addition
10 compounds thereof and at least one solvent or diluent and also, if appropriate, processing auxiliaries.
4. Compositions according to Claim 3, characterized in that they comprise at least one further antimicrobially active compound.
5. Compositions according to at least one of Claims 3 and 4, characterized in that they
15 comprise at least one further antimicrobially active compound from the group of the fungicides and insecticides.
6. Compositions according to at least one of Claims 3 to 5, characterized in that they comprise, as biocidally active compound, from 0.00001 to 20% by weight of at least one insecticide, the insecticide consisting of 50 to 100% by weight of the
20 active compound of the formula (I).
7. The use of a composition according to at least one of Claims 3 to 6 for protecting industrial materials against attack and/or destruction by insects.
8. Method for protecting wood and plastics, characterized in that the wood or the plastic is treated with a compound of the formula (I) according to Claim 1.

9. Wood and plastics, characterized in that they comprise a compound of the formula (I) according to Claim 1.