

DESCRIPTION

NONAQUEOUS ELECTROLYTE SOLUTION FOR SECONDARY BATTERY AND
NONAQUEOUS ELECTROLYTE SECONDARY BATTERY

5 Technical Field

[0001]

The present invention relates to a nonaqueous
electrolyte solution for a secondary battery and a nonaqueous
electrolyte secondary battery, and more specifically, to a
10 nonaqueous electrolyte secondary battery having good charge-
discharge characteristics and a nonaqueous electrolyte
solution for a secondary battery, the nonaqueous electrolyte
solution being used in the nonaqueous electrolyte secondary
battery.

15 Background Art

[0002]

Recently, as batteries having high energy densities,
nonaqueous electrolyte secondary batteries have attracted
attention in which metallic lithium, an alloy that can
20 occlude and release lithium ions, a carbon material, or the
like is used as a negative electrode active material and a
lithium transition metal oxide represented by a chemical
formula LiMO_2 (where M represents a transition metal),
lithium iron phosphate having an olivine structure, or the

like is used as a positive electrode material.

[0003]

As an electrolyte solution used as a nonaqueous electrolyte solution, one prepared by dissolving, as an electrolyte, a lithium salt such as LiPF_6 , LiBF_4 , or LiClO_4 in an aprotic organic solvent is usually used. Examples of the aprotic solvent that are usually used include carbonates such as propylene carbonate, ethylene carbonate, diethyl carbonate, and ethyl methyl carbonate; esters such as γ -butyrolactone and methyl acetate; and ethers such as diethoxyethane.

[0004]

Furthermore, PTL 1 and PTL 2 describe that a lithium fluorododecaborate represented by $\text{Li}_2\text{B}_{12}\text{F}_x\text{Z}_{12-x}$ (in the formula, X is an integer of 8 or more and 12 or less, and Z is H, Cl, or Br) is preferably used as an electrolyte from the viewpoint of thermal stability and overcharge characteristics.

[0005]

However, even in the batteries produced by using LiPF_6 or the lithium fluorododecaborate in the related art, battery characteristics such as cycle characteristics are insufficient. It is believed that this is because an electrolyte solution, in particular, a solvent is decomposed during charging of the battery on the negative electrode side or the positive electrode side or while the battery is left

standing with a high voltage, thereby degrading the battery.
To solve this problem, as described in NPL 1, it is believed
that it is effective to use an additive that forms an ion-
conductive protective film suitable for a negative electrode
5 surface or a positive electrode surface.

Citation List

Patent Literature

[0006]

PTL 1: Japanese Unexamined Patent Application Publication No.
10 2007-87883

PTL 2: Japanese Patent No. 4414306

Non Patent Literature

[0007]

NPL 1: GS News Technical Report, June, 2003, Vol. 62, No. 1

15 Summary of Invention

Technical Problem

[0008]

As described above, various additives, solvents, and
electrolytes have been proposed in order to improve the
20 charge-discharge efficiency of a lithium-ion battery.

However, they are not sufficient to improve charge-discharge
characteristics from low temperatures to high temperatures.

In addition, the lithium fluorododecaborate represented by
 $\text{Li}_2\text{B}_{12}\text{F}_x\text{Z}_{12-x}$ has good high-temperature characteristics and a

significant effect of suppressing the degradation due to overcharging, but does not have a sufficient effect of improving charge-discharge characteristics such as cycle characteristics.

5 [0009]

An object of the present invention is to provide a nonaqueous electrolyte solution that can improve charge-discharge characteristics of a nonaqueous electrolyte secondary battery from a low temperature to a high
10 temperature, and a nonaqueous electrolyte secondary battery including the nonaqueous electrolyte solution. An object of the present invention is to provide a nonaqueous electrolyte solution that can further significantly improve high-temperature characteristics and overcharge characteristics of
15 a nonaqueous electrolyte secondary battery, and a nonaqueous electrolyte secondary battery including the nonaqueous electrolyte solution.

Solution to Problem

[0010]

20 The present invention that achieves the above objects is summarized as [1] to [8] below.

[1] A nonaqueous electrolyte solution for a secondary battery, the nonaqueous electrolyte solution containing an electrolyte, a solvent, and an additive,

in which the additive contains a compound represented by formula (1) below:

[0011]

[Chem. 1]



[0012]

(in the formula (1), R^1 and R^2 are each independently a hydrogen atom, a methyl group, or an amino group, n is 1, 2, or 4, when n is 1, Y is a hydrogen atom or a monovalent organic group, when n is 2, Y is a divalent organic group, and when n is 4, Y is a tetravalent organic group), and

10

the content of the compound is 0.05 to 10 parts by mass relative to 100 parts by mass of the total of the solvent.

[2] The nonaqueous electrolyte solution for a secondary

15 battery according to [1] above, in which the compound represented by the formula (1) is at least one selected from the group consisting of 1,1-bis(acryloyloxymethyl)ethyl isocyanate, N,N'-bis(acryloyloxyethyl)urea, 2,2-bis(acryloyloxymethyl)ethyl isocyanate diethylene oxide, 2,2-

20 bis(acryloyloxymethyl)ethyl isocyanate triethylene oxide, tetrakis(acryloyloxymethyl)urea, 2-acryloyloxyethyl isocyanate, methyl crotonate, ethyl crotonate, methyl aminocrotonate, ethyl aminocrotonate, and vinyl crotonate.

[3] The nonaqueous electrolyte solution for a secondary battery according to [1] or [2] above, in which the electrolyte contains a lithium fluorododecaborate represented by a formula $\text{Li}_2\text{B}_{12}\text{F}_x\text{Z}_{12-x}$ (in the formula, X is an integer of 8 to 12, and Z is H, Cl, or Br) and at least one selected from LiPF_6 and LiBF_4 , the concentration of the lithium fluorododecaborate is 0.2 mol/L or more relative to the total of the electrolyte solution, and the total concentration of the at least one selected from LiPF_6 and LiBF_4 is 0.05 mol/L or more relative to the total of the electrolyte solution.

[4] The nonaqueous electrolyte solution for a secondary battery according to [3] above, in which a ratio (A:B) of the content A of the lithium fluorododecaborate to the content B of the at least one selected from LiPF_6 and LiBF_4 is 90:10 to 50:50 in terms of molar ratio.

[5] The nonaqueous electrolyte solution for a secondary battery according to [3] or [4] above, in which the total molar concentration of the lithium fluorododecaborate and the at least one selected from LiPF_6 and LiBF_4 is 0.3 to 1.5 mol/L relative to the total of the electrolyte solution.

[6] The nonaqueous electrolyte solution for a secondary battery according to any one of [3] to [5] above, in which X in the formula $\text{Li}_2\text{B}_{12}\text{F}_x\text{Z}_{12-x}$ is 12.

[7] The nonaqueous electrolyte solution for a secondary

battery according to any one of [1] to [6] above, in which the solvent contains at least one selected from the group consisting of cyclic carbonates and chain carbonates.

[8] A nonaqueous electrolyte secondary battery including a positive electrode, a negative electrode, and the nonaqueous electrolyte solution for a secondary battery according to any one of [1] to [7] above.

Advantageous Effects of Invention

[0013]

10 The nonaqueous electrolyte solution of the present invention contains the additive in a predetermined amount. Thus, charge-discharge characteristics of a nonaqueous electrolyte secondary battery can be significantly improved.

[0014]

15 Furthermore, the nonaqueous electrolyte solution of the present invention contains a predetermined amount of lithium fluorododecaborate represented by $\text{Li}_2\text{B}_{12}\text{F}_x\text{Z}_{12-x}$ (in the formula, X is an integer of 8 or more and 12 or less, and Z is H, Cl, or Br). Thus, charge-discharge characteristics of a
20 nonaqueous electrolyte secondary battery can be significantly improved.

[0015]

That is, the nonaqueous electrolyte solution of the present invention can improve thermal stability of a

nonaqueous electrolyte secondary battery at high temperatures,
a charge-discharge performance of the nonaqueous electrolyte
secondary battery at low temperatures, and rate
characteristics of the nonaqueous electrolyte secondary
5 battery at room temperature. In addition, in the nonaqueous
electrolyte solution of the present invention, in the case of
overcharging, a redox shuttle mechanism acts, and
decomposition of the electrolyte solution and decomposition
of a positive electrode can be prevented. As a result,
10 degradation of the nonaqueous electrolyte secondary battery
can be prevented.

Brief Description of Drawings

[0016]

[Fig. 1] Fig. 1 is a graph showing cycle test results (a) of
15 a nonaqueous electrolyte secondary battery of Example 1 and
cycle test results (b) of a nonaqueous electrolyte secondary
battery of Comparative Example 1 at 25°C.

[Fig. 2] Fig. 2 is a graph showing cycle test results (a) of
a nonaqueous electrolyte secondary battery of Example 1 and
20 cycle test results (b) of a nonaqueous electrolyte secondary
battery of Comparative Example 1 at 60°C.

[Fig. 3] Fig. 3 is a graph showing cycle test results (a) of
a nonaqueous electrolyte secondary battery of Example 1 and
cycle test results (b) of a nonaqueous electrolyte secondary

battery of Comparative Example 1 at -10°C.

Description of Embodiments

[0017]

< Nonaqueous electrolyte solution for secondary battery>

5 A nonaqueous electrolyte solution for a secondary battery according to the present invention includes an electrolyte, a solvent, and an additive.

[0018]

<Additive>

10 In the present invention, an "additive" is incorporated in an amount of 10 parts by mass or less per additive when the total of the solvent contained in the electrolyte solution of the present invention is assumed to be 100 parts by mass. Furthermore, if a small amount of a solvent
15 component is present in the solvent and the amount of solvent component contained in the small amount is less than 10 parts by mass relative to 100 parts by mass of the total amount of the solvent except for the small amount of the solvent component, the small amount of solvent component is
20 considered to be an additive and is eliminated from the solvent. Herein, in the case where two or more solvent components are present in small amounts and a small amount of certain solvent component (i) is considered to be an additive on the basis of the above definition, a solvent component

contained in an amount equal to or smaller than the amount of the solvent component (i) is also considered to be an additive.

[0019]

5 The additive in the nonaqueous electrolyte solution for a secondary battery of the present invention contains a compound represented by formula (1) below.

[0020]

[Chem. 1]



[0021]

(In the formula (1), R^1 and R^2 are each independently a hydrogen atom, a methyl group, or an amino group, n is 1, 2, or 4, when n is 1, Y is a hydrogen atom or a monovalent
15 organic group, when n is 2, Y is a divalent organic group, and when n is 4, Y is a tetravalent organic group.)

Since the additive is the compound represented by the formula (1), in a second battery including the nonaqueous electrolyte solution for a secondary battery of the present
20 invention, a part of this additive is decomposed by reduction on a negative electrode at the time of initial charging, thereby forming a suitable ion-conductive protective coating film on a surface of the negative electrode. As a result,

charge-discharge characteristics from a low temperature of about -25°C to a high temperature of about 60°C are improved.

[0022]

In the formula (1), when n is 1, Y is a hydrogen atom or
5 a monovalent organic group. Examples of the monovalent organic group include an allyl group, alkyl groups each having 1 to 6 carbon atoms, an isocyanate group, an amino group, an imide group, an amide group, a vinyl group, a benzoyl group, an acyl group, an anthraniloyl group, and a
10 glycoloyl group. The monovalent organic group may be a group formed by replacing a hydrogen atom of an alkyl group having 1 to 6 carbon atoms with a group other than the alkyl group having 1 to 6 carbon atoms.

[0023]

15 When n is 2, Y is a divalent organic group. Examples of the divalent organic group include a phenylene group, alkylene groups, polymethylene groups, a urea group, and a malonyl group. The divalent organic group may be a group formed by replacing a hydrogen atom of an alkylene group or a
20 polymethylene group with a group other than an alkyl group having 1 to 6 carbon atoms, the alkyl group being exemplified as the monovalent organic group.

[0024]

When n is 4, Y is a tetravalent organic group. Examples

of the tetravalent organic group include groups formed by removing four hydrogen atoms from an aliphatic hydrocarbon, benzene, or urea. The tetravalent organic group may be a group formed by replacing a hydrogen atom of a group formed by removing four hydrogen atoms from an aliphatic hydrocarbon with a group other than an alkyl group having 1 to 6 carbon atoms, the alkyl group being exemplified as the monovalent organic group.

[0025]


The additive in the nonaqueous electrolyte solution for a secondary battery of the present invention may be one compound represented by the formula (1) or may include two or more compounds each represented by the formula (1).

[0026]

Specific examples of the compound represented by the formula (1) include 1,1-bis(acryloyloxymethyl)ethyl isocyanate, which is represented by chemical formula (2) below, N,N'-bis(acryloyloxyethyl)urea, 2,2-bis(acryloyloxymethyl)ethyl isocyanate diethylene oxide, 2,2-bis(acryloyloxymethyl)ethyl isocyanate triethylene oxide, tetrakis(acryloyloxymethyl)urea, 2-acryloyloxyethyl isocyanate, methyl crotonate, ethyl crotonate, methyl aminocrotonate, ethyl aminocrotonate, and vinyl crotonate.

[0027]

[Chem. 2]



(2)

[0028]

A nonaqueous electrolyte solution for a secondary
5 battery, the nonaqueous electrolyte solution containing any
of these compounds as an additive, can significantly improve
charge-discharge characteristics of a second battery from a
low temperature to a high temperature of about 60°C.

[0029]

10 The content of the compound represented by the formula
(1) in the nonaqueous electrolyte solution for a secondary
battery of the present invention is 0.05 to 10 parts by mass,
preferably 0.5 to 8 parts by mass, and more preferably 1 to 5
parts by mass relative to 100 parts by mass of the total of
15 the solvent contained in the nonaqueous electrolyte solution
for a secondary battery. When the content of the compound
represented by the formula (1) is within the above range, a
suitable ion-conductive protective coating film can be formed
on a surface of the negative electrode. As a result, charge-

discharge characteristics from a low temperature to a high temperature can be improved in the second battery. When the content of the compound represented by the formula (1) is lower than 0.05 parts by mass, the protective coating film is not sufficiently formed on the negative electrode, and sufficient charge-discharge characteristics from a low temperature to a high temperature may not be obtained in the second battery. When the content of the compound represented by the formula (1) is higher than 10 parts by mass, the reaction on the negative electrode excessively proceeds, the thickness of the coating film formed on the surface of the negative electrode increases, and the reaction resistance of the negative electrode increases. As a result, a decrease in the discharge capacity of the battery and a decrease in charge-discharge characteristics such as a cycle performance may be caused.

[0030]

The nonaqueous electrolyte solution for a secondary battery of the present invention may contain, besides the compound represented by the formula (1), other additives according to a desired use within a range that does not impair the effects of the present invention. Examples of the other additives include vinylene carbonate, 4,5-dimethylvinylene carbonate, 4,5-diethylvinylene carbonate,

4,5-dipropylvinylene carbonate, 4-ethyl-5-methylvinylene carbonate, 4-ethyl-5-propylvinylene carbonate, 4-methyl-5-propylvinylene carbonate, vinyl ethylene carbonate, divinyl ethylene carbonate, methyl difluoroacetate, 1,3-propane sultone, 1,4-butane sultone, monofluoroethylene carbonate, and lithium-bisoxalate borate. These other additives may be used alone or in a mixture of two or more additives.

[0031]

Among these other additives, 1,3-propane sultone is particularly preferable in the case where this additive is added as a mixture with the additive represented by the formula (1). By using 1,3-propane sultone, the charge-discharge characteristics of a secondary battery in a wide temperature range from a low temperature to a high temperature can be easily improved.

[0032]

In the case where these other additives are used, from the viewpoint of forming a good coating film, the content of each of the other additives is preferably 5 parts by mass or less, and more preferably 2 parts by mass or less relative to 100 parts by mass of the total of the solvent. In addition, from the viewpoint of forming a good coating film, preferably, the content of the other additives does not exceed the content of the additive represented by the formula (1).

[0033]

Considering that a coating film having good conductivity is formed, the total amount of additives added is preferably 0.5 to 15 parts by mass, and more preferably 1 to 10 parts by mass relative to 100 parts by mass of the total of the solvent. When the total amount of additives added is smaller than 0.5 parts by mass, a coating film is not sufficiently formed on the negative electrode. As a result, sufficient charge-discharge characteristics may not be obtained. When the total amount of additives added is larger than 15 parts by mass, the thickness of the coating film formed on the surface of the negative electrode increases, and the reaction resistance of the negative electrode increases, which may result in a decrease in charge-discharge characteristics.

15 [0034]

<Electrolyte>

The electrolyte is not particularly limited, but preferably includes at least one selected from a lithium fluorododecaborate represented by a formula $\text{Li}_2\text{B}_{12}\text{F}_x\text{Z}_{12-x}$ (in the formula, X is an integer of 8 to 12, and Z is H, Cl, or Br), LiPF_6 and LiBF_4 . It is more preferable to contain both the lithium fluorododecaborate and at least one selected from LiPF_6 and LiBF_4 .

[0035]

By using the lithium fluorododecaborate as an electrolyte, battery characteristics such as high-temperature heat resistance, in particular, the charge-discharge efficiency at 45°C or higher, 60°C or higher, and furthermore, 80°C or higher and the cycle life can be markedly improved as compared with the case where LiPF_6 is used alone. In addition, even in the case of overcharging, not only an increase in the voltage is suppressed and decomposition of a solvent and an electrode is prevented but also the formation of dendrite of lithium can be suppressed by a redox shuttle mechanism due to an anion of the lithium fluorododecaborate. Thus, degradation of the battery and thermal runaway caused by the overcharging can be prevented.

[0036]

Furthermore, by adding at least one electrolyte salt selected from LiPF_6 and LiBF_4 as a mixed electrolyte, not only the electrical conductivity can be improved but also dissolution of aluminum can be suppressed when aluminum is used as a current collector of a positive electrode.

[0037]

Whether the lithium fluorododecaborate is used as the electrolyte alone, at least one selected from LiPF_6 and LiBF_4 is used as the electrolyte alone, or both the lithium fluorododecaborate and at least one selected from LiPF_6 and

LiBF₄ are used as the electrolyte in the form of a mixture is determined depending on the use of the battery and is not particularly limited. That is, the additive described above can be used in an electrolyte solution containing, as an electrolyte, only at least one selected from LiPF₆ and LiBF₄, an electrolyte solution containing, as an electrolyte, only the lithium fluorododecaborate, and an electrolyte solution containing, as an electrolyte, the lithium fluorododecaborate and at least one selected from LiPF₆ and LiBF₄. However, in the case where the prevention of overcharging is aimed, the incorporation of the lithium fluorododecaborate is essential.

[0038]

Specific examples of the lithium fluorododecaborate include Li₂B₁₂F₉H₄, Li₂B₁₂F₉H₃, Li₂B₁₂F₁₀H₂, Li₂B₁₂F₁₁H, Li₂B₁₂F₁₂, mixtures of lithium fluorododecaborates each represented by the above formula where the average of x is 9 to 10, Li₂B₁₂F_xCl_{12-x} (in the formula, x is 10 or 11), and Li₂B₁₂F_xBr_{12-x} (in the formula, x is 10 or 11).

[0039]

Herein, X in Li₂B₁₂F_xZ_{12-x} is an integer of 8 to 12. When X is less than 8, the electric potential that causes a redox reaction is excessively low, and thus the reaction occurs during a so-called usual operation of a lithium-ion battery, which may result in a decrease in the charge-discharge

efficiency of the battery. Accordingly, it is necessary to select the numerical value of X in the range of 8 to 12 in accordance with the type of electrode used and the use of the battery. In general, a lithium fluorododecaborate where X in the formula is 12 is easily produced and has a high electric potential that causes a redox reaction. However, the type of lithium fluorododecaborate used cannot be simply determined because the characteristics of the lithium fluorododecaborate are affected by the type of solvent and the like. The lithium fluorododecaborate where X in the formula is 12 is preferable from the viewpoint that the electric potential that causes a redox reaction is higher than those of other compounds, the redox reaction does not easily occur in a usual operation of the battery, and thus the redox shuttle mechanism easily effectively acts only in the case of overcharging.

[0040]

The concentration of the lithium fluorododecaborate is preferably 0.2 mol/L or more, and more preferably 0.3 mol/L or more and 1.0 mol/L or less relative to the total of the electrolyte solution.

[0041]

When the amount of lithium fluorododecaborate is excessively small, the electrical conductivity is excessively

low and the resistance in charging and discharging of the battery is increased, which may result in a degradation of rate characteristics and the like. Furthermore, the action of the redox shuttle mechanism in the case of overcharging may become insufficient. On the other hand, when the amount of lithium fluorododecaborate is excessively large, the viscosity of the electrolyte solution increases and the electrical conductivity decreases, which may result in a decrease in the charge-discharge performance such as rate characteristics.

[0042]

"At least one selected from LiPF_6 and LiBF_4 " may be any of only LiPF_6 , only LiBF_4 , and LiPF_6 and LiBF_4 . In the case where at least one of LiPF_6 and LiBF_4 is used in combination with the lithium fluorododecaborate, in general, LiPF_6 , which has a high electrical conductivity, is preferably used. However, the type of mixed electrolyte selected from LiPF_6 and LiBF_4 cannot be simply determined because there are effects of the affinity of the mixed electrolyte with other additives etc., the specification of the battery, and the like.

[0043]

The concentration of at least one selected from LiPF_6 and LiBF_4 is preferably 0.05 mol/L or more, and more preferably

0.075 mol/L or more and 0.4 mol/L or less relative to the total of the electrolyte solution.

[0044]

When the amount of at least one selected from LiPF_6 and LiBF_4 is excessively small, a sufficient protective film is not formed on an aluminum current collector and good charge-discharge characteristics may not be obtained. Furthermore, the electrical conductivity of the electrolyte solution is also insufficient, and good charge-discharge characteristics may not be obtained.

[0045]

In the case where both the lithium fluorododecaborate and at least one selected from LiPF_6 and LiBF_4 are used as an electrolyte, a ratio (A:B) of the content A of the lithium fluorododecaborate to the content B of the at least one selected from LiPF_6 and LiBF_4 is preferably 90:10 to 50:50, and more preferably 85:15 to 60:40 in terms of molar ratio.

[0046]

The total molar concentration of the lithium fluorododecaborate and the at least one selected from LiPF_6 and LiBF_4 is preferably 0.3 to 1.5 mol/L, and more preferably 0.4 to 1.0 mol/L relative to the total of the electrolyte solution. When the total molar concentration is within the above range, a good overcharge-preventing effect and good

charge-discharge characteristics can be obtained.

[0047]

In the case where both the lithium fluorododecaborate and at least one selected from LiPF_6 and LiBF_4 are used as an electrolyte, the molar concentration of the at least one selected from LiPF_6 and LiBF_4 is preferably equal to or lower than the molar concentration of the lithium fluorododecaborate. When the molar concentration of the at least one selected from LiPF_6 and LiBF_4 is higher than the molar concentration of the lithium fluorododecaborate, heat resistance at a high temperature of 45°C or higher and charge-discharge characteristics may be decreased, and furthermore, degradation of the battery due to overcharging may not be sufficiently prevented.

15 [0048]

<Solvent>

Examples of the solvent include, but are not particularly limited to, cyclic carbonates such as ethylene carbonate, propylene carbonate, and butylene carbonate; chain carbonates such as diethyl carbonate, dimethyl carbonate, methyl ethyl carbonate, methyl propyl carbonate, ethyl propyl carbonate, and dipropyl carbonate; and fluorine-substituted cyclic or chain carbonates, such as trifluoropropylene carbonate, bis(trifluoroethyl) carbonate, and trifluoroethyl

methy1 carbonate, in which some of hydrogen atoms are substituted with fluorine atoms. These solvents may be used alone or in a mixture of two or more solvents. The solvent preferably contains at least one selected from the group
5 consisting of cyclic carbonates and chain carbonates from the viewpoint that good electrochemical stability and good electrical conductivity can be obtained. In order to obtain a good battery performance even over a wide temperature range from a low temperature to a high temperature, a mixed solvent
10 containing two or more solvents is preferably used.

[0049]

From the viewpoint of improving the battery performance, solvents such as dimethoxyethane, diglyme, triglyme, polyethylene glycol, γ -butyrolactone, sulfolane, methyl
15 acetate, ethyl acetate, propyl acetate, methyl propionate, ethyl propionate, tetrahydrofuran, 2-methyltetrahydrofuran, 1,4-dioxane, and acetonitrile may be used as solvents other than the carbonates mentioned above. However, the solvents are not particularly limited thereto.

20 [0050]

<Nonaqueous electrolyte secondary battery>

A nonaqueous electrolyte secondary battery of the present invention includes a positive electrode, a negative electrode, and the above-described nonaqueous electrolyte

solution for a secondary battery. Since the nonaqueous electrolyte secondary battery of the present invention includes the nonaqueous electrolyte solution for a secondary battery of the present invention, the nonaqueous electrolyte secondary battery exhibits good charge-discharge characteristics.

[0051]

The structure and the like of the nonaqueous electrolyte secondary battery are not particularly limited, and may be appropriately selected in accordance with a desired use. The nonaqueous electrolyte secondary battery of the present invention may further include, for example, a separator composed of polyethylene or the like.

[0052]

The negative electrode used in the present invention is not particularly limited and may contain a current collector, a conductive material, a negative electrode active material, a binder, and/or a thickener.

[0053]

As the negative electrode active material, any material that can occlude and release lithium can be used without particular limitation. Typical examples thereof include non-graphitized carbon, artificial graphite carbon, natural graphite carbon, metallic lithium, aluminum, lead, silicon,

alloys of lithium with tin or the like, tin oxide, and titanium oxide. Any of these negative electrode active materials is kneaded with a binder such as polytetrafluoroethylene (PTFE), polyvinylidene fluoride

5 (PVdF), or styrene-butadiene rubber (SBR) in accordance with a usual method, and the kneaded product can be used as a mixture. The negative electrode can be prepared by using this mixture and a current collector such as a copper foil.

[0054]

10 The positive electrode used in the present invention is not particularly limited and preferably contains a current collector, a conductive material, a positive electrode active material, a binder, and/or a thickener.

[0055]

15 Typical examples of the positive electrode active material include lithium composite oxides with a transition metal such as cobalt, manganese, or nickel; and lithium composite oxides obtained by replacing a part of the lithium site or the transition metal site of any of the above lithium
20 composite oxides with cobalt, nickel, manganese, aluminum, boron, magnesium, iron, copper, or the like. Furthermore, for example, lithium transition metal phosphates having an olivine structure can also be used. Any of these positive electrode active materials is kneaded with a conductive agent

such as acetylene black or carbon black and a binder such as polytetrafluoroethylene (PTFE) or polyvinylidene fluoride (PVdF), and the kneaded product can be used as a mixture.

The positive electrode can be prepared by using this mixture

5 and a current collector such as an aluminum foil.

EXAMPLES

[0056]

The present invention will now be described in more detail on the basis of Examples. However, the present
10 invention is not limited by the Examples below and can be carried out by making appropriate changes as long as the gist of the present invention is not changed.

[0057]

(Preparation 1 of lithium fluorododecaborate)

15 [Preparation of $\text{Li}_2\text{B}_{12}\text{F}_x\text{H}_{12-x}$ (X is 10 to 12)]

First, 100% F_2 (142 mmol) was added as a mixed gas of 10% F_2 /10% O_2 /80% N_2 at 0°C to 20°C to a colorless slurry containing 2.96 g (11.8 mmol) of $\text{K}_2\text{B}_{12}\text{H}_{12}\text{CH}_3\text{OH}$ in 6 mL of formic acid at an average Hammett acidity of $\text{H}_0 = -2$ to -4 ,
20 thus preparing a colorless solution. The above mixed gas was added to this solution at 30°C to further conduct fluorination (3%). A solid was precipitated from the solution. The solvent was evacuated for one night to prepare 5.1 g of a colorless, brittle solid. This crude product was

analyzed by ^{19}F NMR. According to the results, it was found that the crude product was mainly composed of $\text{B}_{12}\text{F}_{10}\text{H}_2^{2-}$ (60%), $\text{B}_{12}\text{F}_{11}\text{H}^{2-}$ (35%), and $\text{B}_{12}\text{F}_{12}^{2-}$ (5%). The crude reaction product was dissolved in water, and the pH of the solution was
5 adjusted to 4 to 6 with triethylamine and trimethylamine hydrochloride. The precipitated product was filtered and dried. The dried product was again suspended in water to prepare a slurry. Two equivalents of lithium hydroxide monohydrate were added to this slurry, and triethylamine was
10 removed. After the triethylamine was completely removed by distillation, lithium hydroxide was further added thereto, and the pH of the final solution was adjusted to 9.5. Water was removed by distillation, and the final product was dried under vacuum at 200°C for six hours. The yield of $\text{Li}_2\text{B}_{12}\text{F}_x\text{H}_{12-x}$
15 ($x = 10, 11, \text{ or } 12$) was about 75%.

[0058]

(Preparation 2 of lithium fluorododecaborate)

[Preparation of $\text{Li}_2\text{B}_{12}\text{F}_x\text{Br}_{12-x}$ ($x \geq 10$, average $x = 11$)]

Three grams (0.008 mol) of $\text{Li}_2\text{B}_{12}\text{F}_x\text{H}_{12-x}$ ($x \geq 10$) having an
20 average composition of $\text{Li}_2\text{B}_{12}\text{F}_{11}\text{H}$ was dissolved in 160 mL of 1 M HCl. Next, 1.4 mL (0.027 mol) of Br_2 was added to this solution, and the resulting liquid mixture was refluxed at 100°C for four hours. A sample was taken for the purpose of NMR analysis.

[0059]

A part of the sample was returned to the reflux, and chlorine was added thereto over a period of six hours to form a brominating agent BrCl . At the time when the addition of chlorine was completed, a sample was taken and analyzed by NMR. The result showed that the sample had the same composition as the composition before the addition of chlorine. Water and HCl were removed by distillation, and the resulting product was dried under vacuum at 150°C . A total 2.55 g of a white solid product was isolated. The theoretical amount of the obtained $\text{Li}_2\text{B}_{12}\text{F}_x\text{Br}_{12-x}$ ($x \geq 10$, average $x = 11$) is 3.66 g.

[0060]

(Preparation 3 of lithium fluorododecaborate)

15 [Preparation of $\text{Li}_2\text{B}_{12}\text{F}_x\text{Cl}_{12-x}$ (average $x = 11$)]

Twenty grams of a mixture of $\text{Li}_2\text{B}_{12}\text{F}_x\text{H}_{12-x}$ having an average composition of $\text{Li}_2\text{B}_{12}\text{F}_{11}\text{H}$ was dissolved in 160 mL of 1M HCl in a three-necked round-bottom flask equipped with a reflux condenser and a glass bubbler (fritted bubbler). The resulting liquid mixture was heated to 100°C and bubbled with Cl_2 gas at 15 standard cubic centimeters per minute (sccm/min). A discharged solution passing through the condenser was allowed to pass through a solution containing KOH and Na_2SO_3 . Bubbling was performed with Cl_2 for 16 hours

and the solution was then purged with air. Water and HCl were removed by distillation, and the residue was titrated with an ether. The ether was evaporated, and a white solid was dried in a vacuum dryer. Thus, 20 g of a substance
5 represented by $\text{Li}_2\text{B}_{12}\text{F}_x\text{Cl}_{12-x}$ (average $x = 11$) was recovered (yield 92%). ^{19}F -NMR in D_2O : -260.5, 0.035F; -262.0, 0.082F; -263.0, 0.022F; -264.5, 0.344F; -265.5, 0.066F; -267.0, 0.308F; -268.0, 0.022F; -269.5, 1.0F. ^{11}B -NMR in D_2O : -16.841; -17.878.

10 [0061]

[EXAMPLE 1]

(Battery evaluation 1)

[Preparation of electrolyte solution]

Lithium hexafluorophosphate (LiPF_6) was used as an
15 electrolyte. A solvent composed of a mixture containing 10% by volume of ethylene carbonate, 20% by volume of propylene carbonate, 40% by volume of methyl ethyl carbonate, and 30% by volume of diethyl carbonate was used. Lithium hexafluorophosphate (LiPF_6) was dissolved in this solvent so
20 as to have a concentration of 1.1 mol/L. Furthermore, as an additive for forming an ion-conductive coating film on an electrode, 1.5 parts by mass of 1,1-bis(acryloyloxymethyl)ethyl isocyanate was added relative to 100 parts by mass of the total of the solvent. Thus, an

electrolyte solution was prepared.

[0062]

[Preparation of positive electrode]

First, $\text{LiCo}_{1/3}\text{Ni}_{1/3}\text{Mn}_{1/3}\text{O}_2$ functioning as a positive

5 electrode active material, a carbon material functioning as a
conductive agent, and an N-methyl-2-pyrrolidone solution in
which polyvinylidene fluoride functioning as a binder was
dissolved were mixed so that a mass ratio of the active
material, the conductive agent, and the binder was 95:2.5:2.5.
10 The mixture was then kneaded to prepare a positive electrode
slurry. The prepared slurry was applied onto an aluminum
foil functioning as a current collector, and then dried. The
resulting aluminum foil was then rolled with a rolling mill,
and a current collector tab was attached thereto. Thus, a
15 positive electrode was prepared.

[0063]

[Preparation of negative electrode]

Artificial graphite functioning as a negative electrode
active material, an SBR functioning as a binder, and

20 carboxymethyl cellulose functioning as a thickener were mixed
with water so that a mass ratio of the active material, the
binder, and the thickener was 97.5:1.5:1. The mixture was
then kneaded to prepare a negative electrode slurry. The
prepared slurry was applied onto a copper foil functioning as

a current collector, and then dried. The resulting copper foil was then rolled with a rolling mill, and a current collector tab was attached thereto. Thus, a negative electrode was prepared.

5 [0064]

[Preparation of battery]

The positive electrode and negative electrode prepared as described above were made to face each other with a polyethylene separator therebetween, and put in an aluminum
10 laminated container. In a glove box in an Ar (argon) atmosphere, the electrolyte solution prepared as described above was added dropwise to the container including the electrodes therein, and the laminated container was thermo-compression bonded while the pressure was removed. Thus, a
15 battery was prepared.

[0065]

[Evaluation of battery]

The battery prepared as described above was slowly charged up to 4.2 V at 0.05C (a current at which full
20 charging or full discharging is performed in 1/0.05 hours (= 20 hours)) and then slowly discharged down to 3.0 V, and the charging and discharging operation was then performed once more. Thus, aging was performed.

[0066]

Subsequently, constant-current charging was conducted up to 4.2 V at 25°C at 1C. When the voltage reached 4.2 V, the battery was maintained at this voltage until the current was decreased to a value corresponding to 0.05C. Subsequently, 5 discharging was conducted at a constant current of 1C until the battery voltage became 3.0 V. The discharge capacity at this time was defined as a (an initial) discharge capacity at the first cycle (initial discharge capacity). Furthermore, the charging and discharging operation was repeatedly 10 performed by the same method to examine the cycle performance of the battery. Fig. 1 shows the results of this cycle test. In the battery of Example 1, the discharge capacity for each cycle is shown by curve a in Fig. 1. Even after 500 cycles, the decrease in the capacity was small and 95% of the initial 15 discharge capacity was maintained.

[0067]

A battery was prepared in the same manner, and the cycle performance of this battery was examined at 60°C as in the above test. Fig. 2 shows the results of this cycle test. In 20 the battery of Example 1, the discharge capacity for each cycle is shown by curve a in Fig. 2. Even after 100 cycles, 93% of the initial discharge capacity was maintained.

[0068]

A battery was prepared in the same manner, and the cycle

performance of this battery was examined at -10°C as in the above test. Fig. 3 shows the results of this cycle test. In the battery of Example 1, the discharge capacity for each cycle is shown by curve a in Fig. 3. Even after 100 cycles, 5 90% of the initial discharge capacity was maintained.

[0069]

[EXAMPLE 2]

(Battery evaluation 2)

[Preparation of electrolyte solution]

10 Lithium hexafluorophosphate (LiPF_6) was used as an electrolyte. A solvent composed of a mixture containing 30% by volume of ethylene carbonate, 40% by volume of methyl ethyl carbonate, and 30% by volume of diethyl carbonate was used. Lithium hexafluorophosphate (LiPF_6) was dissolved in 15 this solvent so as to have a concentration of 1.1 mol/L. Furthermore, as an additive for forming an ion-conductive coating film on an electrode, 2.0 parts by mass of N,N'-bis(acryloyloxyethyl)urea was added relative to 100 parts by mass of the total of the solvent. Thus, an electrolyte 20 solution was prepared.

[0070]

[Preparation of positive electrode]

First, $\text{LiCo}_{1/3}\text{Ni}_{1/3}\text{Mn}_{1/3}\text{O}_2$ functioning as a positive electrode active material, a carbon material functioning as a

conductive agent, and an N-methyl-2-pyrrolidone solution in which polyvinylidene fluoride functioning as a binder was dissolved were mixed so that a mass ratio of the active material, the conductive agent, and the binder was 95:2.5:2.5.

5 The mixture was then kneaded to prepare a positive electrode slurry. The prepared slurry was applied onto an aluminum foil functioning as a current collector, and then dried. The resulting aluminum foil was then rolled with a rolling mill, and a current collector tab was attached thereto. Thus, a
10 positive electrode was prepared.

[0071]

[Preparation of negative electrode]

Natural graphite functioning as a negative electrode active material, an SBR functioning as a binder, and
15 carboxymethyl cellulose functioning as a thickener were mixed with water so that a mass ratio of the active material, the binder, and the thickener was 97.5:1.5:1. The mixture was then kneaded to prepare a negative electrode slurry. The prepared slurry was applied onto a copper foil functioning as
20 a current collector, and then dried. The resulting copper foil was then rolled with a rolling mill, and a current collector tab was attached thereto. Thus, a negative electrode was prepared.

[0072]

[Preparation of battery]

The positive electrode and negative electrode prepared as described above were made to face each other with a polyethylene separator therebetween, and put in an aluminum
5 laminated container. In a glove box in an Ar (argon) atmosphere, the electrolyte solution prepared as described above was added dropwise to the container including the electrodes therein, and the laminated container was thermo-compression bonded while the pressure was removed. Thus, a
10 battery was prepared.

[0073]

[Evaluation of battery]

In initial two cycles, the battery prepared as described above was slowly charged up to 4.2 V at 0.05C and then slowly
15 discharged down to 3.0 V and the charging and discharging operation was then performed once more. Thus, aging was performed.

[0074]

Subsequently, constant-current charging was conducted up
20 to 4.2 V at 25°C at 1C. When the voltage reached 4.2 V, the battery was maintained at this voltage until the current was decreased to 0.05C. Subsequently, discharging was conducted at a constant current of 1C until the battery voltage became 3.0 V. The discharge capacity at this time was defined as a

discharge capacity at the first cycle. Furthermore, the charging and discharging operation was repeatedly performed by the same method to examine the cycle performance of the battery. In the battery of Example 2, the discharge capacity
5 after 500 cycles maintained 96% of the initial discharge capacity.

[0075]

In addition, a battery was prepared in the same manner, and the cycle performance of this battery was examined at
10 60°C as in the above test. In the battery of Example 2, the discharge capacity after 100 cycles maintained 94% of the initial discharge capacity.

[0076]

A battery was prepared in the same manner, and the cycle
15 performance of this battery was examined at -10°C as in the above test. In the battery of Example 2, the discharge capacity at the 100th cycle maintained 84% of the initial discharge capacity.

[0077]

20 [EXAMPLE 3]

(Battery evaluation 3)

[Preparation of electrolyte solution]

A lithium fluorododecaborate that was separated from the product obtained in Preparation 1 of lithium

fluorododecaborate so as to contain 99.9% or more of a lithium fluorododecaborate having a composition formula of $\text{Li}_2\text{B}_{12}\text{F}_{12}$ was used as an electrolyte, and LiPF_6 was used as a mixed electrolyte. A solvent composed of a mixture

5 containing 10% by volume of ethylene carbonate, 20% by volume of propylene carbonate, 50% by volume of methyl ethyl carbonate, and 20% by volume of diethyl carbonate was used. The lithium fluorododecaborate and LiPF_6 were dissolved in this solvent so that the concentration of the lithium

10 fluorododecaborate was 0.4 mol/L and the concentration of LiPF_6 was 0.1 mol/L. Furthermore, as an additive for forming an ion-conductive coating film on an electrode, 2.0 parts by mass of 1,1-bis(acryloyloxymethyl)ethyl isocyanate was added relative to 100 parts by mass of the total of the solvent.

15 Thus, an electrolyte solution was prepared.

[0078]

[Preparation of battery]

A battery was fabricated as in Battery evaluation 1 using a positive electrode and a negative electrode that were

20 the same as those used in Battery evaluation 1 except for the electrolyte solution.

[0079]

(Evaluation of battery)

The battery evaluation was also conducted as in Battery

evaluation 1. According to the results, in the cycle test at 25°C, the discharge capacity at the 500th cycle maintained 96% of the initial discharge capacity. In the cycle test at 60°C, the discharge capacity at the 100th cycle maintained 94% of the initial discharge capacity. In the cycle test at -0°C, 90% of the initial discharge capacity was maintained at the 100th cycle.

[0080]

In addition, a battery was prepared in the same manner as described above, and charging and discharging of this battery were conducted at 25°C for five cycles. An overcharge test was then conducted at 25°C at a rate of 3C. Even when the state of charging was increased to 300%, the battery voltage became substantially constant at 4.75 V and did not increase any more. This battery was discharged at 25°C at a discharge rate of 1C. According to the result, discharging at 99% of the initial discharge capacity could be achieved. Subsequently, constant-current constant-voltage (CCCV) charging was conducted at a rate of 1C up to 4.2 V, and discharging was conducted at 1C down to 3.0 V. This charging and discharging operation was repeatedly performed. At the 500th cycle, 90% of the initial discharge capacity was maintained. Accordingly, it was found that the battery did not degrade due to overcharging.

[0081]

[EXAMPLE 4]

(Battery evaluation 4)

[Preparation of electrolyte solution]

5 A lithium fluorododecaborate that was separated from the product obtained in Preparation 2 of lithium fluorododecaborate so as to contain 99.9% or more of a lithium fluorododecaborate having a composition formula of $\text{Li}_2\text{B}_{12}\text{F}_{11}\text{Br}$ was used as an electrolyte, and LiPF_6 was used as a
10 mixed electrolyte. A solvent composed of a mixture containing 10% by volume of ethylene carbonate, 20% by volume of propylene carbonate, 50% by volume of methyl ethyl carbonate, and 20% by volume of diethyl carbonate was used. The lithium fluorododecaborate and LiPF_6 were dissolved in
15 this solvent so that the concentration of the lithium fluorododecaborate was 0.4 mol/L and the concentration of LiPF_6 was 0.1 mol/L. Furthermore, as an additive for forming an ion-conductive coating film on an electrode, 2.0 parts by mass of tetrakis(acryloyloxymethyl)urea was added relative to
20 100 parts by mass of the total of the solvent. Thus, an electrolyte solution was prepared.

[0082]

[Preparation of battery]

A battery was fabricated as in Battery evaluation 1

using a positive electrode and a negative electrode that were the same as those used in Battery evaluation 1 except for the electrolyte solution.

[0083]

5 (Evaluation of battery)

The battery evaluation was also conducted as in Battery evaluation 1. According to the results, in the cycle test at 25°C, the discharge capacity at the 500th cycle maintained 93% of the initial discharge capacity. In the cycle test at 10 60°C, the discharge capacity at the 100th cycle maintained 90% of the initial discharge capacity. In the cycle test at -10°C, 82% of the initial discharge capacity was maintained at the 100th cycle.

[0084]

15 In addition, a battery was prepared in the same manner as described above, and charging and discharging of this battery were conducted at 25°C for five cycles. An overcharge test was then conducted at 25°C at a rate of 3C. Even when the state of charging was increased to 300%, the 20 battery voltage became substantially constant at 4.70 V and did not increase any more. This battery was discharged at 25°C at a discharge rate of 1C. According to the result, discharging at 91% of the initial discharge capacity could be achieved. Subsequently, CCCV charging was conducted at a

rate of 1C up to 4.2 V, and discharging was conducted at 1C down to 3.0 V. This charging and discharging operation was repeatedly performed. At the 100th cycle, 80% of the initial discharge capacity was maintained. Accordingly, it was found
5 that the battery did not substantially degrade due to overcharging.

[0085]

[EXAMPLE 5]

(Battery evaluation 5)

10 [Preparation of electrolyte solution]

A lithium fluorododecaborate that was separated from the product obtained in Preparation 3 of lithium fluorododecaborate so as to contain 99.9% or more of a lithium fluorododecaborate having a composition formula of
15 $\text{Li}_2\text{B}_{12}\text{F}_{11}\text{Cl}$ was used as an electrolyte, and LiPF_6 was used as a mixed electrolyte. A solvent composed of a mixture containing 10% by volume of ethylene carbonate, 20% by volume of propylene carbonate, 50% by volume of methyl ethyl carbonate, and 20% by volume of diethyl carbonate was used.
20 The lithium fluorododecaborate and LiPF_6 were dissolved in this solvent so that the concentration of the lithium fluorododecaborate was 0.4 mol/L and the concentration of LiPF_6 was 0.1 mol/L. Furthermore, as an additive for forming an ion-conductive coating film on an electrode, 1.0 part by

mass of 1,1-bis(acryloyloxymethyl)ethyl isocyanate was added relative to 100 parts by mass of the total of the solvent. Thus, an electrolyte solution was prepared.

[0086]

5 [Preparation of battery]

A battery was fabricated as in Battery evaluation 1 using a positive electrode and a negative electrode that were the same as those used in Battery evaluation 1 except for the electrolyte solution.

10 [0087]

(Evaluation of battery)

The battery evaluation was also conducted as in Battery evaluation 1. According to the results, in the cycle test at 25°C, the discharge capacity at the 500th cycle maintained 89% of the initial discharge capacity. In the cycle test at 60°C, the discharge capacity at the 100th cycle maintained 82% of the initial discharge capacity. In the cycle test at -10°C, 74% of the initial discharge capacity was maintained at the 100th cycle.

20 [0088]

In addition, a battery was prepared in the same manner as described above, and charging and discharging of this battery were conducted at 25°C for five cycles. An overcharge test was then conducted at 25°C at a rate of 3C.

Even when the state of charging was increased to 300%, the battery voltage became substantially constant at 4.68 V and did not increase any more. This battery was discharged at 25°C at a discharge rate of 1C. According to the result,
5 discharging at 91% of the initial discharge capacity could be achieved. Subsequently, CCCV charging was conducted at a rate of 1C up to 4.2 V, and discharging was conducted at 1C down to 3.0 V. This charging and discharging operation was repeatedly performed. At the 100th cycle, 82% of the initial
10 discharge capacity was maintained. Accordingly, it was found that the battery did not substantially degrade due to overcharging.

[0089]

[EXAMPLE 6]

15 (Battery evaluation 6)

[Preparation of electrolyte solution]

Lithium hexafluorophosphate (LiPF_6) was used as an electrolyte. A solvent composed of a mixture containing 10% by volume of ethylene carbonate, 20% by volume of propylene
20 carbonate, 50% by volume of methyl ethyl carbonate, and 20% by volume of diethyl carbonate was used. Lithium hexafluorophosphate (LiPF_6) was dissolved in this solvent so as to have a concentration of 1.1 mol/L. Furthermore, as additives for forming an ion-conductive coating film on an

electrode, 1.5 parts by mass of 1,1-bis(acryloyloxymethyl)ethyl isocyanate and 0.75 parts by mass of 1,3-propane sultone were added relative to 100 parts by mass of the total of the solvent. Thus, an electrolyte
5 solution was prepared.

[0090]

[Preparation of battery]

A battery was fabricated as in Battery evaluation 1 using a positive electrode and a negative electrode that were
10 the same as those used in Battery evaluation 1 except for the electrolyte solution.

[0091]

(Evaluation of battery)

The battery evaluation was also conducted as in Battery
15 evaluation 1. According to the results, in the cycle test at 25°C, the discharge capacity at the 500th cycle maintained 96% of the initial discharge capacity. In the cycle test at 60°C, the discharge capacity at the 100th cycle maintained 88% of the initial discharge capacity. In the cycle test at
20 -10°C, 85% of the initial discharge capacity was maintained at the 100th cycle.

[0092]

[EXAMPLE 7]

(Battery evaluation 7)

[Preparation of electrolyte solution]

Lithium hexafluorophosphate (LiPF_6) was used as an electrolyte. A solvent composed of a mixture containing 10% by volume of ethylene carbonate, 20% by volume of propylene carbonate, 50% by volume of methyl ethyl carbonate, and 20% by volume of diethyl carbonate was used. Lithium hexafluorophosphate (LiPF_6) was dissolved in this solvent so as to have a concentration of 1.1 mol/L. Furthermore, as an additive for forming an ion-conductive coating film on an electrode, 2.0 parts by mass of 1,1-bis(acryloyloxymethyl)ethyl isocyanate was added relative to 100 parts by mass of the total of the solvent. Thus, an electrolyte solution was prepared.

[0093]

15 [Preparation of battery]

A battery was fabricated as in Battery evaluation 1 using a positive electrode and a negative electrode that were the same as those used in Battery evaluation 1 except for the electrolyte solution.

20 [0094]

(Evaluation of battery)

The battery evaluation was also conducted as in Battery evaluation 1. According to the results, in the cycle test at 25°C, the discharge capacity at the 500th cycle maintained

95% of the initial discharge capacity. In the cycle test at 60°C, the discharge capacity at the 100th cycle maintained 90% of the initial discharge capacity. In the cycle test at -10°C, 93% of the initial discharge capacity was maintained at the 100th cycle.

[0095]

In addition, a battery was prepared in the same manner as described above, and charging and discharging of this battery were conducted at 25°C for five cycles. An overcharge test was then conducted at 25°C at a rate of 3C. After the state of charging exceeded 130%, the battery voltage became 5.2 V or more. Subsequently, with an increase in the state of charging, the voltage gradually increased. From the time when the state of charging exceeded about 200%, the voltage rapidly increased. The battery voltage reached 10.0 V at a state of charging of 215%, and the overcharge test was finished. This battery was then discharged at 25°C at a discharge rate of 1C. According to the result, discharging at only 11% of the initial discharge capacity was achieved. Subsequently, CCCV charging, in which charging was conducted at 1C until the battery voltage reached 4.2 V and the voltage was maintained from the time when the battery voltage reached 4.2 V until a current value became 0.05C, and discharging at 1C down to 3.0 V were repeatedly performed.

Even after these charging and discharging were conducted for 10 cycles, the discharge capacity did not exceed 10% of the initial discharge capacity, and the test was finished.

[0096]

5 [EXAMPLE 8]

(Battery evaluation 8)

[Preparation of electrolyte solution]

A lithium fluorododecaborate that was separated from the product obtained in Preparation 1 of lithium
10 fluorododecaborate so as to contain 99.9% or more of a lithium fluorododecaborate having a composition formula of $\text{Li}_2\text{B}_{12}\text{F}_{12}$ was used as an electrolyte, and LiPF_6 was used as a mixed electrolyte. A solvent composed of a mixture
15 of methyl ethyl carbonate, and 20% by volume of diethyl carbonate was used. The lithium fluorododecaborate and LiPF_6 were dissolved in this solvent so that the concentration of the lithium fluorododecaborate was 0.4 mol/L and the concentration of LiPF_6 was 0.2 mol/L. Furthermore, as an
20 additive for forming an ion-conductive coating film on an electrode, 0.5 parts by mass of 2-acryloyloxyethyl isocyanate was added relative to 100 parts by mass of the total of the solvent. Thus, an electrolyte solution was prepared.

[0097]

[Preparation of battery]

A battery was fabricated as in Battery evaluation 1 using a positive electrode and a negative electrode that were the same as those used in Battery evaluation 1 except for the electrolyte solution.

[0098]

(Evaluation of battery)

The battery evaluation was also conducted as in Battery evaluation 1. According to the results, in the cycle test at 25°C, the discharge capacity at the 500th cycle maintained 89% of the initial discharge capacity. In the cycle test at 60°C, the discharge capacity at the 100th cycle maintained 75% of the initial discharge capacity. In the cycle test at -10°C, 88% of the initial discharge capacity was maintained at the 100th cycle.

[0099]

In addition, a battery was prepared in the same manner as described above, and charging and discharging of this battery were conducted at 25°C for five cycles. An overcharge test was then conducted at 25°C at a rate of 3C. Even when the state of charging was increased to 300%, the battery voltage became substantially constant at 4.70 V and did not increase any more. This battery was discharged at 25°C at a discharge rate of 1C. According to the result,

discharging at 87% of the initial discharge capacity could be achieved.

[0100]

[EXAMPLE 9]

5 (Battery evaluation 9)

[Preparation of electrolyte solution]

A lithium fluorododecaborate that was separated from the product obtained in Preparation 1 of lithium fluorododecaborate so as to contain 99.9% or more of a lithium fluorododecaborate having a composition formula of $\text{Li}_2\text{B}_{12}\text{F}_{12}$ was used as an electrolyte, and LiPF_6 was used as a mixed electrolyte. A solvent composed of a mixture containing 30% by volume of ethylene carbonate, 50% by volume of methyl ethyl carbonate, and 20% by volume of diethyl carbonate was used. The lithium fluorododecaborate and LiPF_6 were dissolved in this solvent so that the concentration of the lithium fluorododecaborate was 0.4 mol/L and the concentration of LiPF_6 was 0.2 mol/L. Furthermore, as additives for forming an ion-conductive coating film on an electrode, 1.5 parts by mass of ethyl crotonate and 0.5 parts by mass of 1,3-propane sultone were added relative to 100 parts by mass of the total of the solvent. Thus, an electrolyte solution was prepared.

[0101]

[Preparation of battery]

A battery was fabricated as in Battery evaluation 1 using a positive electrode and a negative electrode that were the same as those used in Battery evaluation 1 except for the electrolyte solution.

[0102]

(Evaluation of battery)

The battery evaluation was also conducted as in Battery evaluation 1. According to the results, in the cycle test at 25°C, the discharge capacity at the 500th cycle maintained 93% of the initial discharge capacity. In the cycle test at 60°C, the discharge capacity at the 100th cycle maintained 90% of the initial discharge capacity. In the cycle test at -10°C, 91% of the initial discharge capacity was maintained at the 100th cycle.

[0103]

In addition, a battery was prepared in the same manner as described above, and charging and discharging of this battery were conducted at 25°C for five cycles. An overcharge test was then conducted at 25°C at a rate of 3C. Even when the state of charging was increased to 300%, the battery voltage became substantially constant at 4.71 V and did not increase any more. This battery was discharged at 25°C at a discharge rate of 1C. According to the result,

discharging at 96% of the initial discharge capacity could be achieved.

[0104]

[EXAMPLE 10]

5 (Battery evaluation 10)

[Preparation of electrolyte solution]

A lithium fluorododecaborate that was separated from the product obtained in Preparation 1 of lithium fluorododecaborate so as to contain 99.9% or more of a lithium fluorododecaborate having a composition formula of $\text{Li}_2\text{B}_{12}\text{F}_{12}$ was used as an electrolyte, and LiPF_6 was used as a mixed electrolyte. A solvent composed of a mixture containing 30% by volume of ethylene carbonate, 50% by volume of methyl ethyl carbonate, and 20% by volume of diethyl carbonate was used. The lithium fluorododecaborate and LiPF_6 were dissolved in this solvent so that the concentration of the lithium fluorododecaborate was 0.4 mol/L and the concentration of LiPF_6 was 0.2 mol/L. Furthermore, as an additive for forming an ion-conductive coating film on an electrode, 1.5 parts by mass of vinyl crotonate was added relative to 100 parts by mass of the total of the solvent. Thus, an electrolyte solution was prepared.

[0105]

[Preparation of battery]

A battery was fabricated as in Battery evaluation 1 using a positive electrode and a negative electrode that were the same as those used in Battery evaluation 1 except for the electrolyte solution.

5 [0106]

(Evaluation of battery)

The battery evaluation was also conducted as in Battery evaluation 1. According to the results, in the cycle test at 25°C, the discharge capacity at the 500th cycle maintained
10 91% of the initial discharge capacity. In the cycle test at 60°C, the discharge capacity at the 100th cycle maintained 84% of the initial discharge capacity. In the cycle test at -10°C, 88% of the initial discharge capacity was maintained at the 100th cycle.

15 [0107]

In addition, a battery was prepared in the same manner as described above, and charging and discharging of this battery were conducted at 25°C for five cycles. An overcharge test was then conducted at 25°C at a rate of 3C.
20 Even when the state of charging was increased to 300%, the battery voltage became substantially constant at 4.70 V and did not increase any more. This battery was discharged at 25°C at a discharge rate of 1C. According to the result, discharging at 93% of the initial discharge capacity could be

achieved.

[0108]

[EXAMPLE 11]

(Battery evaluation 11)

5 [Preparation of electrolyte solution]

A lithium fluorododecaborate that was separated from the product obtained in Preparation 1 of lithium fluorododecaborate so as to contain 99.9% or more of a lithium fluorododecaborate having a composition formula of $\text{Li}_2\text{B}_{12}\text{F}_{12}$ was used as an electrolyte, and LiPF_6 was used as a mixed electrolyte. A solvent composed of a mixture containing 30% by volume of ethylene carbonate, 50% by volume of methyl ethyl carbonate, and 20% by volume of diethyl carbonate was used. The lithium fluorododecaborate and LiPF_6 were dissolved in this solvent so that the concentration of the lithium fluorododecaborate was 0.4 mol/L and the concentration of LiPF_6 was 0.2 mol/L. Furthermore, as additives for forming an ion-conductive coating film on an electrode, 1.5 parts by mass of vinyl crotonate and 0.5 parts by mass of 1,3-propane sultone were added relative to 100 parts by mass of the total of the solvent. Thus, an electrolyte solution was prepared.

[0109]

[Preparation of battery]

A battery was fabricated as in Battery evaluation 1 using a positive electrode and a negative electrode that were the same as those used in Battery evaluation 1 except for the electrolyte solution.

5 [0110]

(Evaluation of battery)

The battery evaluation was also conducted as in Battery evaluation 1. According to the results, in the cycle test at 25°C, the discharge capacity at the 500th cycle maintained
10 95% of the initial discharge capacity. In the cycle test at 60°C, the discharge capacity at the 100th cycle maintained 91% of the initial discharge capacity. In the cycle test at -10°C, 93% of the initial discharge capacity was maintained at the 100th cycle.

15 [0111]

In addition, a battery was prepared in the same manner as described above, and charging and discharging of this battery were conducted at 25°C for five cycles. An overcharge test was then conducted at 25°C at a rate of 3C.
20 Even when the state of charging was increased to 300%, the battery voltage became substantially constant at 4.70 V and did not increase any more. This battery was discharged at 25°C at a discharge rate of 1C. According to the result, discharging at 96% of the initial discharge capacity could be

achieved.

[0112]

[COMPARATIVE EXAMPLE 1]

(Battery evaluation 12)

5 [Preparation of electrolyte solution]

Lithium hexafluorophosphate (LiPF_6) was used as an electrolyte. A solvent composed of a mixture containing 10% by volume of ethylene carbonate, 20% by volume of propylene carbonate, 50% by volume of methyl ethyl carbonate, and 20%
10 by volume of diethyl carbonate was used. Lithium hexafluorophosphate (LiPF_6) was dissolved in this solvent so as to have a concentration of 1.1 mol/L. Thus, an electrolyte solution was prepared. No additive for forming a coating film was added to this electrolyte solution.

15 [0113]

[Preparation of battery]

A battery was fabricated as in Battery evaluation 1 using a positive electrode and a negative electrode that were the same as those used in Battery evaluation 1 except for the
20 electrolyte solution.

[0114]

(Evaluation of battery)

The battery evaluation was also conducted as in Battery evaluation 1. Fig. 1 shows the results of the cycle test at

25°C. In the cycle test at 25°C, the discharge capacity of the battery of Comparative Example 1 decreased to less than 80% of the initial discharge capacity at the 220th cycle, as shown by curve b in Fig. 1. Fig. 2 shows the results of the cycle test at 60°C. In the cycle test at 60°C, the discharge capacity decreased to less than 80% of the initial discharge capacity at the 48th cycle, as shown by curve b in Fig. 2. Fig. 1 shows the results of the cycle test at -10°C. In the cycle test at -10°C, the discharge capacity decreased to less than 80% of the initial discharge capacity at the 58th cycle, as shown by curve b in Fig. 3.

[0115]

[COMPARATIVE EXAMPLE 2]

(Battery evaluation 13)

[Preparation of electrolyte solution]

A lithium fluorododecaborate that was separated from the product obtained in Preparation 1 of lithium fluorododecaborate so as to contain 99.9% or more of a lithium fluorododecaborate having a composition formula of $\text{Li}_2\text{B}_{12}\text{F}_{12}$ was used as an electrolyte, and LiPF_6 was used as a mixed electrolyte. A solvent composed of a mixture containing 10% by volume of ethylene carbonate, 20% by volume of propylene carbonate, 50% by volume of methyl ethyl carbonate, and 20% by volume of diethyl carbonate was used.

The lithium fluorododecaborate and LiPF_6 were dissolved in this solvent so that the concentration of the lithium fluorododecaborate was 0.4 mol/L and the concentration of LiPF_6 was 0.1 mol/L. Thus, an electrolyte solution was prepared. No additive for forming an ion-conductive coating film on an electrode was added to this electrolyte solution.

[0116]

[Preparation of battery]

A battery was fabricated as in Battery evaluation 1 using a positive electrode and a negative electrode that were the same as those used in Battery evaluation 1 except for the electrolyte solution.

[0117]

(Evaluation of battery)

The battery evaluation was also conducted as in Battery evaluation 1. According to the results, in the cycle test at 25°C, the discharge capacity decreased to less than 80% of the initial discharge capacity at the 285th cycle. In the cycle test at 60°C, the discharge capacity decreased to less than 80% of the initial discharge capacity at the 145th cycle. In the cycle test at -10°C, the discharge capacity decreased to less than 80% of the initial discharge capacity at the 108th cycle.

[0118]

The results of the Examples and Comparative Examples described above are summarized in Tables 1 and 2.

[0119]

In Tables 1 and 2, the characters shown as solvents
5 represent the substances below.

[0120]

EC: ethylene carbonate

PC: propylene carbonate

EMC: methyl ethyl carbonate

10 DEC: diethyl carbonate

In Tables 1 and 2, the term "discharge capacity ratio" means a ratio of the discharge capacity after a test to the initial discharge capacity.

[0121]

15 [Table 1]

Table 1

	Electrolyte (Concentration)	Solvent (volume %)	Positive electrode active material	Negative electrode active material	Additive (Amount added)	Cycle test			Overcharge test	
						25°C, 500c	60°C, 100c	-10°C, 100c	25°C, 5c → 25°C, 3C State of charging: 300%	25°C, 5c → 25°C, 3C State of charging: 300%
						Discharge capacity ratio	Discharge capacity ratio	Discharge capacity ratio	Discharge capacity ratio	Discharge capacity ratio
Example 1	LiPF ₆ (1.1 mol/L)	EC (10%) PC (20%) EMC (40%) DEC (30%)	LiCo _{1/3} Ni _{1/3} Mn _{1/3} O ₂	Artificial graphite	1,1- Bis(acryloyloxymethyl) ethyl isocyanate (1.5 parts by mass)	95%	93%	90%		
Example 2	LiPF ₆ (1.1 mol/L)	EC (30%) EMC (40%) DEC (30%)	LiCo _{1/3} Ni _{1/3} Mn _{1/3} O ₂	Natural graphite	N,N'- Bis(acryloyloxyethyl)urea (2.0 parts by mass)	96%	94%	84%		
Example 3	Li ₂ B ₁₂ F ₁₂ (0.4 mol/L) LiPF ₆ (0.1 mol/L)	EC (10%) PC (20%) EMC (50%) DEC (20%)	LiCo _{1/3} Ni _{1/3} Mn _{1/3} O ₂	Artificial graphite	1,1- Bis(acryloyloxymethyl) ethyl isocyanate (2.0 parts by mass)	96%	94%	90%	99%	90% (500c)
Example 4	Li ₂ B ₁₂ F ₁₁ Br (0.4 mol/L) LiPF ₆ (0.1 mol/L)	EC (10%) PC (20%) EMC (50%) DEC (20%)	LiCo _{1/3} Ni _{1/3} Mn _{1/3} O ₂	Artificial graphite	Tetrakis (acryloyloxymethyl)urea (2.0 parts by mass)	93%	90%	82%	91%	80% (100c)
Example 5	Li ₂ B ₁₂ F ₁₁ Cl (0.4 mol/L) LiPF ₆ (0.1 mol/L)	EC (10%) PC (20%) EMC (50%) DEC (20%)	LiCo _{1/3} Ni _{1/3} Mn _{1/3} O ₂	Artificial graphite	1,1- Bis(acryloyloxymethyl) ethyl isocyanate (1.0 part by mass)	89%	82%	74%	91%	82% (100c)
Example 6	LiPF ₆ (1.1 mol/L)	EC (10%) PC (20%) EMC (50%) DEC (20%)	LiCo _{1/3} Ni _{1/3} Mn _{1/3} O ₂	Artificial graphite	1,1- Bis(acryloyloxymethyl) ethyl isocyanate (1.5 parts by mass)	96%	88%	85%		

[0122]

[Table 2]

Table 2

	Electrolyte (Concentration)	Solvent (volume %)	Positive electrode active material	Negative electrode active material	Additive (Amount added)	Cycle test			Overcharge test	
						25°C, 500c	60°C, 100c	-10°C, 100c	25°C, 5c → 25°C, 3C State of charging 300%	25°C, 5c → 25°C, 3C State of charging 300%
						Discharge capacity ratio	Discharge capacity ratio	Discharge capacity ratio	Discharge capacity ratio	Discharge capacity ratio
Example 7	LiPF ₆ (1.1 mol/L)	EC (10%) PC (20%) EMC (50%) DEC (20%)	LiCo _{1/3} Ni _{1/3} Mn _{1/3} O ₂	Artificial graphite	1,1- Bis(acryloyloxymethyl) ethyl isocyanate (2.0 parts by mass)	95%	90%	93%		
Example 8	0.4 mol/L Li ₂ B ₁₂ F ₁₂ 0.2 mol/L LiPF ₆	EC (30%) EMC (50%) DEC (20%)	LiCo _{1/3} Ni _{1/3} Mn _{1/3} O ₂	Artificial graphite	2-Acryloyloxethyl isocyanate (0.5 parts by mass)	89%	75%	88%	87%	
Example 9	Li ₂ B ₁₂ F ₁₂ (0.4 mol/L) LiPF ₆ (0.2 mol/L)	EC (30%) EMC (50%) DEC (20%)	LiCo _{1/3} Ni _{1/3} Mn _{1/3} O ₂	Artificial graphite	Ethyl crotonate (1.5 parts by mass) Propane sultone (0.5 parts by mass)	93%	90%	91%	96%	
Example 10	Li ₂ B ₁₂ F ₁₂ (0.4 mol/L) LiPF ₆ (0.2 mol/L)	EC (30%) EMC (50%) DEC (20%)	LiCo _{1/3} Ni _{1/3} Mn _{1/3} O ₂	Artificial graphite	Vinyl crotonate (1.5 parts by mass)	91%	84%	88%	93%	
Example 11	Li ₂ B ₁₂ F ₁₂ (0.4 mol/L) LiPF ₆ (0.2 mol/L)	EC (30%) EMC (50%) DEC (20%)	LiCo _{1/3} Ni _{1/3} Mn _{1/3} O ₂	Artificial graphite	Vinyl crotonate (1.5 parts by mass) Propane sultone (0.5 parts by mass)	95%	91%	93%	96%	

Table 2 (Continued from the previous page)

	Electrolyte (Concentration)	Solvent (volume %)	Positive electrode active material	Negative electrode active material	Additive (Amount added)	Cycle test			Overcharge test	
						25°C, 500c	60°C, 100c	-10°C, 100c	25°C, 5c → 25°C, 3C State of charging 300%	25°C, 5c → 25°C, 3C State of charging 300%
Com. Ex. 1	LiPF ₆ (1.1 mol/L)	EC (10%) PC (20%) EMC (50%) DEC (20%)	LiCo _{1/3} Ni _{1/3} Mn _{1/3} O ₂	Artificial graphite	Not added	Discharge capacity ratio < 80%, 220c	Discharge capacity ratio < 80%, 48c	Discharge capacity ratio < 80%, 58c	Discharge capacity ratio	Discharge capacity ratio
Com. Ex. 2	Li ₂ B ₁₂ F ₁₂ (0.4 mol/L) LiPF ₆ (0.1 mol/L)	EC (10%) PC (20%) EMC (50%) DEC (20%)	LiCo _{1/3} Ni _{1/3} Mn _{1/3} O ₂	Artificial graphite	Not added	< 80%, 285c	< 80%, 145c	< 80%, 108c		

Com. Ex.: Comparative Example

CLAIMS

[Claim 1]

A nonaqueous electrolyte solution for a secondary
5 battery, the nonaqueous electrolyte solution comprising an
electrolyte; a solvent; and an additive,

wherein the additive contains a compound represented by
formula (1) below:

[Chem. 1]



(in the formula (1), R^1 and R^2 are each independently a
hydrogen atom, a methyl group, or an amino group, n is 1, 2,
or 4, when n is 1, Y is a hydrogen atom or a monovalent
organic group, when n is 2, Y is a divalent organic group,
15 and when n is 4, Y is a tetravalent organic group), and

the content of the compound is 0.05 to 10 parts by mass
relative to 100 parts by mass of the total of the solvent.

[Claim 2]

20 The nonaqueous electrolyte solution for a secondary
battery according to Claim 1, wherein the compound
represented by the formula (1) is at least one selected from
the group consisting of 1,1-bis(acryloyloxymethyl)ethyl
isocyanate, N,N'-bis(acryloyloxyethyl)urea, 2,2-

bis(acryloyloxymethyl)ethyl isocyanate diethylene oxide, 2,2-bis(acryloyloxymethyl)ethyl isocyanate triethylene oxide, tetrakis(acryloyloxymethyl)urea, 2-acryloyloxyethyl isocyanate, methyl crotonate, ethyl crotonate, methyl
5 aminocrotonate, ethyl aminocrotonate, and vinyl crotonate.

[Claim 3]

The nonaqueous electrolyte solution for a secondary battery according to Claim 1 or 2, wherein the electrolyte
10 contains a lithium fluorododecaborate represented by a formula $\text{Li}_2\text{B}_{12}\text{F}_x\text{Z}_{12-x}$ (in the formula, X is an integer of 8 to 12, and Z is H, Cl, or Br) and at least one selected from LiPF_6 and LiBF_4 , the concentration of the lithium fluorododecaborate is 0.2 mol/L or more relative to the total
15 of the electrolyte solution, and the total concentration of the at least one selected from LiPF_6 and LiBF_4 is 0.05 mol/L or more relative to the total of the electrolyte solution.

[Claim 4]

20 The nonaqueous electrolyte solution for a secondary battery according to Claim 3, wherein a ratio (A:B) of the content A of the lithium fluorododecaborate to the content B of the at least one selected from LiPF_6 and LiBF_4 is 90:10 to 50:50 in terms of molar ratio.

[Claim 5]

The nonaqueous electrolyte solution for a secondary battery according to Claim 3 or 4, wherein the total molar concentration of the lithium fluorododecaborate and the at
5 least one selected from LiPF_6 and LiBF_4 is 0.3 to 1.5 mol/L relative to the total of the electrolyte solution.

[Claim 6]

The nonaqueous electrolyte solution for a secondary
10 battery according to any one of Claims 3 to 5, wherein X in the formula $\text{Li}_2\text{B}_{12}\text{F}_x\text{Z}_{12-x}$ is 12.

[Claim 7]

The nonaqueous electrolyte solution for a secondary
15 battery according to any one of Claims 1 to 6, wherein the solvent contains at least one selected from the group consisting of cyclic carbonates and chain carbonates.

[Claim 8]

20 A nonaqueous electrolyte secondary battery comprising a positive electrode; a negative electrode; and the nonaqueous electrolyte solution for a secondary battery according to any one of Claims 1 to 7.