

CYANIDE ROUGHENING SILVER ELECTROPLATING SOLUTION

ABSTRACT

The present invention provides an electrolytic silver plating liquid which contains from 10 g/L to 100 g/L of silver cyanide or a silver cyanide salt in terms of elemental silver, from 1 g/L to 200 g/L of an electrically conductive salt, and from 3 g/L to 500 g/L of a thiosulfate or a salt thereof.

[No Figure]