

Description

This invention relates generally to conical cutters (usually called cones) used in roller bits employed in oil-well drilling and in drilling of holes for mining purposes. The invention further concerns a process through which the conical cutters may be most conveniently manufactured as integrated composite structures, and secondly, novel cutters and cutter component structures as well as composition thereof provide important properties associated with localised sections of the cutters.

Conical cutters must operate under severe environmental conditions and withstand a variety of "bit-life" reducing interactions with the immediate surroundings. These include abrasive or erosive actions of the rock being drilled, impact, compressive and vibrational forces that result from rotation of the bit under the weight put on the bit, and the sliding wear and impact actions of the journal pin around which the cone is rotating. The severity, as well as the variety of life-reducing forces acting upon conical cutters, dictate that these cutters not be made of a simple material of uniform properties if they are to provide a cost-effective, down-hole service life. Instead, localised properties of cone sections should withstand the localised forces acting on those sections.

Conventional cones utilising tungsten carbide inserts (TCI) are commonly manufactured from a forged shape. Holes are drilled circumferentially around the forged cutter body to receive hard-cutting elements, such as cobalt cemented tungsten carbide inserts or TCI's, which are press-fitted into the holes. TCI shape must, therefore, be the same as the hole shape, and have parallel side surfaces.

The cone body normally requires surface hardening to withstand the erosive/abrasive effect of rock drilling. This may be accomplished by any of the widely used surface modification or coating techniques, such as transformation hardening, carburizing, nitriding, hard-facing, hard metal coating or brazed-on hard metal cladding.

In addition, interior surfaces of the cone are required in certain areas to be hard, wear and impact resistant to accommodate loading from both the thrust and the radial directions (with respect to the journal pin axial direction). Consequently, these surfaces are also hardened by a surface hardening process. On the journal side, the pin surfaces likely to contact "thrust bearing" surfaces are usually hardfaced and run against a hardened cone or a hardened nose button insert in the cone or a carburized tool steel bushing. In most roller cones, a row of uncapped balls run in races between the nose pin and the roller or journal bearing. These balls may carry some thrust loading, but their primary function is to retain the cone on the journal pin when not pressing against the bottom of the hole.

The major load is the radial load and is carried substantially either by a full complement of cylindrical rollers used primarily in mining operations, or a sealed journal bearing used in oil-field drilling. The journal bearings are normally operated with grease lubrication and employ additional support to prolong bearing life, i.e. self-lubricating porous floating rings (US-A-3,984,158), beryllium-copper alloy bearing coated with a soft metal lubricating film (US-A-4,074,922 and US-A-3,721,307), a bearing with inlays of soft metal to provide lubrication and heat transfer (US-A-3,235,316), or an aluminium bronze inlay (US-A-3,995,917) in the cone as the soft, lubricating member of the journal-cone bearing couple.

US-A-4,172,395 discloses a rolling cone earth boring bit having a bearing surface that has been infiltrated to a controlled depth. A groove is machined in one of the bearing members. The bearing member is placed in a die and an alloy powder material is pressed into the groove recess thereby producing a porous matrix for the bearing element. The bearing element is sintered to provide a porosity within the range of 10% to 20%. An anti-galling material is infiltrated into said porous matrix bearing element and the porous matrix bearing element is hardened.

Deficiencies in the prior art

The present manufacturing of cones for TCI bits is a tedious and precise art, regardless of the manufacturer. Hole sizes and shapes must be matched with those of the TCI's in order to have a tight fit. The fit must not be too tight for fear of causing damage to either the hole periphery or the insert itself during press-fitting operations. If the fit is less than the threshold tightness, the insert may come loose in drilling and be lost, causing major damage to the bit, and most frequently leading to premature (and costly) pull of the bit out of the hole being drilled. This may occur most readily when drilling soft (rock) formations and is one reason to limit the insert extension to prevent insert pull-out. Limiting insert extension (out of the cone), in turn, may slow the rate of penetration into the formation during drilling and thus has a negative influence on the bit performance.

Cone surfaces, must also be treated to impart the desired localised properties. These treatments are usually long i.e. carburizing; or inadequate, i.e. hard coatings that are sprayed or electro-deposited, or have side effects that compromise overall properties of the cone, i.e. hardfacing of weld cladding cause heat-affected regions of inferior properties.

In addition, each of the above-mentioned operations require prior preparation, labour expertise and multiple inspections to assure the needed accuracy both in dimensions and materials properties. In short, cone manufacturing as it is performed presently, is a long, precise and labour-intensive operation.

It is a major object of the invention to provide manufacturing methods that can eliminate separate surface hardening or modification treatments for different cone surfaces. Desired localised properties are obtained in preferred embodiments, by applications of selected powders or shaped inserts rather than by

thermal treatments, thus providing a wider selection of property variation for a more precise means of meeting external wear, impact of simple loading requirements.

EP—A—142,941 forms part of the state of the art against the present application by virtue of Article 54(3) EPC and discloses roller bit cutter, comprising, in combination:

- 5 a) a tough, metallic generally conical and fracture resistant core having a hollow interior, the core defining an axis;
- b) an annular metallic radial bearing layer carried by said core at the interior thereof to support the core for rotation, said bearing layer extending about said axis;
- c) an impact and wear resistant metallic inner layer on the core, at the interior thereof, to provide an
- 10 axial thrust bearing; and
- d) hard metallic inserts having anchor portions carried by the core and partly embedded in recesses therein, the inserts protruding outwardly at the exterior of the core to define cutters, at least some of the inserts being spaced about said axis;
- e) and a wear resistant outer metallic layer on the exterior of said core.
- 15 EP—A—142,941 also discloses a method of producing a roller bit cutter, that includes the steps:
- a) providing a tough, metallic generally conical and fracture resistant core having a hollow interior, and recesses in its exterior the core defining an axis and at least some of the recesses being spaced about said axis;
- b) providing an annular metallic radial bearing layer carried by said core at the interior thereof to
- 20 support the core for rotation, said bearing layer extending about said axis;
- c) providing an impact and wear resistant metallic inner layer on the core, at the interior thereof, to provide an axial thrust bearing;
- d) providing hard metallic inserts having anchor portions carried by the core and partly embedded in said recesses therein, the inserts protruding outwardly at the exterior of the core to define cutters, at least
- 25 some of the inserts being spaced about said axis;
- e) and providing a wear resistant outer metallic layer on the exterior of said core.

Summary of the invention

According to the present invention a roller bit cutter is provided with wear resistant outer metallic layer

30 extending into said recesses and between the core and said insert anchor portions. Similarly, according to another aspect of this invention a method of producing a roller bit cutter is characterised in that the wear resistant outer metallic layer extends into said recesses and between the core and said insert anchor portions.

In preferred embodiments, near isostatic hot pressing of cold formed powders is employed in forming

35 the roller bit cutter. See U.S. Patents 3,356,496 and 3,689,259. Such a process isostatically hot presses near neat shape parts in a matter of a few minutes, producing properties similar to those produced by the conventional Hot Isostatic Pressing (HIP) process without the lengthy thermal cycle required by HIPing. Further, and as will be seen, the inserts may consist of tungsten carbide; the core defines multiple

40 recesses receiving the insert anchor portions, the outer metallic layer extending into said recesses and between the core and said insert anchor portions. In preferred embodiments, at least one and typically all of the layers consists or consist of consolidated powder metal; the insert anchor portions typically have non-parallel side surfaces, and said outer layer suitable has non-parallel sided portions compressively engaging said insert ends, in the recesses.

In addition, in preferred embodiments the core consists of steel alloyed with elements that include

45 carbon, manganese, silicon, nickel, chromium, molybdenum and copper, or in other preferred embodiments the core may consist of cast alloy steel, or of ultra high strength steel. The outer layer may suitably consist of a composite mixture of refractory particles in a binder metal such particles typically having micro hardness in excess of 1,000 kg/mm², and a melting point in excess of 1,600°C. Also, in preferred embodiments the refractory particles are selected from the group consisting of Ti, W, Al, V, Zr, Cr,

50 Mo, Ta, Nb, Hf and carbides, oxides, nitrides, and borides thereof. As an alternative, the outer layer may consist of tool steel initially in powder form, or of a hardfacing alloy, as will be seen, or of wear resistant, internally Laves phase materials, as will appear.

Other preferred features of the invention are defined in the dependent claims.

These and other objects and advantages of the invention, as well as details of an illustrative

55 embodiment, will be more fully understood from the following specification and drawings, in which:

Drawing description

Figure 1 is an elevation, in section of a conical cutter used in three cone rock bits;

Figure 2 is a perspective view showing components of a three-cone rotary bit;

60 Figure 3 is a flow diagram showing steps of a manufacturing process for the conical cutter;

Figure 4 is an enlarged section showing details of a wear resistant skin or layer in a body means receiving and mounting a tungsten carbide insert;

Figures 5a and 5b are elevations showing different forms of inserts; and

Figures 6a and 6b are sections showing modified cutter constructions; and

65 Figures 7a to 7h show detailed process steps.

Detailed description

In Figure 1, the illustrated improved roller bit cutter 10 incorporating the invention includes a tough, metallic, generally conical and fracture resistant core 11. The core has a hollow interior 12, and defines a central axis 13 of rotation. The bottom of the core is tapered at 14, and the interior includes multiple successive zones 12a, 12b, 12c, 12d, 12e and 12f, concentric to axis 13, as shown. An annular metallic radial (sleeve type) bearing layer 15 is carried by the core at interior zone 12a to support the core for rotation. Layer 15 is attached to annular surface 11a of the core, and extends about axis 13. It consists of a bearing alloy, as will appear.

An impact and wear resistant metallic inner layer 16 is attached to the core at its interior zones 12b—12f, to provide an axial thrust bearing; as at end surface 16a. A plurality of hard metallic inserts 17, as for example of tungsten carbide, have inner anchor portions 17a carried by the core to be partly embedded or received in core recesses 18. The inserts also have portions 17b that protrude outwardly, as shown, to define cutters (see also Figures 4, 5a and 5b), at least some of the inserts spaced about axis 13. One insert 17' may be located at the extreme outer end of the core, at axis 13.

Finally, a wear resistant outer metallic skin or layer 19 is on and attached to the core exterior surface, to extend completely over that surface including the surfaces of the core portions that define the recesses 18, whereby the inserts are in fact attached to the layer portions 19a in those recesses.

Preferably, at least one or two of the layers 15, 16 and 19 consists of consolidated powder metal, and preferably all three layers consist of such consolidated powder metal. A variety of manufacturing schemes are possible using the herein disclosed hot pressing technique and the alternative means of applying the surface layers indicated in Figure 1. It is seen from the previous discussion that surface layers 15, 16 and 19 are to have quite different engineering properties other than the interior core section 11. Similarly, layers 16 and 19 should be different than 15, and even 16 should differ from 19. Each of these layers and the core piece 11 may, therefore, be manufactured separately or applied in place as powder mixtures prior to cold pressing. Thus, there may be a number of possible processing schemes as indicated by arrows in Figure 3. The encircled numbers in this Figure refer to the possible processing steps (or operations) listed below in Table 1. Each continuous path in the Figure, starting from Step No. 1 and ending at Step No. 15, defines a separate processing scheme which, when followed, is capable of producing integrally consolidate composite conical cutters.

TABLE 1

A list of major processing steps which may be included in the processing:

1. Blend powders.
2. Cold press powder to pre-form green interior core piece 11 (see Figure 1 for location).
3. Cold press and sinter or hot press within a range 982°C to 671°C (1,800°F to 1,240°F), powder to pre-form, less than fully dense, core piece 11.
4. Forge or cast fully dense core piece 11.
5. Place TCI's in blind end holes or recesses in core piece 11.
6. Apply powdered hard metal compound skin 19, i.e. by painting, slurry dipping or cold spraying a mixture of hard metal powder, a fugitive organic binder and a volatile solvent.
7. Apply thrust-bearing alloy powder layer 16, i.e. by painting, slurry dipping or cold spraying a mixture of thrust-bearing alloy powder, a fugitive organic binder and a volatile solvent.
8. Place wrought, cast or sintered powder metal thrust-bearing piece 16 in the core piece 11.
9. Apply powdered radial bearing alloy 15 in the core piece, i.e. by painting, slurry dipping or cold spraying a mixture of bearing alloy powder, a fugitive organic binder and a volatile solvent.
10. Place wrought, cast or sintered powder metal radial bearing alloy 15 in the core piece.
11. Dry or bake to remove binder from powder layers 19, 16 or 15. Drying temperatures may be typically 15.6°C to 149°C (60—300°F), preferably in a neutral or a reducing atmosphere except when dried at or near room temperature.
12. Hot press to consolidate the composite into a fully dense (99+% of theoretical density) conical cutter. Typically, the hot pressing may be carried out at 1149°C±111°C (2100°F±200°F) and under pressure of 31.5 to 78.7 MPa (20—50 tons per square inch).
13. Weld deposit thrust-bearing alloy at desired locations of layer 16 in the densified cone.
14. Weld deposit radial-bearing alloy 15 in the densified cone.
15. Final finish; i.e. grind or machine ID profile, finish grind bearings, finish machine seal seat, inspect, etc.

The processing schemes outlined, include only the major steps involved in the flow of processing operations. Other secondary operations that are routinely used in most processing schemes for similarly manufactured products, are not included for sake of simplicity. These may be cleaning, manual patchwork to repair small defects, grit blasting to remove loose particles or oxide scale, dimensional or structural inspections etc.

All of the processing steps are unique, as may easily be recognised by those who are familiar with the metallurgical arts in the powder metals processing field. Each provides a number of benefits from the processing point of view, and some of which are listed as follows:

(1) All assembly operations; i.e. painting, spraying, placing, etc., in preparing the composite cutter structure for the hot-pressing operation (Step No. 12 in Table 1) are performed at or near room temperature. Thus, problems associated with thermal property differences or low strength, unconsolidated state of the composite cone prior to hot densification, are avoided. Repair work, geometrical or dimensional control, and in-process handling are greatly simplified.

(2) Application of powdered metal or alloy or metal compound surface layers, using volatile binders, such as cellulose acetate, corn starch and various distilled products, provide sturdy powder layers strongly held together by the binding agent, thus adding to the green strength of the total unconsolidated cone structure. This makes it easy to control surface layer thickness, handling of the assembly in processing and provides mechanical support for the TCI's.

(3) Low temperature application of afore-mentioned surface layers avoids pitfalls associated with high temperature spraying of powders, as promoted by Nederveen® et al. As is well known, thermally-sprayed metal powders incorporate oxides into the sprayed layers. Oxide particles in surface layers may act as structural discontinuities or notches, thus weakening the part.

(4) The proposed schemes in every case produce a near-net-shape product, greatly reducing the labour-intensive machining operations required in the conventional conical cutter production.

(5) The consolidation of various components of the cone, after applying them in powder or insert form, allows the use of inserts having non-parallel side surfaces, as illustrated in Figure 5b (see insert 370 with bottom portions 370a to be received in the cone recesses). This provides, in the finished product, a greatly increased support for each insert, practically eliminating in-service pull-out. In addition, the structural integrity thus provided for the inserts allows insert extensions substantially more than is otherwise. Further benefits in insert wear mode and increased rate of penetration into the rock formation can be achieved with one portion of the insert being longer than the other as shown in Figure 5b, where A'B' is longer than AB.

Proposed cone material
Various sections of the cone cross-section have been identified in Figure 1, each requiring different engineering properties to best function in service. Consequently, materials for each section should be selected separately.

Interior core piece 11 should be made of an alloy possessing high strength and toughness, and preferably requiring thermal treatments below 927°C (1700°F) (to reduce damage to cooling stresses) to impart its desired mechanical properties. Such restrictions can be met by the following classes of materials:

(1) Hardening grades of low-alloy steels (ferrous base) with carbon contents ranging nominally between 0.1 and 0.65%, manganese 0.01 to 2.0%, silicon 0.01 to 2.2%, nickel 0.4 to 3.75%, chromium 0.01 to 1.2%, molybdenum 0.15 to 0.40%, copper to 0.3% and remainder substantially iron, total of all other elements to be less than 1.0% by weight.

(2) Castable alloy steel having less than 8% total alloying element content, most typically ASTM-A148-80 grades.

(3) Ultra-high strength steels most specifically known in the industry as: D-6A, H-11, 9Ni-4Co, 18-Ni maraging, 300-M, 4130, 4330 V, 4340. These steels nominally have the same levels of C, Mn and Si as do the low-alloy steels described in (1) above. However, they have higher contents of other alloying elements: chromium up to 5.0%, nickel to 19.0%, molybdenum to 5.0%, vanadium to 1.0%, cobalt to 8.0%, with remaining substantially iron, and all other elements totalling less than 1.0%.

(4) (Ferrous) powder metal steels with nominal chemistries falling within: 79 to 98% iron, 0-20% copper, 0.4 to 1.0% carbon, and 0-4.0% nickel.

(5) Age hardenable and martensitic stainless steels whose compositions fall into the limits described in (3) above, except that they may have chromium up to 20%, aluminium up to 2.5%, titanium up to 1.5%, copper, up to 4.0%, and columbium plus tantalum up to 0.5%.

In all cases, the core piece mechanical properties should exceed the following:

- 1.98 MPa (130 ksi) ultimate tensile strength
- 1.22 MPa (80 ksi) yield strength
- 5% tensile strength
- 15% reduction in area
- 13.6 Nm (10 ft-lb) (izod) impact strength

Wear resistant exterior skin 19, which may have a thickness within 0.0254 to 5.08 mm (0.01 to 0.20 inch) range, need not be uniform in thickness. This layer of hard wear-resistant material may, indeed, have islands of "inserts" whose thickness, composition, as well as shape, may be quite different than those of the remaining "skin". Materials suitable for the cone skin include:

(1) A composite mixture of particles of refractory hard compounds in a binding metal or alloy where the refractory hard components have a micro-hardness of higher than 1,000 kg/mm² (50-100 g testing load), and a melting point of 1600°C or higher in their commercially pure forms, and where the binding metal or alloy may be those based on iron, nickel, cobalt or copper.

Examples of such refractory hard compounds include carbides, oxides, nitrides and borides (or their mixtures) of elements Ti, W, Al, V, Zr, Cr, Mo, Ta, Nb and Hf.

(2) Speciality tool steels, readily available in powder form, having large amounts of strong carbide formers such as Ti, V, Nb, Mo, W and Cr, and a carbon content higher than 2.0% by weight.

(3) Hardfacing alloys based on transition elements Fe, Ni, or Co, with the following general chemistry ranges:

		Cobalt base	Nickel base	Iron base
10	Chromium	25—30% (*)	10—30%	0—27%
	Carbon	0.1—3.5%	0.4—3.0%	0.1—4.0%
	Tungsten	4—13%	0—5.0%	—
	Molybdenum	0—5%	0—17.0%	0—11%
15	Boron	0—2.5%	0—5.0%	—
	Iron	0—3.0%	3—29%	Balance
	Nickel	0—3.0%	Balance	0—1.75%
	Cobalt	Balance	0—12%	—
	Silicon	0—2.0%	0—4.5%	0—1.5%
20	Manganese	0—1.0%	0—1.0%	0—1.0%

(*) percentage by weight

(4) Wear-resistant intermetallic (Lave phase) materials based on cobalt or nickel as the primary constituent and having molybdenum (25—35%), chromium (8—18%), silicon (2—4%) and carbon 0.08% maximum.

Thrust-bearing 16 may be similar in composition to the exterior skin 19. In addition, when they are incorporated into the cone as inserts (pre-formed, separately processed cast, wrought or powder metal-produced shapes), they may be made of any metal or alloy having a hardness above 35 R_c. They may, in such cases, have a composite structure where part of the structure is a lubricating material such as molybdenum disulfide, tin, copper, silver, lead or their alloys; or graphite.

Cobalt-cemented tungsten carbide inserts (TCI's), 17 in Figure 1, are to be readily available cobalt-tungsten carbide compositions whose cobalt content usually is within the 5—18% range.

Bearing alloy 15, if incorporated into the cone as a separately-manufactured insert, may either be a hardened or carburized or nitrided or borided steel or any one of a number of readily available commercial non-ferrous bearing alloys, such as the bronzes. If the bearing is weld deposited, the material may still be a bronze. If, however, the bearing is integrally hot pressed in place from a previously applied powder, or if the insert is produced by any of the known powder metallurgy techniques, then it may also have a composite structure having dispersed within it a phase containing lubricating properties to the bearing.

The cone configuration accords with the journal pin shape and is affected by the interaction of the cone with the other cones of the same bit. While configuration may vary somewhat, there are certain configurations associated with the cone sections identified as 11, 15, 16, 17 and 19 which are unusually advantageous, and are listed as follows:

(1) Extension of the wear-resistant alloy skin layer 19 into the clearance between the walls of the blind end hole or recess in core piece 11, as well as the configuration of the insert 170 in Figure 4 and having a non-parallel anchor portion 170a.

(2) Non-parallel sided inserts or TCI's, where the cross-sectional area at A—A' in Figure 5b is smaller than that at the bottom of the TCI 370. Note anchor portion 370a. In addition, cross-sections on planes parallel to the bottom surface of the TCI need not be a circle, as customary, but may be any shape other than a circle; i.e. elliptical, irregular, polygonal, etc., and sides may not be equal in length.

(3) Thrust-bearing layer 16 may or may not be a single piece insert or a continuously applied powder metal layer. Indeed, this layer may be made up of several inserts 160—162 most likely to be circular in shape as indicated in Figure 6(a), or a combination of inserts and powdered metal layer 40 as exemplified in Figure 6(b).

Examples

A typically processing route involves the steps numbered 1, 3, 5, 6, 7, 10, 11, 12 and 15 in Table 1. A low alloy steel composition is blended to form a powder mixture of composition suitable for the core. In one instance, this mixture constituted an alloy having the following final analysis: 0.22% manganese, 0.23% molybdenum, 1.84% nickel, 0.27% carbon and remainder substantially iron. The powder was cold pressed to a preform and sintered at 1121°C (2050°F) for one hour in a reducing furnace atmosphere. Carbide inserts were placed in the blind holes created in the preform and the exterior of the cone was painted with a slurry containing hardfacing metal powder, Stellite No. 1, making sure the slurry filled all clearance space between the carbide insert and the preform.

The slurry was prepared by mixing Stellite powder with 3% cellulose acetate powder and adding

sufficient amount of acetone to develop the desired slurry fluidity. The Stellite No. 1 alloy powder had a nominal chemistry (in weight percent) of: 30% chromium, 2.5% carbon, 1% silicon, 12.5% tungsten, 1% maximum each of manganese and molybdenum, and 3% maximum each of iron and nickel, with remainder being substantially cobalt. Once applied, the outer skin formed on the core piece quickly dried at room temperature.

A thin layer of a thrust bearing alloy was similarly applied on surfaces identified by 16 in Figure 1. The composition of this layer was the same as the exterior skin applied over the core piece. A radial bearing alloy tube segment was then fitted within the cylindrical section identified as 15 in Figure 1. The AISI 105 carbon steel tube having 0.1 inch wall thickness was fixed in place by placing it on a thin layer of slurry applied core piece alloy steel powder.

The preform assembly, thus prepared, was dried in an oven at 37.8°C (100°F) for overnight, driving away all volatile constituents of the slurries. It was then induction heated to 1232°C (2250°F) in less than 4 minutes and immersed in hot ceramic grain, which was also at 1232°C (2250°F) within a cylindrical die. A pressure of 63 MPa (40 tons per square inch) was applied by way of a hydraulic press, onto the grain which transmitted the pressure, in various degrees to the preform in all directions. The peak pressure of 63 MPa (40 tsi) was reached within 4—5 seconds and the peak pressure was maintained for less than 2 seconds and released. The die contents when emptied separated into grain and the consolidated conical cutter. Before the part had a chance to cool below 871°C (1600°F) it was transferred to a furnace operating at 852°C (1565°F), kept there for an hour and oil quenched. To prevent oxidation, the furnace atmosphere was adjusted to be a reducing atmosphere, e.g. cracked ammonia. The hardened part was then tempered for one hour at 538°C (1000°F) and air cooled to assure a tough and strong core.

A similarly processed tensile test bar when tensile tested exhibited 2.21 MPa (152 ksi) ultimate tensile strength, 2.14 MPa (141 ksi) yield strength, 12% elongation and 39% reduction of area. Another test bar which was processed in the same manner as above, except tempered at 232°C (450°F) exhibited 3.27 MPa (215 ksi) ultimate tensile strength, 2.81 MPa (185 ksi) yield strength, 7% elongation and 21% reduction of area. Thus, one may easily develop a desired set of mechanical properties in the consolidated core piece by tempering a selected temperature.

In another example, powder slurry for the wear resistant exterior skin and the thrust bearing surface was prepared using a 1.5% by weight mixture of cellulose acetate with Stellite alloy No. 1 powder. This preform was dried at 121°C (250°F) for two hours instead of 37.8°C (100°F) for overnight and the remaining processing steps were identical to the above example. No visible differences were detected between the two parts produced by the two experiments.

In yet another example, radial bearing alloy was affixed to the interior wall of the core through the use of nickel powder slurry similarly prepared as above. Once again the bond between the radial bearing alloy and the core piece was extremely strong as determined by separately conducted bonding experiments.

Other pertinent information

The term "composite" is used both in the micro-structural sense or from an engineering sense, whichever is more appropriate. Thus, a material made up of discrete fine phase(s) dispersed within another phase is considered a composite of phases, while a structure made up of discrete, relatively large regions joined or assembled by some means, together is also considered a "composite". An alloy layer composed of a mixture of carbide particles in cobalt, would micro-structurally be a composite layer, while a cone cutter composed of various distinct layers, TCI's and other inserts, would be a composite part as well.

The term "green" in Table 1, line 2, refers to a state where the powder metal part is not yet fully densified, but has sufficient strength to be handled without chipping or breakage. Sintering, (the same table, line 3), is a process by which powdered (or otherwise) material is put in intimate contact and heated to cause a metallurgical bond between them.

Preferred embodiments of this invention introduces, for the first time, the following novel features to a TCI drill bit cone:

(1) a "high temperature-short heating cycle" means of consolidation of a composite cone into a nearly finished product, saving substantial labour time and allowing the use of multiple materials tailored to meet localised demands on their properties.

(2) Various material layers are applied at or near room temperature, thus eliminating damage that would otherwise be occurring if a thermally-activated process was used.

(3) Unlike hot isostatic pressing (HIP) inside an autoclave pressurised by gas, the hot pressing, as described herein, requires only a short time at high consolidation temperatures. This is partially due to the fact that rapid heating techniques most particularly usable in hot pressing, may be not suitable for heating inside an autoclave. This is a major advantage for the hot pressing process, whereby bonding of discrete particles takes place quickly (few minutes) without unwanted diffusion reactions. Thus, consolidation of a composite part, such as the conical cutter, is accomplished without any side effects, whereas in HIP, processing cycle takes up to 20... sometimes 30 hours, mostly at high temperatures. Diffusion of such elements as carbon from the carbides, for example, then creates metallurgical problems of structural integrity. In the absence of such fears, as in the present method, the conical cutters have superior properties and superior field performance, and furthermore no diffusion barrier layer between the carbides and the cone material would be necessary.

- (4) The use of non-parallel sided inserts.
 (5) The use of a hard wear-resistant exterior layer, for example painted on cold, the same hard layer surrounding and locking the TCI in place after hot consolidation. The latter feature greatly simplifies the method of application of the exterior layer.
- 5 (6) Provision of lubricious inserts or insert, plus powder metal layers providing the thrust-bearing surface layer.
- (7) Elimination of lengthy surface hardening processes such as carburizing.
- (8) Vastly increased freedom of selection of materials.
- (9) Increased freedom to extend the TCI's further outward for more aggressive cutting of the rock.
- 10 Figure 2 shows the conical bit cutter 10 of the invention applied to the journal pin 50 on a bit body 51, having a threaded stem 52. Pin 50 also provides a ball bearing race 53 adapted to register with race surface 20 about zone 12b, and journal bearing 54 adapted to mount layer 15 as described.
- Step 3 of the process as listed in Table 1 is for example shown in Figure 7a, the arrows 100 and 101 indicating isostatic pressurisation of both interior and exterior surfaces of the core piece 11. Pressure application is effected for example by the use of rubber moulds or ceramic granules packed about the core, and pressurised. Blind holes are shown at 103. Steps 5—10 of the Table 1 process are indicated in Figure 7b. Step 11 of the process is exemplified by the induction heating step of Figure 7c.
- 15 In Figure 7d, the hot part (cone, as in Figure 1) is indicated at 99 as embedded in hot ceramic grain 106, in shuttle die 107. The latter is then introduced into a press die 108 (see Figure 7e), and the outer wall 107a of the shuttle die is upwardly removed. Die 108 has cylindrical wall 108a and bottom wall 108b. Figure 7f is like Figure 7e, but shows a plunger 109 applying force to the grain 106, in response to fluid pressure application at 110 to the plunger via actuator cylinder 111. This corresponds to step 12 of the Table 1 process. In Figure 7g the part 99 and grain 106 are upwardly ejected by a second plunger 112 elevating the bottom wall 107.
- 20 In Figure 7g, the grain is removed from the part 106 and is recycled to step 7d. The consolidated part including its component may then be finished, as by grit blasting, finish machining and grinding, and inspected. See Step 15 of Table 1.

Claims

- 30 1. A roller bit cutter (10), comprising, in combination:
 a) a tough, metallic generally conical and fracture resistant core (11) having a hollow interior (12), the core defining an axis (13);
 b) an annular metallic radial bearing layer (15) carried by said core at the interior thereof to support the
 35 core for rotation, said bearing layer (15) extending about said axis;
 c) an impact and wear resistant metallic inner layer (16) on the core (11), at the interior thereof, to provide an axial thrust bearing; and
 d) hard metallic inserts (17; 170; 270; 370) having anchor portions (17a) carried by the core (11) and partly embedded in recesses (18) therein, the inserts protruding outwardly at the exterior of the core (11) to
 40 define cutters, at least some of the inserts being spaced about said axis (13);
 e) and a wear resistant outer metallic layer (19) on the exterior of said core (11) which layer extends into said recesses (18) and between the core (11) and said insert anchor portions (17a).
2. A roller bit cutter (10) as claimed in claim 1 wherein said inserts (17; 170; 270; 370) consist essentially of tungsten carbide.
- 45 3. A roller bit cutter (10) as claimed in claim 1 or claim 2 wherein at least one of said layers (15, 16, 19) consists essentially of consolidated powder metal.
4. A roller bit cutter (10) as claimed in claim 3 wherein at least two of said layers (15, 16, 19) consist of consolidated powder metal.
5. A roller bit cutter (10) as claimed in claim 4 wherein all three of said layers (15, 16, 19) consist of
 50 consolidated powder metal.
6. A roller bit cutter (10) as claimed in any preceding claim wherein the insert anchor portions (370) have non-symmetrically flared ends (370a), and said outer layer (19) has flared portions compressively engaging said insert flared ends, in said recesses.
7. A roller bit cutter (10) as claimed in any preceding claim wherein said core (11) consists essentially of
 55 steel alloyed with elements selected from: carbon, manganese, silicon, nickel, chromium, molybdenum and copper.
8. A roller bit cutter (10) as claimed in claim 7 wherein said elements have the following weight percentage:

carbon	0.0 to 0.65
manganese	0.01 to 2.0
60 silicon	0.01 to 2.2
nickel	0.40 to 3.75
chromium	0.01 to 1.2
molybdenum	0.15 to 0.40
65 copper	0 to 0.3.



(4) The use of non-parallel sided inserts.

() The use of a hard wear-resistant exterior layer, for example painted on cold, the same hard layer surrounding and locking the TCI in place after hot consolidation. The latter feature greatly simplifies the method of application of the exterior layer.

5 (6) Provision of lubricious inserts or insert, plus powder metal layers providing the thrust-bearing surface layer.

(7) Elimination of lengthy surface hardening processes such as carburizing.

(8) Vastly increased freedom of selection of materials.

(9) Increased freedom to extend the TCI's further outward for more aggressive cutting of the rock.

10 Figure 2 shows the conical bit cutter 10 of the invention applied to the journal pin 50 on a bit body 51, having a threaded stem 52. Pin 50 also provides a ball bearing race 53 adapted to register with race surface 20 about zone 12b, and journal bearing 54 adapted to mount layer 15 as described.

Step 3 of the process as listed in Table 1 is for example shown in Figure 7a, the arrows 100 and 101 indicating isostatic pressurisation of both interior and exterior surfaces of the core piece 11. Pressure application is effected for example by the use of rubber moulds or ceramic granules packed about the core, and pressurised. Blind holes are shown at 103. Steps 5—10 of the Table 1 process are indicated in Figure 7b. Step 11 of the process is exemplified by the induction heating step of Figure 7c.

20 In Figure 7d, the hot part (cone, as in Figure 1) is indicated at 99 as embedded in hot ceramic grain 106, in shuttle die 107. The latter is then introduced into a press die 108 (see Figure 7e), and the outer wall 107a of the shuttle die is upwardly removed. Die 108 has cylindrical wall 108a and bottom wall 108b. Figure 7f is like Figure 7e, but shows a plunger 109 applying force to the grain 106, in response to fluid pressure application at 110 to the plunger via actuator cylinder 111. This corresponds to step 12 of the Table 1 process. In Figure 7g the part 99 and grain 106 are upwardly ejected by a second plunger 112 elevating the bottom wall 107.

25 In Figure 7g, the grain is removed from the part 106 and is recycled to step 7d. The consolidated part including its component may then be finished, as by grit blasting, finish machining and grinding, and inspected. See Step 15 of Table 1.

Claims

30

1. A roller bit cutter (10), comprising, in combination:

a) a tough, metallic generally conical and fracture resistant core (11) having a hollow interior (12), the core defining an axis (13);

35 b) an annular metallic radial bearing layer (15) carried by said core at the interior thereof to support the core for rotation, said bearing layer (15) extending about said axis;

c) an impact and wear resistant metallic inner layer (16) on the core (11), at the interior thereof, to provide an axial thrust bearing; and

40 d) hard metallic inserts (17; 170; 270; 370) having anchor portions (17a) carried by the core (11) and partly embedded in recesses (18) therein, the inserts protruding outwardly at the exterior of the core (11) to define cutters, at least some of the inserts being spaced about said axis (13);

e) and a wear resistant outer metallic layer (19) on the exterior of said core (11) which layer extends into said recesses (18) and between the core (11) and said insert anchor portions (17a).

2. A roller bit cutter (10) as claimed in claim 1 wherein said inserts (17; 170; 270; 370) consist essentially of tungsten carbide.

45 3. A roller bit cutter (10) as claimed in claim 1 or claim 2 wherein at least one of said layers (15, 16, 19) consists essentially of consolidated powder metal.

4. A roller bit cutter (10) as claimed in claim 3 wherein at least two of said layers (15, 16, 19) consist of consolidated powder metal.

50 5. A roller bit cutter (10) as claimed in claim 4 wherein all three of said layers (15, 16, 19) consist of consolidated powder metal.

6. A roller bit cutter (10) as claimed in any preceding claim wherein the insert anchor portions (370) have non-symmetrically flared ends (370a), and said outer layer (19) has flared portions compressively engaging said insert flared ends, in said recesses.

55 7. A roller bit cutter (10) as claimed in any preceding claim wherein said core (11) consists essentially of steel alloyed with elements selected from: carbon, manganese, silicon, nickel, chromium, molybdenum and copper.

8. A roller bit cutter (10) as claimed in claim 7 wherein said elements have the following weight percentage:

60	carbon	0.0 to 0.65
	manganese	0.01 to 2.0
	silicon	0.01 to 2.2
	nickel	0.40 to 3.75
	chromium	0.01 to 1.2
	molybdenum	0.15 to 0.40
65	copper	0 to 0.3.



9. A roller bit cutter (10) as claimed in any of claims 1 to 6 wherein said core consists essentially of cast alloy steel.

10. A roller bit cutter (10) as claimed in any of claims 1 to 6 wherein said core (11) consists of ultra high strength steel.

11. A roller bit cutter (10) as claimed in claim 10 wherein said steel is selected from the group consisting of D-6A, H-1, 9Ni-4Co, 18-Ni maraging, 300-M (4134, 4330V and 4340).

12. A roller bit cutter (1) as claimed in any of claims 1 to 6 wherein said core (11) consists of consolidated ferrous powder metal steel having the following composition, with percentages being by weight:

iron	79 to 80%
copper	0 to 20%
carbon	0.4 to 1.0%
nickel	0 to 4.0%.

13. A roller bit cutter (10) as claimed in any one of claims 1 to 8 wherein the core (11) has mechanical properties in excess of the following lower limits:

1.98 MPa (130 ksi) ultimate tensile strength
1.22 MPa (80 ksi) yield strength
5% tensile elongation
15% reduction in area
13.6 Nm (10 ft-lb) (izod) impact strength.

14. A roller bit cutter (10) as claimed in any preceding claim wherein said outer layer (19) consists of a composite mixture of refractory particles in a binder metal.

15. A roller bit cutter (10) as claimed in claim 14 wherein said refractory particles have micro hardness in excess of 1,000 kg/mm², and a melting point in excess of 1,600°C.

16. A roller bit cutter (10) as claimed in claim 14 or claim 15 wherein said refractory particles are selected from the group consisting of Ti, W, Al, V, Zr, Cr, Mo, Ta, Nb, Hf and carbides, oxides, nitrides and borides thereof.

17. A roller bit cutter (10) as claimed in claim 1 wherein said outer layer consists of tool steel initially in powder form.

18. A roller bit cutter (10) as claimed in claim 1 wherein said outer layer consists of a hardfacing alloy having a composition selected from one of the following three columnar groups:

	Cobalt base	Nickel base	Iron base
Chromium	25—30%*	10—30%	0—27%
Carbon	0.1—3.5%	0.4—3.0%	0.1—4.0
Tungsten	4—13%	0—5.0%	—
Molybdenum	0—5%	0—17.0%	0—11%
Boron	0—2.5%	0—5.0%	—
Iron	0—3.0%	3—29%	Balance
Nickel	0—3.0%	Balance	0—1.75%
Cobalt	Balance	0—12%	—
Silicon	0—2.0%	0—4.5%	0—1.5%
Manganese	0—1.0%	0—1.0%	0—1.0%

*percentages by weight

19. A roller bit cutter (10) as claimed in claim 1 wherein said outer layer consists of wear resistant, intermetallic Laves phase, materials based on a primary constituent selected from the group consisting of cobalt and nickel, and having the following alloying elements, with indicated weight percentages:

molybdenum	25 to 35%
chromium	8 to 18%
silicon	2 to 4%
carbon	0 to 0.08%.

20. A roller bit cutter (10) as claimed in claim 1 wherein said inner layer consists of one of the compositions defined in one of claims 18 to 20.

21. A roller bit cutter (10) as claimed in any preceding claim wherein said anchor portions are flared toward the exterior of the core.



22. A roller bit (10, 50, 51) incorporating a roller bit cutter (10) as claimed in any preceding claim, said (11) and bearing layer (15) being carried for rotation in a drilling operation on said roller bit.
23. A method of producing a roller bit cutter (10), that includes the steps:
- a) providing a tough, metallic generally conical and fracture resistant core (11) having a hollow interior (12) and recesses (18) in its exterior, the core (11) defining an axis (13) and at least some of the recesses being spaced about said axis,
 - b) providing an annular metallic radial bearing layer (15) carried by said core at the interior thereof to support the core for rotation, said bearing layer extending about said core,
 - c) providing an impact and wear resistant metallic inner layer (16) on the core, at the interior thereof, to provide an axial thrust bearing,
 - d) providing hard metallic inserts (17; 170; 270; 370) having anchor portions (17a) carried by the core and partly embedded in said recesses (18) therein, the inserts protruding outwardly at the exterior of the core to define cutters, at least some of the inserts being spaced about said axis,
 - e) and providing a wear resistant outer metallic layer (19) on the exterior of said core, which layers extends into said recesses (18) and between the core (11) and said insert anchor portions (17a).

Patentansprüche

1. Rollenmeißelschneidkopf (10), welcher in Kombination aufweist:
 - a) einen widerstandsfähigen, metallischen, insgesamt konischen und bruchfesten Kern (11), der einen hohlen Innenraum (12) hat, wobei der Kern eine Achse (13) festlegt;
 - b) eine ringförmige, metallische, radiale Lagerschicht (15), die von dem Kern an seinem Innenraum zur Lagerung des Kerns für eine Rotation getragen wird, wobei die Lagerschicht (15) sich um die Achse herum erstreckt;
 - c) eine stoß- und verschleißfeste, metallische Innenschicht (16) an dem Kern (11) an seinem Innenraum zur Schaffung eines axialen Drucklagers; und
 - d) harte, metallische Einsätze (17; 170; 270; 370), die Verankerungsabschnitte (17a) aufweisen und von dem Kern (11) getragen und teilweise in Aussparungen (18) darin eingebettet sind, wobei die Einsätze nach außen am Äußeren des Kerns (11) zur Bildung von Schneideinrichtungen vorgesehen oder wenigstens einige der Einsätze um die Achse (13) herum im Abstand angeordnet sind;
 - e) und eine verschleißfeste, äußere metallische Schicht (19) außen am Kern (11), die sich in die Aussparungen (18) und zwischen dem Kern (11) und den Einsatzverankerungsabschnitten (17a) erstreckt.
2. Rollenmeißelschneidkopf (10) nach Anspruch 1, bei welchem die Einsätze (17; 170; 270; 370) im wesentlichen aus Wolframkarbid bestehen.
3. Rollenmeißelschneidkopf (10) nach Anspruch 1 oder Anspruch 2, bei welchem wenigstens eine der Schichten (15, 16, 19) im wesentlichen aus verfestigtem Pulvermetall besteht.
4. Rollenmeißelschneidkopf (10) nach Anspruch 3, bei welchem wenigstens zwei der Schichten (15, 16, 19) aus verfestigtem Pulvermetall bestehen.
5. Rollenmeißelschneidkopf (10) nach Anspruch 4, bei welchem alle drei der Schichten (15, 16, 19) aus verfestigtem Pulvermetall bestehen.
6. Rollenmeißelschneidkopf (10) nach einem vorhergehenden Anspruch, bei welchem die Einsatzverankerungsabschnitte (370) sich nicht symmetrisch erweiternde Enden (370a) aufweisen und bei welchem die äußere Schicht (19) sich erweiternde Abschnitte aufweist, welche in Druckeingriff mit den sich erweiternden Einsatzenden in den Ausnehmungen stehen.
7. Rollenmeißelschneidkopf (10) nach einem vorhergehenden Anspruch, bei welchem der Kern (11) im wesentlichen aus Stahl besteht, der mit Elementen legiert ist, die ausgewählt sind aus Kohlenstoff, Mangan, Silizium, Nickel, Chrom, Molybdän und Kupfer.
8. Rollenmeißelschneidkopf (10) nach Anspruch 7, bei welchem die Elemente die folgenden Gewichtsprozente haben:

50	Kohlenstoff	0,0 bis 0,65
	Mangan	0,01 bis 2,0
	Silizium	0,01 bis 2,2
	Nickel	0,40 bis 3,75
	Chrom	0,01 bis 1,2
55	Molybdän	0,15 bis 0,40
	Kupfer	0 bis 0,3.

9. Rollenmeißelschneidkopf (10) nach einem der Ansprüche 1 bis 6, bei welchem der Kern im wesentlichen aus Gußlegierungsstahl besteht.
10. Rollenmeißelschneidkopf (10) nach einem der Ansprüche 1 bis 6, bei welchem der Kern (11) aus ultrahochfestem Stahl besteht.
11. Rollenmeißelschneidkopf (10) nach Anspruch 10, bei welchem der Stahl aus der Gruppe ausgewählt ist, die aus D-6A, H-1, 9Ni-4Co, 18-Ni mit Martensithärtung, 300-M (4134, 4330V und 4340) besteht.



12. Rollenmeißelschneidkopf (1) nach einem der Ansprüche 1 bis 6, bei welchem der Kern (11) aus verfestigtem Eisenpulvermetallstahl besteht, der die folgende Zusammensetzung hat, wobei die Prozentsätze Gewichtsprozentsätze sind:

5	Eisen	79 bis 80%
	Kupfer	0 bis 20%
	Kohlenstoff	0,4 bis 1,0%
	Nickel	0 bis 4,0%.

13. Rollenmeißelschneidkopf (10) nach einem der Ansprüche 1 bis 8, bei welchem der Kern (11) mechanische Eigenschaften hat, die über die folgenden unteren Grenzen hinausgehen:

	1,98 MPa (130 ksi) Zugfestigkeit
	1,22 MPa (80 ksi) Streckgrenze
15	5% Dehnung
	15% Querschnittsverringering
	1,36 Nm (10 ft-lb) (izod) Schlagfestigkeit.

14. Rollenmeißelschneidkopf (10) nach einem vorhergehenden Anspruch, bei welchem die äußere Schicht (19) aus einer Verbundmischung aus feuerfesten Teilchen in einem Bindemetall besteht.

15. Rollenmeißelschneidkopf (10) nach Anspruch 14, bei welchem die feuerfesten Teilchen eine Mikrohärtigkeit von mehr als 1000 kg/mm² und einen Schmelzpunkt von mehr als 1600°C haben.

16. Rollenmeißelschneidkopf (10) nach Anspruch 14 oder Anspruch 15 bei welchem die feuerfesten Teilchen aus der Gruppe ausgewählt sind, die aus Ti, W, Al, V, Zr, Cr, Mo, Ta, Nb, Hf sowie Karbiden, Oxyden, Nitriden und Boriden davon besteht.

17. Rollenmeißelschneidkopf (10) nach Anspruch 1, bei welchem die äußere Schicht aus ursprünglich in Pulverform vorliegendem Werkzeugstahl besteht.

18. Rollenmeißelschneidkopf (10) nach Anspruch 1, bei welchem die äußere Schicht aus einer Aufschweißlegierung besteht, die eine Zusammensetzung hat, welche aus einer der folgenden drei, in 30 Kolonnen aufgeführten Gruppen ausgewählt ist:

	Kobaltbasis	Nickelbasis	Eisenbasis
35	Chrom 25—30% *	10—30%	0—27%
	Kohlenstoff 0,1—3,5%	0,4—3,0%	0,1—4,0
	Wolfram 4—13%	0—5,0%	—
	Molybdän 0—5%	0—17,0%	0—11%
	Bor 0—2,5%	0—5,0%	—
	Eisen 0—3,0%	3—29%	Rest
40	Nickel 0—3,0%	Rest	0—1,75%
	Kobalt Rest	0—12%	—
	Silizium 0—2,0%	0—4,5%	0—1,5%
	Mangan 0—1,0%	0—1,0%	0—1,0%

45 *Gewichtsprozent

19. Rollenmeißelschneidkopf (10) nach Anspruch 1, bei welchem die äußere Schicht aus einer verschleißfesten intermetallischen Laves-Phase besteht, wobei die Materialien auf der Basis eines Grundmetalls aus der Gruppe ausgewählt sind, die aus Kobalt und Nickel besteht, und die folgenden Legierungselemente aufweisen, die in Gewichtsprozenten angegeben sind:

55	Molybdän	25 bis 35%
	Chrom	8 bis 18%
	Silizium	2 bis 4%
	Kohlenstoff	0 bis 0,08%.

20. Rollenmeißelschneidkopf (10) nach Anspruch 1, bei welchem die innere Schicht aus einem der in einem der Ansprüche 18 bis 20 definierten Zusammensetzungen besteht.

21. Rollenmeißelschneidkopf (10) nach einem vorhergehenden Anspruch, bei welchem die Verankerungsabschnitte sich zu dem Äußeren des Kerns hin erweitern.

22. Rollenmeißel (10, 50, 51) mit einem Rollenmeißelschneidkopf (10) nach einem vorhergehenden Anspruch, wobei der Kern (11) und die Lagerschicht (15) für die Rotation in einem Bohrvorgang an dem Rollenmeißel gehalten sind.

23. Verfahren zur Herstellung eines Rollenmeißelschneidkopfs (10), welches die folgenden Schritte aufweist:



- a) Schaffen eines widerstandsfähigen, metallischen, insgesamt konischen und bruchfesten Kerns (11),
 5 den hohlen Innenraum (12) und Aussparungen (18) in seinem Äußeren aufweist, wobei der Kern (11)
 eine Achse (13) festlegt und wenigstens einige der Aussparungen im Abstand um die Achse angeordnet
 sind,
 b) Schaffung einer ringförmigen, metallischen, radialen Lagerschicht (15), die von dem Kern an seinem
 Innenraum zur Lagerung des Kerns für eine Rotation getragen wird, wobei die Lagerschicht sich um den
 Kern erstreckt,
 c) Schaffen einer stoß- und verschleißfesten, metallischen Innenschicht (16) an dem Kern an seinem
 Innenraum zur Bildung eines axialen Drucklagers,
 10 d) Schaffung harter, metallischer Einsätze (17; 170; 270; 370), die Verankerungsabschnitte (17a)
 aufweisen, welche von dem Kern getragen werden und teilweise in den Aussparungen (18) eingebettet
 sind, wobei die Einsätze nach Außen am Äußeren des Kerns zur Bildung von Schneideinrichtungen
 vorstehen oder wenigstens einige der Einsätze im Abstand um die Achse angeordnet sind,
 e) Schaffung einer verschleißfesten, äußeren, metallischen Schicht (19) am Äußeren des Kerns, wobei
 15 sich die Schicht in die Aussparungen (18) und zwischen dem Kern (11) und die Einsatzverankerungsab-
 schnitte (17a) erstreckt.

Revendications

- 20 1. Outil de coupe tournant pour trépan (10), comprenant, en combinaison:
 a) un noyau (11) dur, métallique de forme générale conique et résistant à la rupture comportant un
 intérieur creux (12), le noyau définissant un axe (13);
 b) une couche (15) formant palier radial métallique annulaire portée par ledit noyau à l'intérieur de
 25 celui-ci pour supporter le noyau en vue de sa rotation, ladite couche (15) formant palier s'étendant autour
 dudit axe,
 c) une couche interne métallique résistant au choc et à l'usure sur le noyau (11) à l'intérieur de ce
 dernier pour constituer un palier de butée axial; et
 d) des inserts métalliques durs (17, 170, 270, 370) comportant des parties d'ancrage (17a) portées par le
 30 noyau (11) et noyées partiellement dans des cavités (18) de ce dernier, les inserts faisant saillie vers
 l'extérieur, à l'extérieur du noyau (11) pour définir des couteaux, au moins certains des inserts étant
 espacés autour dudit axe (13);
 e) et une couche (19) métallique extérieure résistant à l'usure sur l'extérieur dudit noyau (11) laquelle
 couche s'étend à l'intérieur des cavités (18) et entre le noyau (11) et lesdites portions d'ancrage (17a) des
 35 inserts.
 2. Outil de coupe tournant pour trépan (10) tel que revendiqué dans la revendication 1 dans lequel
 lesdits inserts (17, 170, 270, 370) sont réalisés essentiellement en carbure de tungstène.
 3. Outil de coupe tournant pour trépan (10) tel que revendiqué dans la revendication 1 ou la
 revendication 2, dans lequel au moins l'une desdites couches (15, 16, 19) consiste essentiellement en une
 40 poudre métallique compactée.
 4. Outil de coupe tournant pour trépan (10) tel que revendiqué dans la revendication 3 dans lequel au
 moins deux desdites couches (15, 16, 19) consistent en de la poudre métallique compactée.
 5. Outil de coupe tournant pour trépan (10) tel que revendiqué dans la revendication 4 dans lequel les
 trois couches (15, 16, 19) consistent en de la poudre métallique compactée.
 45 6. Outil de coupe tournant pour trépan (10) tel que revendiqué dans l'une quelconque des
 revendications précédentes dans lequel les parties d'ancrage d'inserts (370) ont des extrémités évasées
 non-symétriques (370a), et ladite couche extérieure (19) comporte des parties évasées qui coopèrent en
 compression avec lesdites extrémités évasées des inserts, dans lesdites cavités.
 7. Outil de coupe tournant pour trépan (10) tel que revendiqué dans l'une quelconque des
 50 revendications précédentes dans lequel ledit noyau (11) consiste essentiellement en de l'acier allié avec
 des éléments choisis parmi: le carbone, le manganèse, le silicium, le nickel, le chrome, le molybdène et le
 cuivre.
 8. Outil de coupe tournant pour trépan (10) tel que revendiqué dans la revendication 7 dans lequel
 lesdits éléments ont les pourcentages suivants, en poids:

55	carbone	0,0 à 0,65
	manganèse	0,01 à 2,0
	silicium	0,01 à 2,2
	nickel	0,40 à 3,75
	chrome	0,01 à 1,2
60	molybdène	0,15 à 0,40
	cuivre	0 à 0,3.

9. Outil de coupe tournant pour trépan (10) tel que revendiqué dans l'une quelconque des
 65 revendications 1 à 6 dans lequel ledit noyau consiste essentiellement en de l'acier allié moulé.



10. Outil de coupe tournant pour trépan (10) tel que revendiqué dans l'une quelconque des revendications 1 à 6 dans lequel ledit noyau (11) consiste en de l'acier à très haute résistance.

11. Outil de coupe tournant pour trépan (10) tel que revendiqué dans la revendication 10 dans lequel ledit acier est choisi dans le groupe consistant en D-6A, H-1, 9Ni-4Co, 18-Ni maraging, 300-M (4134, 4330V and 4340).

12. Outil de coupe tournant pour trépan (10) tel que revendiqué dans l'une quelconque des revendications 1 à 6 dans lequel ledit noyau (11) consiste en de l'acier se présentant sous la forme d'une poudre de fer compactée ayant la composition suivante, les pourcentages étant indiqués en poids:

10	fer	79 à 80%
	cuivre	0 à 20%
	carbone	0,4 à 1,0%
	nickel	0 à 4,0%.

13. Outil de coupe tournant pour trépan (10) tel que revendiqué dans l'une quelconque des revendications 1 à 8 dans lequel le noyau (11) a des propriétés mécaniques meilleures que les limites inférieures suivantes:

20	résistance à la traction maximale 1,98 MPa (130 ksi)
	résistance à la traction 1,22 MPa (80 ksi)
	allongement à la traction 5%
	réduction en section 15%
	résistance au choc 13,6 Nm (10-ft-lb) (izod).

14. Outil de coupe tournant pour trépan (10) tel que revendiqué dans l'une quelconque des revendications précédentes dans lequel la couche extérieure (19) consiste en un mélange composite de particules réfractaires dans un métal formant liant.

15. Outil de coupe tournant pour trépan (10) tel que revendiqué dans la revendication 14 dans lequel lesdites particules réfractaires ont une micro-dureté dépassant 1 000 kg/mm², et un point de fusion dépassant 1 600°C.

16. Outil de coupe tournant pour trépan (10) tel que revendiqué dans la revendication 14 ou la revendication 15 dans lequel lesdites particules réfractaires sont choisies dans le groupe consistant en Ti, W, Al, V, Zr, Cr, Mo, Ta, Nb, Hf et leurs carbures, oxydes, nitrures et borures.

17. Outil de coupe tournant pour trépan (10) tel que revendiqué dans la revendication 1 dans lequel ladite couche extérieure consiste en de l'acier à outil qui se trouve initialement sous la forme d'une poudre.

18. Outil de coupe tournant pour trépan (10) tel que revendiqué dans la revendication 1 dans lequel ladite couche extérieure consiste en un alliage à surface dure dont la composition est choisie parmi l'un des groupes présenté sous forme de colonnes ci-dessous, en pourcentages, en poids

40		Base cobalt	Base nickel	Base iron
	Chrome	25—30%	10—30%	0—27%
	Carbone	0,1—3,5%	0,4—3,0%	0,1—4,0
45	Tungstène	4—13%	0—5,0%	—
	Molybdène	0—5%	0—17,0%	0—11%
	Bore	0—2,5%	0—5,0%	—
	Fer	0—3,0%	3—29%	reste
	Nickel	0—3,0%	reste	0—1,75%
50	Cobalt	reste	0—12%	—
	Silicium	0—2,0%	0—4,5%	0—1,5%
	Manganèse	0—1,0%	0—1,0%	0—1,0%

19. Outil de coupe tournant pour trépan (10) tel que revendiqué dans la revendication 1 dans lequel ladite couche extérieure consiste en des matériaux résistant en phase intermétallique basés sur un constituant primaire sélectionné dans le groupe comprenant le cobalt et le nickel et ayant les éléments d'alliage suivants, qui sont indiqués en pourcentages, en poids:

60	molybdène	25 à 35%
	chrome	8 à 18%
	silicium	2 à 4%
	carbone	0 à 0,08%.

20. Outil de coupe tournant pour trépan (10) tel que revendiqué dans la revendication 1 dans lequel ladite couche interne consiste en une des compositions définies dans l'une des revendications 18 à 20.

21. Outil de coupe tournant pour trépan (10) tel que revendiqué dans l'une quelconque des revendications précédentes dans lequel lesdites parties d'ancrage sont évasées vers l'extérieur du noyau.

22. Trépan (10, 50, 51) comportant un outil de coupe tournant (10) tel que revendiqué dans l'une des revendications précédentes, ledit noyau (11) et la couche formant palier (15) étant portés en vue de leur rotation dans une opération de forage effectuée par ledit trépan.

23. Procédé pour fabriquer un outil de coupe tournant pour trépan (10) qui comporte les étapes suivantes

a) on utilise un noyau (11) dur, généralement conique et résistant à la rupture ayant un intérieur creux (12) et des cavités (18) dans son extérieur, le noyau (11) définissant un axe (13) et au moins certaines des cavités étant espacées autour dudit axe,

b) on utilise une couche radiale métallique annulaire formant palier (15) portée par ledit noyau à l'extérieur de celui-ci pour supporter le noyau en rotation, ladite couche formant palier s'étendant autour dudit noyau,

c) on applique une couche interne (12) métallique résistant au choc et à l'usure sur le noyau, à l'extérieur de celui-ci, pour constituer un palier de butée axiale,

d) on introduit des inserts métalliques durs (117, 170, 270, 370) comportant des parties d'ancrage (17a) portées par le noyau et partiellement noyées dans lesdites cavités (18) de celui-ci, les inserts faisant saillie vers l'extérieur, à l'extérieur du noyau pour définir des couteaux, au moins certains des inserts étant espacés par rapport audit axe,

e) et on applique une couche métallique extérieure résistant à l'usure (19) à l'extérieur dudit noyau, laquelle couche s'étend à l'intérieur desdites cavités (18) et entre le noyau (11) et lesdites parties d'ancrage d'inserts (17a).

