

## Cationic Surfactant Systems Comprising Microfibrous Cellulose

### BACKGROUND OF THE INVENTION

5 [0001] Cationic surfactant-based products such as anti-bacterial surface cleaners, fabric softeners, skin conditioners, hair conditioners, conditioning shampoos, among others, are often difficult to thicken with conventional thickeners. Many common thickeners such as xanthan gum, CMC (carboxymethylcellulose), carrageenan, and polyacrylates are anionic and therefore, can react with the cationic surfactants and cause precipitation of the cationic and thickener or  
10 reduce the efficacy of the cationic surfactant. Non-ionic thickeners such as hydroxyethylcellulose (HEC), hydroxypropylmethylcellulose (HPMC), and scleroglucan can provide viscosity in cationic systems, however in the case of HEC and HPMC, very little suspension properties are imparted to the fluid. In the case of scleroglucan, good suspension is often achieved but cost-in use can be prohibitive. Cationic thickeners such as polyquaternium  
15 10 (cationic HEC) and cationic guar provide thickening in cationic systems but not suspension. Some forms of polyacrylates are effective at thickening cationic systems but they can be limited by pH, require high concentrations, have high cost-in-use, and often have narrow limits of compatibility with the cationic surfactants.

[0002] There is a need in industry to provide reliable suspension and viscosity to  
20 cationic surfactant systems. In these systems, the suspension of particles is often desired and such particulates might include abrasive agents, aesthetic agents (decorative beads, pearlescents, air bubbles, fragrance beads, etc.) or active ingredients (insoluble enzymes, encapsulated actives such as moisturizers, zeolites, exfoliating agents (e.g. alpha hydroxyl and/or glycolic acids or polyethylene beads), vitamins (e.g. vitamin E)) etc. or both.

25 [0003] It has been discovered that microfibrinous cellulose (MFC), bacterially derived or otherwise, can be used to provide suspension of particulates in cationic systems. It was also discovered that the MFC may be used for this purpose with or without co-agents. When bacterially-derived microfibrinous cellulose is utilized, cellular debris can be eliminated which can also result in transparent solutions at typical use levels with some formulations.

30 [0004] The microfibrinous cellulose is non-ionic and is therefore unaffected by the cationic surfactants and maintains good suspension in these systems. Microfibrinous cellulose is

unique in its ability to function in these systems in part because it is dispersed rather than solubilized, thereby allowing its use in a wide range of pH and cationic surfactant concentrations without concern of precipitating the polymer due to "salting out" or other effects related to the competition for water.

DE10215602 (Henkel) discloses a composition comprising 0.5% Cellulon® (microfibrous cellulose), 2.5% Stepanex VA90 (a cationic surfactant) and 0.04% cellulase. WO00/40153 (Monsanto) discloses an acid stable and cationic compatible high surface area cellulose composition.

WO2006/127810 describes a method for the production of a bacterial cellulose through fermentation, the formulation comprising at least one bacterial cellulose material and at least one polymeric thickener.

#### BRIEF SUMMARY OF THE INVENTION

[0005] Cationic surfactant systems comprising microfibrous cellulose are described. "Cationic systems" is intended to include but is not limited to cationic surfactants used in industrial and personal care applications for anti-microbial, fabric softening, and skin and hair conditioning. Microfibrous cellulose (MFC) includes MFC prepared by microbial fermentation or MFC prepared by mechanically disrupting/altering cereal, wood, or cotton-based cellulose fibers. When bacterially-derived microfibrous cellulose is utilized, cellular debris can be eliminated which results in transparent solutions at typical use levels. The present invention utilizes MFC to provide suspension of particulates in formulations containing cationic surfactants.

[0006] The cationic surfactant concentration of these systems ranges from about 0.1% to about 50% (w/w active surfactant) wherein the specific concentration is product dependent. Anti-bacterial household surface cleaners typically contain about 0.1% to about 4% (w/w) active cationic surfactant, hair and skin conditioners typically contain about 0.5% to about 3% cationic surfactants, and fabric softeners typically contain about 3% to about 15% (w/w) cationic surfactant (with 15% being a "concentrated" fabric softener product). Concentrates of the cationic surfactants can also be thickened for later dilution into formulated products. These concentrates can contain greater than 50% active cationic surfactant.

[0007] The MFC is present at concentrations from about 0.05% to about 1.0%, but the concentration will depend on the desired product. For example, while about 0.06% (w/w) MFC is preferred for suspending small alginate beads in a household cleaner containing 4% of the anti-bacterial cationic surfactant, benzylalkonium chloride, about 0.075% is preferred for suspending air bubbles in fabric softener.

[0008] Particulates to be suspended could include abrasive agents, aesthetic agents (decorative beads, pearlescents, air bubbles, fragrance beads, etc.) or active ingredients

(insoluble enzymes, encapsulated actives such as moisturizers, zeolites, exfoliating agents (e.g. alpha hydroxyl and/or glycolic acids or polyethylene beads), vitamins (e.g. vitamin E) etc. or both. Other suitable particulates would be apparent to one of skill in the art.

[0009] The invention is also directed to the use of co-agents and/or co-processing agents such as cationic HEC, cationic guar and/or guar gum with the microfibrinous cellulose in the surfactant systems described herein. Microfibrinous cellulose blends are microfibrinous cellulose products which contain co-agents. Four blends are described MFC, cationic guar, and guar in a ratio of 6:3:1, MFC and cationic guar in a ratio of 1:1 and 3:2 and MFC and cationic HEC in a ratio of 1:1. These blends allow MFC to be prepared as a dry product which can be "activated" with high shear or high extensional mixing into water or other water-based solutions. "Activation" occurs when the MFC blends are added to water and the co-agents/co-processing agents are hydrated. After the hydration of the co-agents/co-processing agents, high shear is generally then needed to effectively disperse the microfibrinous cellulose fibers to produce a three-dimensional functional network that exhibits a true yield point.

[00010] The invention is further directed to methods of making the cationic surfactant systems described, with or without co-agents and/or co-processing agents.

#### BRIEF DESCRIPTION OF THE SEVERAL VIEWS OF THE DRAWINGS

[00011] The foregoing summary will be better understood when read in conjunction with the Detailed Description of the Invention.

#### DETAILED DESCRIPTION OF THE INVENTION

[00012] A simplified anti-bacterial hard surface cleaner formulation demonstrating the cationic surfactant compatibility with 4% benzylalkonium chloride and suspension properties using a 0.15% MFC/cationic guar (1:1) blend are described in Example 1. The cleaner exhibits the ability to suspend beads.

[00013] Example 2 describes a concentrated commercial liquid fabric softener with about 7.5% cationic surfactant and 0.15% MFC/cationic guar (1:1) blend and alginate suspended therein.

[00014] A conditioning hair spray containing cationic surfactant and a 0.125% MFC/cationic guar (6:4) blend. This product has suspended glitter and is described in Example 3.

5 [00015] A wet-cake form of microfibrinous cellulose was used in Example 4 for preparing a high cationic surfactant system comprising a concentrated benzylalkonium solution. The 40% benzylalkonium chloride and 0.06% active MFC solution exhibits the ability to suspend alginate beads and is described in Example 4.

10 [00016] A wet-cake form of microfibrinous cellulose was used in Example 4 for preparing a high cationic surfactant system comprising a concentrated benzylalkonium solution. The 50% benzylalkonium chloride and 0.075% active MFC solution exhibits the ability to suspend air bubbles and is described in Example 5.

15

#### EXAMPLE 1

[00017] A simplified anti-bacterial hard surface cleaner containing 4% benzylalkonium chloride with suspended alginate beads was prepared. The cleaner exhibited a measurable yield value and possessed the ability to suspend air bubbles and beads. A yield value of 0.82 Pa (as measured with a Brookfield<sup>®</sup> Yield Rheometer) was obtained. A concentrate was first prepared containing 0.3% microfibrinous cellulose blend (MFC/cationic guar 1:1 blend) in deionized water. The concentrate was made by mixing the solution on an Oster<sup>®</sup> blender at "liquefy" (top speed) for 5 minutes. The microfibrinous cellulose mixture was then diluted 1:1 with an 8% solution of benzylalkonium chloride. The cationic solution was added to the microfibrinous cellulose solution while mixing at about 600 rpm with a jiffy mixing blade. Alginate beads were added to demonstrate suspension. Excellent suspension of air and/or alginate beads was achieved with no settling observed at room temperature or at 45°C for 3 months. The microfibrinous cellulose diluted well notwithstanding the relative low shear of the jiffy or propeller mixing blade.

20

25

30

## EXAMPLE 2

[00018] A concentrated commercial fabric softener containing about 7.5% cationic surfactant was prepared. "Downy® Clean Breeze™ ultra concentrated" liquid fabric softener was modified with MFC. A 0.3% microfibrinous cellulose blend (MFC/cationic guar 1:1 blend) concentrate was activated in distilled water with an Oster® blender set at top speed (liquefy) by mixing for 5 minutes. The microfibrinous cellulose solution was diluted 1:1 with Downy® ultra concentrated fabric softener while mixing at about 600 rpm with a jiffy mixing blade. Alginate beads were added to test suspension. Very good suspension of the beads was achieved for the dilution resulting in a yield point of 1.4 Pa (as measured with a Brookfield® Yield Rheometer). The fabric softener was put in a 45°C oven to assess heat stability and showed excellent stability with no loss in suspension over 4 weeks of aging.

## EXAMPLE 3

15

[00019] A conditioning hair spray with glitter suspended therein was prepared. The resulting hair spray exhibited good spray characteristics and excellent suspension properties. A yield value of about 0.2 Pa (as measured with a Brookfield® Yield Rheometer) was obtained.

[00020] Step A: Deionized water and disodium EDTA were added to a small Oster® mixing jar. Microfibrinous cellulose (MFC/cationic guar 6:4 blend) was added to the top of the water and then the Oster® mixer blade was assembled and the combination was mixed at top speed for 5 minutes ("Liquify" speed).

[00021] Step B: STS and fragrance were mixed with pre-warmed RH-40 and propylene glycol and solubilized in the water phase.

25 [00022] Step C: The remaining ingredients were added sequentially and mixed. The result was a low viscosity, sprayable hair conditioner with glitter suspended therein and a pH of 4.8.

[00023] Table 1: Sprayable Hair Conditioner with Suspension Properties

| Process Step | Ingredient | % (w/w) | Grams |
|--------------|------------|---------|-------|
|              |            |         |       |

|        |                                                                         |         |         |
|--------|-------------------------------------------------------------------------|---------|---------|
| A      | Deionized Water                                                         | 93.725  | 374.9   |
| A      | Microfibrous Cellulose blend<br>(MFC/cationic guar 6:4 blend)           | 0.125   | 0.5     |
| A      | Disodium EDTA                                                           | 0.1     | 0.4     |
| B      | Fragrance                                                               | To Suit |         |
| B      | Crodamol™ STS (Croda International Plc)                                 | 0.5     | 2       |
| B      | Cremophor™ RH 40 (BASF SE)                                              | 1.5     | 6       |
| B      | Propylene glycol                                                        | 0.75    | 3       |
| C      | CTAC 29<br>(29% Cetrimonium Chloride, a cationic<br>conditioning agent) | 1       | 4       |
| C      | Wheat Protein                                                           | 1       | 4       |
| C      | Panthenol                                                               | 0.2     | 0.8     |
| C      | Acetamide MEA                                                           | 1       | 4       |
| C      | Kathon                                                                  | 0.1     | 0.4     |
| C      | Color                                                                   | To Suit | To Suit |
| C      | Glitter                                                                 | To Suit | To Suit |
| Totals |                                                                         | 100.00  | 400.00  |

#### EXAMPLE 4

[00024] High cationic surfactant systems were prepared having a 40% concentration of benzylalkonium chloride and the wet-cake version of microfibrous cellulose. Alginate beads or air was suspended in the solutions. A concentrate of 1.85% wet-cake microfibrous cellulose was activated in distilled water with an Oster® blender set at top speed (liquefy) by mixing for 5 minutes. The microfibrous cellulose solution was diluted by 80% with a 50% benzylalkonium chloride solution while mixing at 600 rpm with a jiffy mixing blade. Alginate beads were added to test suspension. The activity (% solids) of this wet-cake form of MFC was about 16% yielding an active MFC level of 0.06% in the final solution. Upon visual inspection, good suspension was achieved for the dilution resulting in a yield point of 0.36 Pa (as measured with a Brookfield® Yield Rheometer).

## EXAMPLE 5

[00025] High cationic surfactant systems were prepared having about 50% concentration  
5 of benzylalkonium chloride and the wet-cake version of microfibrinous cellulose. Air was  
suspended in the solution. 0.47% wet-cake microfibrinous cellulose was activated in a 50%  
concentrate of benzylalkonium chloride solution with an Oster® blender set at top speed  
(liquefy) by mixing for 5 minutes. The activity (% solids) of this wet-cake form of MFC was  
16% yielding an active MFC level of 0.075% in the final solution. Upon visual inspection,  
10 good suspension of air was achieved for the dilution resulting in a yield point of 4.5 Pa. Clarity  
was very good with only a slight haze.

## CLAIMS

1. A cationic surfactant system comprising microfibrinous cellulose at a concentration of  
5 about 0.05% to about 1.0% (w/w), cationic surfactant at about 0.05% to about 50% (w/w active  
surfactant), and a particulate.
2. The cationic surfactant system according to claim 1, wherein the microfibrinous cellulose  
is present at about 0.06%.
- 10 3. The cationic surfactant system according to claim 1, wherein the microfibrinous cellulose  
is present at about 0.075%.
4. The cationic surfactant system according to claim 1, wherein the microfibrinous cellulose  
15 is present at about 0.09%.
5. The cationic surfactant system according to claim 2, wherein the cationic surfactant is  
present at about 0.5% to about 3% (w/w active surfactant).
- 20 6. The cationic surfactant system according to claim 4, wherein the surfactant is present at  
about 50% (w/w active surfactant).
7. The cationic surfactant system according to claim 5, further comprising air bubbles  
suspended therein.
- 25 8. The cationic surfactant system according to claim 5, further comprising beads  
suspended therein.
9. The cationic surfactant system according to claim 6, further comprising beads  
30 suspended therein.

10. The cationic surfactant system according to claim 6, further comprising air bubbles suspended therein.
11. Method of preparing a surfactant system, comprising,  
5 combining microfibrinous cellulose with water and mixing,  
adding cationic surfactant and then mixing,  
adding a particulate followed by mixing,  
wherein the resulting system is clear and the particulates are suspended therein.
- 10 12. The method of claim 11 wherein the microfibrinous cellulose is present at a concentration of about 0.05% to about 1.0% (w/w), and the cationic surfactant is present at about 0.1% to about 50% (w/w active surfactant).
13. The method of claim 11 wherein the microfibrinous cellulose is present at about 0.06%.
- 15 14. The method of claim 11, wherein the microfibrinous cellulose is present at about 0.075%.
15. The method of claim 11, wherein the microfibrinous cellulose is present at about 0.09%.
- 20 16. The method of claim 11, wherein the cationic surfactant is present at about 0.1% to about 15% (w/w active surfactant).