

REPLACED SHEETS		SG
☒	Description : paged ...1... to paged ...20...	
☒	Claim(s) : paged ...21... to paged ...22...	
☐	Drawing(s) : paged to paged	
☒	Abstract : paged ...4... to paged ...-	
DATE OF RECEIPT		

41-287

HOECHST AKTIENGESELLSCHAFT

HOE 91/F 243

Dr.DA/-

Description

Process for the preparation of ethylene (co)polymers

The invention relates to a process for the (co)polymer-
 5 ization of ethylene to give coarse polymer particles
 having a narrow particle size distribution and high bulk
 density by using catalyst particles obtained by after-
 treating Ti(III)-containing Ziegler-Natta catalysts whose
 support component is a magnesium alkoxide with metal
 10 halides, in particular $TiCl_4$.

Processes are known for the preparation of Ti(III)-
 containing Ziegler-Natta catalysts in which the support
 component used is a suspended, dissolved or soluble
 magnesium alkoxide or a gel dispersion of a magnesium
 15 alkoxide (cf. EP 302 242, EP 398 167, DE 33 25 221 and
 DE 40 17 661). In the (co)polymerization of ethylene,
 these catalysts generally give ethylene (co)polymers
 having a narrow molecular weight distribution.

The object was to find a simple process for the prepara-
 20 tion of catalysts which allow the preparation of polymers
 having a large mean and uniform particle diameter and
 high bulk density. These polymers should furthermore have
 a moderate to broad molecular weight distribution (MFR
 21.6/5 of greater than or equal to 11).

It has now been found that this object can be achieved if
 25 a magnesium alkoxide is allowed to react with a transi-
 tion-metal compound, in particular a titanium compound,
 and then with an aluminum compound, the transition metal
 is reduced to a lower oxidation state, and the reaction
 30 product is then treated with a metal halide.

This Sheet Has Been Replaced





The invention thus relates to a process for the preparation of an ethylene polymer having a uniform coarse particle shape and high bulk density by polymerizing ethylene or ethylene with up to 10% by weight, based on the total amount of the monomers, of a 1-olefin of the formula $R^6-CH=CH_2$, in which R^6 is a straight-chain or branched alkyl radical having 1 to 12 carbon atoms, in suspension, in solution or in the gas phase, at a temperature of from 20 to 120°C and at a pressure of from 2 to 60 bar, in the presence of a catalyst comprising the product of the reaction of a magnesium alkoxide with a tetravalent titanium compound and an organoaluminum compound, which comprises carrying out the polymerization in the presence of a catalyst which comprises

a) the entire product from the reaction

a1) of a magnesium alkoxide of the formula I



in which R^1 and R^2 are identical and are an unbranched or branched alkyl radical having 1 to 20 carbon atoms or a $-(CH_2)_nOR^3$ radical where R^3 is an alkyl radical having 1 to 4 carbon atoms and n is an integer from 2 to 6,

which is dissolved, suspended or dispersed as a gel in an inert solvent, with

a2) a tetravalent transition-metal compound of the formula II



in which M^1 is titanium, zirconium or hafnium, R^4 is an alkyl radical having 1 to 9 carbon atoms, X is a halogen atom and m is an integer from zero to 4, and

a3) an organoaluminum compound of the formula III



in which R^5 is an alkyl radical having 1 to 6 carbon atoms, X is a halogen atom and p is a number from zero to 3, in the Mg : M^1 : Al ratio of 1 : 0.05 to 10 : 0.01 to 4,
5 washing the solid with an inert solvent and reacting the product with
a4) a metal halide of the formula IV



10 in which M^2 is titanium, silicon or tin, or BCl_3 , in the M^1 : M^2 ratio of from 1 : 0.5 to 100, and washing the solid with an inert solvent, and

b) a trialkylaluminum compound having 1 to 6 carbon atoms in the alkyl radicals or the product of the reaction of
15 a trialkylaluminum compound or dialkylaluminum hydride with isoprene.

To prepare the mixed catalyst component to be employed according to the invention, a magnesium alkoxide of the formula (I)



is used. In this formula, R^1 and R^2 are identical or different and are an unbranched or branched alkyl radical having 1 to 20 carbon atoms, preferably 2 to 10 carbon atoms, or a $-(\text{CH}_2)_n\text{OR}^3$ radical where R^3 is a C_1 - to C_4 -alkyl
25 radical, preferably a C_1 - to C_2 -alkyl radical, and n is an integer from 2 to 6.

Examples of magnesium alkoxide of this type are

magnesium bismethoxide,
magnesium bisethoxide,

This Sheet Has Been Replaced



magnesium bis-i-propoxide,
magnesium bis-n-propoxide,
magnesium bis-n-butoxide,
magnesium methoxyethoxide,
5 magnesium ethoxy-n-propoxide,
magnesium bis(2-methyl-1-pentoxide),
magnesium bis(2-methyl-1-hexoxide),
magnesium bis(2-methyl-1-heptoxide),
magnesium bis(2-ethyl-1-pentoxide),
10 magnesium bis(2-ethyl-1-hexoxide),
magnesium bis(2-ethyl-1-heptoxide),
magnesium bis(2-propyl-1-heptoxide),
magnesium bis(2-methoxy-1-ethoxide),
magnesium bis(3-methoxy-1-propoxide),
15 magnesium bis(4-methoxy-1-butoxide),
magnesium bis(6-methoxy-1-hexoxide),
magnesium bis(2-ethoxy-1-ethoxide),
magnesium bis(3-ethoxy-1-propoxide),
magnesium bis(4-ethoxy-1-butoxide),
20 magnesium bis(6-ethoxy-1-hexoxide),
magnesium bispentoxide and
magnesium bishexoxide.

Preference is given to the simple magnesium alkoxides
such as magnesium diethoxide, magnesium di-n-propoxide
25 and magnesium di-i-butoxide. Other magnesium alkoxides
which can be used are the products of the reaction of
magnesium metal, alkylmagnesium compounds or magnesium
alkoxides with alcohols R^1OH (R^1 as above). Of these
products, preference is given to the product of the
30 reaction of a magnesium alkoxide with an alcohol R^1OH in
the presence of 0.02 - 0.2 mol % of triethylaluminum (as
viscosity reducer) at from 100 to 140°C.

The magnesium alkoxide is employed as a suspension,
solution or as a gel dispersion.



The magnesium alkoxide is first reacted with a tetra-valent transition-metal compound of the formula II



in which M^1 is titanium, zirconium or hafnium, preferably titanium or zirconium, R^3 is an alkyl radical having 1 to 9 carbon atoms, preferably 1 to 4 carbon atoms, X is a halogen atom, preferably chlorine, and m is zero to 4, preferably 2 to 4. The tetravalent transition-metal compound of the formula II or an adduct thereof with an electron donor, for example an ester, ether, ketone or the like, is soluble in hydrocarbons.

Examples which may be mentioned are:

$TiCl_4$, $TiCl_3(OC_2H_5)$, $TiCl_2(OC_2H_5)_2$, $TiCl(OC_2H_5)_3$, $Ti(OC_2H_5)_4$,
 $TiCl_3(OC_3H_7)$, $TiCl_2(OC_3H_7)_2$, $TiCl(OC_3H_7)_3$, $Ti(OC_3H_7)_4$,
 15 $TiCl_3(OC_4H_9)$, $TiCl_2(OC_4H_9)_2$, $TiCl(OC_4H_9)_3$, $Ti(OC_4H_9)_4$,
 $TiCl_3(OC_6H_{13})$, $TiCl_2(OC_6H_{13})_2$, $TiCl(OC_6H_{13})_3$, $Ti(OC_6H_{13})_4$,
 $Ti(OC_9H_{19})_4$, $TiBr_4$, $TiBr_3(OR^3)$, $TiBr_2(OR^3)_2$, $TiBr(OR^3)_3$, TiI_4 ,
 $TiI_3(OR^3)$, $TiI_2(OR^3)_2$, $TiI(OR^3)_3$, $ZrCl_4$, $ZrBr_4$, ZrI_4 ,
 $Zr(OC_2H_5)_4$, $Zr(OC_3H_7)_4$, $Zr(OC_4H_9)_4$, $ZrCl_2(OC_3H_7)_2$, preferably
 20 $TiCl_4$, $ZrCl_4$, $Ti(OC_2H_5)_4$, $Ti(OC_3H_7)_4$, $Zr(OC_3H_7)_4$, $Ti(OC_4H_9)_4$
 and $Zr(OC_4H_9)_4$. Particular preference is given to $TiCl_4$.

The third reactant for the preparation of the catalyst component a is an organoaluminum compound of the formula III



in which R^4 is an alkyl radical having 1 to 6 carbon atoms, preferably 1 to 4 carbon atoms, X is a halogen atom, preferably chlorine, and p is a number from zero to 3, preferably 1 to 2, or the product of the reaction of a trialkylaluminum compound or dialkylaluminum hydride with a diene, preferably isoprene.





Suitable organoaluminum compounds are:

$\text{Al}(\text{C}_2\text{H}_5)_3$, $\text{Al}(\text{C}_2\text{H}_5)_2\text{Cl}$, $\text{Al}_2(\text{C}_2\text{H}_5)_3\text{Cl}_3$, $\text{Al}(\text{C}_2\text{H}_5)\text{Cl}_2$, AlCl_3 ,
 $\text{Al}(\text{C}_3\text{H}_7)_3$, $\text{Al}(\text{C}_3\text{H}_7)_2\text{Cl}$, $\text{Al}_2(\text{C}_3\text{H}_7)_3\text{Cl}_3$, $\text{Al}(\text{C}_3\text{H}_7)\text{Cl}_2$, $\text{Al}(\text{C}_4\text{H}_9)_3$,
5 $\text{Al}(\text{C}_4\text{H}_9)_2\text{Cl}$, $\text{Al}_2(\text{C}_4\text{H}_9)_3\text{Cl}_3$, $\text{Al}(\text{C}_4\text{H}_9)\text{Cl}_2$ and monohalides and
dihalides of various composition. From this group,
preference is given to $\text{Al}_2(\text{C}_2\text{H}_5)_3\text{Cl}_3$ and $\text{Al}(\text{C}_2\text{H}_5)_3$.

The catalyst component a is formed by the following possible routes, it also being possible to employ each reactant as a plurality of similar compounds.

10 i) The solution of the transition-metal compound is added to a solution, dispersion or suspension of the magnesium alkoxide, and the resultant solid is then reacted with an organoaluminum compound of the formula III.

15 ii) The solution or dispersion of a magnesium alkoxide and the solution of the transition-metal compound are added simultaneously to an initially introduced solvent, and the resultant suspension is reacted with an organoaluminum compound of the formula
20 III.

iii) The solution or dispersion of a magnesium alkoxide, the solution of the transition-metal compound and an organoaluminum compound of the formula III are reacted with one another simultaneously in an initially
25 introduced dispersant.

iv) The solution of the transition-metal compound is added to a solution, dispersion or suspension of the magnesium alkoxide, and the resultant solid is washed and then reacted with an organoaluminum compound of the
30 formula III.

v) The solution or dispersion of a magnesium alkoxide and the solution of the transition-metal



compound are added simultaneously to an initially introduced solvent, and the resultant solid is washed and then reacted with an organoaluminum compound of the formula III.

- 5 It is furthermore possible to carry out the preparation by combination of methods i) to v).

The reaction of the magnesium alkoxide with the tetra-valent transition-metal compound is carried out at a temperature of from -50 to 150°C, preferably at from -20
10 to 120°C, for from 0.1 to 12 hours, preferably from 0.13 to 6 hours.

The reaction with the organoaluminum compound is carried out at a temperature of from -50 to 150°C, preferably at from -20 to 130°C, particularly preferably at from 20 to
15 120°C, for a period of from 0.1 to 10 hours, preferably for from 0.25 to 4 hours.

Suitable inert solvents for said reactions are aliphatic and cycloaliphatic hydrocarbons, such as butane, pentane, hexane, heptane, cyclohexane and isooctane, and aromatic
20 hydrocarbons, such as benzene and xylene. It is also possible to employ gasoline and hydrogenated diesel oil fractions which have been carefully freed from oxygen, sulfur compounds and moisture.

The magnesium alkoxide, the tetravalent transition-metal
25 compound (M^1) and the organoaluminum compound of the formula III are reacted in an Mg : M^1 : Al ratio of from 1 : 0.05 to 10 : 0.01 to 4, preferably from 1 : 0.08 to 4 : 0.02 to 3.

After the reaction, the suspension of the solid is
30 stirred for from 0 to 48 hours, preferably for from 0.5 to 16 hours, at from 80 to 150°C, preferably at from 100 to 120°C, and then washed until the supernatant mother



liquor is free from Cl and Ti (Zr, Hf).

The solid is subsequently mixed with a chlorinating compound of the formula IV



5 in which M^2 is Ti, Si or Sn,
or BCl_3 , in an $M^1 : M^2$ (or B) ratio of from 1 : 0.2 to
100, preferably from 1 : 1 to 50, in particular from
1 : 1.5 to 20, and the mixture is stirred at a temper-
10 ature of from 50 to 150°C for from 0.1 to 100 hours,
preferably for from 0 to 48 hours, in particular for from
1 to 30 hours. The resultant catalyst component a is
subsequently washed repeatedly in order to remove soluble
compounds.

15 The catalyst component b is a trialkylaluminum compound
having 1 to 6 carbon atoms in the alkyl radicals, such
as, for example, triethylaluminum, triisobutylaluminum,
triisohexylaluminum or the product of the reaction of a
trialkylaluminum compound or of a dialkylaluminum hydride
with isoprene, which is known as isoprenylaluminum.
20 Preference is given to triethylaluminum and isoprenyl-
aluminum.

It is possible to preactivate the catalyst component a
by means of a trialkylaluminum compound. This improves
the shelf life of the component before polymerization and
25 increases the polymerization activity. The actual activa-
tion with component b then takes place at the beginning
of the polymerization.

The polymerization is carried out in one or two steps,
preferably as suspension polymerization, in an inert
30 dispersant. Suitable dispersants are the same organic
solvents described for the preparation of the catalyst
component a. However, polymerization in the gas phase is



also possible.

The polymerization temperature is from 20 to 120°C, preferably from 70 to 90°C; the pressure is in the range from 2 to 60 bar, preferably from 4 to 20 bar.

- 5 If the reaction is carried out in two steps, the mixing ratio between the polyolefins formed in steps 1 and 2 is in the range from 30 : 70 to 70 : 30.

The catalyst system used according to the invention is used to polymerize ethylene or ethylene with up to 10% by weight, based on the total amount of monomers, of a 1-olefin of the formula $R^1-CH=CH_2$, in which R^1 is a straight-chain or branched alkyl radical having 1 to 12 carbon atoms, preferably 1 to 10 carbon atoms. Examples are propylene, 1-butene, 1-pentene, 1-hexene, 1-octene and 4-methyl-1-pentene. Preference is given to propylene, 1-butene and 1-hexene. The comonomer is preferably introduced in the first step, in which a polymer of relatively high molecular weight is formed.

20 The entire polymer from the second step is separated off from the dispersant in a known manner and dried.

A characteristic of the catalyst component a is a Cl/transition-metal ratio which is increased compared with the prior art and, in the case of reaction with $TiCl_4$, an increased titanium content, the content of Ti^{3+} (Zr^{3+} , Hf^{3+}) not being reduced. This is connected with an increase in the mmol activity of the catalyst. The additional immobilization of titanium(IV) compounds requires an increase in the gram activity (kg of PE/g of component a), and thus an increase in the mean particle diameter and a broadening of the molecular weight distribution.



The particle size distribution of the polymer is highly uniform.

The molecular weight of the polyolefins is regulated efficiently by hydrogen.

5 The examples below serve to illustrate the invention.

The following abbreviations are used:

	CTA _{red}	reduced catalyst-time activity
	MFI 190/5	melt flow index in accordance with DIN 53735, measured at 190°C and a load of 5 kg
10	MFI 190/15	measured at 190°C at a load of 15 or MFI 190/21.6 21.6 kg respectively
	MFR 15/5	MFI 190/15 / MFI 190/5
	MFR 21.6/5	MFI 190/21.6 / MFI 190/5
15	d ₅₀	mean particle size, obtained by sieve fractionation
	BD	bulk density, measured in accordance with DIN 53468
	Cl _{corr.}	Cl - 2 Mg
20	VN	viscosity number in accordance with ISO / R 1191

Comparative Example A

Preparation of the catalyst component a₀

114.4 g of Mg(OC₂H₅)₂ and 1 dm³ of diesel oil were intro-
duced into a 2 dm³ reactor fitted with stirrer, thermo-
meter and dropping funnel. 500 cm³ of TiCl₄ were metered
in at 90°C over the course of 6 hours. The white product
was subsequently washed repeatedly until the Ti content
of the suspension was less than 5 mmol/dm³. 80 cm³ of a 1
molar solution of triethylaluminum in diesel oil were
subsequently added to the suspension, and the mixture was
stirred at 120°C for 12 hours. The brown-black solid was



separated off and washed four times with 0.5 dm³ of diesel oil.

Analysis: Mg : Ti : Cl = 1 : 0.065: 2.102; Ti³⁺/Ti⁴⁺ = 0.98; Cl_{corr.}/Ti = 1.57.

5 Comparative Example B
Polymerization of ethylene

Part of the suspension from Comparative Example A was diluted with diesel oil to a Ti concentration of 0.01 mol/dm³. 3 cm³ of a 1 molar triethylaluminum solution and 1 cm³ of the dilute suspension were introduced at 85°C
10 under a blanket of N₂ into a 1.5 dm³ steel autoclave containing 750 cm³ of diesel oil. The autoclave was then flushed twice with hydrogen, and 2.15 bar of hydrogen and 4.85 bar of ethylene were injected. The overall pressure
15 of 7 bar was maintained for 2 hours by replenishing consumed ethylene. The polymerization was terminated by decompressing the gases, and the polymer was separated off from the dispersant by filtration and drying. 208 g of polyethylene having an MFI 190/5 of 1.1 g/10 min and
20 an MFR 21.6/5 of 10.2 were formed. This corresponds to a CTA_{red} of 2144 g/mmol of Ti.bar.h or a CA of 12.6 kg of PE/g of component a. The powder had a bulk density of 360 g/dm³ and contained 8% by weight of fine particles of < 100 μm. The mean particle size d₅₀ was 197 μm.

25 Example 1
Preparation of the catalyst component a

153.8 cm³ (10 mmol of Ti) of the suspension of the catalyst component a₀ from Comparative Example A were transferred into a 250 cm³ reactor, and 8.8 cm³ of TiCl₄ were
30 added at 120°C. The mixture was stirred at this temperature for 5 hours and subsequently washed six times with 200 cm³ of diesel oil at 70°C (Ti in the mother liquor < 1 mmol/dm³).



Analysis: $\text{Mg} : \text{Ti} : \text{Cl} = 1 : 0.108 : 2.253$; $\text{Ti}^{3+}/\text{Ti}^{4+} = 0.57$;
 $\text{Cl}_{\text{corr.}}/\text{Ti} = 2.34$.

The polymerization of ethylene was carried out in accordance with Comparative Example B. 219 g of polyethylene
5 having an MFI 190/5 of 0.92 g/10 min and an MFR 21.6/5 of 13.4 were obtained. This corresponds to a CTA_{red} of 2257 g/mmol of $\text{Ti} \cdot \text{bar} \cdot \text{h}$ or a CA of 20.7 kg of PE/g of component a. The powder had a bulk density of 360 g/dm³ and contained 4% by weight of fine particles. The mean
10 particle size d_{50} was 237 μm .

Comparative Example C

228.8 g of $\text{Mg}(\text{OEt})_2$ from Nippon Soda and 1600 cm³ of diesel oil were dispersed for 24 hours at room temperature under a blanket of argon in a 4 dm³ reactor using a
15 high-speed stirrer (Ultra-Turrax from IKA). 180 cm³ of the 1.11 molar solution were reacted at 85°C for 4 hours with 200 cm³ of a 0.3 molar TiCl_4 solution in diesel oil and at 110°C for 2 hours with 200 cm³ of a 0.8 molar $\text{Al}_2\text{Et}_3\text{Cl}_3$ solution in diesel oil. The batch was subsequently stirred at 110°C for a further 1 hour. The
20 suspension was then filtered at 110°C and washed four times with 400 cm³ of hot diesel oil. The red-brown product was taken up in 200 cm³ of cold diesel oil. The analytical results are shown in Table 2.

25 The polymerization of ethylene was carried out in accordance with Comparative Example B, but at 2 bar of H_2 and 5 bar of C_2H_4 . The polymerization results and the amount of catalyst and cocatalyst used are shown in Table 3.

Comparative Example D

30 228.8 g of $\text{Mg}(\text{OEt})_2$ and 1600 cm³ of diesel oil were dispersed for 20 hours at room temperature under a blanket of argon in a 4 dm³ reactor using a high-speed



stirrer (Ultra-Turrax from IKA). 180 cm³ of the 1.11 molar solution were reacted at 85°C for 4 hours with 220 cm³ of a 0.3 molar TiCl₄ solution in diesel oil and at 130°C for 2 hours with 200 cm³ of a 0.8 molar Al₂Et₃Cl₃ solution in diesel oil. The batch was subsequently stirred at 110°C for a further 1 hour. The suspension was then washed five times with 400 cm³ of diesel oil at 25°C and the dark brown product was taken up in 200 cm³ of diesel oil. The analytical results are shown in Table 2.

- 10 The polymerization of ethylene was carried out in accordance with Comparative Example B, but at 2 bar of H₂ and 5 bar of C₂H₄. The polymerization results and the amount of catalyst and cocatalyst used are shown in Table 3.

Comparative Example E

- 15 800 cm³ of a 0.5 molar solution of magnesium 2-methylpentoxide in diesel oil, 400 cm³ of a 0.3 molar solution of TiCl₄ in diesel oil and 400 cm³ of a 0.8 molar solution of Al₂Et₃Cl₃ in diesel oil were metered simultaneously at 25°C over the course of 1 hour into 800 cm³ of diesel oil in a 4 dm³ reactor. The batch was subsequently diluted with 400 cm³ of diesel oil, heated to 110°C and stirred at this temperature for 2 hours. The suspension was filtered at 100°C, and the red-brown product was washed twice with 800 cm³ of hot diesel oil. The analytical results are shown in Table 2.

The polymerization of ethylene was carried out in accordance with Comparative Example B, but at 2 bar of H₂ and 5 bar of C₂H₄. The polymerization results and the amount of catalyst and cocatalyst used are shown in Table 3.

30 Comparative Example F

1500 cm³ of a 0.4 molar solution of magnesium 2-methylpentoxide in diesel oil, 500 cm³ of a 0.36 molar solution



of TiCl_4 in diesel oil and 500 cm^3 of a 0.96 molar solution of $\text{Al}_2\text{Et}_3\text{Cl}_3$ in diesel oil were metered simultaneously at 25°C over the course of 1 hour into 1000 cm^3 of diesel oil in a 4 dm^3 reactor. The mixture was subsequently diluted with 300 cm^3 of diesel oil, heated to 120°C and stirred at this temperature for 3 hours. The suspension was filtered at 100°C , and the red-brown product was washed twice with 1 dm^3 of hot diesel oil and taken up in 1.5 dm^3 of diesel oil. The analytical results are shown in Table 2.

The polymerization of ethylene was carried out in accordance with Comparative Example B, but at 2 bar of H_2 and 5 bar of C_2H_4 . The polymerization results and the amount of catalyst and cocatalyst used are shown in Table 3.

Examples 2 to 15
Preparation of component a

Component a was prepared analogously to Example 1. The type and amount of the initially introduced component a_0 , the amount of TiCl_4 or halogenating agent and the time and temperature at which the reaction took place are shown in Table 1. The analytical results are listed in Table 2 and the polymerization results in Table 3.

Table 1

	Comp. a	Comp. a ₀ 10 mmol from	Addition of	T [°C]	t [h]
	Ex. 2	Comp. E	50 mmol of TiCl ₄	120	2
5	Ex. 3	Comp. F	100 mmol of TiCl ₄	120	2
	Ex. 4	Comp. D	50 mmol of TiCl ₄	120	2
	Ex. 5	Comp. C	100 mmol of TiCl ₄	120	2
	Ex. 6	Comp. C	50 mmol of TiCl ₄	120	22
	Ex. 7	Comp. E	20 mmol of TiCl ₄	85	1
10	Ex. 8	Comp. E	50 mmol of TiCl ₄	85	1
	Ex. 9	Comp. E	50 mmol of TiCl ₄	85	2
	Ex. 10	Comp. F	100 mmol of TiCl ₄	85	2
	Ex. 11	Comp. D	50 mmol of TiCl ₄	85	2
	Ex. 12	Comp. C	100 mmol of TiCl ₄	85	2
15	Ex. 13	Comp. D	570 mmol of TiCl ₄	85	2
	Ex. 14	Comp. E	50 mmol of TiCl ₄	85	2
	Ex. 15	Comp. D	500 mmol of TiCl ₄	85	1

This Sheet Has Been Replaced



Table 2

Analytical results for the washed component a_0 or a

	Component a_0 or a	Mg : Ti : Cl	Cl _{corr.} /Ti		mmol of Ti/g calculated
			obs.	(theor.)	
5	Comp. C	1:0.317:2.540	1.70	(3)	2.10
	Comp. D	1:0.336:2.656	1.95	(3)	2.60
	Comp. E	1:0.266:2.406	1.52	(3)	1.62
	Comp. F	1:0.261:2.345	1.33	(3)	1.58
	Example 2	1:0.722:3.78	2.47	(3.64)	2.58
10	Example 3	1:0.723:3.79	2.47	(3.64)	2.58
	Example 4	1:0.823:4.11	2.56	(3.67)	3.30
	Example 5	1:0.755:4.03	2.68	(3.58)	3.23
	Example 6	1:0.797:3.94	2.44	(3.58)	3.26
	Example 7	1:0.580:3.56	2.68	(3.54)	2.53
	Example 8	1:0.537:3.61	3.01	(3.53)	2.60
15	Example 9	1:0.471:3.226	2.69	(3.39)	2.40
	Example 10	1:0.474:3.336	2.82	(3.45)	2.40
	Example 11	1:0.693:3.49	2.14	(3.61)	3.08
	Example 12	1:0.639:3.64	2.56	(3.50)	3.04
	Example 13	1:0.737:3.773	2.41	(3.54)	3.16
20	Example 14	1:0.286:2.83	2.90	(3)	2.02
	Example 15	1:0.312:2.850	2.73	(3)	2.20

This Sheet Has Been Replaced



Table 3

Test polymerizations: 2 h, 85°C, 2 bar of H₂, 5 bar of C₂H₄

	Comp. a ₀ / a	Comp. b	CA *	CA **	MFI 190/5 dg/min	MFR #	d ₅₀ μm	< 100 μm %	BD g/cm ³
5	mmol	mmol							
	0.01 Comp.C	5 IPRA	19.7	41.4	1.20	9.3	289	1.4	0.31
	0.01	3 TEA	9.5	19.9	1.40	10.6	223	2.4	0.31
	0.01 Comp.D	5 IPRA	22.7	58.9	2.10	10.0	374	1.2	0.34
	0.01	3 TEA	10.5	27.3	1.94	9.3	306	1.9	0.34
10	0.02 Comp.E	5 IPRA	12.2	19.8	2.38	8.7	349	2.1	0.30
	0.02	3 TEA	12.6	20.4	3.14	9.6	361	1.2	0.29
	0.01 Comp.F	5 IPRA	11.5	18.3	0.79	8.9	242	1.5	0.34
	0.01	3 TEA	10.8	17.1	1.21	10.5	256	0.7	0.30
	0.005 Ex. 2	5 IPRA	22.5	58.2	0.62	12.0	514	1.4	0.31
15	0.01 Ex. 3	5 IPRA	21.8	56.2	0.72	12.0	421	0.7	0.33
	0.01 Ex. 4	5 IPRA	20.5	67.7	0.72	13.1	375	1.4	0.31
	0.01 Ex. 5	5 IPRA	18.4	59.3	1.08	12.9	479	0.7	0.31
	0.01 Ex. 6	5 IPRA	17.3	56.3	0.51	13.8	474	0.5	0.30
	0.005 Ex. 7	5 IPRA	30.7	77.6	0.93	11.6	582	1.0	0.35
20	0.005 Ex. 8	2 IPRA	39.8	103.5	1.35	12.2	642	0.5	0.32
	0.005 Ex. 9	2 IPRA	44.8	107.5	1.58	11.7	569	0.5	0.32
	0.005 Ex.10	2 IPRA	37.0	88.8	0.85	12.2	537	0.6	0.33
	0.01 Ex. 11	5 IPRA	20.1	61.9	0.76	12.4	368	1.0	0.31
	0.01 Ex. 12	5 IPRA	21.3	64.8	1.36	12.9	446	0.7	0.33
25	0.005 Ex. 13	2 IPRA	24.0	75.8	0.81	12.5	359	2.2	0.30
	0.005 Ex. 14	2 IPRA	34.7	70.1	1.92	10.2	477	0.7	0.32
	0.01	3 TEA	15.7	31.7	1.89	10.7	310	0.9	0.30
	0.01 Ex. 15	5 IPRA	24.3	53.5	1.79	10.4	404	1.3	0.31
	0.01	3 TEA	8.3	18.2	1.64	10.5	330	1.5	0.31

This Sheet Has Been Replaced



Table 3 (continuation)

Test polymerizations: 2 h, 85°C, 5 bar of H₂, 2 bar of C₂H₄.

	Comp. a	Comp. b	CA	CTA _{red}	VN	d ₅₀	<100	BD
	mmol	mmol	g/mmol	***	cm ³ /g	μm	μm	g/cm ³
5	0.01 Ex. 10	5	IPRA	8650	2163	84	168	12.5 0.29
	0.01 Ex. 14	5	IPRA	8670	2168	71	195	16.5 0.27

* CA [kg of PE / mmol of Ti (Zr, Hf)]

** CA [kg of PE / g of component a₀ or a]

*** g/mmol.h.bar

10 # MFR 21.6 / 5

This Sheet Has Been Replaced





Example 16

100 dm³ of diesel oil were introduced into a 150 dm³ reactor, which was flushed four times with 2 bar of hydrogen. 50 mmol of isoprenylaluminum and 5.9 cm³ (0.5 mmol of Ti) of the dispersion of component b (Example 9) were then introduced, and 0.75 bar of hydrogen was injected. Ethylene was introduced at a rate of 6 kg/h and at a temperature of 85°C. Sufficient hydrogen was subsequently metered in so that the H₂ content in the gas space was 30% by volume during the entire polymerization. After 315 minutes and a final pressure of 8.2 bar, the polymerization was terminated by decompression. The suspension was filtered, and the polyethylene powder was dried by means of a stream of hot nitrogen.

31.6 kg of polyethylene having a density of 0.958 g/cm³ were obtained. This corresponds to a catalyst activity of 151.7 kg of polyethylene/g of component a or 1319 kg of polyethylene/g of Ti. The polyethylene powder had an MFI 190/5 of 0.86, an MFR 21.6/5 of 14.5, a bulk density of 340 g/dm³ and a mean particle diameter of 610 μm. The content of fine particles of <100 μm was less than 1%.

Example 17

The preparation was carried out analogously to Example 1 using 10 mmol of Ti-containing suspension from Comparative Example C and 50 mmol of TiCl₄ over the course of 2 hours at a temperature of 80°C.

Analysis: Mg : Ti : Cl = 1 : 0.565 : 3.485

Ti³⁺/Ti⁴⁺ = 0.53; Cl_{corr.}/Ti = 2.63.

30 Copolymerization of ethylene with 1-butene

100 dm³ of diesel oil were introduced into a 150 dm³ reactor, which was flushed four times with 2 bar of hydrogen. 50 mmol of isoprenylaluminum and 7.2 cm³ (0.6 mmol of Ti) of the dispersion of component a were

introduced, and 0.75 bar of hydrogen was injected. At a temperature of 80°C, 100 cm³ of 1-butene were introduced and ethylene was passed in at a rate of 6 kg/h. Sufficient hydrogen was subsequently metered in so that the H₂ content in the gas space was 30% by volume during the entire polymerization. An additional 1100 cm³ of butene were introduced over the course of 2 hours. After 165 minutes and a final pressure of 8.5 bar, the polymerization was terminated by decompression. The suspension was filtered, and the polyethylene powder was dried by means of a stream of hot nitrogen.

17.2 kg of polyethylene were obtained. This corresponds to a catalyst activity of 598 kg of polyethylene/g of Ti. The polyethylene powder had an MFI 190/5 of 3.28 dg/min, an MFR 21.6/5 of 11.0, a bulk density of 360 g/dm³ and a mean particle diameter of 430 μm. The proportion of fine particles of <100 μm was less than 2%. The density was 0.951 g/cm³.

This Sheet Has Been Replaced





Patent claim

1. A process for the preparation of an ethylene polymer having a uniform coarse particle shape and high bulk density by polymerizing ethylene or ethylene with up to 10% by weight, based on the total amount of the monomers, of a 1-olefin of the formula $R^6-CH=CH_2$ in which R^6 is a straight-chain or branched alkyl radical having 1 to 12 carbon atoms, in suspension, in solution or in the gas phase, at a temperature of from 20 to 120°C and at a pressure of from 2 to 60 bar, in the presence of a catalyst comprising the product of the reaction of a magnesium alkoxide with a tetravalent transition-metal compound and an organoaluminum compound, which comprises carrying out the polymerization in the presence of a catalyst which comprises

- a) the entire product from the reaction
a1) of a magnesium alkoxide of the formula I



- 20 in which R^1 and R^2 are identical and are an unbranched or branched alkyl radical having 1 to 20 carbon atoms or a $-(CH_2)_nOR^3$ radical where R^3 is an alkyl radical having 1 to 4 carbon atoms and n is an integer from 2 to 6,

- 25 which is dissolved, suspended or dispersed as a gel in an inert solvent, with

- a2) a tetravalent transition-metal compound of the formula II



- 30 in which M^1 is titanium, zirconium or hafnium, R^4 is an alkyl radical having 1 to 9 carbon atoms, X is a halogen atom and m is an integer from zero to 4,



and

a3) an organoaluminum compound of the formula III



5 in which R^5 is an alkyl radical having 1 to 6 carbon atoms, X is a halogen atom and p is a number from zero to 3, in the Mg : M^1 : Al ratio of 1 : 0.05 to 10 : 0.01 to 4,

washing the solid with an inert solvent and reacting the product with

10 a4) a metal halide of the formula IV



in which M^2 is titanium, silicon or tin, or BCl_3 , in the M^1 : M^2 ratio of from 1 : 0.2 to 100, and washing the solid with an inert solvent, and

15 b) a trialkylaluminum compound having 1 to 6 carbon atoms in the alkyl radicals or the product of the reaction of a trialkylaluminum compound or dialkylaluminum hydride with isoprene.

This Sheet Has Been Replaced

