

## Description

The present invention relates to the manufacture of plastic optical articles such as video discs and ophthalmic lenses. The most widely used plastic ophthalmic lens material is polymerised diethylene glycol bis (allyl carbonate). This polymer has proved a satisfactory material for the manufacture of ophthalmic lenses because of a combination of features, including excellent transmission, resistance to discolouration, high strength and high impact resistance. The material has a reasonable abrasion resistance and can be coated to improve that resistance.

The manufacturing process involves the polymerisation of diethylene glycol bis (allyl carbonate) by curing the material within a pair of glass moulds sealed by a gasket and held together by a clip. The cure times are lengthy and can be as long as 16 hours or more. Such extended cure times not only mean that a large stock of glass moulds is required but that also, warehouse stocks of cast polymerised lenses are high so as to meet order requirements as they arise.

There has been a long felt need for a material which could be cast using the existing arrangements with a considerably reduced cure time while still producing a lens with all the desirable characteristics of those made with diethylene glycol bis (allyl carbonate).

Urethane acrylates and methacrylates have been widely used in the formulation of coating compositions, photosensitive compositions for making flexographic printing plates, adhesives and dental filling materials. In such formulations the urethane material is usually chosen so as to have a high viscosity and low shrinkage and forms the principal component of any formulation.

In order to cast a satisfactory lens by a commercially useful casting process from a composition containing a urethane acrylate or methacrylate, it is necessary to formulate the composition so as to have a viscosity not exceeding approximately 0,2 Pas (200 cps) at 25 °C.

Accordingly, it is an object of the present invention to overcome, or at least alleviate, one or more of the difficulties related to the prior art.

Accordingly, the present invention provides a cross-linkable polymeric casting composition for use in the manufacture of optical articles such as lenses, characterised in that:

(i) the composition is optically clear;

(ii) the composition comprises:

(A) at least one polyoxyalkylene glycol diacrylate or dimethacrylate compound;

(B) at least one unsaturated polyfunctional cross-linking agent which is a tri - or tetra-functional vinyl, acrylic or methacrylic monomer;

(C) a urethane monomer having from two to six terminal acrylic and/or methacrylic groups; the weight ratio of the cross-linking agent (B) to the urethane monomer (C) being in the range of approximately 1:4 to 2:1; and

(iii) the viscosity of the composition at 25 ° is 0,2 Pas (200 cps) or lower.

The at least one polyoxyalkylene glycol diacrylate or dimethacrylate compound according to the present invention may include ethylene oxide or propylene oxide repeating units in its backbone. An ethylene glycol derivative is preferred.

Preferably from approximately 6 to 11 alkylene oxide repeating units may be included.

A polyethylene glycol dimethacrylate is preferred. A polyethylene glycol dimethacrylate with an average molecular weight of the order of 600 is preferred. One suitable material is that sold under the trade name NKESTER 9G by SHIN NAKAMURA which has an average molecular weight of 536. The average number of ethylene oxide polymerised units is 9. Alternatively, an NK Ester 6G having an average number of 6 ethylene oxide polymerised units may be used.

Though the use of polyethylene glycol dimethacrylate on its own is exemplified below, it is also possible to use mixtures of polyethylene glycol diacrylates and dimethacrylates. Mixed esters can also be used.

The at least one polyoxy alkylene glycol diacrylate or dimethacrylate component may be present in an amount suitable to provide a viscosity of not greater approximately 0,2 Pas (200 cps) at 25 °C in the final product. The diacrylate or dimethacrylate compound may be present in amounts of from approximately 40% by weight to 60% by weight based on the total weight of the casting composition. The diacrylate or dimethacrylate component is preferably present in amounts of at least approximately 45% by weight, more preferably 50% by weight.


The dimethacrylates are more preferred than the diacrylates as the diacrylates need to be used with care, as with their greater reactivity than the corresponding dimethacrylates, distortion may be introduced into the lens blank as cast due to strain. Any particular diacrylate also tends to be more water absorbing than the corresponding dimethacrylate. It has also been found that as the number of polymerised alkylene

oxide groups is increased from six, in the case of both dimethacrylates and diacrylates the water absorption increases and becomes unacceptably high at an average value of 12 alkylene oxide groups per molecule.


Water absorption can occur during tinting in boiling water and can result in cracking subsequent to tinting.

5      The poly functional unsaturated cross-linking agent according to the present invention may be a tri- or tetra-functional vinyl, an acrylic or methacrylic monomer. The cross-linking agent may be a short chain monomer for example trimethylol propane trimethacrylate, pentaerythritol triacrylate or tetracrylate. Other polyfunctional cross-linking agents which may be used include


**NK ESTER TMPT**




## NK ESTER A-TMPT




## NK ESTER A-TMM-3



## NK ESTER A-TMMT



## DI-TRIMETHYLOL PROPANE TETRAACRYLATE



50 trimethylolpropane triacrylate, pentaerythritol tetramethacrylate, dipentaerythritol monohydroxypentaacrylate, pentaerythritol triacrylate, ethoxylated trimethylolpropane triacrylate, ethoxylated trimethylolpropane trimethacrylate.

It has been found when operating at the lower end of the preferred range 40 to 60% for the diacrylate or dimethacrylate component that it is preferable to select as the polyfunctional unsaturated cross linking agent, material such as that sold under the trade name SR-454 which is an ethoxylated trimethylol propane triacrylate.

The poly functional unsaturated cross-linking agent may be present in amounts of from approximately 10 to 30% by weight preferably approximately 20% by weight based on the total weight of the casting


composition. The weight ratio of cross-linking agent to tetracrylic urethane monomer is preferably in the range of approximately 1:4 to 2:1.

As stated above, the cross-linkable polymeric coating composition also includes a further component (C) which is a urethane monomer having terminal acrylic and/or methacrylic groups. The number of such groups can vary from 2 to 6, and we have found that satisfactory materials for use in this invention are those in which the molecular weight of the compound divided by the functionality or number of groups is  $200 \pm 50$ . Suitable materials falling within this definition include materials supplied under the trade names U-4H, U-4HA and U-6HA by Shin Nakamura, NF-201 and NF-202 by Mitsubishi Rayon. These monomers are included to improve physical toughness without causing the lens material to become too brittle. Impact resistance is improved without adversely affecting abrasion resistance.

The structures contained within any particular monomer can be selected from those containing aliphatic, aromatic, and cyclic structures of other forms. We have found that in the formulations of the present invention, the tetracrylic urethane monomer gives particularly satisfactory results.

The inclusion of the tetracrylic urethane monomer may provide a product of increased hardness.

The tetracrylic urethane monomer according to a preferred aspect of the present invention may be a compound of the formula




wherein R, R<sup>1</sup>, R<sup>2</sup> and R<sup>3</sup> which may be the same or different are selected from hydrogen, alkyl of 1 to 6 carbon atoms or a substituted alkyl of 1 to 6 carbon atoms; and X is an organic residue having 1 to 20 carbon atoms. X may be an aliphatic, alicyclic or aromatic residue. X may be a C<sub>1</sub>-C<sub>20</sub> alkyl, alkoxy, alkylamino, alkyl carbonyl alkoxy carbonyl, alkylamido or alkoxy amide group.

X may be substituted with one or more halogen, hydroxyl, nitro, amino, alkyl or alkoxy groups.


The tetracrylic urethane monomer may be present in any suitable amount to provide a desired level of hardness. The tetracrylic urethane monomer may be present in an amount of up to approximately 40% by weight, preferably 10 to 30% by weight based on the total weight of the casting composition.

Where X is an aromatic group, the article formed therefrom may exhibit a high refractive index and be suitable for applications where this is desirable. A urethane monomer having the following structure is preferred:




wherein R is a hydrogen atom or a methyl group or a substituted methyl group and X is an organic residue having 2 - 20 carbon atoms, preferably 6 carbon atoms.

In the above formula, while X may be any of organic residues having 2 - 20 carbon atoms, it is generally an aliphatic or alicyclic hydrocarbon residue, the backbone of which may be interrupted by oxygen. Specific examples thereof are as follows: Examples of aliphatic hydrocarbon residues include (i) alkylene groups such as  $-\text{CH}_2\text{CH}_2-$ ,  $-(\text{CH}_2)_3-$ ,  $-(\text{CH}_2)_4-$ ,  $-(\text{CH}_2)_6-$ ,



$-(\text{CH}_2)_8-$ ,  $-(\text{CH}_2)_{18}-$ ,  $-(\text{CH}_2)_{11}-$ ,  $-\text{CH}_2-$ ; (ii) alkyloxyalkylene groups such as  $-\text{C}_2\text{H}_4\text{OC}_2\text{H}_4-$ ,  $-(\text{CH}_2)_6\text{O}-(\text{CH}_2)_6-$ .

The urethane monomer may be produced by reacting 2 moles of a glycerin di(meth)acrylate



and 1 mole of an organic diisocyanate compound ( $\text{OCN}-\text{X}-\text{NCO}$ ). The glycerin di(meth)acrylates are known compounds which can be obtained by reacting glycidyl (meth)acrylate and (meth)acrylic acid. The organic diisocyanate compounds are known compounds, many of which are on the market and thus easily available. The organic diisocyanate comply with the definition of X and thus their examples include ethylene diisocyanate, trimethylene diisocyanate, tetramethylene diisocyanate, hexamethylene diisocyanate, 2,2,4-trimethyl-hexamethylene diisocyanate. The reaction of the glycerin di(meth)acrylate and the organic diisocyanate may be conducted using a catalyst commonly used for reactions of alcohols and isocyanates (e.g. dibutyltin dilaurate) in the absence of a solvent, or by dissolving in a solvent. The solvent used is an organic solvent having no active hydrogen such as methyl chloride, benzene, toluene, etc. The reaction is preferably carried out at a temperature of up to  $100^\circ\text{C}$  (generally  $20^\circ - 90^\circ\text{C}$ ), thereby free radical polymerisation of the di(meth)acrylate monomer can be prevented, and a reaction time of 1 - 2 hours affords the monomer almost in a quantitative yield. After the reaction, the monomer may be obtained by removing the reaction solvent.

The cross-linkable casting composition according to the present invention may further include a cross-linking initiator. The cross-linking initiator may be a heat and/or ultraviolet (U.V.) initiator.

The compositions are preferably cured by a combination of UV radiation and heat. The combination of UV radiation and heat may reduce the possibility of incomplete curing for example due to the phenomenon known as "radical trapping".

The composition, with the addition of approximately 0.5 to 2.0% by weight of cross-linking initiator may be exposed to UV radiation for between 0.5 and 10 seconds.

Any commercially viable UV curing system may be used. We have used a Fusion System with microwave driven lamps. A number of fusion bulbs with different output Spectra may be considered.

5 Presently we prefer the "D" bulb and the "V" bulb.

One source we have found satisfactory is a 10 inch, 300 watt/inch mercury lamp. The mould assembly is then heated to 100°C for one hour or the lens may be removed from the assembly and heated in air for about one hour at 100°C. This means that fully cured lenses can be manufactured, if desired, in about one hour. Heat curing can also be used without any use of U.V. radiation.

10 Typically 2 - 4 passes under the UV lamps plus an hour of heat treatment at 100°C completes the cure.

Any suitable UV initiator may be used. An initiator available under the trade designation Irgacure 184 has been found to be satisfactory. More than one curing agent may be present. It has been possible to operate with a relatively low level of initiator of between 0.05 and 0.2% by weight.

15 A range of photoinitiators available commercially can be used, depending on sample thickness, type of UV lamp used and the absorption wavelength of the monomer mix.

The following photoinitiators have been found to be suitable.

- Alcolac Vicure 10 - isobutyl benzoin ether
- Alcolac Vicure 30 - isopropyl benzoin ether
- 20 - Alcolac Vicure 55 - methyl phenyl glyoxylate
- Ciba Geigy Irgacure 184 - 1 - hydroxy cyclohexyl phenyl ketone
- Ciba Geigy Irgacure 651 - benzildimethyl ketal
- Ciba Geigy Irgacure 907 - 2 - methyl - 1 - [4-(methylthio)phenyl] - 2 - morpholino - propanone - 1
- Merck Darocur 1664
- 25 - Rohm Catalyst 22

A mixture of the above may also be used. Additionally, combination of photoinitiator mixtures or photoinitiator mixtures with a heat induced free radical initiator such as peroxides, peroxypercarbonates or an azo compound may also be employed.

30 As an alternative to photo curing a heat curing may be used, for example 1,1 di-tert butyl peroxy -3,3,5-trimethylcyclohexane or secondary isopropyl percarbonate.

Other additives may be present which are conventionally used in casting compositions such as inhibitors, dyes, UV stabilisers and materials capable of modifying refractive index. Mould release agents can be added but they are in general not required with the compositions used in the method of the present invention. Such additives may include:

35

#### UV Absorbers including

- Ciba Geigy Tinuvin P - 2(2'-hydroxy-5' methyl phenyl) benzotriazole
- Cyanamid Cyasorb UV 531 -2-hydroxy-4-n-octoxybenzophenone
- 40 - Cyanamid Cyasorb UV5411-2(2-hydroxy-5-t-octylphenyl)benzotriazole
- Cyanamid UV 2098 - 2 hydroxy-4-(2-acryloyloxyethoxy) benzophenone
- National S + C Permasorb MA - 2 hydroxy-4-(2 hydroxy-3-methacryloxy)propoxybenzophenone
- Cyanamid UV24 - 2,2'-dihydroxy-4-methoxybenzophenone
- BASF UVINUL 400 - 2,4 dihydroxy-benzophenone
- 45 - BASF UVINUL D-49 - 2,2'-dihydroxy-4,4' dimethoxy-benzophenone
- BASF UVINUL D-50 - 2,2', 4,4' tetrahydroxy benzophenone
- BASF UVINUL D-35-ethyl-2-cyano-3,3-diphenyl acrylate
- BASF UNINYL N-539-2-ethexyl-2-cyano-3,3-diphenyl acrylate
- Ciba Geigy Tinuvin 213

50

#### Hindered amine light stabilizers (HALS), including

- Ciba Geigy Tinuvin 765/292 - bis (1,2,2,6,6-pentamethyl-4-piperidyl)sebacate
- Ciba Geigy 770 - bis (2,2,6,6-tetramethyl-4-piperidiny)l sebacate

55

Antioxidants including

- Ciba Geigy Irganox 245 - triethylene glycol-bis-3-(3-tert butyl-4-hydroxy-5-methyl phenyl)propionate
- Irganox 1010 - 2,2-bis[[3-[3,4-bis(1,1-dimethylethyl)-4-hydroxyphenyl]-1-oxopropoxy]methyl]-1,3-propanediyl 3,5-bis (1,1-dimethyl ethyl)-4-hydroxy benzene propanoate
- Irganox 1076 - octadecyl 3-(3',5'-di = tert = butyl(-4'-hydroxy phenyl) propionate

Anticolouring agents including

- Triphenyl phosphine
- 9, 10 dihydro-9-oxa-10-phosphaphenanthrene-1-oxide

Cure modifiers including

- Dodecyl mercaptan
- Butyl mercaptan
- Thiophenol

Other monomeric additives can be present in amounts up to 10% by weight as diluents, and include monomers such as methacrylic acid, vinyl silanes, methyl allyl, hydroxy ethyl, benzyl and phenyl methacrylate, styrene and N-vinyl pyrrolidone. Other monomeric additives may be included to improve processing and/or material properties, these include:

- methacrylic acid, maleic anhydride, acrylic acid
- adhesion promoters/modifiers such as Sartomer 9008, Sartomer 9013, Sartomer 9015.
- dye-enhancing, pH-adjusting monomers like Alcolac SIPOMER 2MIM
- a charge-reducing cationic monomer to render the material more antistatic, example Sipomer Q5-80 or Q9-75
- hydrophobic comonomers: Shin Nakamura NPG, P9-G to reduce the water adsorption of the material
- refractive index modifiers such as benzyl or phenyl methacrylates to adjust the refractive index to the desired value.

In a further aspect of the present invention there is provided a polymeric article formed from a cross linkable casting composition as described above. The polymeric article may be an optical article. The optical article may provide characteristics equal to or greater than those achievable with articles made from diethylene glycol bis(allyl carbonate) but with a considerably reduced cure time and substantially increased throughput.

The optical articles prepared by the method of this invention include camera lenses, ophthalmic lenses and video discs.

The casting composition may be formed into a suitable article by mixing in a convenient vessel the components making up the material, and then adding the curing catalyst and/or photo-initiator. The mixed material is then degassed or filtered. As the curing time is substantially reduced the casting process may be undertaken on a continuous or semi-continuous basis.

The present invention will now be more fully described with reference to the accompanying examples.

The following Examples 1 to 4 are provided for purposes of comparison. In all cases the casting material was used to fill the space between a pair of glass moulds separated by a plastic gasket at their periphery and held together by a clip.

| EXAMPLE<br>NUMBER | CASTING<br>MATERIAL                                                                    | CURING<br>CATALYST/<br>INITIATOR | CURING<br>TEMP.<br>AND<br>TIME  | YELLOWNESS<br>INDEX<br>(1.8 m)<br>THICK PLANO<br>LENS | TRANSMISSION<br>%<br>HAZE | BARCOL<br>HARD-<br>NESS | ABRASION<br>200 CYCLES<br>W 500 g<br>LOAD<br>% HAZE | SHRINK-<br>AGE<br>CALCU.<br>MONOMER<br>VALUES<br>% |
|-------------------|----------------------------------------------------------------------------------------|----------------------------------|---------------------------------|-------------------------------------------------------|---------------------------|-------------------------|-----------------------------------------------------|----------------------------------------------------|
| 1.                | Diethylene<br>Glycol Bis<br>(allyl<br>carbonate)                                       | 3.0% SIP                         | 40-90°C<br>17 Hours             | 0.62                                                  | 92.0                      | 31.8                    | 19.0                                                | 14.0                                               |
| 2.                | Example 1<br>coated with<br>Abrasion<br>Resistant<br>coating                           |                                  |                                 | 0.78                                                  | 91.3                      | 33.8                    | 6.7                                                 | 14.0                                               |
| 3.                | 20% PEGM<br>50% U-4HA<br>30% TMPT                                                      | 2%<br>IRGACURE<br>184            | 0.5 Secs.<br>UV 1 Hour<br>100°C | 2.21                                                  | 90.9                      | 56.3                    | 6.8                                                 | 10.4                                               |
| 4.                | 40% PEHM<br>40% Difunctional<br>Urethane<br>Acrylate<br>(Sartomer<br>9504)<br>20% TMPT | 0.2% SIP                         | 40-90°C<br>5 Hours              | Cloudy                                                | Cloudy                    | Soft/<br>Rubber         | -                                                   | -                                                  |

THE FOLLOWING EXAMPLES 5 - 10 ILLUSTRATE BUT DO NOT LIMIT THE INVENTION

| EXAMPLE<br>NUMBER | CASTING<br>MATERIAL               | CURING<br>CATALYST/<br>INITIATOR | CURING<br>TEMP.<br>AND<br>TIME              | YELLOWNESS<br>INDEX<br>(1.8 m)<br>THICK PLANO<br>LENS | %<br>TRANS<br>MISSION | BARCOL<br>HARD-<br>NESS | TABAR<br>ABRASION<br>200 CYCLES<br>W 500 g<br>LOAD<br>% HAZE | SHRINK-<br>AGE<br>CALCU.<br>MONOMER<br>VALUES<br>% |
|-------------------|-----------------------------------|----------------------------------|---------------------------------------------|-------------------------------------------------------|-----------------------|-------------------------|--------------------------------------------------------------|----------------------------------------------------|
| 5.                | 80% PEGM<br>20% TEGM              | 0.1% SIP                         | 40-90°C<br>5 Hours                          | 0.90                                                  | 91.7                  | 1.1                     | 6.8                                                          | 8.0                                                |
| 6.                | 40% PEGM<br>40% U-4HA<br>20% TMPT | 0.1% SIP                         | 40-90°C<br>5 Hours                          | 0.77                                                  | 91.9                  | 47.5                    | 6.8                                                          | 9.2                                                |
| 7.                | 60% PEGM<br>15% U-4HA<br>25% TMPT | 0.2% SIP                         | 40-90°C<br>5 Hours                          | 0.76                                                  | 91.9                  | 28.5                    | 6.5                                                          | 8.0                                                |
| 8.                | 50% PEGM<br>20% U-4HA<br>30% TMPT | 0.2% SIP                         | 40-90°C<br>5 Hours                          | 0.78                                                  | 91.9                  | 43.6                    | 7.1                                                          | 9.2                                                |
| 9.                | 50% PEGM                          | 0.5%<br>IRGACURE<br>184          | 0.5 Secs<br>UV<br>+ 1 hour<br>at 100°C      | 1.05                                                  | 92.3                  | 47.0                    | 6.6                                                          | 9.2                                                |
| 10.               | 50% PEGM<br>30% U-4HA<br>20% TMPT | 0.5%<br>IRGACURE<br>184          | 0.5 secs<br>UV + 1 hour<br>at 100°C (2.2mm) | 2.20                                                  | -                     | 44.0                    | -                                                            | -                                                  |

| EXAMPLE<br>NUMBER | CASTING<br>MATERIAL                        | CURING<br>CATALYST/<br>INITIATOR | CURING<br>TEMP.<br>AND TIME | YELLOWNESS<br>INDEX<br>(1.8 mm)<br>THICK<br>PLANO LENS | TRANS-<br>MISSION<br>HARDNESS<br>% | BARCOL<br>HARDNESS | TABER<br>ABRASION<br>200 CYCLES<br>W 500 g<br>LOAD<br>% HAZE | SHRINKAGE<br>CALCU.<br>MONOMER<br>VALUES<br>% |
|-------------------|--------------------------------------------|----------------------------------|-----------------------------|--------------------------------------------------------|------------------------------------|--------------------|--------------------------------------------------------------|-----------------------------------------------|
| 11.               | 60% 4G<br>20% U-4HA<br>20% TMPT            | 0.1% SIP                         | 40-90°C<br>5 hours          | 1.10                                                   | 91.8                               | 49.2               | 22.0                                                         | 12.6                                          |
| 12.               | 50% 4G<br>30% U-4HA<br>20% TMPT            | 0.1% SIP                         | 40-90°C<br>5 hours          | 1.25                                                   | 91.7                               | 53.4               | 20.1                                                         | 12.3                                          |
| 13.               | 30% 23G<br>30% 3G<br>15% U-4HA<br>25% TMPT | 0.1% SIP                         | 40-90°C<br>5 hours          | 0.80                                                   | 91.2                               | 28.5               | 27.5                                                         | 12.4                                          |
| 14.               | 20% 23G<br>40% 3G<br>20% U-4HA<br>20% TMPT | 0.1% SIP                         | 40-90°C<br>5 hours          | 0.86                                                   | 91.2                               | 40.1               | 27.2                                                         | 12.6                                          |
| 15.               | 55% 9G<br>20% TMPT<br>25% NF201            | 0.2%<br>Vicure 55                | UV +<br>1 hr 100°C          | 0.86                                                   | 91.5                               | 24.2               | 12.0                                                         | 7.9                                           |

| EXAMPLE<br>NUMBER | CASTING<br>MATERIAL             | CURING<br>CATALYST/<br>INITIATOR | CURING<br>TEMP.<br>AND TIME | YELLOWNESS<br>INDEX<br>(1.8 mm)<br>THICK<br>PLANO LENS | TRANS-<br>MISSION<br>HARDNESS | BARCOL<br>HARDNESS | TABER<br>ABRASION<br>200 CYCLES<br>W 500 g<br>LOAD<br>% HAZE | SHRINKAGE<br>CALCU.<br>MONOMER<br>VALUES<br>% |
|-------------------|---------------------------------|----------------------------------|-----------------------------|--------------------------------------------------------|-------------------------------|--------------------|--------------------------------------------------------------|-----------------------------------------------|
| 16.               | 55% 9G<br>20% TMPT<br>25% NF202 | 0.2%<br>Vicure 55                | UV +<br>1 hr 100°C          | 0.63                                                   | 91.6                          | 28.7               | 15.2                                                         | 7.9                                           |
| 17.               | 60% 9G<br>20% TMPT<br>20% U-6HA | 0.2% SIP                         | 40-90°C<br>5 hour           | 0.60                                                   | 92.2                          | 24.2               | 7.0                                                          | 8.8                                           |
| 18.               | 60% 6G<br>20% U-4HA<br>20% TMPT | 0.1% SIP                         | 40-90°C<br>5 hours          | 1.10                                                   | 92.4                          | 38.5               | 8.5                                                          | -                                             |
| 19.               | 60% 6G<br>20% U-4H<br>20% TMPT  | 0.1% SIP                         | 40-90°C<br>5 hours          | 1.15                                                   | 92.4                          | 40.5               | 9.4                                                          | -                                             |
| 20.               | 60% 9G<br>20% U-4H<br>20% TMPT  | 0.1% SIP                         | 40-90°C<br>5 hours          | 0.72                                                   | 92.4                          | 28.8               | 7.6                                                          | -                                             |

5

10

15

20

25

30

35

40

45

50

55

| EXAMPLE<br>NUMBER | CASTING<br>MATERIAL | CURING<br>CATALYST/<br>INITIATOR | CURING<br>TEMP.<br>AND TIME | YELLOWNESS                               |                        | BARCOL<br>HARDNESS | TABER                         |        | SHRINKAGE<br>CALCU.<br>MONOMER<br>VALUES<br>% |
|-------------------|---------------------|----------------------------------|-----------------------------|------------------------------------------|------------------------|--------------------|-------------------------------|--------|-----------------------------------------------|
|                   |                     |                                  |                             | INDEX<br>(1.8 mm)<br>THICK<br>PLANO LENS | %<br>TRANS-<br>MISSION |                    | 200 CYCLES<br>W 500 g<br>LOAD | % HAZE |                                               |
| 21.               | 50% 9G              | 0.1% SIP                         | 40-90°C                     | 0.83                                     | 92.5                   | 40.2               | 7.6                           | -      | -                                             |
|                   | 30% U-4H            |                                  | 5 hours                     |                                          |                        |                    |                               |        |                                               |
|                   | 20% TMPT            |                                  |                             |                                          |                        |                    |                               |        |                                               |
| 22.               | 50% 6G              | 0.1% SIP                         | 40-90°C                     | 1.20                                     | 92.4                   | 46.4               | 9.2                           | -      | -                                             |
|                   | 30% U-4H            |                                  | 5 hours                     |                                          |                        |                    |                               |        |                                               |
|                   | 20% TMPT            |                                  |                             |                                          |                        |                    |                               |        |                                               |
| 23.               | 40% 9G              | 0.1% SIP                         | 40-90°C                     | 0.94                                     | 92.6                   | 43.6               | 7.5                           | -      | -                                             |
|                   | 30% U-4H            |                                  | 5 hours                     |                                          |                        |                    |                               |        |                                               |
|                   | 20% ETMPT           |                                  |                             |                                          |                        |                    |                               |        |                                               |
| 24.               | 40% 9G              | 0.1% SIP                         | 40-90°C                     | 1.06                                     | 92.6                   | 34.8               | 9.4                           | -      | -                                             |
|                   | 20% U-4H            |                                  | 5 hours                     |                                          |                        |                    |                               |        |                                               |
|                   | 40% ETMPT           |                                  |                             |                                          |                        |                    |                               |        |                                               |
| 25.               | 60% 9G              | 0.1% SIP                         | 40-90°C                     | 0.93                                     | 92.8                   | 12.9               | 6.2                           | -      | -                                             |
|                   | 20% ETMPT           |                                  | 5 hours                     |                                          |                        |                    |                               |        |                                               |
|                   | 20% U-4HA           |                                  |                             |                                          |                        |                    |                               |        |                                               |

| EXAMPLE<br>NUMBER | CASTING<br>MATERIAL              | CURING<br>CATALYST/<br>INITIATOR | CURING<br>TEMP.<br>AND TIME | YELLOWNESS<br>INDEX<br>(1.8 mm)<br>THICK<br>PLANO LENS | TRANSP-<br>MISSION<br>HARDNESS | BARCOL<br>HARDNESS | ABRASION<br>200 CYCLES<br>W 500 g<br>LOAD | SHRINKAGE<br>CALCU.<br>MONOMER<br>VALUES |
|-------------------|----------------------------------|----------------------------------|-----------------------------|--------------------------------------------------------|--------------------------------|--------------------|-------------------------------------------|------------------------------------------|
| 26.               | 60% 9G<br>20% ETMPT<br>20% U-4H  | 0.1% SISP                        | 40-90°C<br>5 hours          | 0.87                                                   | 92.8                           | 13.1               | 11.3                                      | -                                        |
| 27.               | 60% 6G<br>20% ETMPT<br>20% U-4HA | 0.1% SIP                         | 40-90°C<br>5 hours          | 1.30                                                   | 92.1                           | 28.5               | 8.5                                       | -                                        |
| 28.               | 60% 6G<br>20% ETMPT<br>20% U-4H  | 0.1% SIP                         | 40-90°C<br>5 hours          | 1.27                                                   | 92.5                           | 31.0               | 8.7                                       | -                                        |
| 29.*              | 40% U-6HA<br>20% ATMWT<br>40% 9G | 0.1% SIP                         | 40-90°C<br>5 hours          | 0.90                                                   | 92.3                           | 39.8               | 4.7                                       | -                                        |
| 30.*              | 40% U-6HA<br>20% ATMWT<br>40% 4G | 0.1% SIP                         | 40-90°C<br>5 hours          | 1.33                                                   | 91.8                           | 50.4               | 7.6                                       | -                                        |

| EXAMPLE<br>NUMBER | CASTING<br>MATERIAL                                                                                               | CURING<br>CATALYST/<br>INITIATOR | CURING<br>TEMP.<br>AND TIME | YELLOWNESS<br>INDEX<br>(1.8 mm)<br>THICK<br>PLANO LENS | TRANS-<br>MISSION<br>HARDNESS | BARCOL<br>HARDNESS | TABER<br>ABRASION<br>200 CYCLES<br>W 500 g<br>LOAD<br>% HAZE | SHRINKAGE<br>CALCU.<br>MONOMER<br>VALUES<br>% |
|-------------------|-------------------------------------------------------------------------------------------------------------------|----------------------------------|-----------------------------|--------------------------------------------------------|-------------------------------|--------------------|--------------------------------------------------------------|-----------------------------------------------|
| 31.*              | 40% U-6HA                                                                                                         | 0.1% SIP                         | 40-90°C<br>5 hours          | 1.53                                                   | 91.6                          | 51.6               | 9.1                                                          | -                                             |
|                   | 20% ATMWT                                                                                                         |                                  |                             |                                                        |                               |                    |                                                              |                                               |
|                   | 40% 3G                                                                                                            |                                  |                             |                                                        |                               |                    |                                                              |                                               |
| PEGM              | = polyethylene glycol dimethacrylate with 9 polymerisation units of ethylene glycol                               |                                  |                             |                                                        |                               |                    |                                                              |                                               |
| U-4HA             | = tetra functional urethaneacrylate of the general formula given above sold under the trade name by SHIN NAKAMURA |                                  |                             |                                                        |                               |                    |                                                              |                                               |
| TMPT              | = trimethylol propane trimethacrylate                                                                             |                                  |                             |                                                        |                               |                    |                                                              |                                               |
| SIP               | = Secondary Isopropyl Percarbonate                                                                                |                                  |                             |                                                        |                               |                    |                                                              |                                               |
| 3G                | = polyethylene glycol dimethacrylate with 3 ethylene oxide units.                                                 |                                  |                             |                                                        |                               |                    |                                                              |                                               |
| 4G                | = polyethylene glycol dimethacrylate with 4 ethylene oxide units.                                                 |                                  |                             |                                                        |                               |                    |                                                              |                                               |
| 23G               | = polyethylene glycol dimethacrylate with 23 ethylene oxide units.                                                |                                  |                             |                                                        |                               |                    |                                                              |                                               |
| NF201             | = aliphatic urethane dimethacrylate produced by Mitsubishi Rayon Corporation                                      |                                  |                             |                                                        |                               |                    |                                                              |                                               |
| NF202             | = aromatic urethane dimethacrylate produced by Mitsubishi Rayon Corporation                                       |                                  |                             |                                                        |                               |                    |                                                              |                                               |
| U-6HA             | = urethane oligomer from Shin Nakamura with 6 polymerizable groups per molecule.                                  |                                  |                             |                                                        |                               |                    |                                                              |                                               |
| 6G                | = polyethylene glycol dimethacrylate with 6 ethylene oxide units                                                  |                                  |                             |                                                        |                               |                    |                                                              |                                               |
| U-4H              | = aliphatic urethane tetramethacrylate oligomer manufactured by Shin Nakamura                                     |                                  |                             |                                                        |                               |                    |                                                              |                                               |
| ETMPT             | = ethoxylated trimethylolpropane trimethacrylate                                                                  |                                  |                             |                                                        |                               |                    |                                                              |                                               |
| ATMWT             | = pentaerythritol tetraacrylate                                                                                   |                                  |                             |                                                        |                               |                    |                                                              |                                               |

\* Examples 29-31 have unacceptably high viscosities of 1110, 582 and 446 cp (25°C) respectively.

The above examples demonstrate that lenses cast in accordance with the method of the present invention have an abrasion resistance of the same order as a lens cast from diethylene-glycol bis (allyl carbonate) which has been coated with an abrasion resistant coating. It can be seen from Example 5, that the absence of the urethane acrylate gave a product with a low level of hardness measured on the Barcol scale. Such flexible lenses may provide useful products in the safety field. The unacceptability of a

difunctional acrylate in combination with a polyethylene glycol dimethacrylate and TMPT is demonstrated by comparison of Examples 4 and 6. All significant characteristics of the lens made in accordance with the invention can be seen to be equivalent or superior to a lens cast from diethylene glycol bis (allyl carbonate).

The following examples illustrate how the relevant proportions of the polyethylene glycol monomer and the urethane monomer can affect the viscosity of the monomer mixture used for casting lenses:

|    | Monomer Mixture % by weight |       |      | Viscosity in Pas (CPS) at 25 Degrees C |
|----|-----------------------------|-------|------|----------------------------------------|
|    | PEGM                        | U-4HA | TMPT |                                        |
| 1. | 70                          | 10    | 20   | 0,0524 (52.4)                          |
| 2. | 65                          | 15    | 20   | 0,0637 (63.7)                          |
| 3. | 60                          | 20    | 20   | 0,0768 (76.8)                          |
| 4. | 55                          | 25    | 20   | 0,0966 (96.6)                          |
| 5. | 50                          | 30    | 20   | 0,1239 (123.9)                         |
| 6. | 40                          | 40    | 20   | 0,2079 (207.9)                         |
| 7. | 30                          | 50    | 20   | 0,3777 (377.7)                         |
| 8. | 20                          | 60    | 20   | 0,796 (796)                            |

It can be seen that the compositions which are outside the scope of the invention have a viscosity which would render casting difficult.

#### Claims

- A cross-linkable polymeric casting composition for use in the manufacture of optical articles such as lenses, characterised in that:
  - the composition is optically clear;
  - the composition comprises:
    - at least one polyoxyalkylene glycol diacrylate or dimethacrylate compound;
    - at least one unsaturated polyfunctional cross-linking agent which is a tri - or tetra-functional vinyl, acrylic or methacrylic monomer other than (C);
    - a urethane monomer having from two to six terminal acrylic and/or methacrylic groups; the weight ratio of the cross-linking agent (B) to the urethane monomer (C) being in the range of approximately 1:4 to 2:1; and
  - the viscosity of the composition at 25° is 0,2 Pas (200 cps) or lower.
- A casting composition according to claim 1, wherein the diacrylate or dimethacrylate compound (A) includes ethylene oxide or propylene oxide repeating units in its backbone.
- A casting composition according to claim 2, wherein the diacrylate or dimethacrylate compound (A) includes 6 to 20 ethylene oxide repeating units in the backbone thereof.
- A casting composition according to claim 3, wherein the diacrylate or dimethacrylate compound (A) is a polyethylene glycol dimethacrylate with an average molecular weight of the order of 600.
- A casting composition according to any one of the preceding claims, wherein the diacrylate or dimethacrylate compound (A) is present in amounts of from 40% by weight to 60% by weight, based on the total weight of the casting composition.
- A casting composition according to any one of the preceding claims, wherein the polyfunctional unsaturated cross-linking agent (B) is selected from trimethylol propane trimethacrylate, pentaerythritol triacrylate or pentaerythritol tetracrylate.
- A casting composition according to any one of the preceding claims, wherein the polyfunctional unsaturated cross-linking agent (B) is present in amounts of from 10 to 30% by weight, based on the total weight of the casting composition.

difunctional acrylate in combination with a polyethylene glycol dimethacrylate and TMPT is demonstrated by comparison of Examples 4 and 6. All significant characteristics of the lens made in accordance with the invention can be seen to be equivalent or superior to a lens cast from diethylene glycol bis (allyl carbonate).

The following examples illustrate how the relevant proportions of the polyethylene glycol monomer and the urethane monomer can affect the viscosity of the monomer mixture used for casting lenses:

|    | Monomer Mixture % by weight |       |      | Viscosity in Pas (CPS) at 25 Degrees C |
|----|-----------------------------|-------|------|----------------------------------------|
|    | PEGM                        | U-4HA | TMPT |                                        |
| 1. | 70                          | 10    | 20   | 0,0524 (52.4)                          |
| 2. | 65                          | 15    | 20   | 0,0637 (63.7)                          |
| 3. | 60                          | 20    | 20   | 0,0768 (76.8)                          |
| 4. | 55                          | 25    | 20   | 0,0966 (96.6)                          |
| 5. | 50                          | 30    | 20   | 0,1239 (123.9)                         |
| 6. | 40                          | 40    | 20   | 0,2079 (207.9)                         |
| 7. | 30                          | 50    | 20   | 0,3777 (377.7)                         |
| 8. | 20                          | 60    | 20   | 0,796 (796)                            |


It can be seen that the compositions which are outside the scope of the invention have a viscosity which would render casting difficult.

#### Claims

1. A cross-linkable polymeric casting composition for use in the manufacture of optical articles such as lenses, characterised in that:
  - (i) the composition is optically clear;
  - (ii) the composition comprises:
    - (A) at least one polyoxyalkylene glycol diacrylate or dimethacrylate compound;
    - (B) at least one unsaturated polyfunctional cross-linking agent which is a tri - or tetra-functional vinyl, acrylic or methacrylic monomer other than (C);
    - (C) a urethane monomer having from two to six terminal acrylic and/or methacrylic groups; the weight ratio of the cross-linking agent (B) to the urethane monomer (C) being in the range of approximately 1:4 to 2:1; and
  - (iii) the viscosity of the composition at 25° is 0,2 Pas (200 cps) or lower.
2. A casting composition according to claim 1, wherein the diacrylate or dimethacrylate compound (A) includes ethylene oxide or propylene oxide repeating units in its backbone.
3. A casting composition according to claim 2, wherein the diacrylate or dimethacrylate compound (A) includes 6 to 20 ethylene oxide repeating units in the backbone thereof.
4. A casting composition according to claim 3, wherein the diacrylate or dimethacrylate compound (A) is a polyethylene glycol dimethacrylate with an average molecular weight of the order of 600.
5. A casting composition according to any one of the preceding claims, wherein the diacrylate or dimethacrylate compound (A) is present in amounts of from 40% by weight to 60% by weight, based on the total weight of the casting composition.
6. A casting composition according to any one of the preceding claims, wherein the polyfunctional unsaturated cross-linking agent (B) is selected from trimethylol propane trimethacrylate, pentaerythritol triacrylate or pentaerythritol tetracrylate.
7. A casting composition according to any one of the preceding claims, wherein the polyfunctional unsaturated cross-linking agent (B) is present in amounts of from 10 to 30% by weight, based on the total weight of the casting composition.




8. A casting composition according to any one of the preceding claims, wherein the urethane monomer (C) is a tetracrylic urethane monomer.
9. A casting composition according to claim 8, wherein the urethane monomer (C) is a tetracrylic urethane monomer of the formula



wherein R, R<sup>1</sup>, R<sup>2</sup> and R<sup>3</sup> which may be the same or different are selected from hydrogen, alkyl of 1 to 6 carbon atoms or a substituted alkyl of 1 to 6 carbon atoms; and X is an organic residue having 1 to 20 carbon atoms.

10. A casting composition according to claim 9, wherein X is selected from C<sub>1</sub>-C<sub>20</sub> alkyl, alkoxy, alkyl-amino, alkyl carbonyl, alkoxy carbonyl, alkylamido or alkoxy amide group; which may be substituted or unsubstituted with one or more halogen, hydroxyl, nitro, amino, alkyl or alkoxy groups.
11. A casting composition according to claim 9, wherein the urethane monomer is a compound of the formula



55 wherein R is a hydrogen atom or a methyl group or a substituted methyl group and X is an organic residue having 2 to 20 carbon atoms.




12. A casting composition according to any one of the preceding claims, wherein the tetracrylic urethane monomer (C) is present in amounts of from 10 to 40% by weight, based on the total weight of the casting composition.
- 5 13. A casting composition according to any one of the preceding claims, further including a heat and/or ultraviolet cross-linking initiator.
14. A casting composition according to claim 13, wherein the cross-linking initiator is selected from 1 - hydroxy cyclohexyl phenyl ketone; 1,1 - di-tert butyl peroxy-3,3,5-trimethylcyclohexane or secondary  
10 isopropyl percarbonate.
15. A polymeric article formed from a cross-linkable polymeric casting composition according to any one of the preceding claims.
- 15 16. A polymeric article according to claim 15, which is an ophthalmic lens.
17. Use of a polymeric casting composition as defined in any one of claims 1 to 16 for the manufacture of an ophthalmic lens.

## 20 Patentansprüche

1. Vernetzbare polymere Gießmasse zur Verwendung bei der Herstellung von optischen Gegenständen wie Linsen, dadurch gekennzeichnet, daß:
- (i) die Masse optisch klar ist;
- 25 (ii) die Masse umfaßt:
- (A) mindestens eine Polyoxyalkylenglykol-diacrylat- oder -dimethacrylat-Verbindung;
- (B) mindestens ein ungesättigtes polyfunktionelles Vernetzungsmittel, das ein drei- oder vierwertiges Vinyl-, Acryl- oder Methacrylmonomer ist, außer (C);
- (C) ein Urethanmonomer mit zwei bis sechs terminalen Acryl- und/oder Methacrylgruppen; wobei  
30 das Gewichtsverhältnis des Vernetzungsmittels (B) zu dem Urethanmonomer (C) im Bereich von etwa 1:4 bis 2:1 liegt; und
- (iii) die Viskosität der Masse bei 25 °C 0,2 Pa·s (200 cps) oder weniger beträgt.
2. Gießmasse nach Anspruch 1, wobei die Diacrylat- oder Dimethacrylat-Verbindung (A) wiederkehrende  
35 Ethylenoxid- oder Propylenoxid-Einheiten in der Hauptkette enthält.
3. Gießmasse nach Anspruch 2, wobei die Diacrylat- oder Dimethacrylat-Verbindung (A) 6 bis 20 wiederkehrende Ethylenoxid-Einheiten in der Hauptkette enthält.
- 40 4. Gießmasse nach Anspruch 3, wobei die Diacrylat- oder Dimethacrylat-Verbindung (A) ein Polyethylenglykol-dimethacrylat mit einem mittleren Molekulargewicht in der Größenordnung von 600 ist.
5. Gießmasse nach einem der vorangehenden Ansprüche, wobei die Diacrylat- oder Dimethacrylat-Verbindung (A) in einer Menge von 40 bis 60 Gew.-%, bezogen auf das Gesamtgewicht der  
45 Gießmasse, vorhanden ist.
6. Gießmasse nach einem der vorangehenden Ansprüche, wobei das polyfunktionelle ungesättigte Vernetzungsmittel (B) ausgewählt ist aus Trimethylolpropan-trimethacrylat, Pentaerythrit-triacrylat oder Pentaerythrit-tetraacrylat.
- 50 7. Gießmasse nach einem der vorangehenden Ansprüche, wobei das polyfunktionelle ungesättigte Vernetzungsmittel (B) in einer Menge von 10 bis 30 Gew.-%, bezogen auf das Gesamtgewicht der Gießmasse, vorhanden ist.
8. Gießmasse nach einem der vorangehenden Ansprüche, wobei das Urethanmonomer (C) ein Tetraacrylurethanmonomer ist.
- 55




9. Gießmasse nach Anspruch 8, wobei das Urethanmonomer (C) ein Tetraacryl-urethanmonomer ist der Formel



in der R, R<sup>1</sup>, R<sup>2</sup> und R<sup>3</sup>, die gleich oder verschieden sein können, ausgewählt sind aus Wasserstoff, Alkyl mit 1 bis 6 Kohlenstoffatomen oder einem substituierten Alkyl mit 1 bis 6 Kohlenstoffatomen, und X ein organischer Rest mit 1 bis 20 Kohlenstoffatomen ist.

10. Gießmasse nach Anspruch 9, wobei X ausgewählt ist aus C<sub>1</sub>-C<sub>20</sub>-Alkyl-, Alkoxy-, Alkylamino-, Alkylcarbonyl-, Alkoxycarbonyl-, Alkylamido- oder Alkoxyamidgruppen, die unsubstituiert sein können oder substituiert mit einer oder mehreren Halogen-, Hydroxyl-, Nitro-, Amino-, Alkyl- oder Alkoxygruppen.

11. Gießmasse nach Anspruch 9, wobei das Urethanmonomer eine Verbindung ist der Formel



in der R ein Wasserstoffatom oder eine Methylgruppe oder eine substituierte Methylgruppe ist und X ein organischer Rest mit 2 bis 20 Kohlenstoffatomen.

12. Gießmasse nach einem der vorangehenden Ansprüche, wobei das Tetraacryl-urethanmonomer (C) in einer Menge von 10 bis 40 Gew.-%, bezogen auf das Gesamtgewicht der Gießmasse, vorhanden ist.

13. Gießmasse nach einem der vorangehenden Ansprüche, enthaltend zusätzlich einen Wärme- und/oder UV-Vernetzungsinitiator.




14. Gießmasse nach Anspruch 13, wobei der Vernetzungsinitiator ausgewählt ist aus 1-Hydroxycyclohexylphenylketon, 1,1-Di-tert.-butylperoxy-3,3,3-trimethylcyclohexan oder sec.Isopropylpercarbonat.
15. Polymerer Gegenstand, gebildet aus einer vernetzbaren polymeren Gießmasse nach einem der vorangehenden Ansprüche.
16. Polymerer Formkörper nach Anspruch 15, der eine Augenlinse ist.
17. Verwendung einer polymeren Gießmasse nach einem der Ansprüche 1 bis 16 zur Herstellung einer Augenlinse.

# Revendications

1. Une composition de coulée à base de polymères réticulable destinée à être utilisée pour la fabrication d'articles optiques tels que des lentilles, caractérisée en ce que:
- (i) la composition est optiquement transparente;
  - (ii) la composition comprend:
    - (A) au moins un composé de diacrylate ou diméthacrylate de polyoxyalkylèneglycol,
    - (B) au moins un agent de réticulation polyfonctionnel non saturé qui est un monomère tri- ou tétrafonctionnel vinylique, acrylique ou méthacrylique autre que (C),
    - (C) un monomère d'uréthane ayant de deux à six groupements acrylique et/ou méthacrylique terminaux; le rapport en poids de l'agent de réticulation (B) au monomère d'uréthane (C) étant compris dans la gamme d'approximativement 1/4 à 2/1; et
    - (iii) la viscosité de la composition à 25 °C est de 0,2 Pas (200 cps) ou moins.
2. Une composition de coulée selon la revendication 1, dans laquelle le composé de diacrylate ou de diméthacrylate (A) comprend dans sa chaîne des unités répétitives d'oxyde d'éthylène ou d'oxyde de propylène.
3. Une composition de coulée selon la revendication 2, dans laquelle le composé (A) de diacrylate ou de diméthacrylate comprend de 6 à 20 unités répétitives d'oxyde d'éthylène dans sa chaîne.
4. Une composition de coulée selon la revendication 3, dans laquelle le composé (A) de diacrylate ou de diméthacrylate est un diméthacrylate de polyéthylèneglycol ayant un poids moléculaire moyen de l'ordre de 600.
5. Une composition de coulée selon l'une quelconque des revendications précédentes, dans laquelle le composé (A) de diacrylate ou de diméthacrylate est présent en quantité de 40% en poids à 60% en poids, calculée sur le poids total de la composition de coulée.
6. Une composition de coulée selon l'une quelconque des revendications précédentes, dans laquelle l'agent de réticulation (B) polyfonctionnel non saturé est choisi dans le groupe comprenant le triméthacrylate de triméthylolpropane, le triacrylate de pentaérythritol ou le tétracrylate de pentaérythritol.
7. Une composition de coulée selon l'une quelconque des revendications précédentes, dans laquelle l'agent de réticulation (B) polyfonctionnel non saturé est présent en quantité de 10 à 30% en poids, calculée sur le poids total de la composition de coulée.
8. Une composition de coulée selon l'une quelconque des revendications précédentes, dans laquelle le monomère d'uréthane (C) est un monomère d'uréthane tétracrylique.
9. Une composition de coulée selon la revendication 8, dans laquelle le monomère d'uréthane (C) est un monomère d'uréthane tétracrylique ayant la formule:





dans laquelle:

R, R<sup>1</sup>, R<sup>2</sup> et R<sup>3</sup>,


qui peuvent être identiques ou différents, sont choisis dans le groupe comprenant l'hydrogène, un alkyle ayant de 1 à 6 atomes de carbone ou un alkyle substitué ayant de 1 à 6 atomes de carbone; et

X

est un reste organique ayant de 1 à 20 atomes de carbone.

10. Une composition de coulée selon la revendication 9, dans laquelle X est choisi dans le groupe comprenant un groupement C<sub>1</sub> à C<sub>20</sub> alkyle, alcoxy, alkylamino, alkylcarbonyle, alcoxycarbonyle, alkylamido ou alcoxyamide; qui peut être substitué ou non substitué avec un ou plusieurs groupements halogène, hydroxyle, nitro, amino, alkyle ou alcoxy.

11. Une composition de coulée selon la revendication 9, dans laquelle le monomère d'uréthane est un composé de formule:



dans laquelle:

R est un atome d'hydrogène ou un groupement méthyle ou un groupement méthyle substitué, et

X est un résidu organique ayant de 2 à 20 atomes de carbone.

12. Une composition de coulée selon l'une quelconque des revendications précédentes, dans laquelle le monomère (C) d'uréthane tétracrylique est présent en quantité de 10 à 40% en poids, calculée sur le poids total de la composition de coulée.



13. Une composition de coulée selon l'une quelconque des revendications précédentes, comprenant en outre un initiateur de réticulation thermique et/ou ultraviolet.
14. Une composition de coulée selon la revendication 13, dans laquelle l'initiateur de réticulation est choisi dans le groupe formé de 1-hydroxy-cyclohexylphénylcétone, 1,1-di-tertbutylpéroxy-3,3,5-triméthylcyclohexane ou percarbonate isopropylique secondaire.
15. Un article à base de polymères réalisé à partir d'une composition de coulée de polymère réticulable selon l'une quelconque des revendications précédentes.
16. Un article à base de polymères selon la revendication 15, qui est une lentille ophtalmique.
17. Utilisation d'une composition de coulée à base de polymères telle que définie dans l'une quelconque des revendications 1 à 16, pour la fabrication d'une lentille ophtalmique.

