CLAIMS

1. A fibrous sheet having a stress relaxation rate defined by a formula below of less than or equal to 85%:

stress relaxation rate [%] = (stress S_5 at extension after five minutes/stress S_0 at initial extension) × 100

when a stress at extension immediately after extension in an in-plane first direction at 50% elongation is defined as a stress S_0 (N/50 mm) at initial extension, and a stress at extension at a time of extending in the first direction at 50% elongation for five minutes is defined as a stress S_5 (N/50 mm) at extension after five minutes.

2. The fibrous sheet according to claim 1,
wherein the stress relaxation rate is greater than or equal to 65%.

3. The fibrous sheet according to claim 1 or 2,
wherein the stress S_0 at initial extension is from 2 to 30 N/50 mm.

4. The fibrous sheet according to any one of claims 1 to 3,
wherein the fibrous sheet has a length direction and a width direction, and
the first direction is the length direction.

5. The fibrous sheet according to any one of claims 1 to 4,
wherein the fibrous sheet is a nonwoven fabric sheet.

6. The fibrous sheet according to claim 5,
wherein the fibrous sheet comprises crimped fibers.

7. The fibrous sheet according to any one of claims 1 to 6,
wherein the fibrous sheet has a curved surface sliding stress of 3 to 30 N/50 mm.

8. The fibrous sheet according to any one of claims 1 to 7,
wherein the fibrous sheet is a bandage.