

DESCRIPTION

TITLE OF INVENTION

5 SCREEN PRINTING PLATE FOR SOLAR CELL AND
 METHOD FOR PRINTING SOLAR CELL ELECTRODE

TECHNICAL FIELD

10 [0001]

 This invention relates to a screen printing plate which enables manufacture of solar cells with long-term reliability at good productivity. More particularly, it relates to a screen printing plate whose bus bar electrode mask pattern is
15 modified such that electrodes may be formed at low cost while maintaining high conversion efficiency; and a method of printing solar cell electrodes using the screen printing plate.

BACKGROUND ART

20 [0002]

 A solar cell manufactured by the prior art technology is described with reference to its cross-sectional view (FIG. 1), front surface configuration (FIG. 2), and back surface configuration (FIG. 3). In general, the solar cell includes
25 a p-type semiconductor substrate 100 of silicon or the like in which an n-type dopant is diffused to form an n-type diffusion layer 101 to define a p-n junction. On the n-type diffusion layer 101, an antireflection film 102 such as SiNx film is formed. On the back surface of p-type semiconductor
30 substrate 100, aluminum paste is coated over substantially the entire surface and fired to form a back surface field (BSF) layer 103 and an aluminum electrode 104. Also on the back surface, a broad electrode 106, known as bus bar
electrode, is formed for current collection by coating a
35 conductive paste containing silver or the like and firing. On the light-receiving surface side, finger electrodes 107 for current collection and broad electrodes 105, known as bus

bar electrodes, for collecting current from the finger electrodes are arranged in a comb-shaped pattern so as to cross at substantially right angles.

[0003]

5 In the manufacture of solar cells of this type, electrodes may be formed by various methods including evaporation, plating, printing and the like. The front finger electrodes 107 are generally formed by the printing/firing method to be described below because of ease
10 of formation and low cost. Specifically, a conductive paste obtained by mixing silver powder, glass frit, organic vehicle, and organic solvent as main ingredients is generally used as the front electrode material. The conductive paste is coated by screen printing process or the like, and fired at high
15 temperature in a firing furnace to form the front electrode.

[0004]

The screen printing process is described below.

The screen printing process uses a screen printing plate which is prepared by providing a mesh fabric 110 of
20 orthogonally woven warp and weft filaments, coating the fabric with a photosensitive emulsion 111, exposure, and removing parts of the emulsion to define a substantially rectangular pattern hole (FIG. 4). The screen printing plate is placed over the work to be printed. A print paste (ink) is rested on
25 the screen printing plate and spread over the pattern. A flexible blade known as printing squeegee 112 is traversed at a suitable squeegee hardness (60 to 80 degrees), squeegee angle (60 to 80 degrees), pressure or applied pressure (0.2 to 0.5 MPa), and printing speed (20 to 100 mm/sec) for thereby
30 transferring the print paste to the work to be printed through the pattern hole. The print paste applied to the work to be printed is then dried to form a printed pattern.

[0005]

Immediately after the print paste falls down through
35 meshes in the pattern hole where filaments are absent and attaches to the work to be printed, the print paste remains unattached to portions corresponding to warp and weft

filaments in the pattern hole. Later, the print paste attached to the portions corresponding to meshes starts flowing, resulting in a continuous printed pattern of uniform thickness.

5 [0006]

As described above, the screen printing process is such that the print paste filled in the pattern hole on the screen printing plate is transferred to the work to be printed by traversing movement of the printing squeegee (or blade) whereby the same pattern as the pattern hole defined on the screen printing plate is formed on the work to be printed.
10 [0007]

The contact resistance between the front finger electrode 107 formed by the above process and the silicon substrate 100 and the interconnect resistance of the electrode largely affect the conversion efficiency of a solar cell. To gain a high efficiency (low cell series resistance, high fill factor (FF)), the contact resistance and the interconnect resistance of the front finger electrode 107 must have fully low values.
15 [0008]

Also, the electrode area must be small so that the light-receiving surface may take in as much light as possible. To improve short-circuit current (J_{sc}) while maintaining the FF, the finger electrode must be formed such that it may have a reduced width (thin) and an increased cross-sectional area, that is, a high aspect ratio.
25 [0009]

While various methods are used to form solar cell electrodes, known methods of forming ultra-fine lines having a high aspect ratio include a method of forming grooves in a cell and filling the grooves with paste (JP-A 2006-54374) and a printing method based on inkjet printing. However, the former method is undesirable because the step of forming grooves in a substrate can cause damage to the substrate.
30 Since the latter, inkjet printing method is designed to apply pressure to liquid to inject droplets through a thin nozzle,

it is suitable to form fine lines, but difficult to gain a height.

[0010]

On the other hand, the screen printing method is a
5 low-cost, high-productivity method because formation of a
printed pattern is easy, damaging of the substrate is
minimized by adjusting the applied pressure, and the working
rate per cell is high. If a conductive paste having high
thixotropy is used, an electrode retaining the shape as
10 transferred and having a high aspect ratio can be formed.

[0011]

As discussed above, the screen printing method is more
suitable to form high-aspect-ratio electrodes at low cost,
than other printing methods.

15 [0012]

However, when fine lines are printed using the above
method, there arise a problem that the connection between bus
bar electrode and finger electrode becomes very thin and at
the worst, broken. If the finger electrode on the
20 light-receiving side is locally thinned or even broken, that
portion becomes a controlling factor of resistance, resulting
in a drop of fill factor.

[0013]

The cause of breakage is a difference in film
25 thickness at the connection between bus bar electrode and
finger electrode. In screen printing, the buildup of paste
is in proportion to the size of an opening. Namely, a large
buildup of paste is given for the bus bar electrode
corresponding to a large opening whereas a small buildup of
30 paste is given for the finger electrode corresponding to a
small opening. Thus a difference arises in film thickness
between the bus bar electrode and the finger electrode. If
the electrodes are fired in this state, breakage occurs at
the boundary between bus bar electrode and finger electrode
35 because the bus bar electrode with a larger buildup undergoes
a more shrinkage. If the difference is small, there arises a

phenomenon that the connection between bus bar electrode and finger electrode becomes very thin.

[0014]

Further, in the screen printing process, the printing
5 direction (traversing direction of a printing squeegee) also becomes a factor of promoting breakage. For preventing breakage of a finger electrode, the screen printing plate 1 is generally patterned such that the printing direction and the finger electrode opening 2 are substantially parallel,
10 and the printing direction and the bus bar electrode opening 3 are substantially perpendicular (FIG. 8). With this design, the electrodes as printed are configured such that the width of the connection between bus bar electrode 13 and finger electrode 12 positioned on the upstream printing side with
15 respect to finger electrode 12 is very narrow (FIG. 9). Such narrowing is outstanding particularly when fine lines are printed. This is because at the connection between finger electrode opening 2 and bus bar electrode opening 3, the printing squeegee falls in bus bar electrode opening 3,
20 resulting in a less buildup of paste at this connection. In contrast, the width of the connection between bus bar electrode 13 and finger electrode 12 positioned on the downstream printing side tends to be broad because of a more buildup of paste (FIG. 9). Notably the plate includes
25 blocked or masked zones 5.

[0015]

In addition, a saddle phenomenon is likely to occur since the bus bar electrode opening 3 is considerably wider than the finger electrode opening 2 and the squeegee 112
30 traverses across the plate perpendicular to the bus bar electrode opening 3 as mentioned above. The saddle phenomenon is that when a wide open portion like bus bar is printed, the open portion is pressed by the squeegee 112 (FIG. 5), and a central portion 113 is dented deeper than edges of paste in
35 the width direction of bus bar electrode (FIG. 6). Occurrence of a saddle phenomenon brings a difference between the height of bus bar electrode at its edge in its width direction and

the height of finger electrode. Since the bus bar electrode edge with a more buildup has a higher shrinkage factor during electrode firing, the connection between bus bar electrode 13 and finger electrode 12 can be broken 114 (FIG. 10). It is
5 noted that in FIG. 10, the broken line denotes the connection between bus bar electrode 13 and finger electrode 12.

[0016]

Even when a finger electrode and a bus bar electrode are separately printed, a saddle phenomenon occurs at the bus
10 bar electrode, failing to prevent breakage at the connection between bus bar electrode and finger electrode.

[0017]

To solve the above problem, JP-A 2009-272405 discloses broadening of the connection between bus bar electrode and
15 finger electrode. On use of this method, however, blurs or clumps form because the connection between bus bar electrode and finger electrode is extremely thick. This gives rise to problems like an increased shadow loss and deteriorated properties. Since the solar cell is, as a matter of course,
20 a device which is used under sunlight, there are many chances to public view, unlike other semiconductor devices. Accordingly, not only the performance, but also the appearance is very important for the solar cell. The method of the above patent has the problem that since the connection
25 between bus bar electrode and finger electrode is thick, the finger electrode becomes discontinuous in width, detracting from the aesthetic appearance.

[0018]

It is also known to prevent the squeegee from falling
30 in the bus bar opening by performing screen printing with the installation position of the screen printing plate rotated to an angle other than multiples of 90° relative to the squeegee travel direction (FIG. 7). This method, however, has the problem that since the squeegee travel direction is not
35 parallel to the finger opening, the finger electrode is blurred, failing in precise printing.

SUMMARY OF INVENTION

Technical Problem

[0019]

While the invention is made to overcome the above
5 problems, its object is to provide a screen printing plate
for use with solar cells and a method of printing solar cell
electrodes through the screen printing plate, by which
electrodes having a high aspect ratio and low resistance are
formed for enabling low-cost manufacture of solar cells with
10 high conversion efficiency.

Solution to Problem

[0020]

The present invention aims to solve the above problems
15 and pertains to a method of manufacturing a solar cell by
printing a conductive paste to simultaneously form a bus bar
electrode and a finger electrode. With respect to electrode
formation by screen printing through a screen printing plate
including a bus bar electrode opening, it has been found that
20 if the bus bar electrode opening is partially provided with a
blocked zone, the pressure applied by the squeegee to the
paste filled in the opening is reduced. Then electrode
breakage is inhibited. The invention is predicated on this
finding.

25 [0021]

Accordingly, the invention provides a screen printing
plate for use with solar cells and a method of printing solar
cell electrodes as defined below.

[1] A screen printing plate for use in printing a
30 conductive paste to simultaneously form a bus bar electrode
and a finger electrode on a solar cell, characterized in that
the screen printing plate includes a finger electrode opening
having an opening width of less than 80 μm and a bus bar
electrode opening including a blocked zone.

35 [2] The screen printing plate of [1] wherein the blocked
zone accounts for up to 60% of a bus bar area computed from

the contour of the bus bar electrode opening of the screen printing plate.

[3] The screen printing plate of [1] or [2] wherein the blocked zone in the bus bar electrode opening is spaced apart
5 a distance of 50 to 700 μm from the boundary between the finger electrode opening and the bus bar electrode opening.

[4] A method of printing solar cell electrodes, characterized in that a conductive paste is printed while using the screen printing plate of any one of [1] to [3] and
10 moving a squeegee in a direction perpendicular to a longitudinal direction of the bus bar electrode.

[0022]

It is noted that breakage rarely occurs with a commonly used finger opening having a width of 80 to 100 μm .
15 The invention is effective for fine lines corresponding to a finger opening width of less than 80 μm .

In order to take full advantage of the invention when solar cell electrodes are printed using the screen printing plate having the features described above, it is desired that
20 the printing direction be substantially perpendicular to the longitudinal direction of bus bar electrode.

Advantageous Effects of Invention

[0023]

25 The use of the inventive screen printing plate makes it possible to reduce the cost of manufacturing solar cells, to prevent the connection between the bus bar electrode and the finger electrode from breaking without increasing the shadow loss or compromising the aesthetic appearance of solar
30 cells, and to manufacture reliable solar cells at high productivity.

BRIEF DESCRIPTION OF DRAWINGS

[0024]

35 FIG. 1 is a cross-sectional view of electrodes of a typical solar cell.

FIG. 2 is a plan view showing the front surface configuration of a typical solar cell.

FIG. 3 is a plan view showing the back surface configuration of a typical solar cell.

5 FIG. 4 schematically illustrates a printing step using a conventional screen printing plate.

FIG. 5 schematically illustrates a saddle phenomenon during the printing step using a conventional screen printing plate.

10 FIG. 6 is a cross-sectional view showing the profile of an electrode as printed using the conventional screen printing plate.

FIG. 7 schematically illustrates one exemplary method of avoiding breakage using a conventional screen printing plate.

FIG. 8 is an enlarged view of openings in a conventional screen printing plate.

FIG. 9 is an enlarged view of electrodes printed using the conventional screen printing plate.

20 FIG. 10 is a cross-sectional view of the connections between bus bar electrode and finger electrode taken along line A-A in FIG. 9.

FIG. 11 is an enlarged view showing openings on a screen printing plate in one embodiment of the invention.

25 FIG. 12 is an enlarged view of electrodes printed using the screen printing plate in one embodiment of the invention.

FIG. 13 is a cross-sectional view of the connections between bus bar electrode and finger electrode taken along line B-B in FIG. 12.

30

DESCRIPTION OF EMBODIMENTS

[0025]

One embodiment of the invention is described below in detail. The screen printing plate for use in the manufacture of solar cells includes a bus bar electrode-providing portion including a blocked zone. In a preferred embodiment, the blocked zone accounts for up to 60%, more preferably up to

55% of an opening area computed from the contour of the bus bar electrode. The invention exerts its effect more when the blocked zone accounts for at least 30%, more preferably at least 45% of the opening area. The screen printing plate
5 also includes a finger electrode opening having a width of less than 80 μm , preferably 40 μm to less than 80 μm , more preferably 40 to 75 μm , even more preferably 45 to 70 μm , and most preferably 50 to 60 μm .

[0026]

10 FIG. 11 illustrates an exemplary screen printing plate of the invention. In FIG. 11, the screen printing plate 1 includes a plurality of finger electrode openings 2 extending parallel to the printing direction (shown by arrow) and a bus bar electrode opening 3 of a broad width (W_b) extending
15 perpendicular to the printing direction. The width W_b is preferably 0.5 to 3 mm, more preferably 1 to 2 mm. In the screen printing plate 1 according to the invention, the bus bar electrode opening 3 includes a plurality of blocked zones 4 arranged therein. These blocked zones 4 are formed at
20 positions aligned with the longitudinal direction of the finger electrode openings 2. The blocked zone 4 within the bus bar electrode opening 2 is preferably spaced apart a distance (W_c) of 50 to 700 μm , more preferably 100 to 300 μm from the boundary between finger electrode opening 2 and bus
25 bar electrode opening 3. If the distance is less than 50 μm , then the amount of paste discharged may be reduced, inviting breakage. If the distance exceeds 700 μm , then the push-out of paste by pressing of the squeegee becomes outstanding for a saddle phenomenon to occur, leaving a risk of breakage due
30 to differential shrinkage upon firing. The spacing between blocked zones 4 is preferably 100 to 2,000 μm , more preferably 300 to 1,000 μm .

[0027]

The total area of blocked zones 4 is up to 60% of the
35 overall area of the bus bar electrode opening 3 and blocked

zones 4 (that is, bus bar area computed from the contour of bus bar electrode opening 3 of the screen printing plate). The width W_f of the finger electrode opening 2 is less than 80 μm .

5 Use of the screen printing plate configured as above is effective for preventing breakage of the finger electrodes, fall-down of the squeegee in the bus bar electrode opening during printing, and a thickening of the finger electrode at transition from the bus bar electrode to the finger electrode,
10 as best shown in FIGS. 12 and 13.

[0028]

Now, one exemplary method of fabricating a solar cell using the screen printing plate according to the invention is described. The invention is not limited to the solar cell
15 fabricated by this method.

An as-cut monocrystalline {100} p-type silicon substrate in which high purity silicon is doped with a Group III element such as boron or gallium so as to give a resistivity of 0.1 to 5 $\Omega\cdot\text{cm}$ is etched with a conc. alkali
20 solution of sodium hydroxide or potassium hydroxide having a concentration of 5 to 60% by weight or mixed acid of hydrofluoric acid and nitric acid for removing the work damaged surface layer. The monocrystalline silicon substrate may have been prepared by either the CZ or FZ method.

25 [0029]

Subsequently, the substrate surface is provided with microscopic asperities known as texture. The texture is an effective means for lowering the reflectivity of solar cells. The texture may be readily provided by immersing the
30 substrate in a hot alkaline solution of sodium hydroxide, potassium hydroxide, potassium carbonate, sodium carbonate or sodium hydrogencarbonate (concentration 1 to 10 wt%) at a temperature of 60 to 100°C for about 10 to about 30 minutes. Often, a proper amount of 2-propanol is dissolved in the
35 alkaline solution to promote the reaction.

[0030]

The texturing is followed by washing with an aqueous acidic solution such as hydrochloric acid, sulfuric acid, nitric acid or hydrofluoric acid or a mixture thereof.

5 Washing with hydrochloric acid is preferred from the cost and efficiency standpoints. To enhance cleanness, washing may be carried out by mixing 0.5 to 5 wt% of aqueous hydrogen peroxide with aqueous hydrochloric acid and heating at 60 to 90°C.

10 [0031]

On the substrate, an emitter layer is formed by vapor phase diffusion using phosphorus oxychloride. In common silicon solar cells, a p-n junction must be formed only on the light-receiving surface. To this end, suitable means
15 must be taken for avoiding any p-n junction on the back surface, for example, by carrying out diffusion while two substrates are mated together, or by forming a SiO_2 or SiNx film on the back surface as diffusion mask prior to diffusion. At the end of diffusion, the glass formed on the surface is
20 removed using hydrofluoric acid or the like.

[0032]

Next, an antireflection film is formed on the light-receiving surface. Using a plasma-enhanced chemical vapor deposition (CVD) system for film formation, a SiNx film
25 is deposited to a thickness of about 100 nm. Often a mixture of monosilane (SiH_4) and ammonia (NH_3) is used as the reactant gas although nitrogen may be used instead of NH_3 . Also hydrogen may be mixed with the reactant gas to adjust the process pressure, to dilute the reactant gas, or to enhance
30 the bulk passivation effect when the substrate used is of polycrystalline silicon.

[0033]

Next, a back electrode is formed by the screen printing method. On the back surface of the substrate, a
35 paste obtained by mixing silver powder and glass frit with an organic binder is screen printed in a bus bar pattern, after which a paste obtained by mixing aluminum powder with an

organic binder is screen printed in the region excluding the bus bar. After printing, the pastes are fired at a temperature of 700 to 800°C for 5 to 30 minutes to form a back electrode. The back electrode is preferably formed by the printing method, although it can be formed by evaporation, sputtering or the like.

[0034]

Next, a front electrode is formed by the screen printing method using the screen printing plate according to the invention.

Specifically, a paste obtained by mixing silver powder and glass frit with an organic binder is printed onto the front surface of the substrate using a screen printing plate having a comb-shaped printing pattern designed to a finger electrode width of 30 to 80 μm and a finger electrode spacing of 0.5 to 4.0 mm.

[0035]

The screen printing plate of the invention may be obtained simply by providing the bus bar electrode opening with blocked zones as shown in FIG. 11, without a need to change the conventional solar cell pattern as mentioned above.

[0036]

Commonly used screen printing plates include finger openings having a width of 80 to 100 μm . In this case, breakage as mentioned above rarely occurs because the finger electrodes are fully wide and can be printed thick. However, as lines are narrowed to a finger opening width of less than 80 μm , the difference in film thickness between bus bar electrode and finger electrode becomes greater. Then breakage can occur due to differential thermal shrinkage (FIG. 9).

[0037]

In contrast, when a solar cell is manufactured by printing a bus bar electrode and a finger electrode simultaneously, the risk of breakage is avoidable by the printing step using a screen printing plate including a bus bar electrode opening including blocked zones accounting for

up to 60% of the opening area computed from the contour of the bus bar electrode (FIG. 13).

In order to take full advantage of the invention when solar cells are manufactured by printing electrodes through the screen printing plate having the features described above, it is desired that the printing direction be substantially perpendicular to the bus bar electrode.

[0038]

The use of the screen printing plate according to the invention has the additional effect of suppressing the finger electrode from thickening because the presence of blocked zones in the bus bar electrode opening reduces the amount of paste discharged at the last printing side (FIG. 12).

[0039]

When a blocked zone is partially included in the bus bar opening, an unprinted area may be left after the printing. However, this causes no problems to the outer appearance because a solder-coated copper lead is bonded to the area upon fabrication of a module. As long as the area of bus bar electrode is at least 40% of the standard bus bar electrode area, the bond strength of the lead to the bus bar electrode is maintained. Since the amount of bus bar electrode used is reduced, solar cells can be manufactured at lower cost. The inclusion of blocked zones in the bus bar electrode opening of the screen printing plate avoids any breakage of the connection between bus bar electrode and finger electrode.

Once electrodes are formed by the above-mentioned method, they are fired by heating in air at a temperature of 700 to 800°C for 5 to 30 minutes. Firing of the back electrode and light-receiving side electrode may be performed at a time.

EXAMPLES

[0040]

Examples and Comparative Examples are given below by way of illustration and not by way of limitation.

[0041]

[Examples and Comparative Examples]

To demonstrate the benefits of the invention, solar cells were manufactured by processing thirty (30)

5 semiconductor substrates as follows.

There were provided screen printing plates bearing a conventional pattern A having a finger electrode opening width (W_f) of 60 μm (Comparative Example, FIG. 8), a pattern B including a bus bar electrode opening including blocked zones (FIG. 11), otherwise equivalent to pattern A, and a
10 pattern C having a finger electrode opening width (W_f) of 100 μm (Comparative Example, FIG. 8) as the printing pattern. All the patterns commonly had a bus bar electrode opening width (W_b) of 1.5 mm.

15 More particularly, in pattern B, the bus bar electrode opening was spaced apart a distance W_c of 100 μm from the boundary between the finger electrode opening and the bus bar electrode opening, the spacing between blocked zones was 1,000 μm , and the total area of blocked zones was 55% of the
20 bus bar area computed from the contour of the bus bar electrode opening.

[0042]

There was provided an as-cut boron-doped {100} p-type silicon substrate 100 of 15 cm square having a thickness of
25 250 μm and a resistivity of 2.0 $\Omega\cdot\text{cm}$. The substrate was immersed in a conc. potassium hydroxide aqueous solution to remove the work damaged layer, textured, heat treated at 850°C in a phosphorus oxychloride atmosphere to form an emitter layer 101, and etched with hydrofluoric acid to
30 remove phosphorus glass, followed by washing and drying. Thereafter, a SiN_x film 102 was formed using a plasma-enhanced CVD system. On the back surface, a paste of silver powder, glass frit and organic binder was screen printed in a bus bar pattern 106, after which a paste of
35 aluminum powder and organic binder was screen printed in a pattern 104 excluding the bus bar. The organic solvent was

evaporated off, yielding a semiconductor substrate having a back electrode formed thereon.

[0043]

Next, a conductive paste based on silver powder, glass
5 frit, organic vehicle and organic solvent and further
containing a metal oxide as additive was applied onto the
antireflection film on the semiconductor substrate by using a
screen printing plate having the selected printing pattern at
a squeegee hardness of 70 degrees, a squeegee angle of 70
10 degrees, an applied pressure of 0.3 MPa, and a printing speed
of 50 mm/sec. After printing, the substrate was heated in a
clean oven at 150°C for drying and fired in air at 800°C.

[0044]

Thirty (30) solar cells thus manufactured were
15 observed for electrodes under an optical microscope and
evaluated by a solar simulator (25°C atmosphere, irradiation
intensity 1 kW/m², spectrum AM 1.5 Global). Also under the
optical microscope, the width of finger electrodes after
printing and the width of connection were observed to inspect
20 any breakage. The results on average of Example and
Comparative Examples are shown in Table 1.

[0045]

Table 1

Level	Finger opening (μm)	Bus bar opening (mm)	Blocked zones	Breakage	Short-circuit current (mA/cm ²)	Fill factor (%)	Conversion efficiency (%)
A (Comparative Example)	60	1.5	absent	found	35.1	73.6	15.50
B (Example)	60	1.5	present	none	35.1	75.1	15.82
C (Comparative Example)	100	1.5	absent	none	33.8	76.2	15.20

25

[0046]

Breakage at the connection between bus bar electrode and finger electrode was observed under standard level A, but not in the method of the invention and also under level C
5 using a large opening width.

The short-circuit current dropped under level C using a large finger electrode width. This drop is caused by a shadow loss due to the increased width. The fill factor under level B free of breakage was 75.1%, which was about
10 1.5% higher than that under level A undergoing breakage.

In the prior art, breakage at the connection between bus bar electrode and finger electrode occurred. Using the screen printing plate of the invention, electrodes having a high aspect ratio can be formed at no risk of breakage
15 without increasing the number of steps.

[0047]

As demonstrated above, the invention ensures that bus bar electrode and finger electrode are formed at no risk of breakage at the connection between bus bar electrode and
20 finger electrode. Thus solar cells having a high conversion efficiency can be manufactured in high yields.

Reference Signs List

[0048]

- 25 1 screen printing plate
- 2 finger electrode opening
- 3 bus bar electrode opening
- 4 blocked zone in bus bar electrode opening
- 5 blocked zone
- 30 12 finger electrode
- 13 front bus bar electrode
- 100 p-type semiconductor substrate
- 101 n-type diffusion layer
- 102 antireflection film (SiNx film)
- 35 103 BSF layer
- 104 aluminum electrode
- 105 front bus bar electrode

	106	back bus bar electrode
	107	finger electrode
	110	mesh fabric
	111	emulsion
5	112	squeegee
	113	dent
	114	breakage

CLAIMS:

1. A screen printing plate for use in printing a conductive paste to simultaneously form a bus bar electrode and a finger electrode on a solar cell, characterized in that the screen printing plate includes a finger electrode opening having an opening width of less than 80 μm and a bus bar electrode opening including a blocked zone.
2. The screen printing plate of claim 1 wherein the blocked zone accounts for up to 60% of a bus bar area computed from the contour of the bus bar electrode opening of the screen printing plate.
3. The screen printing plate of claim 1 or 2 wherein the blocked zone in the bus bar electrode opening is spaced apart a distance of 50 to 700 μm from the boundary between the finger electrode opening and the bus bar electrode opening.
4. A method of printing solar cell electrodes, characterized in that a conductive paste is printed while using the screen printing plate of any one of claims 1 to 3 and moving a squeegee in a direction perpendicular to a longitudinal direction of the bus bar electrode.