

Claims:

1. A method of processing an underlayer, comprising:
 - depositing an amorphous carbon film on an underlayer positioned on a susceptor in a first processing region;
 - forming a doped amorphous carbon film by implanting a dopant or an inert species into the amorphous carbon film in a second processing region, wherein the dopant or the inert species is selected from carbon, boron, nitrogen, silicon, phosphorous, argon, helium, neon, krypton, xenon, beryllium, germanium, or combinations thereof, wherein a target temperature during implanting the dopant or the inert species is between about -100 degrees Celsius and about 550 degrees Celsius;
 - patterning the doped amorphous carbon film; and
 - etching the underlayer.
2. The method of claim 1, wherein the underlayer comprises a single layer or a dielectric stack.
3. The method of claim 1, wherein depositing the amorphous carbon film on the underlayer comprises:
 - flowing a hydrocarbon-containing gas mixture into the first processing region;
 - and
 - generating an RF plasma in the first processing region to form the amorphous carbon film on the underlayer.
4. The method of claim 3, wherein a distance between a gas distribution showerhead positioned in the first processing region and the susceptor is between about 200 mils and about 1,000 mils.
5. The method of claim 4, wherein a pressure within the first processing region is between about 4 Torr and about 8 Torr.
6. The method of claim 1, wherein an implant energy utilized to energize the dopant or the inert species is between about 5 keV and about 300 keV.

7. The method of claim 6, wherein an ion dosage is between about 1×10^{13} ions/cm² and about 5×10^{16} ions/cm².

8. The method of claim 6 where implanting the dopant or the inert species into the patterned amorphous carbon film is performed at an angle between about 1 degree and about 80 degrees.

9. A method of processing an underlayer, comprising:

depositing an amorphous carbon film on an underlayer positioned on a susceptor in a first processing region;

forming a doped amorphous carbon film by implanting a dopant or an inert species into the amorphous carbon film in a second processing region, wherein the dopant or the inert species is selected from carbon, boron, nitrogen, silicon, phosphorous, argon, helium, neon, krypton, xenon, beryllium, germanium, or combinations thereof, wherein a target temperature during implanting the dopant or the inert species is between about -100 degrees Celsius and about 550 degrees Celsius;

 patterning the doped amorphous carbon film; and

 etching the underlayer, wherein the doped amorphous carbon film has a refractive index at 633 nm of from about 2.1 to about 2.2.

10. The method of claim 9, wherein the doped amorphous carbon film has a k-value at 633 nm of less than 1.0.

11. The method of claim 9, wherein the doped amorphous carbon film has a Young's modulus (GPa) of from about 70 to about 200 GPa.

12. The method of claim 11, wherein the doped amorphous carbon film has a hardness (GPa) of from about 14 GPa to about 22 GPa.

13. The method of claim 12, wherein the doped amorphous carbon film has a stress (MPa) of from about -600 MPa to about 0 MPa.

14. The method of claim 13, wherein the doped amorphous carbon film has a density (g/cc) from about 1.95 g/cc to about 2.1 g/cc.

15. The method of claim 14, wherein the doped amorphous carbon film has a thickness between about 10 Å and about 50,000 Å.

16. A method of processing an underlayer, comprising:

depositing an amorphous carbon film on an underlayer positioned on a susceptor in a first processing region;

forming a doped amorphous carbon film by implanting a carbon dopant into the amorphous carbon film in a second processing region, wherein a target temperature during implanting the carbon dopant is between about -100 degrees Celsius and about 550 degrees Celsius;

patterning the doped amorphous carbon film; and

etching the underlayer, wherein the doped amorphous carbon film has a hardness (GPa) of from about 14 GPa to about 22 GPa.

17. The method of claim 16, wherein the doped amorphous carbon film has a refractive index at 633 nm of from about 2.1 to about 2.2.

18. The method of claim 17, wherein the doped amorphous carbon film has a k-value at 633 nm of less than 1.0.

19. The method of claim 16, wherein the doped amorphous carbon film has a Young's modulus (GPa) of from about 70 to about 200 GPa.

20. The method of claim 19, wherein the doped amorphous carbon film has:

a stress (MPa) of from about -600 MPa to about 0 MPa;

a density (g/cc) from about 1.95 g/cc to about 2.1 g/cc; and

a thickness between about 10 Å and about 50,000 Å.