

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
9 March 2006 (09.03.2006)

PCT

(10) International Publication Number
WO 2006/026234 A3

(51) International Patent Classification:

H01M 10/40 (2006.01) *H01M 4/02* (2006.01)
H01M 10/36 (2006.01) *H01M 6/16* (2006.01)
H01M 4/58 (2006.01)

[GB/US]; 32611 Greenwood Drive, Avon Lake, OH 44012 (US).

(21) International Application Number:

PCT/US2005/029804

(22) International Filing Date: 22 August 2005 (22.08.2005)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:

10/928,943 27 August 2004 (27.08.2004) US

(71) Applicant (for all designated States except US): EVEREADY BATTERY COMPANY, INC. [US/US]; 533 Maryville University Drive, St. Louis, MO 63141 (US).

(72) Inventor; and

(75) Inventor/Applicant (for US only): WEBBER, Andrew


(74) Agent: TOYE, Russell, H., Jr.; Eveready Battery Company, Inc., 25225 Detroit Road, Westlake, Ohio 44145 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,

[Continued on next page]

(54) Title: LOW TEMPERATURE Li/FeS₂ BATTERY



(57) Abstract: The invention is a 1.5 volt primary electrochemical battery cell with an alkali metal lithium negative electrode (such as lithium), a positive electrode (comprising iron disulfide for example) and a nonaqueous electrolyte. The electrolyte has a solute including lithium iodide dissolved in an ether-containing solvent including a 1,2-dimethoxypropane based solvent component and no more than 30 volume percent 1,2-dimethoxyethane. When 1,2dimethoxypropane is used to replace at least most 1,2-dimethoxyethane in the solvent, the cell provides good discharge capacity at low temperature while maintaining excellent discharge capacity at room temperature.



FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT,
RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA,
GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(88) Date of publication of the international search report:
30 November 2006

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.